

INDEX

- ACCESSORIES 53
 ACID EXTRACTION 68, 79
 ALBITE 76
 ALUMINA 2
 ALUMINUM FLUORITE 2
 AMPHIBOLITE 31
 ANDALUSITE 2
 ANDESITE 3
 ANHYDRITE 3
 ANORTHOSITE 4
 ANTIMONY ORE 4
 AQUA REGIA METHOD 44, 78
 ARAGONITE 4
 ARSENIC ORE 55
 ASCHARITE ORE 4
- BASALT 5
 BAUXITE 2, 6, 7
 BERYLLIUM ORE 7
 BORATE ORE 7
 BRUCITE 7
- CALCEROUS OOZE 60
 CALCINED BONE 7
 CALCITE 4
 CARBONATITE 8
 CHROME MAGNESITE 8
 CHROMITE 8
 CHROMIUM ORE 8
 CLAY 9, 76
 CONTAMINATED RIVER SEDIMENT 73
 CONTAMINATED SOIL 84, 85
 COPPER ORE 10, 11, 12, 13, 55
 CRYOLITE 13
 CYANIDE 84
- DIABASE 14
 DIORITE 14, 27, 29
 DOLERITE 15
 DOLOMITE 16, 45, 46, 47
 DOLOMITE SUBSTITUTE 16
 DUNITE 17
- ESTUARY SEDIMENT 69
 EXTRACTION 68, 79
- FELDSPAR 18, 76
 FIRECLAY 9
 FLUORITE 19
 FLUORSPAR 19
- GABBRO 20
 GAIROME CLAY 76
 GOLD ASSAY PILLS 21
 GOLD ORE
 21, 22, 23, 24, 25, 26, 27, 58
 GRANITE 27, 28
 GRANODIORITE 27, 29
 GRAPHITE 29, 30
 GREISEN 30
 GYPSUM 30, 31
- HEXAVALENT CHROMIUM 84
 HORNBLENDITE 31
- ICP-MS 53
 ILMENITE 90
 IRON ORE
 33, 34, 35, 36, 37, 38, 39, 40, 41, 55
 IRON ORE SINTER 42
 IRON PELLETS 32
 IRON SULPHIDE 32
- KAOLIN 42, 76
 KIMBERLITE 43
 KINZINGITE 43
 KOMATIITE 92
- LAKE SEDIMENT 68
 LASER ABLATION 53
 LATERITE 43
 LEAD BASILICATE 44
 LEAD ORE 44, 55
 LIMESTONE 16, 45, 46, 47
 LITHIUM ORE 48
 LUJAVRITE 48
- MAGNESITE 49
 MANGANESE NODULE 51
 MANGANESE ORE 50
 MARINE SEDIMENT 69
 MARIPOLITE 52
 MERCURY IN SOIL 78
 MERCURY ORE 52, 78
 MICROSAMPLES 53
 MOLOCHITE 54
 MOLYBDENUM ORE 54
 MOUNTED SAMPLES 53
 MULLITE 2, 9
 MULTI-METAL ORE 55, 56, 86
- NEPHELINE SYENITE 88
 NICKEL ORE 43, 57
 NIOBIUM ORE 58
 NOBLE METAL ORE 58, 59
 NUTRIENTS IN SOIL 78
- OBSIDIAN 60
 OLIVINE 5, 60
 OOZE 60
- PEGMATITE 61
 PERIDOTITE 61
 PHOSPHATE ROCK 62
 PLAGIOGNEISS 62
 POTASSIUM FELDSPAR 76
 POTTERY STONE 76
 PRESSED POWDER SAMPLES 53
 PROPHILITE 62
 PROPHYLITE 76
 PYROXENITE 63
- QUARTZ 63
- RARE EARTH ORE 64, 65
 RHYOLITE 66
 RIVER SEDIMENT 70, 73
 RUTILE 66
- SANDSTONE 67
 SCHIST 67, 76
 SEDIMENT 68, 69, 70, 72, 73, 74
 SEQUENTIAL EXTRACTION 68
 SERPENTINITE 75
 SHALE 75
 SILICEOUS MINERALS 76
 SILICEOUS OOZE 60
 SILLIMANITE 2, 76
 SILLIMANITE SCHIST 76
 SILT 76
 SILVER ORE
 21, 22, 23, 24, 25, 26, 27, 58, 77
 SLATE 77
 SOIL
 27, 78, 79, 80, 81, 82, 83, 84, 85
 STEATITE 85
 STONE 76
 STREAM SEDIMENT 70, 71, 72
 SULPHIDE ORE 55
 SULPHUR ORE 86, 87
 SYENITE 88
- TALC 89
 TANTALUM ORE 89
 TIBET SEDIMENT 74
 TILL 79
 TIN ORE 55, 89
 TITANIUM ORE 90
 TUNGSTEN ORE 89, 91
- ULTRAMAFIC ROCK 92
 URANIUM ORE 92
 URTITE 92
- VOLCANIC TUFF 92
- WOLLASTONITE 93
- XRF 53
- ZEOLITE 93
 ZINC ORE 55, 94
 ZIRCONIUM MATERIALS 95
 ZIRCONIUM ORE 95

ALUMINA

= class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg T = Total

#	Number	Al ₂ O ₃	Be*	CaO	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	MnO*	Na ₂ O	P*	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Units
AVAILABLE INDIVIDUALLY																
2	CERAM AN27	99.76	.	0.03	.	0.02	<0.01	<0.01	.	0.08	.	.	0.08	<0.01	.	25 or 100 g
2	CERAM AN26	99.76	.	0.03	.	0.03	<0.01	<0.01	.	0.02	.	.	0.12	<0.01	(0.08)	25 or 100 g
2	CERAM AN25	99.39	.	0.03	.	0.03	0.01	<0.01	.	0.53	.	<0.01	<0.01	<0.01	(0.34)	25 or 100 g
1	VS SH12/3	73.6	.	18.8	0.46	0.66T	.	2.15	0.76	.	.	100 g
1	NCS DC62107	64.92	.	1.34	.	6.26	0.22	0.47	.	0.06	SO ₂ :0.29	.	8.30	2.81	14.39	20 g
1	SRM 699 *	.	2.81	0.036	.	0.013T	(0.005)	0.0006	5	0.59	2 ³	.	0.0120	(0.001)	0.69	60 g
1	DSZU 123.45-03	.	.	.	2.7*	0.02	V2O5: 3.7*	.	2.3	0.33	.	4.0*	0.022	0.0046	.	50 g

AVAILABLE ONLY AS SET 1-5

1	DSZU 123.46-03-1	0.022	.	.	.	0.20	.	.	0.020	.	.	30 g SET 1-5 only
1	DSZU 123.46-03-2	0.022	.	.	.	0.33	.	.	0.021	.	.	30 g SET 1-5 only
1	DSZU 123.46-03-3	0.037	.	.	.	0.44	.	.	0.037	.	.	30 g SET 1-5 only
1	DSZU 123.46-03-4	0.055	.	.	.	0.47	.	.	0.054	.	.	30 g SET 1-5 only
1	DSZU 123.46-03-5	0.090	.	.	.	0.72	.	.	0.077	.	.	30 g SET 1-5 only

* SRM 699 also contains Cr₂O₃: 0.0002, Ga₂O₃: 0.010, Li₂O: 0.002, V₂O₅: 0.0005, and ZnO: 0.013CRM ALUMINA SET available in SET/3 only trace informational Cl, NiO, SO₃ 50 g units

Number	B ₂ O ₃	CaO	CuO	Fe ₂ O ₃	Ga ₂ O ₃	K ₂ O	MgO	Na ₂ O	SiO ₂	SrO	TiO ₂	ZnO	ZrO ₂	LOI
JCRM R034	(<0.0006)	0.0002	(<0.0003)	(0.0003)	0.0021	0.0020	(<0.0001)	0.0018	0.0045	(<0.0001)	(<0.0004)	(<0.0002)	(<0.0002)	0.188
JCRM R035	(<0.0006)	0.0188	0.0018	0.0151	0.0074	0.0005	0.0013	0.222	0.0116	0.0007	0.0029	0.0012	0.0009	0.156
JCRM R036	0.0533	0.0242	(<0.0003)	0.0139	0.0076	(0.0002)	0.0006	0.0316	0.0569	0.0002	0.0032	0.0007	0.0004	0.072

CRM ALUMINOUS SET available in SET/3 only 100 g units

Number	Type	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	ZrO ₂ +HfO ₂	LOI
JCRM R303	Bauxite	88.49	0.012	1.51	.	0.006	.	0.064	5.55	2.93	0.110	.
JCRM R304	Sillimanite	55.94	0.427	0.585	0.329	0.451	0.273	.	35.90	1.33	0.105	4.26
JCRM R041	Mullite	70.18	0.059	0.598	0.174	0.190	0.197	0.136	28.11	0.185	0.058	.

CRM ALUMINUM FLUORITE

analysis listed in mass %

100 g units

Number	F	Al	Fe ₂ O ₃	Na	P ₂ O ₅	SiO ₂	SO ₄	LOI
NCS DC91016	64.97	31.92	0.025	0.028	0.0275	0.196	0.076	1.25
NCS DC91008	61.79	30.70	0.132	0.097	0.0253	0.104	0.585	(4.61)
NCS DC91011	61.51	32.28	0.021	0.121	0.1317	0.429	0.627	0.754
NCS DC91010	60.96	30.52	0.126	0.125	0.0265	0.251	0.748	(5.48)
NCS DC91013	60.88	33.12	0.020	0.315	0.0013	0.017	0.098	0.467
NCS DC91007	60.76	30.27	0.156	0.104	0.0295	0.146	0.654	(6.00)
NCS DC91015	59.99	30.70	0.107	0.111	0.0247	0.301	0.702	(5.61)
NCS DC91012	59.74	33.93	0.037	0.126	0.0027	0.016	0.136	0.547
NCS DC91009	57.79	34.68	0.028	0.113	0.0008	0.015	0.093	0.662
NCS DC91014	57.72	34.76	0.015	0.113	0.0007	0.014	0.104	0.640

CRM ANDALUSITE 100 g units

Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	SiO ₂	TiO ₂	LOI
SARM 34	59.15	(0.13)	0.75	0.23	0.13	0.093	39.04	0.16	0.62

CRM ANDESITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	Si	SiO ₂	Al	Al ₂ O ₃	CO ₂	CaO	Fe	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI	
JA-1	29.90	63.97	8.06	15.22	.	5.70	4.95	3.98	2.59	7.07	+0.72	-0.30	0.77	1.57	0.157	3.84	0.165	0.85	.
JA-1a	.	63.66	.	15.40	.	5.74	.	3.67	.	7.17	.	.	0.78	1.55	0.157	3.90	0.165	0.87	.
GBW 07110	.	63.06	.	16.1	1.03	2.47	.	0.19	4.51	.	+1.79	.	5.17	0.84	0.089	3.06	0.36	0.80	.
JA-3	29.11	62.27	8.23	15.56	.	6.24	4.62	4.83	1.15	6.60	+0.20	-0.11	1.41	3.72	0.104	3.19	0.116	0.70	.
GBW 07104	.	60.62	.	16.17	3.47	5.20	.	2.39	.	4.90	+(1.5)	.	1.89	1.72	.	3.86	.	.	4.44
US AGV-2	27.7	59.3	8.95	16.91	.	5.20	4.68	.	.	6.69	.	.	2.88	1.79	.	4.19	0.48	1.05	.
USZ 48-2009	.	59.20	.	16.72	.	5.58	.	(1.66)	.	5.43	.	.	2.42	3.52	0.081	4.46	0.264	0.71	1.39
JA-2	26.37	56.42	8.16	15.41	.	6.29	4.34	3.69	2.16	6.21	+1.12	-1.25	1.81	7.60	0.108	3.11	0.146	0.66	.

continued analysis listed in mg/kg except * which is ppb and % which is mass %

Number	Ag	As	Au*	B	Ba	Be	Bi	Ca%	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu
JA-1	.	2.78	0.16	21.0	311	0.50	.	4.07	0.11	13.3	43.0	12.3	7.83	0.62	43.0	4.55	3.04	1.20
JA-1a	(322)	(12.9)	(4.1)	.	(41.8)	.	.	.
GBW 07110	0.17	5.96	.	10.8	1053	3.64	0.09	.	0.61	117	160	7.9	7.7	7.16	9.1	5.32	2.93	1.96
JA-3	0.084	.	.	24.8	323	0.80	.	4.46	.	22.8	.	21.1	66.2	2.08	43.4	3.01	1.57	0.82
GBW 07104	0.071	2.1	(0.95)	4.7	1020	1.1	0.081	.	0.061	40	(46)	13.2	32	2.3	55	1.85	0.85	1.02
US AGV-2	1140	2.3	.	3.72	.	68	.	16	17	(1.16)	53	3.6	(1.79)	(1.54)
USZ 48-2009	(0.08)	(3.64)	.	.	672	(2.01)	(0.12)	.	(0.06)	55.2	.	19.2	95.9	1.09	41.2	(2.55)	(1.18)	1.44
JA-2	.	.	0.26	20.7	321	2.05	.	4.50	.	32.7	.	29.5	436	4.63	29.7	2.80	1.48	0.93

Number	F	Ga	Gd	Ge	Hf	Hg	Ho	I	In	K%	La	Li	Lu	Mg%	Mn%	Mo	Na%	Nb
JA-1	161	16.7	4.36	1.33	2.42	.	0.95	.	.	0.64	5.24	10.8	0.47	0.95	0.122	1.59	2.85	1.85
JA-1a	(11.6)	.	.	.	(1.2)	.	.
GBW 07110	1120	19.8	6.54	1.11	7.5	0.014	1.10	0.07	0.11	.	62.5	17.5	0.49	.	.	0.95	.	20.8
JA-3	.	16.3	2.96	.	3.42	.	0.51	.	.	1.17	9.33	14.5	0.32	2.24	0.081	1.89	2.37	3.41
GBW 07104	280	18.1	2.7	0.93	2.9	0.012	0.34	(0.14)	0.037	.	22	18.3	0.12	.	0.0604	0.54	.	6.8
US AGV-2	(440)	20	(4.69)	.	(5.08)	.	(0.71)	.	.	2.39	38	(11)	(0.25)	1.08	0.0770	.	3.11	15
USZ 48-2009	.	21.1	(3.93)	.	3.80	(0.004)	(0.46)	.	.	.	26.2	(13.2)	(0.15)	.	.	(0.60)	.	3.23
JA-2	.	16.9	3.06	.	2.86	.	0.50	.	.	1.50	15.8	27.3	0.27	4.58	0.084	0.60	2.31	9.47

Number	Nd	Ni	P%	Pb	Pr	Rb	S	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Ti%
JA-1	10.9	.	0.072	6.55	1.71	12.3	21.6	0.22	28.5	.	3.52	.	263	0.13	0.75	.	0.82	0.51
JA-1a	.	(2.3)	(268)
GBW 07110	47.2	12.6	.	97.7	13.2	183	230	1.34	7.52	0.03	8.63	3.12	318	1.42	0.99	(0.007)	16.7	.
JA-3	12.3	32.2	0.051	7.70	2.40	36.7	.	.	22.0	.	3.05	.	287	0.27	0.52	.	3.25	0.42
GBW 07104	19	17	0.1030	11.3	4.9	38	192	0.12	9.5	(0.04)	3.4	0.79	790	0.40	0.41	0.017	2.6	0.3090
US AGV-2	30	19	0.21	13	8.3	68.6	.	(0.6)	13	.	(5.7)	(2.3)	658	(0.89)	(0.64)	.	6.1	0.63
USZ 48-2009	27.2	61.2	.	18.7	(6.77)	49.7	.	(0.27)	11.8	.	5.16	(0.86)	1116	(0.25)	0.49	.	6.46	.
JA-2	13.9	130	0.064	19.2	3.84	72.9	.	.	19.6	.	3.11	1.68	248	0.80	0.44	.	5.03	0.40

Number	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units
JA-1	.	0.47	0.34	105	.	30.6	3.03	90.9	88.3	20 g
JA-1a	.	.	.	(107)	.	.	.	(91)	(94.9)	100 g
GBW 07110	1.02	0.50	3.04	64.3	1.62	28.0	3.15	164	335	50 g
JA-3	.	.	1.18	169	.	21.2	2.16	67.7	118	20 g
GBW 07104	0.16	0.15	0.90	94	(0.45)	9.3	0.89	71	99	70 g
US AGV-2	(0.27)	(0.26)	1.88	120	.	20	1.6	86	230	25 g
USZ 48-2009	(0.22)	(0.17)	1.96	123	(1.70)	11.8	1.00	71.5	141	100 g
JA-2	0.32	0.28	2.21	126	.	18.3	1.62	64.7	116	20 g

CRM ANHYDRITE

analysis listed in mass %

50 g units

Number	Al ₂ O ₃	CO ₂	CaO	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	SO ₃	SiO ₂	Sr	TiO ₂
GUW AN	(0.023)	0.65	40.7	0.014	(0.5)	0.013	0.34	(0.002)	0.032	57.6	(0.22)	0.14	(0.003)

continued analysis listed in mg/kg

Number	B	Ba	Cl	Cr	Cs	Cu	Ga	Li	Mo	Rb	Sb	Ta	Th	V	Zn	Zr
GUW AN	100	14.8	0.033	0.90	0.037	4	4.3	9	1.2	4.7	0.044	0.007	0.048	18	7.9	13

CRM ANORTHOSITE

analysis listed in mass %

40 g units

Number	SiO ₂	Al ₂ O ₃	Ba	CaO	CO ₂	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	H ₂ O+	T.H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂
VS M011	53.46	27.42	0.0319	10.95	0.0	1.09	0.53	1.74	0.088	0.33	0.42	0.65	0.49	0.037	4.39	0.041	0.0100	0.18
VS 2120-81	51.77	22.78	0.051	10.06	0.36	4.66	6.26	.	0.40	.	.	0.76	2.10	0.076	4.04	0.140	0.069	1.87
VS M010	51.65	23.91	0.0294	10.18	0.14	4.40	1.45	6.34	0.095	0.26	0.36	0.50	2.24	0.073	3.99	0.13	0.0460	0.83

continued

analysis listed in mg/kg except % which is mass %

Number	B	Be	Co	Cr	Cs	Cu	F	Ga	La	Li	Mo	Nb	Ni	Pb	Rb	Sc	Sn	Sr	V%	Y	Yb	Zn	Zr
VS M011	4.5	0.8	9.6	12	0.73	26	420	21	20	7.5	1.2	2.6	14	6.8	2.7	5	5.1	802	0.0024	8	1.1	50	42
VS 2120-81	.	0.9	23	36	.	31	.	17	10	7	.	23	.	.	0.013	.	.	83	72
VS M010	8.7	1.1	27	23	0.55	44	380	26	24	7.1	2.0	3.9	32	8.0	5.5	11	5.0	477	0.0109	17	2.0	96	58

CRM ANTIMONY ORE

analysis listed in mass

200 g units

Number	Al	As	C	Ca	Cu	Fe	H ₂ O	K	Mg	Na	Pb	S	Sb	Si	LOI
CAN CD-1	(5.5)	0.66	(0.2)	(1.4)	(<0.01)	(2.8)	(0.2)	(1.8)	(0.6)	(0.1)	(0.02)	(3.1)	3.57	(32.9)	(4.0)

CRM ANTIMONY ORE

analysis listed in mass %

analysis in mg/kg * Sb calculated from certified results for 4ACID, ICP, and XRF

Number	Sb	Pb	S	Se	Zn	Ag	As	Au	Bi	Cd	Co	Cu	Ga	Li	Nb	Ni	Sn	Units
GSb-3 *	53.69	10 g
GSb-2	31.0838	23.64	10 g
GSb-11 *	21.10	10 g
GSb-10 *	11.66	10 g
GSb-6 *	9.88	10 g
GSb-9 *	6.50	10 g
GSb-4 *	3.43	10 g
NCS DC70013	1.81	0.012	1.02	0.018	0.037	7.3	25.3	.	(0.24)	2.6	2.2	51.3	9.1	22.8	5.4	3.2	3.0	50 g
GSb-7 *	1.75	10 g
GSb-8 *	1.63	10 g
GSb-5 *	0.18	10 g
GSb-1	0.1636	10 g

CRM ARAGONITE/CALCITE

100 g units

Number	Al ₂ O ₃	CO ₂	CaO	F	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	S	SiO ₂	SrO	LOI
UNS AK	0.11	43.0	54.9	0.20	0.130	0.037	0.110	0.047	0.029	0.046	0.64	0.28	43.27

CRM ASCHARITE ORE

Number	B ₂ O ₃	CaO	T.Fe	FeO	MgO	P	S	SiO ₂	Ins.Res.	Units
NCS DC16005	5.65	0.15	52.98	26.13	11.64	0.016	1.242	4.51	4.72	100 g

BAUXITE

# = class, 1=CRM and 2=RM		BCS: 100g		CERAM: 25 or 100g		CETEM: 90-120g		GBAP: 10g		NCS: 50-100g		SRM 600: 90g		other SRM: 60g			
#	Number	Al ₂ O ₃	A.Al ₂ O ₃	CaO	Cr ₂ O ₃	Fe	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	R.SiO ₂	TiO ₂	V ₂ O ₅	ZrO ₂	LOI
1	BCS 394/1	88.88	.	0.0173	.	.	1.372	.	0.0047	.	0.0574	6.47	.	2.969	.	.	.
1	NCS HC28815	88.55	.	0.15	.	.	1.75	0.11	0.073	0.017	0.23	4.88	.	3.69	.	.	.
1	JCRM R301	87.5	.	0.03	.	.	1.40	0.04	0.02	0.03	0.07	7.24	.	2.90	.	0.13*	0.35
1	NCS DC61105	85.07	.	0.24	.	.	1.18	0.44	0.21	0.080	.	8.17	.	3.76	.	.	0.29
1	NCS HC28814	83.07	.	0.22	.	.	2.71	0.17	0.088	0.022	0.18	9.69	.	3.64	.	.	0.15
1	NCS DC91017	71.14	.	0.75	.	.	2.01	0.477	0.090	0.022	0.221	3.16	.	3.04	.	.	.
1	NCS HC28813	70.28	.	0.37	.	.	6.64	0.20	0.18	0.051	0.25	14.20	.	2.85	.	.	4.57
1	NCS DC91018	64.53	.	0.26	.	.	6.06	0.22	0.246	0.030	0.185	8.02	.	2.59	.	.	.
1	CETEM BXGO-1	60.7	59.3	(0.02)	0.010	.	4.6	(0.004)	(0.03)	(0.006)	0.042	0.63	0.52	0.46	0.017	(0.003)	33.3
1	NCS HC28812	60.41	.	0.51	.	.	9.69	0.22	0.26	0.070	0.30	17.82	.	2.22	.	.	7.96
1	CETEM BXGO-2	60.3	57.20	(0.016)	(0.006)	.	3.26	0.024	(0.03)	(0.02)	0.040	2.13	1.74	0.27	0.011	0.017	29.1
1	DSZU 123.38-03	58.9	.	0.14	0.043	FeO:0.062	1.62	0.026	.	0.085	0.073	5.73	.	2.69	.	0.054	.
1	DSZU 123.62-13	57.4	.	0.12	0.035	.	0.88	.	0.075	.	0.073	8.73	.	2.51	.	0.044	.
1	CETEM BXPA-4	57.3	52.7	(0.01)	0.007	.	6.9	(0.009)	(0.03)	(0.02)	0.027	4.65	3.7	1.31	0.018	0.16	29.7
1	NCS DC91019	57.15	.	0.089	.	.	16.11	1.00	0.235	0.31	0.077	6.31	.	2.65	.	.	.
1	CETEM BXBA-3	56.5	54.00	(0.012)	(0.0008)	.	8.41	(0.005)	(0.02)	(0.009)	0.156	2.91	1.08	0.96	0.017	0.018	27.2
1	CETEM BXPA-2	55.4	50.6	(0.01)	0.013	.	9.2	trace	(0.03)	(0.01)	0.016	4.91	4.2	1.35	0.035	0.073	29.03
1	SRM 696	54.5	.	0.018	0.047	.	8.70	0.009	0.012	(0.007)	0.050	3.79	.	2.64	0.072	0.14	29.9
1	IPT 131	54.1	11.5	0.022	.	.	0.15	0.78	.	1.77	0.042	0.35	30.0
1	CETEM BXPA-3	53.7	49.8	(0.01)	0.016	.	11.6	(0.011)	(0.03)	(0.02)	0.042	4.19	3.4	1.92	0.029	0.21	28.2
1	BCS 395	52.4	.	0.05	(0.07)	.	16.3	(0.02)	0.02	(0.02)	.	1.24	.	1.93	.	.	27.8
1	CETEM BXPA-1	52.8	49.0	.	.	.	12.8	.	.	.	(0.018)	(4.93)	3.8	1.42	0.058	(0.066)	27.5
1	GBAP-15	50.93	.	0.02	0.050	.	18.18	0.019	0.055	0.026	0.039	6.62	.	4.416	0.099	0.110	19.41
1	CETEM BXMG-5	50.5	39.7	(0.02)	(0.004)	.	9.2	0.54	(0.04)	(0.03)	0.111	10.7	7.8	1.28	0.030	0.25	26.7
1	CETEM BXMG-2	50.4	45.5	(0.01)	0.028	.	13.7	0.013	(0.04)	(0.01)	0.209	6.36	1.88	1.64	0.035	0.042	27.5
1	CETEM BXSP-1	50.1	40.0	(0.03)	0.003	.	6.7	0.53	(0.06)	(0.02)	0.203	14.7	7.8	1.24	0.016	0.15	26.1
1	CETEM BXBA-4	49.7	43.70	(0.014)	(0.0010)	.	12.78	(0.007)	(0.02)	(0.02)	0.195	8.45	4.50	1.55	0.023	0.028	23.3
1	SRM 69b	48.8	.	0.13	0.011	.	7.14	0.068	0.085	(0.025)	0.118	13.43	.	1.90	0.028	0.29	27.2
1	SRM 698	48.2	.	0.62	0.080	.	19.6	0.010	0.058	.	0.37	0.69	.	2.38	0.064	0.061	27.3
1	CETEM BXMG-6	46.8	41.80	(0.03)	0.030	.	19.4	0.018	(0.04)	(0.025)	0.229	4.41	1.06	2.22	0.081	0.020	23.7
1	NCS HC28811	46.52	.	0.69	.	.	14.01	0.25	0.37	0.10	0.35	22.96	.	1.36	.	.	12.75
1	SRM 697	45.8	.	0.71	0.100	.	20.0	0.062	0.18	.	0.97	6.81	.	2.52	0.063	0.065	22.1
1	DSZU 123.61-13	42.8	.	0.13	0.22	.	27.2	.	0.046	.	0.086	3.36	.	2.15	0.071	.	.
1	GBAP-16	42.60	.	0.11	0.047	.	16.52	0.126	0.146	0.057	0.034	21.56	.	3.587	0.081	0.107	14.94
1	SRM 600	40.0	.	0.22	0.024	.	17.0	0.23	0.05	0.022	0.039	20.3	.	1.31	0.060	0.060	20.5
1	CETEM BXMG-3	37.9	33.2	(0.02)	0.029	.	35.3	0.021	(0.04)	(0.02)	0.184	2.29	0.75	2.01	0.051	0.050	22.0
1	GBAP-13	36.92	.	0.02	0.011	.	7.487	0.1004	0.0159	0.018	0.031	34.6	.	0.7516	0.024	.	19.92
1	GBAP-14	35.07	.	0.03	0.122	.	40.67	0.073	0.042	0.024	0.042	6.74	.	2.502	0.177	0.062	14.32

#	Number	Al ₂ O ₃	A.Al ₂ O ₃	CaO	Cr ₂ O ₃	Fe	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	R.SiO ₂	TiO ₂	V ₂ O ₅	ZrO ₂	LOI
---	--------	--------------------------------	----------------------------------	-----	--------------------------------	----	--------------------------------	------------------	-----	-------------------	-------------------------------	------------------	--------------------	------------------	-------------------------------	------------------	-----

A.Al₂O₃: Available AluminaR.SiO₂: Reactive Silica* Includes HfO₂

Number	BaO	MnO	MnO ₂	SO ₃	ZnO
BCS 394/1
NCS HC28815	C: 0.018
JCRM R301
NCS DC61105
NCS HC28814	.	0.011	.	.	C: 0.050
NCS DC91017	.	0.036	.	S:0.031	0.0018 Ga ₂ O ₃ : 0.0114
NCS HC28813	.	0.053	.	.	C: 0.099
NCS DC91018	.	0.012	.	S:0.040	0.0040 Ga ₂ O ₃ : 0.0106
CETEM BXGO-1	.	.	0.005	(0.22)	(0.002)
NCS HC28812	.	0.082	.	.	C: 0.14
CETEM BXGO-2	.	.	0.015	0.31	(0.002) Org.C: 0.21
DSZU 123.38-03	.	0.012	.	S:0.032	C: 0.12 CO ₂ : 0.15 Ga ₂ O ₃ : 0.012 50 g unit
DSZU 123.62-13	.	0.009	.	S:0.030	C: 0.10 CO ₂ : 0.09 Ga ₂ O ₃ : 0.013 100 g unit
CETEM BXPA-4	.	.	0.037	(0.05)	(0.002)
NCS DC91019	.	0.021	.	S:0.033	0.0036 Ga ₂ O ₃ : 0.008
CETEM BXBA-3	.	.	0.022	0.228	(0.004) Org.C: (0.16)
CETEM BXPA-2	.	.	(0.0013)	(0.07)	(0.003)
SRM 696	.	0.004	.	0.150	0.0014
IPT 131	.	0.31	.	.	0.013
CETEM BXPA-3	.	.	0.045	(0.09)	(0.003)
BCS 395
CETEM BXPA-1	.	(0.0017)	.	.	0.004
GBAP-15	(0.005)	0.014	.	0.055	.
CETEM BXMG-5	.	.	0.34	(0.05)	0.012
CETEM BXMG-2	.	.	0.016	(0.15)	(0.004)
CETEM BXSP-1	.	.	0.070	(0.07)	0.009
CETEM BXBA-4	.	.	0.035	0.23	(0.006) Org.C: 0.28
SRM 69b	.	0.110	.	0.551	0.0035
SRM 698	.	0.38	.	0.143	0.029
CETEM BXMG-6	.	.	0.120	0.19	(0.005) Org.C: 0.17
NCS HC28811	.	0.13	.	.	C: 0.20
SRM 697	.	0.41	.	0.0770	0.037
DSZU 123.61-13	.	0.023	.	S:0.045	.
GBAP-16	(0.011)	0.022	.	0.068	.
SRM 600	.	0.013	.	0.155	0.003 last of stock
CETEM BXMG-3	.	.	0.102	(0.13)	(0.005)
GBAP-13	<0.01	0.01	.	0.1032	.
GBAP-14	(0.006)	0.017	.	0.145	.

Number	BaO	MnO	MnO ₂	SO ₃	ZnO
--------	-----	-----	------------------	-----------------	-----

CRM BAUXITE SET

shown in mass %, available in set/9 ONLY, 50 g units

Number	Al ₂ O ₃	Cr ₂ O ₃	Fe ₂ O ₃	SiO ₂	TiO ₂	
DSZU 123.40-03 3	59.6	0.014	2.91	4.25	0.81	one final set remaining in stock
DSZU 123.40-03 9	59.2	0.05	1.46	5.46	3.51	
DSZU 123.40-03 4	57.1	0.020	7.58	3.21	1.24	
DSZU 123.40-03 1	53.0	0.021	13.9	2.86	1.29	
DSZU 123.40-03 7	52.4	0.25	15.4	1.70	2.04	
DSZU 123.40-03 8	49.4	0.21	16.8	4.38	2.24	
DSZU 123.40-03 5	47.9	0.28	21.2	2.20	2.16	
DSZU 123.40-03 6	43.6	0.26	24.9	4.31	2.67	
DSZU 123.40-03 2	39.4	0.033	34.3	2.60	1.24	

RM BAUXITEAl₂O₃: Available Alumina

C.Org: Organic Carbon

BXT-04, BXT-06 500 g units

others 100 g

Number	Al ₂ O ₃	C.Org	CaO	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	SiO ₂	TiO ₂	V ₂ O ₅	ZnO	ZrO ₂	A.Al ₂ O ₃	LOI
ALC-BXT-10	54	(0.08)	(<0.01)	(0.03)	12.4	(<0.01)	.	(0.01)	.	(0.05)	.	2.7	2.01	(0.06)	.	(0.07)	.	28.6
ALC-BXT-09	53.4	(0.2)	(0.01)	0.037	14.5	(0.01)	(0.03)	(0.04)	(0.01)	(0.07)	(0.06)	7.57	2.98	(0.06)	(0.002)	(0.12)	.	20.8
ALC-BXT-13	53.4	0.051	(0.02)	0.016	11.44	(0.01)	(0.01)	(0.01)	(0.01)	(0.02)	(0.09)	4.82	1.54	(0.04)	(0.002)	(0.08)	53.3	28.52
ALC-BXT-08	51.5	(0.082)	(0.02)	(0.049)	9.6	(0.018)	(0.03)	(0.021)	(0.02)	(0.26)	.	3.2	9.5	(0.17)	(0.006)	(0.089)	.	25.6
ALC-BXT-14	51.2	0.162	(0.01)	(0.01)	13.17	(0.01)	(0.01)	(0.02)	(0.01)	(0.062)	(0.11)	5.86	1.11	(0.01)	(0.005)	0.131	50.4	28.35
ALC-BXT-06	48.7	(0.14)	0.122	0.130	18.8	(0.011)	(0.06)	0.27	(0.03)	0.61	(0.15)	0.79	2.65	(0.12)	0.025	(0.065)	.	27.2
ALC-BXT-04	48.6	(0.13)	(0.013)	(0.089)	17.0	(0.026)	(0.04)	0.041	(0.02)	0.13	(0.13)	2.69	5.33	(0.16)	(0.002)	(0.064)	.	25.8

CRM BERYLLIUM ORE

analysis listed in mass %

Number	BeO	Al ₂ O ₃	CaO	F	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Units
NCS DC86313	3.02	15.55	0.52	0.0088 (F-)	0.15	0.47	(0.63)	3.28	0.083	0.020	3.63	(0.018)	71.97	0.010	0.86	70 g
NCS DC86302	0.365	14.86	0.584	0.041	(0.18)	0.593	0.59	3.89	0.069	0.036	4.67	0.013	73.99	0.016	0.73	70 g
NCS DC86301	0.060	14.86	0.582	0.019	(0.18)	0.513	0.60	4.10	0.071	0.030	4.79	(0.012)	73.97	0.015	0.68	70 g

continued analysis listed in mg/kg

Number	CeO ₂	Dy ₂ O ₃	Er ₂ O ₃	Eu ₂ O ₃	Gd ₂ O ₃	Ho ₂ O ₃	La ₂ O ₃	Lu ₂ O ₃	Mo	Nd ₂ O ₃	Pr ₆ O ₁₁	RE _x O _y *	Sc ₂ O ₃	Sm ₂ O ₃	Tb ₄ O ₇	Tm ₂ O ₃	W	Y ₂ O ₃	Yb ₂ O ₃
NCS DC86313	13.1	3.62	1.95	0.11	2.83	0.67	6.08	0.25	3.37	5.96	1.58	63.6	1.91	1.99	0.57	0.29	.	23.0	1.88
NCS DC86302	14.8	4.6	2.2	0.15	3.8	0.87	7.7	0.36	1.2	7.6	2.0	78.6	3.1	2.7	0.80	0.36	5.5	28.9	2.5
NCS DC86301	14.3	4.5	2.1	0.14	3.6	0.82	7.0	0.31	0.41	6.6	1.7	75.6	1.7	2.5	0.80	0.32	1.3	29.2	2.2

* RE_xO_y: Rare Earth Oxide**CRM BORATE ORE**

analysis listed in mass %

60 g units

Number	Al ₂ O ₃	B ₂ O ₃	BaO	CaO	F	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	SO ₃	SiO ₂	SrO	TiO ₂	LOI+H ₂ O
SRM 1835	3.474	18.739	0.0497	21.622	0.348	1.141	1.261	3.411	0.0333	3.484	1.477	18.408	0.9418	0.1332	25.724

CRM BRUCITE

T = total

50 g units

Number	Al ₂ O ₃	CaO	CO ₂	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂
NCS DC60129	0.053	2.51	8.08	0.49	(25.24)	0.0041	61.43	0.036	0.0066	0.12	2.69
NCS DC60130	0.067	6.18	9.95	0.40	(23.22)	0.0066	56.21	0.033	0.013	0.12	4.47

RM CALCINED BONE

25 or 100 g

Number	Al ₂ O ₃	BaO	CaO	F	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	SO ₃	SrO	TiO ₂	LOI
CERAM CCB1	0.05	0.031	53.4	0.13	0.04	(0.12)	0.011	1.14	0.52	40.5	1.28	0.114	0.049	<0.01	2.60

CRM CLAY

analysis listed in mass %

Number	Al	B	Ba	Ca	Ce	Co	Cr	Fe	K	Li	Mg	Mn	Na	P	Si	Sr
SRM 97b	20.76	.	(0.018)	0.0249	.	(0.00038)	0.0227	0.831	0.513	0.0550	0.113	0.0047	0.0492	(0.02)	19.81	0.0084
SRM 98b	14.30	.	(0.07)	0.0759	.	(0.00163)	0.0119	1.18	2.81	0.0215	0.358	0.0116	0.1496	(0.03)	26.65	0.0189
SRM 679	11.01	.	0.0432	0.1628	(0.0105)	(0.0026)	0.01097	9.05	2.433	0.00717	0.7552	(0.1730)	0.1304	(0.075)	24.34	0.00734

continued analysis listed in mass %

analysis listed in mg/kg

Number	Ti	Zn	Zr	LOI	Cs	Eu	Hf	Rb	Sb	Sc	Th	Units
SRM 97b	1.43	(0.0087)	(0.05)	(13.3)	(3.4)	(0.84)	(13)	(33)	(2.2)	(22)	(36)	60 g powder
SRM 98b	0.809	(0.0110)	(0.022)	(7.5)	(16.5)	(1.3)	(7.2)	(180)	(1.6)	(22)	(21)	60 g powder
SRM 679	0.577	(0.0150)	.	.	(9.6)	(1.9)	(4.6)	(190)	.	(22.5)	(14)	75 g powder

CLAYS and FIRECLAYS

= class, where 1 = CRM and 2 = RM

analysis listed in mass %

* CERAM AN41 lists Mn₃O₄ as MnO

** CERAM: 25 or 100g

#	Number	SiO ₂	Al ₂ O ₃	CaO	Cl-	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	TiO ₂	LOI	Units	Other
1	NH 139	82.41	13.80	0.14	.	0.84	0.51	0.12	.	0.059	.	.	0.53	.	75 g	
1	NH 138	68.90	26.01	0.23	.	1.47	0.98	0.22	.	0.10	.	.	0.92	.	75 g	
1	NCS DC62108c	67.74	13.79	1.62	.	5.17	2.40	1.82	.	1.50	.	0.08	0.71	4.54	20 g	
1	GBW 03103	66.64	13.28	3.23	0.011	4.64	2.50	1.84	0.088	1.81	0.106	0.027	.	5.10	60 g	CO ₂ : 1.66
1	VS K11	62.2	16.8	1.2	.	(6.3)	.	2.01	0.064	.	S:0.05	0.98	.	.	50 g	
1	NH 137	61.46	32.43	0.28	.	1.63	1.31	0.28	.	0.126	.	.	1.13	.	75 g	
1	GBW 03115	55.90	28.57	0.70	.	0.87	1.54	0.30	.	1.74	.	.	1.21	8.72	50 g	
1	GBW 03102a	53.67	31.32	1.80	0.0029	0.33	1.15	0.083	0.020	2.55	0.053	0.023	0.030	8.81	50 g	CO ₂ : (0.051)
1	IPT 42	51.9	32.2	0.05	.	1.09	0.47	0.19	.	0.02	0.07	.	0.96	12.9	50 g	
1	IPT 32	51.8	28.5	0.17	.	3.46	0.80	0.39	.	0.16	0.13	.	1.49	12.6	50 g	
1	BCS 348	51.13	31.59	0.173	.	1.04	2.23	0.305	.	0.344	0.071	.	1.08	11.75	100 g	
1	GBW 03101a	49.98	26.27	0.13	0.0041	10.55	0.79	0.46	0.052	0.060	0.14	0.49	0.70	10.62	50 g	CO ₂ : (0.041)
2	CERAM AN41 *	48.5	36.4	0.09	.	0.62	1.59	0.35	0.01*	0.10	0.14	.	0.03	12.3		** BaO ² 0.02 SrO, ZnO: 0.01

CRM CLAY - SYNTHETIC MULLITE

60 g units

Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P	SiO ₂	TiO ₂
NCS HCl4809	72.39	0.19	0.93	0.24	0.42	0.16	0.043	21.81	3.64
NCS HCl4808	57.47	0.15	0.46	1.69	0.14	0.46	0.022	37.41	1.45
NCS HCl4807	43.62	0.23	1.14	1.62	0.21	0.46	0.062	51.43	0.65

CRM COPPER ORE WITH EXTENSIVE ANALYSIS - CONTINUED ON THE NEXT PAGE

analysis listed in mass % except * which is mg/kg # = provisional analysis OREAS samples list multiple methods, more information upon request

Number	Cu	Ag*	Au*	C	F	Fe	Fe ₂ O ₃	Mo	Ni	Pb	Pd*	Pt*	S	Zn	LOI
VS 2891-84	40.4	707.7	.	.	.	(5.78)	.	.	.	2.25	.	.	(15.98)	2.89	.
CGL 203	31.80	(66)	.	.	.	(21.0)	.	0.1399	.	0.01366	.	.	(33.94)	0.1526	.
CETEM CBPA-2	27.9	12	(8)	(0.07 org)	(0.0322)	.	39.6	(0.0054)	(0.203)	0.0112	.	.	(30.6)	0.0096	(14.5)
CAN CCU-1e	23.07	205.2	20.27	0.100	(0.0255)	30.7	.	(0.00161)	(0.000727)	0.703	.	.	35.28	3.02	(17.14)
JCu-1 #	3.73	.	.	(3.06T)	.	.	17.5T	.	(0.0425)	(0.0004)	.	.	(7.00)	0.0679	(15.37)
GBW 07233	1.15	3.9	.	.	0.079	.	55.58	0.00014	0.00096	0.00091	.	.	0.72	0.059	.
OREAS 504	.	.	1.48	(0.47)	.	.	(11.6)	.	.	.	(0.014)	(0.007)	(1.3)	.	(3.6)
OREAS 504 4	1.137	(3.0)	.	.	.	(8.6)	.	0.0643	(0.0036)	(0.0021)	.	.	1.37	(0.0113)	.
OREAS 504 A	1.123	(2.7)	1.47	.	.	(7.3)	.	0.0624	(0.0035)	(0.0018)	.	.	1.37	(0.0093)	.
CETEM CBPA-1	0.98	.	(0.17)	(0.16 org)	(0.0708)	.	16.5	(0.0010)	0.0276	(0.0033)	.	.	(0.16)	0.0126	(3.8)
SRM 330a	0.845	(1.06)	.	(0.00045)	0.002895	(0.0027)	.	.	.	0.00949	.
CGL 103	0.8080	2.05	.	.	.	2.75	.	0.0160	(0.000950)	(0.00727)	.	.	2.12	0.0096	(4.27)
OREAS 502b 4	0.773	2.09	0.495 FA	.	.	5.57	.	0.0238	0.00372	0.00315	(0.010FA)	(0.008FA)	0.950	0.0134	.
OREAS 502b A	0.758	2.01	0.487	.	.	5.02	.	0.0229	0.00335	0.00196	(<0.010)	(<0.005)	0.970	0.0124	.
OREAS 904	0.519	.	0.045	(<0.002)	(<0.010)	.	.	.
OREAS 904 4	0.612	0.551	.	.	.	6.68	.	0.000212	0.00401	0.00106	.	.	0.063	0.00263	.
OREAS 904 A	0.630	0.366	(0.02)	.	.	6.40	.	0.000202	0.00366	0.000849	.	.	0.034	0.00224	.
CAN HV-2a	0.3808	1.448	.	(0.4)	.	2.044	.	0.01254	0.000647	0.00069	.	.	0.344	0.00565	(3.01)
GBW 07234	0.19	0.7	.	.	0.080	.	12.25	0.00024	0.00056	0.00130	.	.	0.14	0.013	.
USZ 4-85	0.115	(1.1)	3.9T	0.007	(0.00165)	(0.00510)	.	.	2.03	(0.00680)	(4.26)
OREAS 901	0.083	.	0.363	(0.002)
OREAS 901 4	0.141	0.439	.	.	.	4.03	.	0.000336	0.00399	0.00174	.	.	0.036	0.00240	.
OREAS 901 A	0.144	0.276	0.34	.	.	3.70	.	0.000323	0.00347	0.00146	.	.	0.033	0.00202	.
SRM 331a	0.0789	.	(0.121)	(0.0565)	.	(4.207)	.	(0.00032)	(0.00081)	(0.0006)	.	.	(0.0870)	0.00718	.

Number	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	SiO ₂	Ti	TiO ₂
VS 2891-84	(21.74)	.	.
CGL 203	(6)	.	.
CETEM CBPA-2	.	1.57	.	1.21	.	(0.22)	.	0.79	(0.0048)	.	.	0.35	.	(0.38)	(6.3)	(0.060)	.
CAN CCU-1e	0.1385	.	0.129	.	(0.0133)	.	0.706	.	0.0096	.	(0.0147)	.	.	.	3.134	(0.00549)	.
JCu-1 #	.	0.29	.	23.5	.	0.015	.	2.13	.	0.59	.	0.052	.	(<0.005)	(28.68)	.	0.013
GBW 07233	.	1.73	.	9.61	.	0.071	.	3.91	.	0.60	.	0.044	.	.	9.27	.	0.079
OREAS 504	.	(13.2)	.	(4.2)	.	(3.5)	.	(3.2)	.	(0.08)	.	(2.9)	.	(0.24)	(55.0)	.	(0.58)
OREAS 504 4	(8.2)	.	(3.2)	.	(3.1)	.	(2.2)	.	(0.07)	.	.	.	(0.10)	.	.	(0.36)	.
OREAS 504 A	(1.7)	.	(1.9)	.	(0.25)	.	(1.5)	.	(0.04)	.	(0.11)	.	(0.09)	.	.	(0.15)	.
CETEM CBPA-1	.	10.1	.	2.97	.	1.85	.	3.29	0.058	.	.	1.42	.	1.00	(56.4)	(0.35)	.
SRM 330a	7.053	.	0.323	.	5.47	.	0.868	.	.	.	0.657	.	(0.0326)	Si: 33.4	(0.1223)	.	.
CGL 103	.	16.19	.	0.285	.	3.71	.	0.69	.	(0.0160)	.	1.48	.	0.139	67.07	.	0.463
OREAS 502b 4	7.47	.	2.71	.	3.06	.	1.54	.	0.0550	.	2.06	.	0.100	.	(Si:28.75)	0.440	.
OREAS 502b A	1.90	.	1.10	.	0.941	.	1.22	.	0.0398	.	0.148	.	0.098	.	(Si: 0.027)	0.307	.
OREAS 904
OREAS 904 4	6.30	.	0.046	.	3.31	.	0.556	.	0.041	.	0.034	.	0.098	.	.	(0.19)	.
OREAS 904 A	1.25	.	0.0404	.	0.603	.	0.143	.	0.041	.	(0.01)	.	0.095	.	.	(0.007)	.
CAN HV-2a	7.96	.	1.891	.	2.31	.	0.329	.	0.0545	.	2.335	.	0.0427	.	Si:31.34	0.128*	.
GBW 07234	.	15.18	.	4.95	.	2.71	.	1.30	.	0.12	.	3.21	.	.	53.36	.	0.50
USZ 4-85	(3.38)	(1.74)	.	(0.15)	.	.	.
OREAS 901
OREAS 901 4	6.81	.	0.092	.	3.67	.	0.600	.	0.0290	.	0.042	.	0.062	.	.	(0.23)	.
OREAS 901 A	0.992	.	0.091	.	0.512	.	0.124	.	0.030	.	(0.01)	.	0.059	.	.	(0.01)	.
SRM 331a	(7.92)	.	(1.552)	.	(0.967)	.	(1.623)	.	0.0497	.	(3.15)	.	(0.0550)	.	.	(0.228)	.

continued analysis listed in mg/kg

Number	As	Ba	Be	Bi	Cd	Ce	Co	Cr	Cs	Dy	Er	Eu	Ga	Gd	Ge	Hf
VS 2891-84	290
CGL 203	(9.31)	.	(86.87)	(42.97)
CETEM CBPA-2	(9)	.	.	.	(4)	(43)	444	20
CAN CCU-1e	101	(6)	.	(3)	74.2	(2)	301	(3)	.	(1)	.
JCu-1 #	(173)	(3.5)	.	.	(3.6)	.	(324)	(10)
GBW 07233	4.2	.	.	1.5	0.42	13.2	.	(7)	.	1.1	0.78	0.28	22.6	1.1	0.89	.
OREAS 504
OREAS 504 4	(6.5)	(604)	(1.1)	(5.0)	(1.0)	(25)	(22)	(60)	(2.3)	(2.8)	(1.6)	(0.8)	(19)	(3.4)	.	(1.6)
OREAS 504 A	(5.5)	(65)	(<1)	(4.8)	(0.4)	(18)	(18)	(48)	(8.0)	.	.	(0.6)
CETEM CBPA-1	(9)	(478)	.	.	(3)	(427)	78	26	(22.2)	.	.	.
SRM 330a	.	1560	.	.	3.391	22.32	4.542	77.0	17.4	.	.	.
CGL 103	167	958	(1.04)	.	(0.57)	(40.35)	12	(18)	(2.27)	.	.	.	(18.92)	.	.	.
OREAS 502b 4	19.1	928	2.57	5.14	(0.28)	61	20.2	84	10.3	(4.43)	2.43	1.29	18.6	4.95	(0.19)	2.27
OREAS 502b A	18.6	299	0.43	5.22	(0.20)	52	19.0	79	8.34	(2.99)	(1.58)	(0.40)	8.58	(3.54)	0.22	0.43
OREAS 904
OREAS 904 4	98	194	7.86	4.05	(0.07)	86	83	54	3.79	(5.6)	(3.4)	(1.4)	16.7	(6.6)	0.18	5.0
OREAS 904 A	91	68	6.54	3.74	0.058	70	82	17.5	0.62	(3.0)	(1.6)	(1.0)	3.40	(4.9)	(0.1)	(0.6)
CAN HV-2a	12.1	869	(1.02)	(1.58)	(0.2)	19.1	3.40	100	2.70	1.126	0.646	(0.502)	19.56	1.40	.	(2)
GBW 07234	1.5	(800)	.	0.43	0.14	72.6	.	(10)	(10)	2.4	1.3	1.3	22.6	3.6	0.93	.
USZ 4-85	(47)	.	(4.5)	(21.7)	.	.	(12)	(22)
OREAS 901
OREAS 901 4	71	229	6.17	4.75	(0.05)	95	73	57	5.12	(6.4)	(3.7)	(1.7)	18.7	(8.2)	(0.2)	5.27
OREAS 901 A	66	86	4.49	4.35	(0.05)	78	73	23.0	0.97	(3.5)	(1.8)	(1.1)	3.15	(5.6)	0.11	(0.8)
SRM 331a	.	259	.	.	(0.1)	(9.6)	12.6	13.9	(1)	.	.	.	(16.3)	.	.	.

CRM COPPER ORE WITH EXTENSIVE ANALYSIS - CONTINUED FROM THE PREVIOUS PAGE

analysis listed in mg/kg																# = provisional analysis	OREAS samples list multiple methods, more information upon request															
Number	Hg	Ho	In	La	Li	Lu	Nb	Nd	Pr	Rb	Re	Sb	Sc	Se	Sm	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zr	Units	Other		
VS 2891-84	28.2	50 g			
CGL 203	(400)	.	(77)	100 g				
CETEM CBPA-2	.	.	.	(21)	(38)	(3.3)	(21)	160 g				
CAN CCU-1e	10.4	.	(6)	(1)	(0.5)	.	(0.2)	(1)	.	(0.5)	(0.004)	104	(1)	(304)	(0.3)	(15)	(5)	200 g	H ₂ O%:(0.150)				
JCu-1 #	(2.9)	(1.9)	.	(3.8)	100 g	H ₂ O%:(0.54-, 1.00+)				
GBW 07233	.	0.26	1.4	7.5	(9)	0.16	.	4.7	1.4	.	.	0.36	1.8	5.1	1	11.1	50 g				
OREAS 504	60 g, various methods, last of stock				
OREAS 504 4	(<0.1)	(0.6)	(0.7)	(13)	(23)	(0.2)	(6.8)	(13)	(3.1)	(69)	(<0.1)	(1.1)	(18)	(9.8)	(2.9)	(11)	(55)	" 4 acid digestion					
OREAS 504 A	(<0.1)	.	.	(9.0)	(20)	.	(0.5)	.	.	(16)	.	(0.5)	(7.9)	(11)	(11)	" aqua regia					
CETEM CBPA-1	.	.	.	(267)	.	.	(10)	(143)	.	(101)	.	.	(16)	.	(20)	(7)	135 g				
SRM 330a	22.19	.	(5.7)	5.693	80.5	90 g				
CGL 103	.	.	.	(19.38)	(83.76)	.	23	(102.76)	100 g				
OREAS 502b 4	(<1)	0.85	0.60	29.9	31.0	0.34	16.2	26.9	7.13	167	(0.007)	1.66	13.2	8.47	5.33	11.1	71	10 or 60 g 4-Acid except FA Au Pd Pt					
OREAS 502b A	(0.038)	(0.60)	0.58	25.4	29.1	0.20	1.44	23.1	6.27	106	0.005	1.09	7.00	7.97	(4.20)	9.93	10.9	10 or 60 g Aqua Regia					
OREAS 904	10 g or 60 g			
OREAS 904 4	.	(1.1)	0.22	43.2	16.7	0.47	(6.3)	(36)	(9.7)	130	(<0.002)	1.48	11.2	3.30	(7.1)	2.83	" 4 acid digestion				
OREAS 904 A	(0.04)	(0.6)	0.17	33.9	(3.5)	0.21	(0.09)	(32)	(7.7)	22.4	(<0.001)	0.78	3.83	2.81	(5.4)	0.58	" aqua regia B: (12ppm)				
CAN HV-2a	.	(0.2)	.	9.1	(11)	(0.109)	(2)	8.77	(2.32)	48.3	(0.1)	0.689	(3)	(0.7)	1.69	(1.2)	200 g	H ₂ O%:(0.3)			
GBW 07234	.	0.48	0.25	40.3	(15)	0.2	.	29.4	8.1	(94)	.	0.23	5.4	0.89	5.1	3.8	50 g				
USZ 4-85	(80)	.	.	.	(5.4)	100 g				
OREAS 901	10 g or 60 g, various methods			
OREAS 901 4	.	(1.3)	0.26	47.0	17.9	0.53	(8.0)	(46)	(13)	161	(0.002)	2.61	14.0	(3.2)	(9.0)	3.33	" 4 acid digestion				
OREAS 901 A	(0.02)	(0.7)	0.21	38.1	(3.1)	0.22	(0.1)	(35)	(8.9)	23.9	(0.002)	1.47	5.55	2.68	(6.4)	0.58	" aqua regia B: (13ppm)				
SRM 331a	0.00184	.	.	(4)	(3)	(25)	.	.	(11.4)	40 g				

CRM COPPER ORE

analysis listed in mass %															F = Sodium Peroxide Fusion ICP	A = Four Fcid Digestion ICP-OES/MS values										10 g
Number	Cu	Ag	Al ₂ O ₃	As	CaO	Cd	Co	Fe	MgO	Pb	S	Sb	SiO ₂	Zn												
OREAS 113 4	13.5	0.00226	.	0.0234	.	0.00155	0.0766	28.2	.	0.0230	.	0.0008	.	0.4178												
OREAS 113 F	13.3	(0.0025)	.	0.0238	.	(0.0016)	0.0754	28.0	.	0.0248	.	0.00076	.	0.4158												
OREAS 166 4	8.82	0.00108	1.38	.	0.98	.	0.1970	11.38	1.67	0.0140	11.6	.	.	0.0037												
OREAS 166 F	8.75	0.0012	1.34	.	0.98	.	0.2077	11.45	1.67	0.0128	11.29	.	61.4	0.0037												
OREAS 112 F	5.13	0.0017	.	0.0240	.	0.0015	0.0547	33.3	.	0.0349	.	0.0017	.	0.4302												
OREAS 112 4	5.10	0.00132	.	0.0222	.	0.00146	0.0551	34.1	.	0.0360	.	0.0016	.	0.4351												
OREAS 165 F	3.21	0.00031	2.61	.	0.11	.	0.2485	8.86	3.48	0.0434	8.28	.	72.0	0.0044												
OREAS 165 4	3.20	0.000302	2.59	.	0.081	.	0.2445	8.86	3.53	0.0443	8.5	.	.	0.0037												
OREAS 111b 4	2.47	0.00101	.	0.0220	.	0.00143	0.0490	36.1	.	0.0393	.	0.0021	.	0.4334												
OREAS 111b F	2.44	<0.0020	.	0.0212	.	0.00148	0.0488	35.5	.	0.0397	.	0.0019	.	0.4370												
OREAS 111 4	2.37	0.00101	.	0.0215	.	0.00120	0.0452	35.2	.	0.0377	.	0.0018	.	0.4196												
OREAS 111 F	2.30	<0.0020	.	0.0217	.	0.0014	0.0457	34.1	.	0.0375	.	0.0019	.	0.4099												
OREAS 164 4	2.25	0.000294	2.07	.	0.393	.	0.0168	6.80	3.07	0.0214	6.2	.	.	0.0045												
OREAS 164 F	2.22	<0.0005	2.05	.	0.401	.	0.0167	6.88	3.07	0.0199	5.98	.	77.9	0.0047												
OREAS 163 4	1.76	0.00043	3.24	.	0.860	.	0.0230	11.07	5.42	0.0492	10.4	.	.	0.0108												
OREAS 163 F	1.71	0.0005	3.16	.	0.92	.	0.0230	11.1	5.34	0.0461	9.98	.	.	0.0102												
OREAS 162 4	0.772	0.00035	1.70	.	13.2	.	0.0631	8.57	9.17	0.0340	4.38	.	.	0.0026												
OREAS 162 F	0.761	0.000358	1.64	.	13.1	.	0.0660	8.63	9.04	0.0320	4.40	.	.	0.002755												

CRM COPPER ORE - EXTENSIVE ANALYSIS NOT SHOWN

analysis listed in mass % except * which is mg/kg

10 or 60 g

Number	Cu	Ag*	Au*	Bi	Co	Ni	Pb	Rb	Se	Sn	Zn	Zr
OREAS 98 4	14.8	45.1	.	0.00972	0.0121	(0.00353)	0.0345	(0.00817)	0.0158	0.0206	0.1355	(0.00667)
OREAS 98 A	14.7	42.8	.	0.00928	0.0111	.	0.0343	.	0.0143	0.0171	0.1302	.
OREAS 935 I	12.43	43.73	.	0.0679	0.0085	(0.0156)	0.0233	(0.0089)	0.0105	0.0119	0.0721	(0.0074)
OREAS 935 4	12.55	43.87	(<0.1)	0.0709	0.0077	0.00297	0.0225	(0.0080)	0.0088	0.0108	0.0692	0.00474
OREAS 935 A	12.48	43.67	(0.04)	0.0680	0.0077	0.00262	0.0222	(0.00136)	0.0086	0.0096	0.0666	(0.00133)
OREAS 935 F	12.54	.	.	.	<0.0100	(0.00158)	(0.0255)	.	.	(0.0138)	0.0688	(0.0050)
OREAS 934 I	9.50	34.67	.	0.0517	0.0075	(0.00320)	0.0262	(0.0106)	0.0096	0.0095	0.0744	(0.0093)
OREAS 934 4	9.59	36.46	(<0.1)	0.0527	0.0071	0.00282	0.0240	(0.0097)	0.0085	0.0083	0.0724	0.0058
OREAS 934 A	9.58	34.40	(0.022)	0.0515	0.0067	0.00257	0.0242	(0.00145)	0.0080	0.0076	0.0692	(0.00162)
OREAS 934 F	9.51	.	.	.	<0.0100	(0.000917)	0.0242	.	.	(0.0116)	0.0718	(0.0073)
OREAS 933 I	8.34	29.32	.	0.0466	0.0063	(0.0108)	0.0197	(0.0103)	0.0079	0.0086	0.0617	(0.0101)
OREAS 933 4	8.37	31.05	(<0.1)	0.0451	0.0060	0.00281	0.0189	(0.0095)	0.0068	0.0073	0.0602	0.0063
OREAS 933 A	8.27	29.62	(0.027)	0.0449	0.0061	0.00281	0.0187	(0.00126)	0.0066	0.0066	0.0596	(0.00164)
OREAS 933 F	8.38	.	.	.	<0.0100	(0.000800)	0.0210	.	.	(0.0106)	0.0606	(0.0090)
OREAS 97 4	6.31	19.6	.	0.00401	0.00629	(0.00370)	0.0147	(0.0126)	0.00714	0.00957	0.0646	(0.00965)
OREAS 97 A	6.28	19.5	.	0.00403	0.00625	.	0.0142	.	0.00673	0.00838	0.0635	.
OREAS 932 I	6.17	23.00	.	0.0337	0.0062	(0.00303)	0.0195	(0.0122)	0.0073	0.0067	0.0590	(0.0114)
OREAS 932 4	6.13	22.41	(<0.1)	0.0324	0.0060	0.00274	0.0184	(0.0112)	0.0067	0.0058	0.0591	0.0073
OREAS 932 A	6.11	21.96	(0.012)	0.0322	0.0061	0.00282	0.0182	(0.00162)	0.0063	0.0051	0.0579	(0.00191)
OREAS 932 F	6.19	.	.	.	<0.0100	(0.00133)	0.0200	.	.	(0.0092)	0.0599	(0.0093)
OREAS 96 4	3.93	11.5	.	0.00263	0.00499	(0.00393)	0.0101	(0.0141)	0.00407	0.00656	0.0457	(0.0109)
OREAS 96 A	3.91	11.5	.	0.00279	0.00492	.	0.0100	.	0.00410	0.00528	0.0448	.
OREAS 931 I	3.83	13.62	.	0.0205	0.00466	(0.00362)	0.0155	(0.0134)	0.0050	<0.0060	0.0490	(0.0132)
OREAS 931 4	3.82	14.04	(<0.1)	0.0204	0.00469	0.00288	0.0147	(0.0128)	0.00435	0.00421	0.0480	(0.0085)
OREAS 931 A	3.81	14.18	(0.006)	0.0206	0.00453	0.00287	0.0146	(0.00153)	0.00422	0.00330	0.0472	(0.00199)
OREAS 931 F	3.82	.	.	.	<0.0050	(<0.0010)	(0.0159)	.	.	(0.0064)	0.0495	(0.0097)
OREAS 930 I	2.51	8.63	.	0.0138	0.00391	(<0.0050)	<0.0150	(0.0150)	0.00336	0.00351	0.0499	(0.0147)
OREAS 930 4	2.52	9.00	(<0.1)	0.0136	0.00374	0.00311	0.0141	(0.0136)	0.00301	0.00311	0.0492	0.0089
OREAS 930 A	2.51	9.13	(0.004)	0.0139	0.00364	0.00306	0.0142	(0.00181)	0.00286	0.00234	0.0488	(0.00220)
OREAS 930 F	2.51	.	.	.	<0.0100	(0.00217)	<0.0160	.	.	(0.0059)	0.0504	(0.0112)
OREAS 929 I	2.00	<8	.	0.0114	0.00362	(<0.0020)	0.0116	(0.0141)	0.00243	0.00311	0.0492	(0.0141)
OREAS 929 4	2.00	7.18	(<0.1)	0.0111	0.00336	0.00307	0.0130	(0.0129)	0.00241	0.00291	0.0477	0.0088
OREAS 929 A	2.02	7.03	(0.004)	0.0114	0.00336	0.00297	0.0131	(0.00175)	0.00240	0.00201	0.0468	(0.00211)
OREAS 929 F	2.02	.	.	.	(<0.0100)	(0.00275)	0.0143	.	.	(0.00458)	0.0486	(0.0127)
Number	Cu	Ag*	Au*	Bi	Co	Ni	Pb	Rb	Se	Sn	Zn	Zr
OREAS 928 I	1.52	<8	.	0.0083	0.00335	(0.00376)	0.0112	(0.0127)	<0.0020	0.00278	0.0432	(0.0141)
OREAS 928 4	1.53	5.39	(<0.100)	0.0079	0.00313	0.00296	0.0122	(0.0116)	0.00188	0.00262	0.0436	(0.0094)
OREAS 928 A	1.52	5.11	(0.006)	0.0080	0.00306	0.00281	0.0122	(0.00148)	0.00179	0.00157	0.0429	(0.00199)
OREAS 928 F	1.52	.	.	.	<0.0050	(0.00208)	(0.0133)	.	.	(0.00300)	0.0435	(0.0108)
OREAS 504b 4	1.11	3.07	1.61	0.000492	0.00209	0.00345	0.00262	0.0106	0.00124	0.00114	0.0108	0.0060
OREAS 504b A	1.10	2.98	1.56	0.000513	0.00187	0.00300	0.00201	0.0051	0.00116	0.00104	0.0096	0.00142
OREAS 927 I	1.09	.	.	0.0062	0.00310	0.00302	0.0214	0.0122	.	0.00238	0.0750	.
OREAS 927 4	1.08	4.08	.	0.0057	0.00287	0.00297	0.0209	0.0119	0.00157	0.00207	0.0716	0.0097
OREAS 927 A	1.06	3.90	<0.010	0.0059	0.00286	0.00280	0.0203	0.00147	0.00153	0.00122	0.0717	0.00201
OREAS 502c	0.783	0.779	0.488	0.000067	0.00144	0.00381	0.00235	0.0187	0.000340	0.000340	0.0109	0.0078
OREAS 903 4 **	0.652	0.432	(<0.050)	0.00089	0.0131	0.0054	0.00113	0.0137	0.000606	0.000263	0.00243	0.0152
OREAS 903 A	0.671	0.349	(<0.005)	0.00088	0.0131	0.00487	0.000895	0.00126	0.000534	(0.00004)	0.00213	0.00182
OREAS 925 I	0.621	.	.	0.00336	0.00254	0.00355	0.0115	0.0166	.	0.00179	0.0459	.
OREAS 925 4	0.615	2.36	.	0.00313	0.00246	0.00348	0.0110	0.0163	0.000907	0.00149	0.0446	0.0106
OREAS 925 A	0.629	2.41	<0.005	0.00324	0.00238	0.00317	0.0111	0.00189	0.000891	0.000777	0.0437	0.00218
OREAS 503c	0.538	0.830	0.698	0.000060	0.00146	0.00386	0.00206	0.0178	0.000331	0.000338	0.0087	0.0075
OREAS 924 I	0.520	.	.	0.00293	0.00244	0.00385	0.0096	0.0173	.	0.00167	0.0389	.
OREAS 924 4	0.512	1.99	.	0.00273	0.00234	0.00360	0.0092	0.0172	0.000786	0.00136	0.0380	0.0109
OREAS 924 A	0.516	1.92	<0.005	0.00257	0.00227	0.00326	0.0092	0.00203	0.000732	0.000672	0.0370	0.00222
OREAS 923 I	0.4328	.	.	0.00212	0.00239	0.00407	0.0086	0.0169	.	0.00161	0.0358	.
OREAS 923 4	0.4230	1.60	.	0.00214	0.00231	0.00358	0.0083	0.0166	0.000654	0.00133	0.0345	0.0116
OREAS 923 A	0.4248	1.62	<0.005	0.00218	0.00222	0.00327	0.0081	0.00196	0.000599	0.000599	0.0335	0.00225
OREAS 501c	0.276	0.461	0.221	0.000069	0.00151	0.0060	0.00215	0.0196	0.000207	0.000338	0.0081	0.0081
OREAS 922 I	0.2215	.	.	0.00108	0.00209	0.00434	0.0064	0.0167	.	0.00100	0.0277	.
OREAS 922 4	0.2122	0.888	.	0.00101	0.00204	0.00379	0.0059	0.0164	0.000376	0.000995	0.0267	0.0127
OREAS 922 A	0.2176	0.851	<0.005	0.00103	0.00194	0.00343	0.0060	0.00227	0.000344	0.000383	0.0256	0.00223
OREAS 921 I	0.0293	.	.	<0.0002	0.00173	0.00419	0.00271	0.0178	.	<0.0010	0.0139	.
OREAS 921 4	0.0274	0.152	.	0.000120	0.00165	0.00411	0.00280	0.0176	<0.0002	0.000582	0.0132	0.0147
OREAS 921 A	0.0278	0.164	<0.005	0.000125	0.00155	0.00380	0.00260	0.00242	0.000104	0.000145	0.0124	0.00214
OREAS 501b 4	0.260	0.778	0.248	0.000154	0.00158	0.00415	0.00230	0.0184	(0.000363)	0.000558	0.0089	0.0077
OREAS 501b A	0.258	0.721	0.243	0.000160	0.00149	0.00375	0.000942	0.0126	0.000278	0.000465	0.0080	0.00109
OREAS 920 I	0.0113	.	.	<0.00008	0.00161	0.00440	0.00229	0.0179	.	<0.0006	0.0122	.
OREAS 920 4	0.0112	<0.2	.	0.000069	0.00156	0.00418	0.00235	0.0176	<0.0002	0.000504	0.0116	0.0151
OREAS 920 A	0.0110	0.099	<0.010	0.000068	0.00150	0.00384	0.00215	0.00248	0.000087	0.000121	0.0106	0.00213
Number	Cu	Ag*	Au*	Bi	Co	Ni	Pb	Rb	Se	Sn	Zn	Zr

** OREAS 903 also certifies Cu at 0.434% using acid leach

These samples also detail up to 74 additional elements, certificates available upon request.
Each sample is certified for a variety of methods: 4 = 4 ACID DIGESTION, A = AQUA REGIA, F = FUSION, I = ICP

COPPER ORE

= class, where 1=CRM and 2=RM analysis in mass % except * = mg/kg GBM: 250g IMN: 200g NCS: 50g OREAS: see below VS: 100g

#	Number	Cu	Ag*	As	Ni	Pb	Tot.S	Zn	Au*	Bi*	Co*	Cd*	Fe	Hg*	Mo*	Sb*	SiO ₂
1	OREAS 992	43.90	(33.50)	.	(1.50)	(0.0470)	36.97	(17.8*)	(7.92)	.	(790)	.	.	.	(2.00)	.	10 g units
1	GBM914-12	27.0618	61.5	.	0.0020	0.1256	29.74	0.824
1	GBM315-15	25.0264	334.2	.	0.0842	0.7680	26.74	1.2523
1	GBM313-16	24.2702	109.3	.	0.0153	0.0035	3.64	0.0043
1	GBM316-12	23.8210	86.0	.	0.0009	0.0236	25.43	0.0480
1	GBM310-15	23.7854	78.8	.	0.0293	0.3327	27.6	1.1931
1	GBM913-14	22.7577	200.3	.	0.0053	0.0029	6.22	0.0107
1	GBM314-15	21.2876	176.2	.	0.0037	0.0145	6.54	0.02
1	OREAS 991	20.66	48.14	(0.0170)	(0.00320)	(0.0123)	(30.77)	.	47.04	(<50)	(122)	.	(26.92)	.	(490)	.	50 g units
1	GBM908-11	17.7033	11.4	.	.	0.0547	29.78	2.3604
1	VS R34/1	17.21	81	0.35	.	0.17	38.6	2.45	4.7	60	.	32.9	.	97	680	1.92	.
1	GBM905-14	17.3667	.	.	0.0531	0.0334	.	0.0074
1	GBM314-16	16.0964	89.4	.	0.0661	0.0884	22.79	0.2898
1	GBM913-13	12.1059	74.1	.	0.0084	0.0125	2.43	0.0386
1	NCS DC29110	8.53	120	0.020	.	0.027	(15.42)	0.19	.	.	.	13.5	.	(0.039)	.	35.3	.
1	GBM908-16	7.0180	22.5	.	.	0.0735	7.54
1	GBM908-15	5.0027	13.7	.	.	0.4961	5.04
1	NCS DC29109	3.84	59.9	0.046	.	0.024	(8.58)	0.083	.	.	.	5.68	.	(0.043)	.	71	.
1	GBM905-11	3.1758	.	.	0.0038	0.0042	.	0.0084
1	GBM911-16	2.4774	7.9	.	0.0229	0.0325	3.6	0.1210
1	GBM915-16	2.2960	51.2	.	0.0197	0.9698	3.88	1.9551
1	GBM915-9	2.2767	50.0	0.1265	0.0198	0.9502	.	1.9314	.	.	106
1	GBM316-11	2.2288	21.7	.	0.0021	0.1065	18.11	1.0133
1	GBM905-12	2.1853	.	.	0.0062	0.0033	.	0.0100
1	GBM915-15	1.0954	11.9	.	0.7954	0.0066	1.29	0.0050
1	GBM915-4	1.1835	25.7	0.0663	0.0118	0.4921	.	1.0035	.	.	69
1	GBM311-14	1.7501	04.5	.	0.0045	0.0508	2.0	0.0872
1	GBM311-10	1.7334	3.8	0.0040	0.0031	0.0505	.	0.0841	.	.	65
1	VS R35	1.65	17.4	0.067	.	0.036	26.7	0.74	1.23	35.2
2	IMN MR2	1.61	29	0.013	.	0.085	.	0.025	0.88
2	IMN MR1	1.23	58	0.028	.	0.15	.	0.040	1.41
1	GBM911-11	1.1499	10.2	.	0.0026	0.1722	2.9	0.1422
1	GBM910-6	1.0084	3.6	0.0117	0.0044	0.0173	.	0.0907	.	.	131
1	GBM910-16	1.0069	3.7	.	0.0048	0.0180	1.5	0.0943
1	NCS DC29108	0.90	14.9	0.00766	.	0.0080	(1.65)	0.020	(0.028)	.	11.7	.	.
1	NCS DC29107	0.29	6.1	0.00414	.	0.00345	(0.68)	0.010	(0.15)	.	23.4	.	.

CRM COPPER ORE

analysis listed in mass % except * which is mg/kg

Number	Cu	As	Bi	Cd	F	Fe	MgO	Mn	Ni	Pb	S	Sb	Zn	Ag*	Au*	Units
NCS DC28058	20.56	0.012	.	<0.001	0.056	24.70	7.63	0.013	0.093	0.015	22.87	.	0.194	17.1	4.68	20 g
NCS DC28059	16.60	0.020	.	<0.001	0.052	26.39	5.81	0.044	0.082	0.017	23.92	.	0.131	14.8	5.10	20 g
NCS DC28055	12.79	4.68	0.023	0.0067	0.028	3.22	0.18	0.110	0.017	0.037	1.54	0.25	0.64	85.9	0.04	50 g
NCS DC28057	10.71	0.034	.	<0.001	0.036	29.34	4.01	0.084	0.072	0.019	25.05	.	0.052	12.0	6.16	20 g
NCS DC28056	8.46	2.14	0.19	0.0064	0.53	10.44	7.04	0.169	0.011	0.087	0.86	0.22	0.503	109.9	0.05	50 g
NCS DC28054	6.78	0.209	0.283	0.0021	1.15	15.39	12.51	0.124	<0.005	0.106	0.082	.	0.456	126.1	0.05	50 g

CRM CRYOLITE

analysis listed in mass %

Number	Al	CaO	F	Fe ₂ O ₃	Na	P ₂ O ₅	SO ₄ ²⁻	SiO ₂	LOI	Units
NCS DC91001	17.34	(0.606)	55.45	0.053	21.75	0.0034	0.233	0.087	4.53	100 g
NCS DC91002	15.18	(0.597)	54.66	0.032	26.32	0.025	0.199	0.211	2.97	100 g
NCS DC91003	13.65	(0.719)	53.89	0.036	29.29	0.013	0.205	0.363	2.25	100 g
NCS DC91004	13.16	(0.508)	53.2	0.033	30.26	0.037	0.293	0.389	2.12	100 g
NCS DC91005	12.69	(0.0062)	52.14	0.0098	32.01	0.065	0.45	0.485	1.4	100 g
NCS DC91006	11.75	0.112	51.21	0.04	33.24	0.051	0.683	0.238	1.6	100 g

CRM DIABASE WITH EXTENSIVE ANALYSIS

analysis listed in mass %																		US: 25 g units	NCS: 70 g units
Number	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SO ₃	SiO ₂	TiO ₂	LOI	
US W-2a	15.45	.	10.86	(0.0205)	8.34	1.53	10.83	.	0.626	6.37	0.167	2.20	0.14	(0.0079)	.	52.68	1.06	.	
NCS DC71311	13.21	(0.11)	7.83	(0.07)	7.24	.	(13.40)	(2.44)	1.49	5.08	.	3.17	0.55	.	0.44	49.88	2.94	2.30	
continued analysis listed in mg/kg except % which is mass %																			
Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Cl%	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	
US W-2a	.	.	.	170	1.5	0.39	0.39	78.1	(0.04)	37.5	111	1.7	82.6	5.5	(2.6)	3.5	21.2	7.2	
NCS DC71311	0.33	5.1	17.0	614	1.5	0.39	0.39	78.1	(0.04)	37.5	111	1.7	82.6	5.5	(2.6)	3.5	21.2	7.2	
Number	Ge	Hf	Hg	Ho	La	Li	Lu	Mn%	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se	Sm
US W-2a	.	.	.	1.2	38.1	20.8	0.34	(0.16)	1.4	25.3	42.8	56.8	33.0	10.6	47.4	2.3	27.1	(0.19)	8.6
NCS DC71311	1.5	9.2	0.017	1.2	38.1	20.8	0.34	(0.16)	1.4	25.3	42.8	56.8	33.0	10.6	47.4	2.3	27.1	(0.19)	8.6
Number	Sn	Sr	Ta	Tb	Th	Tm	U	V	W	Y	Yb	Zn	Zr						
US W-2a	.	190	.	.	4.9	0.36	1.2	268	1.4	24.5	2.2	(160)	359						
NCS DC71311	2.0	470	1.8	1.1	4.9	0.36	1.2	268	1.4	24.5	2.2	(160)	359						

DIORITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %																		T = Total	IAG: RM, ~35 g units	all others: CRM, 100 g units
Number	Al ₂ O ₃	CaO	CO ₂	Fe	FeO	Fe ₂ O ₃	H ₂ O+	H ₂ O-	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Type			
CAN SY-4	20.69	8.05	3.5	4.2	2.86	6.21	(1.0)	(0.15)	1.66	0.54	0.108	7.10	0.131	49.9	0.287	4.56	Diorite Gneiss			
VS 6103-91	16.56	4.84	(0.18)	.	3.79	5.55	(1.6)	(0.14)	2.98	3.05	0.086	3.57	0.17	60.45	0.86	1.59	Quartz			
USZ 50-2009	15.97	6.99	.	.	4.82	8.10T	0.35	(0.11)	1.55	3.81	0.12	3.33	(0.39)	57.75	1.34	0.51	Diorite			
IAG OU-4	14.83	4.48	.	.	4.52	5.82T	.	.	2.70	2.30	0.14	3.61	0.173	63.34	0.77	1.72	Microdiorite			
continued analysis listed in mg/kg																				
Number	B	Ba	Be	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	Gd	Hf	Ho				
CAN SY-4	.	340	2.6	122	2.8	12	1.5	7	18.2	14.2	2.00	.	335	14.0	10.6	4.3				
VS 6103-91	46	720	2.4	46	17	58	2.9	39	.	.	1.3	710	18	.	.	.				
USZ 50-2009	.	425	.	50.8	84.9	100	(5.24)	100	(4.29)	(2.29)	(1.41)	.	419.58	(5.21)	(3.69)	(0.85)				
IAG OU-4	.	360.8	1.79	55.7	13.5	54.7	2.07	27.3	7.81	4.83	1.64	.	17.4	7.39	5.54	1.63				
Number	La	Li	Lu	Mn	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Sm	Sn	Sr					
CAN SY-4	58	37	2.1	819	13	57	9	10	15.0	55	.	1.1	12.7	.	1191					
VS 6103-91	27	30	0.30	.	12	24	33	24	.	83	.	15	4.8	.	410					
USZ 50-2009	24.40	(13.9)	(0.30)	.	6.92	30.48	40.94	8.97	(6.45)	48.5	.	20.46	(5.61)	.	454					
IAG OU-4	24.96	35.0	0.71	.	12.8	27.9	21.0	14.1	6.85	98.5	0.30	19.1	6.94	2.42	99.9					
Number	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr								
CAN SY-4	0.9	2.6	1.4	.	2.3	0.8	8	.	119	14.8	93	517								
VS 6103-91	.	.	6.8	.	.	.	96	.	21	2.1	71	173								
USZ 50-2009	(0.48)	(0.76)	3.88	.	(0.32)	(1.09)	213	266	23.62	2.05	92.77	191								
IAG OU-4	1.00	1.25	8.42	0.46	0.72	2.19	82.7	.	47.1	4.70	69.5	195.1								

DOLERITE WITH EXTENSIVE ANALYSIS

= class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	SiO ₂	Al ₂ O ₃	CaO	F	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI	Units
1	SARM 50	51.56	15.28	10.80	.	8.49	11.0	.	.	0.61	7.57	0.17	2.30	0.15	.	0.86	.	100 g
2	IAG OU-2	51.095	13.801	8.994	.	8.404	.	13.253	.	0.990	5.585	0.170	2.480	0.300	.	2.425	.	~35 g
2	IAG OU-5	49.10	13.62	6.63	.	8.74	14.60	.	.	0.826	5.17	0.310	4.29	0.440	.	2.718	2.08	~35 g
1	VS 8671-2005	47.99	14.63	10.42	(0.021)	10.33	.	14.62	(0.88)	0.46	7.51	0.21	2.32	0.17	(0.026)	1.59	(0.42)	100 g
1	US DNC-1a	47.15	18.34	11.49	(0.0066)	7.32	1.79	9.97	.	0.234	10.13	0.15	1.89	0.07	.	0.48	.	25 g

continued analysis listed in mg/kg

Number	Ag	As	Au	B	Ba	Be	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu
SARM 50	220	.	.	(30)	.	40	357	.	84	.	.	.
IAG OU-2	341.1	1.11	.	60.2	.	44.8	97.0	0.495	63.0	6.09	3.06	2.23
IAG OU-5	.	(2.45)	.	.	309.2	1.31	(0.20)	44.17	.	38.60	38.40	0.555	27.32	9.04	5.49	2.35
VS 8671-2005	(0.05)	.	(0.0026)	(3.8)	227	0.8	.	22	.	52	213	(0.45)	180	5.1	2.9	1.4
US DNC-1a	.	(0.12)	.	(0.9)	118	(1)	.	.	(60)	57	270	.	100	(3)	.	0.59

Number	Ga	Gd	Ge	Hf	Ho	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb
SARM 50	(10)	.	(85)	25	.	14
IAG OU-2	23.05	7.26	.	5.29	1.21	27.71	12.79	0.372	3.05	17.25	33.35	51.77	13.12	7.92	25.44
IAG OU-5	21.2	8.64	(2.03)	5.59	1.92	18.10	21.74	0.767	.	9.58	28.47	15.00	4.66	6.29	19.29
VS 8671-2005	17	4.5	1.5	2.7	(1)	8	8.6	0.44	0.98	6	13.2	126	(3)	2.6	11
US DNC-1a	(15)	(2)	.	.	(0.62)	3.6	5.2	.	.	(3)	5.2	247	(6.3)	.	(4.5)

Number	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
SARM 50	195	.	.	(6)	.	.	.	216	.	23	.	81	86
IAG OU-2	.	28.21	8.70	17.73	403.7	1.20	1.11	3.02	.	0.427	0.63	339.3	.	30.93	2.52	113.0	200.5
IAG OU-5	0.42	42.4	7.64	2.00	226.8	(0.546)	1.46	2.25	(0.125)	0.789	0.500	447.8	(0.865)	51.8	5.10	133.6	219.9
VS 8671-2005	.	41	4	2.64	197	0.35	0.8	1.0	.	0.44	0.45	315	(0.4)	29	3.3	112	125
US DNC-1a	0.96	31	.	.	144	148	.	18	2	70	38

CRM DOLOMITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	CaO	MgO	Al ₂ O ₃	CO ₂	Cl	F	FeO	Fe ₂ O ₃	H ₂ O	K ₂ O	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Units
UL DW1	30.84	21.40	(0.05)	.	.	.	0.27	0.04	.	0.010	(0.06)	0.042	(0.023)	(0.06)	(0.010)	47.29	50 g
GBW 07114	30.02	21.8	0.10	46.77	0.012	0.014	0.15	0.04	(0.34)	0.038	0.010	(0.03)	0.006	0.62	0.015	.	50 g

continued analysis listed in mg/kg except % which is mass %

Number	Ag	As	B	Ba	Be	Bi	Br	Tot.C%	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd
UL DW1	.	(1.3)	.	24	2.2	(0.2)	(4)	.	(4)	0.82	0.50	0.16	.	0.81
GBW 07114	0.04	0.23	20.5	44.3	(0.22)	0.03	0.84	(12.88)	0.07	3.58	3.88	2.6	0.07	30.2	0.19	0.09	0.05	(0.21)	0.18

Number	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	S%	Sb	
UL DW1	.	(0.03)	.	0.18	.	.	3.6	.	0.05	.	.	3	.	(35)	0.67
GBW 07114	0.15	(0.10)	(0.004)	0.04	0.23	(0.066)	1.34	2.30	0.019	(0.24)	(2.77)	1.39	241	(4.44)	(0.44)	(1.42)	0.011	0.04	

Number	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
UL DW1	0.24	.	0.62	.	284	.	0.12	.	0.08	.	0.06	1.4	6.9	.	9.4	0.39	83	.
GBW 07114	0.098	0.08	0.25	0.53	49	(0.18)	0.05	(0.012)	0.11	(0.070)	(0.040)	0.16	2.10	0.11	(1.40)	0.09	11.7	3.0

DOLOMITE

= class, where 1 = CRM and 2 = RM analysis listed in mass %

#	Number	CaO	MgO	SiO ₂	Al ₂ O ₃	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MnO	Na ₂ O	P	P ₂ O ₅	PbO
1	NCS DC28009a	45.90	6.65	2.56	0.47	.	0.235	0.272	0.0049	0.012	0.0033	.	.
1	NCS DC28206	41.66	11.31	4.64	0.16	.	0.112	.	0.0050	.	0.0032	.	.
1	NCS DC14020a	37.59	15.38	0.25	0.11	.	0.459	0.019	0.020	0.015	0.0012	.	.
1	NCS DC14019b	34.82	17.34	1.30	0.18	.	0.447	0.027	0.0072	0.019	0.0057	.	.
1	NCS DC28203	34.74	17.16	1.45	0.286	.	0.404	.	0.012	.	0.016	.	.
1	NCS DC28015a	33.60	15.50	4.89	1.40	.	0.641	0.35	0.0085	0.019	0.011	.	.
1	NCS DC14018b	31.96	19.92	0.77	0.23	.	0.269	0.030	0.031	0.033	0.0023	.	.
1	NCS DC11003a	31.49	21.06	0.098	0.083	.	0.024	0.0030	0.0061	0.017	0.0016	.	.
1	NCS DC28014a	31.46	18.60	2.97	0.81	.	0.472	0.29	0.012	0.021	0.0061	.	.
1	NCS DC28013a	31.12	19.10	2.65	0.73	.	0.504	0.13	0.011	0.034	0.0034	.	.
1	NCS DC28012a	30.94	20.92	1.48	0.23	.	0.26	0.085	0.011	0.012	0.014	.	.
1	NCS DC28208	30.80	20.79	0.99	0.23	.	0.32	.	0.019	.	0.0013	.	.
1	NCS DC28202	30.79	20.73	2.12	0.203	.	0.275	.	0.026	.	0.0013	.	.
1	NCS DC28201	30.62	20.53	6.75	0.048	.	0.085	.	0.0072	.	0.0012	.	.
1	BCS 512	30.61	21.59	0.379	0.055	(<0.001)	0.030	(<0.02)	0.0036	.	.	(<0.02)	(<0.001)
1	CGL 021	30.59	21.40	0.267	0.200	.	0.228	0.062	0.047	(0.040)	.	0.044	.
2	DH 0915	30.59	21.21	0.035	0.019	.	0.191	0.007	0.050	0.026	.	0.008	.
1	ECRM 782-1	30.34	21.29	0.266	0.104	0.0009	0.450	0.0260	0.081	.	.	0.0128	0.0029
1	NCS DC28207	30.33	20.88	1.26	0.27	.	0.44	.	0.013	.	0.018	.	.

Number	S	Sr	SrO	Ti	TiO ₂	ZnO	LOI	Units
NCS DC28009a	0.021	.	0.020	.	0.024	.	43.48	50 g
NCS DC28206	0.0093	.	0.015	.	0.0056	.	41.70	50 g
NCS DC14020a	0.046	45.88	50 g
NCS DC14019b	0.009	0.021	.	0.085	.	.	45.37	50 g
NCS DC28203	0.028	45.58	50 g
NCS DC28015a	0.013	.	0.0060	.	0.074	.	43.24	50 g
NCS DC14018b	0.010	0.0081	.	0.011	.	.	46.24	70 g
NCS DC11003a	0.011	0.021	.	0.0043	.	.	46.71	70 g
NCS DC28014a	0.019	.	0.0058	.	0.041	.	44.94	50 g
NCS DC28013a	0.007	.	0.0064	.	0.034	.	45.49	50 g
NCS DC28012a	0.003	.	0.0070	.	0.0080	.	45.58	50 g
NCS DC28208	0.022	46.20	50 g
NCS DC28202	0.016	45.22	50 or 100 g
NCS DC28201	0.0019	41.00	50 g
BCS 512	.	.	0.024	.	0.0020	(<0.01)	46.80	100 g
CGL 021	.	(0.0057)	.	(0.013)	.	(46.63)	50 g	C:(12.925)
DH 0915	100 g	
ECRM 782-1	.	.	.	0.0042	0.0082	47.25	100 g	
NCS DC28207	0.033	46.11	50 g	

RM DOLOMITE SUBSTITUTE

typical analysis

* DH 0710 also contains 0.015% CuO

100 g units

Number	CaO	MgO	Al ₂ O ₃	Cr ₂ O ₃	Fe	Fe ₂ O ₃	K ₂ O	Mn ₃ O ₄	NiO	P ₂ O ₅	PbO	S	SiO ₂	SrO	TiO ₂	V ₂ O ₅	ZnO	ZrO ₂
DH 0710 *	35.36	35.30	8.28	0.591	5.14	.	0.077	1.079	0.013	0.107	0.011	0.265	10.23	0.028	0.301	0.032	0.159	0.051
DH 0711	32.46	28.57	9.49	0.84	8.81	.	0.092	1.745	0.020	0.262	0.015	0.314	12.07	0.029	0.370	0.056	0.183	0.068
DH 0709	23.45	63.07	5.62	0.071	1.96	.	0.053	0.444	0.010	0.133	0.029	0.097	3.69	0.011	0.131	0.021	0.014	0.057

DUNITE

= class, where 1 = CRM and 2 = RM analysis listed in mass % DH, SARM: 100 g US: 25 g VS 2112: 40 g VS 4233: 100 g

#	Number	MgO	SiO ₂	Si	Al ₂ O ₃	Al	CO ₂	Tot.C	CaO	Ca	Co	Cr	Cr ₂ O ₃	T.Fe	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃
1	US DTS-2B	49.4	39.4	18.4	0.45	0.24	.	.	0.12	0.09	0.0120	1.5500	.	5.43	(4.27 FeII)	.	7.76
1	SARM 6	43.51	38.96	.	(0.3)	.	.	.	0.28	.	.	.	0.42	.	14.63	0.71	.
1	VS 2112-81	42.40	35.07	.	.	.	0.46	.	.	.	0.0129	10.06
1	VS 4233-88	41.86	39.58	.	0.97	.	(1.61)	.	1.52	.	0.012	0.41	.	.	(5.54)	.	8.91
2	DH 1002	23.79	41.87	.	8.87	.	0.767	0.332	4.36	.	.	.	0.037	5.40	0.623	.	.

continued analysis listed in mass %

Number	H ₂ O	K ₂ O	Mg	MnO	Mn ₃ O ₄	Na	Na ₂ O	Ni	NiO	P ₂ O ₅	S	TiO ₂	V	LOI @ 900 °C
US DTS-2B	.	.	29.8	.	.	(0.02)	.	0.3780	0.0022	.
SARM 6	.	(0.01)	.	0.22	.	.	(0.04)	(0.02)	.	.
VS 2112-81	11.35	.	.	0.176	.	.	.	0.133	0.00069	.
VS 4233-88	(+4.82 -0.4)	0.010	.	0.13	.	.	0.035	0.22	.	(0.01)	(0.041)	0.018	0.0033	6.31
DH 1002	.	4.80	.	.	0.061	.	0.068	.	0.022	0.922	.	0.929	.	5.95

continued analysis listed in mg/kg except % which is mass %

Number	Ba	Cu	Ge	Li	Mn	Mo	Pb	Rb	Sb	Sc	Sn	Sr	Zn
US DTS-2B	(16)	(3)	(0.7)	.	830	.	(4)	(2)	(0.6)	(3)	.	.	45
SARM 6
VS 2112-81	.	27	.	.	1.4	2.2	.	82
VS 4233-88	.	33	1.1	2.0	9	.	18	30
DH 1002

H₂O+: (4.82)

FELDSPAR

= class, where 1 = CRM and 2 = RM analysis listed in mass %

#	Number	SiO ₂	Al ₂ O ₃	BaO	CaO	F	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	PbO	Rb ₂ O	SrO	TiO ₂	LOI	Units
1	FLX CRM129	69.84	16.44	0.130	0.374	.	(0.104)	10.78	.	2.11	0.068	.	.	(0.014)	(0.036)	(0.428)	40 g
1	BCS 375/1	69.24	17.88	.	0.78	.	0.291	1.47	0.180	8.89	0.226	.	.	.	0.312	0.72	100 g
1	FLX CRM128	67.88	19.95	(0.007)	1.08	.	0.021	0.206	.	10.74	(0.008)	.	.	0.049	(0.017)	(0.171)	40 g
1	BCS 376/1	65.77	18.63	0.0210	0.421	.	0.085	11.59	(0.03)	3.00	(0.02)	0.0090	.	.	(<0.01)	0.203	100 g
2	CERAM CAS8	66.8	18.5	.	0.20	.	0.11	10.6	0.03	3.62	.	.	.	last	0.02	0.24	25 g
2	DH X1602	66.93	17.16	0.323	0.032	0.047	.	14.19	0.001	.	0.087	0.012	.	0.036	0.038	.	100 g
1	GBW 03116	66.26	18.63	.	0.76	.	0.19	9.60	0.054	3.69	0.048	0.86	50 g
1	IPT 72	66.2	20.26	.	0.18	.	0.09	1.47	(0.022)	10.0	1.03	.	.	.	0.005	0.66	80 g
1	IPT 53	65.8	18.3	.	0.27	.	0.13	12.1	0.05	2.5	0.072	.	.	.	0.013	0.51	80 g
	Number	Si	Al	Ba	Ca		Fe	K		Na	P	Pb	Rb	Sr			Units
1	SRM 99b	(32.07)	10.36	0.1409	(1.18)	.	0.02787	3.09	.	5.25	(0.0044)	0.00712	0.00726	0.0444	.	.	40 g

CRM FELDSPAR WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	Li ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Rb ₂ O	TiO ₂	LOI	Units
GUV FK	88.2	6.18	.	0.110	.	0.261	.	.	4.23	.	0.15	0.0037	0.25	0.077	.	0.058	.	50 g
UNS ZK	74.38	14.19	.	0.43	0.73	0.88	.	.	4.06	0.06	0.067	0.025	4.50	.	0.094	0.039	0.54	100 g
JF-1	66.69	18.08	.	0.93	.	0.06	0.08	+0.23 -0.13	9.99	.	0.006	0.001	3.37	0.01	.	0.005	.	100 g
JF-2	65.30	18.52	.	0.09	.	0.06	0.06	+0.24 -0.18	12.94	.	.	0.001	2.39	.	.	0.005	20 or	100 g
VS 811-89	60.67	18.20	0.20	0.51	4.8	7.20	.	4.0	3.43	.	2.22	0.042	2.31	0.19	.	0.94	.	100 g
SRM 70b	40 g

analysis listed in mg/kg except % indicating mass %, * indicating ppb, and ! indicating scientific notation

Number	Al%	As	B%	Ba%	Be	Ca%	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	F%	Fe%	Ga	Ge
GUV FK	.	.	.	0.0700	2.6	11	6	.
UNS ZK	.	4.8	5.7	7.0	.	38.7	12.2	33.3	.
JF-1	9.57	.	.	0.1750	.	0.66	4.19	0.12	5.48	2.09	0.82	0.39	0.31	0.87	.	0.06	17.4	.
JF-2	9.80	.	.	0.0298	.	0.06	0.84	0.68	.	1.06	0.78	.	.	0.59	.	0.04	17.9	.
VS 811-89	.	.	0.008	0.09	3.0	0.007*	21	96	.	6.3	41	.	.	0.06	.	.	22	1.7
SRM 70b	7.98	.	.	0.00282	.	0.1770	.	(0.7)	(0.13)	.	.	.

Number	Hf	Ho	K%	La	Li%	Mg%	Mn%	Mo	Na%	Nb	Nd	Ni	P%	Pb	Pr	Ra!	Rb%	S%
GUV FK	0.0008	0.004	18	.	.	0.0132	.
UNS ZK	1.4	21.0	.	33.5	.	29.4
JF-1	1.18	0.11	8.29	2.80	0.000981	0.004	0.001	.	2.50	0.74	1.46	.	.	33.4	0.48	.	0.0266	.
JF-2	0.19	.	10.74	0.63	0.000219	.	0.001	.	1.77	0.70	.	.	.	48.7	.	.	0.0218	.
VS 811-89	0.006	.	.	2.0	.	14	.	59	.	20	.	3e-10	0.012	0.087
SRM 70b	.	.	6.33	.	.	(0.0298)	0.00630	.	2.36	.	.	.	0.0790	(57)	.	.	(0.0495)	.

Number	Sc	Si%	Sm	Sr%	Ta	Tb	Th	Ti%	Tl	U	V	Y	Yb	Zn%	Zr%
GUV FK	.	.	.	0.0072	0.0014
UNS ZK	3.6	.	16.8	.	19.4	.	4.7	8.4	.	0.00194	.
JF-1	0.23	31.17	0.41	0.0172	0.079	0.076	1.17	0.003	1.18	0.33	5.43	2.84	0.35	0.000441	0.00386
JF-2	0.089	30.52	0.11	0.0200	.	.	0.31	0.003	1.10	.	4.86	2.67	.	0.000140	0.000673
VS 811-89	19	.	3.2	0.017	1.3	.	11	.	.	2.5	0.016%	32	3.4	0.012	0.021
SRM 70b	.	(34.4)	.	(0.0027)	.	.	.	(0.0032)	.	.	(0.93)	.	.	(0.00077)	.

CRM TRACE ELEMENTS IN FELDSPAR

analysis listed in mg/kg

Number	Rb	Uncertainty	Sr	Uncertainty	⁸⁷ Sr/ ⁸⁶ Sr	⁸⁶ Sr/ ⁸⁸ Sr	Units
SRM 607	523.90	1.01	65.485	0.320	1.20039	0.1194	5 g

CRM FLUORSPAR (FLUORITE)

analysis listed in mass % NCS DC62003a: 20g NCS DC14046-8,NCS DC282x, RH03: 50g other NCS, CMSI, GBW: 65g SRM: 120g all others: 100g

Number	CaF ₂	F	Al ₂ O ₃	BaO	CaCO ₃	CaO	Fe	Fe ₂ O ₃	K ₂ O	Na ₂ O	P	S	SiO ₂	Others
SRM 180	98.80
SARM 15	97.84	.	.	.	0.95	.	.	(0.23)	.	.	0.007	.	(0.26)	MgCO ₃ : 0.55 Mn: 0.0213
SRM 79a	97.39
SARM 14	97.32	.	.	.	(0.3)	.	.	(0.06)	.	.	(0.079)	.	(0.57)	.
BCS 392	97.2	.	.	0.37	.	0.52	0.12	0.67	CO ₂ : 0.48 Pb: 0.18
JK D	97.07	47.24	0.04	0.20	.	.	0.035	0.004	(1.5)	.
NCS DC28088	96.87	.	0.14	.	0.14	.	.	0.173	0.036	0.019	0.015	0.092	1.76	MgO: 0.015 Mn: 0.040
VS 1823-80	95.83	.	.	.	0.20	0.024	.	2.92	.
GBW 07250	94.91	.	.	.	(0.02)	.	.	0.096	0.019	0.005	0.0025	0.029	4.72	.
NCS DC28228	94.81	.	.	.	0.99	.	0.26	.	.	.	0.076	0.107	2.76	Mn: 0.010
VS 1822-80	93.86	.	.	.	0.41	0.057	0.410	3.16	.
NCS DC14022a	93.68	.	.	.	0.30	0.166	.	.	0.026	0.006	0.014	0.35	3.06	.
NCS DC14024a	93.28	.	.	.	0.62	0.22	.	.	0.040	0.006	0.0014	0.009	5.44	.
VS 3383-86	91.84	0.53	.	.	.	0.612	0.063	0.095	5.03	.
GBW 07251	90.87	.	.	.	(0.02)	.	.	0.124	0.026	0.005	0.0031	0.090	8.35	.
NCS DC28230	90.72	.	.	.	0.87	0.25	0.063	0.084	7.68	Mn: 0.012
CGL 132	88.65	.	.	.	(0.78)	(0.012)	(0.019)	10.15	.
NCS DC28229	85.56	.	.	.	0.58	0.28	0.045	0.079	10.62	Mn: 0.013
IPT 95	85.4	0.36	8.3	.
GBW 07253	85.21	.	.	.	(0.02)	.	.	0.209	0.044	0.005	0.0013	0.045	14.15	.
VS SH13	84.7	.	.	.	0.51	0.353	0.012	0.103	13.0	.
RH03 (RM)	84.6	0.35	0.0110	0.101	13.1	last of stock
NCS DC28087	83.12	0.69	.	.	1.06	.	0.36	0.28	0.031	0.018	0.050	0.050	13.74	MgO: 0.14 Mn: 0.0099
NCS DC28227	78.75	.	.	.	0.33	0.28	0.028	0.028	19.36	Mn: 0.012
NCS DC28226	77.33	.	.	.	0.20	0.31	0.068	0.068	18.04	Mn: 0.014
JK C	76.91	37.43	0.66	8.2	.	.	0.70	.	.	.	0.026	1.75	8.2	Pb: 0.07
NCS DC14048	76.79	.	.	.	0.34	0.4	.	0.081	0.007	0.0021	0.11	0.11	21.10	.
NCS DC28086	73.73	1.07	.	.	2.06	.	0.87	0.38	0.054	0.023	0.28	0.28	19.27	MgO: 0.73 Mn: 0.027
NCS DC14047	65.80	.	.	.	0.060	0.49	.	0.093	0.009	0.0027	0.26	31.04	.	.
NCS DC62003a	60.98	3.69	.	.	.	1.17	2.35	1.44	0.52	.	SO ₃ :0.12	26.20	MgO: 0.18 TiO ₂ : 0.15 LOI: 1.38	.
NCS DC28085	60.16	1.29	.	.	3.73	.	1.32	0.41	0.067	0.021	0.52	27.17	MgO: 1.99 Mn: 0.034	.
NCS DC28084	46.59	0.99	.	.	9.08	.	0.52	0.34	0.061	0.0071	0.071	28.89	MgO: 5.51 Mn: 0.051	.
VS 2665-83	38.00	.	.	.	6.80	0.036	0.32	25.57	.
CGL 135	35.60	.	.	.	(0.68)	0.037	0.41	47.67	.
VS 4182-87	32.75	.	.	.	1.70	0.114	0.038	47.52	.
VS 5132-89	32.69	.	.	.	11.75	(27.68)	.
VS 2666-83	32.02	.	.	.	0.70	0.055	1.24	47.73	.	.
VS 5133-89	4.17	.	.	.	1.10

Number	CaF ₂	F	Al ₂ O ₃	BaO	CaCO ₃	CaO	Fe	Fe ₂ O ₃	K ₂ O	Na ₂ O	P	S	SiO ₂	Others
--------	------------------	---	--------------------------------	-----	-------------------	-----	----	--------------------------------	------------------	-------------------	---	---	------------------	--------

FLUORSPAR (FLUORITE)

= class where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg IGS: 55 g all others: 100 g

#	Number	Ca	F	Al ₂ O ₃	BaO	CO ₂	CuO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	SiO ₂	SO ₄	TiO ₂	ZnO	LOI 900°C
1	IGS 39	.	46.69
2	DH 2712	44.18	40.6	1.01	.	2.11	0.199	0.373	0.125	0.739	0.237	.	8.91	0.103	0.069	0.103	0.370
2	DH 2709	39.98	38.10	0.310	.	0.027	0.052	15.72	0.029	0.017	0.077	0.030	3.93	0.027	.	0.004	0.929
1	USZ HJ	37.32	34.92	2.35	.	.	.	0.34	0.99	.	.	.	23.01	.	0.047	.	.
1	UNS FM **	35.89	34.03	(0.329)	3.89	(0.13)	.	0.496	0.097	(0.036)	.	(0.087)	22.59	.	0.018	.	.

Number	Bi*	Ce*	Cr*	Cr ₂ O ₃ %	Cu*	Eu*	La*	Mo*	Pb*	S	Sb*	Sc*	Sm*	Sr%	Y*
IGS 39	(0.014)	.
DH 2712	.	.	.	0.106	.	NiO:0.153	.	PbO:0.102	SnO ₂ :0.054	.	.
DH 2709	.	.	.	0.004
USZ HJ
UNS FM **	(58.8)	28.3	272	.	60.7	1.16	14.1	44.6	72.2	0.91	2.1	0.67	5.6	(0.0580)	154

** UNS FM also contains Co: 2.6*, Cs: 0.81*, Mn: 64*, U: 2.9*, Yb: 3* and trace informational values for 19 other elements

CRM GABBRO

analysis listed in mass %																			40 g units					
Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	H ₂ O+	T.H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂						
VS M08	51.98	16.39	0.43	9.02	0.0390	9.61	0.85	11.55	0.088	0.22	0.31	0.46	6.39	0.16	3.27	0.21	0.1700	1.15						
VS M07	40.79	17.60	0.03	14.62	0.1300	7.76	3.73	12.35	0.12	0.70	0.82	0.75	6.46	0.15	2.05	1.08	0.1800	3.39						
continued																			analysis listed in mg/kg except % which is mass %		VS M08: Gabbro		VS M07: Orthoclase Gabbro	
Number	B	Ba	Be	Co	Cr	Cs	Cu	Ga	La	Li	Mo	Nb	Ni	Pb	Rb	Sc	Sn	Sr	V	Y	Yb	Zn	Zr	
VS M08	7.5	272	0.8	48	126	1.1	40	18	26	5.5	3.2	3.7	18	7.3	4.0	31	2.7	477	199	18	2.0	84	48	
VS M07	4.5	7480	(1.2)	49	76	1.1	59	(18)	37	5.4	(2.4)	12	45	7.6	12	(25)	(3.8)	1745	270	.	.	65	53	

CRM GABBRO WITH EXTENSIVE ANALYSIS

analysis listed in mass % except * which is mg/kg																			CAN WMG-1A: 350 g		CGL: 100 or 250 g		GBW: 50 g		JGb-1: 20 g		others: 100 g	
Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI												
VS 2118-81	52.04	16.94	0.37	7.36	(0.0690)	5.43	9.93	.	1.67	2.25	3.74	0.187	4.20	0.476	1.02	.												
USZ 51-2009	48.00	26.26	.	13.61	(0.085)	2.00	.	4.22	(+0.61 -0.13)	0.31	2.85	0.080	2.42	0.078	0.37	1.40												
VS 8670-2005	46.63	14.93	.	10.68	0.13	6.23	.	11.33	(+0.93)	3.09	6.81	0.167	2.72	1.03	1.72	(0.77)												
JGb-2	46.47	23.48	.	14.10	.	5.41	0.62	6.69	-0.14	0.059	6.18	0.13	0.92	0.017	0.56	.												
JGb-1 *	43.66	17.49	.	11.90	0.0133	9.43	4.79	15.06	+1.28 -0.13	0.24	7.85	0.189	1.20	0.056	1.60	.												
CGL 013	43.15	22.57	.	14.99	(0.099)	4.57	.	10.99	(+0.46 -0.21)	0.11	4.51	0.10	1.41	(0.038)	0.94	(1.03)												
VS 2119-81	37.66	13.35	0.33	7.81	0.16	14.98	4.33	20.98	1.25	0.80	7.48	0.198	2.35	2.21	6.99	.												
VS 2117-81	37.62	13.67	(0.16)	15.75	0.0720	9.05	18.54	.	(0.12)	0.204	8.66	0.222	0.72	2.15	1.46	.												
GBW 07112	35.69	14.14	0.12	9.86	0.006	13.36	9.90	.	1.09	0.15	5.25	0.193	2.11	0.028	7.69	.												
	Si	Al		Ca		Fe				K	Mg	Mn	Na	P	Ti													
JGb-1 *	20.41	9.26	.	8.50	.	10.53	4.79	15.05	+1.28 -0.13	0.20	4.73	0.146	0.89	0.024	0.96	.												
CAN WMG-1A	18.27	4.75	.	10.06	.	12.71	.	.	.	0.1021	7.41	(0.1141)	0.1119	0.0731	0.419*	(4.31)												

* JGb-1 is certified for major elements and their oxides

continued																				analysis listed in mg/kg except % which is mass %																		
Number	Ag	As	B	Ba%	Be	Bi	Cd	Ce	Cl%	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd																				
VS 2118-81	.	.	.	0.1300	2.9	24	21	.	100	.	.	.	24	.																				
USZ 51-2009	.	.	.	0.0119	.	.	.	7.90	.	14.93	69.97	.	45.32	.	.	.	18.87	.																				
VS 8670-2005	(0.09)	.	(15)	0.152	1.9	.	.	163	.	40	58	3.3	58	6.2	2.8	3.9	17	11.5																				
JGb-2	.	.	.	0.00365	.	.	.	3.0	.	25.8	125	0.51	11.4	.	.	0.59	15.9	.																				
JGb-1 *	1.09	4.03	0.00643	.	0.087	8.17	.	60.1	57.8	0.26	85.7	1.56	1.04	0.62	17.9	1.61																						
CGL 013	.	.	0.004994	.	.	(3.43)	.	35.21	35.72	.	608	(0.79)	(0.44)	(0.37)	17.94	(0.8)																						
VS 2119-81	.	.	0.0440	0.82	.	.	.	69	56	.	69	.	.	.	13	.																						
VS 2117-81	.	.	0.0110	65	14	.	3600	.	.	.	21	.																						
GBW 07112	0.05	1.84	0.00862	.	0.04	0.09	4.2	0.006	93.0	14.5	.	28.3	1.11	0.47	0.74	23.7	1.31																					
CAN WMG-1A	3.03	5.99	.	0.0216	.	(0.251)	(0.818)	(17.18)	.	191	804	.	7120	2.291	(1.34)	(0.733)	(12.4)	(2.351)																				
Number	Ge	Hf	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pd	Pb	Pr	Pt	Rb	S%																				
VS 2118-81	1.1	46	13	.	2.0	.	.	14	.	20	.	.	42	.																				
USZ 51-2009	23.94	.	6.00	.	.	6.58	.																				
VS 8670-2005	1.3	5.3	1.1	.	.	82	12	0.3	1.4	8.4	89	47	.	15	20.7	.	80	(0.015)																				
JGb-2	.	0.25	.	.	.	1.5	.	0.062	0.42	1.9	1.8	13.6	.	1.5	.	.	2.9	.																				
JGb-1 *	1.01	0.88	0.33	.	.	3.60	4.59	0.15	0.59	3.34	5.47	25.4	.	1.92	1.13	.	6.87	0.1910																				
CGL 013	.	(0.32)	(0.16)	.	.	(1.31)	(4.89)	(0.06)	(0.5)	(0.36)	(2.33)	23.34	.	4.68	(0.5)	.	(1.96)	.																				
VS 2119-81	63	.	11	.	.	.	0.082																				
VS 2117-81	2.1	3.3	.	.	2.0	.	.	28	.	6	.	.	.	0.1240																				
GBW 07112	1.06	0.65	0.20	0.08	0.12	1.71	1.94	0.06	.	9.3	4.10	69	.	.	0.84	.	.	0.37																				
CAN WMG-1A	8.47	(44.7)	(0.196)	2.49	(5.26)	9.41	2480	0.484	(9.2)	(2.220)	0.899	(2.53)	3.43																				
Number	Sc	Se	Sm	Sn	Sr%	Ta	Tb	Te	Th	Tl	Tm	U	V	Y	Yb	Zn	Zr																					
VS 2118-81	24	.	.	5.5	0.0810	220	38	2.8	77	160																					
USZ 51-2009	12.33	.	.	0.1196	85.28	5.14	.	59.87	(33.49)																					
VS 8670-2005	26	.	17	3.2	0.224	0.5	1.5	.	8	.	(0.35)	1.8	250	30	2.5	120	219																					
JGb-2	27	.	0.51	.	0.0438	0.29	0.15	.	0.19	.	.	.	174	4.5	0.39	48.5	11.6																					
JGb-1 *	35.8	.	1.49	0.48	0.0327	0.18	0.29	.	0.48	.	0.16	0.13	635	10.4	1.06	109	32.8																					
CGL 013	39.66	.	(0.72)	.	0.0778	.	(0.13)	.	.	.	(0.05)	.	420	4.30	(0.39)	98.00	(12)																					
VS 2119-81	17	.	.	4.4	120	.	.	120	100																					
VS 2117-81	37	.	.	6.5	0.1040	960	.	2.6	136	.																					
GBW 07112	22.5	0.26	1.22	0.89	0.0612	.	0.20	0.010	.	0.07	0.09	.	768	4.9	0.36	118	29																					
CAN WMG-1A	21.33	14.1	2.211	(1.91)	0.00390	(0.355)	.	(1.19)	1.07	.	(0.192)	(0.65)	158	12.67	(1.220)	112	35.7																					

CRM GOLD ORE

ng/g (ppb) 1 kg units

Number Au

GLG914-4	369.36
GLG313-3	227.70
GLG912-5	224.34
GLG911-5	209.21
GLG914-3	205.83
GLG904-4	204.08
GLG914-5	195.97
GLG315-5	194.82
GLG313-4	183.83
GLG303-1	164.48
GLG304-1	151.64
GLG304-4	121.43
GLG310-3	119.30
GLG314-3	103.11
GLG305-1	101.57

GLG314-5	95.23
GLG913-5	84.83
GLG313-5	83.36
GLG907-5	81.81
GLG310-5	79.83
GLG908-4	66.63
GLG305-3	55.48
GLG908-1	52.65
GLG908-5	52.56
GLG312-3	48.55
GLG908-3	34.86
GLG910-3	32.02
GLG302-3	30.79
GLG313-1	30.63
GLG307-5	27.57

GLG910-2	24.31
GLG913-2	22.75
GLG904-2	21.55
GLG312-1	20.65
GLG901-1	18.99

GLG312-4	18.33
GLG302-2	16.67
GLG915-1	14.01
GLG913-1	11.13
GLG902-2	10.66

GLG901-2	9.92
GLG912-1	6.86
GLG910-4	6.36
GLG916-1	5.06
GLG911-4	4.65

GLG910-1	4.89
GLG907-1	4.18
GLG912-3	3.98
GLG307-2	3.83
GLG904-1	3.82

GLG911-3	3.74
GLG914-2	3.68
GLG314-1	3.63
GLG316-5	3.50
GLG916-2	3.48

GLG916-3	3.45
GLG911-1	3.35
GLG916-4	3.27
GLG302-4	3.23
GLG913-4	3.10

GLG314-2	2.98
GLG913-3	2.81
GLG312-2	2.78
GLG316-3	2.75
GLG910-5	2.58

GLG912-2	2.54
GLG316-4	2.52

CRM GOLD ORE

analysis listed in grams per Ton

Number Ag Au Units

NCS DC93008	63.1	20.9	500 g
NCS DC93006	43.4	57.2	1 kg
NCS DC93007	26.2	37.3	750 g
NCS DC93009	7.8	2.5	500 g

CRM GOLD ORE

analysis listed in mg/kg (ppm) except % which is mass 200 g units

Number Au Fire Au Aqua Ag As Co Cu Ni Pb S% Zn

GBMS911-4	6.78	6.73	1.79	36	54	900	32	35	0.79	115
GBMS304-4	5.67	5.29	3.4	535	.	9786	732	271	6.27	149
GBMS304-1	3.06	2.96	1.4	168	.	3156	380	197	1.33	120
GBMS911-2	2.88	2.82	1.24	62	78	1417	34	47	1.30	122
GBMS304-3	2.68	2.51	1.5	263	137	3637	376	159	2.35	143
GBMS911-3	1.33	1.31	0.17	13	31	7652	27	37	0.99	196
GBMS911-1	1.04	1.04	1.19	335	31	10028	23	5844	1.40	1221

Fire = Fire Assay, Aqua = Aqua Regia

CRM GOLD ASSAY PILLS

25 x 1g pressed powder

Number Au mg/kg (ppm)

GAP-06	2.2202
GAP-03	1.0000
GAP-05	0.5249
GAP-01	0.3237
GAP-04	0.2117
GAP-02	0.1025
GAP-07	0.0304

RM GOLD ORE

g/t = mg/kg = ppm 100 g or 1 kg

Number Au Pd* Pt*

CDN GS-50	50.5	.	.
CDN GS-40	39.95	.	.
CDN GS-22	22.94	.	.
CDN GS-20A	21.12	.	.
CDN GS-20B	20.23	.	.
CDN GS-14A	14.90	.	.
CDN GS-13A	13.20	.	.
CDN GS-12A	12.31	.	.
CDN GS-10D	9.50	.	.
CDN GS-9A	9.31	.	.
CDN GS-7F	6.90	.	.
CDN GS-4E	4.19	.	.
CDN GS-3K	3.19	.	.
CDN GS-3L	3.18	.	.
CDN GS-2P	1.99	.	.
CDN GS-P7H	0.799	.	.
CDN GS-P8C	0.784	.	.
CDN GS-P5C	0.571	.	.
CDN BL-10	<0.01	<0.01	<0.01

RM GOLD AND SILVER ORE

data in mg/kg (ppm) 100 g or 1 kg units

Number Au Ag

CDN GS-3M	3.10	95.4
CDN GS-2Q	2.37	73.2
CDN GS-1Q	1.24	40.7

RM GOLD AND SILVER ORE

analysis listed in mg/kg (ppm) 100 g or 1 kg

Number Ag Au Au

CDN GS-8C	.	8.59 FA/Inst	8.62 FA/Grav
CDN GS-5Q	60.3	5.59 FA/Inst	5.64 FA/Grav
CDN GS-5P	119	4.78 FA/Inst	4.80 FA/Grav
CDN GS-5L	.	4.68 FA/ICP	4.74 FA/Grav

CRM GOLD ORE

mg/kg (ppm) 1 kg units

Number Au Fire Au Aqua

G310-10	48.53	47.74 last
G917-1	48.52	47.79
G916-6	30.94	30.47
G312-10	24.94	24.67
G915-8	24.72	24.58
G916-5	19.92	19.63
G915-5	17.95	17.29
G914-9	16.77	16.62
G915-7	12.38	12.35
G301-9	10.47	.

G914-10	10.26	10.17
G311-9	10.01	7.45
G315-8	9.93	9.83
G915-9	9.82	9.83
G914-7	9.81	9.68

G915-3	9.39	9.22
G915-4	9.16	9.00
G306-3	8.66	8.60
G307-7	7.87	7.75
G311-10	7.32	5.54

G912-1	7.29	7.33
G913-10	7.09	7.10
G313-5	7.07	7.05
G313-7	6.93	6.97
G314-3	6.70	6.68

G316-8	6.11	6.06
G313-7	5.85	5.79
G312-9	5.84	5.69
G315-6	5.68	5.26
G315-1	5.64	5.38

G904-8	5.53	5.51
G312-4	5.30	4.98
G314-5	5.29	5.30
G915-2	4.98	4.96
G913-9	4.91	4.88

G913-8	4.87	4.93
G396-8	4.82	4.75
G316-10	4.65	4.56
G915-1	4.56	4.51
G916-7	4.51	4.48

G998-4	4.36	4.27
G912-6	4.08	4.05
G398-10	4.07	3.99
G397-6	3.95	3.82
G905-7	3.92	3.89

G913-5	3.70	3.21
G911-8	3.65	2.68
G307-1	3.37	3.35
G310-9	3.29	3.25 last
G900-7	3.22	3.19

G916-8	3.20	3.15
G914-6	3.21	3.16
G305-8	3.14	2.80
G916-9	3.13	2.88
G910-6	3.09	3.05

G398-6	2.94	2.86
G916-10	2.81	2.73
G914-1	2.57	2.55
G912-2	2.51	2.51
G308-3	2.50	2.47
G914-2	2.48	2.44

G906-2	2.46	2.40
G314-7	2.45	2.43
G303-4	2.43	2.45
G911-4	2.43	2.45
G313-8	2.43	2.41

G312-6	2.42	2.42
G913-2	2.40	2.42
G913-3	2.36	2.21
G913-7	2.31	2.26
G913-6	2.19	2.16

G912-3	2.09	2.10
G313-2	2.04	2.07
G313-4	2.00	2.00
G307-8	1.99	1.97
G314-6	1.98	1.98

G916-2	1.98	1.96
G315-3	1.97	1.97
G912-4	1.91	1.95
G316-9	1.75	1.71
G916-1	1.72	1.70

Number Au Fire Au Aqua

Number Au Fire Au Aqua

Number Au Fire Au Aqua

Number Au Fire Au Aqua

Number Au Fire Au Aqua

Number Au Fire Au Aqua

Number Au Fire Au Aqua

Number Au Fire Au Aqua

CRM GOLD AND SILVER ORE

analysis listed in mass % except * which is mg/kg																				For U, MM = /ICP and X = XRF					D = Demotu/Specific Gravity					100 g units				
Number	Au*	Ag*	Al ₂ O ₃	As	CaO	Cr ₂ O ₃	Cu	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	U M	U X	U ₃ O ₈	LOI	D													
AMIS 0429	22.93	.	.	.	0.48	(0.11)	.	4.97	0.54	.	(0.04)	.	.	1.57	87.70	.	0.0722	.	.	(1.87)	.													
AMIS 0218	7.35	9.1	0.0083	9.07	last	3.18												
AMIS 0401	6.54	.	6.67	.	15.10	(0.024)	.	27.00	1.60	3.60	3.85	(0.16)	.	8.85	29.63	0.40	.	.	.	(3.51)	3.38													
AMIS 0312	4.00	(5.8)	11.24	.	2.37	(0.03)	0.8104	6.55	3.74	0.69	0.060	1.55	.	2.58	68.18	0.24	.	.	.	(3.30)	2.84													
AMIS 0335	3.83	(1.3)	7.63	.	3.65	(0.03)	0.0110	17.72	3.15	2.27	0.07	1.36	.	3.09	56.85	(0.20)	.	.	.	(5.88)	2.96													
AMIS 0359	3.80	.	2.54	0.2334	1.82	(0.048)	(0.0105)	38.83	0.56	5.28	0.72	(0.089)	.	6.91	45.11	0.18	.	.	.	(4.15)	3.39													
AMIS 0333	3.73	3.1	7.39	.	2.88	(0.04)	0.0128	20.26	3.63	1.91	0.091	1.52	.	3.24	56.34	0.20	.	.	.	(3.88)	2.97													
AMIS 0360 *	2.94	.	5.94	0.7951	5.74	(0.11)	0.0577	18.04	0.95	3.47	0.39	0.29	.	6.46	48.05	0.30	.	.	.	(12.88)	3.05													
AMIS 0430	2.68	.	2.80	.	0.19	0.12	.	2.03	0.32	(0.11)	0.030	(0.06)	.	0.33	92.3	(0.14)	0.0113	.	.	(1.66)	2.71													
AMIS 0353	2.02	.	4.16	.	0.59	0.030	0.0055	2.65	1.77	0.55	0.22	0.18	.	(0.16)	87.88	0.16	.	.	.	1.43	2.68													
AMIS 0288	1.66	.	11.80	.	6.70	(0.02)	.	10.90	1.23	3.59	0.14	3.44	.	0.55	50.29	0.96	.	.	.	10.21	2.84													
AMIS 0213	1.38	.	13.17	(0.0288)	3.68	0.008	0.3295	2.45	2.06	0.84	(0.091)	4.30	.	0.48	67.57	0.26	.	.	.	4.73	2.75													
AMIS 0220	1.38	(0.06)	0.0164	23.25	2.01	.	(0.09)	.	.	4.45	53.72	0.20	.	.	.	(5.40)	3.07													
AMIS 0332	1.29	(1.4)	8.58	.	3.07	(0.04)	0.0232	17.62	3.50	1.95	0.09	(2.23)	.	1.72	58.08	0.22	.	.	.	(3.83)	2.93													
AMIS 0221	1.14	.	11.03	.	4.13	.	(0.0050)	12.58	2.93	2.56	.	.	.	1.84	56.40	0.28	2.88													
AMIS 0261	1.12	.	10.66	(0.0098)	7.55	(0.05)	0.0086	10.52	1.46	4.61	0.20	2.21	.	1.49	46.30	1.01	.	.	.	13.78	2.91													
AMIS 0310	1.03	(2)	12.25	.	2.22	0.30	0.1399	5.46	3.88	0.74	(0.065)	1.89	.	1.58	69.38	0.26	.	.	.	(2.67)	2.81													
AMIS 0309	0.96	(2.1)	12.37	.	2.13	(0.04)	0.1406	5.31	3.96	0.57	(0.06)	1.93	.	1.49	69.40	0.28	.	.	.	(2.74)	2.80													
AMIS 0337	0.66	.	12.81	.	7.85	1.12	.	7.66	3.34	5.01	0.24	1.05	.	0.38	55.11	0.81	.	.	.	(4.12)	2.88													
AMIS 0352	0.45	.	14.36	.	0.48	(0.02)	0.0138	8.17	7.75	0.94	0.15	0.55	.	0.56	62.13	1.00	.	.	.	3.34	2.70													
AMIS 0307	0.43	.	4.27	.	0.95	0.13	.	3.61	0.86	0.71	(0.05)	0.57	.	0.94	84.98	0.23	(0.0079)	0.0082	.	(3.19)	2.74													
AMIS 0351	(0.25)	.	13.65	.	5.10	(0.02)	0.0465	6.59	3.59	3.29	0.14	1.95	.	0.44	58.56	0.61	.	.	.	5.28	2.74													

* AMIS 0360 also contains Ni:(0.0358) and Zn:(0.1786)

CRM GOLD AND SILVER ORE

analysis listed in mg/kg (ppm) * and mass percent %						
Number	Ag*	Au*	As%	S%	Sb%	Units
NCS DC28104	62.2	63.4	.	.	.	250 g
USZ 29-2000	6.05	42.26	.	.	.	100 or 200 g
VS 5938-91	6.5	36	8.45	28.73	0.021	100 g
VS 5937-91	6.4	33	7.78	25.83	0.019	100 g
VS 2739-83	5.7	34	8.0	26.0	0.020	100 g
NCS DC28107	20.4	20.0	.	.	.	250 g
NCS DC29103	18.0	20.0	.	.	.	500 g
CAN MA-1b	(4)	17.0	.	.	.	200 g
VS 5936-91	3.5	20	4.72	15.26	0.012	100 g
VS 5935-91	23	13	.	15.10	0.044	100 g
NCS DC28106	11.0	11.0	.	.	.	500 g
USZ 39-2005	49.33	10.92	.	.	.	250 g
VS 5934-91	1.8	8.9	2.11	6.77	0.0057	100 g
CAN MA-3a	(2.4)	8.56	.	.	.	200 g
USZ 40-2005	27.06	7.38	.	.	.	100 or 250 g
USZ 30-2000	1.18	5.92	.	.	.	250 g
NCS DC28105	5.8	5.0	.	.	.	500 g
VS 5933-91	1.1	4.6	1.08	3.35	0.0039	100 g
NCS DC29102	37.4	4.30	.	.	.	500 g
VS 8815-2006	0.75	4.25	1.000	3.27	0.00260	100 g
USZ 31-2000	1.07	3.28	.	.	.	250 g
CAN MA-2c	(0.51)	3.02	.	.	.	400 g
VS 5932-91	0.9	3.0	0.54	1.77	0.0021	100 g
NCS DC28102	2.2	2.5	.	.	.	500 g
VS 8816-2006	0.360	2.13	0.500	1.64	0.00135	100 g
NCS DC28103	3.1	1.8	.	.	.	500 g
NCS DC28101	4.2	1.7	.	.	.	500 g
USZ 21-98	.	1.06	.	.	.	250 g
VS 2740-83	0.31	0.9	0.17	0.38	0.0019	100 g
NCS DC29101	.	0.64	.	.	.	500 g
VS 5940-91	0.9	0.55	0.063	0.34	0.0075	100 g
VS 5939-91	0.7	0.37	.	0.24	0.0025	100 g
KZ 63-86	.	0.023	.	.	.	100 g
KZ 64-86	.	0.0076	.	.	.	100 g
KZ 65-86	.	0.0067	.	.	.	100 g
NCS DC90006	732	50 g
NCS DC90005	559	50 g
NCS DC90004	446	50 g
NCS DC90003	298	50 g
NCS DC29106	199	50 g
NCS DC29105	138.1	50 g
NCS DC90002	112	50 g
NCS DC29104	50.3	50 g
NCS DC90001	46.9	50 g

CRM GOLD AND SILVER ORE - minesite carbon material

data listed in mg/kg (ppm) 10 g units		
Number	Au	Ag
GLC302-3	7467	1248 (last of stock)
GLC615-7	6815	4835
GLC615-6	4442	1373
GLC615-5	3629	757
GLC917-2	2460	175
GLC917-1	2361	154
GLC616-2	2311	1050
GLC915-1	2077	416
GLC314-1	2031	947 (last of stock)
GLC915-3	1791	548
GLC915-3	1472	114
GLC316-2	1211	527
GLC916-2	1174	209
GLC616-1	1330	601
GLC315-4	974	360
GBC916-1	933	265
GLC915-2	829	27
GBC917-4	811	229
GLC315-2	790	530
GBC917-2	770	219
GBC917-1	713	207
GBC917-3	628	195
GBC913-2	508	214
GBC911-3	470	596 (last of stock)
GBC615-2	467	(57)
GBC916-2	465	102
GBC616-2	454	233
GBC12	448	.
GBC312-3	360	491
GBC315-2	350	(70)
GBC316-2	319	508
GBC316-1	318	191
GBC314-4	306	(181)
GBC912-2	301	528
GBC902-3	285	83 (last of stock)
GBC916-3	218	493
GBC316-4	109	74
GBC314-2	96	(72)
GBC915-3	76	58
GBC314-1	51	38
GBC316-3	21	21
GBC616-1	12	46
GBC915-2	6	21
Number	Au	Ag

CRM GOLD AND SILVER ORE - CONTINUED ON THE NEXT PAGES

analysis listed in mass % except * which is mg/kg														OREAS samples list multiple methods, more information upon request
Number	Au*	Ag*	As	Ba	Cu	Fe	Fe ₂ O ₃	Pb	S	SO ₃	Sb	Zn	LOI	
CAN DS-1	32.59	0.47	0.6960	0.0221	0.00271	(3.0)	.	0.00138	(2.609)	.	(0.0107)	0.0206	(13)	
USZ 38-2005	31.28	.	.	0.02	0.43	.	14.71	0.006529	2.59	
KZ 3594-86	12.1	107	0.18	10.7	4.16	.	.	0.34	.	.	.	2.25	.	
OREAS 12a	11.79	(3)	(0.6795)	(0.0646)	(0.0262)	.	(20.9)	(0.0015)	(5.34)	.	(0.00152)	(0.0129)	(8.91)	
OREAS 62d	10.50	8.37	(0.0028)	(0.0210)	(0.0042)	.	(2.88)	(0.0015)	(0.47)	(1.49)	(0.00019)	(0.0029)	(11.24)	
USZ 20-98	10.05	3.05	1.92	0.95	
KZ 3597-86	8.8	.	3.96	
KZ 16-2004	8.57	1.35	.	.	0.02	
KZ 3596-86	7.6	155.4	1.21	25.0	13.1	.	.	0.56	.	.	.	1.22	.	
KZ 62-86	5.7	2.3	
OREAS 19a	5.49	(1.5)	(0.3410)	(0.0469)	(0.0163)	.	(15.9)	(0.00105)	(2.54)	.	(0.00075)	(0.0128)	(4.70)	
KZ 61-86	4.4	14.7	0.32	.	0.00044	0.076	.	.	
OREAS 61e 4	4.43	5.27	(0.00173)	(0.0272)	(0.0060)	(2.66)	.	(0.00133)	0.790	.	(<0.0005)	(0.0051)	(7.74)	
OREAS 61e A	4.51	5.37	(0.00159)	(0.00344)	(0.0058)	(2.37)	.	(0.00120)	(0.824)	.	(<0.0002)	(0.00469)	.	
OREAS 61e F	.	.	.	(0.0277)	.	(2.56)	.	.	(0.760)	
KZ 3593-86	3.2	20.9	0.08	6.8	0.99	.	.	0.27	.	.	.	4.63	.	
OREAS 17c	3.04	(0.5)	(0.2055)	(0.0398)	(0.0130)	.	(14.1)	(0.00105)	(1.59)	.	(0.00045)	(0.0139)	(2.72)	
OREAS 23a	3	0.1	0.0037	0.1092	0.00421	.	.	0.00213	.	.	0.000045	0.0069	.	
OREAS 7Ca	2.54	.	(0.1917)	(0.0683)	.	.	(4.06)	.	.	(0.04)	(0.0161)	(0.0030)	.	
UNS AuM	2.5	.	0.08765	BaO:0.066	0.00359	.	5.55	
OREAS 60C	2.47	.	.	(0.0355)	.	(3.13)	.	.	(0.830)	.	.	.	(7.38)	
OREAS 60C 4	.	4.87	(0.00204)	(0.0342)	(0.0073)	(3.24)	.	(0.00187)	0.860	.	(<0.0005)	(0.0090)	.	
OREAS 60C A	2.45	4.81	(0.00189)	(0.00400)	(0.0073)	(2.97)	.	(0.00187)	(0.908)	.	(<0.0002)	(0.0085)	.	
KZ 3595-86	2.1	36.7	0.12	2.40	2.15	.	.	0.13	.	.	.	0.81	.	
OREAS 16a	1.81	(0.5)	(0.0625)	(0.0365)	(0.0084)	.	(13.9)	(0.0006)	(1.24)	.	(0.0001)	(0.0136)	(1.22)	
OREAS 15d	1.559	(0.5)	(0.2445)	(0.0252)	(0.0068)	.	(12.17)	(0.0012)	(0.62)	.	(0.00023)	(0.0107)	(1.28)	
KZ 15-2004	1.48	17.4	.	.	0.02	.	.	0.18	.	.	.	0.055	.	
OREAS 66a	1.237	18.9	(0.0282)	(0.08085)	0.0121	.	(6.745)	(0.0260)	(1.075)	.	(0.0064)	(0.0091)	(4.16)	
USZ 41-2006	0.91	.	.	0.0249	0.75	.	.	0.0027	.	3.87	.	0.0136	5.43	
CAN CH-4	0.88	2.1	0.00088	(0.0425)	0.20	5.42	.	.	0.63	.	0.77	0.020	(0.9)	
USZ 34-2002	0.79	1.7	0.12	.	0.001484	2.18T	.	0.002	.	.	0.14	0.0025	2.84	
US DCPM-1	0.73	.	0.0180	.	.	.	1.92	.	.	.	0.0014	.	.	
USZ 35-2002	0.57	1.25	
KZ 17-2004	0.49	1.78	.	.	1.59	3.91	.	.	1.73	
OREAS 15f	0.334	(<0.5)	(0.0127)	(0.0328)	(0.0061)	.	(12)	(0.0005)	(0.24)	.	(0.00004)	(0.0113)	(0.44)	
KZ 6585-93	0.28	11.6	0.075	0.064	.	.	.	0.12	.	.	.	0.60	.	
CAN GTS-2a	0.272	(0.64)	0.0124	0.0186	0.00886	7.56	.	.	0.348	.	(0.000133)	0.0208	(9.87)	
OREAS H5	0.047	
OREAS H5 A	0.057	1.92	0.0000008	(0.0052)	0.0099	0.813	.	0.00361	(0.017)	.	(0.000485)	0.000658	.	
OREAS H5 N	(0.053)	.	(0.0000014)	(0.0173)	.	(1.24)	(0.000510)	(0.00460)	.	
OREAS 24b	<0.003	.	(0.00100)	BaO:0.0819	.	.	6.35	.	0.190	.	.	(0.0113)	2.46	
OREAS 24b 4	.	(0.127)	(0.000835)	0.0716	0.00380	4.39	.	0.00231	0.198	.	0.000100	0.0105	.	
OREAS 24b A	(0.002)	(0.058)	0.000796	0.0146	0.00364	3.93	.	0.000923	0.200	.	(0.000048)	0.0093	.	
OREAS 24b F	.	(2.17)	(0.000974)	0.0739	(0.00351)	4.45	.	(0.00229)	0.203	.	(0.000133)	(0.0103)	.	
OREAS 25a	<0.002	.	.	BaO:(0.0151)	.	.	9.77	.	0.044	.	.	(0.00467)	11.70	
OREAS 25a 4	.	(0.168)	(0.000994)	0.0147	0.00339	6.60	.	0.00252	0.051	.	0.000067	0.00444	.	
OREAS 25a A	(0.001)	(0.035)	(0.000284)	0.0056	0.00249	5.99	.	0.00210	(0.050)	.	(0.000018)	0.00301	.	
OREAS 25a F	.	(0.570)	(0.000983)	0.0151	(0.00391)	6.72	.	(0.00244)	(0.046)	.	(0.000102)	0.00468	.	
OREAS 24c	<0.001	<0.2	<0.00002	0.0269	0.00486	7.62	.	0.000290	(<0.01)	.	<0.00001	0.0108	.	
OREAS 22d	<0.001	<0.1	<0.0001	0.000617	0.000923	0.468	.	0.000072	(<0.01)	.	0.000021	0.000670	.	
Number	Au*	Ag*	As	Ba	Cu	Fe	Fe ₂ O ₃	Pb	S	SO ₃	Sb	Zn	LOI	

CRM GOLD AND SILVER ORE - CONTINUED FROM THE PREVIOUS AND ON TO THE NEXT PAGE

analysis listed in mass % except * which is mg/kg																		OREAS samples list multiple methods, more information upon request	
Number	Al	Al ₂ O ₃	C	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	Si	SiO ₂	Ti	TiO ₂
CAN DS-1	4.48	.	(3.126)	(6.248)	.	(1.1)	.	2.76	.	0.0437	.	.	.	0.0340	.	(25.68)	.	.	.
USZ 38-2005	.	2.03	.	.	0.56	.	0.64	.	1.01	.	0.03	.	0.17	.	0.05	.	77.37	.	0.15
KZ 3594-86
OREAS 12a	.	(9.3)	(1.51)	.	(7.95)	.	(0.64)	.	(4.22)	.	(0.78)	.	(0.89)	.	(0.63)	.	(43.0)	.	(0.56)
OREAS 62d	.	(6.75)	(2.61)	.	(12.27)	.	(1.97)	.	(0.95)	.	(0.08)	.	(0.36)	.	(0.102)	.	(62.48)	.	(0.29)
USZ 20-98	.	1.70	.	.	0.77	.	0.37	.	.	.	0.025	.	0.07	.	0.037	.	92.57	.	0.08
KZ 3597-86
KZ 16-2004
KZ 3596-86
KZ 62-86
OREAS 19a	.	(11.9)	(0.81)	.	(8.29)	.	(0.68)	.	(5.94)	.	(0.45)	.	(1.96)	.	(0.47)	.	(47.4)	.	(1.17)
KZ 61-86
OREAS 61e 4	(4.50)	.	.	(4.93)	.	(2.00)	.	(0.818)	.	(0.061)	.	(0.656)	.	(0.051)	.	.	.	(0.220)	.
OREAS 61e A	(1.25)	.	.	(4.61)	.	(0.203)	.	(0.723)	.	(0.059)	.	(0.064)	.	(0.048)	.	.	.	(0.042)	.
OREAS 61e F	(4.45)	.	(1.61)	(4.88)	.	(1.99)	.	(0.820)	.	(0.062)	.	(0.705)	.	(0.048)	.	(31.90)	.	(0.231)	.
KZ 3593-86
OREAS 17c	.	(12.8)	(0.56)	.	(8.40)	.	(0.71)	.	(6.63)	.	(0.33)	.	(2.40)	.	(0.41)	.	(49.1)	.	(1.41)
OREAS 23a
OREAS 7Ca	.	(15.2)	.	.	<0.01	.	(4.23)	.	(0.72)	.	<0.01	.	<0.05	.	(0.08)	.	(71.1)	.	(0.68)
UNS AuM	.	14.06	.	.	4.09	.	1.92	.	1.81	.	0.082	.	3.08	.	.	.	66.15	.	0.39
OREAS 60C	(5.45)	.	(1.27)	(3.92)	.	(2.33)	.	(0.962)	.	(0.077)	.	(0.972)	.	(0.063)	.	(30.92)	.	(0.288)	.
OREAS 60C 4	(5.45)	.	.	(4.00)	.	(2.31)	.	(0.957)	.	(0.072)	.	(0.892)	.	(0.065)	.	.	.	(0.274)	.
OREAS 60C A	(1.71)	.	.	(3.73)	.	(0.271)	.	(0.873)	.	(0.070)	.	(0.089)	.	(0.062)	.	.	.	(0.063)	.
KZ 3595-86
OREAS 16a	.	(13.15)	(0.28)	.	(8.09)	.	(0.817)	.	(6.79)	.	(0.26)	.	(2.81)	.	(0.4)	.	(49.88)	.	(1.67)
OREAS 15d	.	(13.25)	(0.20)	.	(7.95)	.	(0.743)	.	(6.47)	.	(0.188)	.	(2.74)	.	(0.326)	.	(52.86)	.	(1.61)
KZ 15-2004
OREAS 66a	.	(8.49)	(0.03)	.	(2.32)	.	(0.355)	.	(1.82)	.	(0.04)	.	(0.85)	.	(0.1635)	.	(73.6)	.	(0.83)
USZ 41-2006	.	14.58	.	.	3.14	.	2.81	.	5.52	.	0.12	.	2.36	.	0.27	.	52.09	.	0.93
CAN CH-4	7.73	.	0.12	1.96	.	1.81	.	1.43	.	0.043	.	3.26	.	0.061	.	.	63.10	0.31	.
USZ 34-2002	.	4.79	.	.	2.53	.	1.48	.	0.37	.	0.017	.	0.055	.	0.125	.	84.70	.	0.17
US DGPM-1	.	9.56	.	.	(0.22)	.	2.74	.	(0.56)	79.82	.	.
USZ 35-2002
KZ 17-2004
OREAS 15f	.	(14.2)	(0.16)	.	(8.59)	.	(0.82)	.	(7.13)	.	(0.18)	.	(3.02)	.	(0.336)	.	(51.0)	.	(1.78)
KZ 6585-93
CAN GTS-2a	6.96	.	2.011	4.01	.	2.021	.	2.412	.	0.1510	.	0.617	.	0.0892	.	23.65	.	(0.5*)	.
OREAS H5
OREAS H5 A	(2.31)	.	.	(0.014)	.	(0.059)	.	(0.073)	.	0.007	.	(0.135)	.	0.010	.	.	.	(0.040)	.
OREAS H5 N	(0.500)	(0.215)
OREAS 24b	.	15.15	0.189	.	1.47	.	3.39	.	2.75	.	0.059	.	1.15	.	0.161	.	66.0	.	0.798
OREAS 24b 4	8.02	.	.	1.08	.	2.81	.	1.65	.	0.044	.	0.846	.	0.069	.	.	.	0.468	.
OREAS 24b A	3.15	.	.	0.461	.	1.17	.	1.36	.	0.035	.	0.108	.	(0.062)	.	.	.	0.198	.
OREAS 24b F	7.81	.	.	1.06	.	2.74	.	1.62	.	0.046	.	0.824	.	(0.073)	.	31.12	.	0.481	.
OREAS 25a	.	18.24	1.56	.	0.438	.	0.599	.	(0.579)	.	0.063	.	0.191	.	0.117	.	56.7	.	1.93
OREAS 25a 4	8.87	.	.	0.309	.	0.482	.	0.327	.	0.047	.	0.134	.	0.048	.	.	.	0.977	.
OREAS 25a A	5.85	.	.	0.150	.	0.131	.	(0.193)	.	0.042	.	(0.040)	.	0.037	.	.	.	(0.036)	.
OREAS 25a F	9.25	.	.	0.302	.	0.493	.	0.324	.	0.049	.	(0.126)	.	0.049	.	25.85	.	1.14	.
OREAS 24c	7.45	.	.	5.86	.	0.735	.	3.93	.	0.108	.	2.42	.	0.156	.	.	.	1.06	.
OREAS 22d	0.132	.	.	(0.010)	.	(0.008)	.	(0.009)	.	0.011	.	(0.009)	.	(0.001)	.	.	.	0.021	.

Number	Al	Al ₂ O ₃	C	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	Si	SiO ₂	Ti	TiO ₂
--------	----	--------------------------------	---	----	-----	---	------------------	----	-----	----	-----	----	-------------------	---	-------------------------------	----	------------------	----	------------------

CRM GOLD AND SILVER ORE - CONTINUED FROM THE PREVIOUS AND ON TO THE NEXT PAGE

analysis listed in mg/kg except % which is mass %

OREAS samples list multiple methods, more information upon request

Number	B	Be	Bi	Cd	Ce	Co	Cr	Cr ₂ O ₃	Cs	Dy	Er	Eu	Ga	Gd	Ge	Hf	Hg
CAN DS-1	.	(0.819)	(0.1)	(0.98)	(40)	9.5	(59)	.	(7)	.	.	(1)	(10)	.	.	(4)	82
USZ 38-2005
KZ 3594-86	.	.	.	75
OREAS 12a	.	(0.8)	(0.3)	.	(21.7)	(31)	.	.	(4)	(4)	(2.0)	(1.1)	(13.3)	(4.4)	.	(1)	.
OREAS 62d	.	(0.5)	.	.	(16.2)	(6.0)	.	.	(5.2)	(1.2)	(0.7)	(0.5)	(7.1)	(1.4)	.	(1.0)	.
USZ 20-98
KZ 3597-86	1.08%	0.17%
KZ 16-2004
KZ 3596-86	.	.	.	52.5
KZ 62-86
OREAS 19a	.	(1.0)	(0.2)	.	(29.6)	(40.5)	.	.	(2)	(4)	(2.1)	(1.5)	(17)	(4.8)	.	(2.5)	.
KZ 61-86
OREAS 61e 4	.	(0.89)	(<2)	(<0.5)	.	(9.29)	(24.4)	(10.0)
OREAS 61e A	(<10)	(0.58)	(<2)	(1.15)	.	(8.83)	(21.6)	(<10)	.	.	.	(0.70)
OREAS 61e F	(18.7)	.	(<70)	.	(5.58)	(1.48)	(0.89)	(0.58)	(9.75)	(1.74)	.	(1.5)	.
KZ 3593-86	.	.	.	162.8
OREAS 17c	.	(1.0)	(0.1)	.	(32.7)	(44)	.	.	(2)	(5)	(2.3)	(1.6)	(18.5)	(5)	.	(3)	.
OREAS 23a	.	.	0.15	0.15	.	14.8
OREAS 7Ca	(90)	.	(502)	.	(10)	.	.	(1.4)	.	.	.	(4.4)	.
UNS AuM	47	12.9
OREAS 60C	(24.8)	.	(<70)	.	(6.36)	(1.93)	(1.13)	(0.73)	(12.0)	(2.25)	.	(2.00)	.
OREAS 60C 4	.	(0.92)	(<2)	(0.39)	.	(10.8)	(24.3)	(10.0)
OREAS 60C A	(10.0)	(0.60)	(<2)	(1.33)	.	(10.9)	(24.0)	(10.0)	.	.	.	(0.65)
KZ 3595-86	.	.	.	52.3
OREAS 16a	.	(0.7)	.	.	(36.4)	(44)	.	.	(1.6)	(4.6)	(2.20)	(1.72)	(18.1)	(5.2)	.	(3.6)	.
OREAS 15d	.	(0.9)	(0.4)	.	(34.1)	(43)	.	.	(0.8)	(4.3)	(2.1)	(1.6)	(17.9)	(4.9)	.	(3.2)	.
KZ 15-2004
OREAS 66a	.	(0.6)	(10.2)	(1)	(33.6)	(18)	.	.	(0.5)	(2.15)	(1.23)	(0.98)	(17.4)	(2.9)	.	(1.9)	.
USZ 41-2006	24.3	99.3
CAN CH-4	.	.	.	1.14	.	26	114
USZ 34-2002
US DGPm-1
USZ 35-2002
KZ 17-2004
OREAS 15f	.	(1.3)	.	.	(38.8)	(47)	.	.	(1.1)	(5.18)	(2.48)	(1.98)	(18.8)	(5.9)	.	(4.5)	.
KZ 6585-93	.	.	.	96
CAN GTS-2a	.	.	.	(0.58)	.	22.1	(270)
OREAS H5
OREAS H5 A	(23.0)	(<1)	5.44	1.28	.	3.68	31.1	(11.4)	.	(<0.1)	.	(0.14)
OREAS H5 N	.	.	Br: (4.99)	.	(76)	(4.64)	(108)	.	(1.94)	.	.	(0.93)	.	.	.	(57)	(<1)
OREAS 24b	(28.3)	.	201
OREAS 24b 4	.	2.92	0.68	(0.049)	84	16.9	118	.	10.7	(4.47)	(2.54)	(1.36)	20.1	(6.02)	(0.83)	3.90	.
OREAS 24b A	(6.23)	(1.65)	0.73	(0.046)	(61)	15.7	106	.	9.15	(2.65)	(1.21)	(0.66)	10.8	(3.96)	(0.26)	(0.52)	.
OREAS 24b F	(69)	2.95	(1.03)	.	86	16.9	142	.	10.5	5.83	3.41	1.39	20.2	6.27	(1.64)	6.15	.
OREAS 25a	(10.0)	.	(167)
OREAS 25a 4	.	1.02	0.35	(0.041)	48.9	8.20	115	.	6.46	(2.67)	(1.50)	(0.64)	25.9	(2.91)	(0.22)	4.53	.
OREAS 25a A	(5.92)	(0.65)	0.30	(0.041)	33.1	5.72	73	.	4.45	(1.15)	(0.50)	(0.43)	20.6	(1.74)	(0.13)	(0.47)	(0.053)
OREAS 25a F	(39.2)	(0.94)	(0.40)	.	51	8.05	125	.	6.36	4.31	2.76	0.80	25.4	3.79	(2.02)	11.1	.
OREAS 24c	.	1.05	<0.1	<0.1	(40.2)	42.7	193	.	(0.80)	(4.82)	(2.35)	(1.94)	(20.7)	(5.95)	(0.43)	3.75	.
OREAS 22d	.	(0.066)	<0.1	<0.1	(2.43)	0.85	(11.9)	.	(0.10)	(0.15)	(<0.1)	(<0.05)	(0.26)	(0.20)	(0.065)	0.22	.

Number	B	Be	Bi	Cd	Ce	Co	Cr	Cr ₂ O ₃	Cs	Dy	Er	Eu	Ga	Gd	Ge	Hf	Hg
--------	---	----	----	----	----	----	----	--------------------------------	----	----	----	----	----	----	----	----	----

CRM GOLD AND SILVER ORE - CONTINUED FROM THE PREVIOUS AND ON TO THE NEXT PAGE

analysis listed in mg/kg except % which is mass %																	OREAS samples list multiple methods, more information upon request
Number	Ho	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pd	Pr	Pt	Rb	Re	Sc	Se	Sm
CAN DS-1	.	(0.5)	(20)	(20)	48.7
USZ 38-2005	0.11%	.	.	28.27
KZ 3594-86	.	9.7	50.9	.
OREAS 12a	(0.73)	(0.05)	(17.7)	(19.5)	(0.28)	(5.5)	(3.25)	(19.5)	(71.5)	.	(4.56)	.	(20.5)	.	(20)	.	(4.18)
OREAS 62d	(0.24)	(0.02)	(7.6)	(39)	(0.1)	(6.7)	(1.2)	(7.8)	(7.0)	.	(1.9)	.	(72)	.	(7.0)	.	(1.7)
USZ 20-98
KZ 3597-86
KZ 16-2004
KZ 3596-86	.	13.1
KZ 62-86
OREAS 19a	(0.8)	(0.05)	(17.7)	(13.0)	(0.27)	(4.0)	(10)	(19.8)	(106)	.	(4.78)	.	(19.5)	.	(20)	.	(4.68)
KZ 61-86
OREAS 61e 4	.	.	(10.0)	(50)	.	(5.67)	.	.	(8.37)	.	.	(0.004)	.	.	(10.0)	.	.
OREAS 61e A	.	.	(15.0)	.	.	(5.67)	.	.	(9.14)	(6.00)	(0.60)	.
OREAS 61e F	(0.33)	.	(8.95)	.	(0.14)	.	(1.80)	(9.75)	.	.	(2.33)	.	(91)	.	.	.	(2.03)
KZ 3593-86	.	5.5	20	.
OREAS 17c	(0.82)	(0.05)	(18.1)	(10.3)	(0.26)	(4.3)	(13)	(19.7)	(136)	.	(4.84)	.	(21.5)	.	(20.5)	.	(4.83)
OREAS 23a	9.6	.	.	40.5
OREAS 7Ca	.	.	(50)	(168)	.	(14)	.	(10)
UNS AuM
OREAS 60C	(0.43)	.	(12.0)	.	(0.17)	.	(2.35)	(12.8)	.	(<0.005)	(3.06)	(0.004)	(103)	.	.	.	(2.67)
OREAS 60C 4	.	.	(10.0)	(45.0)	.	(6.70)	.	.	(9.71)	(12.6)	.	.
OREAS 60C A	.	.	(13.3)	.	.	(6.78)	.	.	(10.6)	(8.00)	(0.75)	.
KZ 3595-86	.	2.5	58.2	.
OREAS 16a	(0.86)	(0.05)	(19.3)	(8.0)	(0.25)	(3.2)	(18.8)	(20.6)	(157)	.	(5.19)	.	(26.1)	.	(18.3)	.	(5.2)
OREAS 15d	(0.81)	(0.06)	(16.9)	(8.3)	(0.23)	(2)	(17.8)	(18.2)	(147)	.	(4.29)	.	(21.1)	.	(21)	.	(4.7)
KZ 15-2004
OREAS 66a	(0.4)	(0.48)	(17.6)	(14.8)	(0.21)	(5.5)	(6.8)	(16.0)	(59)	.	(4)	.	(8)	.	(9)	.	(3.35)
USZ 41-2006	51.8	.	.	25.4
CAN CH-4	51
USZ 34-2002	2.1	.
US DGPM-1
USZ 35-2002
KZ 17-2004
OREAS 15F	(0.91)	(0.06)	(17.9)	(8.8)	(0.24)	(4.5)	(20.8)	(21.6)	(157)	.	(4.82)	.	(22.4)	.	(18.5)	.	(5.28)
KZ 6585-93
CAN GTS-2a	77.1
OREAS H5
OREAS H5 A	.	.	(27.5)	(2.00)	.	7.22	(0.75)	.	11.9	(2.50)	(1.86)	.
OREAS H5 N	.	Ir: (<0.005)	(52)	.	(0.69)	(13.7)	.	(32.4)	(28.1)	.	.	.	(58)	.	(9.11)	(12.4)	(5.28)
OREAS 24b	(59)	<0.001	.	<0.001
OREAS 24b 4	(0.80)	(0.077)	42.4	52	(0.32)	4.03	14.6	(36.2)	60	.	(9.86)	.	164	(0.002)	15.3	(0.66)	(7.06)
OREAS 24b A	(0.46)	(0.048)	(29.2)	45.6	(0.20)	3.86	(0.31)	(24.6)	57	(<0.01)	(6.87)	(0.001)	114	(<0.001)	9.51	(0.42)	(4.68)
OREAS 24b F	1.17	.	44.0	52	0.49	(4.91)	16.0	38.7	61	.	10.2	.	161	(<0.1)	14.1	.	7.17
OREAS 25a	(31.2)	<0.001	.	<0.001
OREAS 25a 4	(0.46)	(0.091)	21.8	36.7	(0.23)	2.55	22.4	(17.0)	45.8	.	(4.71)	.	61	.	13.7	(2.86)	(3.41)
OREAS 25a A	(0.20)	(0.081)	(13.0)	(23.7)	(0.057)	(1.36)	(0.52)	(11.7)	26.9	(<0.01)	(3.35)	(0.004)	(31.4)	(<0.05)	8.64	(0.87)	(2.26)
OREAS 25a F	0.92	.	23.3	(35.1)	0.45	(2.99)	26.5	20.0	(55)	.	5.33	.	60	(<0.1)	13.5	.	3.90
OREAS 24c	(0.90)	(0.056)	(19.7)	8.32	(0.27)	2.49	23.8	(20.7)	138	(<0.005)	(5.28)	(<0.005)	21.9	(<0.002)	21.6	(1.00)	(5.55)
OREAS 22d	(<0.05)	(<0.005)	(1.20)	14.2	(0.013)	2.36	0.88	(1.03)	4.38	(<0.005)	(0.32)	(<0.005)	0.54	(<0.002)	(0.20)	(<1)	(0.22)

Number	Ho	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pd	Pr	Pt	Rb	Re	Sc	Se	Sm
--------	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----

CRM GOLD AND SILVER ORE - CONTINUED FROM THE PREVIOUS PAGES

analysis listed in mg/kg except % which is mass %													OREAS samples list multiple methods, more information upon request		
Number	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	W	Y	Yb	Zr	Units	Other
CAN DS-1	20	400 g	
USZ 38-2005	.	88.71	0.01%	.	.	.	250 g	
KZ 3594-86	210.4	100 g	
OREAS 12a	(1)	(136)	(0.3)	(0.64)	(0.4)	(4.4)	.	.	(1.85)	(6.5)	(20.2)	(1.88)	(40.5)	60 g	
OREAS 62d	.	(217)	.	(0.2)	(3.5)	(1.5)	.	.	(0.4)	(6.7)	(6.5)	(0.7)	(34)	60 g	
USZ 20-98	250 g	
KZ 3597-86	100 g	
KZ 16-2004	100 g	
KZ 3596-86	100 g	
KZ 62-86	100 g	
OREAS 19a	(1)	(279)	(0.65)	(0.7)	(0.2)	(3.7)	.	.	(1.3)	(3.5)	(19.9)	(1.75)	(99)	60 g	
KZ 61-86	100 g	
OREAS 61e 4	.	(245)	.	.	.	(<20)	(<10)	.	(<10)	(<10)	.	.	.	Au/Pd/Pt FA, others 4-acid	
OREAS 61e A	.	(113)	.	.	(2.21)	(<20)	(<10)	.	(<10)	(<10)	.	.	.	60 or 500g, Aqua Regia	
OREAS 61e F	(<1)	(245)	(0.10)	(0.27)	.	(2.31)	(0.85)	(0.14)	(0.61)	(3)	(8.70)	(0.83)	(54)	Borate Fusion, C/S combust	
KZ 3593-86	33.3	100 g	last of stock
OREAS 17c	(1)	(333)	(0.85)	(0.76)	.	(3.5)	.	.	(1.05)	(3.8)	(20.5)	(1.8)	(123)	60 g	
OREAS 23a	3.1	20.9	.	.	6.2	3.7	.	.	.	10 g or 60 g, GRANITE	
OREAS 7Ca	(16)	.	.	.	(18)	.	(2.8)	.	chips 500g Br:(5ppm) H ₂ O:(3.44+)	
UNS AuM	.	187.7	14.2	.	.	200 g	
OREAS 60C	(<1)	(284)	(0.10)	(0.33)	.	(3.04)	(0.95)	(0.17)	(0.79)	(3.00)	(11.1)	(1.07)	(70)	60/500g Au Pd Pt Flame V:(0.0120%)	
OREAS 60C 4	.	(282)	.	.	.	(<20)	(<10)	.	(<10)	(<10)	.	.	.	Four acid digestion V:(0.0104%)	
OREAS 60C A	.	(122)	.	.	(2.11)	(<20)	(<10)	.	(<10)	(<10)	.	.	.	Aqua regia V:(0.0069%)	
KZ 3595-86	72.6	100 g	
OREAS 16a	(3)	(369)	(1.1)	(0.8)	.	(3.2)	.	.	(0.9)	(1)	(22.8)	(1.82)	(161)	60 g	
OREAS 15d	(1)	(357)	(1)	(0.75)	(0.3)	(2.9)	.	.	(0.8)	(1.5)	(20.2)	(1.73)	(120)	60 g	
KZ 15-2004	100 g	
OREAS 66a	(3.50)	(488)	(0.4)	(0.40)	(9.6)	(4.1)	.	.	(1.4)	(10.5)	(10.3)	(1.3)	(75)	60 g	
USZ 41-2006	.	259	78.3	100 or 250 g	
CAN CH-4	.	(209)	200 g	
USZ 34-2002	250 g	H ₂ O: 0.10-
US DCPM-1	(76)	.	.	.	200 g	
USZ 35-2002	250 g	
KZ 17-2004	100 g	
OREAS 15f	(2)	(382)	(1.1)	(0.88)	.	(3.05)	.	.	(0.9)	(0.5)	(23.2)	(1.9)	(166)	60 g	
KZ 6585-93	100 g	
CAN GTS-2a	.	92.8	.	.	.	1.244	350 g	
OREAS H5	60 g	fire assay
OREAS H5 A (<10)	.	(6.89)	(<10)	.	(2.37)	(19.1)	(0.71)	.	.	(<5)	(5.00)	.	(47.8)	Aqua regia V: 0.00350%	
OREAS H5 N (<100)	.	.	(2.83)	(0.72)	.	(29.0)	.	.	(7.60)	(8.35)	.	(4.33)	(2085)	Neutron activation analysis	
OREAS 24b	.	(134)	10 g 60 g or 1 kg	Cl:(<10ppm)
OREAS 24b 4	4.25	124	1.23	(0.87)	.	16.4	0.86	(0.31)	3.06	3.64	19.9	(2.17)	134	" 4 acid digestion, GRANODIORITE	
OREAS 24b A	2.26	(29.0)	.	(0.54)	.	14.3	0.66	(0.17)	1.74	(1.19)	12.3	(1.15)	24.5	" aqua regia	
OREAS 24b F	4.65	125	1.32	0.98	.	16.5	0.91	0.50	3.31	4.13	32.5	3.24	213	" fusion ICP-OES/MS	
OREAS 25a	.	(56)	(135)	10 g 60 g or 1 kg	Cl:(<10ppm)
OREAS 25a 4	4.06	48.5	1.60	(0.41)	(0.10)	15.8	0.35	(0.3)	2.94	2.10	12.3	(1.48)	(159)	" 4 acid digestion, SOIL	
OREAS 25a A	2.70	17.3	(0.099)	(0.24)	.	10.7	0.20	(0.062)	1.49	.	4.56	(0.41)	(19.0)	" aqua regia	
OREAS 25a F	4.83	49.4	1.99	0.66	.	16.4	(0.30)	0.43	3.51	2.89	25.1	2.89	398	" fusion ICP-OES/MS	
OREAS 24c	1.51	442	1.48	(0.90)	(<0.05)	3.08	(0.064)	(0.31)	0.76	0.53	22.3	(1.88)	143	10 g 60 g or 1 kg Basalt V: 161	
OREAS 22d	0.61	(1.14)	(0.036)	(<0.05)	(<0.05)	0.67	(<0.02)	(<0.05)	0.18	0.21	0.69	(<0.1)	7.02	10 g 60 g or 1 kg Quartz V: 2.63	

Number	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	W	Y	Yb	Zr	Units	Other
--------	----	----	----	----	----	----	----	----	---	---	---	----	----	-------	-------

GRANITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %														IAG: RM		all others: CRM	
Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI	
JG-2	76.83	12.47	.	0.70	(0.0972)	0.57	0.33	0.97	+0.33 -0.12	4.71	0.037	0.016	3.54	0.002	0.044	.	
VS 3333-85	74.76	10.64	(0.1)	0.32	0.062	1.61	4.50	.	(0.30)	4.64	0.10	0.120	4.24	0.024	0.26	.	
IAG OU-3	74.09	11.10	1.913	0.2	0.1100	3.255	.	3.8341	.	4.55	.	0.090	3.678	.	0.224	1.815	
GUW GM	73.42	13.55	0.28	1.07	0.067	1.13	2.01	.	0.35	4.76	0.37	0.043	3.78	0.062	2.12	.	
GBW 07103	72.83	13.40	(0.15)	1.55	0.235	1.02	.	2.14	+0.60	5.01	0.42	.	3.13	.	.	(0.70)	
USZ 47-2008	72.37	14.07	.	1.15	.	1.81	2.44	.	.	4.68	0.38	0.06	3.63	0.13	0.30	0.64	
USZ 28-99	71.61	16.13	.	0.39	1.25	0.29	.	0.51	-(0.05)	3.52	(0.29)	0.13	5.25	0.028	(0.03)	1.14	
SARM 48	67.11	11.24	.	8.90	.	(0.2)	0.58	.	.	4.26	0.18	0.02	3.22	(0.09)	0.10	.	
NCS DC73376	66.27	16.33	0.35	2.66	0.0670	(1.6)	.	3.12	(1.0)	2.60	1.63	.	5.3	.	.	1.28	

continued analysis listed in mg/kg except % which is mass % and * which is ng/g																		
Number	Ag	Al%	As	B	Ba	Be	Bi	Ca%	Cd	Ce	Cl	Co	Cr	Cs	Cs ₂ O%	Cu	Dy	
JG-2	(0.019)	6.60	(0.68)	(1.78)	81.0	3.26	(0.64)	0.50	(0.004)	48.3	.	3.62	6.37	6.79	.	0.49	10.5	
VS 3333-85	(0.06)	.	(4)	11	90	5	.	.	.	90	.	1.3	3.1	4.5	.	12	(10)	
IAG OU-3	.	.	3.3793	.	28	10.94	.	.	0.38	196.3	.	.	18.61	0.66	.	3.3	18.87	
GUW GM	(0.09)	.	4.1	11	340	(4.8)	.	.	.	65	.	3.7	11	8.1	.	13	(5.4)	
GBW 07103	0.033	.	2.1	24	343	12.4	0.53	.	0.029	108	127	3.4	3.6	38.4	.	3.2	10.2	
USZ 47-2008	.	.	2.28	.	350	8.63	1.03	.	.	64.38	.	2.71	182	17.02	.	7.36	4.42	
USZ 28-99	.	.	(3)	(25)	.	(130)	.	0.012	8	.	.	
SARM 48	(290)	(850)	.	.	23	.	(10)	.	.	
NCS DC73376	0.03	.	(0.25)	15	1140	1.7	0.096	.	(0.06)	48	(120)	7.8	24	2.6	.	(3.1)	1.52	

Number	Er	Eu	Fe%	Ga	Gd	Ge	Hf	Hg	Ho	In	K%	La	Li	Li ₂ O%	Lu	Mg%	Mn%
JG-2	6.04	0.10	0.68	18.6	8.01	(1.70)	4.73	(0.0033)	1.67	.	3.91	19.9	42.2	.	1.22	0.02	0.012
VS 3333-85	(6)	0.4	.	27	.	2.2	12	45	52	.	0.9	.	.
IAG OU-3	11.44	1.152	.	32.1	18.073	1.5	22.631	.	4.011	.	.	94.64	1.41	.	1.628	.	.
GUW GM	(2.2)	0.60	.	15	(5.2)	(1.6)	5.1	(0.0033)	(1.0)	.	.	41	50	.	0.40	.	.
GBW 07103	6.5	0.85	.	19	9.3	2.0	6.3	0.0041	2.05	.	.	54	131	.	1.15	.	0.0463
USZ 47-2008	2.37	0.58	.	22.80	4.95	1.50	4.75	.	0.85	.	.	29.59	124	.	0.35	.	.
USZ 28-99	(15)	.	0.37	.	.	.
SARM 48
NCS DC73376	0.76	1.0	.	18.2	2.4	0.93	3.3	0.0035	0.27	(0.03)	.	25	24.7	.	0.11	.	0.0430

Number	Mo	Na%	Nb	Nd	Ni	P%	Pb	Pr	Rb	Rb ₂ O%	S	Sb	Sc	Se	Si%	Sm	Sn	Sr
JG-2	0.37	2.63	14.7	26.4	(4.35)	0.001	31.5	6.20	301	.	(7.0)	(0.057)	2.42	.	35.91	7.78	3.00	17.9
VS 3333-85	1.7	.	17	50	6	.	10	.	140	.	(160)	(0.5)	4.6	.	.	10	5	8
IAG OU-3	1.975	.	80.2	87	.	.	36	22.7	171	.	.	0.3	.	.	.	18.71	11.45	11.2
GUW GM	1.1	.	18	30	6.8	.	30	(7.2)	260	.	.	(0.51)	4.8	.	.	4.9	4.4	133
GBW 07103	3.5	.	40	47	2.3	0.0405	31	12.7	466	.	380	0.21	6.1	(0.04)	.	9.7	12.5	106
USZ 47-2008	3.06	.	15.22	27.10	5.76	.	24.81	7.27	275	.	.	0.19	4.36	.	.	5.54	13.30	111
USZ 28-99	.	.	71	.	10	.	64	.	.	0.24	.	.	(7)
SARM 48	(5)	.	202	.	.	.	135	29
NCS DC73376	(0.27)	.	4.5	21	13	0.0570	7.6	5.8	57	.	(50)	0.063	5.0	0.019	.	3.3	0.8	690

Number	Ta	Tb	Te	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units
JG-2	2.76	1.62	.	1.62	0.026	1.55	1.16	11.3	3.78	23.0	86.5	6.85	13.6	97.6	20 g
VS 3333-85	1.1	0.4	.	80	.	.	.	1.8	6	(1.1)	60	7	140	470	100 g
IAG OU-3	5.748	3.081	.	22.845	.	0.735	1.731	5.5396	.	.	113.1	11.3	149.22	942	~35 g
GUW GM	1.7	0.7	.	36	.	.	.	6.4	11	1.6	26	3.1	34	149	50 g
GBW 07103	7.2	1.65	0.021	54	0.1720	1.93	1.06	18.8	24	8.4	62	7.4	28	167	70 g
USZ 47-2008	2.56	0.79	.	19.35	.	1.72	0.37	5.44	14.03	0.56	25.19	2.36	54.59	169	100 g
USZ 28-99	54	0.086%	46	100 g
SARM 48	.	.	.	113	(8)	.	436	.	53	300	100 g
NCS DC73376	(0.34)	0.29	.	1.9	0.1800	(0.20)	0.11	(0.4)	45	0.38	7.3	0.69	47	(100)	70 g

last of stock

CRM GRANODIORITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	Al	CO ₂	CaO	Fe	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Si	TiO ₂
JG-1a	72.30	14.30	7.57	.	2.13	1.40	1.36	0.51	2.00	+0.59 -0.12	3.96	0.69	0.057	3.39	0.083	33.80	0.25
JG-1	72.30	14.24	7.54	.	2.20	1.52	1.61	0.38	2.18	+0.54 -0.07	3.98	0.74	0.063	3.38	0.099	33.80	0.26
JG-3	67.29	15.48	8.19	.	3.69	2.58	1.83	1.62	3.69	+0.67 -0.17	2.64	1.79	0.071	3.96	0.122	31.45	0.48
US GSP-2	66.6	14.9	7.88	.	2.10	3.43	.	.	4.90	.	5.38	0.96	.	2.78	0.29	31.1	0.66
VS 2125-81	64.08	15.35	.	0.14	3.93	.	2.87	5.23	.	.	3.98	1.87	0.160	3.25	0.228	.	0.517
GBW 07111	59.68	16.56	.	0.15	4.72	.	3.08	2.64	.	0.88	3.50	2.81	0.094	4.05	0.34	.	0.77

continued analysis listed in mg/kg except % which is mass % and * which is ppb

Number	Ag	As	Au*	B	Ba%	Be	Bi	Br	C%	Ca%	Cd	Ce	Cl%	Co	Cr	Cs	Cu
JG-1a	(0.023)	(0.43)	0.21	3.95	0.0470	3.16	(0.43)	.	(0.0295)	1.52	(0.026)	45.0	(0.0065)	5.90	17.6	10.6	1.67
JG-1	0.034	0.33	0.11	6.87	0.0466	3.15	0.50	(0.068)	(0.0216)	1.57	0.040	45.8	0.00581	4.06	53.2	10.1	2.52
JG-3	(0.029)	(0.37)	0.17	(2.15)	0.0466	(1.60)	(0.05)	.	(0.0120)	2.64	(0.054)	40.3	(0.0156)	11.7	22.4	1.78	6.81
US GSP-2	0.1340	(1.5)	.	.	.	1.50	.	410	.	7.3	20	(1.2)	43
VS 2125-81	.	.	.	27	0.14	3.7	13	37	.	57
GBW 07111	0.066	0.4	.	3.92	0.1900	2.11	0.05	(0.34)	(0.057 Org)	.	0.08	112	0.023	15.6	37.6	0.97	8.8

Number	Dy	Er	Eu	F%	Ga	Gd	Ge	Hf	Hg*	Ho	I*	In	Ir*	K%	La	Li	Lu
JG-1a	4.44	2.57	0.70	0.0439	16.5	4.08	(1.5)	3.59	(4.1)	0.82	.	(0.025)	.	3.29	21.3	79.5	0.44
JG-1	4.14	2.16	0.73	0.0498	17.8	4.28	1.44	3.56	16.5	0.81	(0.012)	(0.044)	.	3.30	22.4	86.6	0.39
JG-3	2.59	1.52	0.90	(0.0317)	17.1	2.92	(1.06)	4.29	(2.4)	0.38	.	.	(0.0016)	2.19	20.6	20.9	0.26
US GSP-2	(6.1)	(2.2)	2.3	(0.3000)	22	(12)	.	(14)	.	(1.0)	.	.	.	4.48	180	(36)	(0.23)
VS 2125-81	22	.	1.8	20	.	.
GBW 07111	3.20	1.57	1.91	0.084	20.8	5.09	1.00	5.2	35	0.60	(78)	0.08	.	60.5	16.2	0.24	

Number	Mg%	Mn%	Mo	Na%	Nb	Nd	Ni	P%	Pb%	Pd*	Pr	Rb%	S%	Sb	Sc	Se	Sm
JG-1a	0.42	0.044	0.45	2.51	11.4	20.4	6.91	0.036	0.00264	(<0.2)	5.63	0.0178	(0.0011)	(0.048)	6.21	.	4.53
JG-1	0.45	0.049	1.75	2.51	12.4	19.3	7.47	0.043	0.00254	(<0.2)	4.83	0.0182	0.00109	0.13	6.53	0.0030	4.62
JG-3	1.08	0.055	0.45	2.94	5.88	17.2	14.3	0.053	0.00117	(<0.2)	4.70	0.00673	(0.0055)	(0.08)	8.76	.	3.39
US GSP-2	0.58	0.0320	(2.1)	2.06	27	200	17	0.13	0.0042	.	(51)	0.0245	.	.	6.3	.	27
VS 2125-81	.	.	3.22	8.8	.	15	.	.	0.016	.	.	0.016	0.019	.	13	.	.
GBW 07111	.	.	0.47	10.6	48.1	24.4	.	.	0.00198	.	13.2	0.00701	0.011	0.06	10.3	0.03	7.74

Number	Sn	Sr%	Ta	Tb	Te	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn%	Zr%	Units
JG-1a	4.47	0.0187	1.90	0.81	.	12.8	0.15	0.98	0.38	4.69	22.7	12.4	32.1	2.70	0.00365	0.0118	20 g
JG-1	3.60	0.0184	1.79	0.78	.	13.2	0.16	1.03	0.41	3.47	25.2	(1.58)	30.6	2.47	0.00411	0.0111	20 g
JG-3	1.40	0.0379	0.70	0.46	.	8.28	0.29	(0.40)	0.24	2.21	70.1	(14.1)	17.3	1.77	0.00465	0.0144	100 g
US GSP-2	.	0.0240	.	.	.	105	0.40	(1.1)	(0.29)	2.40	52	.	28	1.6	0.0120	0.0550	50 g
VS 2125-81	8.0	0.048	.	.	.	90	90	.	.	.	0.012	0.021	40 g
GBW 07111	1.44	0.1198	0.62	0.68	0.011	10.9	.	0.39	0.26	1.40	104	0.19	15.5	1.56	0.00854	0.0224	50 g

GRAPHITE

analysis listed in mass %

Graph = Graphitic, T = Total

CDN: RM, all others: CRM

CDN: 10 g

GGC: 10 g

NCS: 50 g

USZ: 100 g

Number	Al ₂ O ₃	C.Graph	T.C	CO ₂	CaO	Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	Ni	P ₂ O ₅	Rb	S	SiO ₂	TiO ₂	Zn	Zr	LOI	
NCS DC60121	5.60	76.50	.	0.28	0.74	1.48T	1.98	0.99	0.50	0.022	0.23	.	0.16	.	0.14	10.34	0.55	Volatile:2.72		Ash:20.78	
GGC-02	.	27.04	28.25	0.04
GGC-01	.	24.97	26.68	0.04
GGC-03	.	16.29	17.61	0.04
USZ 32-2000	9.33	(12.0)	14.43	4.10	7.05	3.48	.	2.54	1.94	0.03	0.47	0.007	.	0.014	.	52.20	0.57	0.018	0.012	22.21	
USZ 33-2000	8.46	(11.34)	13.38	2.45	.	3.61	.	2.09	.	0.07	0.51	52.84	0.49	.	.	17.0	
NCS DC60120	13.03	9.91	.	0.67	5.34	6.99T	2.80	2.17	5.35	0.054	1.56	.	0.14	.	2.59	49.34	0.64	.	.	.	
GGC-05	.	8.60	9.20	0.05	last
GGC-06	.	7.68	8.16	0.05	last
GGC-10	.	4.79	5.22	4.40
CDN GR-1	(8.6)	3.12	.	.	(6.3)	(4.2)	.	(3.0)	(2.4)	(<0.1)	(0.3)	.	.	.	(1.0)	(65.3)	(0.4)	.	.	(6.8)	
NCS DC60119	12.93	2.91	.	3.60	9.37	6.73T	2.60	2.54	6.10	0.084	1.60	.	0.13	.	1.18	49.84	0.57	.	.	.	
GGC-09	.	2.41	2.95	4.59
CDN GR-3	(9.3)	2.39	.	.	(6.2)	(4.3)	.	(3.1)	(2.5)	(<0.1)	(0.4)	.	.	.	(1.0)	(66.2)	(0.4)	.	.	(4.9)	
CDN GR-2	(7.9)	1.93	.	.	(11.6)	(3.3)	.	(2.9)	(1.9)	(<0.1)	(0.2)	.	.	.	(1.0)	(57.5)	(0.3)	.	.	(10.9)	
CDN GR-4	(12.9)	1.01	.	.	(6.6)	(6.3)	.	(2.3)	(2.4)	(0.2)	(1.8)	.	.	.	(1.0)	(61.8)	(0.5)	.	.	(2.7)	
GGC-08	.	0.39	1.03	1.57
GGC-07	.	0.13	0.56	0.51

CRM	GRAPHITE ORE												analysis listed in mass %		50 g units	
Number	Al ₂ O ₃	Ash	CaO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	Volatile			
NCS DC28120	10.93	95.62	11.81	5.34	2.39	8.79	0.048	1.50	0.083	1.06	52.73	0.39	2.22			
NCS DC28121	10.72	90.65	11.12	5.00	2.32	8.43	0.047	1.38	0.083	0.99	50.28	0.36	2.48			
NCS DC28119	8.13	29.00	0.23	2.09	1.33	0.55	0.032	0.28	0.087	0.02	15.66	0.44	2.88			
NCS DC28118	1.92	11.45	0.91	1.98	0.19	1.00	0.021	0.088	0.007	0.49	5.00	0.085	1.87			
NCS DC28117	0.63	3.47	0.19	0.46	0.17	0.18	0.005	0.009	0.004	0.17	1.76	0.014	1.33			

CRM	GRAPHITE - SYNTHETIC															
available as a set or individually																
analysis listed in mg/kg																
50 g units																
Number	Al	As	Ca	Cl	Co	Cr	Cu	Fe	K	Mg	Mn	Mo	NO ₃	Na	Ni	Pb
CIBA KD-2	35	(0.05)	98	(4.1)	(0.10)	1.3	1.0	180	(41)	(21)	23	(0.22)	(0.5)	(20)	3.9	(1.6)
CIBA LD-4	33	(0.06)	126	(3.3)	(0.11)	3.4	1.3	149	(25)	(7.5)	3.5	(0.62)	(0.5)	(13)	5.5	(1.1)
CIBA KD-3	15	(0.04)	62	(4.4)	(0.07)	0.69	0.81	111	(39)	(22)	13	(0.44)	(0.5)	(17)	4.2	(0.90)
CIBA KD-1	12	(0.09)	74	(5.4)	(0.19)	3.2	0.97	428	(21)	(6.7)	56	(0.95)	(0.5)	(10)	6.0	(1.3)
CIBA KD-6	8.4	(0.04)	79	(3.3)	(0.03)	0.44	0.62	37	(17)	.	4.3	(0.39)	(0.5)	(7)	2.0	(1.2)
CIBA PD-7	5.5	(0.03)	22	(6.4)	(0.03)	2.2	0.51	59	(17)	.	1.1	(0.25)	(0.5)	(2)	1.1	(1.0)

continued

Number	S	SO ₄	Sb	Si	Sn	Sr	Ta	Ti	V	W	Zn	Zr
CIBA KD-2	(44)	(88)	(0.05)	(145)	(<0.2)	(2.8)	(0.005)	(46)	(3.6)	(<0.08)	(4.4)	(3.7)
CIBA LD-4	(68)	(98)	(0.03)	(404)	.	(2.7)	(0.011)	(49)	(4.3)	(<0.06)	(2.9)	(8.6)
CIBA KD-3	(43)	(85)	(0.02)	(147)	.	(1.9)	(0.006)	(38)	(3.8)	(<0.08)	(1.2)	(4.5)
CIBA KD-1	(45)	(93)	(0.03)	(390)	(<0.2)	(1.8)	(0.008)	(53)	(6.6)	(0.04)	(2.3)	(7.5)
CIBA KD-6	(44)	(73)	(0.03)	(66)	.	(1.9)	(0.006)	(51)	(4.9)	(0.03)	(1.7)	(6.0)
CIBA PD-7	(23)	(25)	(0.02)	(50)	.	(1.3)	(0.005)	(29)	(2.0)	(0.03)	(0.9)	(4.5)

last of stock

CRM	GREISEN														analysis listed in mass%		T = Total		CGL: 17025, 100 g units		GUW: 50 g units	
Number	SiO ₂	Al ₂ O ₃	CaO	F	Fe ₂ O ₃	FeO	K ₂ O	MgO	MnO	Na ₂ O	Li	P ₂ O ₅	Rb	Sn	TiO ₂	Zn	Zr	LOI				
CGL 022	80.93	10.26	0.836	(1.48)	3.25T	.	(1.47)	0.044	0.102	(0.038)	.	0.018	(0.0463)	0.1884	0.086	0.0273	0.0148	1.46				
GUW GNA	71.47	14.7	0.62	3.32	5.92	3.81	2.63	0.168	0.034	0.08	0.49	.	0.202	0.19	0.022	0.0078	0.0070	.				

continued

analysis listed in mg/kg

Number	As	Ba	Bi	Cr	Cs	Cu	Dy	Ga	Mo	Nb	Sr	Ta	Th	U
CGL 022	63.6	(25.6)	(29.6)	271	(29.7)	563	(14.1)	26.1	.	28.4	16.6	(4.01)	32.9	(6.12)
GUW GNA	7	51	220	.	45	.	3	.	100	.	.	29	.	22

also 19 more informational elements

CRM	GYPSUM ROCK														
analysis listed in mass %															
100 g units															
Number	SO ₃	CaO	Al ₂ O ₃	CO ₂	Fe ₂ O ₃ *	H ₂ O+G	H ₂ O+C	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	SrO	%Total	L.O.I.**
DOMTAR GYP A	46.2	32.9	0.10	0.47	0.05	19.4	.	0.021	0.18	0.009	0.011	0.45	0.11	99.90	20.06
DOMTAR GYP D	36.7	28.2	2.03	3.6	1.08	16.39	0.37	0.54	1.73	0.07	0.025	8.7	0.18	99.62	20.82

* Total iron calculated as Fe₂O₃
H₂O+C Water from clay between 450-550°C.** Loss on ignition at 1000°C
H₂O+G Water from CaSO₄ 2H₂O and some CaSO₄ 1/2H₂O between 80-300°C.

continued

analysis listed in mg/kg

Number	As	Ba	Br	Cd	Ce	Cl	Co	Cr	Cs	Eu	Hf	La
DOMTAR GYP A	0.19	(28)	(0.5)	0.51	(0.70)	12	(0.2)	(2)	(0.15)	0.060	0.26	0.24
DOMTAR GYP D	3	106	1.3	.	9	234	2.4	9	1.3	0.17	0.6	5

continued

Number	Lu	Mn	Rb	Sb	Sc	Sm	Ta	Th	Ti	U	V	Yb	Zn	Zr
DOMTAR GYP A	(0.006)	19	(0.8)	0.04	0.09	0.041	.	(0.1)	(78)	0.10	.	0.020	7	(9)
DOMTAR GYP D	0.067	200	25	0.28	2	0.83	0.15	1.3	473	0.65	17	0.44	16	29

CRM GYPSUM ROCK

analysis listed in mass %

Number	SO ₃	CaO	Al ₂ O ₃	CO ₂	Cl-	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	Na ₂ O	SiO ₂	SrO	TiO ₂	LOI	Units
GBW 03109a	51.91	39.24	0.34	(4.02)	0.033	0.16	0.39	0.094	1.74	0.065	1.68	(0.27)	0.016	4.55	50 g
GBW 03111a	40.72	32.30	0.14	(5.44)	0.0032	0.11	17.95	0.026	2.47	0.014	0.63	(0.096)	0.010	23.60	50 g
NCS DC62106c *	38.66	29.83	1.85	.	.	0.58	.	0.35	1.61	0.09	5.45	.	0.09	21.11	20 g

* NCS DC62106c also contains 0.21% adhered water and 17.09% crystallized water.

RM GYPSUM BYPRODUCT

analysis listed in mass % based on a dry (40°C) sample

100 g units

Number	SO ₃	CaO	Al ₂ O ₃	CO ₂	Cr ₂ O ₃	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	SrO	TiO ₂	V ₂ O ₅	%Total	LOI*
DOMTAR FGD-1	46.4	32.7	0.023	0.02	0.0002	0.014	20.70	0.007	0.007	0.005	0.03	0.13	0.012	.	0.0003	100.05	21.04
DOMTAR FGD-2	45.6	32.8	0.033	0.62	0.0015	0.043	20.38	0.01	0.019	0.02	0.05	0.21	0.024	.	0.0009	98.81	21.33
DOMTAR TIG-1	43.4	32.3	0.57	1.41	0.036	0.26	20.3	0.008	0.12	0.036	0.04	0.11	0.42	0.82	0.10	99.93	22.03

H₂O+ combined water at 250°C * Loss on ignition at 1000°C (1 hr)

continued

analysis listed in mg/kg

Number	As	Ce	Cl	Co	Cr	Dy	Eu	F	Hf	La	Mn	Sb
DOMTAR FGD-1	0.10	0.5	(100)	0.02	1.2	.	0.02	95	.	0.35	2.0	0.03
DOMTAR FGD-2	0.48	1.7	(115)	0.07	10.2	0.48	0.09	320	0.06	2.18	2.5	0.024
DOMTAR TIG-1	0.22	6	400	0.26	246	0.42	0.08	230	3.0	2.7	36	0.05

Number	Sc	Se	Sm	Ta	Tb	Th	Ti	U	V	Yb	Zn	Zr
DOMTAR FGD-1	0.023	0.8	0.07	.	.	0.03	75	.	1.5	.	1.7	.
DOMTAR FGD-2	0.166	3.0	0.52	.	0.07	0.38	75	1.10	5.1	0.27	2.3	(10)
DOMTAR TIG-1	17.1	.	0.65	3.1	(2)	2.14	6154	2.5	560	0.31	(32)	(80)

CRM HORNBLENDITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	Al ₂ O ₃	CO ₂	CaO	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	Mn	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	Ti	TiO ₂	LOI
VS 2113-81	14.24	.	11.04	9.72	18.26	.	0.382	12.70	.	0.144	2.14	.	.	37.95	.	1.91	.
NCS DC73377	13.76	(0.16)	9.6	10.8	14.8	(1.7)	0.48	7.2	0.1600	.	2.07	.	(0.0060)	49.62	0.5510	.	1.06
JH-1	5.66	.	15.02	(8.09)	10.27	.	0.53	16.73	.	0.19	0.71	0.099	.	48.18	.	0.67	.

continued analysis listed in mg/kg except * which is ng/g

Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Cl	Co	Cr	Cs	Cu%	Dy	Er	Eu	F	Ga	Gd
VS 2113-81	.	.	.	99	74	15	.	0.074	25	.
NCS DC73377	(0.05)	26	12	62	0.34	(0.06)	(0.14)	7.7	(116)	52	137	1.8	0.0084	3.5	2.3	0.91	200	17.2	2.8
JH-1	.	.	.	106	.	.	.	17.6	.	51.5	616	0.87	0.00086	2.5	1.2	0.86	.	7.9	.

Number	Ge	Hf	Hg*	Ho	In	La	Li	Lu	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	Sb	Sc
VS 2113-81	1.3	.	.	57	.	4.9	.	.	.	58
NCS DC73377	1.46	1.5	3.3	0.85	(0.06)	2.9	11.2	0.39	0.15	2.7	6.5	117	360	(8)	1.25	29	0.63	43
JH-1	.	1.4	.	0.53	.	7.9	.	0.17	0.77	4.2	11.6	58.2	.	2.6	.	14.4	.	77.6

Number	Se	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units
VS 2113-81	.	.	2.9	39	.	.	1.5	1370	21	40 g
NCS DC73377	0.083	2.1	(0.8)	142	(0.18)	0.57	(0.4)	(0.11)	0.37	(0.14)	296	0.34	20	2.4	100	(57)	70 g
JH-1	.	3.1	.	153	0.23	0.52	1.4	.	.	0.58	228	.	13.7	1.2	61.8	48.3	100 g

AMPHIBOLITE

IRON PELLETS (supplied in homogeneous powder form)

= class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Fe	Fe(met)	FeO	Al	Al ₂ O ₃	Ca	CaO	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂
1	SRM 691	90.8	84.6	.	.	1.22	.	0.63	.	0.52	.	0.043	.	0.186	0.006	0.008	.	3.7	.	0.27
1	VS R10/3	90.9	82.5	.	.	0.30	.	0.182	.	0.32	.	.	.	0.073	0.0102	0.0013	.	4.04	.	.
1	NCS DC28240a	66.18	.	0.78	.	0.43	.	0.51	.	0.79	.	0.040	.	.	0.010	0.0066	.	3.81	.	0.048
2	BS 105	65.95	.	.	0.10	.	0.50	.	0.19	.	0.09	.	0.017	.	0.008	(0.001)	2.14	.	0.008	.
1	VS R29	64.95	.	0.48	.	0.38	.	0.45	.	0.149	0.0123	0.0118	.	6.13	.	.
1	NCS DC28240b	64.58	.	0.78	.	0.80	.	0.73	.	1.33	.	0.057	.	.	0.014	0.0080	.	4.79	.	0.136
1	NCS DC28239b	63.78	.	0.77	.	0.98	.	0.85	.	1.59	.	0.065	.	.	0.016	0.0086	.	5.29	.	0.18
1	NCS DC28020a	63.07	.	(0.04)	.	1.47	.	1.34	.	0.96	.	0.303	.	0.103	0.028	0.0084	.	5.22	.	0.258
1	VS R28	63.01	.	1.16	.	0.37	.	4.09	.	0.194	0.0121	0.087	.	5.11	.	.
1	NCS DC14004b	62.79	.	0.72	.	1.32	.	1.16	.	1.58	0.130	.	.	0.112	0.016	0.012	.	5.31	.	0.113
1	NCS DC28239a	62.14	.	0.77	.	1.36	.	1.09	.	2.13	.	0.082	.	.	0.020	0.010	.	6.32	.	0.267
1	NCS DC28020b	61.81	.	(0.18)	.	1.48	.	1.30	.	1.00	.	0.310	.	0.099	0.032	0.0055	.	6.88	.	0.251
1	NCS DC11025	61.37	.	(1.92)	.	1.35	.	1.04	.	0.80	.	0.120	.	0.105	0.093	0.021	.	6.59	.	1.61
1	NCS DC28020	60.77	.	0.97	.	1.25	.	1.08	.	1.99	0.110	.	.	.	0.021	0.019	.	8.25	0.063	.
1	NCS DC28020c	60.46	.	0.33	.	0.76	.	0.75	.	5.15	.	0.130	.	0.036	0.013	0.029	.	6.12	.	0.154
1	VS R3/2	58.72	.	2.53	.	2.50	.	4.47	.	2.48	.	0.232	.	.	0.0027	0.005	.	3.74	.	2.49
1	VS R23/1	58.7	4.45	3.75	.	.
1	NCS DC28021a	57.88	.	6.53	.	2.54	.	3.15	.	3.11	.	0.126	.	0.105	0.016	0.115	.	7.92	.	0.207

Number	As*	C	Cd*	Co	Cr	Cu	K	K ₂ O	Mo*	N*	Ni	Pb*	Sn	V	V ₂ O ₅	Zn	Units
SRM 691	(14)	0.12T	(<5)	0.030	(0.03)	0.032	(0.06)	.	(<20)	(50)	(0.3)	(<20)	(<0.0010)	(0.0135)	.	(0.0040)	100 g
VS R10/3	.	2.18	.	.	.	0.0025	.	0.037	.	.	.	1.4	.	.	.	0.0019	100 g
NCS DC28240a	50 g
BS 105	13	.	.	(0.0004)	0.013	0.001	0.014	.	.	.	0.004	(3)	(0.001)	0.003	.	(0.001)	100 g
VS R29	100 g
NCS DC28240b	50 g
NCS DC28239b	50 g
NCS DC28020a	0.0089	.	0.078	0.012	50 g
VS R28	100 g
NCS DC14004b	0.071	.	0.250	0.042	50 g
NCS DC28239a	50 g
NCS DC28020b	0.0089	.	0.066	0.155	.	0.012	50 g
NCS DC11025	0.111	0.012	70 g
NCS DC28020	last	.	100 g
NCS DC28020c	0.010	.	0.081	0.012	50 g
VS R3/2	.	.	.	0.020	0.56	100 g
VS R23/1	150 g
NCS DC28021a	12	0.018	.	0.265	.	.	.	47	.	.	.	0.039	50 g

CRM IRON SULPHIDE CONCENTRATE

analysis listed in mass %

25 g units

Number	Al	Ca	Co	Cr	Cu	Fe	K	Mg	Mn	Na	Ni	P	Pb	S	SiO ₂	Ti	Zn
CAN TPO-1	(3.51)	(2.17)	0.021	(0.03)	0.118	34.85	(0.56)	(1.66)	(0.08)	(0.85)	0.617	(0.03)	(0.02)	18.03	25.52	(0.35)	(0.02)

IRON ORE, chart 3 of 9

= class, where 1 = CRM and 2 = RM

analysis listed in mass % except * which is mg/kg

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂
1	GIOP-127	64.499	.	.	2.815	.	0.1522	.	0.0195	.	0.0644	0.0633	.	0.0184	.	0.0457	.	0.0133	.	2.578	.	0.0581
1	NCS DC14001b	64.48	0.34	.	1.26	.	0.15	.	0.096	.	0.041	0.087	.	.	0.013	0.049	.	0.018	.	3.40	.	0.057
1	NCS DC28113	64.42	27.00	.	0.90	.	1.06	.	0.099	.	3.28	0.109	.	.	0.034	0.011	.	0.381	.	3.56	0.315	0.522
1	ECRM 691-1	64.39	.	0.475	.	0.999	.	0.0504	.	2.022	.	0.1734	.	0.0164	.	0.0877	.	0.0632	0.556	.	0.966	.
1	NCS DC14028d	64.37	20.96	.	1.10	.	1.17	.	0.036	.	1.30	0.147	.	.	0.017	0.013	.	0.371	.	2.95	0.294	.
1	NCS DC93025	64.17	31.34	.	0.29	.	0.56	.	0.012	.	0.49	0.032	.	.	0.011	0.033	.	0.624	.	9.43	.	0.049
2	DH 1125	64.05	0.193	.	1.200	.	2.53	.	0.033	.	0.421	0.068	.	.	0.016	.	0.087	0.010	.	2.52	.	0.045
1	NM 613C	64.03	.	.	3.11	.	0.24	.	.	.	0.35	0.025	.	.	.	0.023	.	0.013	3.63	.	.	.
1	VS R15/2	64.0	28.0	.	.	.	0.9	2.3	.	.
1	NCS DC28215	63.93	26.9	.	1.09	.	2.06	.	.	.	0.79	.	0.136	.	.	0.017	.	0.282	.	5.90	0.444	.
1	NCS DC14049	63.86	0.25	.	2.04	.	0.084	.	0.33	.	0.056	0.170	.	.	0.027	0.037	.	0.020	.	4.62	.	0.12
1	NCS DC28051	63.56	0.35	.	0.926	.	1.12	.	0.13	.	1.48	0.134	.	.	0.070	0.018	.	0.015	.	4.57	0.071	.
1	ASCRM 032	63.53	.	0.97	.	0.040	.	0.006	.	0.039	.	0.071	.	0.0085	.	0.074	.	0.011	1.81	.	0.043	.
1	NCS DC11005a	63.34	(0.07)	.	0.52	.	0.12	.	0.070	.	0.146	.	0.84	.	0.020	0.016	.	0.107	.	3.36	.	0.034
1	NCS DC11017	63.33	1.76	.	1.13	.	1.05	.	0.115	.	1.30	.	0.086	.	0.070	0.011	.	0.0030	.	5.56	.	0.151
1	GIOP-141	63.226	.	.	1.8	.	0.036	.	0.0189	.	0.1003	0.0691	.	0.024	.	0.0665	.	0.0281	.	3.548	.	0.0574
1	NCS DC28224	63.20	1.4	.	1.02	.	0.86	.	.	.	0.50	.	0.083	.	.	0.020	.	0.015	.	6.55	0.319	.
1	NM 161.6	63.18	.	.	2.85	0.067	.	0.009	.	2.37	.	0.10
1	KZ 181-89	63.18	.	.	1.18	.	2.19	.	0.10	.	0.74	.	.	.	0.20	0.035	.	4.16	.	6.11	.	0.070
2	DH 1115	63.17	.	.	2.68	.	0.494	.	0.008	.	0.244	0.074	.	.	0.020	.	0.101	.	.	5.79	.	0.128
1	IMZ 330	63.09	1.19	.	0.13	.	1.04	.	0.18	.	0.23	0.012	.	.	0.073	0.013	.	0.003	.	8.26	.	0.01
1	NCS DC28003b	63.07	23.93	.	0.64	.	0.71	.	0.025	.	4.82	.	1.08	.	0.016	0.016	.	0.024	.	3.38	.	0.224
1	IMZ 331	63.05	1.55	.	0.24	.	3.78	.	0.092	.	0.21	0.028	.	.	0.037	0.015	.	0.107	.	5.11	.	0.017
1	GIOP-143	62.97	.	.	1.49	.	0.0348	.	0.00942	.	0.0475	0.1353	.	0.0121	.	0.064	.	0.01731	.	3.086	.	0.0531
1	GIOP-55	62.8	.	.	2.18	.	0.0393	.	0.0131	.	0.047	0.0798	.	0.0155	.	0.0755	.	0.0223	.	0.0977	.	0.0977
1	JSS 806-1	62.77	.	0.96	.	0.0197	.	0.0091	.	0.034	.	0.125	.	0.0115	.	0.083	.	0.019	1.55	.	0.044	.
1	GIOP-44	62.75	.	.	2.216	.	0.0255	.	0.0127	.	0.0571	0.0709	.	(0.02)	.	0.06267	.	0.0199	.	4.55	.	0.1064
1	VS 5403-90	62.74	25.74	.	0.73	.	0.89	.	.	.	0.65	0.162	3.89	.	7.14	.	0.055	.
1	NCS DC28003a	62.65	24.53	.	0.39	.	0.71	.	0.040	.	4.73	.	0.113	.	0.013	0.011	.	0.114	.	4.20	.	0.117
1	NCS DC28110	62.63	23.21	.	1.19	.	1.09	.	0.068	.	5.21	0.170	.	.	0.028	0.017	.	0.255	.	3.15	0.096	0.160
1	ASCRM 031	62.53	.	0.80	.	0.011	.	0.005	.	0.035	.	0.110	.	0.0010	.	0.062	.	0.025	1.29	.	0.032	.
1	GIOP-37	62.53	.	.	2.037	.	0.0341	.	0.0146	.	0.0446	0.0959	.	0.015	.	0.1097	.	0.0159	.	3.877	.	0.0615
1	NCS DC73007	62.51	21.54	.	1.02	.	0.18	.	0.037	.	0.28	0.061	.	.	0.016	0.11	.	0.0058	.	10.93	0.059	.

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂	
	Number	As	Ba	C	Cl	Co	Cr	Cr ₂ O ₃	Cu	Ni	Pb	V	V ₂ O ₅	Zn	Zr	LOI	Units	Other					
	GIOP-127	0.0066	0.0072	.	0.0066 (0.0034)	.	0.007	.	0.0024	0.0042	0.0065	0.01274	.	0.0023	(0.0028)	1.834	10 g	Sr: 0.0036					
	NCS DC14001b	50 g						
	NCS DC28113	0.013	0.047	0.0096	.	.	70 g						
	ECRM 691-1	Fe II: 20.71	.	0.307	.	.	0.0095	.	0.0768	0.0299	0.0008	0.0603	.	0.0195	.	.	100 g						
	NCS DC14028d	50 g						
	NCS DC93025	100 g						
	DH 1125	.	.	0.671	CO ₂ : 0.93	.	0.002	0.008	.	.	0.354	100 g						
	NM 613C	100 g						
	VS R15/2	0.6	.	.	.	100 g						
	NCS DC28215	50 g						
	NCS DC14049	65 g						
	NCS DC28051	70 g						
	ASCRM 032	0.0018	0.0037	.	0.0080	0.0008	0.0022	.	0.0009	0.0011	0.0008	0.0022	.	0.0022	0.0019	2.90	10x10 g	Sr: 0.0013	Sr: 0.0008				
	NCS DC11005a	0.0044	(0.62 Bao)	0.119	.	0.0031	.	.	0.034	.	0.035	.	.	0.026	.	.	50 g						
	NCS DC11017	(0.0006)	0.0045	.	(0.0006)	.	.	0.0058	.	.	70 g						
	GIOP-141	0.00195 (0.004)	.	.	0.0103	0.00159	0.0154	.	0.0043	0.0055	(0.0034)	0.0022	.	0.00282	0.0027	3.687	10 g	Sr: 0.0027					
	NCS DC28224	100 g						
	NM 161.6	100 g						
	KZ 181-89	0.0080	.	.	0.046	100 g						
	DH 1115	0.005	0.010	.	.	.	100 g						
	IMZ 330	.	(0.003)	0.016	.	.	0.003	.	0.0017	(0.002)	0.0016	.	.	0.002	.	-0.04	100 g						
	NCS DC28003b	0.055	.	.	50 g						
	IMZ 331	(0.0004)	0.0025	.	.	0.001	0.0051	.	0.0016	0.002	0.002	0.003	.	0.003	.	0.22	100 g		Sn: 11*				
	GIOP-143	(0.0016)	(0.0059)	.	0.009	0.00187 (0.0016)	.	.	(0.0021)	(0.0028)	(0.004)	0.0016	.	0.00168	(0.0018)	4.898	10 g	Sr: 0.0029					
	GIOP-55	.	.	.	0.015	0.006	0.00528	3.389	10 g					
	JSS 806-1	0.0033	.	0.0012	0.0013	.	0.0018	.	0.0020	.	4.4	150 g		FeII: 0.15				
	GIOP-44	.	.	.	0.0082	.	0.0033	.	0.0026	2.929	10 g						
	VS 5403-90	0.32	0.029	.	.	50 g		Ag: 5.9*	CO ₂ : 0.39			
	NCS DC28003a	0.0071	0.0085	.	.	50 g						
	NCS DC28110	0.018	0.010	.	.	70 g						
	ASCRM 031	0.0011	0.0029	.	0.0106	0.0012	0.0026	.	0.0011	0.0013	0.0006	0.0013	.	0.0018	0.0014	5.80	10x10 g	Sn: 0.0013	Sr: 0.0001				
	GIOP-37	.	.	.	0.0109	4.021	10 g						
	NCS DC73007	(0.0015	50 g						

CRM IRON ORE, chart 4 of 9 # = class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂
1	GIOP-56	62.41	.	.	1.969	.	0.0369	.	0.0184	.	0.0513	0.2196	.	0.0174	.	0.0902	.	0.0164	.	3.594	.	0.06
1	GIOP-43	62.39	.	.	2.368	.	0.028	.	0.0134	.	0.0623	0.0821	.	(0.012)	.	0.0587	.	0.024	.	4.707	.	0.1213
1	NCS DC15005	62.36	0.48	.	2.56	.	0.050	.	0.015	.	0.062	.	0.112	.	0.015	0.073	.	0.022	.	4.69	.	0.113
1	ASCRM 035	62.35	.	0.72	.	0.117	.	0.022	.	0.150	.	0.152	.	0.0565	.	0.078	.	0.057	1.99	.	0.046	.
1	NCS DC28026	62.27	0.59	.	2.39	.	0.144	.	0.023	.	0.156	0.17	.	.	0.024	0.078	.	0.02	.	4.2	0.055	.
1	IRSID 611-1	62.22	.	0.69	.	2.85	.	.	.	0.32	.	1.97	.	.	.	0.030	.	(0.008)	2.07	.	0.033	.
1	USZ 27-99	62.2	21.06	.	1.37	.	0.56	.	0.07	.	2.78	.	0.105	.	(0.04)	.	(0.016)	.	.	3.37	.	0.101
1	SARM 132	62.2	.	.	1.84	.	(0.086)	.	0.219	.	.	.	(0.0200)	.	(0.031)	0.054	.	.	.	7.82	.	(0.094)
1	GIOP-38	62.15	.	.	2.008	.	0.0407	.	0.023	.	0.07	0.5627	.	0.0195	.	0.0515	.	0.0256	.	3.101	.	0.0687
1	NCS DC28025	62.11	0.58	.	2.06	.	0.021	.	0.023	.	0.101	0.65	.	.	0.013	0.067	.	0.013	.	2.92	0.051	.
1	IMZ 332	62.10	1.61	.	0.32	.	0.39	.	0.117	.	0.71	0.026	.	.	0.050	0.010	.	0.003	.	9.63	.	0.027
1	NCS DC28216	62.01	26.9	.	1.46	.	3.65	.	.	.	1.10	.	0.176	.	0.020	.	0.028	.	6.74	0.388	.	.
1	NCS DC11009a	61.96	15.13	.	0.914	.	0.375	.	0.093	.	0.364	.	0.947	.	0.024	0.027	.	0.212	.	4.92	.	0.447
1	GIOP-47	61.9	.	.	1.88	.	0.0151	.	0.0064	.	0.041	0.0782	.	(0.015)	.	0.0688	.	0.0199	.	2.809	.	0.0614
1	IMZ 333	61.87	1.65	.	0.33	.	0.34	.	0.11	.	0.73	0.034	.	.	0.057	0.008	.	0.001	.	10.07	.	0.026
1	GIOP-41	61.85	.	.	1.978	.	0.0368	.	0.0113	.	0.053	0.1078	.	0.018	.	0.1109	.	0.0335	.	3.043	.	0.0762
1	NCS DC28031	61.82	0.55	.	2.26	.	0.024	.	0.024	.	0.085	0.61	.	.	0.012	0.073	.	0.012	.	2.94	0.054	.
1	NCS DC18011	61.80	0.30	.	3.05	.	0.051	.	.	.	0.102	.	0.170	.	.	0.076	.	0.022	.	4.52	.	0.134
1	JSS 801-6	61.75	.	1.09	.	(0.014)	.	.	(0.032)	.	0.707	0.060	.	0.0093	1.95	.	0.051	.
1	NCS DC14033	61.73	1.51	.	0.48	.	0.11	.	0.056	.	0.055	0.027	.	.	0.0056	0.024	.	0.036	.	9.82	0.041	.
1	GIOP-42	61.7	.	.	1.896	.	0.0172	.	(0.0049)	.	0.045	0.0541	.	0.018	.	0.0618	.	0.0137	.	2.743	.	0.0674
1	GIOP-46	61.699	.	.	1.854	.	0.0159	.	(0.0056)	.	0.045	0.0685	.	(0.012)	.	0.0684	.	0.0152	.	3.064	.	0.0656
1	NCS DC28053	61.68	0.24	.	0.84	.	0.33	.	0.071	.	0.38	0.042	.	.	0.046	0.017	.	0.020	.	10.32	0.063	.
1	GIOP-121	61.609	.	.	2.174	.	0.0207	.	0.0093	.	0.049	0.1915	.	0.011	.	0.0629	.	0.0168	.	2.986	.	0.0588
1	ASCRM 034	61.59	.	1.19	.	0.029	.	0.012	.	0.040	.	0.141	.	0.0117	.	0.082	.	0.024	2.00	.	0.054	.
1	GIOP-82	61.58	.	.	1.255	.	0.02	.	0.0097	.	0.04	0.2102	.	0.0172	.	0.0524	.	0.0155	.	3.079	.	0.697
1	NCS DC28024	61.53	0.24	.	2.12	.	0.118	.	0.026	.	0.109	0.276	.	.	0.034	0.068	.	0.038	.	3.43	0.052	.
1	GIOP-25	61.5	.	.	3.58	.	(<0.05)	.	0.028	.	0.055	0.023	.	.	.	0.023	.	0.017	.	5.28	.	0.135
1	NCS DC73006	61.46	(0.35)	.	1.68	.	0.52	.	0.098	.	0.77	0.072	.	.	0.080	0.019	.	(0.0067)	.	6.65	1.12	.
1	IMZ 340	61.45	3.40	.	2.37	.	1.22	.	(0.020)	.	2.40	0.15	.	.	0.066	(0.002)	.	.	.	4.20	.	2.45
1	OREAS 406	61.44	.	.	1.14	.	0.157	.	0.019	.	(0.037)	.	0.039	.	(0.017)	0.085	.	(0.006)	.	7.96	.	0.047
1	ECRM 688-1	61.38	.	0.679	.	1.449	.	0.180	.	1.061	.	0.0457	.	0.333	.	0.337	.	(0.0468)	3.383	.	0.408	.
1	GIOP-14	61.36	.	.	3.6	0.039	.	.	.	5.27	.	0.07
1	NCS DC93023	61.34	29.68	.	0.45	.	0.64	.	0.018	.	(0.60)	0.056	.	.	0.012	0.036	.	0.494	.	12.36	.	0.064
1	GIOP-62	61.3	.	.	2.254	.	0.0628	.	0.0476	.	0.085	0.308	.	0.0209	.	0.0537	.	0.0348	.	4.282	.	0.1592
1	GIOP-115	61.28	.	.	1.748	.	0.2298	.	0.0205	.	0.1622	0.0166	.	0.0595	.	0.00882	.	0.0073	.	9.046	.	0.199
1	GIOP-51	61.126	.	.	2.096	.	0.0287	.	0.0114	.	0.049	0.274	.	0.0134	.	0.0665	.	0.0196	.	3.133	.	0.063
1	BAM 631-1	61.09	.	.	1.06	.	0.75	.	(0.04)	.	0.54	0.044	.	.	(0.04)	0.114	.	0.033	.	3.20	.	0.109
1	GIOP-124	61.051	.	.	2.529	.	0.0148	.	0.012	.	0.0679	0.0769	.	0.0193	.	0.0667	.	0.0178	.	3.535	.	0.0735
1	GIOP-59	61.04	.	.	2.501	.	0.0825	.	0.0765	.	0.096	0.638	.	0.0208	.	0.0516	.	0.0581	.	4.355	.	0.2088
1	NCS DC28030	60.82	0.21	.	2.27	.	0.035	.	0.022	.	0.112	0.298	.	.	0.026	0.073	.	0.041	.	3.45	0.056	.
1	CAN SCH-1	60.73	.	0.509	.	0.029	.	0.027	.	0.020	.	0.777	.	0.019	.	0.054	.	0.007	3.78	.	0.031	.
1	GIOP-18	60.64	.	.	2.4	0.056	.	.	.	4.74	.	0.04

#	Number	As	Ba	C	CO ₂	Cl	Co	Cr	Cr ₂ O ₂	Cu	Ni	Pb	V	V ₂ O ₅	Zn	Zr	LOI	Units	Other
	GIOP-56	.	.	.	0.014	0.007	0.0038	0.00237	.	4.076	10 g	
	GIOP-43	.	.	.	0.0088	.	0.0038	.	0.0027	3.167	10 g	
	NCS DC15005	0.0019	100 g	
	ASCRM 035	0.0079	0.0017	.	0.0398	0.0018	0.0048	.	0.0087	0.0033	0.0005	0.0024	.	.	0.0029	0.0023	4.02	10x10 g	Sn: 0.0011 Sr: 0.0009
	NCS DC28026	0.0013	.	.	.	0.001	0.0027	.	0.0015	0.0024	0.0004	.	.	.	0.0026	.	.	50 g	
	IRSID 611-1	100 g	
	USZ 27-99	0.013	.	.	0.030	0.008	.	.	.	(0.013)	.	(1.46)	100 g	
	SARM 132	100 g	
	GIOP-38	.	.	.	0.0124	.	0.0078	4.87	10 g	
	NCS DC28025	0.0011	.	.	.	0.0015	0.0038	.	0.0018	0.0033	0.0008	.	.	.	0.0026	.	.	50 g	
	IMZ 332	.	0.0036	0.012	.	.	0.005	.	0.0021	0.002	0.0016	(0.001)	.	.	0.0023	.	0.11	100 g	
	NCS DC28216	100 g	
	NCS DC11009a	0.011	.	0.128	.	0.0061	.	.	0.063	.	0.042	.	.	.	0.054	.	.	50 g	BaO: (0.71)
	GIOP-47	0.00263	6.309	10 g	
	IMZ 333	.	0.003	0.011	.	.	0.006	.	0.002	0.002	0.0015	0.001	.	.	0.0014	.	0.13	100 g	
	GIOP-41	.	.	.	0.0125	5.784	10 g	
	NCS DC28031	70 g	
	NCS DC18011	100 g	
	JSS 801-6	(0.005)	.	(0.002)	0.0033	.	(0.003)	100 g	
	NCS DC14033	.	.	.	0.0048	.	.	.	0.061	0.0023	100 g	
	GIOP-42	0.00222	.	0.0032	6.76	10 g	
	GIOP-46	0.0023	.	0.0027	6.385	10 g	
	NCS DC28053	70 g	
	GIOP-121	(0.0014)	(0.0056)	.	0.0088	(0.0015)	(0.0017)	.	(0.0016)	(0.0026)	(0.0012)	(0.001)	.	.	(0.0017)	(0.0021)	6.237	10 g	
	ASCRM 034	0.0011	0.0055	.	0.0110	0.0009	0.0022	.	0.0009	0.0015	0.0012	0.0021	.	.	0.0016	0.0021	4.76	10x10 g	Sn: 0.0005 Sr: 0.0013
	GIOP-82	.	.	.	0.0118	0.013	6.411	10 g	
	NCS DC28024	0.0011	.	.	.	0.0009	0.0054	.	0.0014	0.0027	0.0008	.	.	.	0.002	.	.	50 g	
	GIOP-25	2.72	10 g	
	NCS DC73006	0.0028	50 g	
	IMZ 340	(0.068)	0.30	100 g	
	OREAS 406	(0.001)	(0.00374)	.	(0.006)	(0.0009)	.	(0.002)	(0.0019)	(0.0058)	(0.00196)	(0.00114)	.	.	(0.00174)	(0.003)	2.69	10 g	
	ECRM 688-1	(0.0011)	.	.	.	0.0096	(0.002)	.	0.0023	0.0136	0.00025	0.135	.	.	0.0015	(0.0015)	.	100 g	
	GIOP-14	2.4	10 g	
	NCS DC93023	100 g	
	GIOP-62	0.0068	0.0075	.	0.0184	.	0.0143	0.02073	.	0.0064	.			

CRM		IRON ORE, chart 6 of 9										# = class, where 1 = CRM and 2 = RM										analysis listed in mass % except * which is mg/kg									
#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂										
1	VS R36	57.47	0.73	.	0.71	.	0.037	.	0.015	.	0.39	.	0.024	.	0.076	0.0138	0.0064	.	16.28	.	0.031										
1	NCS DC28081	57.41	1.89	.	5.11	.	0.34	.	0.150	.	0.142	.	0.228	.	0.045	0.054	0.018	.	7.31	.	0.230										
1	GIOP-86	57.26	.	.	2.657	.	0.1514	.	0.0107	.	0.1758	0.085	.	0.0184	.	0.03934	0.0139	.	5.752	.	0.1434										
1	GIOP-75	57.23	.	.	2.649	.	0.1564	.	0.01048	.	0.1778	0.0875	.	0.0182	.	0.0394	0.014	.	5.761	.	0.143										
1	GIOP-68	57.18	.	.	4.126	.	0.0414	.	0.0173	.	0.063	0.1027	.	0.0163	.	0.0555	0.0293	.	5.51	.	0.2228										
1	GIOP-61	57.14	.	.	2.523	.	0.1735	.	0.0194	.	0.068	0.228	.	0.0199	.	0.0426	0.0388	.	5.946	.	0.115										
1	JSS 821-1	57.05	.	1.24	.	0.159	.	0.0055	.	0.113	.	0.085	.	0.0095	.	0.0415	0.0108	2.28	.	0.0718	.										
1	ECRM 689-1	57.05	.	1.185	.	1.183	.	0.462	.	0.980	.	0.1196	.	0.638	.	0.0706	.	(5.4)	.	0.3264	.										
1	ASCRM 030	56.76	.	1.42	.	0.245	.	0.009	.	0.108	.	0.079	.	0.0170	.	0.038	0.021	2.71	.	0.089	.										
1	JSS 831-2	56.64	1.97	FeII: 21.82	1.05	.	0.061	.	.	2.09	.	0.501	.	0.082	.	0.153	0.0049	1.93	.	4.51	.										
1	NCS DC73005	56.60	20.50	.	0.99	.	1.36	.	0.071	.	3.62	0.076	.	.	0.058	0.017	2.44	.	11.48	0.043	.										
1	GIOP-142	56.58	.	.	3.032	.	0.2678	.	0.0109	.	0.218	0.0892	.	0.0126	.	0.0412	0.01404	.	6.704	.	0.1782										
1	NCS DC28212	56.29	26.9	.	2.53	.	8.04	.	.	.	1.96	.	0.289	.	.	0.032	0.197	.	8.86	.	0.208										
1	GIOP-137	56.285	.	.	6.029	.	0.966	.	0.0691	.	0.5292	0.04	.	0.2205	.	0.0579	0.0209	.	7.946	.	0.3815										
1	NCS DC28112	56.23	24.15	.	1.39	.	2.73	.	0.133	.	4.89	0.132	.	.	0.070	0.023	0.369	.	7.81	0.620	1.03										
1	NCS DC11018	56.02	7.78	.	2.20	.	9.89	.	0.038	.	2.87	.	0.355	.	0.057	0.058	0.023	.	4.50	.	0.108										
1	IMZ 313	55.85	0.68	.	1.13	.	0.079	.	0.030	.	0.31	0.03	.	0.23	0.031	0.0085	.	17.29	.	0.044											
1	NCS DC15002a	55.81	1.86	.	1.93	.	1.10	.	0.433	.	0.36	.	0.026	.	0.33	0.011	0.469	.	13.00	.	0.083										
1	VS R5/6	55.8	9.81	.	2.57	.	9.30	.	.	.	1.95	.	0.86	.	.	0.029	0.035	.	5.71	.	0.29										
1	NCS DC14013a	55.56	(22.60)	.	1.98	.	3.33	.	0.33	.	2.13	0.31	.	.	0.075	0.029	1.84	.	8.10	.	0.10										
1	NCS DC18012	55.51	9.04	.	5.54	.	0.42	.	0.069	.	0.67	.	0.455	.	.	0.376	0.023	.	7.62	.	0.129										
1	NCS DC19016	55.23	1.01	.	3.07	.	1.08	.	0.123	.	1.88	.	0.199	.	0.173	0.037	0.0087	.	6.43	.	7.69										
1	GIOP-136	55.22	.	.	6.493	.	1.055	.	0.0757	.	0.5767	0.0402	.	0.241	.	0.0578	0.0241	.	8.632	.	0.4166										
1	OREAS 404	55.14	.	.	2.97	.	0.102	.	(0.008)	.	(0.074)	.	(0.007)	.	(0.014)	0.151	0.032	.	7.88	.	0.385										
1	IMZ 343	55.09	6.37	.	0.74	.	10.93	.	0.037	.	1.21	0.0200	.	.	(0.040)	0.030	0.021	.	9.31	.	0.032										
1	NCS DC28225	54.96	10.7	.	2.93	.	11.49	.	.	.	0.98	.	0.171	.	.	0.050	0.032	.	5.89	.	0.152										
1	NCS DC18018	54.90	7.87	.	2.34	.	10.36	.	.	.	2.41	.	0.29	.	.	0.064	0.036	.	5.81	.	0.50										
1	NCS DC11004a	54.86	1.17	.	2.85	.	0.630	.	0.26	.	0.524	.	1.04	.	0.047	0.119	0.258	.	8.27	.	0.120										
1	VS 5405-90	54.83	.	.	2.04	.	.	.	0.33	.	0.29	0.62	.	.	.	0.034	0.018	.	16.23	.	0.092										
1	NCS DC11006a	54.74	3.90	.	1.48	.	1.02	.	0.214	.	0.657	.	1.31	.	0.048	0.036	0.439	.	8.53	.	0.154										
1	NCS DC18019	54.03	7.98	.	2.57	.	10.50	.	.	.	2.71	.	0.70	.	.	0.073	0.027	.	6.11	.	0.24										
1	NM 161.5	53.85	.	.	7.53	0.071	0.008	.	7.13	.	0.29										
1	IRSID 603-1	53.65	.	4.20	.	(0.91)	.	.	.	(0.2)	.	0.440	.	.	.	0.084	0.097	1.28	.	0.137	.										
1	GIOP-135	53.505	.	.	7.322	.	1.184	.	0.0825	.	0.655	0.0588	.	0.2743	.	0.05917	0.0191	.	9.633	.	0.4731										
1	NCS DC28034	53.42	15.27	.	0.57	.	0.31	.	0.086	.	11.21	0.065	.	.	0.25	0.018	0.192	.	5.22	0.044	.										

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂	
	Number	As	Ba	C	Cl	Co	Cr	Cr ₂ O ₃	Cu	Ni	Pb	V	V ₂ O ₅	Zn	Zr	LOI	Units	Other				
	VS R36	Insoluble Residue: 16.5	100 g					
	NCS DC28081	0.0014	0.032	.	0.0038	0.0027	.	50 g					
	GIOP-86	0.00336	.	0.0094	.	8.94	10 g			
	GIOP-75	0.00312	.	0.0092	.	8.954	10 g			
	GIOP-68	.	.	.	0.011	.	0.0051	0.00353	.	.	.	7.876	10 g			
	GIOP-61	.	.	.	0.0094	0.0042	.	8.961	10 g			
	JSS 821-1	0.0027	.	0.0007	0.0035	0.0006	0.0040	.	0.0074	.	9.16	70 g					
	ECRM 689-1	0.0103	.	.	0.0068	0.0195	0.1020	.	.	0.0042	.	.	100 g					
	ASCRM 030	0.0014	0.0034	.	0.0101	0.0014	0.0020	.	0.0016	0.0019	0.0008	0.0042	.	0.0096	0.0037	9.24	10x10 g	Sr: 0.0010				
	JSS 831-2	0.028	.	0.0068	0.0077	.	0.299	.	0.074	.	(0.11)	100 g					
	NCS DC73005	0.068	50 g				
	GIOP-142	(0.0015)	(0.0052)	.	(0.0035)	0.00182	0.00206	.	(0.0019)	0.002	(0.0038)	0.00499	.	0.00871	0.0054	8.368	10 g	Sr: 0.004				
	NCS DC28212	50 g				
	GIOP-137	(0.001)	0.0053	.	(0.0032)	(0.0017)	0.0051	.	(0.0019)	0.00175	(0.0026)	0.00726	.	0.00233	0.0079	3.111	10 g	Sr: 0.0056				
	NCS DC28112	0.167	0.527	0.037	.	.	70 g					
	NCS DC11018	0.0014	0.0044	.	0.0031	.	.	0.065	.	.	70 g					
	IMZ 313	(0.0008)	0.0017	0.031	(0.29)	0.0002	0.0067	.	0.0015	0.0024	0.0009	(0.001)	.	0.0028	.	-1.31	100 g					
	NCS DC15002a	0.23	0.134	.	0.319	.	.	0.161	.	.	50 g					
	VS R5/6	150 g					
	NCS DC14013a	0.035	0.40	.	(0.009)	.	.	0.062	.	.	50 g					
	NCS DC18012	100 g				
	NCS DC19016	0.010	.	0.34	.	0.021	.	.	0.51	0.033	.	.	100 g					
	GIOP-136	(0.001)	0.0056	.	0.0036	(0.0018)	0.00537	.	(0.0016)	0.00194	(0.003)	0.00768	.	0.00257	0.0087	3.266	10 g	Sr: 0.0053				
	OREAS 404	(0.00176)	(0.00312)	.	(0.00379)	.	.	0.0124	(0.0018)	(0.0031)	(0.0006)	(0.00422)	.	(0.0018)	(0.0107)	9.40	10 g	Sr: (23.6*)				
	IMZ 343	0.004	0.005	.	.	100 g					
	NCS DC28225	100 g				
	NCS DC18018	100 g				
	NCS DC11004a	0.096	(BaO: 0.86)	0.310	.	0.0054	.	.	0.066	.	0.101	.	.	0.144	.	.	50 g					
	VS 5405-90	0.23	.	.	0.089	.	.	50 g				Ge: 5.1*	
	NCS DC11006a	0.215	(BaO: 1.08)	0.227	.	0.0086	.	.	0.102	.	0.182	.	.	0.30	.	.	50 g					
	NCS DC18019	0.021	100 g				
	NM 161.5	100 g				
	IRSID 603-1	100 g				
	GIOP-135	(0.001)	0.0088	.	0.0034	(0.0017)	0.00614	.	(0.0013)	0.00248	(0.0023)	0.00914	.	0.00233	0.0095	3.562	10 g	Sr: 0.0058				
	NCS DC28034	70 g			B ₂ O ₃ : 3.62	

CRM IRON ORE, chart 8 of 9 # = class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂
1	IRSID 612-1	42.4	.	3.00	.	12.06	.	.	.	1.20	.	0.363	.	.	.	0.885	0.053	5.94	.	0.151	.
1	NCS DC18020	41.81	21.87	.	3.23	.	18.30	.	.	.	4.85	.	1.80	.	.	0.159	0.302	.	10.21	.	0.50
1	GIOP-131	41.08	.	.	12.77	.	2.23	.	0.151	.	1.231	0.0612	.	0.5184	.	0.0561	0.0329	.	17.619	.	0.8557
1	NCS DC73003	40.51	(14.5)	.	2.27	.	2.00	.	0.27	.	2.22	0.122	.	.	0.16	0.032	0.94	.	33.93	0.067	.
1	NCS DC28006	40.24	.	.	0.65	.	11.95	.	0.20	.	1.17	1.32	.	.	(0.006)	0.042	0.087	.	8.40	.	0.031
1	NCS DC14031a	39.79	18.53	.	3.29	.	7.63	.	0.72	.	3.62	0.15	.	0.54	0.078	0.601	.	16.54	.	0.171	
1	NCS DC28065	39.68	0.10	.	9.98	.	0.30	.	.	.	2.54	0.59	.	.	0.010	0.23	.	10.00	.	0.14	
1	GIOP-130	38.65	.	.	13.812	.	2.441	.	0.1649	.	1.348	0.0637	.	0.5737	.	0.0564	0.0369	.	19.22	.	0.9328
1	KZ 182-89	38.63	1.61	.	1.04	.	0.14	.	0.11	.	.	0.044	.	.	0.065	.	.	42.64	.	0.144	
1	VS R8/3	38.2	.	.	10.35	.	0.89	.	.	.	2.17	.	0.432	.	.	0.165	0.031	.	16.57	.	0.85
1	VS 5407-90	38.15	.	.	2.62	.	5.78	.	0.51	.	0.23	10.42	.	0.15	.	0.024	.	12.46	.	0.083	
1	IMZ 265/1	37.74	.	.	3.10	.	1.50	.	.	.	0.53	0.056	.	.	0.039	0.047	.	37.02	.	.	
1	GIOP-129	37.56	.	.	14.34	.	2.534	.	0.1711	.	1.397	0.0618	.	0.5898	.	0.05535	0.0382	.	19.931	.	0.968
1	IRSID 601-1	36.76	.	2.33	.	4.05	.	.	1.21	.	.	0.370	.	.	0.590	0.065	8.95	.	0.114	.	.
1	NCS DC13033	35.36	5.18	.	(0.11)	.	(0.13)	.	.	.	0.20	.	0.125	.	.	0.022	0.0064	.	48.50	.	0.007
1	KZ 183-89	35.16	1.32	.	1.66	.	.	.	0.35	.	.	0.046	.	.	0.019	0.7	.	41.56	.	0.073	
1	GIOP-108	34.73	.	.	0.1985	.	2.244	.	0.0119	.	1.889	0.0347	.	0.0242	.	0.0617	0.1366	.	46.93	.	(0.013)
1	VS R20/2	34.7	.	.	0.64	.	2.44	.	.	.	3.34	38.0	.	.	.
1	NCS DC28069	34.18	0.11	.	2.39	.	0.12	.	.	.	12.12	0.78	.	.	.	0.0015	0.082	.	18.28	.	0.030
1	NCS DC11013	34.07	20.15	.	0.74	.	0.99	.	0.165	.	2.86	.	0.093	.	0.065	0.054	0.118	.	48.27	.	0.043
1	VS R24/1	33.96	2.25	.	.	.	8.28	4.94	.	.	.
1	VS R24/2	33.73	.	.	1.52	.	2.12	.	.	.	8.29	0.0055	0.065	.	5.46	.	.
1	GIOP-111	33.35	.	.	0.2213	.	2.496	.	0.0157	.	1.977	0.0489	.	0.0216	.	0.0674	0.299	.	48.26	.	0.0141
1	GIOP-110	33.21	.	.	0.0893	.	1.417	.	0.0159	.	1.778	0.021	.	0.0152	.	0.0928	0.0042	.	50.09	.	0.0141
1	VS R9/2	33.01	40.0	.	0.64	.	2.55	.	.	.	10.9	.	.	.	0.0056	0.205	.	2.29	.	.	.
1	GIOP-98	32.63	.	.	0.1008	.	1.409	.	0.0121	.	1.875	0.0179	.	0.0163	.	0.1103	0.0273	.	50.88	.	0.138
1	GIOP-107	32.23	.	.	0.246	.	3.523	.	0.0135	.	1.257	0.037	.	0.0279	.	0.0497	0.1871	.	49.76	.	0.014
1	GIOP-113	32.11	.	.	0.5359	.	2.403	.	0.0218	.	2.343	0.1712	.	0.0276	.	0.0793	0.453	.	48.98	.	0.0298
1	BAM 627-2	31.77	.	.	4.49	.	15.67	.	.	.	1.57	0.250	.	.	0.661	0.114	.	9.24	.	0.225	
1	GIOP-99	31.7	.	.	0.2553	.	1.5672	.	0.039	.	1.967	0.0248	.	0.0197	.	0.1006	0.003	.	51.54	.	0.0278
1	GIOP-114	31.53	.	.	1.071	.	2.697	.	0.112	.	2.284	0.154	.	0.074	.	0.0761	0.969	.	48.26	.	0.0437
1	GIOP-105	31.04	.	.	0.438	.	1.841	.	0.075	.	2.289	0.0446	.	0.0238	.	0.0876	0.1507	.	51.51	.	0.0374
1	IRSID 607-1	30.89	.	2.48	.	13.74	.	.	0.77	.	.	0.254	.	.	0.529	0.050	3.07	.	0.123	.	.
1	GIOP-93	30.04	.	.	0.512	.	2.964	.	0.0228	.	3.394	0.0507	.	0.0431	.	0.0848	0.2003	.	50.32	.	0.0857

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂
	Number	As	Ba	CO ₂	Cl	Co	Cr	Cr ₂ O ₃	Cu	Ni	NiO	Pb	V	V ₂ O ₅	Zn	ZnO	Zr	LOI	Units	Other	
	IRSID 612-1	100 g	
	NCS DC18020	0.051	0.208	.	.	0.223	.	.	.	100 g		
	GIOP-131	(0.001)	0.0081	.	0.004	(0.0015)	0.009	.	(0.0017)	0.00236	.	(0.0016)	0.0166	.	0.00326	.	0.0173	5.405	10 g	Sr: 0.0086	
	NCS DC73003	0.028	50 g		
	NCS DC28006	100 g		
	NCS DC14031a	0.089	0.023	.	.	.	100 g		
	NCS DC28065	0.085	1.71	.	.	1.30	50 g		
	GIOP-130	0.0021	0.0088	.	(0.0034)	(0.0013)	0.0084	.	0.0028	0.0022	.	0.0026	0.0183	.	0.0035	.	0.0188	5.711	10 g	Sr: 0.0087	
	KZ 182-89	100 g		
	VS R8/3	(0.06)	.	2.53	.	.	0.67	75 g		
	VS 5407-90	.	0.74	4.16	0.15	.	.	.	0.20	.	.	.	50 g	Ge: 21.9*	
	IMZ 265/1	100 g		
	GIOP-129	(0.001)	0.0074	.	0.0043	0.00113	0.01	.	0.0026	0.0026	.	(0.0027)	0.0187	.	0.0033	.	0.01952	5.916	10 g	Sr: 0.0112	
	IRSID 601-1	100 g		
	NCS DC13033	50 g		
	KZ 183-89	.	3.10	0.026	100 g	Ge: 36.6*	
	GIOP-108	(0.0042)	(0.0041)	.	(0.006)	(0.0029)	(0.0039)	.	(0.0046)	(0.0043)	.	(0.0038)	(0.001)	.	0.0042	.	(0.0019)	-1.22	10 g		
	VS R20/2	100 g		
	NCS DC28069	0.13	1.48	.	.	1.50	50 g		
	NCS DC11013	0.0003	0.0031	.	.	0.028	.	.	0.0045	.	.	.	70 g		
	VS R24/1	125 g	last	
	VS R24/2	100 or 125 g		
	GIOP-111	(0.0068)	(0.0032)	.	0.0109	(0.003)	(0.0041)	.	(0.0047)	(0.0036)	.	(0.0041)	(0.0014)	.	0.0055	.	(0.0017)	-1.069	10 g		
	GIOP-110	(0.0032)	(0.0046)	.	(0.0047)	(0.0032)	(0.0048)	.	(0.0055)	(0.0064)	.	(0.0022)	(0.001)	.	0.0031	.	(0.0015)	-1.17	10 g		
	VS R9/2	.	.	10.6	125 g		
	GIOP-98	(0.0044)	0.0067	.	(0.0045)	(0.0037)	(<0.01)	.	(0.0047)	(0.004)	.	(0.0062)	(0.001)	.	(0.0041)	.	(0.002)	-1.217	10 g		
	GIOP-107	(0.0044)	(0.0047)	.	0.0058	(0.0028)	(0.0026)	.	(0.0045)	(0.0032)	.	(0.0032)	(0.0017)	.	0.0047	.	(0.0022)	-1.224	10 g		
	GIOP-113	(0.0033)	(0.0042)	.	0.0117	0.0034	(0.0019)	.	(0.0048)	(0.0048)	.	(0.0042)	(0.0021)	.	0.0107	.	(0.0021)	-0.719	10 g		
	BAM 627-2	0.020	0.018	100 g		
	GIOP-99	(0.0055)	(0.0041)	.	(0.0045)	(0.0032)	(0.0046)	.	(0.0051)	(0.003)	.	(0.0032)	(0.0016)	.	(0.0036)	.	(0.0023)	-0.984	10 g		
	GIOP-114	0.019	0.0063	.	0.0102	(0.0039)	(0.0028)	.	0.0208	(0.0046)	.	0.0455	(0.0017)	.	0.1657	.	(0.0038)	-0.349	10 g		
	GIOP-105	(0.004)	0.0077	.	0.0078	(0.0032)	(0.0036)	.	(0.004)	(0.003)	.	(0.0026)	(0.0023)	.	(0.0049)	.	(0.0021)	-0.997	10 g		
	IRSID 607-1	100 g		
	GIOP-93	.	.	.	0.0096	0.0063	0.0144	.	0.0098	0.0153	0.019	.	.	-0.686	10 g		

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂
---	--------	----	-----	----	--------------------------------	----	-----	---	------------------	----	-----	----	-----	----	-------------------	---	---	----	------------------	----	------------------

CRM IRON ORE, chart 9 of 9

= class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂
1	IMZ 266/1	29.04	.	.	3.13	.	3.42	.	.	.	0.95	.	0.078	.	.	0.030	0.10	.	44.94	.	.
1	GIOP-104	29.83	.	.	0.526	.	2.168	.	0.0409	.	2.535	0.0762	.	0.0235	.	0.1065	0.2414	.	52.59	.	0.0283
1	GIOP-112	29.46	.	.	0.405	.	2.047	.	0.0267	.	2.323	0.0678	.	0.0248	.	0.0876	0.3007	.	53.57	.	0.0207
1	GIOP-97	28.234	.	.	0.746	.	3.028	.	0.0522	.	2.093	0.0742	.	0.0552	.	0.0396	0.554	.	54.4	.	0.0279
1	VS R39	28.03	.	.	3.92	.	1.69	.	1.29	.	1.97	.	0.069	.	0.083	0.073	0.245	.	49.1	.	0.155
1	GIOP-96	27.442	.	.	0.723	.	2.884	.	0.051	.	2.819	0.107	.	0.038	.	0.0507	0.94	.	54.38	.	0.0289
1	GIOP-103	27.186	.	.	0.722	.	3.065	.	0.0476	.	2.368	0.0909	.	0.0496	.	0.0474	0.768	.	55.26	.	0.0278
1	GIOP-102	25.604	.	.	2.051	.	3.748	.	0.04997	.	3.668	0.3268	.	0.071	.	0.0758	1.297	.	53.35	.	0.0832
1	NCS DC28071	25.15	20.15	.	6.68	.	11.80	.	.	.	12.48	0.54	.	.	.	0.017	0.22	.	29.18	.	0.17
1	GIOP-95	24.215	34.86	.	1.259	.	4.804	.	0.0806	.	4.374	0.2045	.	0.049	.	0.066	0.497	.	54.85	.	0.0584
1	ECRM 651-1	23.85	.	2.25	.	16.15	.	0.27	.	1.04	.	0.97	.	0.05	.	0.35	0.40	3.46	.	0.10	.
1	GIOP-139	22.43	.	.	4.974	.	1.316	.	2.617	.	1.978	0.068	.	0.5068	.	0.0995	0.39	.	53.76	.	0.1922
1	NCS DC73001	20.17	(7.5)	.	3.57	.	2.84	.	0.53	.	1.68	0.168	.	.	0.28	0.045	0.051	.	60.86	0.085	.
1	IMZ 267/1	19.75	.	.	4.05	.	4.73	.	.	.	1.22	(0.16)	0.16	.	.	0.030	0.17	.	53.72	.	.
1	NCS DC28070	19.43	10.20	.	7.10	.	20.02	.	.	.	11.58	0.50	.	.	.	0.024	0.35	.	28.78	.	0.24
1	NCS DC28068	16.83	0.10	.	2.06	.	0.16	.	.	.	21.32	0.40	.	.	.	0.0018	0.025	.	34.93	.	0.043
1	GIOP-128	16.494	.	.	34.64	.	0.1797	.	0.1797	.	0.035	0.0336	.	0.0194	.	0.012	0.0518	.	21.726	.	1.581
1	NCS DC28066	12.97	0.33	.	1.40	.	0.41	.	.	.	19.98	0.23	.	.	.	0.0017	0.012	.	46.34	.	0.024
1	GIOP-123	12.036	.	.	25.46	.	4.665	.	0.3153	.	2.593	0.0795	.	1.102	.	0.0482	0.0672	.	36.33	.	1.754
1	GIOP-120	2.826	.	.	0.03	.	3.613	.	(0.006)	.	5.57	0.0173	.	0.036	.	0.1296	0.00451	.	85.75	.	(0.013)

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂	
	Number	As	Ba	Cl	Co	Cr	Cu	Ni	Pb	V	V ₂ O ₅	Zn	Zr	LOI	Units	Other						
	IMZ 266/1	100 g							
	GIOP-104	(0.006)	(0.0047)	0.0099	(0.0031)	(0.0013)	(0.0043)	(0.0045)	(0.0042)	(0.0016)	.	0.006	(0.0017)	-0.992	10 g							
	GIOP-112	(0.0063)	(0.0038)	0.0104	(0.0033)	(0.0016)	(0.0045)	(0.0031)	(0.0045)	(0.0013)	.	0.0061	(0.002)	-0.922	10 g							
	GIOP-97	(0.0085)	(0.0037)	0.0095	(0.003)	(0.0011)	0.0062	(0.004)	(0.0041)	(0.0012)	.	0.006	(0.0021)	-0.92	10 g							
	VS R39	23.1% Iron Magnetite	100 g Fe ₂ O ₃ : 14.96							
	GIOP-96	(0.0081)	(0.0059)	0.0201	(0.0032)	(0.0034)	(0.0064)	(0.0046)	(0.004)	(0.0018)	.	0.0076	(0.0027)	-0.454	10 g							
	GIOP-103	(0.008)	(0.0041)	0.0155	(0.0034)	(0.0022)	0.0067	(0.004)	(0.0036)	(0.0018)	.	0.0072	(0.0028)	-0.705	10 g							
	GIOP-102	(0.008)	(0.0035)	0.0244	0.004	(0.0046)	0.0075	(0.0068)	(0.0046)	0.0037	.	0.0199	(0.0019)	-0.194	10 g							
	NCS DC28071	.	.	.	0.066	1.16	.	1.41	50 g							
	GIOP-95	(0.0084)	(0.002)	0.0184	(0.0031)	(0.0031)	0.005	(0.0055)	(0.0056)	(0.003)	.	0.0087	(0.002)	-0.546	10 g						last	
	ECRM 651-1	100 g							
	GIOP-139	0.0075	0.0183	(0.006)	(0.0017)	(0.0023)	0.0041	(0.0019)	0.0054	0.00332	.	0.155	0.0081	1.63	10 g						Sr: 0.0101	
	NCS DC73001	0.0028	50 g							
	IMZ 267/1	100 g							
	NCS DC28070	.	.	.	0.055	0.81	.	1.07	50 g							
	NCS DC28068	.	.	.	0.064	0.81	.	1.74	50 g							
	GIOP-128	0.0034	(0.0063)	0.0085	(0.0095)	0.0151	(0.004)	(0.0038)	(0.0066)	0.0424	.	(0.0033)	0.049	17.964	10 g						Sr: 0.0047	
	NCS DC28066	.	.	.	0.037	0.58	.	2.00	50 g							
	GIOP-123	(0.0015)	0.0123	(0.0047)	(0.0015)	0.017	(0.0032)	(0.0018)	(0.0021)	0.03282	.	0.0058	0.0336	9.693	10 g						Sr: 0.0134	
	GIOP-120	(0.0034)	(0.008)	0.009	(0.0044)	0.0192	(0.0054)	0.0119	(0.0022)	(0.0015)	.	(0.0081)	(0.001)	0.659	10 g							

CRM COARSE AND RAW IRON ORE

2 kg of raw, coarse material

Number	Fe	Al ₂ O ₃	CaO	K ₂ O	MgO	Mn	Na	P	S	SiO ₂	Sr	TiO ₂	LOI
GIOC-10	61.30	2.12	0.023	0.009	0.052	0.262	(0.012)	0.066	0.021	3.04	(0.002)	0.068	6.52
GIOC-6	61.26	2.17	0.021	(0.008)	0.050	0.263	(0.015)	0.068	(0.020)	3.10	(0.003)	0.067	6.50
GIOC-11	60.13	2.03	0.046	0.010	0.089	0.259	(0.011)	0.070	0.026	3.48	0.009	0.089	7.67
GIOC-14	60.10	1.21	0.027	0.009	0.076	0.154	(0.012)	0.074	0.041	5.78	(0.002)	0.081	6.38
GIOC-12	58.59	1.94	0.037	0.020	0.089	0.113	(0.015)	0.054	0.031	3.90	(0.002)	0.170	9.70
GIOC-16	57.72	2.69	0.041	0.040	0.096	0.537	(0.016)	0.069	0.026	5.13	(0.002)	0.183	8.30
GIOC-9	57.48	2.39	0.131	0.010	0.138	0.150	(0.012)	0.044	0.016	5.43	0.041	0.146	9.22
GIOC-15	57.43	3.40	0.047	0.021	0.080	0.361	(0.011)	0.117	0.068	4.24	(0.002)	0.166	9.01
GIOC-13	57.38	4.15	0.017	0.021	0.098	0.245	(0.010)	0.068	0.016	4.42	(0.002)	0.153	8.57
GIOC-8	57.28	2.42	0.120	0.006	0.145	0.072	(0.011)	0.040	0.014	5.38	0.051	0.147	9.66

Number	As	Ba	Cl	Co	Cr	Cu	Ni	Pb	Sn	V	Zn	Zr
GIOC-10	(0.001)	(0.007)	0.010	(0.002)	(0.003)	(0.003)	(0.002)	(0.003)	(0.001)	(0.001)	(0.002)	(0.002)
GIOC-6	(0.008)	(0.012)	(0.013)	(0.003)	(0.006)	(0.015)	(0.013)	(0.002)	(0.002)	(0.001)	(0.004)	(0.003)
GIOC-11	0.007	(0.006)	0.008	(0.002)	(0.002)	(0.002)	(0.002)	(0.002)	(0.001)	(0.002)	(0.003)	(0.003)
GIOC-14	0.022	(0.005)	(0.005)	(0.002)	0.004	(0.003)	(0.003)	(0.003)	(0.002)	0.004	(0.003)	(0.002)
GIOC-12	0.011	(0.004)	(0.005)	(0.005)	0.007	(0.004)	(0.005)	(0.003)	(0.001)	0.007	(0.002)	(0.004)
GIOC-16	(0.002)	(0.007)	0.007	(0.003)	(0.003)	(0.003)	(0.003)	(0.003)	(0.001)	0.004	(0.004)	(0.005)
GIOC-9	0.002	(0.003)	(0.004)	(0.001)	(0.002)	(0.001)	(0.001)	(0.002)	(0.002)	0.004	0.007	(0.005)
GIOC-15	0.007	(0.005)	0.008	(0.002)	(0.002)	(0.003)	(0.003)	(0.002)	(0.001)	0.003	(0.003)	0.007
GIOC-13	0.005	(0.003)	(0.004)	(0.002)	0.008	(0.003)	(0.003)	(0.003)	(0.001)	(0.003)	0.004	(0.004)
GIOC-8	0.002	(0.002)	(0.004)	(0.001)	(0.002)	(0.001)	(0.002)	(0.002)	(0.006)	(0.003)	0.007	(0.005)

IRON ORE SINTER

= class, where 1 = CRM and 2 = RM analysis listed in mass %

# Number	Fe	FeO	Al	Al ₂ O ₃	C	CO ₂	Ca	CaO	Cr ₂ O ₃	Cu	CuO	F	K	K ₂ O	Mg	MgO	LOI 900°C
2 DH 5630	60.62	4.86	.	1.134	.	.	.	6.99	0.040	.	0.654	.
2 DH 5631	58.54	5.41	.	1.43	.	.	.	6.28	0.247	.	2.01	.
2 DH 5628	57.85	7.21	.	1.466	.	.	.	9.39	0.039	0.051	.	0.897	.
2 DH 5629	57.78	7.12	.	1.453	.	.	.	9.38	0.040	0.050	.	0.919	.
1 NCS DC14203	57.63	10.80	.	1.37	.	.	.	8.17	.	0.0063	.	.	.	0.065	.	1.65	.
2 DH 5616	57.29	6.58	.	1.331	.	.	.	9.51	0.045	0.045	.	1.491	.
1 JSS 851-5	56.67	.	0.89	.	.	.	7.94	Cr:0.0163	0.0034	.	.	Fe II:	5.99	.	0.48	.	0.041
1 NCS DC28046	56.14	9.17	.	2.07	.	.	.	10.35	0.125	.	2.21	.
1 ECRM 683-1	56.06	.	1.30	.	.	.	5.70	Cr:0.018	(0.0022)	.	.	0.020	0.148	.	1.04	.	.
1 NCS DC14009a	55.58	20.06	.	2.38	.	.	.	3.62	0.017	0.316	.	5.99	.
1 NCS DC28046a	55.49	7.93	.	1.84	.	.	.	11.66	.	0.0034	.	.	.	0.045	.	2.83	.
1 NCS DC11024	55.37	(8.20)	.	2.19	.	.	.	10.76	0.082	.	2.14	.
2 BS 104	55.32	.	.	1.26	.	.	.	8.72	(0.15)	.	3.06	.
1 NCS DC28038	55.19	6.23	.	1.83	.	.	.	9.19	0.070	.	2.22	.
1 NCS DC28023a	53.10	7.49	.	2.76	.	.	.	11.78	0.079	.	2.69	.
2 DH 5632	55.03	4.06	.	1.281	.	.	.	10.79	0.174	.	2.070	.
1 BS 104a	54.8	.	.	1.04	0.22	.	.	10.5	0.14	.	1.24	.
1 BCS 377/6	54.78	.	0.783	.	.	.	5.74	Cr:0.0154	0.907	.	.
1 NCS DC14204	54.62	9.26	.	1.49	.	.	.	9.29	.	0.014	.	.	.	0.046	.	1.74	.
1 NCS DC28048	54.16	8.52	.	2.23	.	.	.	10.93	0.076	.	3.05	.
1 NCS DC28023b	53.74	8.52	.	3.05	As:0.020	.	Cr:0.021	9.67	.	0.017	.	.	.	0.145	.	3.45	.
1 NCS DC28050	53.26	9.53	.	2.24	.	.	.	11.31	0.084	.	2.70	.
1 NCS DC14202	52.77	6.55	.	2.54	.	.	.	11.33	.	0.012	.	.	.	0.078	.	2.02	.
1 NCS DC28049	52.16	8.06	.	2.17	.	.	.	13.05	0.082	.	1.63	.
1 NCS DC15007	51.63	12.85	.	2.01	.	.	.	15.79	.	0.0025	.	.	.	0.104	.	1.24	.
1 NCS DC14206	51.13	9.22	.	2.44	.	.	.	9.46	.	(0.007)	.	.	.	0.080	.	4.40	.
1 NCS DC28047	50.04	8.07	.	2.11	.	.	.	13.72	0.091	.	2.08	.
2 DH 5624	49.86	.	.	1.338	0.043	.	.	15.48	0.023	0.233	.	3.36	.
1 ECRM 676-1	39.76	.	3.40	.	.	.	12.78	0.10	0.43	.	1.16	.	.

continued analysis listed in mass % except * which is mg/kg

Number	Mn	MnO	Na	Na ₂ O	Ni*	NiO	P	P ₂ O ₅	PbO	S	Si	SiO ₂	SrO	Ti	TiO ₂	V	V ₂ O ₅	ZnO	Units
DH 5630	0.298	.	.	0.032	.	.	.	0.112	.	0.011	.	3.98	.	.	0.085	.	.	0.016	100 g
DH 5631	0.945	0.107	.	.	.	5.08	.	.	0.076	.	.	0.040	100 g
DH 5628	0.429	.	.	0.026	.	.	.	0.129	.	0.011	.	4.79	.	.	0.109	.	.	0.067	100 g
DH 5629	0.426	.	.	0.026	.	.	.	0.129	.	0.011	.	4.80	0.008	.	0.108	.	.	0.089	100 g
NCS DC14203	0.174	.	.	0.046	.	.	0.102	.	.	0.025	.	5.38	.	0.113	50 g
DH 5616	0.477	.	.	0.025	.	.	.	0.140	.	.	.	5.18	.	.	0.101	.	0.018	0.013	100 g
JSS 851-5	0.241	.	.	.	58	.	0.060	.	.	0.016	2.48	.	.	0.065	.	0.0084	.	Zn:0.0075	100 g
NCS DC28046	0.227	.	.	0.048	.	.	0.064	.	.	0.032	.	5.54	.	0.076	70 g
ECRM 683-1	0.462	.	0.045	.	.	.	0.148	.	.	.	3.38	.	.	0.097	.	0.026	.	Zn:0.010	100 g
NCS DC14009a	.	0.097	.	0.068	.	.	0.017	.	.	0.106	.	9.95	.	.	0.266	.	.	0.011	50 g
NCS DC28046a	.	0.289	.	0.034	.	.	0.045	.	.	0.040	.	4.85	.	.	0.109	.	.	0.0078	50 g
NCS DC11024	.	0.36	.	0.045	.	.	0.056	.	.	0.017	.	5.64	.	.	0.125	.	.	0.0062	70 g
BS 104	.	0.79	.	(0.06)	.	.	.	0.127	.	0.011	.	7.70	.	.	0.08	.	.	.	100 g
NCS DC28038	0.222	.	.	0.057	.	.	0.057	.	.	0.028	.	6.79	.	0.123	70 g
NCS DC28023a	.	0.740	.	0.049	.	.	0.059	.	.	0.042	.	6.49	.	.	0.144	.	.	.	50 g
DH 5632	0.708	0.104	.	0.059	.	5.55	.	.	0.068	.	.	0.026	100 g
BS 104a	.	1.06	.	0.022	.	.	.	0.101	.	0.015	.	7.97	.	.	0.094	.	.	17025	100 g
BCS 377/6	0.604	0.0586	.	Pb:0.1485	.	2.982	.	.	0.1001	.	0.0178	.	Zn:1.002	100 g
NCS DC14204	0.193	.	.	0.019	.	.	0.039	.	.	0.024	.	7.94	.	.	0.092	.	.	.	50 g
NCS DC28048	0.210	.	.	0.19	.	.	0.068	.	.	0.052	.	6.04	.	0.075	70 g
NCS DC28023b	.	0.185	.	0.090	.	.	0.036	.	Pb:0.012	0.022	.	7.11	.	.	0.290	.	.	0.018	50 g
NCS DC28050	0.286	.	.	0.44	.	.	0.049	.	.	0.075	.	6.24	.	0.082	70 g
NCS DC14202	0.199	.	.	0.033	.	.	0.060	.	.	0.033	.	7.51	.	0.062	50 g
NCS DC28049	0.440	.	.	0.38	.	.	0.024	.	.	0.096	.	6.92	.	0.067	70 g
NCS DC15007	.	0.115	.	0.035	.	.	0.036	.	.	0.072	.	7.61	.	.	0.127	.	.	.	100 g
NCS DC14206	0.179	.	.	0.040	.	.	0.066	.	.	0.059	.	8.58	.	0.094	50 g
NCS DC28047	0.390	.	.	0.53	.	.	0.028	.	.	0.125	.	7.60	.	0.067	70 g
DH 5624	1.170	.	.	0.053	.	0.003	.	0.082	.	0.051	.	6.84	0.013	.	0.082	.	0.005	0.004	100 g
ECRM 676-1	0.83	.	0.095	.	.	.	0.59	.	.	0.12	6.40	.	.	0.19	.	0.070	.	.	100 g

CRM

KAOLIN

NCS: 50 g units

UNS: 100 g units

Number	SiO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	TiO ₂	LOI
UNS KK	47.06	36.77	0.236	0.982	12.75	1.063	0.192	0.015	0.032	.	.	0.166	.
NCS DC60123a	45.30	37.70	0.064	0.35	15.26	0.042	0.021	0.0018	0.045	0.16	0.76	0.060	14.81
NCS DC60122a	43.41	34.77	0.038	1.50	13.24	0.78	0.069	0.0020	0.045	0.21	5.51	0.25	17.31

CRM KIMBERLITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %																	NCS: 70 g units			VS: 40 g units		
Number	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SO ₃	SiO ₂	TiO ₂	LOI					
NCS DC71312	3.73	(16.78)	12.64	3.71	.	(6.53)	(4.47)	0.49	17.56	.	(0.1)	0.30	.	0.68	35.88	0.71	20.73					
VS 2114-81	2.66	5.71	6.42	2.24	5.08	7.57	.	0.412	26.96	0.111	0.087	0.216	0.032	.	37.66	0.97	.					
continued analysis listed in mg/kg except % which is mass %																						
Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Cl%	Co	Cr	Cs	Cu	Dy	Er	Eu	F%	Ga	Gd			
NCS DC71312	(0.06)	3.5	(31.8)	(0.177)	1.3	(0.1)	0.46	127	(0.04)	40.0	795	5.2	26.2	2.6	(1.2)	1.6	(0.11)	7.1	4.7			
VS 2114-81	.	.	.	0.025%	1.4	0.068%			
Number	Ge	Hf	Hg	Ho	La	Li	Lu	Mn%	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se	Sm			
NCS DC71312	0.89	4.9	0.010	0.49	69.8	75.7	0.16	(0.09)	1.4	60.4	49.0	516	20.7	13.8	28.4	(0.22)	10.9	0.10	6.5			
VS 2114-81	0.106%	9.1	.	.			
Number	Sn	Sr	Ta	Tb	Th	Tm	U	V	W	Y	Yb	Zn	Zr									
NCS DC71312	1.7	262	3.9	0.54	10.8	0.17	2.2	86	2.4	11.6	1.1	190	182									
VS 2114-81	2.5	0.028%									

CRM KINZINGITE

analysis listed in mass %												100 g units					
Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	FeO	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂						
SARM 45	26.22	0.78	12.60	(10.0)	3.18	3.39	0.10	0.84	0.08	49.62	1.82						
continued analysis listed in mg/kg																	
Number	Ba	Ce	Co	Cr	Cu	Ga	Nb	Ni	Pb	Rb	Sr	Th	V	Y	Zn	Zr	
SARM 45	(900)	(100)	41	256	11	(35)	27	80	(20)	142	92	(21)	266	63	74	322	

CRM LATERITE - NICKEL ORE

analysis listed in mass %, ICP values by fusion ICP, C and S: <0.01% from IR combustion furnace, all others fusion XRF including Cl: <50 ppm																	10g or 1kg	
Number	Ni	Co	Al ₂ O ₃	C	CaO	Cr ₂ O ₃	Cu	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	SiO ₂	TiO ₂	Zn	LOI
OREAS 195	2.94	0.0477	3.13	0.08	0.390	0.958	<0.0050	18.29	<0.01	19.01	0.288	0.034	<0.01	<0.01	44.00	0.037	0.0300	9.71
OREAS 195 ICP	2.89	0.0465	3.07	.	0.397	0.938	(0.0050)	18.16	<0.1	18.88	0.285	(0.03)	<0.01	<0.05	43.30	0.037	0.0293	.
OREAS 194	2.13	0.0428	2.74	0.07	0.311	0.819	(0.0040)	16.47	<0.01	22.83	0.261	(0.03)	<0.01	<0.01	43.02	0.035	0.0174	10.53
OREAS 194 ICP	2.10	0.0424	2.73	.	0.32	0.814	0.0041	16.42	<0.01	22.77	0.262	0.027	<0.01	<0.05	42.90	0.033	0.0184	.
OREAS 193	1.93	0.0495	3.08	0.07	0.362	0.962	<0.0050	19.51	<0.01	20.25	0.317	(0.03)	0.012	<0.01	42.72	0.053	0.0219	9.87
OREAS 193 ICP	1.91	0.0483	3.05	.	0.373	0.956	(0.0040)	19.49	(0.08)	20.26	0.316	0.030	<0.02	<0.05	42.49	0.051	0.0199	.
OREAS 192	1.77	0.0404	2.76	0.07	0.313	0.913	<0.0050	18.10	<0.01	21.32	0.277	0.028	<0.01	(0.004)	43.58	0.036	0.0176	10.17
OREAS 192 ICP	1.75	0.0398	2.75	.	0.316	0.910	(0.0038)	18.14	<0.1	21.26	0.278	0.022	<0.02	<0.02	43.45	0.033	0.0193	.
OREAS 191	1.75	0.0665	4.27	0.09	0.276	1.22	(0.0050)	24.86	<0.01	10.06	0.397	(0.02)	<0.01	<0.01	47.97	0.052	0.0302	8.10
OREAS 191 ICP	1.73	0.0652	4.19	.	0.287	1.21	(0.0050)	24.63	(0.1)	9.95	0.397	0.018	<0.02	<0.05	47.67	0.050	0.0297	.
OREAS 190	1.64	0.0889	6.00	0.07	0.133	1.73	(0.0070)	35.48	<0.01	6.91	0.577	(0.02)	<0.01	<0.01	38.22	0.064	0.0353	8.38
OREAS 190 ICP	1.62	0.0875	5.86	.	0.133	1.71	0.0068	35.40	<0.01	6.85	0.574	(0.01)	<0.02	<0.02	38.06	0.062	0.0327	.
OREAS 189	1.48	0.0326	2.09	0.10	0.326	0.765	<0.0050	15.04	<0.01	23.09	0.227	(0.03)	<0.01	<0.01	46.20	0.029	0.0125	10.13
OREAS 189 ICP	1.47	0.0327	2.08	.	0.328	0.764	(0.0030)	14.94	(0.08)	23.06	0.228	0.021	<0.02	<0.05	46.08	0.026	0.0103	.
OREAS 187	1.37	0.0636	2.80	0.11	0.341	0.987	(0.0040)	19.45	<0.01	17.99	0.356	<0.03	<0.01	<0.01	46.66	0.033	0.0196	9.27
OREAS 187 ICP	1.37	0.0629	2.77	.	0.352	0.987	<0.0050	19.40	<0.1	17.96	0.358	<0.03	<0.02	<0.05	46.37	(0.03)	0.0190	.
OREAS 186	1.23	0.0692	5.19	0.07	0.562	1.42	0.0061	32.04	<0.01	4.89	0.522	(0.02)	(0.01)	<0.01	46.29	0.069	0.0265	6.83
OREAS 186 ICP	1.22	0.0680	5.11	.	0.564	1.41	0.0057	31.72	<0.1	4.82	0.519	<0.01	<0.02	<0.05	46.24	0.070	0.0276	.
OREAS 185	1.14	0.0388	2.48	0.10	0.385	0.914	<0.0050	18.42	<0.01	20.22	0.297	0.027	<0.01	<0.01	45.93	0.033	0.0143	9.61
OREAS 185 ICP	1.12	0.0385	2.47	.	0.39	0.91	<0.0050	18.27	<0.01	20.17	0.295	0.024	<0.02	<0.05	45.58	0.031	0.0128	.
OREAS 184	1.02	0.0903	4.62	0.07	0.216	1.75	0.0070	39.30	<0.01	3.05	0.676	<0.01	0.017	<0.01	42.25	0.060	0.0278	6.24
OREAS 184 ICP	1.02	0.0899	4.58	.	0.231	1.75	0.0060	39.42	<0.1	3.00	0.678	<0.01	(0.02)	<0.05	42.19	0.058	0.0287	.
OREAS 183	0.995	0.0225	1.60	0.22	0.710	0.653	<0.0030	12.73	<0.01	27.31	0.180	(0.03)	0.005	<0.01	44.49	0.023	0.0078	10.90
OREAS 183 ICP	0.983	0.0222	1.60	.	0.72	0.651	0.0021	12.72	<0.1	27.43	0.181	0.030	<0.01	<0.02	44.13	0.020	0.0082	.
OREAS 182	0.707	0.0728	4.07	0.09	0.251	1.29	0.0052	29.40	<0.01	9.16	0.580	0.019	0.010	0.006	46.77	0.053	0.0181	7.14
OREAS 182 ICP	0.706	0.0723	4.02	.	0.253	1.28	0.0049	29.62	<0.1	9.12	0.587	0.014	<0.02	<0.05	46.54	0.051	0.0189	.

RM LEAD BASILICATE

analysis listed in mass %										25 or 100 g units
Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	PbO	SiO ₂	TiO ₂	LOI
CERAM AN28	2.46	0.05	0.018	0.05	<0.01	0.05	64.33	32.76	<0.01	0.15

CRM LEAD ORE TAILINGS WITH EXTENSIVE ANALYSIS

analysis listed mass %													* BCS 362 lists AQUA REGIA results where indicated			GBW: 50 g units		BCS: 100 g units	
Number	Al ₂ O ₃	CaO	Cu	F	Fe ₂ O ₃	K ₂ O	MgO	MnO	Mn ₃ O ₄	Na ₂ O	Pb	PbO	S	SiO ₂	SrO	TiO ₂	Zn	ZnO	LOI
GBW 07235	12.88	19.51	0.20	0.27	4.37	1.42	1.62	1.40	.	1.61	4.17	.	0.86	43.63	.	0.53	0.062	.	.
GBW 07236	8.95	34.56	0.035	0.23	3.79	0.82	2.06	1.53	.	0.066	0.61	.	0.38	30.51	.	0.44	0.092	.	.
BCS 362 *	0.667	44.21	0.0056*	.	0.483	0.14	0.068	.	0.829	0.084	2.30*	2.63	1.48	9.03	0.034	0.047	2.03*	2.59	32.81

continued analysis listed in mg/kg

Number	Ag	As	Bi	Cd	Ce	Cr	Cs	Dy	Eu	Er	Ga	Gd	Ge	Ho	In	La	Li	Lu
GBW 07235	14.7	85.1	15.6	3.2	78.3	(29)	(6)	3.0	1.2	1.5	16.7	3.7	0.90	0.61	0.12	40.5	(19)	0.24
GBW 07236	5.6	43.2	12.5	2.6	66.8	(41)	(2.3)	3.1	0.82	1.6	11.7	3.6	0.93	0.65	0.09	31.2	(18)	0.25
BCS 362 *	.	30*	.	200*	.	11*

Number	Mo	Nd	Ni	Pr	Rb	Sb	Sc	Se	Sm	Sr	Tb	Te	Th	Tl	Tm	W	Y	Yb	pH
GBW 07235	1.6	28.2	27.7	8.1	(55)	39.3	7.5	1.7	5.1	3.0	0.58	3.9	10.2	0.43	0.23	17.6	15.4	1.5	.
GBW 07236	1.3	23.4	34.5	6.2	(74)	12.0	8.1	0.81	4.6	2.9	0.60	1.2	10.5	1.0	0.26	30.6	16.2	1.7	.
BCS 362 *	.	.	12*	8.14*

CRM LEAD ORE

analysis listed in mass %											100 g units
Number	Pb	Ag	Cd	Cu	Fe	Ba	Re	S	Zn	Zr	
KZ 2890-84	61.0	0.01267	0.016	4.99	.	.	0.00214	.	1.85	.	
KZ 6586-93	3.5	0.0019	.	0.013	2.03	0.38	.	0.55	0.045	0.019	
KZ 5177-90	1.84	0.00181	.	.	.	10.3	.	2.96	.	.	

CRM LEAD ORE

analysis listed in mass %														25 g units	
Number	Ag	Al ₂ O ₃	As	Bi	CaO	Cd	Cu	Fe	MgO	Mn	Pb	S	Sb	SiO ₂	Zn
NCS DC28116	0.022	2.56	0.068	0.085	17.16	0.0097	0.85	6.78	1.28	0.029	15.09	19.26	0.0084	7.92	1.44

CRM LIMESTONE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

50 g units

Number	CaO	MgO	CO ₂	SiO ₂	LOI	Al ₂ O ₃	Org.C	FeO	T.Fe ₂ O ₃	H ₂ O ⁻	H ₂ O ⁺	K ₂ O	MnO	Na ₂ O	P ₂ O ₅	SO ₃	Ti%	TiO ₂
NCS DC70303	55.49	0.24	43.10	0.30	43.30	0.15	.	0.007	0.070	(0.06)	0.23	0.012	0.030	0.014	0.023	0.011	0.0042	0.007
NCS DC70304	54.08	1.42	43.13	1.08	42.64	0.18	(0.01)	0.09	0.222	(0.05)	0.14	0.043	0.004	0.015	0.005	0.014	0.0042	0.007
NCS DC70307	53.83	0.75	42.58	1.28	42.75	0.29	(0.12)	0.06	0.155	(0.14)	0.39	0.035	0.011	0.020	0.009	0.058	0.0174	0.029
NCS DC70306	48.16	1.45	38.69	6.27	39.07	1.13	(0.17)	0.49	0.73	(0.15)	0.52	0.40	0.089	0.05	0.121	0.98	0.0288	0.048
NCS DC70301	47.89	6.76	44.39	0.55	43.92	0.17	(0.03)	0.15	0.193	(0.20)	0.37	0.043	0.009	0.022	0.008	0.017	0.0066	0.011
NCS DC70309	43.76	1.36	35.52	11.07	36.57	3.03	(0.76)	0.79	1.77	(0.37)	0.97	0.88	0.041	0.17	0.094	1.18	0.258	0.430
NCS DC70302	41.95	11.62	44.89	0.72	44.75	0.22	(0.03)	0.16	0.205	(0.20)	0.31	0.052	0.009	0.029	0.014	0.013	0.0132	0.022
NCS DC70308	38.08	14.96	45.62	1.17	44.61	0.18	(0.04)	0.05	0.448	(0.17)	0.42	0.026	0.027	0.030	0.009	0.041	0.0054	0.009
NCS DC70305	30.93	20.14	45.58	1.15	45.73	0.29	(0.07)	0.07	0.17	(0.07)	0.39	0.16	0.012	0.036	0.035	0.33	0.0078	0.013

analysis listed in mg/kg except % which is mass %

Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	Gd
NCS DC70303	0.016	0.78	(1.3)	8.0	0.09	0.011	0.4	0.59	2.2	50	(0.5)	3.8	0.13	2.2	0.51	0.50	0.078	60	0.3	0.39
NCS DC70304	(0.013)	0.17	(1.47)	4.9	0.06	0.016	(0.2)	0.05	1.3	28	2.6	54	0.10	2.1	0.09	0.06	0.025	71	0.3	0.10
NCS DC70307	0.029	1.3	(3.1)	18.8	0.15	0.022	0.4	0.39	6.3	60	0.34	10.3	0.14	2.9	1.01	1.20	0.078	92	0.4	0.56
NCS DC70306	0.019	3.7	(3.7)	1.33%	0.30	0.058	(0.5)	0.04	8.1	77	1.9	8.1	0.75	8.3	0.52	0.31	0.30	835	1.6	0.69
NCS DC70301	0.020	0.50	(1.9)	9.7	0.08	0.015	(0.2)	0.10	1.4	34	0.45	4.8	0.07	2.2	0.12	0.09	0.037	76	0.3	0.13
NCS DC70309	0.045	2.2	(14.8)	101	0.56	0.050	0.5	0.15	26.0	96	7.0	34.0	1.98	18.7	1.39	0.75	0.53	454	3.7	1.81
NCS DC70302	0.021	0.29	(2.2)	11.6	0.12	0.020	(0.3)	0.09	1.9	34	0.5	5.6	0.09	2.2	0.15	0.12	0.052	91	0.33	0.16
NCS DC70308	0.035	5.5	(2.3)	10.6	0.15	0.012	0.9	0.39	1.5	123	0.5	9.7	0.10	2.9	0.20	0.15	0.049	179	0.4	0.19
NCS DC70305	(0.016)	0.96	(6.4)	0.52%	0.08	0.025	6.1	0.02	2.5	343	0.52	3.4	0.13	2.8	0.17	0.10	0.14	459	0.31	0.22

Number	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mn	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	Sb
NCS DC70303	0.10	12.4	0.007	0.13	(0.5)	(0.03)	2.6	2.7	0.13	232	0.18	0.34	1.80	(4.1)	99	1.4	0.49	0.6	0.15
NCS DC70304	0.12	0.10	0.003	0.022	(0.3)	(0.02)	0.78	(3.0)	0.010	31	0.14	0.3	0.61	50.5	22	1.7	0.15	1.6	0.03
NCS DC70307	(0.07)	88	0.017	0.27	(0.5)	(0.03)	3.5	3.3	0.53	95	0.35	0.9	2.66	4.8	40	4.0	0.74	1.2	0.17
NCS DC70306	0.16	0.3	(0.005)	0.11	(0.7)	(0.03)	4.1	5.1	0.047	689	0.60	1.0	3.42	6.6	527	5.6	0.94	10.6	0.09
NCS DC70301	0.11	1.4	0.004	0.034	(0.5)	(0.03)	0.9	2.9	0.019	70	0.35	0.3	0.66	5.8	35	2.9	0.22	1.2	0.08
NCS DC70309	0.28	1.2	0.026	0.25	(0.3)	(0.05)	12.5	11.8	0.091	318	0.60	6.5	11.0	19.2	410	5.9	2.84	19.2	0.27
NCS DC70302	0.12	2.1	0.015	0.034	(0.3)	(0.02)	1.2	3.1	0.022	70	0.26	0.46	0.86	4.3	62	3.9	0.24	1.6	0.09
NCS DC70308	0.11	3.1	0.031	0.046	(0.2)	(0.02)	0.9	3.0	0.035	209	0.80	0.4	0.89	5.6	40	7.8	0.21	1.1	0.59
NCS DC70305	0.12	0.13	0.006	0.034	(0.2)	(0.02)	1.3	3.1	0.015	93	0.19	0.4	1.10	2.9	155	2.9	0.28	2.6	0.06

Number	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W%	Y	Yb	Zn	Zr%
NCS DC70303	0.50	0.007	0.38	(0.7)	87	0.04	0.085	0.009	0.54	0.04	0.092	0.66	4.0	0.13	6.1	0.68	6.4	0.0443
NCS DC70304	0.4	(0.016)	0.11	(0.5)	173	0.03	0.020	0.009	0.24	(0.02)	0.021	0.17	3.6	0.13	0.7	0.063	3.3	0.00063
NCS DC70307	1.9	0.087	0.51	(0.5)	278	0.11	0.13	0.012	2.6	0.03	0.27	3.4	6.2	0.18	8.9	2.62	8.6	0.28
NCS DC70306	1.1	0.018	0.74	(0.6)	477	0.11	0.11	0.014	1.3	0.07	0.052	0.94	8.8	0.19	3.1	0.30	13.7	0.00092
NCS DC70301	0.40	0.014	0.15	(0.7)	227	(0.06)	0.022	0.008	0.25	0.022	0.018	0.59	4.8	0.17	1.2	0.11	8.1	0.00537
NCS DC70309	3.5	0.24	2.11	(1.1)	688	0.45	0.29	0.023	1.9	(0.06)	0.099	1.04	38.5	0.25	8.0	0.60	24.5	0.00470
NCS DC70302	0.5	0.015	0.19	(0.6)	191	0.05	0.031	0.008	0.25	0.023	0.020	0.39	5.0	0.18	1.4	0.13	9.5	0.00768
NCS DC70308	0.5	0.10	0.21	(0.9)	85	0.030	0.035	0.016	0.29	0.02	0.030	1.13	7.5	0.13	1.8	0.19	35.7	0.0113
NCS DC70305	0.4	0.013	0.26	(0.7)	158	0.06	0.032	0.008	0.45	0.04	0.017	0.70	5.1	0.17	1.1	0.10	3.6	0.00049

CRM LIMESTONE

Number	Al	Ca	Fe	Mg	Mn	P	S	Si	Ti	Units
IRSID 702-1	0.21	21.48	0.440	12.37	0.098	0.024	0.027	1.04	0.013	100 g

CRM LIMESTONE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

GUW, UL: 50 g GBW, NCS: 70 g others: 100 g

Number	CaO	Al ₂ O ₃	CO ₂	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI
SRM 1d	52.85	0.526	.	.	0.3191	.	.	0.1358	0.301	.	0.0109	0.0413	4.080	0.0306	41.57
UL CCH1	52.05	0.32	.	.	.	0.18	.	0.08	2.71	0.01	0.05	0.05	0.95	0.02	43.20
NCS DC73375	51.1	0.68	39.8	(0.06)	.	0.21	(0.4)	0.15	0.71	.	0.03	.	6.65	.	40.2
GUW KH2	47.64	2.365	37.51	(0.31)	0.855	.	(1.26)	0.437	0.656	0.0848	0.106	0.117	8.66	0.130	.
GUW KH3	47.6	2.40	37.6	0.32	0.87	.	(1.4)	0.43	0.65	0.080	0.10	0.117	8.59	0.130	38.6
VS 3193-85	38.5	1.87	.	1.89	.	2.48	.	0.49	6.04	0.28	0.48	0.027	12.35	0.09	.
VS 3193-89	38.46	1.89	.	1.8	.	2.43	.	0.49	5.97	0.28	0.46	0.030	12.40	0.093	.
GBW 07108	35.67	5.03	32.4	1.64	.	2.52	+(2.12)	0.78	5.19	.	(0.08)	.	15.60	.	34.1
JDo-1	33.96	0.0174	46.50	(0.071)	0.0222	0.0208	+0.395 -0.145	0.00232	18.47	0.00657	0.0129	0.0343	0.216	.	.
VS 813-89	29.48	0.43	45.6	0.36	0.47	.	.	0.35	20.75	0.050	0.07	0.011	2.69	0.025	.
VS 3192-89	21.56	5.48	.	1.8	.	3.15	.	2.75	12.89	0.30	1.38	0.060	19.92	0.28	.

analysis listed in mg/kg except % which is mass % and * which is ng/g

Number	Ag	As	Au*	B	Ba	Be	Bi	Br	Carbon%	Cd	Ce	Cl	Co	Cr	Cs	Cu
SRM 1d	.	.	.	BaO: 33	(0.1)	.	.	.	11.50	(0.3)	(4)	(130)	.	.	(0.4)	.
UL CCH1	(<1)	(1.3)	.	(10)	26	(<4)	(<5)	.	.	.	3.7	(370)	0.23	(5.4)	(0.13)	(<10)
NCS DC73375	(0.025)	0.66	.	(12)	9	0.14	0.032	(0.3)	(0.15 Org)	0.016	4.6	(24)	0.8	3.4	(0.10)	2.2
GUW KH2	.	.	.	46.3	18.1	.	(10)	14.2	12.2	8
GUW KH3	(0.14 Org)
VS 3193-85	.	.	.	(10)	60	(1)	18	.	2.2	13	(0.7)	4
VS 3193-89	.	.	.	50	16	.	2.3	9	.	4
GBW 07108	0.043	4.7	(0.94)	16	120	0.8	0.16	.	9.0 tot (0.11 org)	0.07	25	78	9	32	3.2	23
JDo-1	(0.0019)	(0.114)	trace	.	6.14	.	.	(0.79)	(12.760)	0.644	2.49	.	0.168	7.93	.	1.41
VS 813-89	.	.	.	5	30	1.3	3.0	6	.	8
VS 3192-89	.	.	.	400	27	.	12	30	.	29

Number	Dy	Er	Eu	F	Ga	Gd	Ge	Hf	Hg	Ho	I	In	La	Li	Li ₂ O	Lu	Mn	Mo
SRM 1d	(0.6)	(0.4)	(0.1)	(160)	(1)	(0.5)	.	.	.	(0.1)	.	.	(4)	.	.	.	209	.
UL CCH1	(0.27)	.	0.17	(367)	(<4)	(0.38)	(<10)	0.11	.	(0.4)	.	(<5)	5.0	0.03	.	.	.	(<5)
NCS DC73375	0.28	(0.17)	0.082	249	0.87	0.36	0.14	0.22	0.005	(0.045)	(0.1)	(0.02)	2.3	4.8	.	0.023	28	0.18
GUW KH2	.	.	0.47	610	(7)	.	0.127	.	.
GUW KH3	.	.	.	(610)	(21)	.	.	.
VS 3193-85	other impurities: 37.46%	(7)	.	.	(0.1)	.	.
VS 3193-89	8
GBW 07108	1.6	1.0	0.51	406	7.1	1.9	0.67	1.8	0.016	0.33	0.23	(0.04)	15	20	0.14	434	0.38	
JDo-1	0.814	.	0.176	246	.	(1.3)	.	(0.0897)	(0.0095)	(0.42)	.	.	7.93	(0.4)	.	0.0494	.	(0.78)
VS 813-89	.	.	.	200
VS 3192-89	13	40	.	.	.	0.08

Number	Nb	Nd	Ni	P	Pd	Pb	Pr	Pt	Ra	Rb	S	SO ₃ %	Sb	Sc	Se	Sm	Sn
SRM 1d	(0.7)	(3)	(4)	.	.	.	(0.6)	.	.	(6)	1028	(0.5)	(1)
UL CCH1	.	4.2	11	.	.	6	.	.	.	(2.6)	1283	.	(0.25)	0.45	.	0.77	(<5)
NCS DC73375	0.8	1.96	(4)	57	N:(68)	5	0.60	.	.	4.0	36	.	0.072	(0.7)	0.021	0.40	(0.5)
GUW KH2	.	.	20.3	.	.	(6)	22	.	.	2.83	.	.	.
GUW KH3	900	(0.2)
VS 3193-85	(8)	.	7	.	.	16	.	.	.	15	.	.	.	(2)	.	.	.
VS 3193-89	.	.	5	.	.	10	.	.	.	15	.	.	.	2.2	.	.	.
GBW 07108	6.6	12.0	18	226	.	18	3.4	.	.	32	(370)	.	0.43	6.0	0.09	2.4	(0.98)
JDo-1	(0.4)	5.25	2.90	.	trace	(0.95)	0.956	trace	.	(1.75)	(90.5)	.	(0.036)	0.136	(0.0468)	0.788	.
VS 813-89	.	.	5	.	.	8	.	.	2e-10	5	200
VS 3192-89	37	.	18	.	.	13	.	.	.	57	.	.	.	8	.	.	1.7

Number	Sr	SrO	Ta	Tb	Te	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn	ZnO	Zr
SRM 1d	.	303	.	(0.09)	.	(0.5)	.	.	.	(1)	(10)	.	(5)	(0.3)	.	22	.
UL CCH1	267	.	(0.03)	0.11	.	0.30	.	.	.	3.9	27	.	(7)	0.24	29	.	(35)
NCS DC73375	107	.	(0.05)	0.054	.	0.86	0.230	(0.03)	(0.024)	0.24	5.4	0.13	1.9	0.15	7	.	11
GUW KH2	532	2.08	.	.	.	(8)	22.9	.	.
GUW KH3
VS 3193-85	500	(2)	.	.	.	(1)	24	.	(9)	(1)	25	.	26
VS 3193-89	440	1.8	.	.	.	1.0	.	.	.	0.9	30	.	27
GBW 07108	913	.	0.42	0.35	(0.024)	4.1	0.1960	0.33	0.17	1.9	36	0.67	9.1	0.90	52	.	62
JDo-1	116	.	(0.009)	0.116	.	0.0429	.	(0.003)	(0.059)	0.858	3.14	.	10.3	0.323	35.4	.	6.21
VS 813-89	90	1.0	.	.	.	1.5	25	.	.	.	30	.	30
VS 3192-89	44	15	.	.	.	0.8	22	.	.	2.5	30	.	70

LIMESTONE and DOLOMITE

= class, where 1 = CRM and 2 = RM

f.SiO₂ = free SiO₂

#	Number	CaO	Al ₂ O ₃	Fe	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P	P ₂ O ₅	S	SO ₃	SiO ₂	f.SiO ₂	TiO ₂	LOI
1	NCS DC16006	65.20	0.885	.	0.46	0.19	4.55	0.013	0.021	0.0054	.	0.101	.	3.72	.	.	25.06
1	VS W10/3	55.8	0.012	.	.	.	0.32	.	.	0.0035	.	0.0053	.	0.050	.	.	.
1	ECRM 752-1	55.4	0.12	.	0.045	0.02	0.15	0.01	(<0.03)	.	(0.01)	0.007	.	0.70	.	0.009	43.4
1	GBW 07214A	55.34	0.093	.	0.085	0.020	0.29	0.0050	(0.007)	0.0011	.	0.043	.	0.22	.	.	43.61
1	BCS 513	55.59	0.108	.	0.0275	0.0150	0.182	0.0095	(<0.3)	.	(0.005)	0.0097	.	0.228	.	(0.004)	43.61
1	DK 1a	55.4	0.05	.	0.04	0.01	0.39	0.01	0.01	.	.	.	0.02	0.64	.	<0.01	43.3
1	NCS DC14014b	55.12	0.079	.	0.341	0.0030	0.73	0.0058	0.0075	0.0013	.	0.010	.	0.073	.	Ti:0.0010	43.53
1	NM 711	55.10	0.50	0.52	.	.	43.48
2	DH X3513	55.05	0.097	.	0.082	0.029	0.466	0.017	0.003	.	0.007	.	0.012	0.289	.	0.006	.
1	VB K1	54.58	0.11	.	0.097	(0.028)	0.72	0.0095	0.020	.	(0.016)	.	(0.051)	0.44	.	(0.011)	43.70
1	NCS DC14017b	54.11	0.61	.	0.319	0.0038	0.79	0.0074	0.021	0.0017	.	0.182	.	0.85	.	Ti:0.0021	42.79
1	GBW 03105a	54.03	0.24	.	0.11	0.084	0.81	0.0067	0.017	.	0.0081	.	0.018	1.09	0.67	0.010	43.12
1	NCS DC28205	52.42	0.39	.	0.197	.	1.92	0.0054	.	0.0019	.	0.012	.	2.17	.	0.0093	42.53
1	NCS DC60108a	51.61	0.33	.	0.17	0.17	2.25	0.0089	0.017	.	0.0061	.	0.016	2.09	1.38	0.015	42.84
2	DH X3514	51.49	0.483	.	0.422	0.075	2.161	0.020	0.042	.	0.034	.	0.197	2.533	.	0.023	.
1	NCS DC14015b	51.41	0.74	.	0.838	0.0062	2.31	0.013	0.0073	0.0021	.	0.273	.	2.06	.	Ti:0.0071	41.79
1	NCS DC28204	50.72	0.18	.	0.208	.	3.96	0.012	.	0.0076	.	0.016	.	0.83	.	0.0060	43.70
1	NCS DC60109a	50.09	0.94	.	0.58	(0.42)	1.79	(0.014)	(0.027)	.	0.033	.	(0.054)	4.05	(2.02)	(0.052)	41.53
2	DH X3515	48.91	0.787	.	1.293	0.187	0.379	0.028	0.032	.	0.036	.	0.055	8.75	.	0.048	.
1	NCS DC62002d	48.16	1.67	.	1.17	0.61	0.93	.	0.09	.	.	.	0.06	7.88	.	0.12	38.96
1	NCS DC60110a	47.07	0.60	.	0.38	(0.20)	5.81	(0.012)	(0.016)	.	(0.037)	.	(0.032)	2.25	(1.21)	(0.030)	43.22
1	DK 1b	43.6	3.20	.	1.25	0.96	3.00	0.02	0.13	.	.	.	0.13	9.5	.	0.15	37.7
1	NCS DC14050	42.62	0.36	.	0.260	0.021	9.45	0.015	0.015	0.0033	.	0.039	.	7.97	.	Ti:0.0096	38.80
1	GBW 07217A	32.11	0.017	.	0.224	0.0011	20.37	0.032	0.023	0.0010	.	0.018	.	0.021	.	.	46.89
1	IPT 122	32.0	1.24	.	0.65	0.43	17.5	0.042	0.019	.	0.048	.	.	4.3	.	0.06	43.3
1	VS K4/4	31.2	0.47	.	0.56	.	20.1	0.034	0.96	.	.	.
1	SRM 88b *	29.95	0.336	.	0.277	0.1030	21.03	0.0160	0.0290	.	0.0044	.	.	1.13	.	(0.016)	(46.98)
1	DK 2a **	29.2	0.91	.	1.01	0.37	19.5	0.06	0.04	.	.	.	0.06	4.3	.	0.07	44.3

continued

Number	CO ₂	Cl ⁻	Cr	Cr ₂ O ₃	Cu	Pb	SrO	Zn	Ins.Res	Units
NCS DC16006	15 g
VS W10/3	75 g
ECRM 752-1	0.019	.	.	100 g
GBW 07214A	50 g
BCS 513	.	.	.	0.0012	.	0.0009	0.0176	0.0014	.	100 g
DK 1a	60 g
NCS DC14014b	Sr:0.025	.	.	50 g
NM 711	100 g
DH X3513	43.80	0.019	.	.	100 g
VB K1	(43.54)	.	(0.0025)	.	(0.00055)	100 g
NCS DC14017b	Sr:0.024	.	.	50 g
GBW 03105a	(43.12)	0.0028	50 g
NCS DC28205	0.023	.	.	50 or 100 g
NCS DC60108a	(42.59)	0.0066	50 g
DH X3514	0.030	.	.	100 g
NCS DC14015b	Sr:0.023	.	.	50 g
NCS DC28204	0.046	.	.	50 or 100 g
NCS DC60109a	(41.32)	(0.0062)	50 g
DH X3515	0.050	.	.	100 g
NCS DC62002d	20 g
NCS DC60110a	(43.02)	(0.0054)	50 g
DK 1b	60 g
NCS DC14050	Sr:0.017	.	.	50 g
GBW 07217A	50 g
IPT 122	0.018	.	.	80 g
VS K4/4	1.30	75 g
SRM 88b *	46.37	0.0076	.	.	75 g *
DK 2a **	60 g **

* SRM 88b lists Mn as MnO
** DK 2a lists Mn₃O₄ as MnO

CRM SYNTHETIC LIMESTONE WITH TRACE ELEMENTS

Material base: CaCO₃ 85%, MgCO₃ 8%, SiO₂ 5.2%, Al₂O₃ 1.1%, Fe₂O₃ 0.3%, Na₂SO₄ 0.2%, K₂SO₄ 0.2% analysis listed in mg/kg 70 g units

Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Co	Cr	Cu	Ga	La	Li	Mn
GBW 07712	(0.030)	2.2	2.2	24	0.22	0.23	(0.023)	2.8	2.3	2.3	2.2	2.8	2.6	3.2	37
GBW 07713	0.060	5.2	5	54	0.52	0.53	0.053	5.8	5.3	5.3	5.2	5.8	5.6	6.2	67
GBW 07714	0.11	10.2	10	104	1.0	1.0	0.10	11	10.3	10.3	10.2	10.8	10.6	11.2	117
GBW 07715	0.21	20	20	204	2.0	2.0	0.20	21	20.3	20.3	20	20.8	20.6	21	217
GBW 07717	1.0	100	100	1000	10	10	1.0	101	100	100	100	101	101	101	1020
GBW 07718	2.0	200	200	2000	20	20	2.0	200	200	200	200	200	200	200	2020
GBW 07719	5.0	500	500	5000	50	50	5.0	500	500	500	500	500	500	500	5000
GBW 07720	10	.	.	.	100	100	10	.	.	.	1000	.	.	1000	10000

continued

Number	Mo	Nb	Ni	Pb	Sb	Sn	Sr	Ti	V	W	Y	Yb	Zn	Zr
GBW 07712	0.21	2.5	2.1	2.4	0.21	0.28	170	31	3.2	0.22	2.1	0.22	3.0	4.0
GBW 07713	0.51	5.5	5.1	5.4	0.51	0.58	200	61	6.2	0.52	5.1	0.52	6.0	7.0
GBW 07714	1.0	10.5	10	10.4	1.0	1.1	250	111	11.2	1.0	10	1.0	11	12
GBW 07715	2.0	20.5	20	20.4	2.0	2.1	350	210	21	2.0	20	2.0	21	22
GBW 07717	10	100	100	100	10	10	1150	1010	101	10	100	10	101	102
GBW 07718	20	200	200	200	20	20	2200	2000	200	20	200	20	200	202
GBW 07719	50	.	500	500	50	50	5200	5000	500	50	.	50	500	500
GBW 07720	100	.	.	1000	100	100	.	.	.	100	.	100	1000	.

CRM LITHIUM ORE WITH EXTENSIVE ANALYSIS

analysis listed in mass %														17025		100 g units	
Number	Al ₂ O ₃	CaO	Fe ₂ O ₃ T	K ₂ O	Li ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	Zn	LOI	Units		
CGL 128	13.66	0.746	0.663	6.28	0.578	0.033	0.603	(0.603)	(0.029)	(0.223)	73.40	(0.053)	0.0594	(2.14)	100 g		
continued analysis listed in mg/kg																	
Number	As	Ba	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd			
CGL 128	61.75	83.51	185	(3.64)	(46.93)	(0.401)	(105)	(67.38)	186	(1.37)	(1.18)	(0.091)	(29.69)	(1.22)			
Number	Hf	Ho	Ind	La	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc			
CGL 128	(5.64)	(0.313)	(0.303)	(28.92)	(0.421)	(7.26)	(77.63)	(8.64)	(1.76)	558	(3.41)	(2135)	(20.50)	(9.62)			
Number	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	W	Y	Yb	Zr			
CGL 128	(2.26)	(11.43)	24.54	(9.74)	(0.208)	(1.12)	(24.20)	(14.65)	(0.240)	45.28	107	(12.33)	(2.19)	69.94			

CRM LITHIUM ORE

analysis listed in mass %																	
Number	Li ₂ O	Al ₂ O ₃	CaO	Cs ₂ O	F-	FeO	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Rb ₂ O	SiO ₂	TiO ₂	LOI
NCS DC86314	3.89	24.53	0.063	0.30	5.08	(0.043)	0.30	(2.77+)	7.75	0.027	0.40	1.08	0.13	1.24	53.92	0.029	(5.34)
NCS DC86304	2.29	19.12	0.076	0.177	3.12	(0.020)	0.301	2.29-	4.80	0.036	0.252	2.33	0.237	0.735	64.64	0.028	4.06
NCS DC86303	0.460	14.76	0.335	0.037	0.667	(0.062)	0.394	1.06-	3.17	0.054	0.070	4.19	0.173	0.145	74.37	0.018	1.48
continued analysis listed in mg/kg except % which is mass %																	
Number	BeO%	CeO ₂	Dy ₂ O ₃	Er ₂ O ₃	Eu ₂ O ₃	Gd ₂ O ₃	Ho ₂ O ₃	La ₂ O ₃	Lu ₂ O ₃	Nb ₂ O ₅	Nd ₂ O ₃	Pr ₆ O ₁₁					
NCS DC86314	0.0164	(1.88)	0.50	0.24	0.10	0.56	0.094	1.16	0.036	81	1.66	0.46					
NCS DC86304	0.026	2.6	0.64	0.26	0.13	0.75	(0.13)	(2.1)	0.034	61.1	2.8	0.63					
NCS DC86303	0.018	9.0	2.5	1.2	(0.14)	2.1	0.45	5.1	0.18	27.0	5.0	1.3					
Number	RE _x O _y *	Sc ₂ O ₃	Sm ₂ O ₃	Sn	Ta ₂ O ₅ %	Tb ₄ O ₇	Tm ₂ O ₃	W	Y ₂ O ₃	Yb ₂ O ₃	Units						
NCS DC86314	10.7	0.31	0.52	152	.	0.10	0.038	79.0	3.06	0.22	70 g						
NCS DC86304	15.2	0.44	0.64	97.1	0.012	0.13	0.040	43.7	3.4	0.23	70 g						
NCS DC86303	47.0	0.98	1.6	(36)	0.00494	0.43	0.18	8.9	16.9	1.3	70 g						

* RE_xO_y : Rare Earth Oxide
x y

CRM LITHIUM ORE

45 g units

Number	Li ₂ O%
SRM 181	6.39
SRM 182	4.34
SRM 183	4.12

CRM LUJAVRITE

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	CaO	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	TiO ₂	Ba	Be	Co	Cr	Cu	Ga	Ge
VS 2124-81	56.13	16.96	1.25	1.14	5.52	6.23	0.74	0.254	9.26	0.92	0.080	0.00139	0.00063	0.00125	0.00111	0.0063	0.00013
continued																	
Number	La	Li	Mo	Nb	Ni	Pb	Rb	Sn	Sr	V	Y	Yb	Zn	Units			
VS 2124-81	0.040	0.0037	0.00028	0.034	0.00078	0.0020	0.0250	0.0014	0.080	0.0086	0.0081	0.00057	0.012	40 g			

CRM LOW BORON MAGNESITE

Number	Al	B	Ca	Cr	Fe	K	Mg	Mn	Na	P	Si	Ti	Units
ECRM 779-1	0.105	0.0116	1.691	(0.0030)	3.73	(0.0020)	(54.57)	0.503	(0.0058)	0.0267	0.182	0.0081	100 g

CRM MAGNESITE

analysis listed in mass %												100 g units								analysis listed in mg/kg							
Number	MgO	Al ₂ O ₃	CaO	Fe ₂ O ₃	FeO	K ₂ O	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	Ba	Ce	Co	Cr	Cu	Ni	Sr	Zn								
SARM 43	44.11	(0.06)	0.89	0.26	(0.1)	(0.04)	(0.1)	(0.05)	(0.02)	5.99	(0.01)	(25)	(20)	4	(195)	(15)	252	8	(10)								

MAGNESITE

# = class, where 1 = CRM and 2 = RM		analysis listed in mass %										CERAM: 25 or 100g		NCS: 50g		NH: 75g		others: 100g	
#	Number	MgO	Al ₂ O ₃	B ₂ O ₃	CaO	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MnO	Mn ₂ O ₃	Na ₂ O	P ₂ O ₅	S	SiO ₂	SrO	TiO ₂	LOI		
1	BCS 389/1	97.89	0.104	.	0.880	.	0.607	.	0.100	.	.	0.0295	.	0.274	.	0.0052	.		
2	CERAM AN35	96.4	.	0.10	0.83	0.046	1.34	<0.01	.	0.11	<0.05	0.011	.	0.49	last	0.01	100g		
1	BCS 319/1	95.38	0.109	.	3.00	0.0035	0.291	.	0.108	1.093	.	0.0070	.		
2	CERAM AN37	94.00	.	0.09	1.46	0.005	1.80	<0.01	.	0.12	<0.05	0.02	.	1.39	.	0.03	.		
2	CERAM AN36	93.30	.	0.09	0.94	0.004	4.66	<0.01	.	0.11	<0.05	0.008	.	0.48	.	0.01	.		
1	ECRM 778-1	81.02	0.56	.	1.23	0.15	0.96	.	0.014	.	.	(0.009)	.	1.05	.	(0.013)	.		
1	NCS DC28090	46.40	0.10	.	0.53	.	0.65	0.0050	0.016	.	0.017	0.013	0.0027	0.32	0.005	0.0060	51.58		
1	USZ 37-2003	45.80	0.04	.	1.69	.	0.05	0.011	0.25	.	CO ₂ : 48.31	51.35		
1	UNS MK	45.22	0.414	.	0.581	.	.	0.013	0.160	.	0.024	0.055	.	0.593	.	0.019	.		
1	NCS DC28089	43.45	1.14	.	1.52	.	1.74	0.037	0.095	.	0.018	0.036	0.015	4.13	0.0013	0.041	47.35		
1	NCS DC28089a	43.44	1.46	.	1.26	.	1.66	0.044	0.083	.	0.020	0.037	0.015	4.95	0.0014	0.048	46.57		
2	CERAM AN43	.	.	0.005	.	.	.	(0.06)		
2	CERAM AN45	.	.	0.222		

RM MAGNESITE

typical analysis listed in mass %															100 g units		
Number	MgO	Al ₂ O ₃	C tot.	CO ₂	CaO	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	Mn ₃ O ₄	Na ₂ O	P ₂ O ₅	S	SO ₃	SiO ₂	TiO ₂	-H ₂ O at 900°C	
DH 4209	98.03	0.098	0.031	0.132	0.866	0.016	0.515	.	0.107	.	0.027	.	0.012	0.222	0.007	.	
DH 4207	83.65	2.39	0.539	0.54	2.23	0.036	1.49	0.072	0.074	0.385	0.087	.	0.037	7.73	0.149	0.84	
DH 4203	76.81	1.27	0.396	0.104	1.29	0.119	2.75	0.019	0.090	0.375	0.059	.	0.070	15.94	0.054	1.01	
DH 4208	47.83	41.66	0.353	0.580	2.06	0.040	1.49	0.037	0.070	.	0.077	0.007	.	5.09	0.066	0.894	

continued

Number	V ₂ O ₅	ZnO	ZrO ₂
DH 4209	0.003	0.003	.
DH 4207	.	.	0.011
DH 4203	.	.	.
DH 4208	0.001	0.006	0.091

CRM		MANGANESE ORE																	
		# = class, where 1 = CRM and 2 = RM																	
		analysis in mass %																	
		T = Total																	
#	Number	Mn	MnO ₂	Mn(CO ₃)	Al ₂ O ₃	As	As ₂ O ₃	Ba	BaO	CO ₂	CaO	Fe	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	SiO ₂	TiO ₂	
1	IGS 29		MnO:	93.38				0.59											
1	VS R13/3	58.88	90.4																
1	NCS DC26703	58.80	(62.07)		0.74					C:0.034	0.37	1.45			0.17		5.63	Ti:0.025	
1	VS P13/1	58.8															2.00		
1	SRM 25d	51.78			(5.33)				(0.21)		(0.052)		(3.91)	(0.928)			2.54	(0.136)	
1	SARM 16	49.17			(0.3)			0.60			4.70	11.48		0.02	0.76	(0.03)	5.04		
1	NCS DC35015	49.00	68.28			0.015						3.97							
1	JSS 861-2	48.7		Al:	1.57					Ca:	0.063	(5.7)					Si:	2.62	
1	NCS DC26702	48.53	(72.64)		3.28					C:0.085	0.37	4.93			0.25		5.56	Ti:0.102	
1	BAM 633-1	47.85			1.64		(0.004)	1.13			2.02	1.64			0.58		10.39	0.079	
1	AMIS 0403	46.82	MnO:	60.42						Ca:	3.56	5.12	12.43	18.25	(0.023)	0.66	(0.18)	5.25	(0.02)
2	RH01	46.8	51.3		1.50				(0.3)		1.77	1.63		1.33	1.10	0.41	11.4		
1	AMIS 0404	45.93	MnO:	59.45	(0.40)					Ca:	3.07	4.43	13.63	19.54	(0.06)	0.51	0.79	3.56	(0.02)
1	NCS DC25008	45.47			6.81						0.071	3.21			0.077		9.51	0.087	
1	NCS DC26704	45.20	(67.71)		6.88					C:0.090	0.103	6.03			0.097		5.55	Ti:0.092	
1	NCS DC28045	44.97T	67.67		2.35	0.042		0.058			0.195	2.75T		1.48	0.182	0.034	16.00	0.105	
1	NCS DC26701	44.95	(32.1)		0.37					C:1.22	14.2	15.50			1.05		5.41	Ti:0.010	
1	NCS DC28210	44.76	58.46		7.28						0.24	5.22			0.257		4.62	0.34	
1	VS R12/2	43.24	52.4		1.87				0.53		2.02	1.56			1.16		15.00		
1	AMIS 0402	43.01	MnO:	56.77	0.38				Ca:	3.88	5.70	15.38	22.12	(0.02)	0.54	(0.11)	4.31	(0.024)	
1	SARM 17	38.81			0.24			(0.08)		(14.4)	4.27			0.09	3.03	0.09	4.69		
1	SARM 149	38.0			0.221			0.050			14.2	5.39		0.132	2.08	0.147	5.89		
1	OREAS 170b	MnO:	59.46		3.90						0.270			1.80	0.329	0.318	9.49	0.189	
1	OREAS 170a	MnO:	58.17		4.44						0.090		7.04	1.70	0.222	0.276	11.34	0.179	
1	CMSI 1691	36.99	54.38		3.00				0.47		3.60	2.24		0.46	1.44	0.048	22.24	0.10	
1	NCS DC28044	36.31T	45.02		2.08	0.039		0.410			3.30	6.90T		0.49	1.29	0.076	17.70	0.085	
1	AMIS 0407	35.72	MnO:	46.81	0.29			Ca:	11.04	15.81	4.10	6.03		0.04	3.17	(0.039)	5.51	(0.02)	
1	NCS DC11023	35.54T	52.73		3.80	0.112		1.62		2.34	10.25T			0.396	0.78	(0.053)	13.03	0.143	
1	CGL 127	MnO:	45.9		9.27	(0.0131)		(0.9384)		(1.63)		19.51T		(0.017)	0.79	(0.086)	10.84	0.53	
1	NCS DC28062	34.67	51.64		9.97					0.48	8.05			1.14	0.87	0.063	10.70		
1	VS 5404-90	34.12	48.66		5.28					4.68	6.68			0.83	0.45	0.38	15.69	0.27	
1	NCS DC28211	32.70	32.32		3.30					4.21	10.47				3.04		14.40	0.16	
1	AMIS 0406	32.27	MnO:	41.81	0.24			Ca:	12.62	18.13	4.62	6.77	(0.11)	3.51	(0.14)		4.36	(0.02)	
1	NCS DC28043	30.99T	45.61		6.40	0.089		1.11		1.15	10.68T			0.65	0.70	0.058	17.30	0.215	
1	NCS DC11022	29.48T	41.76		6.49	0.062		1.04		1.82	10.22T			0.89	0.65	0.062	19.84	0.070	
2	DH 4303	29.05			2.17			0.119		0.062	0.060	30.01		0.244	0.032	0.017	3.63	0.024	
1	NCS DC28209	27.76	21.00		1.77					5.44	12.00				4.08		17.54	0.085	
1	NCS DC28063	27.45	39.38		10.05					0.99	8.10			1.57	1.16	0.064	20.96		
1	NCS DC11021	26.53T	36.60		6.99	0.052		0.80		2.31	11.01T			1.01	0.774	0.064	22.10	0.247	
1	CMSI 1693	25.00	36.93		8.97			0.23		0.051	20.99			0.72	0.10	0.030	10.46	0.54	
1	NCS DC28061	22.93	33.45		9.88					1.11	6.71			1.95	0.94	0.053	31.42		
1	CMSI 1694	22.54		22.46	1.68			0.13		14.73	1.40			0.46	3.50	0.024	14.07	0.10	
1	NCS DC28042	22.18T	18.35		2.80	0.032		0.164		6.20	10.62T			0.83	3.14	0.049	24.73	0.123	
1	NCS DC11020	22.31T	30.34		7.69	0.034		0.54		2.36	9.66T			1.11	1.72	0.056	28.11	0.270	
1	KZ 185-89	21.61T			1.42					25.72	1.11T			0.11	0.95		16.07	0.066	
1	NCS DC11019	18.36T	25.59		5.66	0.031		0.43		12.83	8.89T			1.04	0.611	0.045	21.94	0.206	
1	NCS DC28060	18.22	27.06		10.39				2.65	1.29	1.22	5.86		2.34	0.84	0.054	38.94	0.31	
1	VS 5406-90	15.98	14.40		9.78					1.96	2.43			4.99	0.74	0.70	47.66		
1	CMSI 1695	15.74		15.69	2.49			0.15		19.78	2.07			0.70	3.82	0.040	15.82	0.15	
1	NCS DC28041	14.45T	20.66		8.25	0.013		0.064		2.07	0.85T			3.74	0.60	0.48	56.03	0.177	

#	Number	Mn	MnO ₂	Mn(CO ₃)	Al ₂ O ₃	As	As ₂ O ₃	Ba	BaO	CO ₂	CaO	Fe	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	SiO ₂	TiO ₂
Number		Cr	Cu	Ge	Ni	P	P ₂ O ₅	Pb	S	V	Zn	LOI	Units		Other			
IGS 29		.	.	.	0.101	0.196	.	0.0013	0.07	.	.	.	40 g					
VS R13/3		.	0.0219	.	(0.002)	0.033	.	0.013	0.18	.	.	.	100 g					
NCS DC26701		.	0.024	.	.	0.197	.	0.0014	0.070	.	0.013	.	50 g	Co: 0.008				
VS P13/1		0.251	100 g	MnO: 90.4, last of stock				
SRM 25d		60 g	available Oxygen: 14.28, H ₂ O: (0.96)				
SARM 16		.	.	.	0.033	0.033	.	0.17	.	0.0364	.	.	100 g					
NCS DC35015		.	0.006	.	0.014	.	.	0.015	.	0.036	.	.	80 g	Co: 0.025				
JSS 861-2		.	0.0064	.	0.086	.	.	0.0084	.	.	(3.3)	.	100 g	Activated O: 13.55				
NCS DC26702		.	0.005	.	0.012	0.080	.	0.012	0.017	.	0.016	.	50 g	Co: 0.014				
BAM 633-1		.	.	.	0.170	.	.	0.227	100 g					
AMIS 0403		Cr2O3:	(0.03)	.	.	.	0.08	.	specific gravity:	4.63	4.27	100 g	multiple Mn					
RH01		0.28	.	.	(0.025)	.	12.8	100 g						
AMIS 0404		Cr2O3:	(0.024)	.	.	.	(0.08)	.	specific gravity:	4.65	4.88	100 g	multiple Fe, Mn					
NCS DC25008		.	.	.	0.094	50 g	B: 0.0018					
NCS DC26703		.	0.033	.	0.0024	0.009	.	0.018	0.003	.	0.219	50 g	Co: 0.0014					
NCS DC28045		0.038	0.022	.	0.079	0.230	.	0.011	0.0086	0.018	0.070	50 g						
NCS DC26704		.	0.009	.	0.039	0.127	.	(0.007)	0.028	.	0.052	50 g	Co: 0.096					
NCS DC28210		.	0.062	.	0.057	0.099	.	0.014	.	.	0.088	50 g						
VS R12/2		0.209	.	.	0.029	.	.	100 g						
AMIS 0402		Cr2O3:	(0.05)	.	.	.	0.10	.	specific gravity:	4.62	4.97	100 g	multiple Ca, Fe, Mn					
SARM 17		0.018	.	.	(0.01)	.	0.0043	100 g						
SARM 149		0.021	100 g						
OREAS 170b		0.195	11.95	10 g					
OREAS 170a		0.152	12.14	10 g					
CMSI 1691		.	0.014	.	0.019	0.081	.	.	0.013	.	0.029	100 g						
NCS DC28044		0.0018	0.0086	.	0.010	0.105	.	0.0083	0.021	0.0075	0.027	50 g						
AMIS 0407		Cr2O3:	0.22	.	.	.	(0.04)	.	specific gravity:	3.74	17.83	100 g	multiple Mn					
NCS DC11023		0.0053	0.011	.	0.023	0.105	.	0.058	0.052	0.016	0.066	50 g						
CGL 127		(0.0086)	(0.0127)	17025	0.0377	.	0.76	(0.0038)	.	(0.0241)	0.0182	(6.41)	100 g	mg/kg: Co:316 Y:104 Sr:1354 Zr:208				
NCS DC28062		0.050	.	0.011	.	.	.	50 g						
VS 5404-90		.	.	0.00034	0.013	0.027	.	0.15	0.023	.	0.16	50 g	Co: 0.0086					
NCS DC28211		.	0.020	.	0.016	0.087	.	0.0090	.	0.027	.	50 g						
AMIS 0406		Cr2O3:	0.08	.	.	.	(0.04)	.	specific gravity:	3.63	20.67	100 g	multiple Mn					
NCS DC28043		0.013	0.015	.	0.083	0.171	.	0.110	0.100	0.019	0.235	50 g						
NCS DC11022		0.018	0.018	.	0.072	0.150	.	0.107	0.0									

CRM MANGANESE NODULE

analysis listed in mass % except * which is mg/kg T = Total * AMIS lists Mn by XRF and M/ICP

Number	MnO	MnO ₂	Al ₂ O ₃	COrg	CO ₂	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Density	Units
US NOD-P-1	37.6	.	4.8	.	.	3.1	8.3T	1.2	3.3	2.2	0.46	13.9	0.5	.	.	25 g
AMIS 0104*	35.31*	35.49*	2.20	.	.	1.34	20.78	0.26	(0.35)	(0.10)	(P: 192*)	18.30	0.27	(3.28)	4.32	100 g or 1kg
VS 5374-90	35.09T	41.7	5.68	0.18	0.43	2.82	9.28T	1.27	3.40	2.94	0.68	16.60	0.74	15.3	.	50 g
JMn-1	33.09	.	4.30	.	.	2.91	14.40T	0.94	3.12	2.80	0.54	14.11	1.06	.	.	100 g
VS 5375-90	25.16T	31.1	5.46	0.22	0.60	3.01	24.87T	0.83	2.24	2.40	0.80	14.50	1.91	13.8	.	50 g
US NOD-A-1	23.9	.	3.87	.	.	15.4	15.6T	0.6	4.76	1.0	1.40	3.81	0.53	.	.	25 g
VS 5376-90	19.85T	24.2	6.71	.	0.50	5.13	22.13T	1.18	2.29	2.24	1.61	22.30	1.56	11.4	.	100 g

Number	As	Au*	B*	Ba	Be*	Bi*	C*	Cd*	Ce	Cl	Co	Cr	Cr ₂ O ₃	Cs*	Cu	Dy*
US NOD-P-1	.	.	.	0.3350	(0.0290)	.	0.2240	.	.	.	1.1500	(27)
AMIS 0104	(0.0116)	.	.	2.86	(2.1)	(0.61)	.	(0.78)	(0.02994)	.	0.0240	(0.01802)	(0.03)	(0.19)	(0.0192)	(10.6)
VS 5374-90	0.006	0.005	.	0.18	.	.	.	17	0.020	0.7	0.220	0.0018	.	.	1.01	.
JMn-1	0.00754	(0.00095)	(138)	0.1714	(7.8)	(4.3)	(905)	(15.5)	0.0277	.	0.1732	0.00266	.	0.60	1.1132	(28.3)
VS 5375-90	0.017	0.010	.	0.17	.	.	.	5	0.09	0.9	0.47	0.0019	.	.	0.22	.
US NOD-A-1	.	.	.	0.1670	(0.0730)	.	0.3110	.	.	.	0.1100	(23)
VS 5376-90	0.014	.	.	0.16	19	.	.	.	0.10	.	0.27	0.0067	.	.	0.13	.

Number	Er*	Eu*	Ga*	Gd*	Ge*	H ₂ O+	Hf*	Ho*	In*	La	Li	Lu*	Mo	Nb	Nd	Ni
US NOD-P-1	(12)	(7.5)	.	(28)	(0.0104)	.	(1.8)	0.0760	.	(0.0120)	1.3400
AMIS 0104	(5.7)	(4.3)	(35.8)	(12.1)	(1.7)	.	(3.0)	(2.0)	(0.05)	(0.00444)	(0.00183)	(0.66)	(0.00047)	(0.00055)	(0.00557)	(0.00421)
VS 5374-90	0.009	0.014	.	0.052	0.0020	0.008	1.37
JMn-1	14.6	7.6	(37.1)	(29.8)	.	(7.90)	(6.2)	(5.8)	.	0.0122	(0.00717)	2.1	0.0318	(0.00276)	0.0137	1.2632
VS 5375-90	0.014	0.004	.	0.033	0.009	0.014	0.422
US NOD-A-1	(12)	(5)	.	(26)	(0.0120)	.	(2.2)	0.0448	.	(0.0094)	0.6360
VS 5376-90	0.012	0.0019	.	0.035	0.006	0.010	0.34

Number	Li	Lu*	Mo	Nb	Nd	Ni	Pb	Pd*	Pr*	Pt*	Rb*	S	Sb*	Sc
US NOD-P-1	.	(1.8)	0.0760	.	(0.0120)	1.3400	0.0560
AMIS 0104	(0.00183)	(0.66)	(0.00047)	(0.00055)	(0.00557)	(0.00421)	(0.00507)	.	(12.6)	.	(5.3)	(0.32)	(9.7)	(4.6)
VS 5374-90	0.014	.	0.052	0.0020	0.008	1.37	0.040	.	.	0.10	21	0.10	.	11
JMn-1	(0.00717)	2.1	0.0318	(0.00276)	0.0137	1.2632	0.0430	.	(31.4)	(0.110)	10.9	(0.0940)	37.5	(13.0)
VS 5375-90	0.004	.	0.033	0.009	0.014	0.422	0.098	0.003	.	0.21	10	0.16	.	13
US NOD-A-1	.	(2.2)	0.0448	.	(0.0094)	0.6360	0.0846
VS 5376-90	0.0019	.	0.035	0.006	0.010	0.34	0.105	.	.	.	19	0.16	.	19

Number	Sm	Sn*	Sr	Ta*	Tb*	Th*	Tl	Tm*	U*	V	W*	Y	Yb*	Zn	Zr
US NOD-P-1	(0.0030)	.	0.0680	0.0570	.	.	.	(1.3)	0.1600	.
AMIS 0104	(0.00128)	(2.0)	(0.0309)	(0.21)	(1.8)	(9.5)	(0.42*)	(0.78)	(8.1)	(0.0108)	(3.5)	(0.00412)	(4.9)	0.0142	(0.01341)
VS 5374-90	0.0022	.	0.064	.	17	.	.	4	0.043	.	0.011	13	0.12	0.032	.
JMn-1	0.00302	(4.4)	0.0792	(0.64)	4.8	11.7	.	2.1	5.0	0.0424	(45.3)	0.0111	13.8	0.1068	0.0344
VS 5375-90	0.003	.	0.11	.	.	38	.	.	8	0.048	.	0.014	14	0.058	0.060
US NOD-A-1	(0.0021)	.	0.1750	0.0770	.	.	.	(14)	0.0590	.
VS 5376-90	0.0027	.	0.11	.	.	28	0.010%	.	6	0.054	.	0.016	6	0.060	0.055

CRM MANGANESE NODULE

analysis in mass %

Number	SiO ₂	Co	Cu	T.Fe	T.Mn	Ni	Units
NM 2388	16.07	0.14	0.49	14.94	21.28	0.71	100 g last of stock

CRM MARIPOLITE

analysis listed in mass %

40 g units

Number	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	K ₂ O	MnO	Na ₂ O	Nb	Rb	SiO ₂	TiO ₂
VS 2122-81	21.96	0.72	1.20	0.88	2.05	4.30	0.085	10.79	0.034	0.030	56.29	0.045

continued

analysis listed in mg/kg

Number	Ba	Be	Cr	Cu	Ga	Ge	La	Li	Mo	Ni	Pb	Sn	Sr	V	Y	Yb	Zn	Zr
VS 2122-81	170	86	9.8	21	80	1.4	130	4.3	5.2	6.5	25	15	120	13	64	5	69	70

CRM MERCURY ORE

analysis listed in mass %

100 g units

Number	Hg	Al ₂ O ₃	CaO	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	SiO ₂	TiO ₂	Co	Cr	Cu	Ni	Sr	V	LOI
USZ 43-2006	0.0689	0.53	17.39	0.49	4.66	0.03	9.93	0.29	0.07	41.01	0.018	0.0047	0.21	0.0007	0.10	0.0382	0.0038	25.28

**MICROSAMPLES**

The USGS Microanalytical Reference Materials (MRMs) are designed for use in the quantitative analysis of geologic samples using direct solid sampling techniques such as Laser Ablation ICP-MS. Recommended and informational total element concentrations were obtained through international round robin analysis using both bulk and microanalytical data.

Samples are distributed in polished epoxy mounts and ready for immediate use. These MRMs are supplied as individual samples or as sets contained within a plastic holder. Accessories are also available which integrate the USGS MRM holder with standard sample chamber mounts for CETAC® and New Wave® laser ablation systems.

MOUNTED MICROANALYTICAL REFERENCE MATERIALS

Number	Material Type	Form	Comments	Mount Color
US MM BCR-2G	Basalt Glass	Epoxy Mount	Melted BCR-2	Colorless
US MM BHVO-2G	Basalt Glass	Epoxy Mount	Melted BHVO-2	Magenta
US MM BIR-1G	Basalt Glass	Epoxy Mount	Melted BIR-1	Yellow
US MM NKT-1G	Nephelinite Glass	Epoxy Mount	Melted NKT-1	Magenta
US MM TB-1G	Basalt Glass	Epoxy Mount	Melted TB-1	Orange
US MM GSC-1G	Synthetic Basalt Glass	Epoxy Mount	Traces ~ 3 ppm	Light Blue
US MM GSD-1G	Synthetic Basalt Glass	Epoxy Mount	Traces ~ 30 ppm	Medium Blue
US MM GSE-1G	Synthetic Basalt Glass	Epoxy Mount	Traces ~ 300 ppm	Dark Blue

PRESSED POWDER MICROANALYTICAL REFERENCE MATERIALS

Number	Material Type	Form	Comments
US MP MASS-1	Synthetic Polymetal Sulfide	Pressed Pellet	Pellet in 19 mm ring
US MP MACS-3	Synthetic Calcium Carbonate	Pressed Pellet	Pellet alone

MICROANALYTICAL ACCESSORIES FOR LASER ABLATION

Number	Description	Comments
US MA SH-V1	Sample Holder	Plastic, will hold 4 RM plugs
US MA CM-V1	Cetac system sample mount	Mount for sample holder to fit Cetac
US MA NWM-V1	New Wave system sample mount	Mount for sample holder to fit New Wave chambers
US MA RM KIT-1	Contains 1 each of GSD-1G, BCR-2G, BHVO-2G, BIR-1G, and sample holder (SH-V-1)	



US MA SH-V1



US MA CM-V1



US MA NWM-V1



US MA RM KIT-1

RM MOLOCHITE

analysis listed in mass %

25 or 100 g units

Number	Al ₂ O ₃	BaO	CaO	Fe ₂ O ₃	K ₂ O	MgO	Mn ₃ O ₄	Na ₂ O	P ₂ O ₅	SiO ₂	SrO	TiO ₂	ZrO ₂
CERAM AN40	37.9	0.03	0.14	0.85	1.52	0.24	0.01	0.12	0.11	58.8	0.02	0.06	0.016

CRM MOLYBDENUM ORE AND CONCENTRATE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

50 g units

Number	Mo	Al ₂ O ₃	Ba	CaO	F	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	S	SiO ₂	TiO ₂	W	WO ₃	Zn	Zr
GBW 07238	1.51	3.46	.	31.44	4.08	21.34	0.046	0.86	1.40	0.075	1.64	34.10	0.13	0.36	.	0.000655	.
GBW 07239	0.11	7.27	.	23.03	1.33	14.66	0.82	1.83	1.49	0.77	0.48	46.67	0.36	0.10	.	0.012	.
KZ 7025-93	0.067	.	0.27	0.04	.	0.013

continued analysis listed in mg/kg except % which is mass %

Number	Ag	As	Be	Bi	Cd	Ce	Cr	Cu	Dy	Eu	Er	Ga	Gd	Ge	Ho	In	La	Li	Lu
GBW 07238	0.09	1.6	.	2.2	0.12	20.8	(24)	93.6	1.8	0.59	1.0	25.1	1.9	19.0	0.36	2.9	7.1	(3.2)	0.16
GBW 07239	0.12	1.0	.	1.0	0.09	60.3	(35)	48.6	5.8	1.5	3.2	23.1	5.8	12.4	1.2	1.3	37.4	(13)	0.41
KZ 7025-93	0.8	.	19	51	.	.	.	0.077%

Number	Nb	Nd	Ni	Pb	Pr	Re	Sb	Sc	Se	Sm	Sn	Tb	Te	Th	Tl	Tm	Y	Yb
GBW 07238	.	11.3	17.8	18.7	3.0	(0.35)	1.2	3.4	2.1	2.1	86.7	0.34	0.40	2.3	0.06	0.14	11.4	1.0
GBW 07239	.	29.8	20.9	26.1	7.4	(0.12)	0.26	8.4	0.27	6.4	33.2	0.98	0.14	9.7	0.21	0.44	34.2	2.8
KZ 7025-93	13

CRM MOLYBDENUM ORE AND CONCENTRATE

% = mass % * = mg/kg

Insol = Insoluble Residue

Number	Mo%	Ag*	As*	Bi*	Cu%	Fe%	Insol%	Na%	P%	Pb%	Re%	S%	Sb*	SiO ₂ %	W*	Zn%	Units
SRM 423	58.68	(29)	.	(60)	0.0640	1.708	7.69	(0.2)	.	0.0433	(0.004)	(0.063)	(24)	.	.	(0.017)	60 g
SRM 333a	54.86	(13)	(150)	(30)	0.0600	(1.022)	(3.767)	(0.01)	.	(0.0111)	(0.035)	(37.7)	(10)	.	.	(0.002)	60 g
CGL 202	51.5	.	(278)	.	(1.34)	(1.44)	.	.	(0.014)	(0.0160)	(0.05)	(35.66)	.	(4.50)	.	.	100 g
NCS DC93010	40.83	.	160	.	0.26	.	.	.	0.013	0.46	.	.	.	22.07	.	.	50 g
GMO-04	0.7949	1.93	4.52	95	0.0240	0.0046	.	.	8.9	.	.	0.0128	250 g
GMO-03	0.5329	1.47	3.50	72	0.0191	0.0037	.	.	6.8	.	.	0.0122	250 g
GMO-12	0.4797	1.04	3.5	50.0	0.01425	0.00346	.	0.39	4.41	.	1.2	0.0104	250 g
GMO-11	0.2937	0.89	3.3	40.2	0.01155	0.00319	.	0.26	3.40	.	0.8	0.0101	250 g
GMO-10	0.0953	0.55	2.6	15.3	0.00698	0.00262	.	0.13	1.36	.	0.6	0.0096	250 g
GMO-07	0.00447	6.10	74.00	0.3	0.0014	0.0011	.	.	0.1	.	last	0.0011	250 g
GMO-05	0.00277	0.88	12.71	11	0.0639	0.0013	.	.	0.5	.	.	0.0087	250 g

RM MOLYBDENUM CONCENTRATE

analysis listed in mass %

100 g units

Number	Mo	Al ₂ O ₃	Tot.C	CaO	Cr ₂ O ₃	CuO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	S	SiO ₂	SrO	TiO ₂	V ₂ O ₅	ZnO
DH 4707	61.08	0.702	0.040	1.61	0.004	0.504	1.80	0.182	0.117	0.008	0.045	0.069	4.38	.	0.040	.	0.064
DH 4708	59.97	0.959	0.054	0.99	0.38	0.402	1.96	0.188	0.109	0.009	0.042	0.124	5.53	0.009	0.048	0.010	0.018
DH 4706	57.55	1.178	0.016	0.644	.	0.106	3.83	0.407	0.207	0.036	1.009	0.050	7.52	.	0.092	.	.

CRM MULTI-METAL ORE

analysis listed in mass % 50 g units

Number	Al ₂ O ₃	As	CaO	Cu	Fe	K ₂ O	MgO	Mn	Na ₂ O	Pb	S	SiO ₂	Zn
NCS DC73507	14.1	0.043	1.52	0.264	4.68	3.85	1.55	0.090	0.68	0.43	2.67	63.0	0.83
NCS DC73510	(2.5)	0.15	6.5	0.096	19.6	0.78	0.59	0.066	(0.03)	5.13	29.0	14.1	13.9

continued analysis listed in mg/kg except

Number	Ag	Bi	Cd	Ga	Ge	Hg	In	Mo	Re	Sb	Se	Sn	Te	Tl	W
NCS DC73507	18.3	2.8	32	23.4	2.9	4.2	(1.5)	28	.	94	2.3	.	(0.3)	1.2	(10)
NCS DC73510	148	(5)	400	62	25	114	(7.5)	(1.9)	.	260	.	.	.	(0.3)	(1.9)

CRM MULTI-METAL ORE

analysis in mass % except g/T for grams per ton and * for mg/kg

Number	Ag	Al ₂ O ₃	As	Bi	Cd	Cu	Fe	Hg*	Pb	S	Sb	SiO ₂	Sn	Zn	LOI	Units
NCS DC29114	0.03679	(1.42)	0.138	.	0.066	0.071	(11.48T)	(270)	22.96	(15.92)	0.044	(20.20)	.	16.22	(12.14)	50 g
NCS DC29112	0.0362	(7.83)	0.082	.	.	0.10	(11.61T)	(0.233)	2.93	(8.17)	0.011	(59.40)	.	0.51	(10.49)	50 g
NCS DC29113	0.0103	(3.97)	0.040	.	.	0.075	(8.65T)	(0.074)	2.19	(6.02)	0.00383	(31.99)	.	1.54	(13.40)	50 g
NCS DC35008	19.8 g/T	.	0.084	.	.	0.037	22.62	.	2.07	.	0.013	.	0.125	0.51	.	60 g
NCS DC29115	0.000530	(3.25)	0.0095	.	0.119	0.021	(3.93T)	(84.8)	1.25	(16.30)	0.00205	(41.23)	.	30.19	(9.52)	50 g
NCS DC29111	0.00129	(9.96)	0.0090	.	0.019	0.020	(2.62T)	(12.6)	0.48	(3.13)	0.00090	(69.88)	.	4.94	(3.70)	50 g
NCS DC35009	.	6.70	2.17	0.120	.	1.09	.	.	0.095	.	.	4.99	0.930	1.49	.	60 g

T = Total Fe as Fe₂O₃

CRM MULTI-METAL ORE WITH EXTENSIVE ANALYSIS

analysis listed in mass % CAN PTC-1b shows classical and instrumental values for Cu and Ni # SiO₂* RTS-5: 100 g others: 200 g

Number	Al	As	Ca	Cu	Fe	Mg	Mo	Ni	Pb	S	Si	Sn	W	Zn	LOI
CAN RTS-5	6.25	0.1286	3.86	0.0647	11.9	3.31	(0.0001338)	0.1104	0.00663	1.924	19.20	.	.	0.0105	(9.90)
CAN MP-2a	5.99	(0.558)	3.22	0.0459	5.00	0.0923	0.1586	(0.00098)	0.277	0.716	31.2	0.0537	0.338	0.566	(4)
CAN SU-1b	4.30	0.000249	2.21	1.185	25.54	1.790	(0.0004)	1.953	0.0058	14.14	15.23	.	.	0.0235	(8)
CAN PTC-1b	(0.7518)	0.0222	(0.571)	7.919,7.97#	36.78	0.441	(0.0011)	11.256,11.29#	0.0795	29.95	2.468	(0.0120)	.	0.2083	(13.44)
CAN MP-1b	2.30	2.47	3.069	8.19	0.024	0.0285	.	.	2.091	13.79	16.79*	1.61	(0.1100)	16.67	.
CAN RTS-5	6.25	0.1286	3.86	0.0647	11.9	3.31	(0.0001338)	0.1104	0.00663	1.924	19.20	.	.	0.0105	(9.90)

continued analysis listed in mg/kg except % for mass %

Number	Ag	Au	Ba	Be	Bi	C%	Cd	Ce	Co	Cr	Cs	Dy	Er	Eu	Ga	Gd	Ge
CAN RTS-5	1.50	0.408	252	(0.7)	(2.05)	(1.617)	.	(17.0)	76.9	261	(1.0)	(2)	(2)	(0.6)	(14)	.	.
CAN MP-2a	4.82	(0.06)	12.3	1.25	989	(0.04)	14.5	357	5.50	150	5.78	32.5	(22.8)	(0.1)	(26.2)	24.8	(8)
CAN SU-1b	6.39	(0.2)	(350)	(0.4)	(2.73)	(0.04)	(3)	(35)	672	(320)	(0.3)	(1.4)	(0.7)	(0.7)	(10)	(2)	.
CAN PTC-1b	53.1	1.99	(61.5)	.	.	.	(38)	.	3253	(40)
CAN MP-1b	470	.	.	.	954	(0.028)	527	.	(4)	(1)	.	.	.

Number	H ₂ O%	Hf	Ho	In	Ir	K%	La	Li	Lu	Mn%	Na%	Nb	Nd	P%	Pd	Pr	Pt
CAN RTS-5	(1.4)	0.850	(9.7)	(16.9)	(0.3)	0.1092	1.285	(4)	(8)	0.0369	(0.14)	.	(0.2)
CAN MP-2a	.	9.40	(7.04)	(12.09)	.	(1.226)	157	81	4.36	0.1018	(0.03)	97	117.9	(0.0090)	.	38.5	.
CAN SU-1b	.	.	(0.3)	.	.	(0.6)	(17)	.	(0.09)	0.0703	(1.6)	(3)	(15)	(0.06)	0.791	.	0.491
CAN PTC-1b	0.81	.	.	(0.2)	(0.15)	.	.	.	(0.0193)	(0.17)	9.46	.	6.47
CAN MP-1b	.	(6)	.	(565)	.	(0.2)	.	.	(4)	(0.0480)	.	.	.	(0.02)	.	.	.

Number	Rb	Rh	Sb	Sc	Se	Sm	Sr	Ta	Tb	Te	Th	Ti	Tl	Tm	U	V	Y	Yb	Zr
CAN RTS-5	(30.5)	.	SO : (1.23%)	.	(8.03)	.	130.6	.	.	.	(2.25)	3132	.	.	.	(61.2)	(10.1)	.	.
CAN MP-2a	229	.	4 (7.84)	4.87	.	26.7	12.3	.	4.82	(5.75)	61.3	268	(3.16)	4.10	37	.	(229)	28.8	134
CAN SU-1b	(13)	.	(0.2)	(9)	(20.7)	(3)	(280)	11.6	(0.3)	.	(0.2)	.	(82.5)	(7)	(0.6)
CAN PTC-1b	.	(0.5)	(6)	(120)	.	(30)	.	.	(30)	.	.	.	(696)	.	.	(20)	(20)	(3)	.
CAN MP-1b	.	.	(54.0)	(3)	(5)	.	(50)	.	.	.	(20)	.	.	.	(150)

CRM MULTI-METAL ORE								
analysis listed in mass percent % and mg/kg * 250 g units								
Number	Pb%	Cu%	Ni%	S%	Zn%	Ag*	As*	Co*
GBM315-16	18.8046	0.0582	0.0011	8.40	5.9724	577.4	.	.
GBM309-10	4.9144	0.0503	0.0069	.	18.7866	47.3	65	78
GBM913-11	3.5846	0.1453	0.0027	11.18	7.8969	32.5	.	.
GBM315-13	3.4311	1.2570	0.0209	5.34	3.7358	41.5	.	.
GBM306-12	2.6812	1.4804	0.9483	.	2.0500	.	.	.
GBM398-1	2.6770	1.4874	0.9511	.	2.0418	5.2	8	24
GBM995-8	2.5919	0.0264	0.0060	.	12.4308	52.0	53	.
GBM914-13	2.3186	0.8583	0.0052	3.32	2.5491	29.2	.	.
GBM913-12	2.2958	0.1122	0.0028	7.98	7.2593	21.8	.	.
GBM309-3	2.1335	0.0331	0.0058	.	10.8553	30.7	68	67
GBM915-13	2.0016	0.8462	0.0013	28.99	11.5823	182.9	.	.
GBM314-1	2.0010	0.8432	0.0008	.	11.6161	182.3	5246	83
GBM908-12	1.0924	0.2625	.	7.77	2.5161	22.0	.	.
GBM310-3	1.0687	1.4443	0.0073	.	3.0935	19.4	1276	62
GBM313-2	0.8219	0.8049	0.0042	.	1.0891	205.5	157	43
GBM315-14	0.7349	2.9574	0.0301	4.95	2.2481	36.3	.	.
GBM314-11	0.4745	3.4499	0.0063	4.90	1.5367	51.6	.	.
GBM914-10	0.4671	0.1864	0.0011	.	0.9697	9.4	11	20
GBM315-9	0.4600	3.4274	0.0071	.	1.5131	50.2	278	135
GBM311-12	0.3600	1.0188	0.0668	4.4	1.4425	20.6	.	.
GBM311-3	0.3522	1.0089	0.0642	.	1.4291	20.4	359	122
GBM311-4	0.2730	0.6199	0.0233	.	1.2022	15.1	241	86
GBM312-1	0.2638	0.3332	0.0119	.	0.3414	7.2	110	28
GBM313-9	0.2560	0.3313	0.0120	.	0.3394	6.6	112	32
GBM915-7	0.2487	0.5934	0.0073	.	0.5037	12.8	329	47
GBM915-3	0.0031	0.0132	0.0051	.	0.0171	1.1	33	40
GBM908-10	0.2067	0.3630	0.2257	.	0.1046	3.0	55	24
GBM311-2	0.1903	0.2272	0.0391	.	0.1944	10.4	741	57
GBM7	0.1604	1.3973	0.0049	.	0.0861	7.5	341	74
GBM399-6	0.1446	2.1373	0.0020	.	0.2488	15.5	175	4
GBM906-10	0.1252	0.1916	0.0032	.	0.0595	1.6	18	27
GBM316-1	0.1248	0.2966	0.0052	.	0.2572	6.3	163	40
GBM999-8	0.1061	0.1852	0.3014	.	0.0537	1.8	185	25
GBM913-8	0.0923	0.4379	0.0006	.	0.0127	6.7	1409	12
GBM397-7	0.0908	0.0687	0.0243	.	0.0801	3.1	770	.
GBM914-8	0.0849	0.6241	0.0414	.	0.3786	8.5	316	90
GBM309-4	0.0795	2.2334	0.0056	.	0.0914	42.3	83	89
GBM396-6	0.0774	1.3903	0.0083	.	0.0260	5.4	541	.
GBM301-4	0.0762	0.1656	0.1430	.	0.0448	1.9	308	123
GBM313-1	0.0738	0.3079	0.0015	.	0.1170	4.9	26	10
GBM913-7	0.0633	0.7990	0.0010	.	0.0431	7.0	2052	17
GBM316-2	0.0626	0.1523	0.0041	.	0.1331	3.2	82	35
GBM910-7	0.0592	0.5335	0.0117	.	0.1249	7.1	80	86
GBM314-2	0.0532	0.0419	0.0029	.	0.0975	3.3	4912	7
GBM901-5	0.0521	0.1520	0.0063	.	0.5189	6.0	96	43
GBM904-3	0.0489	0.0515	0.0323	.	0.0464	1.8	270	82
GBM313-1	0.0477	0.2964	0.0005	.	0.0787	10.0	705	9
GBM908-2	0.0462	0.0859	0.0866	.	0.0334	1.3	786	61
GBM908-6	0.0461	0.0441	0.4736	.	0.1354	1.2	14	832
GBM305-4	0.0416	0.1138	0.0475	.	0.1199	2.6	263	70
GBM913-9	0.0404	0.4542	0.0006	.	0.0158	3.8	611	13
GBM301-9	0.0389	0.2881	0.0102	.	0.7208	11.2	317	48
GBM907-8	0.0388	0.0339	0.4295	.	0.1234	1.0	11	219
GBM998-4	0.0357	0.7514	0.0025	.	0.0038	4.4	244	47
GBM309-6	0.0341	0.0277	1.6113	.	0.1344	1.2	18	909
GBM996-4	0.0336	0.0492	0.0036	.	0.0968	3.6	442	2
GBM300-5	0.0322	1.0779	0.0076	.	0.0035	3.6	571	332
GBM311-6	0.0302	0.1037	0.0336	.	0.0571	4.2	1540	40
GBM913-10	0.0300	0.3019	0.0007	.	0.0380	3.0	823	10
GBM913-4	0.0291	0.1556	0.0104	.	0.0282	2.0	255	193
GBM906-6	0.0288	0.0171	0.0013	.	0.0210	392.8	10	8
GBM312-6	0.0270	0.3705	0.0229	.	0.0795	7.4	32	34
GBM311-8	0.0266	0.1350	0.2504	.	0.0233	1.2	57	140
GBM915-10	0.0261	0.0907	0.0317	.	0.0938	14.4	497	149
GBM903-5	0.0254	0.1424	0.1772	.	0.0689	3.3	932	50
GBM913-5	0.0243	0.2880	0.0024	.	0.3722	0.3	2492	55
GBM398-5	0.0243	0.1223	0.1944	.	0.0215	3.5	282	83
GBM302-5	0.0239	0.1059	0.0498	.	0.0359	1.8	1873	50
GBM313-3	0.0239	0.0875	0.0256	.	0.1012	4.0	1039	37
GBM316-10	0.0223	0.4554	0.0006	.	0.0178	1.3	179	8
GBM913-6	0.0207	0.3321	0.0004	.	0.0029	0.5	1104	6
GBM907-11	0.0191	0.3873	4.5163	7.56	0.1033	4.7	.	.
GBM397-8	0.0189	0.1419	0.1320	.	0.0363	1.5	55	.
GBM914-2	0.0175	0.1824	0.0099	.	0.0626	5.9	9	26
GBM912-11	0.0170	2.8323	0.0042	3.49	0.0937	8.8	.	.
GBM910-5	0.0161	0.7952	0.0036	.	0.0491	2.7	52	90
GBM311-1	0.0152	0.1233	0.0214	.	0.0629	6.0	395	34
GBM310-6	0.0146	0.6951	0.0083	.	0.0046	2.6	572	476
GBM310-5	0.0140	0.0335	0.3691	.	0.0483	0.5	12	247
GBM312-7	0.0137	0.6182	0.0346	.	0.1157	6.8	14	34
GBM915-1	0.0135	0.0485	0.0176	.	0.0513	7.2	246	89
GBM305-3	0.0135	0.0451	0.0272	.	0.0372	1.7	656	46
GBM311-7	0.0134	0.0947	0.0126	.	0.0452	2.0	830	28
GBM314-4	0.0126	0.3302	0.0021	.	0.0454	5.5	4	19
GBM914-1	0.0118	0.1152	0.0069	.	0.0427	4.8	6	24
GBM305-9	0.0114	0.0565	0.2551	.	0.0104	0.8	219	47
GBM910-4	0.0110	0.5412	0.0030	.	0.0377	1.8	40	67
GBM313-4	0.0110	0.0342	0.0250	.	0.0337	2.7	385	33
GBM908-1	0.0110	0.0074	0.0053	.	0.1012	1.7	10	34
GBM312-8	0.0107	0.1530	0.1927	.	0.0675	1.5	5	22
GBM311-5	0.0105	0.3001	0.0300	.	0.0367	2.5	1153	36
GBM313-7	0.0103	0.2976	0.0299	.	0.0367	2.4	1131	35
GBM914-5	0.0094	1.2970	0.0210	.	0.0592	4.1	43	40
GBM309-1	0.0092	0.1554	0.0023	.	0.5239	6.0	95	22
GBM305-2	0.0091	0.0054	0.0045	.	0.0080	1.2	2	27
GBM915-5	0.0087	0.0307	0.0106	.	0.0333	3.9	128	61
GBM314-12	0.0077	2.9880	0.0127	7.79	0.5516	3.1	.	.
GBM312-5	0.0075	0.0339	0.0114	.	0.0398	5.0	17	34
GBM398-2	0.0074	0.0235	0.0273	.	0.0105	1.0	206	22
GBM903-10	0.0074	0.0198	0.0559	.	0.0140	1.2	2779	57
GBM305-6	0.0069	0.0242	0.0062	.	0.0120	1.5	315	31
Number	Pb%	Cu%	Ni%	S%	Zn%	Ag*	As*	Co*

CRM MULTI-METAL ORE								
analysis listed in mass percent % and mg/kg * 250 g units								
Number	Pb%	Cu%	Ni%	S%	Zn%	Ag*	As*	Co*
GBM315-5	0.0067	0.0045	0.0005	.	0.0154	14.8	72	9
GBM308-15	0.0065	1.5595	2.3913	23.40	0.0113	4.4	.	.
GBM303-6	0.0056	1.3967	0.0106	.	0.0057	5.5	603	151
GBM315-1	0.0051	0.0049	1.9801	.	0.0314	0.6	4	4393
GBM915-6	0.0050	0.0186	0.0068	.	0.0225	2.1	63	47
GBM914-7	0.0050	0.0034	0.0005	.	0.0084	8.8	49	9
GBM903-7	0.0049	0.0313	0.0021	.	0.0669	3.0	33	12
GBM997-9	0.0047	0.0485	0.0016	.	0.0016	0.9	5	.
GBM914-3	0.0046	0.1441	0.0010	.	0.0193	1.2	34	34
GBM312-4	0.0045	0.6004	0.0025	.	0.0127	3.5	9	26
GBM914-15	0.0044	0.0060	1.5093	0.06	0.0354	0.6	.	.
GBM316-3	0.0043	0.0019	0.0011	.	0.0048	0.2	5	8
GBM915-8	0.0042	0.5897	0.4259	.	0.0025	6.6	1873	1083
GBM914-4	0.0042	0.0864	0.0006	.	0.0202	0.8	13	15
GBM998-10	0.0041	1.5414	2.3610	.	0.0090	3.5	25	1202
GBM399-7	0.0040	0.0041	0.0033	.	0.0051	0.6	14	24
GBM305-10	0.0037	0.0114	0.0604	.	0.0066	0.7	569	22
GBM910-10	0.0037	0.0033	0.0013	.	0.0051	0.5	2	9
GBM906-9	0.0035	0.0094	0.0071	.	0.0079	4.0	50	20
GBM904-10	0.0035	0.0162	0.2709	.	0.0039	0.5	35	59
GBM398-10	0.0034	0.0206	0.0175	.	0.0134	1.9	131	48
GBM903-3	0.0034	0.0167	0.2758	.	0.0042	0.7	33	60
GBM307-5	0.0034	0.0031	0.0029	.	0.0018	1.0	23	4
GBM315-10	0.0033	0.2646	0.0017	.	0.0066	4.7	4	14
GBM308-3	0.0033	0.0928	0.0036	.	0.0109	14.5	41	63
GBM912-16	0.0031	0.3442	3.7560	11.51	0.0107	1.9	.	.
GBM904-5	0.0031	0.1111	0.0039	.	0.0026	0.8	108	155
GBM915-3	0.0031	0.0132	0.0051	.	0.0171	1.1	33	40
GBM912-5	0.0031	0.0487	0.0019	.	0.0088	4.2	4	18
GBM310-8	0.0029	0.0396	0.0028	.	0.0027	0.5	85	50
GBM313-10	0.0029	0.0268	0.0025	.	0.0086	3.2	3	22
GBM305-1	0.0029	0.0175	0.0351	.	0.0217	0.6	795	46
GBM911-5	0.0029	0.0042	0.0020	.	0.0060	0.8	6	15
GBM314-7	0.0029	0.0026	0.0014	.	0.0047	0.4	4	9
GBM399-2	0.0028	0.0205	0.0014	.	0.0309	0.		

CRM NICKEL ORE

analysis listed in mass % except * which is mg/kg

GBM: 250 g IGS, NCS: 50 g units

Number	Ni	Cd	Co	Cr	Cu	Fe	Mn	Pb	S	Zn	Ag*	Al ₂ O ₃	CaO	MgO	P	SiO ₂	Ti
GBM909-15	11.5901	.	.	.	1.3120	.	.	0.2120	26.7	2.6608	13.5
NCS DC28072	5.71	0.047	0.042	0.015	0.270	23.73	0.037	0.040	2.51	4.65	.	3.91	6.47	1.14	1.61	21.10	0.15
NCS DC28079	3.98	0.028	0.041	0.364	0.169	20.74	0.147	0.030	1.41	2.85	.	3.55	4.54	8.67	1.08	27.48	0.098
GBM911-14	3.2361	.	.	.	0.2856	.	.	0.0091	10.5	0.0180	1.7
GBM310-12	2.9934	.	.	.	0.9062	.	.	0.0030	26.4	0.0102	14.4
GBM312-16	2.7983	.	.	.	0.3082	.	.	0.0059	9.8	0.0142	1.8
GBM910-13	2.6969	.	.	.	0.2306	.	.	0.0034	8.2	0.0152	1.9
GBM911-15	2.2856	.	.	.	0.5003	.	.	0.0253	8.1	0.0288	2.9
NCS DC28078	2.18	(<0.0015)	0.055	0.76	0.0058	14.89	0.254	0.0020	0.034	0.079	.	1.59	0.46	21.28	0.029	39.20	0.027
GBM310-11	2.1342	.	.	.	1.1695	.	.	0.0041	18.0	0.0142	3.5
GBM915-11	2.0568	.	.	.	1.4092	.	.	0.0183	6.95	0.3387	4.3
GBM915-12	2.0155	.	.	.	0.9137	.	.	0.0051	6.35	0.0573	2.5
GBM307-13	1.9995	.	.	.	0.1251	.	.	0.0045	6.78	0.0117
NCS DC28077	1.97	(<0.0015)	0.060	0.823	0.0016	14.84	0.263	0.0015	0.016	0.021	.	1.03	0.14	25.49	0.0043	36.00	0.017
IGS 21	1.97	.	0.069	.	0.798	23.40
GBM907-12	1.8948	.	.	.	0.0837	.	.	0.0068	2.89	0.0274
NCS DC28076	1.86	(<0.0015)	0.065	0.92	0.0017	15.20	0.282	0.0016	0.016	0.021	.	1.04	0.10	25.70	(<0.007)	34.70	0.015
NCS DC28075	1.70	(<0.0015)	0.043	0.80	0.0025	14.92	0.294	0.0013	0.014	0.019	.	2.00	0.385	21.05	0.0043	38.77	0.039
GBM907-15	1.6470	.	.	.	0.0290	.	.	0.0361	2.84	0.1396
GBM915-14	1.3070	.	.	.	1.7404	.	.	0.0095	2.08	0.0067	18.5
NCS DC28080	1.30	(<0.0025)	0.033	1.38	0.0071	34.55	0.192	0.0019	0.180	0.022	.	6.53	0.070	10.54	0.020	15.48	0.092
GBM316-16	1.2733	.	.	.	0.0050	.	.	0.0012	0.10	0.0243	1.2
GBM316-15	1.2308	.	.	.	0.0056	.	.	0.0022	0.10	0.0257	1.0
NCS DC28073	1.17	(<0.0015)	0.042	0.95	0.0049	18.57	0.327	0.0024	0.024	0.019	.	2.90	0.82	20.75	(<0.007)	37.41	0.024
GBM907-16	1.1511	.	.	.	0.0163	.	.	0.0105	0.79	0.0674
NCS DC28074	0.892	(<0.0020)	0.014	1.84	0.012	46.99	0.149	0.0023	0.288	0.023	.	10.29	0.033	0.51	0.030	2.52	0.145
GBM305-16	0.6503	.	.	.	0.0381	.	.	0.0026	.	0.0092

CRM NICKEL ORE

certified analysis listed in mg/kg except % which is mass %

Number	Ag	Au	Cu%	Ir	Ni%	Os	Pd	Pt	Rh	Ru	Units
VS 1702-86	23.4	0.84	(3)	0.11	5.4	0.06	30.0	8.6	0.98	0.34	200 g

CRM NICKEL SULPHIDE ORE

analysis listed as mass % except ** for ppb * indicates certified as element instead of oxide

much more detail on certificates 10 g units

Number	Ni	Co	Fe	S	Al ₂ O ₃	As	Ca	Cr	Cu	K	MgO	Mn	Na	P	SiO ₂	Ti	Au**	Pd**	Pt**
OREAS 78	25.79	23.74	.	28.61	LOI: (2.36)
OREAS 77b	11.24	0.1604	29.21	22.29	1.86*	.	3.11	0.0341	0.3163	0.344	2.67*	0.068	0.406	.	9.24*	0.065	.	.	.
OREAS 77a	10.71	0.1675	34.0	26.83	1.48	0.0162	.	0.0840	0.4400	.	7.27	.	.	.	13.3	.	61	566	1088
OREAS 76b	7.78	0.1103	21.76	15.18	2.58*	.	3.115	0.0663	.	0.474	5.80*	0.079	0.510	0.0139	13.74*	0.103	.	.	.
OREAS 76a	7.40	0.1215	24.6	18.0	1.78	0.0117	.	0.1283	0.2974	.	16.5	.	.	.	21.7	.	41	403	701
OREAS 75b	5.38	0.0788	17.17	10.79	2.79*	.	3.03	0.0942	0.1483	0.410	8.75*	0.097	.	0.0187	15.67*	0.139	.	.	.
OREAS 75a	5.25	0.0894	19.1	12.5	1.99	0.0080	.	0.1552	0.2005	.	22.3	.	.	.	27.3	.	34	280	353
OREAS 74b	3.39	0.0502	12.40	6.57	3.55*	.	3.09	0.0981	0.0947	0.691	9.23*	.	0.692	0.0195	19.36*	0.1555	.	.	.
OREAS 74a	3.24	0.0581	13.7	7.48	2.21	0.00496	.	0.1780	0.1240	.	27.9	.	.	.	32.4	.	21	172	223
OREAS 14p	2.09	0.997	51	150	99
OREAS 73b	1.50	0.0246	8.63	2.90	3.77*	.	3.15	0.1172	0.0430	0.586	11.80*	0.115	0.736	0.024	20.89*	0.191	.	.	.
OREAS 72b	0.709	0.0126	6.80	1.44	4.75*	.	2.83	0.0971	0.0193	1.09	9.61*	0.1004	0.958	0.0267	23.92*	0.213	.	.	.
OREAS 70b	0.223	.	5.51	0.286	3.81*	.	3.07	0.1243	.	0.585	13.54*	0.115	.	0.024	22.42*	0.178	.	.	.

RM NIOBIUM ORE

analysis listed in mass %

100g units

Number	Nb ₂ O ₅	Al ₂ O ₃	BaO	CO ₂	CaO	CeO ₂	F	Fe	K ₂ O	La ₂ O ₃	MgO	MnO	Na ₂ O	Nd ₂ O ₃	P ₂ O ₅
FQZ 1807	61.95	0.382	0.192	0.056	13.18	0.567	4.12	2.29	0.320	0.150	0.150	0.310	5.42	0.209	0.112
DH X1803	60.62	0.291	0.201	0.097	13.02	0.556	3.65	3.50	0.233	0.153	0.136	0.325	5.28	0.207	0.102
FQZ 1808	56.71	0.614	0.277	0.139	11.67	0.588	4.02	5.41	0.463	0.185	0.177	0.383	4.73	0.214	0.134
DH X1802	0.200	2.67	0.162	30.16	26.96	0.098	.	5.72	1.41	0.041	13.51	0.827	0.109	0.049	3.92
DH X1806	0.095	0.945	0.046	36.82	27.77	0.086	.	5.44	0.525	0.040	16.16	1.12	0.061	0.038	1.75

continued

Number	S	SiO ₂	SrO	Ta ₂ O ₅	ThO ₂	TiO ₂	U ₃ O ₈	V ₂ O ₅	Y ₂ O ₃	ZnO	ZrO ₂	-H ₂ O 900°C
FQZ 1807	0.052	2.28	1.18	0.276	0.734	3.86	0.190	0.056	0.098	0.005	0.868	0.611
DH X1803	0.051	1.91	1.20	0.273	0.770	4.26	0.202	0.073	0.085	0.001	0.847	.
FQZ 1808	0.056	3.52	1.31	0.265	0.802	3.92	0.153	0.075	0.074	0.003	0.837	0.668
DH X1802	0.616	8.91	0.116	0.002	0.010	0.237	0.002	0.027	0.016	0.039	0.074	.
DH X1806	0.798	3.38	0.274	(0.001)	0.010	0.089	(0.002)	(0.009)	(0.009)	0.013	0.027	.

CRM NIOBIUM ORE

certified analysis

analysis listed in mass %

informational values

200 g units

Number	Nb	Al	Ca	Fe	K	Mg	Mn	Na	P	Pb	S	Si	Sr	Zn	LOI
CAN OKA-1	0.37	0.9	31.3	2.8	0.3	1.3	1.1	0.2	1.1	1.1	0.6	2.4	1.0	0.05	31.9

CRM NOBLE METAL ORE

analysis listed in mg/kg except % which is mass %

Number	Ag	Au	Cu%	Fe%	Ir	Ni	Pd	Pt	Rh	Ru	S	Units	Notes
CAN PTM-1a	(135)	3.30	.	.	(0.35)	.	10.01	7.31	(0.92)	(0.7)	.	400 g	
CAN WPR-1a	1.02	(0.05)	0.299	11.34	(0.02)	0.439	0.614	0.452	.	.	1.768	400 g	more data under Peridotite
SARM 66	.	0.66	.	.	7.1	.	51.1	91.2	17.5	26.5	.	500 g	PGM+Au: 161.1 ppm
SARM 72	.	0.13	.	.	(0.28)	.	4.24	3.97	0.83	1.18	.	2.5 kg	last of stock
SARM 75	.	(0.053)	.	.	.	0.23	0.61	0.32	.	.	(0.39)	3 kg	
SARM 107	.	0.046	.	.	(0.14)	.	0.926	1.99	0.320	0.626	.	3 kg	
SARM 81	.	(0.034)	.	.	(0.18)	.	1.46	2.50	0.490	(0.76)	.	3 kg	
CAN PTA-1	3.05	.	.	.	400 g	

CRM NOBLE METAL ORE - CERTIFIED BY ANALYTICAL METHOD

analysis listed in mg/kg Ni = Nickel Sulfide, Pb = Lead Extraction analysis listed in mass % AR = Aqua Regia, M = M/ICP, X = XRF

Number	Pd(Ni)	Pd(Pb)	Pt(Ni)	Pt(Pb)	Rh(Ni)	Ru(Ni)	Au(Ni)	Au(Pb)	Ir(Ni)	Co(M)	Co(AR)	Cu(M)	Cu(AR)	Cu(X)	Ni(M)	Ni(AR)	Ni(X)
AMIS 0164	27.32	26.75	24.52	23.86	1.87	(1.63)	2.89	2.97	(0.48)	0.1126	0.1138	2.55	2.556	(2.4211)	3.555	3.602	.
AMIS 0314	11.74	11.35	34.17	32.20	(1.89)	5.13	2.50	2.53	(0.91)	0.0242	0.0212	0.7326	0.7115	0.7183	0.8790	0.8429	0.9073
AMIS 0414	1.37	1.38	2.20	2.19	(0.21)	(0.38)	(0.15)	(0.16)	(0.07)	0.0081	(0.0045)	0.0648	0.0648	.	0.1406	0.1148	(0.1382)
AMIS 0354	(1.33)	1.34	(2.19)	2.25	(0.25)	(0.39)	(0.68)	0.71	(0.08)	(0.0145)	(0.00911)	0.0582	0.0586	0.0587	(0.1839)	0.1493	(0.1886)
AMIS 0326	1.25	1.26	1.04	1.05	0.081	(0.09)	(0.17)	0.17	(0.02)	0.0083	0.0059	0.1403	0.1416	0.1391	0.2446	0.2241	0.2385
AMIS 0367	0.86	0.84	1.80	1.80	(0.098)	(0.21)	0.18	(0.17)	(0.035)	0.0094	(0.0036)	0.0826	0.0827	.	0.1766	0.1281	0.1755
AMIS 0395	0.59	0.62	(0.50)	0.51	(0.044)	(0.052)	(0.089)	(0.095)	(0.012)	0.0089	(0.0072)	0.0847	0.0861	0.0834	0.1606	0.1485	(0.1628)
AMIS 0209	0.64	0.63	1.20	1.21	(0.09)	(0.17)	(0.09)	(0.09)	(0.031)	0.0049	0.0030	0.0447	0.0449	(0.0445)	0.0909	0.0747	.
AMIS 0442	.	2.66	.	2.11	0.19	.	.	0.33	.	0.00877	0.00645	0.1029	0.1020	0.0975	0.1996	0.1758	0.2008
AMIS 0443	.	0.97	.	0.78	(0.07)	.	.	(0.14)	.	0.00988	(0.00700)	0.0951	0.0935	0.0879	0.1918	0.1678	(0.1833)
AMIS 0452 *	.	0.288	(0.526)	0.549	0.058	.	.	0.091	.	(0.00753)	(0.00219)	0.0204	0.0205	.	0.0849	(0.0425)	0.0849
AMIS 0451 *	.	(0.254)	(0.534)	(0.518)	.	.	.	(0.044)	.	(0.0142)	(0.001312)	0.00755	0.00757	.	0.0903	0.0214	.

analysis listed in mass % S by combustion, rest by XRF SP.G = Specific Gravity 4E = sum Pd + Pt + Rh + Au 100 g units

Number	Al ₂ O ₃	CaO	Co	Cr	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	S	SiO ₂	TiO ₂	Sp.G	LOI	4E g/t
AMIS 0164	(4.4)	(6.5)	(0.1187)	.	(0.1)	(25.3)	(0.2)	(12.7)	(0.2)	(0.4)	(11.6)	31.31	(0.1)	3.34	(8.8)	56.68
AMIS 0314	7.75	5.46	(0.0271)	.	0.96	15.68	0.14	17.04	0.15	0.58	3.49	44.23	0.22	3.11	(4.92)	50.30
AMIS 0414	13.19	7.10	.	.	1.34	9.67	0.14	13.34	0.16	1.05	(0.31)	52.97	0.27	3.03	(0.32)	3.922
AMIS 0354	5.50	4.01	.	.	1.94	18.32	0.09	23.65	0.24	0.37	0.36	44.63	0.59	3.330	.	4.45
AMIS 0326	4.65	3.00	(0.0084)	.	0.56	7.63	0.19	11.05	0.13	0.58	.	70.05	0.11	2.92	(1.56)	2.54
AMIS 0367	9.21	6.00	.	.	0.80	11.27	0.21	18.51	0.18	0.91	.	51.82	0.25	3.17	(0.53)	2.94
AMIS 0395	7.42	5.07	.	.	1.09	9.78	0.27	15.15	0.26	0.40	0.65	54.49	0.23	2.92	(5.03)	1.22
AMIS 0209	5.80	3.10	.	.	0.48	4.74	0.14	6.38	(0.07)	0.46	0.20	77.84	0.11	2.84	(0.29)	2.02
AMIS 0442	7.93	8.27	.	.	0.28	10.69	0.29	18.53	0.23	0.83	.	48.34	0.19	3.02	3.93	5.171
AMIS 0443	8.10	7.08	.	.	1.72	11.61	0.26	20.06	0.32	0.62	.	44.67	0.25	3.03	(4.77)	1.96
AMIS 0452 *	13.78	7.62	.	.	2.15	10.08	0.17	15.37	0.15	1.12	.	48.15	0.25	3.07	(1.05)	0.96
AMIS 0451 *	11.61	4.05	.	.	13.42	16.89	0.13	16.69	(0.19)	0.62	.	36.19	0.46	3.46	.	0.83

CRM NOBLE METAL ORE

analysis listed in ppb (ng/g) mass % except * which is mg/kg GPP: 1kg units CAN WMS-1A: 200g
NCS: 500g or 1kg other CAN: 400g

Number	Au	Ir	Os	Pd	Pt	Rh	Ru	Hg	Al ₂ O ₃	As*	Cr*	Cu	Fe ₂ O ₃	K ₂ O	MnO	Ni	S
NCS DC29116	(2310)	1.6	1.9	1680	2430	1.9	1.5	(0.70)	(1.47)	(12.24)	(0.17)	3.58	(13.10)	(0.12)	(0.11)	1.78	(7.44)
NCS DC29119	(2120)	1.9	1.6	1330	4440	1.4	0.71	(7.01)	(0.87)	(537.6)	(0.06)	0.62	(1.59)	(0.12)	(0.047)	1.76	(0.19)
GPP-10	1576	.	.	2008	2349
NCS DC29118	(1450)	3.2	3.0	700	900	3.2	3.5	(1.01)	(4.90)	(21.58)	(0.093)	3.25	(24.09)	(0.35)	(0.13)	1.76	(13.41)
NCS DC29118	(1450)	3.2	3.0	700	900	3.2	3.5	(1.01)	(4.90)	(21.58)	(0.093)	3.25	(24.09)	(0.35)	(0.13)	1.76	(13.41)
NCS DC29117	(1430)	4.4	3.7	600	10610	3.6	4.2	(1.39)	(4.50)	(22.6)	(0.16)	3.01	(26.66)	(0.39)	(0.12)	0.053	(13.57)
GPP-06	980	.	.	709	938
GPP-02	929	.	.	523	505
GPP-14	909	.	.	481	503
GPP-05	859	.	.	699	912
GPP-11	722	.	.	567	592	last
GPP-13	612	.	.	390	307
GPP-09	603	.	.	408	343
CAN WMS-1A	300	(322)	(150)	1450	1910	222	(145)	.	Al:1.350	30.9	(68)	1.396	45.4	Fe	.	.	28.17
NCS DC29120	(170)	23.6	8.2	400	380	18.0	7.8	(58.1)	(2.83)	(66.0)	(0.30)	0.11	(9.30)	(0.12)	(0.14)	0.22	(0.17)
GPP-04	80	.	.	98	88
GPP-12	50	.	.	47	48
GPP-08	49	.	.	45	54	last
CAN UMT-1	48	8.8	.	106	128	9.5	10.9
NCS DC73357	(45)	28	15.6	568	440	22	13
GPP-07	25	.	.	23	28
NCS DC73353	10	0.05	0.06	2.3	1.6	0.95	(0.10)
CAN TDB-1	6.3	.	.	22.4	5.8
GPP-03	4	.	.	7	8
CAN WGB-1	2.9	(0.33)	.	13.9	6.1	(0.32)	(0.3)	.	.	.	291	.	6.71	0.94	MgO: 9.40	.	.
NCS DC73358	(1.8)	1.2	0.64	15.2	14.7	1.1	0.66
NCS DC73354	1.1	4.3	9.6	4.6	6.4	1.3	14.8
NCS DC73352	0.9	0.032	0.05	0.26	0.26	0.017	(0.05)
NCS DC73356	.	136	353	11.3	20	10	527
NCS DC73398	.	28	43	570	1900	7.3	74
NCS DC73399	.	2.1	(2)	1670	5700	1.5	(2)

Number	Au	Ir	Os	Pd	Pt	Rh	Ru	Hg	Al ₂ O ₃	As*	Cr*	Cu	Fe ₂ O ₃	K ₂ O	MnO	Ni	S
--------	----	----	----	----	----	----	----	----	--------------------------------	-----	-----	----	--------------------------------	------------------	-----	----	---

CRM OBSIDIAN

Number	analysis listed in mass %											analysis listed in mg/kg							
	Al ₂ O ₃	CaO	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	Cu	Ni	Pb	Rb	Sr	Th	Ti	U
SRM 278	14.15	0.983	1.36	2.04	4.16	(0.23)	0.052	4.84	0.036	73.05	0.245	5.9	3.6	16.4	127.5	63.5	12.4	0.54	4.58

RM OLIVINE WITH EXTENSIVE ANALYSIS

Number	* provisional analysis, listed in mass %														100 g units	
	Al ₂ O ₃	SiO ₂	FeO	T.Fe ₂ O ₃	CaO	H ₂ O-	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI		
IAG MUH-1 *	1.341	40.375	3.49	8.59	1.213	0.689	9.31	0.011	38.26	0.119	0.096	0.009	0.035	9.40		
Number	* provisional analysis continued, listed in mg/kg except % which is mass %															
	As	Ba	Be	Ce	Co	Cs	Cr%	Cu	Dy	Er	Eu	Ga	Gd	Hf	Ho	
IAG MUH-1 *	3.819	4.98	0.012	0.212	106.2	0.098	0.2666	19.0	0.155	0.109	0.026	1.40	0.106	0.038	0.035	
Number	La	Li	Lu	Nb	Nd	Ni%	Pb	Pr	Rb	Sb	Sc	Sm	Sn	Sr		
	IAG MUH-1 *	0.136	1.62	0.019	0.062	0.18	0.2091	0.422	0.035	0.27	0.134	9.0	0.068	0.06	8.6	
Number	Ta	Tb	Th	Tm	U	V	Y	Yb	Zn	Zr						
	IAG MUH-1 *	0.008	0.021	0.016	0.017	0.016	38.1	0.94	0.12	44.5	1.7					

RM OLIVINE

Number	typical analysis listed in mass %														100 g units	
	MgO	SiO ₂	Fe	Al ₂ O ₃	C tot	CO ₂	CaO	Co ₃ O ₄	Cr ₂ O ₃	K ₂ O	Mn ₃ O ₄	NiO	P ₂ O ₅	TiO ₂	-H ₂ O at 900°C	
DH 4912	49.18	41.6	5.07	0.432	0.054	0.046	0.081	0.016	0.383	0.014	0.103	0.354	.	0.002	1.25	
DH 4911	47.37	42.63	5.52	0.95	.	.	0.491	0.019	0.425	0.024	0.118	0.340	<0.01	0.013	.	

CRM OOZE

Number	Type	analysis listed in mass %																
		SiO ₂	Al ₂ O ₃	Ba	CO ₂	CaO	Ce	Cr	FeO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI	
VS 5370-90	Calcareous	11.90	3.60	0.010	32.20	39.23	.	0.0034	0.17	2.44	0.51	3.44	0.218	1.86	0.23	0.30	36.6	
VS 5371-90	Siliceous	59.60	8.96	0.15	2.70	6.40	0.033	0.0080	1.2	5.05	1.39	3.16	0.37	4.52	0.12	0.59	9.6	
continued		analysis listed in mass %																
Number	As	B	Org.C	Cu	Ni	S	Sn	Sr	V	Zn	Zr							
VS 5370-90	.	.	.	0.0030	0.0038	0.19	0.021	0.12	0.0057	0.010	0.008							
VS 5371-90	0.0020	0.007	0.34	0.014	0.010	0.17	0.00032	0.034	0.0085	0.0090	0.010							
continued		analysis listed in mg/kg																
Number	Au	Be	Co	Cs	Ga	La	Li	Mo	Nb	Nd	Pb	Rb	Sc	Sm	Th	U	Y	Yb
VS 5370-90	.	1.0	12	.	5	7	13	4	.	.	11	11	6	.	3	.	9	.
VS 5371-90	0.004	1.6	30	3.0	11	15	18	2.8	10	13	24	46	17	2.5	5	1.5	16	2.2

PEGMATITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %																		IAG: RM, ~35 g units	NCS: CRM, 70 g units
Number	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	Mn	MnO	Na ₂ O	P ₂ O ₅	SO ₃	SiO ₂	TiO ₂	LOI		
NCS DC71313	13.19	(0.05)	(0.1)	(0.03)	(0.04)	(0.24T)	(1.02)	6.22	0.13	(0.01)	.	1.60	0.18	0.07	76.40	0.61	1.27		
IAG OU-9	12.35	.	0.29	.	.	0.74	.	1.36	.	.	0.11	4.17	0.03	.	79.5	0.057	0.78		
continued analysis listed in mg/kg except % which is mass %																			
Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd		
NCS DC71313	(0.09)	3.1	(1.9)	(728)	1.3	(0.07)	0.15	(5)	(1.5)	4.8	1.8	4.2	0.20	0.12	(0.16)	13.5	0.22		
IAG OU-9	.	.	.	8.75	.	.	.	7.24	.	.	403.3	.	1.70	0.30	0.05	56.6	2.53		
Number	Ge	Hf	Hg	Ho	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se		
NCS DC71313	1.5	(0.8)	(0.008)	(0.04)	(3.3)	14.4	0.03	(0.29)	14.6	1.5	(1.6)	34.6	0.48	155	0.64	(2.85)	(0.015)		
IAG OU-9	4.95	.	.	0.15	2.03	694.6	0.04	.	155.3	5.07	.	.	1.24	2501	7.67	2.77	.		
Number	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr				
NCS DC71313	(0.24)	3.5	45.5	1.3	(0.04)	0.66	.	(0.02)	(0.75)	44.5	3.2	1.6	0.21	20.3	22.6				
IAG OU-9	3.15	.	.	124.7	0.46	5.08	13.8	0.05	4.37	.	6.1	8.14	.	28.15	.				

CRM PERIDOTITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %																	
Number	Al	Al ₂ O ₃	C	Ca	CaO	Co	CO ₂	Cr	Cu	Fe	Fe ₂ O ₃	T.Fe ₂ O ₃	FeO	H ₂ O-	H ₂ O+	K	K ₂ O
VS 2111-81	.	1.84	.	.	1.26	0.0159	0.69	0.320	0.0140	.	.	11.58	8.83	.	.	.	0.044
JP-1	0.35	0.66	(0.0764)	0.39	0.55	0.0116	.	0.2807	0.000672	5.85	1.98	8.37	5.99	0.44	2.39	0.002	0.003
CAN WPR-1a	2.621	.	(0.15)	2.528	.	0.0213	.	(0.322)	0.299	11.34	0.156	.
Number	Mg	MgO	Mn	MnO	Na	Na ₂ O	Ni	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂	V	Zn	LOI
VS 2111-81	.	37.12	.	0.183	.	0.105	0.160	.	.	0.030	.	45.54	.	0.107	0.0039	0.0137	.
JP-1	26.9	44.60	0.094	0.121	0.02	0.021	0.2460	.	(0.002)	(0.00269)	19.81	42.38	.	(0.006)	0.00276	0.00418	.
CAN WPR-1a	(15.22)	.	0.138	.	(0.050)	.	0.439	0.0303	.	1.768	17.62	.	0.3527	.	0.0135	0.0160	(8.42)
analysis listed in mg/kg																	
Number	Ag	As	Au	B	Ba	Be	Bi	Cd	Ce	Cl	Cs	Dy	Er	Eu	F	Ga	Gd
VS 2111-81	66	5.9	.
JP-1	(1.5)	0.34	(0.00023)	(1.4)	(19.5)	.	.	(0.011)	(0.19)	(97)	(0.15)	(0.022)	(0.016)	(0.004)	(14)	(0.7)	(0.015)
CAN WPR-1a	1.02	9.3	(0.05)	.	70.6	(0.2)	0.122	0.598	9.69	.	2.38	1.624	0.886	0.497	.	7.04	1.76
Number	Ge	Hf	Hg	Ho	In	Ir	La	Li	Lu	Mo	Nb	Nd	Os	Pb	Pd	Pr	
VS 2111-81	1.6	1.3	.	.	.	6.7	.	.	
JP-1	(0.49)	0.2	(0.0053)	(0.018)	.	(2)	0.084	(1.79)	(0.0044)	(0.087)	1.48	(0.072)	(0.0079)	(0.12)	(0.0013)	(0.02)	
CAN WPR-1a	(0.3)	1.142	(0.05)	0.322	(0.0899)	(0.2)	4.04	25.6	0.121	(0.9)	(3.88)	6.26	.	7.92	0.614	1.362	
Number	Pt	Rb	Re	Ru	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	
VS 2111-81	11.3	.	.	3.2	
JP-1	(0.0049)	(0.8)	(0.000015)	(0.0065)	(0.034)	7.24	.	0.019	(0.05)	(3.32)	(0.02)	(0.003)	.	0.19	(0.003)	.	
CAN WPR-1a	0.452	7.06	.	.	3.13	17.3	(7.7)	1.617	(1.16)	19.5	(0.242)	0.269	(0.958)	(0.64)	(0.0752)	0.126	
Number	U	W	Y	Yb	Zr	Units											
VS 2111-81	.	.	.	1.5	21	40 g											
JP-1	0.036	(0.85)	1.54	0.022	5.92	20 g											
CAN WPR-1a	.	.	8.39	0.79	(41.8)	400 g											

CRM PHOSPHATE ROCK

* CaO+SrO	** AFPC Method	(s) = soluble analysis listed in mass %																GPO: 10 g units	SRM: 90 g units	others: 100 g units
Number	P ₂ O ₅	CaO	Al ₂ O ₃	CO ₂	F	Fe ₂ O ₃	TFe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	S	SO ₃	SiO ₂	SrO	TiO ₂	LOI			
SARM 32	39.96	54.44	(0.05)	1.61	2.49	0.14	.	.	0.50	(0.026)	.	.	.	(0.4)	0.52	.	.			
GBW 07210	36.89	51.32*	0.58	2.15	3.54	.	1.04	0.17	0.43	0.024	0.33	.	.	3.26	0.077	0.037	.			
IPT 18B	35.7	52.6	0.35	.	1.33	0.21	.	0.23	1.65(s)	.	0.14(s)	.	.	1.15	0.48(s)	.	.			
SRM 120c	33.34**	48.02**	1.30	3.27**	3.82**	1.08	.	0.147	0.32**	0.027	0.52	(0.37)	.	5.5**	(0.1)	0.103	.			
BCR 032	32.98	51.76	0.55	5.10	4.04	0.231	.	.	0.403	.	.	.	1.84	2.09	.	.	.			
SRM 694	30.2	43.6	1.8	.	3.2	0.79	.	0.51	0.33	0.0116	0.86	.	.	11.2	.	(0.11)	.			
GPO-01	28.66	40.08	6.92	.	.	3.412	.	0.10	0.83	0.093	0.307	.	1.318	4.381	.	0.37	12.45			
USZ 14-94	26.38	38.85	0.85	5.84	.	.	0.63	0.092	2.26	20.57	.	.	6.43			
GPO-15	25.22	45.12	0.74	.	.	0.803	.	0.25	2.90	0.010	1.039	.	2.426	7.77	.	0.05	12.32			
GPO-14	24.52	44.77	0.78	.	.	0.819	.	0.26	3.07	0.047	0.979	.	2.284	8.13	.	0.05	12.96			
GBW 07211	20.86	40.71*	2.58	18.46	2.05	.	1.08	0.28	8.19	0.015	0.059	0.79	.	3.61	0.16	0.14	.			
GPO-16	17.76	42.08	0.80	.	.	0.693	.	0.22	6.38	0.011	0.704	.	1.692	6.97	.	0.05	21.69			
GPO-18	15.09	19.53	7.80	.	.	1.323	.	1.10	0.68	0.067	0.125	.	0.169	50.02	.	0.32	3.09			
USZ HF	13.81	33.80	0.37	0.077	8.30	.	0.12	.	.	28.04	.	.	.			
GPO-17	13.55	39.14	1.83	.	.	1.287	.	0.61	5.82	0.014	0.563	.	1.369	11.62	.	0.09	23.47			
GPO-11	9.72	13.46	9.39	.	.	5.002	.	3.02	0.71	0.040	1.224	.	0.461	50.934	.	0.20	5.22			
GBW 07212	6.06	19.42*	4.06	16.41	0.51	.	3.08	2.63	7.12	0.026	0.14	.	.	38.80	0.055	0.48	.			
GPO-13	4.94	6.84	10.02	.	.	5.391	.	3.75	0.68	0.030	1.454	.	0.239	62.622	.	0.16	3.43			

continued

analysis listed in mass %

analysis listed in mg/kg

Number	BaO	CdO	U	U ₃ O ₈	V ₂ O ₃	V ₂ O ₅	As	B	Cd	Cl	Co	Cr	Cu	Hg	I	Mn	Ni	Ti	V	Zn
SARM 32	(640)
GBW 07210	52
IPT 18B
SRM 120c	.	.	.	0.0135	0.016
BCR 032	9.5	22.6	20.8	.	0.59	257	33.7	0.0551	.	18.8	34.6	171	153	253
SRM 694	.	0.015	0.01414	.	.	0.31
GPO-01	0.05
USZ 14-94
GPO-15	0.015	.	(0.00568)
GPO-14	0.015	.	(0.00566)
GBW 07211	59
GPO-16	0.017	.	(0.00465)
GPO-18	0.060	.	(0.00168)
USZ HF
GPO-17	0.017	.	(0.00324)
GPO-11	0.02	last of stock
GBW 07212	last of stock
GPO-13	0.01	last of stock

CRM PLAGIOGNEISS WITH EXTENSIVE ANALYSIS

analysis listed in mass %

100 g units

Number	Al ₂ O ₃	Ba	CO ₂	CaO	Cr	F	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	Zr	LOI
VS 8871-2007	15.90	0.091	(0.13)	2.85	0.0182	0.0573	4.14	6.06	(1.1)	3.56	2.59	0.069	2.25	0.080	64.92	0.70	0.0234	0.76

analysis listed in mg/kg

Number	Ag	As	B	Be	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Ge	Hf	Ho	La	Li	Lu	Mo
VS 8871-2007	(0.09)	(2.0)	(100)	0.97	(0.10)	104	19.7	182	0.32	31	3.3	2.1	1.8	18.5	4.7	(1.1)	6.2	0.69	53	21	0.31	1.7

Number	Nb	Nd	Ni	Pb	Pr	Rb	S	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn
VS 8871-2007	10.0	43.8	60	14.2	11.5	55	(74)	(0.05)	14.3	6.9	(0.6)	364	0.40	0.6	11.3	0.31	0.33	0.8	98	(0.3)	17.8	2.02	81

CRM PROPHILITE

analysis listed in mass %

50 g units

Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	SiO ₂	TiO ₂	LOI
JCRM R802	32.3	0.04	0.23	.	.	0.07	<0.01	.	0.09	0.05	.	60.7	0.19	6.0
NCS DC60127	23.58	0.17	.	1.94	4.15	0.38	0.087	0.0037	0.34	0.20	0.61	66.84	0.70	5.48
NCS DC60128	22.20	0.066	.	0.22	5.57	0.028	0.041	0.0040	0.043	0.11	0.17	70.34	0.18	6.34

CRM PYROXENITE

analysis listed in mass % 100 g units

Number	Al ₂ O ₃	CaO	Cr ₂ O ₃	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	SiO ₂	TiO ₂
SARM 5	4.18	2.66	3.50	10.59	0.87	0.09	25.33	0.22	0.37	51.10	0.20

CRM QUARTZ

analysis listed in mass %

T = Total

SRM: 5 g US: 25 g

Number	SiO ₂	Al ₂ O ₃	CaO	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	K ₂ O	MgO	Mn	Na ₂ O	P ₂ O ₅	TiO ₂	Respirable Crystalline Phase
US QLO-1A SRM 1878b	65.6	16.2	3.17	2.97	1.02	4.35	3.60	1.00	.	4.20	0.25	0.62	96.56 +/- 0.40%

continued analysis, for SUS only, listed in mg/kg

Number	Ag	As	B	Ba	Br	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ge	La	Li	Lu
US QLO-1A	0.064	(3.5)	36	1370	(2.1)	54	220	7.2	3.2	1.8	29	3.8	2.3	1.43	280	(1.3)	27	25	0.37

Number	Mo	Nb	Nd	Pb	Rb	S	Sm	Sn	Sr	Ta	Tb	Th	Tm	U	V	W	Y	Yb	Zn	Zr
US QLO-1A	2.6	10	(26)	20	74	(30)	4.9	2.3	340	0.82	0.71	4.5	0.37	1.9	54	0.58	24	2.3	61	185

CRM RARE EARTH ORE WITH EXTENSIVE ANALYSIS

% = mass percent, * = mg/kg

AMIS: 100 g or 1 kg

GRE: 10 g

USZ: 100 g units

Number	As*	Ba	Be*	Ce%	Co*	Cr*	Cs*	Cu*	Dy*	Er*	Eu*	Ga*	Gd*	Hf*	Ho*
GRE-06	.	3442	.	15.41	615	111	1773	.	3197	.	70.67
AMIS 0185	(31.01)	(6%)	.	4.075	(6.06)	(48)	(0.2)	(15.35)	(27.1)	(4.24)	(0.009)	(183)	(244)	(1.35)	(3.2)
USZ 25-2006	156	917*	.	2.90	32.46	.	.	128	206	79.50	211	.	553	.	36.60
USZ 42-2006	224	307*	.	2.76	7.89	(34)	(55)	27.37	57.63	(23.88)	87.22	.	(295)	.	7.86
GRE-02	.	.	.	1.6797	28.56	7.96	139.9	.	262.2	.	2.87
GRE-03	.	.	.	0.43541	92.33	28.84	75.24	.	191	.	13.53
GRE-05	.	.	100.89	0.012105	195.6	149.16	3.29	99.91	74	310.7	44.7

continued AMIS 0185 lists La by XRF and M/ICP, some informational values rounded, contains 22 other informational values

Number	La%	Li*	Lu*	Mo*	Nb*	Nd%	P%	Ni*	Pb%	Pr%	Rb*	Sc*	Sm%	Sn%	Sr%
GRE-06	9.14	.	6.81	.	.	7.12	(8.14)	.	.	1.92	.	114	(0.83)	.	.
AMIS 0185	3.003, 2.976	(18.50)	(0.56)	(22.33)	(73)	0.9238	.	(12.57)	(0.0145)	0.3471	(4.70)	(15.4)	0.0556	(1.13)	(5.3344)
USZ 25-2006	1.93	.	7.64	(23.86)	.	0.88	.	70.80	0.11	0.28	43	.	0.09	.	2.24
USZ 42-2006	2.11	21.78	.	34.40	31	0.65	.	13.18	0.16	0.23	67.12	(15.17)	0.0539	.	0.49
GRE-02	0.9786	.	0.42	.	383.6	0.7048	0.19955	.	.	0.1883	.	76.7	0.07692	.	.
GRE-03	0.2224	.	1.81	.	3524	0.18359	6.6520	.	.	0.04966	.	49.85	0.02794	.	.
GRE-05	0.002738	(241)	19.32	.	2832	0.006839	.	.	.	0.001779	.	.	0.004614	0.0308	.

Number	Ta*	Tb*	Th*	Ti%	Tm*	U*	V*	W*	Y*	Yb*	Zn%	Zr%
GRE-06	.	229	1540	Tl*(0.53)	10.27	30.22	.	.	1424	46.32	0.1450	(0.0168)
AMIS 0185	(0.16)	(15.3)	(237)	.	.	(46)	(54)	(1)	(62)	(2.75)	(0.0622)	(0.0057)
USZ 25-2006	.	54.60	217	.	.	.	138.6	.	959	54.52	0.06	.
USZ 42-2006	.	(45)	946	.	.	(52)	115	(19)	167	17.85	0.0469	(0.01)
GRE-02	5.58	14.62	.	0.2628	0.527	.	.	.	55.97	2.96	.	0.01363
GRE-03	161.5	21.65	.	0.979	3.08	.	.	.	320.6	15.5	.	0.0969
GRE-05	181.9	24.55	314.51	.	23.39	42.8	.	9.04	1076.3	145.28	.	0.7133

continued analysis for AMIS, GRE-06 and USZ listed in mass % RExOy = Total Rare Earths

Number	Al	Ca	Fe	K	Mg	Mn	S	Si	TiO ₂											
GRE-06	1.22	1.88	14.42	(0.08)	0.34	0.7396	0.35	0.8388	0.59											
Number	RE _x O _y	Al ₂ O ₃	CO ₂	CaF ₂	CaO	F%	FeO	Fe ₂ O ₃	H ₂ O-	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	SiO ₂	TiO ₂	LOI	Density
AMIS 0185	2.22	.	.	.	11.48	(Fe:3.59)	5.29	.	.	(0.10)	4.69	(1.09)	(0.17)	1.74	S:1.93	21.53	(0.081)	20.69	3.28	
USZ 25-2006	7.56	2.47	1.04	(32.90)	25.51	(1.89)	0.14	13.45	(0.67)	.	0.91	0.50	0.14	0.92	19.26	4.58	14.86	0.15	6.78	.
USZ 42-2006	8.27	2.72	29.00	.	32.68	(1.61)	(0.08)	5.71	(0.19)	(2.03)	1.55	2.78	1.67	0.25	0.22	(0.14)	11.86	0.20	30.56	.

CRM RARE EARTH ORE

analysis listed in mass %

Number	RE _x O _y	Al ₂ O ₃	CaO	F-	FeO	Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI
NCS DC86318	4.30	(14.26)	0.29	0.017	0.20	2.24	3.60	5.52	(0.11)	0.052	0.66	(0.020)	66.90	0.17	5.43
NCS DC86317	1.83	16.59	(0.11)	0.15	0.18	0.71	4.63	4.03	0.13	0.10	0.13	(0.0073)	70.92	(0.018)	5.42
NCS DC86312	0.784	19.00	0.029	0.014	(0.072)	3.46	6.64	2.11	0.231	0.069	0.064	(0.029)	66.72	0.530	6.80
NCS DC86311	0.486	14.65	(0.031)	0.034	(0.039)	1.13	3.61	4.92	0.080	0.016	0.155	(0.0025)	74.34	(0.023)	3.70
NCS DC86310	0.085	14.70	(0.026)	0.034	0.054	1.15	3.61	4.98	0.077	0.017	0.158	(0.0027)	74.55	0.022	3.77
NCS DC86309	0.092	19.04	(0.033)	0.016	(0.071)	3.49	6.64	2.13	0.229	0.070	0.062	0.029	67.28	0.537	6.73

Number	CeO ₂	Cs ₂ O	Dy ₂ O ₃	Er ₂ O ₃	Eu ₂ O ₃	Gd ₂ O ₃	Ho ₂ O ₃	La ₂ O ₃	Li ₂ O	Lu ₂ O ₃
NCS DC86318	0.053	0.00126	0.37	0.20	0.00219	0.25	(0.064)	0.23	0.0121	0.030
NCS DC86317	0.021	0.0148	0.12	0.068	0.000956	0.091	(0.023)	0.25	0.0396	0.00645
NCS DC86312	0.023	0.00055	0.021	0.011	0.00750	0.026	0.00409	0.277	0.00398	0.00136
NCS DC86311	0.00348	0.00178	0.036	0.022	0.00018	(0.027)	0.00750	0.011	0.015	0.00304
NCS DC86310	0.00217	0.00177	0.00563	0.00364	0.000036	0.00324	0.00120	0.00200	0.015	0.00055
NCS DC86309	0.00915	0.00056	0.00273	(0.0016)	0.00081	0.00317	0.00057	0.031	0.00403	0.00020

Number	Nd ₂ O ₃	Pr ₆ O ₁₁	Rb ₂ O	Sc ₂ O ₃	Sm ₂ O ₃	Tb ₄ O ₇	Th	Tm ₂ O ₃	Y ₂ O ₃	Yb ₂ O ₃	Units
NCS DC86318	0.40	0.089	0.0404	0.00072	0.20	0.055	0.00670	0.031	2.16	0.21	70 g
NCS DC86317	0.24	0.066	0.12	0.00101	0.066	0.019	0.00210	0.00829	0.80	0.051	70 g
NCS DC86312	0.186	0.054	0.011	0.00118	0.033	0.00407	0.00236	0.00151	0.124	0.0100	70 g
NCS DC86311	0.022	(0.0045)	0.067	0.00089	0.015	0.00577	0.00390	0.00316	0.303	0.022	70 g
NCS DC86310	0.00276	0.00063	0.069	0.00095	0.00157	0.00082	0.00405	0.00057	0.057	0.00366	70 g
NCS DC86309	0.017	0.00492	0.012	0.00113	0.00338	0.00054	0.00245	0.00024	(0.018)	0.00141	70 g

CRM		RARE EARTH ORE																		
		analysis listed in mass % and mg/kg * RE _x O _y = total rare earth oxides																		
Number	RE _x O _y %	CeO ₂ %	Dy*	Er*	Eu ₂ O ₃ %	Gd ₂ O ₃ %	Ho*	La ₂ O ₃ %	Lu*	Nd ₂ O ₃ %	Pr ₂ O ₃ %	Sc*	Sm ₂ O ₃ %	Tb*	ThO ₂ %	Tm*	Y ₂ O ₃ %	Yb*		
UNS TRV	13.82	6.64	(207.1)	(41.2)	0.042	(0.089)	(41.5)	(4.23)	(6.7)	(1.94)	(0.71)	(22.5)	0.22	(82.3)	(0.29)	(14.8)	(0.048)	(21.6)		
continued		analysis listed in mass % T = total																		
Number	Al ₂ O ₃	BaO	CO ₂	CaO	F	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	T.S	SO ₃	SiO ₂	SrO	TiO ₂	LOI	
UNS TRV	(0.52)	17.02	(16.5)	13.54	1.57	3.61	8.34	(1.24)	0.15	2.27	1.15	(0.07)	(0.12)	6.05	(13.58)	(2.47)	5.92	0.079	17.16	
continued		analysis listed in mg/kg																		
Number	Ag	As	Be	Bi	Cd	Co	Cr	Cu	Li	Mo	Ni	Pb	V	Zn	Units					
UNS TRV	(6.7)	(335)	(4.2)	(72.9)	(7.5)	(26.5)	(40.6)	(41.5)	(28.8)	71.4	(44.0)	(332.9)	(74.2)	767.9	100 g					

CRM		RARE EARTH ORE																			
		analysis listed in mg/kg except % which is mass %																			
		100 g units																			
Number	Al %	As	Ba	Be	Bi	C	Ca %	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Fe %	Ga	Gd	Ge	Hf	Ho
CAN REE-1	3.59	124	100.1	(590)	(0.652)	(786)	2.30	3960	1.58	277	1.07	79.7	847	701	23.5	(4.16)	(64)	433	(3)	479	208
continued																					
Number	In	K %	La	Li	Lu	Mg %	Mn %	Mo	Na %	Nb	Nd	Ni	P	Pb	Pr	Rb	S %	Sb	Sc	Si %	
CAN REE-1	(0.2)	3.09	1661	(205)	(92.4)	(0.895)	(0.155)	(36.6)	1.445	4050	1456	24.7	261	1137	435	1047	(0.03)	(3.16)	(8)	31.36	
Number	Sm	Sn	Sr	Ta	Tb	Th	Ti %	Tl	Tm	U	V	W	Y	Yb	Zn	Zr %	H ₂ O%	LOI%			
CAN REE-1	381	498	129	(231)	106.2	719	(0.384)	(1.85)	106.0	137	(9.9)	(10)	5480	678	(1870)	1.91	(0.6)	(2)			

CRM RHYOLITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	SiO ₂	Al	Al ₂ O ₃	CO ₂	CaO	Fe ₂ O ₃	FeO	T.Fe ₂ O ₃	H ₂ O	K	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Si	TiO ₂	
JR-2	75.69	6.73	12.72	.	0.50	0.27	0.44	0.77	+1.19	-0.22	3.69	4.45	0.04	0.112	3.99	0.012	35.38	0.07
JR-1	75.45	6.79	12.83	.	0.67	0.35	0.49	0.89	+1.16	-0.20	3.66	4.41	0.12	0.099	4.02	0.021	35.27	0.11
US RGM-2 *	73.4	7.31	14.0	.	1.23	.	.	1.86	.	.	3.61	4.35	0.28	.	4.14	(0.05)	34.3	0.25
GBW 07113	72.78	.	12.96	0.52	0.59	1.14	1.86	.	1.18	.	.	5.43	0.16	0.14	2.57	0.045	.	0.30
JR-3	72.76	.	11.90	.	0.093	2.61	1.86	4.72	.	.	.	4.29	0.050	0.083	4.69	0.017	.	0.21

continued analysis listed in mg/kg except % which is mass % and * which is ppb

Number	Ag	As	Au*	B	Ba	Be	Bi	C	Ca%	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er
JR-2	.	19.2	0.13	145	39.5	3.75	0.62	.	0.36	0.023	38.8	.	0.46	3.10	25.0	1.36	6.63	4.36
JR-1	.	16.3	0.25	117	50.3	3.34	0.56	70.8	0.48	0.026	47.2	920	0.83	2.83	20.8	2.68	5.69	3.61
US RGM-2 *	.	3.3	.	.	842	(2.5)	.	.	0.88	.	48	(536)	2	(4)	.	9.8	(3.3)	(2.2)
GBW 07113	0.08	0.66	.	3.5	506	4.09	0.60	(0.15%)	.	0.14	163	.	2.40	7.3	3.34	10.9	8.19	4.31
JR-3	65.8	7.6	327	.	0.98	3.5	1.0	2.9	.	.

Number	Eu	F%	Fe%	Ga	Gd	Ge	Hf	Hg*	Ho	In	La	Li	Lu	Mg%	Mn%	Mo	Na%	Nb	Nd
JR-2	0.14	0.1109	0.54	17.9	5.83	.	5.14	.	1.39	.	16.3	79.2	0.88	0.02	0.087	3.35	2.96	18.7	20.4
JR-1	0.30	0.0991	0.62	16.1	5.06	1.88	4.51	.	1.11	.	19.7	61.4	0.71	0.07	0.077	3.25	2.98	15.2	23.3
US RGM-2 *	(0.7)	.	1.30	16	3.6	.	(6.0)	.	0.8	.	25	(58)	0.4	0.17	(0.0273)	(2.5)	3.07	(9)	20
GBW 07113	1.18	0.13	.	20.5	9.47	1.17	10.8	5	1.64	0.09	82.7	12.7	0.67	.	.	2.46	.	34.3	64.5
JR-3	0.53	.	.	36.6	.	.	40.3	.	.	.	179	.	2.8	.	.	0.49	.	510	107

Number	Ni	P%	Pb	Pr	Rb	S	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Th	Ti%	Tl
JR-2	.	0.005	21.5	4.75	303	.	1.51	5.59	.	5.63	3.51	8.11	2.29	1.10	31.4	0.04	1.85
JR-1	.	0.009	19.3	5.58	257	13.3	1.19	5.07	.	6.03	2.86	29.1	1.86	1.01	26.7	0.066	1.56
US RGM-2 *	(4)	(0.02)	20	(5)	147	.	(0.8)	5	.	4	(4)	108	(1)	(0.6)	15	0.15	(0.9)
GBW 07113	64.5	.	33.3	18.4	213	0.009%	0.38	5.15	0.04	11.7	3.35	43.0	2.41	1.51	27.1	.	0.83
JR-3	.	.	32.8	33.1	453	.	.	0.50	.	21.3	17.4	10.4	36.8	4.29	112	.	.

Number	Tm	U	V	W	Y	Yb	Zn	Zr	Units
JR-2	0.74	10.9	3.00	.	51.1	5.33	27.8	96.3	20 g
JR-1	0.67	8.88	7.0	1.59	45.1	4.55	30.6	99.9	20 g
US RGM-2 *	.	5.9	.	(2)	24	.	33	222	50 g * Provisional Analysis
GBW 07113	0.73	4.83	3.8	1.10	42.5	4.51	86.3	403	50 g
JR-3	.	21.1	4.2	.	166	20.3	209	1494	100 g

RUTILE

= class, where 1 = CRM and 2 = RM analysis listed in mass %

#	Number	TiO ₂	Ti	Al ₂ O ₃	CaO	Cr ₂ O ₃	Fe ₂ O ₃	Nb	Nb ₂ O ₅	P ₂ O ₅	SiO ₂	V ₂ O ₅	ZrO ₂
1	SRM 670	96.16	.	.	.	0.23	0.86	.	.	.	0.51	0.66	0.84
1	DSZU 123.48-05	95.2	.	0.27	.	.	1.43	.	.	0.036	1.28	.	1.07
2	DH 5805	93.35	.	0.500	0.035	0.117	3.53	.	0.532	0.147	0.297	0.243	0.198
1	IGS 32	.	57.19	(0.27)

Number	Tot.C	MgO	Mn ₃ O ₄	S	SO ₃	Units
SRM 670	90 g
DSZU 123.48-05	0.0100	20 or 100 g last of stock
DH 5805	0.23	0.032	0.124	0.027	.	100 g
IGS 32	45 g

CRM SANDSTONE

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂
VS 2888-84	(66.14)	(11.49)	(3.05)	(3.78)	(0.039)	(3.16)	(4.17)	(1.82)	(1.49)	(0.16)	(2.98)	(0.12)	0.60	(0.48)
KZ 8077-94	0.33	.
KZ 8076-94

continued

mg/kg

Number	Cu	Pb	Zn	Ag	Re	Units
VS 2888-84	1.55	0.103	0.023	25.9	1.65	50 g
KZ 8077-94	0.11	.	.	10.2	0.14	100 g
KZ 8076-94	0.036	.	.	0.64	0.023	100 g

SANDSTONE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	C(org)	C(tot)	CO ₂	CaO	F	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI
GBW 07106	90.36	3.52	(0.05)	(0.10)	(0.19)	0.30	0.0183	0.61	3.22	1.01	0.65	0.082	.	0.061	.	.	1.10
UL PRI-1	68.60	10.84	.	.	(2.62)	2.49	(0.0383)	(2.07)	3.32	.	3.79	3.24	0.04	1.71	0.18	0.71	4.99
IAG OU-8	54.120	6.548	.	.	.	16.711	.	.	1.304	.	2.967	1.879	0.138	0.677	.	0.244	15.301

continued

analysis listed in mg/kg except * which is ng/g

analysis listed in mg/kg except * which is ng/g

Number	Ag	As	Au*	B	Ba	Be	Bi	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Ge	Hf
GBW 07106	0.062	9.1	(1.8)	34	143	0.97	0.18	0.060	48	(44)	6.4	20	1.8	19	4.1	2.0	1.02	5.3	4.5	1.16	6.6
UL PRI-1	.	(4.7)	.	(52)	531	1.4	(0.1)	.	82	.	7.4	78	(2.2)	(3.5)	4.3	(2.7)	1.29	(13)	5.3	(<5)	10.7
IAG OU-8	528	1.42	(0.043)	.	41.8	.	.	(21.5)	3.23	8.36	2.25	1.59	0.67	6.28	2.32	(1.10)	4.72

Number	Hg	Ho	I	In	La	Li	Lu	Mn	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	S	Sb
GBW 07106	0.008	0.75	(0.2)	(0.026)	21	11.1	0.30	155	0.76	5.9	21	16.6	970	7.6	5.4	29	860	0.60
UL PRI-1	.	(1)	.	(<1)	38	.	0.41	.	(0.7)	13	36	21	.	(13)	(9.5)	90	(357)	(0.3)
IAG OU-8	.	0.51	.	.	13.8	10.3	0.26	.	.	(4.46)	12.4	.	.	9.64	3.12	64.6	.	0.22

Number	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Ti	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Class	Units
GBW 07106	4.2	0.08	4.7	1.1	58	0.38	0.79	0.038	7.0	1580	0.36	0.32	2.1	33	1.2	21.5	1.9	20	214	CRM	70 g
UL PRI-1	9.7	.	6.6	(2)	88	1	0.85	.	11.3	.	(0.2)	(0.39)	2.5	65	(2.2)	25	2.8	47	386	CRM	50 g
IAG OU-8	(3.63)	.	2.42	.	264.4	0.32	0.36	.	9.5	.	1.01	0.24	0.74	29.8	.	16.0	1.66	.	182.7	RM	~35 g

CRM SCHIST

analysis listed in mass %

UL: 50 g units

UNS, VS: 100 g units

US: 25 g units

Number	SiO ₂	Al ₂ O ₃	BaO	CO ₂	CaO	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SrO	TiO ₂	LOI
US SDC-1	65.8	15.8	.	.	1.40	3.93	2.62	6.32	.	3.28	1.69	.	2.05	0.16	.	1.01	.
VS 3191-85	63.40	16.71	.	.	0.09	4.65	.	7.6	.	3.56	2.52	0.13	0.08	0.030	.	1.01	4.54
UNS MI	62.19	14.54	0.10	2.13	1.96	(6)	.	6.41	(12)	2.15	3.28	0.25	3.33	(10)	0.016	0.71	(16)
UL SBO1	55.16	18.24	.	.	1.76	(5.61)	.	7.15	.	3.55	(1.97)	0.18	0.66	0.17	.	0.94	9.67

continued

analysis listed in mg/kg

Number	Ag	As	B	Ba	Be	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F
US SDC-1	.	0.22	(13)	630	3	.	93	(32)	18	64	4	30	(6.7)	(4.1)	(1.7)	600
VS 3191-85	.	.	100	950	3.5	.	90	.	27	70	(7)	46
UNS MI	(0.006)	(0.007)	(0.005)	.	(0.006)	0.0100	.	.	0.0120	0.1073	.	0.0438
UL SBO1	.	(32)	.	549	(3.2)	.	101	.	22	116	(6.8)	33	(5.1)	(3.4)	1.64	.

Number	Ga	Gd	Ge	Hf	Hg	Ho	La	Li	Lu	Mn	Mo	Nb	Nd	Ni	Pb	Pr	Rb	S
US SDC-1	21	7	.	8.3	(0.2)	(1.5)	42	34	.	880	.	(21)	40	(38)	25	.	127	.
VS 3191-85	(15)	.	(2)	.	.	.	(60)	(0.6)	.	(1.6)	16	.	45	.	15	.	150	.
UNS MI	(0.010)	(0.003)	.	0.0372	0.0945	.	0.0539	3300	.	
UL SBO1	(23)	6.2	5	.	(1.3)	48	.	0.49	.	.	17	42	60	27	11.1	163	.	

Number	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
US SDC-1	0.54	17	8.2	3.0	180	(1.2)	(1.2)	12	(0.7)	(0.65)	3.1	102	(0.80)	.	(4)	103	290
VS 3191-85	.	22	.	(4)	39	.	.	(12)	.	.	(2)	100	.	48	5	100	230
UNS MI	0.1052	(0.003)	0.0198	(0.003)	3000	0.1518
UL SBO1	.	17	7.8	.	150	1.4	1	15.2	.	(0.43)	3.1	153	.	32	3.2	82	183

RM	SEDIMENT													analysis listed in mass %		~35 g units	
Number	Al ₂ O ₃	CO ₂	CaO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Type				
IAG OU-10	10.97	.	2.34	4.92	1.28	1.77	0.120	2.43	0.090	73.12	0.534	(2.20)	Longmyndian Greywacke Loess				
IAG UoK	6.2	14.94	16.31	2.1	1.3	2.9	0.0644	1.058	0.13	53.24	0.423	16.03					
analysis listed in mg/kg																	
Number	As	Ba	Be	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd		
IAG OU-10	.	311	(1.1)	.	(2.8)	(38.0)	12.0	34.0	1.68	22.3	3.65	2.2	1.00	12.0	3.7		
IAG UoK	6.7	200.97	1.102	0.1	.	53	5.95	105.7	2.72	11.31	4.02	2.382	0.888	7.087	4.465		
Number	Hf	Ho	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Sm	Sr	
IAG OU-10	3.3	0.75	18.8	(26.0)	0.34	(0.98)	7.6	18.7	(17.7)	26.9	4.7	35.9	.	11.3	(3.9)	174	
IAG UoK	(9.10)	0.80	25.54	21.90	0.37	(1.40)	8.61	24.32	42.71	11.34	6.24	51.2	0.580	(5.93)	5.01	278.5	
Number	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr					
IAG OU-10	0.56	0.61	5.0	(0.23)	0.34	1.09	77	.	20.5	2.2	54	123					
IAG UoK	(0.73)	0.687	8.111	0.338	0.339	2.697	(37.56)	(1.45)	23.18	2.420	34.4	.					

LAKE SEDIMENT - SEQUENTIAL EXTRACTION METHOD

BCR 701, CRM 20g	Cd	Cr	Cu	Ni	Pb	Zn
Step 1	7.34	2.26	49.3	15.4	3.18	205
Step 2	3.77	45.7	124	26.6	126	114
Step 3	0.27	143	55.2	15.3	9.3	45.7
Concentration	(0.13)	(62.5)	(38.5)	(41.4)	(11.0)	(95)

LAKE SEDIMENT WITH ACID EXTRACTION

analysis in mass % except * for mg/kg CRM, powder 20 g

Number	Analysis	Al	As	Ba	Ca	Cd*	Co	Cr	Cu	Fe	K	La
NIES 31	whole material	9.17	(0.00139)	(0.0338)	1.25	(0.342)	(0.00181)	0.00433	0.00531	5.38	(0.991)	(0.00204)
NIES 31	acid extract	(0.285)	.	(0.00337)	0.00506	.	.	.
Number	Analysis	Mg	Mn	Na	Ni	P	Pb	Sc	Sr	Ti	V	Zn
NIES 31	whole material	(0.836)	0.0978	0.882	0.00253	0.0925	0.00251	(0.00191)	(0.0125)	0.442	0.0154	0.0121
NIES 31	acid extract	.	0.0881	.	0.00222	.	0.00220	.	.	.	0.0133	0.0110

CRM LAKE SEDIMENT

analysis listed in mass %

Number	Al ₂ O ₃	C	CaO	Fe	FeO	Fe ₂ O ₃	H ₂ O-	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	LOI	Other			
JLk-1	16.73	.	0.686	.	2.191	4.251	3.701	6.372	2.805	1.736	0.266	1.051	0.208	0.1052	57.16	0.668	.	T.Fe ₂ O ₃ : 6.929			
VS 7176-95	14.22	.	7.09	.	3.50	5.39T	(0.22)	.	1.51	3.12	0.12	3.11	0.139	.	62.46	0.76	1.78	CO ₂ : (0.74)			
VS 7126-94	13.57	(2.24)	1.85	.	1.60	7.02T	(2.15)	(4.5)	2.21	2.00	0.40	1.96	0.345	0.165	61.07	0.69	8.34	SO ₂ : (0.35)			
NCS DC73372	13.28	1.9	5.0	.	(1.4)	4.8T	.	(4.7)	1.98	1.52	.	1.28	.	0.0241	61.69	.	.	C.Org:1.1 CO ₂ :2.9			
AE SL 1	.	.	.	6.7400	Ca: 11.1100		
AE SL 3		
BCR 280R		
continued analysis listed in mg/kg except % which is mass %																					
Number	Ag	Al%	As	Au	B	Ba	Be	Bi	Br	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	
JLk-1	.	.	26.8	.	.	574	87.9	18.0	69.0	10.9	62.9	6.57	3.59	1.27	589	.	
VS 7176-95	(0.04)	.	.	.	(12)	530	(1.3)	.	.	.	(41)	17	158	.	18	.	.	(1.4)	(380)	.	
VS 7126-94	(0.17)	.	18	(0.004)	34	710	2.7	.	.	.	80	18	66	6	52	(4.6)	(2.6)	1.4	600	16	
NCS DC73372	0.076	.	8.4	Cl:45	52	520	2.2	0.29	3.7	0.10	74	14	75	8.3	25	4.7	2.8	1.30	504	16.7	
AE SL 1	.	.	27.6	.	.	639	.	.	.	0.26	117	19.8	104	7	30	7.5	.	1.6	.	23.7	
AE SL 3	.	2.4500	3.2	5.6	.	45.5	.	.	1.38	.	2.22	.	0.66	.	.	
BCR 280R	33.4	0.85	.	16.8	126	.	53	1.46	69	224	.	.	.	
Number	Gd	Ge	Hf	Hg	Ho	K%	La	Li	Lu	Mg%	Mn	Mo	Na	Nb	Nd	Ni	P	Pb	Pr	Rb	
JLk-1	6.02	.	3.78	.	1.06	.	40.6	.	0.571	15.8	35.7	35.0	.	43.7	8.53	147	
VS 7176-95	.	19	19	8.5	10	31	.	.	14	.	39	
VS 7126-94	(5.8)	1.4	3.9	(0.03)	(1)	.	45	37	0.40	.	.	2.9	12	39	54	.	21	(8)	93		
NCS DC73372	5.4	1.32	6.6	0.032	1.03	I:2.8ppm	38	38	0.43	N:0.1300%	520	0.4	.	14.4	32	33	480	25	8.5	102	
AE SL 1	.	.	4.2	0.13	.	1.4500	52.6	.	0.54	3460	.	.	1700	.	.	44.9	.	37.7	.	113	
AE SL 3	.	.	9.1	.	.	0.8740	22.5	.	0.3	2.7000	.	.	6690	.	21.5	38.8	
BCR 280R	.	.	1.46	69	
Number	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Th	Ti	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units (g)	
JLk-1	.	15.9	.	7.87	.	67.5	1.57	1.23	19.5	.	1.17	.	3.83	117	.	40.0	3.99	152	137	20	
VS 7176-95	.	19	.	3.7	580	105	.	24	2.7	64	204	100	
VS 7126-94	(0.95)	13	(0.97)	7	3.2	266	0.84	0.9	12.7	.	.	.	(0.42)	12.0	110	(4.3)	30	2.9	96	156	100
NCS DC73372	0.85	12.1	0.15	6.2	3.4	172	1.1	0.86	12.8	4240	0.6	0.44	2.1	90	1.9	26	2.6	61	233	70 last	
AE SL 1	1.31	17.3	2.85	9.25	.	80	1.58	1.4	14	5170	.	.	4.02	170	.	.	3.42	223	.	25	
AE SL 3	0.56	3.91	.	3.83	.	0.47	0.7	0.49	7	2610	.	.	2.3	.	.	.	1.89	.	.	25	
BCR 280R	224	.	.	30

CRM ESTUARY AND MARINE SEDIMENT

analysis listed in mg/kg except % which is mass %

Number	Hg	CH ₃ Hg	Ag	Al%	As	Ba	Be	Ca%	Cd	Ce	Co	Cr	Cu	Fe%	Ga
ERM-CC580	132 tot	0.075
NMIJ 7302a	0.52	.	0.49	.	22.1	.	.	.	1.32	.	12.4	145	57.8	.	.
BCR 277R	0.128	.	.	.	18.3	.	.	.	0.61	.	22.5	188	63	.	.
NMIJ 7303a	0.067	.	0.098	.	8.6	(210)	(<1)	0.519	0.342	(34)	11.1	39.1	23.1	.	.
SRM 1646a	(0.04)	.	(<0.3)	2.297	6.23	.	.	.	0.148	.	(5)	40.9	10.01	2.008	(5)

Number	K%	La	Li	Mg%	Mn	Mo	Na%	Nd	Ni	P%	Pb	Rb	S%	Sb	Sc	Se
ERM-CC580
NMIJ 7302a	1.98	.	.	.	25.8	.	82.7	.	.	1.22	.	0.61
BCR 277R	130
NMIJ 7303a	0.96	.	.	.	21.8	.	31.3	.	.	0.69	.	0.24
SRM 1646a	0.864	(17)	(18)	0.388	2345	.	0.741	(15)	22.5	0.027	11.7	(38)	0.352	(0.3)	(5)	0.193

Number	Si%	Sn	Sr	Th	Ti%	Tl	U	V	Zn	Units
ERM-CC580	40 g
NMIJ 7302a	.	18.5	401	60 g
BCR 277R	178	40 g
NMIJ 7303a	.	4.21	107	60 g
SRM 1646a	40.0	(1)	(68)	(5.8)	0.456	(<0.5)	(2)	44.84	48.9	70 g

CRM MARINE SEDIMENT

analysis listed in mass %

T = Total

Number	Al ₂ O ₃	C(org)	T.C	CO ₃ ²⁻	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	LOI	
JMs-1	15.82	.	1.69	.	2.13	2.12	4.54	6.90	6.79	2.24	2.87	0.102	4.07	0.18	1.32T	53.74	0.70	15.44	
JMs-2	14.18	.	0.39	.	4.68	<0.04	10.96	10.96	7.13	2.70	3.24	2.26	5.79	1.26	0.29T	41.78	1.40	19.15	
SRM 2702	8.41	(3.27)	(3.36)	.	(0.343)	.	.	7.91	.	2.054	(0.990)	0.1757	0.681	0.1552	(1.5T)	.	0.884	.	
SRM 2703	8.33	.	.	.	(0.31)	.	.	7.38	.	2.08	(1.0)	0.1734	0.693	(0.16)	.	.	0.880	.	
NRC MESS-4	7.91	.	(1.79)	.	1.31	.	.	3.79	.	2.38	1.58	0.0298	1.26	0.104	0.158	27.8	0.384	.	
NRC PACS-3	6.58	.	.	.	1.89	.	.	4.106	.	1.253	1.402	0.0432	3.52	0.0937	1.17	26.1	0.442	.	
NRC HISS-1	0.73	.	.	.	1.14	.	.	0.246	.	0.332	0.075	0.00661	0.373	.	.	(44)	0.076	.	
BCR 320R	2.5700	.	.	.	0.0910

continued

analysis listed in mg/kg except % which is mass %

SRM 2703 is intended for small sample techniques <10mg

Number	Ag	As	B	Ba%	Be	Bi	Br	Cd	Ce	Cl%	Co	Cr	Cs	Cu	Dy	Er	Eu
JMs-1	.	18	81	0.0307	1.3	2.69	18.1	133	5.9	88	.	.	.
JMs-2	.	35	106	0.1856	1.8	4.05	226	78	3.0	447	.	.	.
SRM 2702	(0.622)	45.3	.	0.03974	(3.0)	.	.	0.817	123.4	.	27.76	352	(7.1)	(117.7)	.	.	.
SRM 2703	(0.59)	45.5	.	0.0416	.	.	.	0.811	125.5	.	27.70	.	(7.7)	(120)	.	.	.
NRC MESS-4	0.161	21.7	.	(0.0920)	2.09	(2.7)	(60)	0.28	(72)	1.31%	13.0	94.3	(10)	32.9	.	.	(1.3)
NRC PACS-3	(1.10)	30.3	.	.	1.06	.	.	2.23	.	.	(12.1)	90.6	.	326	.	.	.
NRC HISS-1	0.016	0.801	.	.	0.129	.	.	0.024	.	(0.35)	(0.65)	30.0	.	2.29	.	.	.
BCR 320R	.	21.7	2.64	.	.	9.7	59	.	46.3	.	.	.

Number	Ga	Gd	Hf	Hg	Ho	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc
JMs-1	0.101	.	62	53	49	.	88	1.4	.
JMs-2	0.178	.	43	311	88	.	65	4.5	.
SRM 2702	(24.3)	.	(12.6)	0.4474	.	.	73.5	(78.2)	.	(10.8)	(63)	(56)	75.4	132.8	.	127.7	5.60	25.9
SRM 2703	.	.	(11.8)	0.474	.	.	75.9	.	.	(11)	(63)	(72)	(75)	130	.	130	5.62	25.95
NRC MESS-4	(18) Ge:	(0.16)	(3.0)	(0.08)	.	(0.10)	(35)	65.3	(0.11)	(2.53)	(12)	(42)	42.8	21.5	.	(180)	1.07	(13.4)
NRC PACS-3	.	.	.	2.98	.	.	.	31.9	.	(5.9)	.	.	39.5	188.0	.	.	14.7	.
NRC HISS-1	.	.	.	(0.01)	.	.	.	2.83	.	(0.13)	.	.	2.16	3.13	.	.	(0.13)	.
BCR 320R	.	.	.	0.85	27.1	85	.	.	.	5.2

* BUTILYN CONTENT DETAILED ON CERTIFICATES

Number	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units
JMs-1	.	.	.	154	.	.	0.132	127	.	24.3	264	132	100 g
JMs-2	.	.	.	454	.	.	1.38	183	.	254	166	220	100 g
SRM 2702	(4.95)	(10.8)	31.6	119.7	.	.	.	20.51	0.8267	.	(10.4)	357.6	(6.2)	.	.	485.3	.	50 g
SRM 2703	(4.9)	(10.8)	(32)	(118)	.	.	.	20.22	(0.83)	.	8.99	360	(6.4)	.	.	480	.	5 g
NRC MESS-4 *	(1.5)	(5.5)	2.35	132	(1)	.	(0.1)	(12)	0.85	.	3.4	216	(1.3)	(20)	(2)	147	(96)	50 g
NRC PACS-3 *	.	.	22.0	267	(2.6)	129	376	.	50 g
NRC HISS-1	0.050	.	(0.11)	96.9	.	.	.	(0.06)	.	(0.26)	6.80	4.94	.	100 g
BCR 320R	5.3	0.65	.	1.56	46.5	.	.	.	319	.	40 g

Re: (0.004)

RIVER SEDIMENT

analysis listed in mg/kg except % which is mass % SRM 1944: CRM, 50 g SRM 8704: RM, 50 g

Number	Ag	Al%	As	Au	Ba	Be	Br	C%	Ca%	Cd	Ce	Cl%	Co	Cr	Cs	Cu	Eu	Hf	Hg	Fe
SRM 1944	6.4	5.33	18.9	(0.1)	.	1.6	86	.	1.0	8.8	(65)	1.4	14	266	3	380	(1.3)	.	3.4	3.53%
SRM 8704	.	6.10	(17)	.	413	.	.	3.351	2.641	2.94	66.5	.	13.57	121.9	5.83	.	1.31	8.4	.	3.97%

continued

Number	K%	Mg%	Mn	Na%	Ni	Pb	Rb	Sb	Sc	Se	Si%	Sn	Th	Ti%	Tl	U	V	Zn
SRM 1944	1.6	(1.0)	505	1.9	76.1	330	75	(5)	10.2	1.4	31	42	(13)	0.4300	0.59	(3.1)	100	656
SRM 8704	2.001	1.200	544	0.553	12.9	150	.	3.07	11.26	.	.	.	9.07	0.457	.	3.09	94.6	408

CRM STREAM SEDIMENT

analysis listed in mass % BCR: 40 g JSd 1-3: 20 g JSd-4: 100 g all others: 70 g units

Number	SiO ₂	Al ₂ O ₃	Org.C	CO ₂	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O+	H ₂ O-	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI
GBW 07311	76.25	10.37	(0.24)	(0.09)	0.47	(0.35)	4.39	.	2.67	.	3.28	0.62	.	0.46	.	.	(3.02)
JSd-3	76.00	9.908	.	.	0.560	1.161	3.057	4.368	2.838	0.964	1.971	1.17	0.149	0.411	0.0817	0.403	.
JSd-1	66.55	14.65	.	(0.0867)	3.034	1.363	3.526	5.059	(2.301)	0.836	2.183	1.813	0.0924	2.727	0.122	0.643	.
GBW 07309	64.89	10.58	0.46	4.20	5.35	1.53	4.86	.	2.93	.	1.99	2.39	.	1.44	.	.	7.21
JSd-2	60.78	12.31	.	(0.501)	3.658	5.955	4.552	11.65	2.554	0.451	1.145	2.731	0.120	2.438	0.105	0.614	.
JSd-4	51.12	13.22	.	.	5.57	(2.08)	.	8.06	.	.	1.40	4.04	0.107	2.28	0.45	0.64	.
BCR 667	estuary sediment

continued analysis listed in mg/kg except * which is ng/g and % which is mass %

Number	Ag	As	Au*	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga
GBW 07311	3.2	188	(3.6)	68	260	26	50	(2.3)	2.3	58	290	8.5	40	17.4	79	7.2	4.6	0.60	1650	18.5
JSd-3	(3.38)	252	(5.66)	.	462	.	.	.	42.0	.	12.7	35.3	30.6	426	2.22	1.07	0.686	3200	.	
JSd-1	(0.036)	2.42	(0.64)	.	520	1.40	.	.	34.4	.	11.2	21.5	1.89	22.0	2.23	0.906	0.925	306	.	
GBW 07309	0.089	8.4	(1.3)	54	430	1.8	0.42	(1.5)	0.26	78	(50)	14.4	85	5.1	32	5.1	2.8	1.33	494	14.0
JSd-2	(1.04)	38.6	(54.6)	.	1199	.	.	.	23.4	.	48.4	108	1.07	1117	2.86	1.48	0.81	259	.	
JSd-4	(888)	(21)	(1215)	.	(486)
BCR 667	(99.7)	(0.67)	56.7	.	(23.0)	(178)	(7.8)	(60)	4.01	2.35	1.00	Fe:	(4.48)

continued

Number	Gd	Ge	Hf	Hg*	Ho	I	In	La	Li	Lu	Mn	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	S
GBW 07311	5.9	1.81	5.4	72	1.4	2.0	1.9	30	71	0.78	2490	5.9	25	27	14.3	255	636	7.4	408	170
JSd-3	.	.	3.21	(254)	.	.	.	19.8	151	0.196	.	.	7.80	15.7	19.6	.	82.1	3.09	285	(399)
JSd-1	2.71	.	3.55	(15.5)	.	.	.	18.1	22.8	0.186	.	.	11.1	17.6	7.04	.	12.9	4.05	67.4	(68)
GBW 07309	5.5	1.3	9.7	83	0.96	(0.61)	0.056	40	30	0.4	620	0.64	18	34	32	670	23	9.2	80	150
JSd-2	.	.	2.70	(106)	.	.	.	11.3	(19.2)	0.252	.	11.5	4.56	13.2	92.8	.	146	2.40	26.9	1.31%
JSd-4	(16)	(32)	(114)	.	(240)	.	(57)	.
BCR 667	4.41	.	.	.	0.80	.	.	27.8	.	0.325	(920)	.	.	25.0	(128)	.	(31.9)	6.1	.	.

continued

Number	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
GBW 07311	14.9	7.4	0.20	6.2	370	29	5.7	1.13	(0.36)	23.3	0.2100	2.9	0.74	9.1	47	126	4.3	5.1	373	153
JSd-3	.	10.5	.	3.26	.	58.7	0.687	0.368	.	7.79	.	.	.	1.66	70.4	.	14.9	1.40	136	124
JSd-1	.	10.9	.	3.48	.	340	0.893	0.431	.	4.44	.	.	.	1.00	76.0	.	14.8	1.18	96.5	132
GBW 07309	0.81	11.1	0.16	6.3	2.6	166	1.3	0.87	(0.04)	12.4	0.5500	0.49	0.44	2.6	97	1.8	27	2.8	78	370
JSd-2	.	17.5	.	2.68	.	202	.	0.440	.	2.33	.	.	.	1.10	125	.	17.4	1.67	2056	111
JSd-4	.	(17)	.	.	.	(220)	(152)	.	(21)	.	(1485)	(90)
BCR 667	(0.96)	13.7	(1.59)	4.66	.	.	(0.876)	0.682	.	10.0	.	.	0.326	2.26	.	.	.	2.20	(175)	.

CRM STREAM SEDIMENT

analysis listed in mass %																	DC360xx: 75 g units		DC730xx: 70 g units	
Number	SiO ₂	Al ₂ O ₃	C	C.Org	CO ₂	CaO	FeO	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	Mn	N	Na ₂ O	P	S	Ti			
NCS DC73017	77.42	11.44	(0.25)	0.20	(0.11)	0.85	(0.2)	1.86	(1.0)	3.89	0.18	0.122	0.0218	2.53	0.0234	0.0066	0.151			
NCS DC73015	74.33	11.65	(0.46)	(0.08)	(1.34)	2.85	(0.57)	1.79	0.98	2.96	0.71	0.0290	(0.0079)	2.85	0.0335	0.0087	0.146			
NCS DC73014	69.40	11.06	(0.48)	0.28	(0.76)	2.96	(1.83)	7.00	2.31	2.35	1.70	0.142	(0.0150)	1.40	0.0568	0.0432	0.32			
NCS DC73018	66.02	11.25	1.01	0.34	2.57	3.82	(2.1)	6.31	3.23	2.41	2.34	0.0798	0.0291	0.83	0.0459	0.0110	0.53			
NCS DC73022	64.35	13.61	0.93	(0.56)	(1.36)	1.64	(1.1)	7.05	(4.4)	2.76	1.25	0.103	0.0711	0.41	0.0589	1.17	0.45			
NCS DC73020	63.12	13.08	(0.48)	0.11	1.36	4.09	(0.73)	4.80	(3.1)	2.44	2.01	0.0829	(0.0140)	3.15	0.0608	0.67	0.328			
NCS DC73021	51.43	10.73	2.6	0.18	8.60	13.12	(0.66)	3.81	(3.5)	2.17	1.83	0.0675	0.0312	1.68	0.0571	(0.62)	0.285			
continued analysis listed in mg/kg except % which is mass %																				
Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	
NCS DC73017	0.044	4.4	5.5	1054	1.6	0.33	1.0	0.095	32	(30)	12.5	8.4	1.5	3.9	1.3	0.8	0.54	131	12.0	
NCS DC73015	0.050	3.6	48	600	3.6	0.48	0.61	0.093	24	33	4.4	21	7.2	7.2	1.7	0.93	0.62	279	12.4	
NCS DC73014	0.14	14.3	53	455	2.2	0.51	0.8	0.34	47	53	10.2	61	5.8	132	4.1	2.5	1.20	550	14.6	
NCS DC73018	0.092	3.0	14	567	1.9	0.22	1.0	0.12	90	62	19.5	79	4.6	43	6.5	3.7	1.4	664	16.5	
NCS DC73022	2.1	304	70	590	2.4	13.1	1.4	4.8	79	46	14.4	72	10.3	483	5.2	3.0	1.36	603	21.5	
NCS DC73020	0.14	19.2	35	727	1.5	0.20	(0.9)	0.76	44	0.28%	8.8	32	2.2	296	4.5	2.7	1.11	535	15.7	
NCS DC73021	0.068	10.5	46	584	1.5	0.25	1.3	0.165	47	298	10.0	48	5.4	22.6	4.5	2.6	1.08	506	13.4	
Number	Gd	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	
NCS DC73017	1.4	1.21	2.7	0.016	0.26	0.46	(0.014)	11.8	8.1	0.14	0.64	9.5	8.9	4.7	22	2.5	81	0.29	2.1	
NCS DC73015	1.7	1.64	2.1	(0.007)	0.33	0.27	0.018	13.9	40	0.16	0.33	5.1	9.8	7.0	31	2.9	118	0.16	4.9	
NCS DC73014	4.1	1.87	3.8	0.018	0.83	0.47	0.14	24	20.7	0.42	0.94	9.4	22	18.9	210	5.9	96	1.18	11.4	
NCS DC73018	7.0	1.45	7.8	(0.014)	1.27	0.4	0.068	45	43	0.60	0.84	15.3	40	70	19	11.0	121	0.15	16.9	
NCS DC73022	5.5	1.74	7.4	0.115	1.04	1.8	0.36	40	38	0.48	1.56	16.4	33	29	126	8.9	130	25	13.8	
NCS DC73020	4.3	1.06	4.8	0.025	0.93	1.6	0.11	21	16.2	0.47	1.7	9.2	22	13.4	26	5.5	53	1.00	12.4	
NCS DC73021	4.5	1.05	4.1	0.019	0.92	1.7	0.046	24	28	0.42	1.1	9.2	23	26	17	5.9	77	0.90	10.3	
Number	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr			
NCS DC73017	0.072	1.6	(1.0)	167	0.81	0.22	(0.03)	5.4	0.44	0.13	1.1	28	0.58	7.0	0.83	19	100			
NCS DC73015	0.053	1.9	2.3	253	0.72	0.29	(0.02)	4.1	0.83	0.16	1.9	31	0.66	9.7	1.0	27	71			
NCS DC73014	0.47	4.5	2.5	171	0.65	0.68	(0.05)	8.3	0.91	0.40	2.2	77	2.0	23	2.6	209	132			
NCS DC73018	0.24	7.5	1.9	117	1.04	1.14	(0.05)	15.4	0.77	0.59	3.5	120	1.7	34	3.8	74	275			
NCS DC73022	0.69	6.2	6.7	111	1.23	0.91	(1.4)	14.0	1.05	0.49	3.7	101	15.5	28	3.1	874	241			
NCS DC73020	1.55	4.7	2.0	355	0.59	0.74	(0.25)	5.5	0.32	0.46	2.1	83	0.97	26	3.0	289	179			
NCS DC73021	0.21	4.7	2.0	273	0.63	0.77	(0.05)	7.8	0.48	0.43	2.3	69	1.3	25	2.7	59	150			

CRM STREAM SEDIMENT

analysis listed in mass % T = total Fe reported

Number	Al2O3	Ba	CaO	Cr2O3	Cu	FeO	T.Fe2O3	K2O	MgO	MnO	Na2O	P2O5	Pb	S	SiO2	TiO2	Zn	Zr
SARM 52	9.38	(0.0410)	0.37	0.19	0.0219	(4.0)	19.71	0.25	0.60	0.27	(0.1)	0.09	0.12	(0.02)	57.81	1.30	0.0264	0.0250

continued analysis listed in mg/kg except % for mass %

Number	Ce	Co	Ga	Nb	Ni	Rb	Sr	Th	V	Y	Units
SARM 52	(210)	81	(15)	11	182	20	25	(11)	346	20	100 g

CRM STREAM SEDIMENT

analysis listed in mass % T = TOTAL 70 g units

Number	SiO ₂	Al ₂ O ₃	C.Org	C.T	CaO	CO ₂	F	Fe ₂ O ₃ .T	FeO	H ₂ O+	K ₂ O	MgO	Mn	Na ₂ O	P	S	Ti
NCS DC73318a	73.58	13.25	0.11	(0.18)	0.17	(0.16)	0.0646	3.70	(0.43)	2.98	4.31	0.47	0.0645	0.38	221	(0.0066)	0.29

continued analysis listed in mg/kg

Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Ge
NCS DC73318a	0.12	7.3	5.3	620	3.5	0.18	1.1	0.16	88	(29)	6.8	11.6	9.7	5.8	5.4	3.1	1.03	18.5	5.6	1.15

Number	Hf	Hg	Ho	I	In	La	Li	Lu	Mo	N	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se
NCS DC73318a	6.7	0.024	1.06	1.2	0.070	45	22	0.54	1.3	(119)	27	33	3.0	37	9.4	232	0.38	9.0	0.14

Number	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
NCS DC73318a	6.3	3.8	52	1.78	0.90	(0.03)	20.5	1.60	0.53	4.7	31	3.3	29	3.4	80	228

CRM SEDIMENT

Number	analysis listed in mass %													3480 series: 100 g units		5360 series: 50 g units	
	SiO ₂	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI		
VS 3486-86	70.54	11.29	.	0.52	.	(3.5)	5.24	2.21	0.48	0.11	1.67	0.28	0.43	0.62	.		
VS 5361-90	70.5	11.31	.	0.48	1.3	.	5.24	2.23	0.49	0.105	1.65	0.27	0.44	0.61	5.5		
VS 5365-90	60.4	16.49	0.13	0.40	3.3	.	8.80	2.44	1.62	0.132	1.57	0.19	0.03	0.98	6.8		
VS 3484-86	51.95	16.76	.	1.13	(2.2)	(3.5)	6.33	2.51	1.53	0.071	1.37	0.18	0.05	0.85	(17.17)		
VS 5363-90	51.9	16.65	.	1.11	2.2	.	6.28	2.50	1.54	0.070	1.34	0.19	0.04	0.83	17.1		
VS 3483-86	45.59	11.60	.	7.05	(1.3)	(2.8)	4.62	2.96	5.82	0.073	0.87	0.15	0.05	0.63	(20.33)		
VS 5362-90	45.4	11.58	.	7.04	1.5	.	4.59	2.96	5.72	0.074	0.85	0.14	0.04	0.63	20.3		
VS 3485-86	25.07	5.03	.	17.76	(0.24)	(0.2)	10.59	1.13	11.70	0.50	0.61	1.82	0.05	0.27	(25.14)		
VS 5364-90	25.0	4.98	21.6	17.83	0.4	.	10.56	1.13	11.7	0.48	0.63	1.82	0.05	0.26	25.1		

continued analysis listed in mg/kg except % which is mass %

Number	Ag	As%	Au	B%	Ba%	Be%	Bi%	Cd	Ce	Co	Cr	Cs	Cu%	F%	Ga	Ge	La%
VS 3486-86	.	.	.	0.016	0.039	0.00036	.	9	.	9	0.0076	.	0.025	.	16	.	0.0032
VS 5361-90	35	0.8	0.11	0.015	0.038	0.004	0.009	9	0.004	9.0	0.0075	17	0.025	0.21	16	15	0.0030
VS 5365-90	.	.	.	0.007	0.055	0.0003	.	.	0.006	29	0.013	4	0.0049	.	17	.	0.0032
VS 3484-86	(0.7)	(0.004)	(0.025)	(0.008)	0.058	0.00023	.	(1.9)	.	18	0.0120	.	0.0052	.	17	.	0.0034
VS 5363-90	0.10	0.004	0.016	0.008	0.050	0.00021	.	.	.	17	0.012	6	0.0050	0.09	17	12	0.0029
VS 3483-86	(0.5)	(0.004)	(0.04)	(0.009)	0.047	0.00020	.	(2)	.	14	0.0066	.	0.0048	.	12	.	0.00322
VS 5362-90	0.06	.	0.03	0.008	0.050	0.00020	.	.	0.005	13	0.0065	4	0.0044	0.12	12	12	0.0030
VS 3485-86	2.6	(0.009)	1.3	(0.0014)	0.035	0.00025	.	(3.5)	.	11	0.0028	.	0.026	.	9	.	0.026
VS 5364-90	2.3	0.006	1.2	0.0013	0.034	0.0003	0.0006	3	0.05	12	0.0029	4	0.024	0.19	8	16	0.022

Number	Li%	Mo	Nb	Ni	Pb%	Rb%	Sb%	Sc	Sn%	Sr%	V%	W%	Y%	Yb	Zn%	Zr%	Others
VS 3486-86	0.015	.	17	25	0.011	0.019	0.017	8	0.04	0.020	0.006	.	0.0016	2.24	0.039	0.021	
VS 5361-90	0.014	2.7	17	24	0.010	0.019	0.015	8	0.040	0.018	0.0058	0.20	0.0018	2.5	0.039	0.020	
VS 5365-90	0.007	2.1	13	72	0.0024	0.0080	.	18	0.00036	0.013	0.018	.	0.0030	4	0.012	0.021	Nd: 25, Sm: 4
VS 3484-86	0.0012	(3)	60	58	0.0016	0.010	.	15	0.00044	0.020	0.014	.	0.0030	3.2	0.009	(0.018)	
VS 5363-90	0.006	1.1	10	55	0.0015	0.0095	.	16	0.00040	0.019	0.014	.	0.0023	3	0.0086	0.018	
VS 3483-86	0.010	(3)	12	33	0.0016	0.009	.	9	0.00037	0.030	0.009	.	0.0023	2.5	0.005	0.014	
VS 5362-90	0.009	1.0	12	31	0.0014	0.0085	.	11	0.00040	0.025	0.0087	.	0.0020	2.6	0.0054	0.015	
VS 3485-86	0.0020	29	(7)	19	(0.020)	0.004	.	9	0.0004	0.018	0.007	.	0.004	3.3	0.014	0.007	
VS 5364-90	0.0020	27	7	18	0.015	0.0045	.	7	0.00033	0.017	0.0075	0.0025	0.0040	2.9	0.014	0.007	Th: 40

CRM RIVER SEDIMENT

Number	analysis listed in mass %													85 g units	
	Al ₂ O ₃	Ba	CaO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Pb	S	SiO ₂	TiO ₂	Zn	LOI
US SDAR-M2	12.47	0.0990	0.84	2.63	5.00	(0.49)	0.134	2.58	(0.079)	0.0808	(0.0970)	73.45	0.300	0.0760	(1.6)

continued analysis listed in mg/kg

Number	Ag	As	Be	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Ge
US SDAR-M2	(15)	(76)	6.6	1.05	5.1	98.8	12.4	49.6	1.82	236	5.88	3.58	1.44	17.6	6.28	(1.5)

Number	Hf	Hg	Ho	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pr	Rb	Sb	Sc
US SDAR-M2	7.29	1.44	1.21	(2.1)	46.6	17.9	0.54	13.3	26.2	39.4	48.8	11.0	149	(107)	4.1

Number	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zr
US SDAR-M2	(2.7)	7.18	(2.4)	144	1.8	0.97	(2.1)	14.2	(2.8)	0.54	2.53	25.2	(3.5)	32.7	3.63	259

CRM CONTAMINATED RIVER SEDIMENT

Number	certified analysis listed in mg/kg										informational analysis listed in mass %									
	As	Cd	Co	Cr	Cu	Hg	Ni	Pb	V	Zn	Al	C.Inorg	C.Org	Ca	Fe	K	Mg	Si	LOI	Units
BAM CC020	56.6	20.8	32.8	290	560	27.4	158	255	53	2030	5.5	0.2	9.7	2.9	5.1	1.7	0.9	25.3	18.5	52 g

CRM TIBET SEDIMENT

analysis listed in mass %																	T = Total		60 g units	
Number	SiO ₂	Al ₂ O ₃	Ba	CaO	F	Fe ₂ O ₃ T	K ₂ O	MgO	Mn	MnO	Na ₂ O	P	P ₂ O ₅	Sr	Ti	TiO ₂				
NCS DC70322	73.67	12.57	0.0711	1.38	0.0415	2.85	3.87	0.62	0.0430	0.056	2.50	0.0455	0.104	0.0250	0.249	0.421				
NCS DC70321	73.59	13.41	0.0875	1.53	0.0452	1.71	4.33	0.49	0.0258	0.034	2.69	0.0459	0.105	0.0340	0.170	0.290				
NCS DC70318	73.37	12.73	0.0437	1.32	0.0456	3.19	3.56	1.07	0.0422	0.055	2.09	0.0420	0.097	0.0165	0.253	0.422				
NCS DC70319	71.23	13.22	0.0470	1.40	0.0459	4.11	3.65	0.70	0.0527	0.069	2.72	0.0484	0.111	0.0256	0.344	0.589				
NCS DC70320	70.36	13.95	0.0483	2.40	0.0505	3.20	3.18	0.93	0.0451	0.059	3.26	0.0564	0.129	0.0404	0.274	0.461				
NCS DC70324	70.16	12.79	0.0472	2.29	0.0457	4.82	2.67	0.62	0.0392	0.051	1.48	0.0625	0.142	0.0157	0.364	0.616				
NCS DC70313	69.70	13.19	0.0508	0.39	0.0622	5.85	2.56	1.58	0.0876	0.113	1.23	0.0613	0.140	0.00593	0.439	0.725				
NCS DC70316	68.50	14.42	0.0476	0.53	0.0440	4.81	2.66	1.74	0.0668	0.087	1.66	0.0571	0.134	0.0113	0.451	0.753				
NCS DC70315	66.50	10.17	0.0384	6.50	0.0539	3.70	2.26	1.14	0.0567	0.074	1.17	0.0501	0.115	0.0132	0.290	0.491				
NCS DC70317	64.22	10.84	0.0369	8.19	0.0424	3.07	2.86	0.87	0.0614	0.079	1.74	0.0389	0.090	0.0185	0.217	0.366				
NCS DC70323	60.95	11.89	0.0475	7.77	0.0555	5.47	2.01	0.78	0.0608	0.078	1.09	0.0542	0.124	0.0327	0.339	0.558				

continued analysis listed in mg/kg except * for ng/g and % for mass percent

Number	Ag	As	Au*	B	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd
NCS DC70322	0.08	28.8	0.7	28.1	2.48	0.29	0.7	0.12	77.6	93	6.0	17.7	48.1	10.7	3.49	1.99	1.05	15.5	4.43
NCS DC70321	0.06	14.3	0.4	19.7	3.60	0.33	0.8	0.07	109	82	4.4	16.5	16.2	10.8	2.95	1.62	0.98	16.5	4.40
NCS DC70318	0.06	18.0	1.4	30.6	3.32	0.49	0.9	0.10	89.6	207	6.7	47.6	20.2	16.2	4.92	2.90	1.07	16.3	5.83
NCS DC70319	0.21	19.6	1.2	66.2	2.31	0.80	1.4	0.19	78.1	244	7.6	22.6	15.0	151	3.91	2.39	0.97	15.8	4.57
NCS DC70320	0.14	12.3	1.1	41.5	2.56	0.70	1.1	0.17	60	152	7.3	24.4	13.0	49.0	2.94	1.64	0.96	16.9	3.74
NCS DC70324	0.07	24.9	1.4	143	5.62	0.45	0.9	0.08	84.4	63	10.3	55.2	16.6	27.7	5.10	2.75	1.29	17.6	6.05
NCS DC70313	0.09	22.0	1.4	77.0	2.34	0.50	1.0	0.54	74.0	63	17.9	93.8	11.9	27.1	4.73	2.81	1.21	17.8	5.40
NCS DC70316	0.07	13.7	1.8	56.1	2.43	0.30	1.9	0.10	93.4	56.7	14.7	139	13.7	23.1	6.10	3.54	1.58	18.5	7.11
NCS DC70315	0.10	22.5	1.6	59.5	2.13	0.46	1.5	0.33	71.3	96.7	9.2	37.5	7.9	16.6	4.40	2.60	1.04	14.1	5.15
NCS DC70317	0.32	37.3	6.2	30.0	2.67	1.22	0.9	0.57	72.0	69.1	9.8	39.8	17.2	247	4.24	2.47	0.96	14.4	4.90
NCS DC70323	0.10	54.6	2.9	134	3.88	0.48	1.3	0.08	90.1	71	13.2	59.0	42.5	44.0	5.56	2.98	1.40	17.1	6.58

Number	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pd*	Pr	Pt*	Rb
NCS DC70322	1.18	6.9	0.017	0.69	(0.22)	(0.042)	41.6	26.7	0.30	0.65	10.9	30.2	8.5	36.3	(0.3)	8.61	(0.4)	170
NCS DC70321	1.02	6.1	0.008	0.58	(0.23)	(0.03)	63.2	25.7	0.24	0.60	10.1	37.0	8.8	48.9	(0.3)	11.2	(0.2)	229
NCS DC70318	1.33	6.7	0.030	0.97	(0.3)	(0.04)	47.8	36.6	0.44	0.59	14.7	35.8	16.9	35.8	(0.4)	9.78	(0.3)	180
NCS DC70319	1.13	9.5	0.028	0.79	(0.3)	(0.04)	42.6	26.1	0.39	7.0	16.1	30.6	9.5	46.8	(0.3)	8.57	(0.3)	154
NCS DC70320	1.12	5.5	0.012	0.58	(0.3)	(0.04)	32.5	25.6	0.25	2.7	10.5	25.7	11.1	45.4	(0.3)	6.94	(0.3)	136
NCS DC70324	1.63	7.4	0.053	0.99	(0.5)	(0.06)	40.0	66.8	0.37	0.65	17.2	34.8	27.8	32.1	(0.7)	9.42	(0.4)	131
NCS DC70313	1.34	6.5	0.033	0.95	(0.8)	(0.06)	38.8	53.9	0.41	0.60	15.9	31.1	51.9	61.9	(0.6)	8.33	(0.4)	115
NCS DC70316	1.22	8.8	0.043	1.20	(0.7)	(0.06)	48.2	41.9	0.52	0.83	15.3	41.9	75.3	24.0	(0.6)	10.9	(0.4)	117
NCS DC70315	1.09	6.0	0.026	0.87	(0.5)	(0.05)	37.0	27.9	0.38	0.83	15.6	29.3	20.1	31.7	(0.4)	8.10	(0.3)	104
NCS DC70317	1.19	5.7	0.034	0.83	(0.4)	(0.07)	37.9	29.7	0.36	6.6	12.0	29.0	20.8	127	(0.3)	7.89	(0.4)	141
NCS DC70323	1.66	6.3	0.066	1.06	(0.5)	(0.07)	42.6	69.8	0.38	0.66	15.5	36.3	37.2	27.7	(0.8)	10.1	(0.6)	110

Number	S	Sb	Sc	Se	Sm	Sn	Ta	Tb	Te	Tm	Th	Tl	U	V	W	Y	Yb	Zn	Zr
NCS DC70322	(59)	2.34	5.5	0.05	5.26	2.0	1.1	0.64	(0.04)	0.32	19.9	1.26	3.5	50.6	3.1	18.6	1.96	50.8	243
NCS DC70321	(57)	0.67	3.9	0.04	5.69	2.1	1.0	0.59	(0.03)	0.25	31.7	1.42	5.1	31.5	2.5	15.5	1.54	39.7	210
NCS DC70318	(48)	0.84	7.3	0.05	6.62	3.8	1.8	0.91	(0.03)	0.46	25.1	1.0	4.8	52.5	4.1	26.5	2.83	54.1	225
NCS DC70319	(480)	2.70	6.2	0.18	5.42	2.7	1.8	0.70	0.10	0.38	25.5	1.1	4.8	74.7	9.3	21.6	2.55	62.9	299
NCS DC70320	(183)	1.27	6.0	0.11	4.49	2.0	1.2	0.54	0.07	0.25	16.7	0.91	3.6	59.4	4.2	15.3	1.63	61.1	184
NCS DC70324	(160)	1.55	9.3	0.33	6.69	6.4	1.4	0.93	0.07	0.41	14.9	0.69	2.3	77.3	2.6	25.9	2.57	76.4	247
NCS DC70313	(123)	1.91	12.0	0.16	5.99	14.9	1.2	0.83	0.05	0.43	12.1	0.64	2.6	101	2.6	24.4	2.73	176	222
NCS DC70316	(157)	1.10	11.7	0.16	8.11	3.2	1.3	1.08	0.05	0.54	15.5	0.67	2.5	87.7	2.3	32.7	3.47	80.9	299
NCS DC70315	(177)	0.82	7.9	0.12	5.61	3.3	1.3	0.78	(0.03)	0.40	12.3	0.62	2.5	57.4	2.4	23.7	2.55	91.1	206
NCS DC70317	(117)	4.44	6.5	0.19	5.39	3.3	1.1	0.76	0.21	0.38	17.5	0.96	3.4	45.7	9.2	23.0	2.46	116	188
NCS DC70323	(528)	10.4	10.5	0.39	7.19	4.6	1.2	1.01	0.15	0.44	15.6	0.66	2.1	85.0	6.5	29.5	2.67	77.1	210

CRM SERPENTINITE

analysis listed in mass %				T = total				GUW: 50 g units				all others: 100 g units				
Number	Al ₂ O ₃	CO ₂	CaO	Cr ₂ O ₃	FeO	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	Ni	P ₂ O ₅	SiO ₂	TiO ₂	LOI
NCS DC21001	3.34	.	2.97	.	T.Fe:5.47	.	.	.	34.25	0.131	.	.	P:0.012	41.37	0.180	8.86
SARM 47	1.09	.	(0.1)	0.29	(0.4)	4.14	.	(0.02)	42.09	0.06	(0.05)	.	0.2221	36.30	(0.01)	.
GUW SW	0.66	0.28	0.18	.	2.00	7.40	13.6	(0.0014)	38.5	0.084	0.013	0.22	(0.0017)	39.04	0.016	.
USZ 24-99	(0.475)	(0.84)	(0.681)	.	(0.27)	8.00T	0.58-	(0.018)	38.22	0.082	(0.038)	0.2300	(0.023)	38.54	(0.022)	13.33

continued analysis listed in mg/kg except % which is mass %

Number	As	B	Ba	Ce	Co	Cr%	Cs	Cu	F	Ga	Li ₂ O	Nd	Pb	Rb	S	Sc	Sn	Sr	U	V	W	Y	Zn	
NCS DC21001	0.066%
SARM 47	.	.	(75)	(20)	79	.	.	(5)	.	(5)	.	.	(60)	.	.	.	(3)	.	.	(16)	.	(5)	45	
GUW SW	(5)	37	19	.	102	0.24	(5)	7	66	(4)	(3)	(4)	(6)	(5)	(3)	(5)	(5)	.	(5)	20	(5)	.	58	
USZ 24-99	106	0.2780	7.3	0.80	33.4	.	.	39	

CRM SHALE WITH EXTENSIVE ANALYSIS

analysis listed in mass %																			
Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	TiO ₂	ZrO ₂ +HfO ₂	LOI	Units	
GBW 03104	69.63	14.82	0.13	0.22	(0.40)	5.67	.	(3.71)	3.76	0.67	0.024	0.20	0.043	0.028	0.68	.	.	4.17	60 g
GUW TS	62.8	15.96	(0.03)	0.12	0.70	7.40	.	4.01	4.86	1.77	0.037	0.078	0.28	.	0.69	.	.	.	50 g
VS 8549-04	61.21	16.80	1.41	1.14	(3.17)	.	5.57	.	3.72	2.67	0.057	0.95	0.086	(1.53)	0.91	.	.	6.00	100 g
UL AWI 1	60.46	16.44	.	0.69	(5.52)	7.21	.	.	3.06	(2.09)	0.14	0.74	(0.15)	.	0.92	.	.	7.75	50 g
GBW 07107	59.23	18.82	(0.10)	0.60	1.39	.	7.60	+5.6	4.16	2.01	.	0.35	(5.95)	70 g
VS 8550-04	57.60	15.53	(3.8)	1.06	(5.3)	.	7.47	.	2.85	3.06	0.110	1.28	0.115	.	0.88	.	.	(9.5)	100 g
SARM 41	56.67	13.50	.	1.50	(0.3)	4.23	.	.	1.39	8.10	0.06	0.93	0.05	.	0.55	.	.	.	100 g
US SBC-1 *	47.64	21.0	.	2.95	.	.	9.71	.	3.45	2.60	0.15	<0.15	0.37	.	0.855	.	.	10.2	50 g
US SGR-1b	28.24	6.52	.	8.38	(1.41)	(1.46)	3.03	.	1.66	4.44	.	2.99	0.328	.	0.253	.	.	.	30 g
JCRM R651	21.74	71.7	.	0.19	.	1.48	.	.	0.65	0.10	.	0.03	0.19	.	3.15	0.18	.	0.58	100 g

continued analysis listed in mg/kg except % which is mass % and * which is ng/g # US SBC-1 also contains 0.85% inorganic C

Number	Ag	As	Au	B	Ba%	Be	Bi	C Org%	T.C%	Cd	Ce	Cl%	Co	Cr	Cs	Cu	
GBW 03104	0.014	
GUW TS	(0.8)	27.5	.	74	(0.18)	4	.	1.42	.	.	(168)	.	41	280	13	460	
VS 8549-04	0.10	40	0.10	103	0.072	2.0	.	(1.31)	.	(0.27)	58	.	13	128	4.4	34	
UL AWI 1	.	(15)	.	0.0378	(2.7)	80	.	20	119	(7)	34	
GBW 07107	0.047	1.4	(1.0*)	154	0.0450	3.0	0.23	(0.16)	(0.19)	0.033	109	0.0041	21	99	14	42	
VS 8550-04	0.47	46	2.5	(118)	0.0376	(2.4)	.	(0.93)	.	(0.4)	53	.	20	116	4.0	39	
SARM 41	.	.	.	0.820	(60)	.	(15)	123	.	53	
US SBC-1 *	.	25.7	.	0.0788	3.2	0.7	1.23#	2.08	0.4	108	.	.	22.7	109	8.2	31	
US SGR-1b	.	67	.	54	0.0290	.	.	(3.2N)	(28)	(0.9)	36	(0.0032)	12	30	5.2	66	
JCRM R651	N = inorganic C

Number	Dy	Er	Eu	F	Ga	Gd	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mn	Mo
GBW 03104
GUW TS	.	.	(3.2)	1150	21	.	.	(7)	(80)	40	(3.6)	.	130
VS 8549-04	5.6	(3.3)	1.2	(0.12%)	21	6.1	(2.1)	4.1	.	(1.1)	.	.	30	56	0.44	.	1.7
UL AWI 1	5.1	2.9	1.47	.	22	6	.	6.3	.	1.1	.	.	38	.	0.45	.	.
GBW 07107	5.1	2.7	1.7	1290	26	6.7	3.1	2.9	0.010	0.98	0.24	0.082	62	44	0.41	173	0.35
VS 8550-04	(4.4)	(2.4)	1.2	.	18	4.5	(2.1)	4.7	.	(0.92)	.	.	28	50	0.40	.	(0.95)
SARM 41	(20)	(5)
US SBC-1 *	7.1	3.8	1.98	.	27	8.5	.	3.7	.	1.4	.	.	52.5	163	0.54	.	2.4
US SGR-1b	(1.9)	1.1	0.56	1960	(12)	(2)	.	1.4	(0.3)	(0.4)	.	.	20	147	.	267	35
JCRM R651

Number	N	Nb	Nd	Ni	P	Pb	Pd	Pr	Pt	Rb	Rh	S%	Sb	Sc	Se	Sm
GBW 03104
GUW TS	.	(13)	(108)	170	.	33	.	.	.	230	.	0.022	(8.2)	22	.	(22.9)
VS 8549-04	.	11	28	39	.	8.2	(0.0013)	(6.5)	(0.0012)	0.014%	.	0.62	.	23	.	5.7
UL AWI 1	.	17	37	61	.	(24)	.	9.3	.	130	.	.	.	16	.	7
GBW 07107	540	14.3	48	37	690	8.7	.	13.6	.	205	.	(0.0066)	0.18	18.5	0.075	8.4
VS 8550-04	.	12	25	50	.	14.9	(0.0023)	6.2	(0.0022)	112	(0.001)	1.02	(1)	20	.	5.4
SARM 41	.	(8)	.	122	.	(30)	.	.	.	59	.	(0.15)
US SBC-1 *	.	15.3	49.2	82.8	.	35	.	12.6	.	147	.	0.715	1.01	20	.	9.6
US SGR-1b	.	(5.2)	16	(29)	.	38	1.53 T	3.4	4.6	(3.5)	2.7
JCRM R651

Number	Sn	Sr	Ta	Tb	Te	Th	Ti	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
GBW 03104
GUW TS	(4.1)	88	(0.97)	(2.4)	.	.	(9.1)	.	.	(22)	960	.	150	(15)	63	290
VS 8549-04	2.2	150	0.86	0.95	.	8.2	.	(0.5)	2.1	148	(3.5)	28	2.9	96	176	
UL AWI 1	.	108	1.2	0.94	.	12	.	0.42	3	134	.	29	3	99	223	
GBW 07107	2.0	90	0.9	1.02	(0.023)	12.8	3950	0.71	0.43	1.5	87	0.79	26	2.6	55	96
VS 8550-04	(3.2)	142	(0.7)	(0.74)	.	7.1	.	(0.33)	1.65	122	(3.3)	26	2.7	97	176	
SARM 41	.	54	.	.	.	(12)	.	.	.	139	.	17	.	76	146	
US SBC-1 *	3.3	178	1.1	1.2	.	15.8	.	0.89	0.56	5.76	220	1.6	36.5	3.64	186	134
US SGR-1b	(1.9)	420	.	.	.	4.8	.	.	(0.18)	5.4	130	2.6	(13)	(0.94)	74	(53)
JCRM R651

* Provisional

SILLIMANITE

= class, where 1 = CRM and 2 = RM

#	Number	Al ₂ O ₃	SiO ₂	CaO	Fe ₂ O ₃	K ₂ O	Li ₂ O	MgO	MnO	Na ₂ O	TiO ₂	LOI	Units
2	CERAM 2CAS12	63.8	33.9	0.25	0.31	0.13	.	0.12	.	0.15	1.31	0.13	25 or 100 g
1	BCS 309	61.1	34.1	0.22	1.51	0.46	(0.01)	0.17	(0.03)	0.34	1.92	.	100 g

CRM SILLIMANITE SCHIST

analysis listed in mass %

Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	FeO	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	100 g units
SARM 44	58.80	0.14	2.06	(1.0)	(0.18)	(0.1)	(0.03)	(0.05)	(0.10)	34.84	1.83	

continued analysis listed in mg/kg

Number	Ba	Ce	Co	Cr	Cu	Ga	Mo	Nb	Ni	Pb	Rb	Sr	Th	V	Y	Zn	Zr
SARM 44	(50)	(220)	(8)	384	(10)	(55)	(15)	96	(15)	(30)	13	5	50	395	84	271	406

CRM SILICEOUS MINERAL SETS

available in SETS/3, as grouped

50 g units

Number	Material	SiO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI
JCRM R702	Albite	67.69	19.64	0.546	0.058	0.137	0.103	0.004	11.31	0.139	.	0.030	0.23
JCRM R703	Potassium Feldspar	66.99	17.93	0.095	0.082	11.02	0.040	0.003	3.32	0.008	.	0.005	0.36
JCRM R803	Prophyllite	68.52	23.95	0.033	0.047	2.32	0.017	0.0014	0.165	0.018	0.02	0.104	4.40
JCRM R604	Gairome Clay	47.88	35.37	0.216	1.357	0.468	0.251	0.006	0.083	0.020	(0.014)	0.865	13.37
JCRM R605	Kaolin	49.77	35.64	0.004	0.283	(0.008)	0.004	.	0.032	0.105	(0.023)	0.068	13.90
JCRM R751	Pottery Stone	79.32	14.15	0.033	0.340	(3.00)	0.049	0.003	0.121	0.009	(0.0010)	0.010	2.73

Also see our Industrial Materials catalog for more Siliceous Materials
<http://www.brammerstandard.com/pdf/industrial.pdf>

CRM SILT

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	Co ₂	CaO	FeO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	L.O.I.	Units
VS 5366-90	60.9	14.35	2.4	2.95	1.9	5.44	3.58	2.54	0.088	2.33	0.18	0.08	0.62	6.5	50 g
VS 3133-85	60.85	14.40	.	2.95	.	5.45	3.56	2.54	0.087	2.33	0.18	(0.10)	0.62	6.39	100 g
VS 3132-85	60.54	16.46	.	0.41	.	8.76	2.43	1.60	0.13	1.61	0.19	(0.027)	0.98	6.78	100 g
VS 3131-85	47.0	9.48	.	7.76	.	5.92	2.26	6.06	0.30	0.53	0.13	(0.037)	0.50	20.10	100 g
VS 5367-90	46.7	9.45	9.8	7.74	1.1	5.88	2.24	6.0	0.30	0.53	0.13	0.03	0.50	20.0	50 g

continued analysis listed mass %

Number	As	B	Ba	Ce	Cr	Cu	Li	Ni	Rb	Sb	Sr	V	Zn	Zr
VS 5366-90	0.04	0.007	0.09	0.007	0.008	0.019	0.0035	0.0036	0.011	0.013	0.027	0.011	0.0094	0.023
VS 3133-85	(0.043)	0.006	0.091	0.008	0.0088	0.019	0.0037	0.0036	0.012	(0.0015)	0.028	0.011	0.009	0.023
VS 3132-85	(0.0038)	0.007	0.057	(0.006)	0.014	0.0048	0.00716	0.0072	0.0077	(0.00019)	0.013	0.018	0.012	0.022
VS 3131-85	(0.0016)	0.007	0.062	(0.006)	0.0068	0.0037	0.0096	0.0040	0.0061	.	0.025	0.011	0.005	0.013
VS 5367-90	.	0.008	0.059	0.005	0.0062	0.0037	0.009	0.0040	0.0062	.	0.025	0.0097	0.0049	0.013

continued analysis listed in mg/kg

Number	Ag	Be	Cd	Co	Cs	Ga	Ge	La	Mo	Nb	Nd	Pb	Sc	Sm	Sn	W	Y	Yb
VS 5366-90	.	4	.	13	5	18	.	55	6.5	11	30	55	12	5	5	12	25	2.9
VS 3133-85	(0.8)	3.7	(1.5)	13	5.8	16	1.4	61	10	17	.	58	17	.	5	.	26	3.3
VS 3132-85	(0.17)	2.8	(0.2)	30	4.1	16	1.6	43	2.5	13	.	23	20	.	3.9	.	30	4.3
VS 3131-85	(0.2)	2.4	(2.3)	21	4	11	(1.2)	(38)	2.4	11	.	20	11	.	5	.	22	(2.8)
VS 5367-90	.	2.1	.	21	3.2	11	.	35	2.1	9	15	17	10	3	3.6	.	21	3

CRM SILVER ORE

analysis listed in mass % except * which is mg/kg

GBM, USZ: 250 g

KZ: 100 g

SRM: 200 g

Number	Ag*	Ba	Cu	Fe	Fe ₂ O ₃	Pb	S	SO ₃	Zn	Al ₂ O ₃	As	Bi	CO ₂	CaO	Cd	Co*	F	Ge*
USZ 9-92	740	.	2.25	.	.	0.041	.	.	0.20
USZ 8-91	331	.	0.83	.	48.40	0.13	.	6.85	0.59	2.11	0.53	0.11	.	0.25	0.0020	.	.	.
USZ 7-91	169	.	0.46	.	.	0.101	.	.	0.42	0.0015	.	.	.
GBM908-13	151.4	.	0.0176	.	.	1.7721	0.29
KZ 6587-93	60.2	33.6	0.019	2.5	.	2.86	11.5	.	2.72	.	0.016	.	.	.	0.012	.	.	.
GBM310-2	45.5	.	0.6936	.	.	0.6577	.	.	2.0680	.	0.0078	39	.	.
KZ 3031-84	37.4	.	3.37	15.17T	.	.	2.78	.	.	4.93	.	2.87	28.05	.	.	.	0.056	.
GBM310-1	19.0	.	0.5825	.	.	0.3046	.	.	0.9772	.	0.0362	36	.	.
KZ 6586-93	19	0.38	0.013	2.03	.	3.5	0.55	.	0.045
KZ 6588-93	13.7	0.42	.	3.67	.	1.57	5.88	.	4.68	0.013	.	.	4.4
KZ 47-85	8.7	.	0.42	21.0	.	.	2.70
KZ 3030-84	8.6	.	.	13.84T	.	.	2.04	.	.	10.85	.	.	1.04	18.94	.	.	0.048	.
SRM 886	8.25	1.466
KZ 48-85	7.3	.	1.98	15.9T	.	.	1.94	.	.	5.47	.	.	2.73	29.75	.	.	0.054	.
KZ 8079-94	3.7	.	0.73	.	.	0.62	1.25	.	0.41	0.016	.	.	.
KZ 3029-84	2.1	.	0.30	3.11T	.	.	1.59	.	.	15.18	0.074	.
KZ 8078-94	1.6	.	0.38	.	.	0.21	0.75	.	0.15	0.0036	.	.	.

continued

Number	K ₂ O	MgO	MnO	Mo	Na ₂ O	Ni	P ₂ O ₅	Re*	Sb	Se*	SiO ₂	Sr	Te*	TiO ₂	Zr
USZ 9-92
USZ 8-91	0.53	1.48	2.77	.	.	.	0.54	.	0.50	.	17.80	.	.	0.12	.
USZ 7-91
GBM908-13
KZ 6587-93	0.013	.	.	0.69
GBM310-2	0.0029
KZ 3031-84	0.26	1.33	0.33	0.18	0.18	.	0.40	.	.	13.1	33.56	.	9.1	0.19	.
GBM310-1	0.0346
KZ 6586-93	0.019
KZ 6588-93	0.0066	.	.	0.029
KZ 47-85	.	.	.	0.012
KZ 3030-84	0.48	2.06	0.41	0.38	0.16	.	0.17	0.30	.	.	42.32	.	.	0.54	.
SRM 886
KZ 48-85	0.13	0.66	0.36	.	0.10	.	0.11	0.04	.	5.7	33.77	.	.	0.147	.
KZ 8079-94	0.29
KZ 3029-84	4.06	.	0.081	0.0086	1.95	.	0.094	0.043	.	.	68.09	.	.	0.42	.
KZ 8078-94	0.072

SLATE WITH EXTENSIVE ANALYSIS

= class, where 1 = CRM and 2 = RM

analysis listed in mass %

#	Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI
1	GUW TB2	60.4	20.5	.	0.20	5.4	6.95T	3.6+	0.86	1.86	0.047	1.29	0.095	.	0.93	3.46
1	GUW TB	60.23	20.64	0.14	.	5.43	6.90	3.78+	3.87	(1.93)	(0.052)	1.32	0.097	.	0.93	.
1	JSL-1	59.47	17.60	(0.769)	1.479	4.523	1.875	+3.92 -0.654	2.845	2.413	0.0599	2.184	0.202	.	0.725	.
1	JSL-2	59.45	18.17	(1.236)	1.885	5.048	0.959	+4.158 -0.362	3.008	2.385	0.0818	1.344	0.164	0.1467	0.754	.
2	IAG OU-6	57.35	20.45	(0.23)	0.74	(1.65)	8.94T	(0.14-)	3.03	2.41	0.28	1.76	0.12	.	0.99	3.62

continued

analysis listed in mg/kg

Number	As	Ba	Be	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	Gd	Hf	Ho	La	Li	Lu
GUW TB2	.	649	.	14	92	11	49	109	.
GUW TB	10.5	780	4.1	104	14	82	9	49	1.8	.	.	740	25	.	5	.	61	111	0.45
JSL-1	14.9	305	2.28	60.6	15.5	60.9	7.60	40.8	(5.11)	.	1.22	598	.	.	4.63	0.688	29.3	(50.7)	0.442
JSL-2	11.4	302	2.68	69.6	15.7	64.7	8.24	44.5	4.71	.	1.14	678	.	.	5.54	(0.671)	32.7	52.6	0.404
IAG OU-6	13.23	480	(2.53)	77.1	29.2	70.7	8.10	40.4	5.06	2.93	1.36	.	24.17	5.30	4.70	1.04	33.2	(95.3)	0.45

Number	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm
GUW TB2	.	.	39	.	.	185	.	.	.	5	159
GUW TB	.	50	40	8	.	180	3.4	16	8.4	6	160	1.4	.	18	.	.
JSL-1	9.53	28.8	37.6	17.4	6.07	117	.	16.7	6.02	.	193	0.842	0.717	9.97	.	.
JSL-2	12.3	32.0	40.6	19.7	(6.44)	118	.	16.8	5.95	.	230	1.04	0.727	11.5	.	.
IAG OU-6	14.49	30.2	40.2	28.80	7.91	121.3	(0.56)	23.1	6.01	2.67	131.7	1.02	0.86	11.3	(0.54)	(0.45)

Number	U	V	Y	Yb	Zn	Zr	Units
GUW TB2	.	96	.	3.8	94	180	50 g
GUW TB	.	107	39	3.3	94	180	50 g
JSL-1	2.63	131	30.0	2.81	108	174	100 g
JSL-2	2.92	122	31.3	3.15	101	191	100 g
IAG OU-6	1.92	129.8	27.75	2.98	111.4	174.2	~35 g

B: 0.0090% W: 0.00022%

CRM SOIL - AQUA REGIA METHOD

certified analysis listed in mg/kg, BAM U115 is one sample with two methods used

Number	As	Cd	Co	Cr	Cu	Hg	Mn	Ni	Pb	V	Zn	Units	Method Used with 11465 Correction
BAM U115	27.7	4.52	7.35	96.9	167	4	.	29.3	16.4	22.4	342	35 g	EN 16174 Method A open vessel reflux
BAM U115	27.9	4.65	7.3	99.6	171	4.07	.	29.9	16.9	23.5	349	35 g	EN 16174 Method B microwave assisted
BAM U110 *	13.0	7.0	14.5	190	262	49.3	580	95.6	185	.	990	60 g	ISO 11466

* BAM U110 spectroscopic analysis also certified, see "Soil - Contaminated"

informational analysis listed in mass %

Number	Si	Al	Ca	Fe	K	S	Mg	Dry Matter	LOI	Org.C	Inorg.C	Tot.C	H	N
BAM U115	34.7	3.2	3.5	2.2	1.4	.	.	98.6 @ 105°C	8.3 @ 550°C	2.5	1.1	.	.	.
BAM U110 *	25.7	5.1	4.1	2.8	1.9	1.1	1.0	97.3 @ 105°C	13.3 @ 550°C	6.7	0.8	7.5	1.2	0.4

CRM AVAILABLE NUTRIENTS IN SOIL

500 g or 1000 g units

Number	Total N w(N)/10 ⁻²	Hydrolyzable N w(N)/10 ⁻⁶	Organic Matter w(OM)10 ⁻²	Cation Exchange Capacity cmol(+)/kg	Exchangeable Al cmol(1/3Al ³⁺)/kg	Available B w(B)/10 ⁻⁶	Exchangeable Ca cmol(1/2Ca ²⁺)/kg	Available Cu w(Cu)/10 ⁻⁶	Available Fe w(Fe)/10 ⁻⁶
NCS DC85103	0.094	66	1.21	(22.4)	.	0.34	.	0.82	26
NCS DC85105	0.078	67	1.63	11.2	0.91	0.34	4.2	(2.9)	29

Number	Exchangeable H cmol(H ⁺)/kg	Available K w(K)/10 ⁻⁶	Exchangeable K cmol(K ⁺)/kg	Exchangeable Mg cmol(1/2Mg ²⁺)/kg	Available Mn w(Mn)/10 ⁻⁶	Available Mo w(Mo)/10 ⁻⁶	Exchangeable Na cmol(Na+)/kg	Available P w(P)/10 ⁻⁶	Available Si w(Si)/10 ⁻⁶	Available Zn w(Zn)/10 ⁻⁶	pH
NCS DC85103	.	298	.	.	(199)	0.10	.	13.8	283	0.66	(8.14)
NCS DC85105	0.22	156	0.40	1.21	(17)	0.20	(0.11)	14.8	432	(2.6)	(5.44)

CRM MERCURY IN SOIL

analysis listed in mass % except * which is mg/kg

30 or 50 g

Number	Hg*	Al ₂ O ₃	C	CaO	Fe ₂ O ₃ T	K ₂ O	MgO	MnO	N	Na ₂ O	S	SiO ₂	TiO ₂	Dry Mass
USZ 305	2.75	(13.38)	(1.31)	(4.02)	(4.95)	(2.88)	(2.10)	(0.104)	(0.085)	(1.63)	(0.071)	(61.89)	(0.659)	(98.90%)
USZ 304	1.52	(11.96)	(1.42)	(4.55)	(4.22)	(2.85)	(1.79)	(0.082)	(0.075)	(1.99)	(0.093)	(64.11)	(0.605)	(99.21%)
USZ 303	0.157	(13.10)	(1.19)	(3.39)	(4.68)	(2.98)	(1.68)	(0.097)	(0.088)	(1.84)	(0.021)	(64.39)	(0.65)	(99.05%)

CRM SOIL

analysis listed in mass %														100 g units	
Number	Al ₂ O ₃	T.C	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O-	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI
JSo-1	17.99	.	2.56	.	.	11.49	.	0.34	2.11	0.202	0.66	0.48	38.28	1.23	.
USZ 15-94	14.84	.	2.66	(1.44)	5.75	.	(4.97)	2.47	1.65	0.08	3.14	0.16	62.51	0.86	(5.29)
USZ 16-94	(14.11)	.	2.78	1.22	(5.18)	.	.	2.61	1.84	(0.08)	3.07	(0.18)	63.18	0.88	(4.53)

continued informational analysis listed in mg/kg

Number	B	Ba	Co	Cr	Cs	Cu	Li	Ni	Pb	Rb	Sr	V	Y	Zn	Zr
JSo-1	12.0	269	32	71	1.5	169	11.2	39	13	14.5	196	300	24.9	105	96
USZ 15-94
USZ 16-94

CRM SOIL SET

available in SET/6 ONLY analysis listed in mg/kg% 25 g units

Number	As	Cd	Cr	Hg	Pb	Se
J SAC 0466	1093	1199	1483	113.5	1214	1175
J SAC 0465	550	607.4	738	57.8	612.4	587
J SAC 0464	271.1	301.0	499	28.6	302.7	291.9
J SAC 0463	137.6	146.8	244	14.76	151.6	141.5
J SAC 0462	71.5	74.2	149.6	7.27	73.7	71.6
J SAC 0461	21.53	(0.30)	97.2	0.075	24.4	(0.44)

CRM SOIL (TILL) REFERENCE MATERIALS WITH ACID EXTRACTION

analysis listed in mass %																100 g units			
Number	SiO ₂	Al ₂ O ₃	CaO	Fe	Fe ₂ O ₃	K ₂ O	MgO	Mn	MnO	Na ₂ O	P	P ₂ O ₅	S	Ti	TiO ₂	LOI 1000°C	LOI 500°C	Sum	
CAN TILL-3	69.1	12.2	2.63	2.78	3.92	2.42	1.71	0.0520	0.06	2.64	0.0490	0.11	<0.05	0.2910	0.49	4.6	3.6	99.88	
CAN TILL-1	60.9	13.7	2.72	4.81	6.82	2.22	2.15	0.1420	0.18	2.71	0.0930	0.22	<0.05	0.5990	0.98	7.3	6.3	99.90	
CAN TILL-2	60.8	16.0	1.27	3.84	5.39	3.07	1.83	0.0780	0.10	2.19	0.0750	0.17	<0.05	0.5300	0.88	8.1	6.8	99.80	

continued analysis in mg/kg except % for mass percent and * for parts per billion

Number	As	Au*	Ba	Be	Bi	Br	Ce	Co	Cr	Cs	Cu	Eu	Er	Hf	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Rb	Sb	Sc
CAN TILL-3	87	6	489	2.0	<5	4.5	42	15	123	1.7	22	<1.0	1.4	8	21	21	0.2	2	7	16	39	26	55	0.9	10
CAN TILL-1	18	13	702	2.4	<5	6.4	71	18	65	1.0	47	1.3	3.6	13	28	15	0.6	2	10	26	24	22	44	7.8	13
CAN TILL-2	26	2	540	4.0	<5	12.2	98	15	74	12.	150	1.0	3.7	11	44	47	0.6	14	20	36	32	31	143	0.8	12

continued partial extraction elements from dilute acid

Number	Sm	Sr	Ta	Tb	Th	U	V	W	Y	Yb	Zn	Zr	Ag	Co	Cu	Fe%	Mn	Mo	Ni	Pb	Zn
CAN TILL-3	3.3	300	<0.5	<0.5	4.6	2.1	62	<1	17	1.5	56	230	49	10	23	2.2	310	1	32	17	43
CAN TILL-1	5.9	291	0.7	1.1	5.6	2.2	99	<1	38	3.9	98	502	<0.2	12	49	3.4	1020	1	17	14	71
CAN TILL-2	7.4	144	1.9	1.2	18.4	5.7	77	5	40	3.7	130	390	12	12	152	3.4	570	13	30	24	116

continued partial extraction elements from concentrated acid

Number	Ag	As	Ba	Bi	Cd	Co	Cr	Cu	Fe%	Hg*	Mn	Mo	Ni	Pb	V	Zn
CAN TILL-3	1.6	84	43	<3	<0.2	11	73	23	2.0	107	310	<2	32	16	33	43
CAN TILL-1	0.2	13	84	<3	<0.2	12	30	48	3.1	92	950	<2	18	12	48	70
CAN TILL-2	0.2	22	95	4	0.3	13	40	149	3.2	74	530	11	31	21	38	116

CRM SOIL

analysis listed in mass %		100 g units											
Number	Type	SiO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	As	B
VS 2498-83	Sandy, Turf-Ash	91.24	3.36	0.27	0.99	1.23	0.13	0.011	0.51	0.036	0.29	0.0003	0.003
VS 2499-83	Sandy, Turf-Ash	91.24	3.36	0.27	0.99	1.23	0.13	0.011	0.51	0.036	0.29	0.0017	0.003
VS 2507-83	Black	71.49	9.81	1.60	3.48	2.42	0.95	0.079	0.81	0.18	0.74	0.0008	0.0056
VS 2508-83	Black	71.49	9.81	1.60	3.48	2.42	0.95	0.079	0.81	0.18	0.74	0.0021	0.0056
VS 2509-83	Black	71.49	9.81	1.60	3.48	2.42	0.95	0.079	0.81	0.18	0.74	0.004	0.0056
VS 2501-83	Red	59.18	17.01	0.17	7.86	0.98	0.92	0.051	0.15	0.10	1.56	0.0010	0.006
VS 2502-83	Red	59.18	17.01	0.17	7.86	0.98	0.92	0.051	0.15	0.10	1.56	0.003	0.006
VS 2503-83	Red	59.18	17.01	0.17	7.86	0.98	0.92	0.051	0.15	0.10	1.56	0.005	0.006
VS 2504-83	Grey	52.65	11.48	11.47	4.60	2.09	2.99	0.089	1.64	0.17	0.64	0.0013	0.0063
VS 2505-83	Grey	52.65	11.48	11.47	4.60	2.09	2.99	0.089	1.64	0.17	0.64	0.0029	0.0063
VS 2506-83	Grey	52.65	11.48	11.47	4.60	2.09	2.99	0.089	1.64	0.17	0.64	0.006	0.0063

continued analysis listed in mass % except * which is mg/kg

Number	Ba	Be*	Cd*	Ce	Co	Cr	Cs*	Cu	F	Ga*	Hg*	La*	Li	Mo*
VS 2498-83	0.031	1.1	0.1	0.0017	0.00020	0.010	1.6	0.0009	.	5	0.03	10	0.00035	1.5
VS 2499-83	0.031	10	1.3	0.0017	0.0045	0.010	1.6	0.010	.	5	0.13	10	0.00035	7
VS 2507-83	0.050	2.0	0.10	0.007	0.0009	0.0083	4	0.0025	0.028	11	0.05	36	0.0023	1.2
VS 2508-83	0.050	9	1.8	0.007	0.0046	0.0083	4	0.011	0.028	11	0.21	36	0.0023	6
VS 2509-83	0.050	24	4.5	0.007	0.013	0.0083	4	0.027	0.028	11	0.4	36	0.0023	11
VS 2501-83	0.027	1.6	0.12	0.007	0.0014	0.018	9	0.0047	0.04	15	0.08	30	0.005	3
VS 2502-83	0.027	10	2.6	0.007	0.0063	0.018	9	0.017	0.04	15	0.26	30	0.005	8
VS 2503-83	0.027	25	5	0.007	0.015	0.018	9	0.031	0.04	15	0.4	30	0.005	13
VS 2504-83	0.050	2.2	0.3	0.006	0.0012	0.0084	5	0.0034	0.05	13	0.025	29	0.0032	1.4
VS 2505-83	0.050	8	2.1	0.006	0.0057	0.0084	5	0.012	0.05	13	0.18	29	0.0032	6
VS 2506-83	0.050	26	5.5	0.006	0.015	0.0084	5	0.029	0.05	13	0.4	29	0.0032	13

Number	Nb*	Ni	Pb	Rb*	S	Sc*	Se*	Sn	Sr	V	Y*	Yb*	Zn	Zr
VS 2498-83	12	0.0010	0.0008	32	.	2.6	(0.8)	0.00019	0.0069	0.0014	13	1.5	0.0010	0.035
VS 2499-83	12	0.0087	0.0087	32	.	2.6	(0.8)	0.0019	0.0069	0.0014	13	1.5	0.014	0.035
VS 2507-83	14	0.0032	0.0018	88	0.05	11	(3)	0.0003	0.011	0.0072	31	4.1	0.0056	0.047
VS 2508-83	14	0.011	0.009	88	0.05	11	(3)	0.0020	0.011	0.0072	31	4.1	0.018	0.047
VS 2509-83	14	0.030	0.026	88	0.05	11	(3)	0.006	0.011	0.0072	31	4.1	0.046	0.047
VS 2501-83	25	0.0054	0.0023	80	0.04	15	(3)	0.0005	0.005	0.018	27	3.6	0.0087	0.034
VS 2502-83	25	0.016	0.015	80	0.04	15	(3)	0.0022	0.005	0.018	27	3.6	0.027	0.034
VS 2503-83	25	0.038	0.028	80	0.04	15	(3)	0.006	0.005	0.018	27	3.6	0.061	0.034
VS 2504-83	13	0.0045	0.0017	81	0.04	14	(1)	0.0004	0.031	0.009	26	3.3	0.0070	0.019
VS 2505-83	13	0.013	0.010	81	0.04	14	(1)	0.0020	0.031	0.009	26	3.3	0.017	0.019
VS 2506-83	13	0.032	0.028	81	0.04	14	(1)	0.006	0.031	0.009	26	3.3	0.039	0.019

CRM SOIL

analysis listed in mass %												
Number	Si	Al	Ca	Fe	K	Mg	Mn	N	Na	P	Ti	Units
SRM 2711a	31.4	6.72	2.42	2.82	2.53	1.07	0.0675	.	1.20	0.0842	0.317	50 g
GBW 08302	30.57	7.11	2.59	3.34	2.12	1.53	0.0677	0.128	1.52	0.086	0.40	15 g
BCR 142R	0.0970	40 g
ERM-CC690	70 g

continued analysis listed in mg/kg except % which is mass %

Number	As	B	Ba	Be	Br	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Hf	Hg	In	La	Lu
SRM 2711a	107	.	730	.	54.1	(70)	9.89	52.3	(6.7)	140	(5)	.	(1.1)	.	(5)	(9.2)	7.42	.	(38)	(0.5)	
GBW 08302	3.8	(25)	(509)	2.96	(1.3)	0.081	83.6	13.1	60.8	(7.3)	24.6	(5)	(239)	1.4	(13)	.	(7.3)	(0.018)	(0.06)	41.9	(0.48)
BCR 142R	0.34	.	12.1	(113)	.	69.7	0.067	.	.	.
ERM-CC690	49.1	2.90	.	.	.	3.2	24.4	.

Number	Mo	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se	Sm	Sr	Ta	Tb	Th	Tm	U	V	W	Y	Yb	Zn
SRM 2711a	.	(29)	21.7	0.140%	.	(120)	23.8	(8.5)	(2)	5.93	242	(1)	(0.8)	(15)	.	3.01	80.7	.	.	(3)	414
GBW 08302	(0.8)	42.3	31.1	14.2	(9)	135	(0.4)	10.8	0.16	7.1	163	(1.1)	(0.9)	17.6	.	3.84	77.5	(3.5)	(25)	3.1	58
BCR 142R	.	.	64.5	40.2	(101)
ERM-CC690	.	19.1	7.9	.	.	3.5	.	.	0.50	7.6	0.232	1.90	.	.	.	1.57	.

CRM SOIL

analysis listed in mass %														70 g units			listed in mg/kg		
Number	Al ₂ O ₃	T.C	C(org)	CO ₂	CaO	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	N	Na ₂ O	SiO ₂	Ti	Ag	As	B		
NCS ZC73005	14.4	1.09	0.79	(1.1)	2.45	(0.8)	5.32	(4.0)	2.46	1.90	0.081	1.59	64.5	0.406	0.084	6.5	46		
NCS ZC73003	13.27	(1.5)	(0.47)	3.9	5.83	1.39	4.71	(3.6)	2.62	2.43	0.055	2.00	60.0	0.392	0.078	12.2	55		
continued analysis listed in mg/kg																			
Number	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	Gd	Ge	Hf
NCS ZC73005	608	2.44	0.35	1.7	0.20	80	50	14.6	70	7.0	27.4	4.8	2.6	1.36	619	18.8	5.5	1.42	6.4
NCS ZC73003	492	2.04	0.30	2.1	0.15	57	(50)	12.6	59	7.2	29	4.9	2.9	1.22	592	16.8	5.1	1.3	5.5
continued analysis listed in mg/kg																			
Number	Hg	Ho	I	In	La	Li	Lu	Mn	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	S		
NCS ZC73005	0.089	0.93	0.9	0.057	41	39	0.42	688	0.65	14.4	36	33	730	31	9.2	108	173		
NCS ZC73003	0.021	1.01	1.4	0.058	29	36	0.46	774	0.96	12	27.9	32	708	19	7.0	94	154		
continued analysis listed in mg/kg (DA) indicates decomposition by aqua regia																			
Number	Sb(DA)	T.Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
NCS ZC73005	0.073	(0.81)	11.7	0.16	6.4	3.1	152	1.08	0.87	12.7	0.63	0.41	2.45	86	1.5	25	2.53	96	227
NCS ZC73003	1.05	(1.17)	12.6	0.16	5.6	2.8	240	0.85	0.84	10	0.51	0.44	2.4	86	1.64	26.4	2.9	78	195

CRM SOIL

analysis listed in mass %														T = Total			100 g units				
Number	SiO ₂	Al ₂ O ₃	CaO	CO ₂	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	MnO	N	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI				
NCS DC87103	72.92	12.28	1.44	(0.083)	(0.36)	3.38	(3.78)	(2.37)	2.16	1.14	0.072	0.029	2.20	0.11	(0.0045)	0.69	(3.28)				
NCS DC87101	67.96	14.35	0.90	(0.076)	(0.34)	4.69	(5.09)	(3.57)	2.56	1.62	0.093	0.035	1.78	0.10	(0.0065)	0.72	4.64				
NCS DC87105	67.53	10.84	5.42	3.59	(0.58)	2.64	(3.26)	(2.49)	2.18	1.68	0.062	0.021	1.87	0.074	0.0092	0.54	6.67				
NCS DC87102	67.21	10.78	5.21	3.48	(1.06)	2.28	(3.46)	2.29	2.15	1.73	0.066	0.064	1.95	0.15	0.034	0.56	6.73				
NCS DC87104	60.76	10.78	9.07	6.44	(0.68)	2.79	(3.55)	(2.56)	2.01	1.83	0.058	0.020	1.74	0.087	(0.048)	0.55	9.62				
continued analysis listed in mg/kg																					
Number	As	B	Ba	Be	Bi	Cd	Cl	Co	Cr	Cu	F	Ga	Hg	I	La	Li	Mo	Nb	Ni	Pb	Rb
NCS DC87103	6.3	50	524	1.9	(0.17)	(0.20)	(50)	12	56	23	383	15	0.017	.	38	28	(0.68)	14	22	19	91
NCS DC87101	10	46	677	2.4	(0.24)	(0.26)	(61)	15	93	23	458	17	0.014	(3.1)	43	37	(1.09)	15	41	28	111
NCS DC87105	8.2	33	555	1.8	(0.21)	(0.21)	(85)	8.9	54	16	657	13	(0.018)	.	32	25	(0.71)	11	22	20	83
NCS DC87102	9.8	(51)	469	2.0	(0.20)	(0.22)	600	9.4	61	17	(414)	12	0.031	.	36	27	(0.94)	12	23	21	86
NCS DC87104	9.4	44	448	1.8	0.24	(0.22)	222	9.2	62	17	559	13	(0.015)	.	34	38	(0.87)	11	23	19	82
continued analysis listed in mg/kg																					
Number	Sb	Se	Sn	Sr	Te	Th	U	V	W	Y	Zn	Zr									
NCS DC87103	0.65	0.11	3.2	227	(0.036)	10	1.9	74	1.5	22	48	331									
NCS DC87101	0.73	(0.12)	(3.2)	168	0.033	12	1.9	88	1.8	24	68	274									
NCS DC87105	0.70	(0.08)	2.2	231	(0.053)	8.9	2.4	66	1.3	19	(39)	298									
NCS DC87102	0.84	0.14	2.9	197	(0.039)	9.6	1.9	63	1.5	21	51	291									
NCS DC87104	0.78	(0.12)	2.4	296	(0.046)	9.4	1.8	65	1.4	19	45	258									

CRM SOIL

analysis listed in mass %		T = Total												100 g units		
Number	Type	SiO ₂	Al ₂ O ₃	CO ₂	CaO	Cr ₂ O ₃	FeO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI
NCS DC85112	Agricultural	83.34	8.89	.	(0.16)	.	.	1.34	0.65	(0.20)	0.015	(0.038)	0.124	(0.014)	0.22	4.86
VS 5360-90	Sod-Pozolic	78.3	9.58	.	0.82	.	0.5	3.00	2.48	0.77	0.070	1.15	0.075	0.03	0.84	2.6
SARM 42	Sedimentary	74.09	10.03	.	0.89	0.63	(4.0)	4.68	0.45	1.92	0.10	(0.15)	(0.03)	(0.02)	0.36	.
NCS DC85111	Agricultural	69.68	14.58	.	(0.22)	.	.	5.21	1.08	0.54	0.029	(0.090)	0.122	(0.014)	0.96	7.52
VS 5359-90	Chernozemic	69.4	10.30	.	1.62	.	.	3.83	2.27	1.03	0.077	0.80	0.18	0.04	0.75	9.3
VS 5358-90	Light Chestnut	65.5	12.45	1.2	2.83	.	.	4.90	2.58	1.95	0.090	1.16	0.22	0.03	0.74	6.7
NCS DC85107	Agricultural	65.37	15.06	.	1.68	.	.	4.98	2.72	1.62	0.094	2.48	0.120	(0.013)	0.74	4.83
NCS DC85108	Agricultural	63.06	12.76	.	4.57	.	.	4.49	2.43	2.01	0.077	1.69	0.162	(0.017)	0.68	7.71
NCS DC85110	Agricultural	61.03	16.21	.	0.84	.	.	6.20	2.45	1.90	0.050	0.99	0.098	(0.033)	0.92	9.01
NCS DC85109	Agricultural	53.72	14.74	.	7.93	.	.	5.72	2.72	2.09	0.106	0.99	0.197	(0.019)	0.65	11.17

continued analysis listed in mg/kg except % which is mass %

Number	Ag	B%	Ba%	Be	C%	Ce%	Co	Cr%	Cs	Cu	F%	Ga	Ge	La	Li
NCS DC85112	.	(0.0020)	2.8
VS 5360-90	0.08	0.004	0.051	1.5	0.55	0.005	10	0.008	0.21	18	0.021	9	.	35	16
SARM 42	.	.	(0.0250)	.	.	(0.0030)	35	.	.	17	.	(12)	.	.	.
NCS DC85111	.	0.0071	32
VS 5359-90	0.10	0.005	0.040	2.0	3.6	0.006	10	0.008	4	23	0.027	10	1.0	35	25
VS 5358-90	0.12	0.007	0.046	2.1	1.7	0.006	14	0.014	4	30	0.034	13	1.6	38	28
NCS DC85107	.	0.0034	24
NCS DC85108	.	0.0054	25
NCS DC85110	.	0.0065	42
NCS DC85109	.	0.0075	29

Number	Mo	Nb	Ni	Pb	Rb	Sc	Sn	Sr%	Th	V%	Y	Yb	Zn	Zr%
NCS DC85112	1.15	22	.
VS 5360-90	0.8	20	25	15	78	9	2.6	0.0012	.	0.0064	27	4	42	0.053
SARM 42	(5)	(8)	125	(10)	22	.	.	0.0037	(5)	0.0094	11	.	44	0.0192
NCS DC85111	1.47	81	.
VS 5359-90	1.0	15	33	16	84	12	3.5	0.014	.	0.0075	30	4	54	0.045
VS 5358-90	1.0	15	58	17	87	13	3.4	0.016	.	0.011	27	3	73	0.030
NCS DC85107	0.80	67	.
NCS DC85108	(0.82)	68	.
NCS DC85110	0.73	93	.
NCS DC85109	1.53	96	.

CRM SOIL

analysis listed in mass %																
Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI	Units
GBW 07418	67.96	14.35	(0.076)	0.90	(0.34)	4.69	(5.09)	(3.57)	2.56	1.62	0.093	1.78	0.10	0.72	4.64	100 g
GBW 07410	65.64	14.55	.	1.42	.	.	4.60	.	2.59	1.25	.	1.90	.	.	.	50 g

continued analysis listed in mg/kg except * which is ng/g

Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu
GBW 07418	.	10	46	677	2.4	(0.24)	.	(0.26)	.	(61)	15	93	.	23
GBW 07410	0.11	10.5	38.3	623	2.6	0.37	(5.0)	0.090	76.6	(45.6)	12.8	66.0	7.9	23.2

Number	Dy	Er	Eu	F	Ga	Gd	Ge	Hg*	Ho	I	In	La	Li	Lu
GBW 07418	.	.	.	458	17	.	.	14	.	(3.1)	.	43	37	.
GBW 07410	(5.3)	(2.9)	1.2	438	18.8	5.6	(1.6)	66	(1.1)	(2.6)	(0.07)	37.6	33.2	0.46

Number	Mn	Mo	N	Nb	Nd	Ni	P	Pb	Pr	Rb	S	Sb	Sc	Se	Sm	Sn
GBW 07418	.	(1.09)	350	15	.	41	.	28	.	111	(65)	0.73	.	(0.12)	.	(3.2)
GBW 07410	706	0.84	(1200)	17.1	34.4	27.6	439	29.2	(8.8)	109	(174)	0.93	11.4	0.28	6.6	4.2

Number	Sr	Tb	Te	Th	Ti	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
GBW 07418	168	.	0.033	12	.	.	.	1.9	88	1.8	24	.	68	274
GBW 07410	188	0.85	(0.035)	12.0	4600	0.62	0.48	2.4	82.7	5.0	27.4	3.1	72.8	337

CRM SOIL

analysis listed in mass %				Org = Organic T = Total						DC360xx: 75 g units				DC730xx: 70 g units						
Number	SiO ₂	Al ₂ O ₃	C	CaO	Cl	CO ₂	C.Org	Fe ₂ O ₃ T	FeO	H ₂ O+	K ₂ O	MgO	Mn	N	Na ₂ O	S	Ti			
NCS DC73023	78.30	9.65	(0.3)	1.83	0.0038	0.76	(0.1)	2.07	(0.5)	(1.2)	2.56	0.78	0.0309	(0.0106)	2.31	0.0108	0.191			
NCS DC73030	69.11	13.58	(0.6)	0.34	0.48	(0.2)	.	4.97	(0.8)	(5.1)	2.48	1.16	0.0717	0.0617	0.83	0.20	0.45			
NCS DC73028	68.23	13.89	(0.4)	1.09	0.51	(0.2)	.	4.06	(0.6)	(3.4)	2.97	1.47	0.0755	0.0438	2.84	0.0440	0.38			
NCS DC73032	66.15	11.73	1.52	4.59	0.0075	(2.9)	0.73	4.00	1.20	(3.2)	2.18	1.87	0.0561	0.0878	1.90	0.0162	0.41			
NCS DC73024	60.40	10.56	(1.4)	6.80	0.78	4.54	0.25	3.63	(1.1)	(2.7)	2.11	2.58	0.0529	0.0273	3.05	(0.7)	0.32			
NCS DC73029	59.80	13.92	1.28	4.21	0.63	(3.0)	(0.5)	5.54	(1.5)	(4.2)	2.64	2.61	0.0882	0.0600	1.91	(0.0420)	0.50			
continued analysis listed in mg/kg except * which is ng/g																				
Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	Gd	Ge
NCS DC73023	0.050	6.2	24	606	1.3	0.15	0.8	0.058	25	5.0	25	3.0	12.6	2.3	1.3	0.66	219	10.8	2.2	1.11
NCS DC73030	0.092	15.8	83	340	2.7	0.98	24	0.106	89	12.4	62	9.8	28	6.1	3.5	1.25	524	18.3	6.3	1.52
NCS DC73028	0.074	7.8	52	749	2.1	0.25	24	0.065	81	11.6	57	5.5	18.3	4.6	2.6	1.30	419	17.4	5.3	1.28
NCS DC73032	0.070	8.9	52	504	1.9	0.28	3.0	0.14	70	11.2	61	6.0	19.1	4.9	2.8	1.21	551	14.8	5.3	1.30
NCS DC73024	0.066	10.7	62	459	1.7	0.25	7.2	0.15	57	10.2	55	6.3	19.5	4.2	2.4	1.06	495	13.2	4.4	1.21
NCS DC73029	0.069	11.8	77	441	2.3	0.44	26	0.15	78	16.0	82	9.3	32	5.4	3.0	1.4	665	18.5	5.8	1.40
Number	Hf	Hg	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	Re*			
NCS DC73023	3.8	(0.007)	0.46	0.52	0.024	14.0	14.2	0.24	0.51	6.3	12.4	9.6	228	17.4	3.2	80	(0.074)			
NCS DC73030	10.6	0.075	1.22	6.4	0.088	44	55	0.59	1.1	19.2	38	24	414	40	9.8	139	(0.45)			
NCS DC73028	7.2	0.020	0.93	8.6	0.051	44	36	0.43	0.63	15.4	35	26	438	26	9.4	108	(0.12)			
NCS DC73032	7.6	0.030	0.99	1.1	0.045	36	31	0.45	0.47	14.9	34	26	846	21	8.2	91	(0.1)			
NCS DC73024	5.8	0.015	0.84	1.4	0.043	30	32	0.38	0.61	12.6	26	25	587	20	6.9	86	(0.25)			
NCS DC73029	6.1	0.058	1.08	6.1	0.066	42	50	0.48	0.65	17.4	36	38	675	28	9.3	123	(0.17)			
Number	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	
NCS DC73023	0.56	5.1	0.093	2.4	1.3	209	0.42	0.37	(0.03)	4.3	0.51	0.23	1.2	40	0.7	12.7	1.5	29	134	
NCS DC73030	1.05	11.7	0.20	7.1	6.2	55	1.96	1.08	(0.06)	20.6	0.86	0.59	4.0	87	4.1	(3)	3.8	81	342	
NCS DC73028	0.50	10.4	0.11	6.1	2.6	202	1.1	0.85	(0.04)	11.7	0.61	0.43	1.9	69	1.5	25	2.8	59	255	
NCS DC73032	0.86	10.6	0.14	5.8	2.8	184	1.12	0.86	(0.04)	11.3	0.57	0.47	2.3	72	(19.2)	27	3.9	(2)	277	
NCS DC73024	0.88	9.7	0.12	5.0	2.4	242	0.91	0.74	(0.03)	9.9	0.55	0.39	2.3	66	1.6	23	2.5	63	204	
NCS DC73029	0.77	13.8	0.13	6.6	3.4	154	1.3	0.93	(0.06)	13.5	0.71	0.49	2.6	104	2.1	29	3.1	97	210	

CRM SOIL - CONTAMINATED

certified analysis listed in mg/kg

T = Total

Number	As	B	Be	Cd	Co	Cr	Cu	F	Hg	Mn	Ni	Pb	Se	V	Zn	Type	Units
JSAC 0403	199	269	.	183	.	257 T	26.2	269	11.1	252	26.2	224	169	101	91.8	Brown Forest Soil	50 g
JSAC 0402	41.6	115	.	18.5	.	90.5 T	31.3	(132)	1.3	265	29.8	45.2	17.0	119.3	100.7	Brown Forest Soil	50 g
BAM U113	41.9	.	.	3.6	32.3	35.5	458	.	1.95	.	37.6	220	.	26.7	614		40 g
BAM U110 *	15.8	.	.	7.3	16.2	230	263	.	51.5	621	101	197	.	.	1000		60 g
JSAC 0411	11.3	.	1.04	0.274	.	23.5	26.7	.	.	943	11	18.9	1.32	68.6	64.6	Volcanic Ash Soil	50 g
JSAC 0401	10.62	.	5.28	4.25	.	50.4	15.3	.	.	266	18.9	26	0.27	65.0	66.8	Brown Forest Soil	50 g

* Aqua Regia values for BAM U110 listed under "Soil - Aqua Regia Method" in this catalog

CRM SOIL - CONTAMINATED

analysis listed in mass % except as noted

powder 75 g

Number	Hexavalent Cr	Cr	Fe	Mn	Al	Tot.Org.C	Ca	K	Mg	Na	Si	Ti	V	PH	Redox Potential
SRM 2701	0.05512	4.26	23.73	0.2137	(5.05)	(3.69)	(7.47)	(0.174)	(7.47)	(0.255)	(4.17)	(0.547)	(0.236)	9.6	(526 mV)

CRM SOIL - CONTAMINATED

certified analysis listed in mg/kg

55 g units

informational analysis in mass %

Number	As	Cd	Co	Cr	Cu	Hg	Ni	Pb	V	Zn	Al	C.Org	C.Inorg	Ca	Si	Fe	K	LOI @ 500°C
BAM CC018	22.9	5.4	5.9	129	80	1.38	25.8	289	19.4	313	2.1	2.4	0.4	2.6	38.8	1.4	0.9	4.6

CRM SOIL - CYANIDE

analysis in mg/kg powder

Number	Total Cyanide	Uncertainty	Units
BAM U114	23.1	1.3	66 g

SOIL - CONTAMINATED

= class where 1 = CRM and 2 = RM analysis listed in mg/kg except % which is mass % CETEM: 80 g all others: 50-55 g units

# Number	Ag	Al%	As	Au	B	Ba	Be	Bi	Br	C%	Ca%	Cd	Ce	Co	Cr	Cs	Cu	Dy
2 SRM 2780a	72.5	8.43	65.9	6.6	(27)	930	(1.1)	(45)	.	(0.19)	0.247	(4.8)	67.7	16.5	205	8.3	240	(3.1)
1 SRM 2710a	(40)	5.95	1,540	(0.2)	(20)	792	0.964	12.3	(60)	5.99	(23)	(8.25)	342	(3)
1 IRNT SVM	(4)	(8.96)	13.6	.	(70)	582	(500)	.	(5)	.	(0.692)	0.214	(100)	15.4	79.8	(6)	30.0	(5)
1 IRNT SSP	(5)	(7.48)	14.0	.	.	315	6.34	0.285	.	15.6	75.3	.	30.9	.
1 SRM 2709a	.	7.37	(10.5)	.	(74)	979	1.91	0.371	(42)	12.8	130	(5.0)	(33.9)	(3)
1 SRM 2586	.	6.652	8.7	.	.	413	(1.4)	.	.	.	2.218	2.71	58	(35)	301	.	(81)	(5.4)
1 SRM 2587	.	5.86	13.7	.	.	568	(9.2)	.	.	.	0.927	1.92	(57)	(14)	92	.	(160)	.

continued

Number	Er	Eu	Fe%	Ga	Gd	Ge	Hf	Hg	Ho	In	K%	La	Li	Lu	Mg%	Mn%	Mo
SRM 2780a	(2.0)	(0.9)	8.75	(21)	(3.2)	(<6)	(5.5)	(0.2)	(0.7)	(1.65)	3.99	34.4	(14)	(0.33)	0.465	0.0490	25.0
SRM 2710a	.	(0.82)	4.32	.	(3.0)	.	(7)	9.88	.	.	2.17	30.6	.	(0.3)	0.734	0.214	.
IRNT SVM	.	(2)	3.73	.	(7)	.	(10)	0.171	.	.	3.08	(60)	(30)	(500)	(0.593)	0.0897	.
IRNT SSP	.	.	3.73	0.0874	.	.	2.63	.	.	.	(1.19)	0.0734	.
SRM 2709a	.	(0.83)	3.36	.	(3.0)	.	(4)	(0.9)	.	.	2.11	(21.7)	.	(0.3)	1.46	0.0529	.
SRM 2586	(3.3)	(1.5)	5.161	(14)	(5.8)	.	.	0.367	(1.1)	.	0.976	29.7	(25)	.	1.707	0.1000	.
SRM 2587	.	.	2.813	(13)	.	.	.	0.29	.	.	1.583	(29)	(32)	.	0.6690	0.0651	.

continued

Number	Na%	Nb	Nd	Ni	P%	Pb%	Pr	Rb	Re	S%	Sb	Sc	Se	Si%	Sm	Sn	Sr
SRM 2780a	0.108	(20)	28.3	95	0.0286	0.665	(8)	220	(0.003)	8.85	18.3	15.6	(6)	24.1	4.7	(7.2)	121
SRM 2710a	0.894	.	(22)	(8)	0.105	0.552	.	(117)	.	.	52.5	(9.9)	(1)	31.1	(4.0)	.	255
IRNT SVM	(0.3)	.	(50)	30.8	(0.000013)	0.00196	.	(200)	.	.	4.58	(15)	(300)	25	(10)	.	(82.0)
IRNT SSP	.	.	.	37.4	.	0.00413	2.11	274
SRM 2709a	1.22	.	(17)	(85)	0.0688	0.00173	.	(99)	.	.	1.55	(11.1)	(1.5)	30.3	(4)	.	239
SRM 2586	0.468	(6)	26.4	(75)	0.1001	0.0432	(7.3)	(24)	(0.6)	29.15	(6.1)	.	84.1
SRM 2587	1.127	(14)	(25)	(36)	0.0970	0.3242	(11)	.	33.13	.	.	126

continued

Number	Ta	Tb	Te	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn%	Zr	
SRM 2780a	(1.2)	(0.5)	(22)	12.0	0.643	(5.5)	(0.31)	4.0	152	(17.4)	(18)	(2)	0.102	206	LOI: (11.1)
SRM 2710a	(0.9)	(0.5)	.	(18.1)	0.311	(1.52)	.	9.11	(82)	(190)	.	(2)	0.418	(200)	.
IRNT SVM	(1)	(1)	.	(20)	0.55	(<200)	.	(3)	98.3	(3)	.	(4)	0.00888	(350)	.
IRNT SSP	89.7	.	.	.	0.0119	(200)	.
SRM 2709a	(0.7)	(0.5)	.	(10.9)	0.336	(0.58)	.	(3.15)	110	.	.	(2)	(0.0103)	195	.
SRM 2586	.	(0.09)	.	(7)	0.605	.	(0.5)	.	(160)	.	(21)	2.64	0.0352	.	.
SRM 2587	.	.	.	(7.5)	0.3920	.	.	.	(78)	.	(15)	(1.6)	0.03358	.	.

RM

STEATITE

analysis listed in mass %

25 or 100 g units

Number	SiO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	TiO ₂	LOI
CERAM 2CAS14	62.7	0.149	0.249	0.314	0.002	31.28	0.008	0.005	5.10

CRM SULPHUR

Number	Recommended S Value (%)	95% Confidence Limits		Standard Deviation of Laboratories (%)		Number of Sets	Results	Units
		Low%	High%	Between	Within			
CAN HCC-1	33.92	33.80	34.03	0.14	0.095	9	53	50 g
CAN INM-1	22.17	21.97	22.37	0.24	0.051	9	53	50 g

CRM SULPHUR IN VARIOUS FORMS - SEE ALSO "MULTI-METAL ORE"

analysis listed in mass %

Number	Type	S	SO ₄	Al	CO ₂	Ca	Cu	Fe	H ₂ O	Mg	Pb	Si	Zn	LOI	Units
NCS DC71307	Sulphide	52.72	0.0431	46.08	.	.	(0.00234)	.	0.0219	.	5 g
NCS DC71308	Sulphide	34.69	33.30	30.30	.	.	0.0128	.	0.30	.	5 g
CAN HCC-1	Concentrate	33.92	50 g
NCS DC71310	Sulphide	32.33	0.10	2.14	.	.	0.099	.	62.51	.	5 g
CAN WMS-1A	Sulphide	28.17	.	1.350	.	3.09	1.396	45.4	(0.2)	(0.331)	(0.0033)	(4.7)	(0.0130)	.	200 g
CAN INM-1	Concentrate	22.17	50 g
NCS DC71309	Sulphide	13.30	0.00624	0.0127	.	.	84.26	.	0.0533	.	5 g
CAN RTS-3a	Ore Tailings	9.59	(1.1)	5.12	0.04	2.14	0.2353	20.49	.	2.483	0.0209	18.28	0.2890	(10.6)	100 g

continued analysis listed in mass %

Number	C	Cd	Co	K	Mn	Na	Ni	P	Sb	Sn	Ti
NCS DC71307	.	0.000071	(0.00039)	.	0.00289	.	0.00340	.	0.00011	(0.00027)	.
NCS DC71308	.	0.00202	0.00751	.	0.00475	.	0.00413	.	(0.00027)	(0.00058)	.
CAN HCC-1
NCS DC71310	.	0.15	0.0491	.	0.0169	.	0.00432	.	0.0249	(0.00032)	.
CAN WMS-1A	(0.1)	(0.00014)	(0.145)	(0.0991)	(0.0600)	(0.0329)	3.02	(0.018)	(0.000692)	(0.00023)	(0.0840)
CAN INM-1
NCS DC71309	.	0.00165	(0.00004)	0.43	0.11	.
CAN RTS-3a	(0.04)	0.000921	0.0143	0.460	0.1585	0.684	0.00613	0.0446	0.000283	.	0.351

continued analysis listed in mg/kg

Number	Ag	As	Au	Ba	Bi	Cr	Ga	Ge	In	Pd	Pt	Se	Sr	Te	Tl	Zr
NCS DC71307	0.59	(14.4)	.	.	2.9	.	0.44	(0.2)	.	.	.	5.8	.	0.95	.	.
NCS DC71308	846	(3.1)	.	.	16.1	.	(0.3)	.	(66.6)	.	.	48.3	.	10.4	.	.
CAN HCC-1
NCS DC71310	5.0	(3.3)	.	.	6.1	.	251	6.0	21.0	.	.	(3.0)	.	(0.3)	.	.
CAN WMS-1A	(3.7)	30.9	0.300	(70)	(1.2)	(68)	(4)	.	(0.2)	1.45	1.91	(87)	(31.3)	.	.	(20)
CAN INM-1
NCS DC71309	0.97%	5.3	.	.	1.4	.	(0.3)	1.47	0.29	(0.07)	0.65	.
CAN RTS-3a	11.1	18.2	0.561	106	31.3	176	(30)	.	(1.6)	(0.004)	.	44.8	44.7	(2.0)	(3)	78

CRM SULPHUR ORE

analysis listed in mass %

Number	Al ₂ O ₃	BaO	CaO	Cu	T.Fe	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	Zn	LOI	Units
UNS MII	10.63	0.049	0.49	0.21	6.79	2.22	2.06	0.11	0.93	(12)	(7)	(16)	0.50	1.79	(10)	100 g

continued analysis listed in mg/kg

Number	Ag	As	B	Cd	Co	Cr	Cs	Eu	Ga	Hf	La	Mo	Ni
UNS MII	(0.012)	0.0901	(0.005)	0.0767	0.0223	(0.012)	(0.003)	(0.003)	(0.008)	(0.003)	(0.003)	(0.003)	0.0329

Number	Pb	Rb	Sb	Sc	Sr	Ta	Th	U	V	W	Y	Yb	Zr
UNS MII	0.868	(0.005)	(0.004)	(0.003)	0.0259	(0.003)	(0.006)	(0.004)	0.0845	(0.004)	(0.008)	(0.006)	(0.008)

CRM SULPHUR ORE

Number	S%	C%
GS908-4	30.08	.
GS914-3	29.86	0.38
GS314-1	29.11	1.41
GS399-10	28.22	.
GS310-2	27.59	.
GS315-7	26.90	0.36
GS900-2	26.62	.
GS300-5	26.54	.
GS310-1	26.44	.
GS301-2	25.86	.
GS316-8	25.59	0.07
GS300-7	24.85	.
GS317-4	24.43	0.25
GS307-8	23.98	.
GS916-8	23.76	0.60
GS917-6	21.99	0.41
GS904-2	21.73	.
GS916-6	19.20	0.48
GS317-2	18.66	0.48
GS303-2	18.51	.
GS316-7	18.13	0.41
GS916-7	17.67	0.52
GS317-3	16.76	0.67
GS317-5	15.53	8.46
GS917-7	14.79	5.15
GS916-9	14.55	0.60
GS910-1	12.96	.
GS912-8	11.63	2.91
GS904-4	11.12	.
GS913-3	10.95	0.03
GS310-7	10.92	.
GS312-7	10.53	2.63
GS916-4	9.95	0.86
GS309-3	9.80	.
GS312-6	9.80	3.10
GS315-10	8.40	0.16
GS910-4	8.27	.
GS913-1	7.90	0.06
GS314-8	7.82	0.26
GS907-4	7.68	.
GS908-7	7.55	.
GS917-1	7.33	0.47
GS913-5	7.30	0.03
GS913-6	7.22	0.04
GS913-7	7.18	0.04
GS307-7	7.04	.
GS915-10	6.90	0.13
GS302-6	6.75	2.84
GS913-4	6.58	0.04
GS913-8	6.56	0.04
GS314-10	6.50	0.37
GS914-6	6.35	1.18
GS301-1	6.13	.
GS310-8	5.91	.
GS907-6	5.77	.
GS905-3	5.64	.
GS913-2	5.49	0.06
GS914-4	5.44	1.00
GS315-6	5.35	0.26
GS300-2	5.16	.
GS315-2	4.91	0.18
GS314-4	4.87	0.24
GS311-7	4.43	.
GS905-8	4.38	.
GS915-5	3.88	0.12
GS902-3	3.84	.
GS912-7	3.52	0.09
GS314-3	3.37	0.36
GS914-7	3.34	0.04
GS901-1	3.20	.
GS310-3	3.30	.
GS917-2	3.09	0.40
GS916-10	2.90	0.03
GS311-2	2.88	.
GS907-7	2.82	.
GS310-6	2.64	.
GS314-2	2.56	5.15
GS903-3	2.54	.
GS311-1	2.35	.
GS902-7	2.32	.

Number	S%	C%
--------	----	----

CRM SULPHUR ORE

Number	S%	C%
GS914-9	2.29	0.57
GS399-5	2.29	.
GS305-1	2.20	.
GS310-5	2.20	.
GS916-3	2.17	0.26
GS915-1	2.06	0.08
GS916-5	2.05	0.07
GS302-5	1.98	.
GS311-9	1.98	.
GS302-9	1.94	.
GS313-9	1.89	0.08
GS911-8	1.76	.
GS997-10	1.74	.
GS305-6	1.71	.
GS901-8	1.65	.
GS910-6	1.50	.
GS300-4	1.43	.
GS305-5	1.41	.
GS305-7	1.41	.
GS313-8	1.24	0.94
GS916-1	1.18	0.59
GS310-4	1.17	.
GS311-3	1.12	.
GS398-2	1.10	.
GS914-5	1.08	1.39
GS915-7	1.07	0.16
GS312-4	1.05	0.04
GS315-9	0.94	0.34
GS900-3	0.92	.
GS910-3	0.92	.
GS910-7	0.86	.
GS313-7	0.78	0.74
GS305-2	0.76	.
GS312-8	0.75	0.03
GS900-4	0.71	.
GS302-3	0.68	.
GS906-9	0.68	.
GS312-1	0.67	0.05
GS314-9	0.64	1.13
GS903-1	0.63	.
GS910-9	0.63	.
GS309-1	0.61	.
GS303-7	0.59	.
GS316-4	0.58	0.09
GS916-2	0.56	0.17
GS314-6	0.56	0.15
GS316-2	0.56	0.08
GS311-4	0.54	.
GS917-5	0.53	0.30
GS912-3	0.52	0.07
GS305-10	0.51	.
GS312-3	0.47	0.06
GS301-6	0.40	.
GS300-8	0.37	.
GS917-4	0.36	0.05
GS316-1	0.36	0.04
GS316-3	0.34	0.06
GS303-9	0.31	.
GS312-5	0.28	0.88
GS915-2	0.28	0.13
GS303-10	0.27	.
GS310-10	0.27	.
GS914-2	0.26	0.06
GS313-3	0.25	0.13
GS315-8	0.25	0.19
GS914-10	0.24	0.21
GS903-6	0.23	.
GS317-1	0.21	0.15
GS906-6	0.21	.
GS312-9	0.21	0.03
GS915-3	0.19	0.11
GS914-1	0.18	0.04
GS906-5	0.18	.
GS398-6	0.16	.
GS915-8	0.13	0.07
GS915-9	0.12	0.04
GS917-8	0.11	5.78
GS314-5	0.11	0.08
GS912-1	0.09	0.03
GS917-9	0.09	5.56

Number	S%	C%
--------	----	----

CRM SULPHUR ORE

Number	S%	C%
GS915-6	0.09	0.04
GS316-9	0.08	0.06
GS316-10	0.08	0.03
GS311-5	0.07	.
GS317-8	0.06	0.04
GS912-2	0.06	0.03
GS307-2	0.06	.
GS316-5	0.05	0.46
GS316-6	0.05	0.45
GS912-10	0.05	0.11
GS912-6	0.05	0.06
GS317-6	0.05	0.05
GS915-4	0.05	0.03
GS313-1	0.05	0.03
GS910-5	0.05	.
GS911-5	0.05	.
GS911-9	0.05	.
GS315-4	0.04	0.11
GS912-9	0.04	0.12
GS314-7	0.04	0.09
GS313-10	0.04	0.06
GS917-3	0.04	0.05
GS315-3	0.04	0.04
GS317-10	0.04	0.04
GS312-10	0.04	0.03
GS312-2	0.04	0.22
GS910-2	0.04	.
GS313-4	0.03	0.26
GS313-5	0.03	0.25
GS313-6	0.03	0.12
GS912-5	0.03	0.10
GS313-2	0.03	0.03

Number	S%	C%
--------	----	----

for all GS Sulfur Ore samples,
unit size is 10 g powder

CRM SYENITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %		* Provisional Analysis ⁸⁷ Sr/ ⁸⁶ Sr ratio: 0.70375														GBW, US: 50 g		all others: 100 g units	
Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	Cl	F	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI	
US STM-2 *	60.98	18.4	.	1.09	(0.0570)	.	(2.08)	.	5.39	T.Fe:3.77	4.07	0.12	Mn:0.1640	8.90	0.17	.	0.16	.	
JSy-1	60.02	23.17	.	0.25	0.084	.	4.82	0.016	0.0024	10.74	
VS 6104-91	57.86	16.68	(0.20)	6.94	.	0.082	2.51	.	5.41	(-0.05, +0.28)	4.77	1.25	0.14	4.51	0.39	(0.017)	0.78	(0.38)	
GBW 07109	54.48	17.72	0.26	1.39	0.059	0.048	1.23	6.04	.	2.38	7.48	0.65	0.12	7.16	0.018	0.011	0.48	.	
CGL 015	52.20	24.59	.	1.98	.	(0.10)	2.60	.	4.67	(-0.104, +0.58)	4.44	0.37	(0.100)	9.76	0.139	.	0.37	1.05	

continued analysis listed in mg/kg except % which is mass %

Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Ge
US STM-2 *	(1.2)	.	(5.4)	639	9.7	.	.	.	256	.	.	1.52	.	(8.01)	(4.4)	3.45	34	(8)	.
JSy-1	.	.	.	15.7	2.6	.	2.0	0.69	1.3	0.37	0.30	0.16	23.5	7.0	0.95
VS 6104-91	(0.03)	(12)	(7)	0.69%	1.9	.	.	.	219	8	16	(1)	5	(6.9)	(2.5)	4.5	17	(10)	(1.2)
GBW 07109	.	6.27	31.8	251	17.2	0.37	1.21	0.07	242	4.59	3.6	2.05	11.8	4.70	2.48	2.35	35.8	.	.
CGL 015	.	.	.	1305	(1.86)	.	.	.	58.24	(5.33)	25.6	(1.31)	6.40	(4.49)	(2.69)	(1.36)	22.63	(4.75)	.

Number	Hf	Hg	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc
US STM-2 *	27	.	(1.55)	.	.	154	36	0.60	6.2	267	81	(4.8)	12	25	114	.	.
JSy-1	1.2	.	0.094	.	.	1.2	.	0.076	.	0.51	1.2	1.1	4.9	0.32	66.3	0.15	.
VS 6104-91	5	.	(1)	.	.	108	10.5	0.33	1.1	20	102	8.4	21	(23)	56	.	4
GBW 07109	34.0	0.005	0.96	0.14	0.15	149	32.9	0.43	0.26	66.9	65.1	1.75	196	22.5	130	0.15	2.22
CGL 015	(3.15)	.	(0.93)	.	.	27.48	64.95	(0.42)	(1.51)	22.63	27.34	(3.4)	7.00	(6.99)	85.36	(0.14)	2.76

Number	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
US STM-2 *	.	12.0	(6.6)	782	16	(1.38)	.	27	.	0.55	(7.6)	(5.5)	(2.2)	43	4.2	223	1280
JSy-1	.	0.27	0.17	19.3	.	.	0.23	.	0.053	0.20	2.1	.	.	2.6	0.41	3.2	70.2
VS 6104-91	.	16	(1.9)	0.52%	(1.8)	(1.7)	.	(12)	.	(0.45)	(2)	79	.	25	2.3	109	185
GBW 07109	0.05	9.7	6.50	1160	1.96	1.02	0.012	79.3	0.76	0.46	14.6	179	1.24	24.7	2.56	112	1540
CGL 015	.	(5.09)	.	312	(1.21)	(0.76)	.	(4.63)	(0.32)	(0.4)	(1.59)	(5.8)	(4.36)	25.32	2.66	75.42	157

NEPHELINE SYENITE

= class, where 1 = CRM and 2 = RM analysis listed in mass % GBW: 50 g units all others: 100 g units

#	Number	SiO ₂	Al ₂ O ₃	Ba	CO ₂	CaO	FeO	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	Sr	TiO ₂	LOI
1	GBW 03124	60.64	20.05	.	.	0.52	0.28	1.37	2.34+	5.06	0.13	0.050	8.97	0.020	(0.011)	.	0.12	2.37
2	BCS 201a	57.3	23.54	.	.	1.07	.	0.12	.	8.90	0.025	.	7.53	0.025	.	.	0.05	0.76
1	USZ 45-2007	51.88	22.58	0.0447	(1.16)	2.28	0.80	2.63	.	9.10	0.24	0.14	6.78	0.04	.	0.01740	0.37	3.35
1	VS 728-75	40.18	28.5	.	1.6	7.13	(1.43)	3.25T	(1.9+)	(3.3)	1.01	(0.04)	12.2	0.51	0.084	.	0.24	.
1	GBW 03125	39.42	29.67	.	2.97	5.98	1.24	0.33	1.78+	4.72	0.92	0.031	12.59	0.072	(0.064)	.	0.14	.

continued analysis in mg/kg except % which is mass %

Number	As	Ce	Cr	Cu	F%	Ga	La%	Li	Nb%	Pb	Rb%	Th	U	V	Y	Zn%	Zr%
GBW 03124
BCS 201a
USZ 45-2007	23.8	30.8	44	(2.6)	(0.26)	23	0.0163	54	0.0040	114	0.0207	61.6	12.4	30	23	0.0098	0.0600
VS 728-75	Fe ₂ O ₃ : (1.66%)	.	.	InsRes: (3.5%)	.
GBW 03125	2.3

TITANIUM ORE

analysis listed in mass %

#	Number	Ilmenite	TiO ₂	Al ₂ O ₃	C	CaO	Co	Cr	Cr ₂ O ₃	Fe	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O
2	OSO Ki-370-99	95.41
1	NCS HC26619	.	98.21	0.65	0.011	0.006
1	DSZU 123.22-95	.	65.33	3.17	.	0.51	.	.	1.32	16.10	.	.	.	0.53	0.92	.
1	DSZU 123.21-95	.	59.48	1.02	.	0.40	.	.	0.15	26.76	.	.	.	0.38	0.51	.
1	VS R31	.	56.5	1.99	2.59	24.4
1	NCS DC28139	.	55.68	2.30	.	0.070	0.0026	.	2.80	22.04	9.15	.	.	1.09	1.26	.
1	NCS DC26705	.	51.35	0.75	0.043	0.16	.	(0.07)	31.40	23.81	.	.	.	0.84	0.90	.
1	NCS DC28142	.	50.06	1.30	.	0.68	0.011	.	0.84	30.23	28.85	.	.	1.52	0.875	.
1	NCS DC19019	.	49.78	0.53	.	0.028	.	.	0.054	34.56	25.05	.	.	0.32	1.55	.
1	NCS DC28138	.	47.82	0.68	.	0.68	0.0087	.	0.014	34.79	39.14	.	.	2.11	0.652	.
1	NCS DC28140	.	45.73	0.95	.	2.23	0.051	.	0.012	33.02	36.68	.	.	1.68	0.882	.
1	NCS DC19017	.	45.71	1.64	.	1.75	.	.	0.014	29.12	32.56	.	.	5.18	0.709	.
1	NCS DC28141	.	45.61	0.867	.	1.65	0.0098	.	0.0067	33.58	37.51	.	.	1.74	0.799	.
1	AMIS 0454 *	Ti: 26.78	44.45	0.731	.	0.216	.	(0.0713)	(0.114)	see below	52.53	(0.045)	.	0.74	1.19	(0.03)
1	NCS DC28137	.	40.66	1.35	.	4.78	0.010	.	0.0064	30.31	33.33	.	.	1.30	1.20	.
1	NCS DC28143	.	35.60	1.65	.	6.25	0.013	.	0.0077	29.29	29.34	.	.	1.55	1.02	.
1	NCS DC19018	.	33.94	4.47	.	3.14	.	.	0.0085	27.30	29.70	.	.	6.88	0.524	.
1	NCS DC28136	.	27.23	2.31	.	9.49	0.015	.	0.0078	26.50	23.62	.	.	2.34	0.802	.
1	CGL 129	17025	14.88	9.79	.	1.16	0.0209	0.3068	.	61.86	.	61.86T	0.137	3.05	0.240	(0.086)
1	NCS DC28134	.	7.11	8.67	.	12.39	0.0052	.	0.0084	14.85	12.45	.	.	6.33	0.216	.
1	NCS DC28135	.	6.14	8.82	.	9.87	0.0079	.	0.0095	15.07	12.77	.	.	6.78	0.187	.

Number	Ni	P	P ₂ O ₅	S	SiO ₂	Sr	V	V ₂ O ₅	Zn	Zr	LOI	Units
OSO Ki-370-99	1 kg of ~3mm material
NCS HC26619	.	.	.	0.006	20 g
DSZU 123.22-95	.	.	0.15	0.0090	1.45	.	.	0.18	.	.	.	100 g
DSZU 123.21-95	.	.	0.24	0.96	3.00	.	.	0.26	.	.	.	100 g
VS R31	.	.	0.25	1.24	100 g
NCS DC28139	0.0007	0.047	.	0.025	1.54	.	.	0.266	0.017	.	Cu:0.0093	50 g
NCS DC26705	.	0.045	.	0.004	1.98	.	.	0.22	.	.	.	40 g
NCS DC28142	0.0021	0.048	.	0.172	2.04	.	.	0.700	0.017	.	Cu:0.0073	50 g
NCS DC19019	.	0.0048	.	0.010	0.578	.	.	0.137	.	.	.	100 g
NCS DC28138	0.0029	0.0076	.	0.184	2.65	.	.	0.095	0.016	.	Cu:0.0056	50 g
NCS DC28140	0.0051	0.048	.	0.74	4.85	.	.	0.203	0.016	.	Cu:0.013	50 g
NCS DC19017	.	0.117	.	0.0080	5.99	.	.	0.090	.	.	.	100 g
NCS DC28141	0.0046	0.047	.	0.536	4.16	.	.	0.188	0.015	.	Cu:0.011	50 g
AMIS 0454 *	.	.	(0.030)	.	2.23	.	.	(0.24)	ZrO ₂ : (0.12)	Nb: (0.0576)	.	100 g
NCS DC28137	0.0084	0.117	.	1.52	9.21	.	.	0.068	0.014	.	Cu:0.022	50 g
NCS DC28143	0.011	0.476	.	2.76	10.41	.	.	0.505	0.016	.	Cu:0.027	50 g
NCS DC19018	.	0.558	.	0.028	11.73	.	.	0.101	.	.	.	100 g
NCS DC28136	0.013	1.07	.	4.77	14.41	.	.	0.066	0.015	.	Cu:0.038	50 g
CGL 129	0.0306	.	0.022	.	7.77	0.0152	0.02818	.	0.0575	0.00354	(-0.25)	100 g (last) or 150 g
NCS DC28134	0.0037	0.883	.	0.196	38.43	.	.	0.062	0.019	.	Cu:0.0082	50 g
NCS DC28135	0.0098	0.232	.	0.021	42.61	.	.	0.092	0.018	.	Cu:0.016	50 g

* AMIS 0454 certifies Fe by XRF 36.50%, Titration 37.14%, and M/ICP 36.37%.

Special Note: more Titanium Powders are in our "Other Chips & Powders Catalog."

RM ILMENITE typical analysis listed in mass % 100 g

Number	TiO ₂	Al ₂ O ₃	C	CaO	Co ₃ O ₄	Cr ₂ O ₃	CuO	Fe	K ₂ O	MgO	Mn	NiO	P ₂ O ₃	S	SiO ₂	SrO	V ₂ O ₅	ZnO	ZrO ₂
DH 6706	32.37	4.46	0.044	1.179	0.024	0.143	0.017	36.83	0.118	2.82	0.094	0.049	0.017	0.288	7.31	0.016	0.285	0.020	0.044

CRM TITANIUM ORE - ILMENITE WITH EXTENSIVE ANALYSIS 80 g units

Number	TiO ₂	Al ₂ O ₃	CaO	CO ₂	Fe	FeO	K ₂ O	MgO	MnO	Na ₂ O	P	S	SiO ₂	Sr	V	Zn	Zr
NCS DC87109	19.83	2.21	6.69	0.15	37.87	24.88	0.17	2.88	0.62	0.39	0.25	0.053	14.22	0.0308	0.1326	0.0162	0.0240
NCS DC87110	16.13	3.68	10.32	0.32	27.10	20.53	0.21	5.78	0.53	0.49	0.26	0.15	24.02	0.0340	0.0902	0.0212	0.0266
NCS DC87108	12.91	6.73	0.98	1.25	51.36	29.65	0.03	3.05	0.24	0.063	0.043	0.28	2.57	0.0470	0.000033	0.0493	0.00168
NCS DC87106	8.96	5.19	13.86	0.50	19.23	15.60	0.23	8.79	0.32	0.54	0.22	0.25	33.46	0.0334	0.0681	0.0267	0.0274
NCS DC87107	2.95	4.23	3.86	0.15	18.88	11.17	0.021	19.40	0.28	0.12	0.089	0.012	37.85	0.00535	0.0303	0.0390	0.0147

Number	As	Ba	Cd	Ce	Co	Cr	Cu	Dy	Er	Eu	Ga	Gd	Ho	La	Li
NCS DC87109	0.52	58.1	0.063	87.8	55.5	82.1	40.5	7.05	2.28	4.14	31.8	11.2	1.04	32.6	4.89
NCS DC87110	0.54	63.3	0.075	85.2	68.1	58.2	49.6	7.14	2.32	4.10	29.0	11.4	1.07	32.8	8.63
NCS DC87108	1.90	38.5	0.050	3.39	236	(0.42)	170	0.28	0.14	0.17	55.4	0.42	0.051	1.34	0.95
NCS DC87106	0.61	71.0	0.072	72.1	84.4	47.4	70.1	6.49	2.18	3.65	30.3	9.91	0.97	28.2	12.7
NCS DC87107	2.16	15.0	0.33	12.9	104	916	213	3.26	1.22	1.01	17.9	3.75	0.53	3.71	1.68

Number	Lu	Nb	Nd	Ni	Pb	Pr	Rb	Sm	Tb	Th	Tm	U	Y	Yb
NCS DC87109	0.16	49.1	66.3	52.6	6.70	13.7	4.92	14.4	1.56	2.30	0.26	0.63	22.8	1.32
NCS DC87110	0.17	44.2	64.3	68.9	6.72	13.3	6.38	14.4	1.62	2.27	0.28	0.64	23.3	1.37
NCS DC87108	0.019	4.25	2.26	611	7.58	0.46	0.35	0.44	0.056	0.10	0.022	0.029	1.52	0.12
NCS DC87106	0.16	30.0	54.6	91.2	6.85	11.1	7.28	12.5	1.43	2.06	0.24	0.61	21.5	1.28
NCS DC87107	0.11	14.5	14.8	700	371	2.60	0.65	4.51	0.62	2.50	0.16	0.67	12.3	0.85

CRM TUNGSTEN ORE

analysis listed in mass % except * which is mg/kg																CAN: 200 g	GW: 10 g	IGS: 65 g	all others: 100 g
Number	W	WO ₃	Ag*	As	Be	Bi	Cu	Fe	Ge*	Mo	Nb	P	Pb	S	Sn	Zn			
VS 1710-79	.	71.96	.	.	.	0.146			
SRM 2430	.	70.26	.	0.002	.	0.078	.	.	.	0.22	.	0.017	.	0.26	.	.			
SRM 277	.	67.50			
CAN CT-1	1.04			
CAN BH-1	0.422			
KZ 7027-93	0.17	0.015	.	.	.	0.0093	0.0014	Zr:0.013			
GW-03	0.1744			
GW-02	0.1231			
KZ 7026-93	0.11	1.2	.	.	0.0022	0.018	0.052	.	3.6	0.00098	0.0015	.	.	Sr:0.017	.	.			
CAN TLG-1	0.083			
IGS 27	0.036	1.76	.	0.29	last of stock			
VS 1712-79	.	6.00	150.3	.	0.021	1.30	0.077	.	3.9	0.26	.	.	0.77	.	0.89	0.28			
VS 1714-79	.	1.04	10.3	.	.	0.089	.	.	.	0.041	0.113	.			
VS 1715-79	.	0.60	.	.	0.013	0.054	0.020	.	3.1	0.026	.	.	0.049	.	0.068	0.038			
VS 2040-81	.	0.49	.	.	.	0.0058	0.053	0.94	.	0.016			
VS 2042-81	.	0.38	.	.	.	0.0032	0.105	4.17	.	0.039			
VS 2039-81	.	0.22	.	.	.	0.023	0.27	2.47	.	0.0026			
VS 1713-79	.	0.17	5.5	.	0.0058	0.015	.	.	2.9	0.011	0.028	.			
VS 2041-81	.	0.076	.	.	.	0.0058	0.053	0.94	.	0.016			
VS 1711-79	.	0.036	.	.	0.0022	0.0044	.	.	.	0.0026	0.0071	.			

CRM TUNGSTEN ORE

analysis listed in mass %																T = Total				GBW: 50 g	USZ: 100 g units
Number	WO ₃	Al ₂ O ₃	As	Bi	CaO	Cy	F	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Mo	Na ₂ O	Pb	Rb	S	SiO ₂			
USZ 26-99	0.41	14.14	0.09	0.0067	1.95	.	.	3.72	5.59T	4.32	2.04	0.12	0.079	2.13	0.0076	0.106	.	64.87			
GBW 07241	.	11.15	.	0.068	4.17	0.096	4.84	.	5.60	1.58	0.14	0.090	0.098	0.12	.	(0.05)	1.90	71.27			
GBW 07240	.	8.24	0.18	0.011	37.73	0.79	9.91	.	7.79	1.94	1.45	0.97	.	0.16	0.26	(0.08)	3.12	13.27			
analysis listed in mass %			analysis listed in mg/kg except % which is mass %																		
Number	Sn	TiO ₂	Zn	Ag	As	Cd	Ce	Co	Cu%	Dy	Eu	Er	Ga	Gd	Ge	Ho	In	La			
USZ 26-99	(0.016)	0.82	0.017	11	0.022			
GBW 07241	0.17	0.044	0.010	1.8	69.6	0.94	60.3	.	.	20.7	0.17	13.1	16.5	14.8	11.2	4.5	1.3	1.8			
GBW 07240	0.14	0.079	0.29	8.3	.	26.1	10.0	.	.	0.46	0.15	0.23	17.8	0.64	2.5	0.11	8.7	5.0			
analysis listed in mg/kg except % which is mass %																					
Number	Lu	Mo	Nd	Ni	Pb	Pr	Sb	Sc	Se	Sm	Sr	Tb	Te	Th	Tl	Tm	Y	V%	Yb	Zr%	
USZ 26-99	.	.	35	.	.	(20)	78	0.010	.	0.017	
GBW 07241	2.4	.	32.9	2.8	81.2	7.9	3.1	5.4	0.96	12.5	.	3.3	2.9	28.3	1.8	2.2	128	.	14.9	.	
GBW 07240	0.06	4.2	4.0	4.1	.	1.1	5.1	1.8	0.39	0.79	.	0.15	0.66	2.2	5.0	0.04	2.8	.	0.28	.	

CRM TUNGSTEN ORE

analysis in mass % except * is mg/kg											more information on certificates				10g, 60g, 500g, or 1 kg units					
Number	W	WO ₃	Au*	Cu	Fe	FeO	Fe ₃ O ₄	Mo	SiO ₂	Sn	Mass Recovered									
OREAS 701	2.43	3.07	1.11	0.491	23.98	17.35	17.95	0.0254	33.95	0.0197	20.80									
OREAS 700	1.13	1.42	0.506	0.202	16.06	12.07	10.91	0.0081	47.30	0.0182	11.28									

RM TUNGSTEN ORE

analysis listed in mass %																10 x 100 g units		
Number	W	Ag	Al ₂ O ₃	Bi	C	CaO	Cu	Fe ₂ O ₃	K ₂ O	MgO	Mo	Na ₂ O	S	SiO ₂	TiO ₂	LOI		
CDN W-2	2.78	.	(3.1)	0.32	.	(10.1)	0.45	(43.4)	(1.0)	(5.2)	.	(0.8)	.	(27.9)	(0.1)	(5.7)		
CDN W-3	1.73	.	(2.4)	0.2142	.	(8.4)	0.44	(49.5)	(0.6)	(3.9)	.	(0.8)	.	(25.3)	(0.1)	(6.5)		
CDN W-5	0.391	.	(12.7)	.	(0.2)	(28.9)	.	(11.9)	(0.1)	(1.0)	.	(0.1)	.	(41.6)	(0.1)	(0.9)		
CDN W-4	0.366	(0.319)	(12.7)	.	.	(3.8)	0.139	(13.7)	(2.4)	(2.3)	0.110	(2.0)	(0.3)	(56.2)	(0.5)	(4.5)		

CRM ULTRAMAFIC ROCK

certified soluble analysis in mass %				informational analysis							last of stock							100 g
Number	Co	Cu	Ni	Al ₂ O ₃	CaO	CO ₂	Cr ₂ O ₃	FeO	H ₂ O	La	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	ZnO
CAN UM-4	0.007	0.054	0.19	8.98	6.27	0.26	2.59	12.8	4.86	0.18	22.5	0.15	0.45	0.007	0.44	39.35	0.35	0.008

RM ULTRAMAFIC ROCK - KOMATIITE * provisional analysis listed in mass % 100 g

Number	Al ₂ O ₃	CaO	FeO	T.Fe ₂ O ₃	H ₂ O-	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI
IAG OKUM *	7.973	7.859	8.10	11.81	0.140	5.75	0.045	21.27	0.181	1.140	0.027	44.113	0.381	4.60

* provisional analysis listed in mg/kg except % which is mass %

Number	As	Ba	Be	Ce	Co	Cr%	Cs	Cu	Dy	Er	Eu	Ga	Gd	Hf	Ho
IAG OKUM *	0.465	6.38	0.066	1.271	89.0	0.2461	0.184	43.0	1.609	1.042	0.303	8.81	1.141	0.548	0.355

Number	La	Li	Lu	Nb	Nd	Ni%	Pb	Pr	Rb	Sb	Sc	Sm	Sn	Sr
IAG OKUM *	0.415	4.38	0.149	0.346	1.49	0.0884	0.265	0.239	0.96	0.077	28.0	0.712	0.25	16.1

Number	Ta	Tb	Th	Tl	Tm	U	V	Y	Yb	Zn	Zr
IAG OKUM *	0.026	0.225	0.031	0.015	0.154	0.014	167	9.27	1.02	61.2	17.4

CRM URANIUM ORE

analysis listed in mass % powder 10 g

Number	U	Cu	Fe
GU-10	0.1876	.	.
GU-09	0.1134	.	.
GU-08	0.03124	.	.
GU-07	0.02429	.	.
GU-11	0.003467	.	.
GU-03	0.00048	0.00210	3.5
GU-04	0.00042	.	.
GU-06	0.000382	.	.
GU-05	0.000356	.	.

CRM URTITE

analysis listed in mass %

40 g units

Number	SiO ₂	TiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MnO	MgO	CaO	Na ₂ O	K ₂ O	FeO	P ₂ O ₅	Ba	Sr
VS 2123-81	42.80	1.79	26.47	2.67	0.084	0.14	3.73	13.33	5.16	1.40	0.388	0.035	0.100

continued analysis listed in mg/kg

Number	Be	Co	Cr	Cu	Ga	La	Li	Mo	Nb	Ni	Pb	Rb	Sn	V	Y	Yb	Zn	Zr
VS 2123-81	5.1	8.1	9.7	24	48	100	8.9	2.3	97	6.5	5.8	79	3.4	86	26	1.7	44	220

RM VOLCANIC TUFF WITH EXTENSIVE ANALYSIS

analysis listed in mass %

~35 g units

Number	Al ₂ O ₃	Ba	CaO	FeO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	Sr	TiO ₂	V	LOI
IAG OU-1	15.136	0.01314	6.488	4.995	8.987	0.215	4.727	0.129	2.463	0.050	58.247	0.010476	0.440	0.022223	3.058

continued analysis listed in mg/kg

Number	As	Be	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Hf	Ho	La	Li
IAG OU-1	8.221	0.43	0.17	12.49	24.41	27.65	0.14	61.55	3.40	2.40	0.52	13.63	2.78	1.65	0.80	5.60	20.35

Number	Lu	Nb	Nd	Ni	Rb	Sb	Sc	Sm	Ta	Tb	Th	Tm	U	Y	Yb	Zn	Zr
IAG OU-1	0.39	2.3	7.32	13.00	2.05	0.22	32.69	2.13	0.15	0.49	1.68	0.37	0.40	21.63	2.49	74.40	55.00

CRM WOLLASTONITE

analysis listed in mass %											50 g units		
Number	Al ₂ O ₃	CaO	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	LOI
GBW 03123	0.39	40.39	0.28	0.10	0.14	0.95	0.096	0.052	0.052	(0.010)	50.50	0.022	6.93

CRM ZEOLITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %															T = Total		
Number	Al ₂ O ₃	Ba	CaO	Fe ₂ O ₃	H ₂ O-	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Rb	SiO ₂	Sr	TiO ₂	Zr	LOI	Units
FLX CRM104	33.74	.	0.063	0.014	.	0.075	.	.	20.06	.	.	45.98	.	.	.	22.64	35 g
USZ 49-2009	12.98	0.0371	1.34	1.27T	.	3.19	0.573	0.033	3.44	0.032	0.0106	67.44	0.0635	0.158	0.0177	8.80	70 g
CGL 017	12.91	0.0383	1.30	0.802T	(4.17)	3.21	(0.55)	0.007	3.35	0.030	0.0107	67.64	0.0651	0.161	(0.0179)	(9.77)	70 g

continued analysis listed in mg/kg

Number	As	Be	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Hf	Hg	Ho
FLX CRM104
USZ 49-2009	60.5	(2.75)	(11.7)	(7.85)	74.8	20.3	12.7	4.73	79.3	(3.46)	(1.83)	(0.50)	13.8	(3.81)	(5.38)	(1.85)	(0.66)
CGL 017	(63)	(2.6)	.	.	(77)	(0.94)	(7.9)	.	(2.9)	(3.5)	(1.91)	(0.49)	14.84	(4.3)	(7.9)	.	(0.67)

Number	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Sb	Sc	Sm	Sn	Ta	Tb	Th	Tm
FLX CRM104
USZ 49-2009	37.2	(6.07)	(0.27)	(0.43)	14.1	27.3	14.6	84.2	(7.97)	(50.9)	3.27	(4.82)	(2.27)	(1.16)	(5.9)	17.2	(0.27)
CGL 017	(39.5)	(6.4)	(0.28)	.	14.17	(27.5)	(2.2)	21.78	(8.4)	.	(3.6)	(5.1)	(2.6)	(1.26)	(0.63)	(17.3)	(0.29)

Number	U	V	W	Y	Yb	Zn
FLX CRM104
USZ 49-2009	3.09	42.3	(1.52)	18.6	(1.81)	79.3
CGL 017	(3.1)	(11.1)	.	20.36	(1.8)	25.37

17025

CRM ZINC ORE

analysis listed in mass % except * which is mg/kg T = Total

Number	Zn	S	Al ₂ O ₃	Ca	CaO	Cd	Cu	Fe	Hg*	Mg	MgO	Ni	Pb	Sb	SiO ₂
CAN CZN-4	55.24	33.07	Al:0.0715	(0.0419)	.	0.2604	0.403	(9)	4.54	(0.0352)	.	(0.0016)	0.1861	(0.0010)	Si:0.295
IMN TC 9	53.4	0.52	.	.	6.96	0.0049	.	5.64	.	.	3.50	.	3.77	.	5.47
GBM310-14	17.9087	11.0	0.0114	0.0042	8.9774	.	.
GBM305-12	17.0581	0.0119	0.0042	0.4214	.
GBM310-16	17.0201	21.4	0.3459	0.0035	11.2603	.	.
GBM310-13	10.8471	5.9	0.0334	0.0072	2.1599	.	.
GBM907-13	6.6270	5.85	1.6853	0.0073	0.4102	.	.
IMN RG 8	5.4	0.57	0.9	.	26.45	0.047	.	6.34	.	.	12.16	.	0.84	.	2.64
GBM910-12	4.5469	16.7	0.1419	0.0026	2.2000	.	.
GBM909-12	4.0073	9.9	1.0830	0.0023	0.4191	.	.
GBM910-11	4.0055	12.9	0.1305	0.0020	1.3656	.	.
GBM907-14	3.1882	2.90	0.8167	0.0061	1.973	.	.
GBM311-11	3.1115	3.3	1.4504	0.0078	1.0730	.	.
IMN RB 7	3.07	(10.3)	.	.	24.35	0.033	.	8.28	.	.	15.26	.	(0.26)	.	(0.8)
GBM307-14	1.7179	23.59	0.7502	0.0054	0.0217	.	.
GBM906-14	1.5949	1.1758	0.0405	.	.
BCR 109	0.46	0.946	14.51	0.96	0.020	.	.	0.738	.	.

continued

Number	Ag*	As	Au*	Bi*	C	Cl	Co	F	In	Mn	PbO	Se*	Sn	ZnO	Units
CAN CZN-4	51.4	0.0356	(0.04)	(10)	(0.09)	(0.003)	0.00935	(0.004)	(0.020)	(0.009)	.	86.7	(0.05)	.	200 g
IMN TC 9	0.033	.	0.055	220 g
GBM310-14	59.6	250 g
GBM305-12	250 g
GBM310-16	314.3	250 g
GBM310-13	30.8	250 g
GBM907-13	250 g
IMN RG 8	(0.72)	.	.	(4.36)	130 g
GBM910-12	24.4	250 g
GBM909-12	51.7	250 g
GBM910-11	19.6	250 g
GBM907-14	250 g
GBM311-11	19.6	250 g
IMN RB 7	170 g
GBM307-14	250 g
GBM906-14	2.9	31	250 g
BCR 109	0.0081	200 g

CRM ZINC ORE WITH EXTENSIVE ANALYSIS

analysis listed in mass % T = Total * Provisional Analysis CGL: 200 g GBW: 50 g JZn-1: 100 g units

Number	Zn	Al ₂ O ₃	CaO	T.C	Cu	F	Fe ₂ O ₃	H ₂ O-	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Pb	S	SiO ₂	TiO ₂	LOI
CGL 207	49.14	0.112	0.850	.	0.1940	.	10.45T	.	.	.	(0.068)	6.20	(0.016)	(0.026)	0.3407	31.12	(1.73)	.	.
GBW 07237	2.75	2.80	1.91	.	0.71	1.20	3.50	.	0.99	0.082	0.026	0.56	.	0.25	0.25	2.87	82.95	0.017	.
JZn-1 *	2.22	6.32	18.1	(1.28)	(0.0029)	.	11.8	(0.61)	(1.71)	0.83	1.94	1.49	0.45	.	0.161	(1.30T)	(43.95)	0.20	(6.61)

continued analysis listed in mg/kg

Number	Ag	As	Ba	Be	Bi	Cd	Ce	Co	Cr	Cs	Dy	Eu	Er	Ga	Gd	Ge	Ho	In	La	Li		
CGL 207	33.43	167.7	(9.48)	(0.254)	309.6	910.5	(9.82)	424.4	(29.86)	(0.425)	.	.	.	(2.83)	.	(0.743)	.	152.9	(7.30)	.		
GBW 07237	13.5	12.4	.	.	56.4	29.3	2.3	.	(62)	.	0.49	0.06	0.28	8.0	0.31	1.4	0.13	0.23	1.3	(86)		
JZn-1 *	.	(99)	(208)	.	.	(114)	.	(24)	(21)	(19.5)	
Number	Lu	Mo	Nd	Ni	Pr	Rb	Sb	Sc	Se	Sm	Sn	Sr	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb
CGL 207	.	255.6	.	11.18	(0.938)	.	(3.24)	(5.65)	.	.	(0.450)	.	.	7.86	(1.52)	.	.	.
GBW 07237	0.08	2.8	0.92	5.5	0.30	(73)	1.1	0.33	2.3	0.36	6.1	.	0.10	0.17	(1.1)	0.49	0.05	.	.	3.4	4.5	0.42
JZn-1 *	.	.	.	(6)	.	(42)	(31)	(358)	(24)	.	.	.

CRM ZINC ORE - EXTENSIVE CERTIFIED ANALYSIS ON CERTIFICATES AVAILABLE ON REQUEST

analysis listed in mass % except * which is mg/kg

Number	Zn	Ag*	Au*	Cu	Pb	S	Units
OREAS 622	10.24	102	1.85	0.486	2.21	7.95	10 or 60 g
OREAS 621	5.22	69	1.25	0.363	1.36	4.54	10 or 60 g
OREAS 620	3.15	38.5	0.685	0.173	0.774	2.52	10 or 60 g
OREAS 624	2.40	45.3	1.16	3.10	0.624	13.29	10 or 60 g
OREAS 623	1.03	20.4	0.827	1.73	0.250	9.07	10 or 60 g

CRM ZIRCONIUM ORE

analysis listed in mass %

Number	ZrO ₂	Al ₂ O ₃	CaO	F	FeO	Fe ₂ O ₃ (T)	H ₂ O+	HfO ₂	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	RE _x O _y *	SiO ₂	TiO ₂	LOI
NCS DC86316	4.68	(14.57)	0.63	0.027(F-)	0.10	0.38	0.49	0.084	3.90	0.079	0.021	4.20	0.040	0.0515	70.73	0.64	0.56
NCS DC86308	1.25	14.70	2.64	0.082	1.82	4.69	1.29	0.025	3.31	2.01	0.083	3.74	0.167	0.022	65.66	0.410	1.51
NCS DC86307	0.187	14.74	2.70	0.080	1.83	4.80	1.35	0.00421	3.37	2.10	0.085	3.83	0.163	0.018	66.02	0.420	1.55

continued analysis listed in mg/kg

Number	CeO ₂	Dy ₂ O ₃	Er ₂ O ₃	Eu ₂ O ₃	Gd ₂ O ₃	Ho ₂ O ₃	La ₂ O ₃	Lu ₂ O ₃	Nd ₂ O ₃	Pr ₆ O ₁₁	Sc ₂ O ₃	Sm ₂ O ₃	Tb ₄ O ₇	Th	Tm ₂ O ₃	W	Y ₂ O ₃	Yb ₂ O ₃	Units
NCS DC86316	146	14.9	16.4	0.55	9.92	3.66	69.2	6.11	53.4	15.7	10.7	10.1	2.02	202	2.84	5.01	142	25.9	70 g
NCS DC86308	74.4	4.6	4.6	1.2	(4.1)	1.3	37.9	1.5	26.9	7.8	14.8	4.9	0.74	15.2	0.92	.	41.9	7.8	70 g
NCS DC86307	70.7	2.8	1.8	1.2	3.4	0.59	36.6	0.38	27.5	7.7	14.1	4.7	0.53	7.8	0.31	.	19.5	2.2	70 g

* RE_xO_y : Rare Earth Oxide**ZIRCONIUM MATERIALS**

CERAM: 25 or 100 g IGS: 50 g NCS: 20 g all others: 100 g units

Number	ZrO ₂	HfO ₂	ZrO ₂ + HfO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Other
CRM														
NCS HC26618	.	.	99.48	0.009	0.17	0.054	.	0.093	.	.	0.11	.	.	
BCS 358	92.70	1.63	.	0.08	1.50	0.065	.	3.42	.	.	0.21	0.20	0.08	BaO: 0.10 SrO: 0.07
VS K7/3	.	.	92.2	(0.1)	5.39	0.73	0.65	.	.	
VS K8/2	65.9	.	.	1.16	.	0.081	.	.	.	0.110	32.3	0.163	.	S: 0.0064
IGS 35	65.86	1.368	0.27	.	
BCS 388	(64.9)	1.28	66.2	0.291	.	0.049	.	.	.	0.122	32.7	0.232	.	ThO ₂ :0.019 U ₃ O ₈ :0.034 Y ₂ O ₃ : 0.136
SARM 13	64.01	1.29	.	0.61	(0.14)	0.187	.	(0.0440)	.	0.23	32.56	0.295	.	Th:2 (0.0300) ₃ U:(0.0328) ₂
RM														
CERAM 2CAS15	(63.6)	(1.28)	65.0	0.38	0.28	0.07	0.01	0.07	0.02	.	33.9	0.20	0.23	
CERAM AN46	15.41	0.32	15.68	30.52	0.20	0.85	1.03	5.34	0.15	.	45.46	0.48	0.08	Li ₂ O: 0.02
BCS 204A	.	.	53.8	0.74	0.15	0.18	0.017	0.012	0.014	0.77	37.6	2.22	0.50	SnO ₂ : 1.69