

INDEX

- ALLOY LISTING 43
ALLOY SPECIFICATIONS 45
ALLOYED CAST IRON 40
ALUMINUM IN STAINLESS STEEL 19
ALUMINUM IN STEEL 2, 6
ANTIMONY IN STEEL 5
ARSENIC IN STEEL 5
- BISMUTH STEEL 5, 8
BORON IN STAINLESS STEEL 19
BORON IN STEEL
- CALCIUM IN STAINLESS STEEL 19
CALCIUM IN STEEL 6
CARBON STEEL 2, 3, 4
CARBON STEEL SPECIFICATIONS 45
CAST IRON 32, 33, 34, 35, 37, 38, 39, 40, 41, 42
CAST IRON WITH MAGNESIUM 34, 35, 36
COBALT ALLOY 9
COBALT IN STAINLESS STEEL 21
COPPER IN STAINLESS STEEL 20
Cr-Mo STEEL 6, 7
- DUCTILE IRON 33
- EPMA SETS 6
- GRAY IRON 33
- HIGH ALLOY STEEL 31, 32
HIGH ALLOY STEEL SPECIFICATIONS 48
HIGH CHROMIUM CAST IRON 40
- IRON 2
- LEADED STEEL 8
LOW ALLOY STEEL
5, 6, 7, 8, 9, 10, 11, 12, 14, 15, 16
LOW ALLOY STEEL SPECIFICATIONS 46
LOW ALLOY STEEL WITH 0.13 % < C < 0.3 % 14
LOW ALLOY STEEL WITH C < 0.13 % 15
LOW ALLOY STEEL WITH C > 0.3% 11, 12
LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS
13
- MAGNETIC ALLOY 9
MANGANESE STAINLESS STEEL 22
MANGANESE STEEL 8
MARAGING STEEL 21
- NICKEL BINARY 22
NITROGEN IN STEEL 6
NODULAR IRON 33
- PERMENDUR 2V 9
PHOSPHORUS IN STAINLESS STEEL 23
- RESULFURIZED STAINLESS STEEL 23
RESULFURIZED STEEL 9
RESULFURIZED STEEL SPECIFICATIONS 45
- SELENIUM IN STAINLESS STEEL 23
SELENIUM STEEL 5
SET 2, 6, 8, 9, 16, 30, 32
Si-Mo CAST IRON 33
SILICON STEEL 10
SOLUBLE ALUMINUM 2
SOLUBLE BORON 2
STAINLESS STEEL
19, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31
STAINLESS STEEL SPECIFICATIONS 48
STAINLESS STEEL WITH C < 0.05 % 28, 29
STAINLESS STEEL WITH C > 0.05% 26, 27
STAINLESS STEEL WITH NI < 5.0 % 24, 25
SULFUR IN STAINLESS STEEL 23
- TOOL STEEL 16, 17, 18
TOOL STEEL SPECIFICATIONS 47
TUNGSTEN IN STAINLESS STEEL 21
- WHITE IRON 33
- XRF 2, 6, 8, 9, 16, 30, 32

CALCIUM IN STEEL

= Class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

Table with columns: #, Number, Ca, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Als, Co, Mo, N, V. Lists various steel grades like BS HiCal-1, SS 115, BS 9325A, etc.

Table with columns: Number, As, B, Bi, Nb, O, Pb, Sb, Sn, Ti, W, Zr, Other. Lists elements and their concentrations for various steel grades.

CRM Al, Ca, AND N IN LOW ALLOY STEEL

Table with columns: Number, Al, Ca, N, Units. Lists CRM grades like BS 9905, IMZ 133, etc.

C-Mo and Cr-Mo STEEL XRF SET

= class, where 1 = CRM ISO 17025 and 2 = RM, Set Part Number: BS MOLY-5 AVAILABLE INDIVIDUALLY ~7 mm discs

Table with columns: #, Grade, Alloy, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Al, Co, N, Sn, V. Lists C-Mo and Cr-Mo steel grades.

CRM EPMA SETS

available in sets only, as grouped 4x10x15mm

Table with columns: Number, Cr, Number, Ni. Lists CRM EPMA sets like NMIJ 1001-a, NMIJ 1002-a, etc.

LOW ALLOY STEEL WITH 0.13 % < C < 0.3 %

CONTINUED FROM THE PREVIOUS PAGE

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
IARM 330A	0.0003	0.0010	.	.	(0.003)	(0.0009)	(0.0004)	(0.001)	.	0.006	(0.004)	.	0.0015	31 mm Ø x 2 mm
SRM 1269	0.005	32 mm Ø x 19 mm
12X 352D	0.285	0.223	.	.	-40 mm Ø x -15 mm
ECRM 086-1D	38 mm Ø x 25 or 30 mm
12X 16604A *	-40 mm Ø x -15 mm
CZ CM-3A	0.0002	.	.	.	0.006	0.006	0.015	.	.	-39 mm Ø x 25 mm
VS UG9/10	0.163	1.34	.	.	-45 mm Ø x -28 mm
HRT FE2000-N	.	0.0015	0.025	.	.	40 mm Ø x 20 mm
VS RG27/1	0.110	0.170	.	.	-45 mm Ø x -28 mm
IMZ 178	0.105	0.017	.	.	40 mm Ø x 40 mm
SRM 1225	32 mm Ø x 19 mm
BS HiCal-1	(0.0001)	0.0140 [91.9]	(0.0003)	(0.002)	(0.002)	.	(0.0005)	.	.	0.0037	(0.0009)	.	(0.0008)	38 mm Ø x -30 mm 17025
IARM 380A	(0.0020)	(0.009)	.	.	31 mm Ø x 2 or 18 mm
RM Fe 2/4	(0.0027)	<0.001	.	.	(0.011)	.	<0.02	<0.03	.	(0.0065)	0.19	.	<0.02	40 mm Ø x 40 mm
BS 69B	(0.002)	.	.	.	38 mm Ø x ~7 or 19+ mm
12X 12750U	0.111	0.159	0.100	.	.	-40 mm Ø x -15 mm
12X 32550A	-38 mm Ø x -15 mm
IARM 195B	0.0039	0.0002	.	.	0.007	0.0017	0.002	0.011	.	0.002	0.38	.	0.002	31 mm Ø x 18 mm last
BS 6418	0.0012	.	.	.	0.003	.	.	.	57 mm Ø x ~7 or 19+ mm
IARM 380B	(0.0016)	0.0011	(0.003)	.	.	31 mm Ø x 2 or 18 mm
CKD 181B	0.0076	.	(95.37)	.	0.062	.	0.0005	0.017	0.042	0.155	0.188	.	0.001	44 mm Ø x 13 or 25 mm
IMZ 113	40 mm Ø x 40 mm
DSZU C043	(0.0005)	0.0005	.	.	0.004	0.046	0.082	.	.	40 mm Ø x 25 mm
12X 722M24A	0.0028	.	-38 mm Ø x -15 mm
VS UG6/5	(0.01)	(0.01)	0.16	.	.	-45 mm Ø x -28 mm
IARM 229B	(0.0006)	(0.0003)	.	.	(0.0019)	(0.0017)	(0.0005)	(0.0006)	(0.003)	0.0019	(0.003)	.	(0.0008)	31 mm Ø x 2 or 18 mm
ECRM 197-1D	0.0005	.	.	.	38 mm Ø x 25 mm
BS 3961	<(0.003)	.	.	.	44 mm Ø x ~7 or 19+ mm
TL 1668	(0.00024)	0.0019	.	(0.0003)	(0.0002)	.	(0.0007)	(0.0003)	.	0.0032	.	0.0008	(0.0003)	37 mm Ø x 25 mm
IPT 502	0.0016	.	.	.	36 mm Ø x 20 mm
BS 8620E	(0.0003)	0.0010	97.2	(0.0003)	(0.002)	0.0016	(0.0008)	0.0015	(0.0004)	0.0016	0.0008	17025	(0.0008)	38 mm Ø x ~7 or 19+ mm
BS 8620F *	.	* Provisional Analysis	<0.0005	<0.05	<0.05	<0.005	<0.005	.	.	<0.05	<0.05	.	<0.005	38 mm Ø x ~7 or 19+ mm
IARM 33D	0.0002	(0.0003)	.	.	0.002	0.0013	<0.001	(0.002)	.	0.003	<0.005	.	<0.002	31 mm Ø x 2 or 18 mm
BS 3952	39 mm Ø x ~7 or 19+ mm
ECRM 187-2D	0.00048	39 mm Ø x 28 mm
BS 9325A	(0.0001)	0.0039	92.8	(0.0002)	0.0017	(0.0003)	.	(0.010)	.	0.0030	0.024	17025	(0.001)	-40 mm Ø x -30 mm
BS 4820A	0.0002	0.0003	.	0.0003	(0.002)	0.0011	(0.0002)	0.0024	(0.011)	0.0012	(0.002)	17025	.	38 mm Ø x ~7 or 19+ mm
SRM 1763a	0.0054	.	(95.3)	.	0.100	.	.	(0.011)	(0.012)	0.308	(0.002)	.	0.044	34 mm Ø x 19 mm
VS RG29/1	0.044	0.020	0.62	.	.	-45 mm Ø x -28 mm
VS RG31/1	0.21	0.39	.	.	-45 mm Ø x -28 mm

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
KUT B3	1.19	.	.	30-35mm Ø x 39 mm
VS UG5/5	(0.01)	(0.003)	0.38	.	.	-45 mm Ø x -28 mm
IARM 155F	0.0016	(0.003)	.	.	.	0.0020	(0.004)	.	.	31 mm Ø x 2 or 18 mm
12X 86200A	-38 mm Ø x -15 mm
12X LA2E	-40 mm Ø x -15 mm
IMZ 112	0.013	0.010	.	.	.	40 mm Ø x 40 mm
12X 349D	0.101	0.049	.	.	-40 mm Ø x -15 mm
VS UG8/10	(0.003)	0.0034	.	.	.	-45 mm Ø x -28 mm
VS UG114	0.006	.	.	.	-45 mm Ø x -25 mm
BS 51F	(0.0001)	(0.0005)	.	(0.0001)	(0.0005)	0.0020	(0.00007)	(0.0011)	.	(0.0012)	(0.0030)	(0.0002)	.	38 mm Ø x ~7 or 19+ mm
IMZ 162	0.12	.	.	.	40 mm Ø x 40 mm
VS UG113	0.006	0.007	.	0.169	-45 mm Ø x -28 mm
BS 4620	0.00006	0.0001	.	0.0001	0.0001	0.0009	0.0002	0.0024	.	0.0026	0.0009	0.0002	.	38 mm Ø x ~7 or 19+ mm
ECRM 192-1D	-35 mm Ø x -30 mm
VS UG112	0.0028	0.005	.	0.0047	-45 mm Ø x -25 mm
DSZU C08	0.011	.	.	.	0.122	0.060	0.966	(0.003)	(0.006)	40 mm Ø x 30 mm last
BS LF3	0.0001	(0.0001)	.	.	.	0.004	38 mm Ø x ~7 or 19+ mm
HRT FE2012-N	40 mm Ø x 20 mm
IMZ 74A	(0.002)	(0.0004)	.	.	0.041	0.022	.	.	.	43 mm Ø x 20 mm
12X 19MNVS6A	-40 mm Ø x -15 mm
ECRM 087-1D	0.0046	.	.	.	0.0016	.	38 mm Ø x 25 or 30 mm
12X 15180A	-40 mm Ø x -15 mm
HRT FE2013-N	34 mm Ø x 20 mm
ECRM 194-2D	0.00155	.	.	.	0.0290	0.00322	.	.	.	39 mm Ø x 28 mm
BS 3962	37 mm Ø x ~7 or 19+ mm
CZ CM-8A	0.004	.	.	.	0.034	(0.001)	0.01	.	.	-39 mm Ø x 25 mm
HRT FB1999-N	0.0002	.	.	.	0.002	0.001	.	.	.	40 mm Ø x 20 mm
BS XCCT	(0.001)	(0.005)	<(0.001)	(0.0004)	.	(0.002)	.	.	<(0.002)	36 mm Ø x ~7 or 19+ mm
IMZ 176A	(0.015)	.	.	40 mm Ø x 40 mm
12X 12747U	0.072	0.030	.	.	42 mm Ø x 15 mm
BS 15A	(0.0002)	(0.0005)	.	.	0.041	.	(0.0003)	(0.003)	.	0.008	(0.004)	.	0.022	32 mm Ø x 17 mm last
RM Fe C/2	0.0030	(0.0013)	.	.	0.0073	.	.	0.0190	.	0.0074	0.34	.	0.010	40 mm Ø x 40 mm
ECRM 193-1D	0.0232	(0.0013)	.	.	.	36-41 mm Ø x 28-35 mm
BS 1972	(0.0001)	(0.0002)	.	.	(0.001)	(0.0026)	(0.001)	(0.004)	.	(0.003)	(0.004)	.	.	39 mm Ø x ~7 or 19+ mm
BS 47A	0.002	(0.003)	.	.	.	0.003	.	.	.	38 mm Ø x ~7 or 19+ mm

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
--------	---	----	----	----	----	---	----	----	----	----	---	----	----	-------

RM LOW ALLOY STEEL XRF SETPart Number: BS LAS-24 Set of 24 samples, each 35 - 45 mm Ø x 7 mm discs **17025**

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
300M	BS 4340M	0.414	0.74	0.004	<0.001	1.65	0.134	1.78	0.78	0.35	0.076	0.007	.	0.013	0.0020	0.009	0.056
1345	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.007	0.033	0.0023	.	0.006	0.0056	(0.0004)	(<0.003)
3115	BS XCCT	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.020	0.006	0.004	.	0.017	0.0076	(0.002)	0.031
4130	BS 3932	0.321	0.54	0.016	0.018	0.33	0.200	0.19	1.00	0.229	0.020	0.004	0.0043	0.011	0.0070	0.012	0.005
4140	BS 1962	0.41	0.94	0.007	0.011	0.242	0.224	0.16	1.05	0.229	0.018	0.007	.	0.008	0.0095	0.010	0.004
4150 + S	BS 42	0.516	1.24	0.021	0.073	0.235	0.252	0.183	0.67	0.190	0.020	(0.004)	.	0.012	0.0080	0.012	0.003
4330	BS 4330V	0.318	0.91	0.008	0.0009	0.240	0.181	1.91	0.91	0.475	0.021	.	0.0010	0.011	0.0076	0.010	0.094
4340	BS 60E	0.408	0.70	0.012	0.024	0.26	0.153	1.73	0.86	0.249	0.024	0.007	0.0010	0.009	0.0087	0.009	0.004
4615	BS 51E	0.15	0.59	0.010	0.021	0.28	0.22	1.75	0.14	0.21	0.028	.	.	0.035	0.0086	0.010	(0.0011)
4620	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.24	0.032	(0.0084)	(0.0001)	0.012	0.0078	0.013	(0.0008)
4820	BS 4820	0.188	0.57	0.010	0.025	0.25	0.11	3.29	0.12	0.21	0.020	0.005	0.0046	0.008	0.0079	(0.008)	(0.002)
6150	BS 43A	0.491	0.811	0.008	0.026	0.252	0.184	0.242	0.93	0.059	0.003	.	.	0.008	0.0074	0.011	0.148
8620	BS 1931	0.194	0.84	0.007	0.018	0.235	0.116	0.42	0.50	0.168	0.021	0.007	(0.0008)	0.012	0.0079	0.007	0.002
8822	BS 8822	0.228	0.92	0.011	0.025	0.26	0.17	0.47	0.52	0.34	0.022	0.007	(0.0004)	0.019	0.0085	0.011	0.003
8740	BS 67B	0.40	0.94	0.007	0.020	0.23	0.19	0.53	0.51	0.22	0.024	.	.	0.011	0.0078	0.009	(0.002)
9310	BS 58D	0.127	0.45	0.010	0.005	0.32	0.156	3.02	1.35	0.14	0.042	.	.	0.009	0.0147	0.012	0.005
9325	BS 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.31	0.030	(0.004)	0.0049	0.010	0.0089	0.009	0.004
P-20	BS 55E	0.307	0.72	0.014	0.024	0.60	0.032	0.053	1.66	0.40	(0.004)	.	.	(0.005)	0.0096	0.002	0.019
AMS 6418	BS 69B	0.2258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.39	0.024	.	.	0.035	0.0057	0.006	(0.002)
A193	BS 4942	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	0.54	(0.004)	0.005	0.0006	0.010	0.0080	0.014	0.28
A485-1	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.029	0.017	0.006	.	0.010	0.0060	0.011	0.003
E52100	BS 53E	1.08	0.37	0.007	0.012	0.24	0.11	0.26	1.45	0.10	0.003	.	.	0.011	0.0086	0.005	0.004
Nitriding	BS 68C	0.38	0.60	0.018	0.008	0.305	0.178	0.166	1.77	0.36	1.06	(0.004)	(0.0002)	0.011	0.0045	0.008	0.007
LF 3	BS LF 3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.056	0.017	0.006	(0.0001)	0.056	0.0054	0.006	(0.002)

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
-------	--------	---	----	---	---	----	----	----	----	----	----	----	----	----	---	----	---

RM TOOL STEEL XRF SETPart Number: BS TS-18 AVAILABLE INDIVIDUALLY **17025** ~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
A-2	BS 36C	0.96	0.46	0.023	0.027	0.31	0.18	0.19	5.01	0.99	.	(0.04)	0.11	0.03	.
A-10	BS A-10	1.41	1.75	0.016	0.022	1.15	0.16	1.82	0.24	1.53	0.006	<0.005	(0.004)	(0.010)	.
D-2	BS 37D	1.54	0.28	0.021	0.015	0.29	0.063	0.21	11.07	1.09	.	0.16	0.80	0.07	0.016
H-10	BS 49	0.36	0.33	0.014	0.015	0.92	0.072	0.20	3.51	2.41	0.004	0.31	0.62	2.00	0.0186
H-11	BS TH11	0.423	0.31	0.016	0.005	0.88	0.041	0.11	5.04	1.27	.	(0.01)	0.46	(0.008)	.
H-12	BS TH12	0.372	0.40	0.020	0.005	0.92	0.064	0.16	5.02	1.41	.	1.06	0.62	0.07	.
H-13	BS 34D	0.395	0.38	0.017	0.005	1.06	0.049	0.10	5.15	1.24	.	0.10	0.94	0.031	.
L-6	BS 39B	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	0.17	(0.011)	.	(0.01)	(0.02)	.
M-1	BS TM1	0.86	0.23	0.007	0.012	0.46	0.054	0.057	3.72	8.4	.	1.7	1.05	0.45	.
M-2	BS 32C	0.84	0.29	(0.018)	0.0010	0.29	0.13	0.35	3.98	4.85	(0.02)	6.3	2.03	0.31	.
O-1	BS 35D	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.035	(0.005)	0.46	0.181	0.012	.
O-6	BS 41	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	0.23	(0.007)	0.035	0.046	.	.
S-1	BS 33E	0.49	0.29	0.022	0.005	0.20	0.038	0.08	1.25	0.045	.	2.75	0.19	0.006	.
S-5	BS 38C	0.60	0.81	0.011	0.012	2.08	0.26	0.24	0.28	0.41	0.015	0.004	0.214	0.036	0.0081
S-7	BS TS7	0.529	0.70	0.016	0.010	0.27	0.05	0.10	3.18	1.34	.	0.19	0.35	0.043	.
T-1	BS 30D	0.745	0.348	0.029	0.0010	0.301	0.116	0.191	3.93	0.342	0.0123	17.73	1.077	0.101	0.0168
	BS 10V	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	1.30	<0.002	0.013	9.50	0.009	0.064
HP9-4-30	BS 9-4-30	0.30	0.22	0.008	<0.001	0.06	0.09	7.25	1.00	1.00	0.004	0.01	0.085	4.40	0.0015

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
-------	--------	---	----	---	---	----	----	----	----	----	----	---	---	----	---

TOOL STEEL

CONTINUED ON THE NEXT PAGE

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

Table with columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Co, Mo, N, Ti, V, W, Al. Contains multiple rows of data for various steel grades like BS PM15, BS 10V, DSZU C070, etc.

ALUMINUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Al	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	Ti	V
1	ECRM 299-1D	5.33	0.172	22.32	0.0154	0.2678	0.0152	0.00022	0.299	0.0382	0.0187	0.0186	0.0198	.	0.1289	0.0329
1	IMZ 158	1.56	0.24	25.51	0.091	1.34	0.015	0.007	2.23	0.097	.	0.025	.	.	0.12	0.078
1	13X PH17700A	1.172	6.98	16.88	0.0732	0.496	0.0181	0.0008	0.551	0.146	0.0464	0.340	0.0192	0.0201	0.051	0.0390
1	BS 192	1.17	7.11	16.44	0.074	0.835	0.025	0.0005	0.387	0.412	0.104	0.430	0.0290	0.168	0.076	0.124
2	CT X92834	1.14	8.32	12.57	0.035	0.044	0.003	0.003	0.019	0.030	0.030	2.20	.	0.001	0.019	<0.004
1	13X PH13800A	1.075	8.04	12.53	0.0386	0.0332	0.0064	0.0030	0.081	0.0449	0.0220	2.10	0.0041	.	0.0122	0.0188
2	BS 184A	1.00	8.34	12.66	0.035	0.06	0.007	0.001	0.080	0.041	0.036	2.20	0.0045	(0.006)	0.051	0.014
1	BS 192A	0.98	7.01	16.44	0.066	0.768	0.021	<0.002	0.300	0.334	0.114	0.28	0.029	0.208	0.083	0.077
1	IARM 152C	0.94	7.30	16.99	0.072	0.74	0.024	0.0006	0.263	0.316	0.113	0.36	0.0172	0.012	0.098	0.072

Number	As	B	Ca	O	Sn	Ta	W	Zr	Units
ECRM 299-1D	0.0054	0.0002	0.1775	40 mm Ø x 25 mm
IMZ 158	40 mm Ø x 40 mm
13X PH17700A	.	0.0033	.	.	0.0055	.	0.009	.	~38 mm Ø x ~15 mm
BS 192	(0.005)	(0.0003)	0.0007	0.0014	0.008	(0.001)	0.05	.	38 mm Ø x ~7 or 19+ mm
CT X92834	.	0.0009	.	.	0.002	.	.	<0.001	30-35 mm Ø x x ~19 mm
13X PH13800A	0.0051	.	.	.	~38 mm Ø x ~15 mm
BS 184A	.	(0.0004)	(0.0003)	(0.0003)	(0.002)	.	0.032	.	38 mm Ø x ~7 or 19+ mm
BS 192A	(0.0035)	(0.0003)	(0.0006)	(0.0006)	0.008	.	0.048	.	38 mm Ø x ~7 or 19+ mm
IARM 152C	(0.004)	0.0029	(0.0005)	(0.001)	0.007	(0.005)	0.026	.	31 mm Ø x 2 or 18 mm

CRM BORON IN STAINLESS STEEL

35 mm x 45 mm x 16 mm

Number	B	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Ti	V	W
DSZU C61	2.14	(0.073)	(0.38)	(0.003)	(0.005)	(0.41)	(0.09)	(0.95)	(17.8)	(0.04)	(0.24)	(0.75)	(0.19)	(0.22)
DSZU C60	1.42	(0.058)	(0.50)	(0.002)	(0.006)	(0.35)	(0.01)	(0.51)	(11.9)	(0.11)	(0.37)	(2.70)	(0.41)	(0.20)
DSZU C62	1.15	(0.065)	(0.31)	(0.010)	(0.024)	(0.32)	(0.24)	(0.84)	(14.4)	(0.59)	(0.16)	(3.36)	(0.18)	(0.14)
DSZU C63	1.05	(0.070)	(0.27)	(0.014)	(0.006)	(0.30)	(0.39)	(0.48)	(11.3)	(0.25)	(0.09)	(0.70)	(0.08)	(0.10)

CALCIUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Ca	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	V	W
2	BS CA304-1	0.0045	8.57	18.30	0.045	1.06	0.026	0.016	0.71	0.34	0.20	0.34	0.083	0.026	0.09	0.04
1	13X 14923A	0.0044	0.452	11.26	0.205	0.501	0.0197	0.0031	0.330	0.0563	0.0207	0.819	0.0321	0.005	0.295	.
1	ECRM 379-1D	0.0033	30.83	26.79	0.0121	1.804	0.0166	0.0006	0.393	0.984	0.0390	3.290	0.0550	(0.0028)	0.0663	(0.0091)
1	13X 31603C	0.0029	10.03	16.83	0.023	1.879	0.0263	0.0245	0.350	0.306	0.148	2.02	0.080	0.0197	0.0895	0.0427
2	BS 193	0.0020	1.82	18.48	0.104	12.11	0.018	0.002	0.66	0.088	0.028	0.21	0.37	0.014	0.107	(0.007)
2	BS SS4952	0.0019	0.23	13.15	0.347	0.41	0.016	0.003	0.66	0.045	0.030	0.049	0.027	0.004	0.089	(0.007)
2	BS 82E	0.0014	12.49	22.38	0.062	1.61	0.027	0.001	0.58	0.26	0.12	0.31	0.072	0.062	0.064	0.041
1	BS 9942	0.0014	13.55	18.21	0.021	1.84	0.025	0.006	0.49	0.305	0.086	3.30	0.071	0.005	0.072	0.032
1	BS 9842	0.0010	20.02	24.19	0.059	1.50	0.025	0.0016	0.99	0.147	0.237	0.111	0.037	0.026	0.075	0.011
1	ECRM 272-1D	0.00090	0.2445	11.927	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.0145	0.0030	0.0508	0.0028	0.0167	.
2	BS 94C	0.0008	0.43	25.90	0.057	0.45	0.024	0.002	0.62	0.056	0.042	0.20	0.065	0.032	0.12	(0.03)
2	BS 82D	0.0007	14.12	22.40	0.058	1.85	0.020	0.009	0.63	0.16	0.042	0.144	0.070	0.053	0.087	0.028
2	BS 87F	0.0007	10.12	17.30	0.055	1.64	0.024	0.025	0.67	0.28	0.17	0.29	0.037	0.57	0.13	0.050
2	BS SS3951	0.0005	9.18	18.17	0.014	1.56	0.023	0.031	0.61	0.22	0.16	0.303	0.077	0.085	0.067	0.040

Number	Al	As	B	O	Pb	Sb	Sn	Ti	Zn	Units
BS CA304-1	0.003	(0.003)	0.0006	0.0041	.	(0.0020)	0.010	0.028	.	38 mm Ø x ~5 mm last, sides not parallel
13X 14923A	0.003	0.004	.	.	~40 mm Ø x ~15 mm
ECRM 379-1D	(0.00246)	(0.0018)	0.00190	(0.0027)	(0.000038)	0.00057	0.0021	(0.0014)	.	38 or 45 mm Ø x 25 mm
13X 31603C	(0.005)	0.0053	.	.	~30 mm Ø x ~20 mm
BS 193	(0.003)	.	0.0007	(0.004)	.	.	0.004	0.003	.	32 mm Ø x ~7 or 19+ mm
BS SS4952	0.003	0.002	(0.0004)	0.005	.	.	0.004	0.002	.	38 mm Ø x ~7 or 19+ mm
BS 82E	0.006	.	0.0024	.	.	.	0.006	0.003	.	38 mm Ø x ~7 or 19+ mm
BS 9942	0.004	(0.004)	0.0014	(0.0023)	.	.	0.006	(0.002)	.	44 mm Ø x ~7 or 19+ mm
BS 9842	0.014	(0.002)	0.0025	(0.0044)	.	.	0.005	0.003	.	38 mm Ø x ~7 or 19+ mm
ECRM 272-1D	0.0046	0.0116	0.0018	.	.	0.0007	.	0.00096	0.0031	38 mm Ø x 25 or 30 mm
BS 94C	0.004	.	(0.0005)	0.0061	.	.	0.006	.	.	44 mm Ø x ~7 or 19+ mm
BS 82D	(0.002)	.	0.0040	0.007	.	.	0.004	0.005	.	38 mm Ø x ~7 or ~11 mm last
BS 87F	0.004	0.005	(0.0006)	0.005	.	.	0.004	0.004	.	41 mm Ø x ~7 or 19+ mm
BS SS3951	0.002	.	(0.0006)	0.0075	.	.	0.007	(0.002)	.	41 mm Ø x ~7 or 19+ mm

COPPER IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

Table with 17 columns: #, Number, Cu, Ni, Cr, C, Mn, P, S, Si, Co, Mo, N, Nb, Ti, V, W. Rows include materials like 13X PH 3M, BS 9621, BS 185A, BS 17-4PHB, BS 9622, BS 17-4PHA, CT 20 Cb-3, IARM 22C, CT 630, BS 187C, BS 187A, 13X PH17400A, ECRM 273-1D, VS LG64, SRM C2400, CT 455, BS SS1962, 13X 45500A, BS SS1961, IARM 16C, SS 475, BS 9812, BS 9811, IARM 318B, 13X PH2S143A, BS 179B, IARM 15C, BS 179C, IARM 15B, 13X NSA6B, CT 450, ECRM 295-1D, IARM 239B, 13X NSA 7A.

* Provisional Analysis

Table with 14 columns: Number, Al, Ag, As, B, Ca, Cd, Fe, Mg, O, Pb, Sb, Sn, Ta, Units. Rows include materials like 13X PH 3M, 13X PH2M, BS 9621, BS 185A, BS 17-4PHB, BS 9622, BS 17-4PHA, CT 20 Cb-3, IARM 22C, CT 630, BS 187C, BS 187A, 13X PH17400A, ECRM 273-1D, VS LG64, SRM C2400, CT 455, BS SS1962, 13X 45500A, BS SS1961, IARM 16C, SS 475, BS 9812, BS 9811, IARM 318B, 13X PH2S143A, BS 179B, IARM 15C, BS 179C, IARM 15B, 13X NSA6B, CT 450, ECRM 295-1D, IARM 239B, 13X NSA 7A.

MARAGING STEEL AND COBALT IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

Table with columns: #, Number, Co, Mo, Ni, Cr, C, Mn, P, S, Si, Cu, Al, B, N, Nb, Ti. Lists various alloy grades like IARM 326A, IMZ 521, etc.

Table with columns: Number, As, Ca, Fe, Mg, O, Sb, Sn, Ta, V, W, Zr, Units. Provides detailed composition for grades like IARM 326A, IMZ 521, etc.

TUNGSTEN IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

Table with columns: #, Number, W, Ni, Cr, C, Mn, P, S, Si, Cu, Co, Mo, N, Nb, Ti, V. Lists grades like VS LG57, 13X 14219K, etc.

Table with columns: Number, Al, As, B, Ca, O, Sb, Sn, Units. Provides detailed composition for grades like VS LG57, 13X 14219K, etc.

MANGANESE STAINLESS STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties * Provisional Analysis

Table with columns: # Number, Mn, Ni, Cr, C, P, S, Si, Cu, Mo, Al, Co, N, Nb, V, W. Rows include various steel grades like 1 IARM 294A, 1 IARM 295A, 1 ECRM 294-1D, etc.

Table with columns: Number, As, B, Ca, O, Pb, Sb, Sn, Ta, Te, Ti, Zr, Units. Rows include steel grades and their mechanical/chemical properties like IARM 294A, IARM 295A, ECRM 294-1D, etc.

CRM NICKEL BINARIES

analysis listed in mass % -40 mm Ø x ~15 mm

Table with columns: Number, Ni, C, Mn, P, S, Si, Cu, Cr, Al, Co, N, Mg, Mo, Nb, Ti, W. Rows include steel grades like 14X FeNi50B, 14X FeNi45B, 14X 94100A, etc.

= Class, 1=CRM, 2=RM, and 3=RM with no uncertainties analysis listed in mass % except * which is mg/Kg ** Provisional Analysis

Table with 17 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Co, Mo, N, Nb, Ti, V, W. Rows include materials like 14X HS10A, BS 156, IARM 13D, etc.

Continuation of the table from the previous block, listing various stainless steel grades and their chemical compositions.

HIGH ALLOY STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

Table with columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, Nb, Ti, V. Lists various steel grades like CZ SP-8B, SRM 1246, BS 800, etc., with their corresponding chemical compositions.

Table with columns: Number, As, B, Ca, Ce, Mg, O, Se, Sn, Ta, W, Zr, Units. Lists grades like CZ SP-8B, SRM 1246, BS 160A, etc., along with their units and specific material notes.

RM HIGH ALLOY STEEL XRF SET

Part Number: BS HAS-12

AVAILABLE INDIVIDUALLY

~7 mm discs

Number Grade	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	B	Co	N	Nb	Sn	Ti	V	W	O
BS 189A AL6XN CRM	0.0147	0.639	0.019	(0.001)	0.30	0.184	23.8	20.4	6.04	0.0129	(0.0002)	0.100	0.198	(0.13)	0.0035	0.0065	0.054	0.037	0.0024
BS 179A Alloy 255	0.017	1.04	0.021	0.001	0.44	1.94	5.84	25.45	3.24	(0.009)	(0.001)	0.58	0.184	0.030	0.005	0.006	0.070	(0.2)	.
BS 183 Greek Ascology	0.16	0.43	0.020	0.013	0.33	0.068	2.00	12.81	0.35	.	.	0.029	.	(0.003)	(0.0016)	0.003	0.12	2.77	.
BS 186A Invar 36	0.040	0.72	0.008	0.0053	0.19	0.016	35.86	0.16	0.0032	(0.001)	.	0.028	0.0026	(<0.002)	(0.002)	(<0.003)	0.0012	(0.01)	.
BS 187A Carp. 20Cb3	0.022	0.52	0.017	0.0025	0.26	3.10	33.06	19.75	2.06	(0.009)	0.0022	0.32	0.0157	0.57	0.003	(0.002)	0.10	(0.02)	.
BS 188A A-286	0.050	0.139	0.015	0.0049	0.15	0.099	24.61	14.04	1.10	0.19	0.0065	0.18	0.0029	0.050	0.002	2.21	0.24	0.055	.
BS 190 Nitronic® 40	0.022	9.72	0.015	0.001	0.46	0.072	6.74	19.57	0.15	(0.004)	0.0005	0.044	0.255	(0.004)	0.003	0.002	0.11	0.015	0.0045
BS 180A Nitronic® 50	0.018	5.05	0.012	0.001	0.32	0.067	13.19	21.09	2.04	0.012	(0.0024)	0.039	0.334	0.20	(0.002)	(0.002)	0.20	0.02	0.003
BS 181A Nitronic® 60	0.071	8.16	0.019	0.001	4.03	0.18	8.15	16.52	0.21	0.022	0.0009	0.072	0.148	0.017	0.005	0.007	0.094	0.04	0.0010
BS 193 18Cr-12Mn	0.104	12.11	0.018	0.002	0.66	0.088	1.82	18.48	0.21	(0.003)	0.0007	0.028	0.37	0.014	0.004	0.003	0.107	(0.007)	.
BS 182 17Cr-15Mn	0.037	15.09	0.022	(0.003)	0.46	0.56	1.11	16.67	0.99	.	.	0.032	(0.40)	(0.005)	(0.003)	(0.003)	0.059	(0.01)	.
BS 191 16Cr-6Mn-4Si	0.098	5.71	0.024	0.023	3.66	0.33	5.34	16.33	0.36	(0.002)	(0.0006)	0.11	0.117	0.024	(0.006)	0.012	0.083	0.033	.

CRM CAST IRON SETS AVAILABLE IN SETS ONLY, as grouped

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Sn	Ti	V	Ce	La	Mg	N
30 mm Ø x 28 mm																	
NCS HS11712a-6	4.02	1.41	0.021	0.026	0.163	1.83	1.89	0.112	0.019	0.726	0.057	0.238	0.509	<0.0001	<0.0001	0.104	0.013
NCS HS11712a-7	3.94	1.38	0.085	0.0048	0.918	1.10	1.37	1.05	0.214	0.168	0.134	0.114	0.390	<0.0001	<0.0001	0.056	0.0063
NCS HS11712a-5	3.52	0.311	0.420	0.019	1.17	0.389	1.03	0.766	.	0.629	0.013	0.161	0.324	<0.0001	<0.0001	0.021	0.0047
NCS HS11712a-4	3.16	0.462	0.396	0.017	1.96	0.921	0.778	1.40	0.0073	0.428	0.024	0.065	0.166	<0.0001	<0.0001	0.025	0.0073
NCS HS11712a-2	2.22	0.301	0.043	0.058	2.44	0.458	0.341	2.13	0.060	0.087	0.044	0.065	0.055	0.0010	0.010	0.0085	0.024
NCS HS11712a-3	2.55	0.878	0.071	0.045	1.50	0.641	0.519	0.417	0.034	0.354	0.021	0.027	0.085	0.027	0.0061	0.024	0.024
NCS HS11712a-1	1.75	0.080	0.580	0.119	3.40	0.025	0.030	2.48	0.248	0.031	0.0031	0.038	0.021	<0.0001	<0.0001	0.0006	0.015
30 mm Ø x 30 mm																	
NCS HS19701-7	4.13	2.06	0.306	0.111	1.85	.	0.026	0.157	.	.	0.043	0.399	0.821
NCS HS19701-6	3.93	1.46	0.168	0.124	0.99	.	0.094	0.387	.	(0.112)	0.0018	0.105	0.506
NCS HS19701-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	(0.68)	0.0022	0.066	0.335
NCS HS19701-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	(0.031)	0.0017	0.030	0.158
NCS HS19701-3	3.29	1.22	0.045	0.056	0.689	.	0.046	0.030	.	.	0.009	0.043	0.071
NCS HS19701-2	2.99	0.329	0.033	0.038	0.937	.	0.194	0.080	.	.	0.024	0.216	0.044
NCS HS19701-1	2.46	0.072	0.011	0.019	0.099	.	0.183	0.511	.	.	0.005	0.0059	0.0090

CRM CAST IRON SET AVAILABLE IN SET ONLY 37 mm x 37 mm x ~20mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Ce	La	Mg	Mo	Sb	Sn	Ti	V
CKD 241	1.71	0.136	0.006	0.14	3.20	0.021	0.014	0.684	.	.	.	0.60	0.13	0.004	0.001	0.092
CKD 242	2.21	0.045	0.040	0.033	2.88	0.045	0.024	0.026	.	.	.	1.20	0.007	0.008	0.314	0.43
CKD 243	2.23	0.385	0.162	0.085	2.44	0.175	0.080	0.378	.	.	.	0.263	0.082	0.111	0.013	0.258
CKD 244	2.60	0.665	0.024	0.019	2.11	0.295	0.36	0.274	0.014	0.005	0.033	0.053	(0.003)	0.177	0.033	0.004
CKD 245	2.78	1.36	0.40	0.049	1.60	0.063	0.165	0.168	.	.	0.004	0.106	0.048	0.074	0.074	0.058
CKD 246	2.82	0.302	0.60	0.022	0.62	1.38	0.043	1.20	(0.01)	0.003	0.010	0.005	0.003	0.005	(0.001)	0.002
CKD 247	3.12	1.01	0.095	0.005	1.16	0.815	0.42	0.054	0.048	0.022	0.037	0.015	0.002	0.038	0.058	0.008
CKD 248	3.41	0.245	0.050	0.006	1.81	0.117	0.70	0.022	0.023	0.014	0.064	0.003	0.012	0.015	0.170	0.171
CKD 249	3.75	0.127	0.25	0.008	0.34	0.485	1.42	0.093	0.077	0.025	0.056	0.013	0.004	0.004	0.096	0.024
Number	Al	As	B	Bi	Ca	Co	Fe	Nb	Nd	Pb	Pr	Se	Te	W	Zn	Zr
CKD 241	0.003	0.003	(0.001)	.	.	0.002	(93.23)	0.002	.	0.003	.	.	.	0.001	.	0.001
CKD 242	0.075	0.007	0.007	0.013	.	0.002	(92.55)	0.007	.	0.020	.	.	0.024	0.011	(0.001)	.
CKD 243	0.012	0.08	0.009	.	.	0.022	(93.03)	0.024	.	(0.04)	.	0.050	.	0.026	(0.016)	.
CKD 244	0.070	0.041	0.084	.	(0.003)	0.047	(92.95)	0.004	(0.004)	0.002	(0.002)	.	.	0.055	0.018	0.034
CKD 245	0.020	0.006	0.008	0.007	.	0.004	(92.89)	.	.	0.015	.	0.034	0.029	0.021	.	0.002
CKD 246	0.006	0.005	.	.	(0.002)	0.008	(92.92)	0.001	(0.003)	(0.0003)	(0.001)	.	.	0.007	.	.
CKD 247	0.013	0.009	(0.01)	.	(0.005)	0.092	(92.82)	0.057	(0.012)	0.002	(0.006)	.	(0.017)	(0.005)	0.013	0.007
CKD 248	0.045	0.019	0.036	0.004	(0.003)	0.016	(92.96)	0.005	(0.005)	0.012	(0.002)	0.003	0.004	(0.003)	0.015	0.015
CKD 249	0.059	0.018	0.018	0.006	(0.002)	0.011	(92.94)	0.035	(0.02)	0.023	(0.009)	0.004	(0.004)	(0.01)	0.004	0.040

These CKD sets may contain 1 or more replacement pieces from later batches.

CAST IRON WITH MAGNESIUM - continued from the previous page

sizes shown below

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
CZ 20034 17b	0.008	(0.0002)	(0.001)	(0.002)	.	.	(0.002)	0.004	.	.
CZ 20034 17a	0.007	(0.0002)	(0.001)	(0.002)	.	.	(0.002)	0.004	.	.
CZ 20034 17c	0.0005	(0.0006)	(0.002)	(0.002)	.	.	(0.002)	0.004	.	.
Y 2863-11	(0.022)	0.053	0.133	(0.0057)	(0.174)	.	(0.108)	0.010	.	.
CZ SPL17 43A	.	0.0014	(0.002)	.	.	N:0.0045	0.008	0.014	(0.004)	.	0.067	0.038	Zn:0.013	.
CZ SPL17 42A	.	0.0036	(0.002)	.	.	N:0.0027	0.045	0.020	0.015	.	0.027	0.020	Zn:0.013	.
Y 451045
CZ 02033 2g	.	0.0023	0.006	0.008	0.029	.	0.015	(0.004)	.	Zn: 0.020
Y 2863-12	(0.0097)	0.0078	0.21	(0.056)	(0.471)	.	(0.307)	0.13	.	.
CZ 02033 2f	.	0.0020	(0.002)	0.005	0.028	.	0.014	(0.003)	(0.005)	Zn: 0.018
Y 4510251-16	.	0.0044	.	.	.	0.016	0.030	.	.
VS ChG 25	0.052	.	0.017	.	.	.
Y 451047	.	0.31	0.012
SCRM 668/13
CZ 02033 3c	(0.007)	0.0044	(0.002)	0.005	.	.	0.009	(0.003)	.	.
SCRM 666/12
CZ 20034 15a	(0.003)	0.0041	0.012	0.058	.	0.005	0.006	.	.
CZ SPL17 31A	.	(0.0004)	.	.	.	N:0.0042	(0.003)	(0.005)	.	.
SCRM 670/19
11X SG1A	0.0021	Zn:0.041	-50Ø x -15mm
CZ 20034 15b	(0.003)	0.0033	0.010	0.058	.	0.005	0.007	.	.
CZ SPL17 34A	.	0.0076	(0.005)	.	.	N:0.0041	0.014	(0.006)	0.007	.	0.051	0.016	Zn:0.007	.
11X SG2A	0.0022	Zn:0.040	-50Ø x -15mm
Y 451042
CZ 02033 2e	.	0.0024	0.005	(0.004)	0.028	.	0.015	0.008	.	Zn: 0.025
CZ 20034 15c	(0.003)	0.0057	0.008	0.056	.	0.006	0.004	.	.
CZ SPL17 32A	.	(0.0005)	(0.007)	.	.	N:0.0042	.	0.022	0.023	.	(0.012)	(0.008)	Zn:0.011	.
CZ 02033 3b	.	0.0042	0.001	0.009	.	.	0.019	.	.	.
CZ SPL17 40A	.	0.0008	.	.	.	N:0.0063	(0.004)	.	Zn:(0.002)	.
Y 451044	last of stock
VS ChG 28	0.015	.	0.0017	.	.	.
CZ 20034 14a	0.036	0.0096	0.007	(0.005)	0.015	.	0.027	(0.005)	0.011	Zn: 0.010
CZ 20034 14b	0.034	0.0100	0.007	(0.005)	0.016	.	0.028	(0.005)	0.014	Zn: 0.009
BS 286AF	(0.01)	0.0085	.	(0.001)	[91.4]	.	(0.003)	.	.	.	(0.004)	(0.008)	(0.007)	17025
BS 286AE	(0.01)	0.0085	.	(0.001)	[91.4]	.	(0.003)	.	.	.	(0.004)	(0.008)	(0.007)	17025

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
CZ 02033 3d	(0.018)	0.0071	(0.002)	0.005	0.007	.	0.009	.	.	.
CZ 02033 1f	.	0.0043	(0.001)	0.009	.	.	0.030	0.022	(0.008)	.
CZ 02033 1g	.	0.0034	0.005	0.016	.	.	0.028	0.015	(0.004)	.
CZ 20034 13c	(0.002)	(0.002)	.	0.014	(0.003)	(0.02)	.
CZ 02033 1e	.	0.0036	(0.002)	0.007	.	.	0.032	0.021	(0.007)	Zn: 0.009
CZ 02033 1c	.	0.0005	0.016	0.006	.	.	0.032	0.015	Zn:0.001	.
CZ 20034 14c	0.035	0.0123	0.020	.	0.025	(0.003)	0.013	Zn: 0.010
CKD 247C (U)	0.012	0.000	0.007	Zn:0.018	(92.6)	0.023	0.048	(0.002)	0.005	(0.000)	0.040	(0.002)	0.009	last of stock
CZ 20034 13a	(0.002)	(0.002)	.	0.014	(0.003)	0.029	.
CZ 20034 13b	(0.002)	(0.002)	.	0.014	(0.003)	0.023	.
CKD 247B	0.010	0.000	0.007	.	(92.7)	0.019	0.052	(0.002)	0.005	(0.000)	0.038	(0.002)	0.009	Zn: 0.012
VS ChG 24	0.009	.	0.077	.	.	.
Y 2863-9	(0.041)	0.153	0.11	(0.093)	(0.116)	.	(0.124)	.	.	.
VS ChM5/1
SCRM 667/13
VS ChM6/1
VS ChM8/1
CZ SPL17 36A	.	0.022	(0.007)	.	.	N:0.0038	.	0.016	.	.	(0.002)	.	Zn:(0.002)	.
VS ChM13
SCRM 669/14
CKD 245B(U)	0.006	0.003	0.009	.	(92.5)	(0.00)	0.029	0.020	0.052	(0.029)	0.076	0.020	0.004	.
CKD 245A	0.002	0.007	0.008	.	(92.7)	(0.00)	(0.001)	0.015	0.050	(0.036)	0.076	0.021	0.003	last
VS ChG 26	0.031	.	.	.
VS ChM10
SRM C1137a
CZ SPL17 33A	.	0.0064	(0.002)	.	.	N:0.0043	0.032	0.010	0.019	.	0.039	0.079	Zn:0.009	.
CKD 246B	0.003	0.000	(0.001)	.	(92.6)	0.003	(0.001)	(0.002)	0.004	(0.00)	0.002	(0.011)	0.000	.
SRM C2424	.	(0.002)	.	.	.	0.0011
VS ChM9
VS ChM11
Y 2863-7	(0.021)	0.100	0.041	(0.0025)	(0.010)	.	(0.0073)	.	.	.

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
BS: 28-34	mm Ø x 17-35 mm			CKD 24x:	37 mm x 37 mm x ~13-20 mm			SCRM:	48 mm x 42 mm x 12 mm			VS:	~39 mm Ø x ~39 mm	
				CZ:	40 mm Ø x 18 mm			SRM:	32 mm Ø x 19 mm			Y:	30 mm Ø x 30 mm	

RM CAST IRON WITH YOUR CHOICE OF MAGNESIUM LEVELS each unit: 2 pcs mushroom 43 mm Ø x 5 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Al	Ce	Co	Sn	Ti	V	Zn	Other
CTIF 6134	3.70	0.25	0.030	<0.01	1.60	0.020	2.00	0.040	*	.	<0.03
CTIF 8532	3.7	0.288	0.05	.	2.6	0.0443	0.888	0.04	*	.	<0.025	.	0.0303	0.02	0.07	.	.
CTIF 6135	3.6	0.38	0.0130	(0.003)	0.9	0.0219	1.98	0.04	*	(0.006)	.	0.037	.	0.007	0.0155	.	.
CTIF 4500	3.38	0.60	0.059	(0.002)	1.97	.	1.45	0.014	*	0.033	0.023	0.065
CTIF 5781	3.35	0.26	0.030	(0.0025)	2.50	0.0061	0.83	0.040	*	.	.	(0.004)	.	0.0208	0.0150	.	.
CTIF 4497	3.12	0.605	0.043	(<0.002)	2.66	0.048	1.90	0.040	*	.	.	.	0.094	0.031	0.44	.	.
CTIF 7160	3.1	0.57	0.05	(0.001)	2.4	0.08	1.0	(0.1)	*	(0.02)	0.02	0.09	.	0.013	0.018	.	As: 0.009
CTIF 5037	3.04	0.76	0.043	(0.0025)	3.40	.	0.64	0.014	*	0.029	.	.	.
CTIF 3601B	3.0	0.35	0.037	(0.005)	2.1	0.019	1.08	0.029	*	.	<0.01	.	.	0.016	(0.005)	<0.05	Pb:(<0.002)
CTIF 8018	3.0	0.7	0.07	(0.0015)	3.0	0.08	0.127	0.09	*	0.02	(<0.02)	.	0.07	0.06	0.39	.	Sb:(0.01)
CTIF 6736	2.8	0.65	0.012	(0.002)	1.6	0.0258	1.7	0.03	*	0.008	(0.03)	.	.
CTIF 5783	2.55	0.2	0.0266	(0.003)	2.3	0.110	1.23	0.05	*	.	.	0.0074	.	0.015	0.0127	.	As: 0.0016

Magnesium level available in the below samples. X = available

For Mg Range	Order Suffix	3601B	4497	4500	5037	5781	5783	6134	6135	6736	7160	8018	8532
<0.005	<0.005	X	.	.	.	X	X	X	.
0.005 - 0.009	0.005	X	.	.	X	X	X	.	.	X	.	X	X
0.010 - 0.014	0.01	X	.	.	X	X	X	.	.	X	X	X	X
0.015 - 0.024	0.02	X	.	.	X	X	X	.	X	X	X	X	X
0.025 - 0.034	0.03	.	.	.	X	.	X	.	X	X	X	X	X
0.035 - 0.044	0.04	.	.	.	X	.	X	.	X	X	X	X	X
0.045 - 0.054	0.05	.	.	.	X	.	X	.	X	X	X	X	X
0.055 - 0.064	0.06	.	X	X	.	.	X	.	X	X	X	X	X
0.065 - 0.074	0.07	.	X	X	.	.	X	.	X	X	X	X	.
0.075 - 0.084	0.08	.	.	X	.	.	.	X	X	X	X	X	.
0.085 - 0.094	0.09	.	X	X	.	.	.	X	X	X	X	X	.
0.095 - 0.104	0.10	X	X	X	X	X	.
0.105 - 0.114	0.11	X	X	X	X	X	.
0.115 - 0.124	0.12	X	X	X	X	X	.
0.125 - 0.134	0.13	X	.	X	X	.	.
0.135 - 0.144	0.14	X	.	.	X	.	.
0.145 - 0.154	0.15	X	.	.
0.155 - 0.164	0.16	X	.	.
0.165 - 0.174	0.17	X	.	.
0.175 - 0.184	0.18

The above cast iron samples can be ordered with your choice of Magnesium. Examples:
to order CTIF 6736 with Mg 0.035 - 0.044 then order as part number CTIF 6736 0.04
to order CTIF 8018 with trace Mg, order as part number CTIF 8018 <0.005

CAST IRON WITH C > 2.75%

CONTINUED FROM THE PREVIOUS PAGE

analysis in mass % except * = mg/kg

Table with columns: Number, As, B, Bi, Ca*, Ce, La, Mg, N, Pb, Sb, Se, Te, W, Zr, Units. Rows include material codes like CZ SPL17 35A, Y 2582-7, VS ChG 2/9, etc.

Table with columns: Number, As, B, Bi, Ca*, Ce, La, Mg, N, Pb, Sb, Se, Te, W, Zr, Units. Rows include material codes like NCS HS11784, Y 2582-3, VS ChG 4/9, etc.

Table with columns: Number, As, B, Bi, Ca*, Ce, La, Mg, N, Pb, Sb, Se, Te, W, Zr, Units. Rows include material codes like NCS HS11786, Y 2863-4, etc.

CAST IRON WITH C < 2.75%

= Class, 1 = CRM and 2 = RM

analysis in mass % except * = mg/kg

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	11X C5Y *	2.75	0.75	0.09	0.09	1.9	0.42	1.2	0.94	0.06	0.045	0.53	0.015	0.03	0.09	0.075	0.01
1	VS ChL4/1	2.69	1.37	0.054	0.027	1.99	0.161	0.725	0.92	.	0.017	0.116	.	.	0.11	0.258	.
1	SRM C1291	2.67	1.14	0.028	0.032	1.34	0.26	4.34	2.78	.	.	0.32	.	.	.	0.031	.
1	VS ChG 6/9	2.65	0.83	0.54	0.027	0.53	0.34	.	0.241	0.028	0.130	.
1	DSZU CH01	2.61	0.258	0.012	0.0045	1.95	0.097	0.072	0.88	0.079	(0.06)	0.070	(0.010)	(0.05)	0.132	0.134	.
1	VS ChG 40	2.59	1.56	0.059	0.019	1.60	0.98	1.61	1.47	.	.	0.229	.	.	0.18	0.325	.
1	SCRM 661/4	2.56	0.30	0.84	0.068	2.96	.	.	(1)
1	SCRM 656/9	2.537	0.820	0.060	0.108	2.504
1	11X C7N	2.51	1.942	0.0266	0.0101	0.829	0.075	0.0303	0.507	0.0127	0.0335	0.071	0.051	0.0114	0.022	0.036	0.0226
1	Y 2863-2	2.50	1.83	0.069	0.026	3.14	0.020	3.73	0.136	.	.	0.096	.	.	0.066	0.61	.
1	VS ChG 37	2.49	0.92	0.038	0.046	2.03	0.512	0.90	0.82	.	.	0.55	.	.	0.092	0.227	.
1	SCRM 673	2.47	0.133	0.328	0.006	1.72	0.023	0.147	0.037	0.028	0.053	0.006	.	0.0191	0.072	0.059	0.0004
1	CZ 20034 11b	2.44	0.382	0.271	0.140	3.67	0.130	0.082	1.178	0.067	0.005	1.144	.	0.074	0.041	0.182	.
1	VS ChG 38	2.43	0.302	0.386	0.084	2.30	1.20	0.162	1.98	.	.	0.046	.	.	0.105	0.119	.
1	CZ 02033 5b	2.42	0.812	0.033	0.073	1.32	0.031	0.188	0.061	0.062	.	0.089	.	.	0.007	0.005	.
1	VS ChL2/1	2.38	1.03	0.054	0.023	0.55	0.97	0.114	0.077	.	0.013	0.012	.	.	0.009	0.050	.
1	CZ 20034 11a	2.37	0.343	0.271	0.163	3.31	0.086	0.084	1.219	0.046	0.005	1.130	.	0.070	0.028	0.184	.
1	SCRM 652/4	2.34	1.19	0.071	0.129	0.878	.	.	(1)
1	DSZU CH07	2.33	1.36	0.090	0.064	3.01	0.35	0.403	0.34	0.036	.	0.66	(0.08)	(0.07)	0.150	0.52	.
1	CZ 02033 5a	2.30	0.804	0.035	0.100	1.26	0.014	0.096	0.054	0.060	.	0.100	.	.	0.008	0.005	.
1	CZ 02033 5c	2.30	0.704	0.027	0.091	1.40	0.013	0.188	0.085	0.103	0.013	0.104	.	(0.002)	0.008	0.054	.
1	SCRM 675	1.92	1.81	0.045	0.072	1.29	0.012	0.210	0.080	0.007	0.023	0.034	.	0.0062	0.007	0.178	0.0006
1	SCRM 655/4	1.90	0.44	0.180	0.076	2.110	.	.	(1)
1	11X C4R	1.86	0.493	0.108	0.098	2.92	0.345	2.02	1.531	0.040	0.0316	0.101	0.0373	0.0102	0.080	0.0208	0.0083
1	CKD 242A	1.84	0.060	0.039	0.036	3.06	0.055	0.039	0.029	0.036	0.002	1.13	0.013	0.010	0.19	0.37	(0.00)
1	Y 2863-1	1.78	2.41	0.021	0.009	3.62	0.022	4.77	0.031	.	.	0.038	0.0052	.	0.068	1.13	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
---	--------	---	----	---	---	----	----	----	----	----	----	----	----	----	----	---	----

Number	As	B	Bi	Ca*	Ce	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
--------	----	---	----	-----	----	----	---	----	----	----	----	---	----	-------

11X C5Y *	0.02	0.005	* Provisional Analysis					0.01	0.005	0.03	0.006	.	0.005	0.001	~40 mm Ø x ~15 mm
VS ChL4/1	~38 mm Ø x ~38 mm	
SRM C1291	32 mm Ø x 19 mm	
VS ChG 6/9	(0.003)	~38 mm Ø x ~38 mm	
DSZU CH01	.	(0.03)	.	(10)	.	(0.0005)	(0.02)	.	~30 mm x ~35 mm	
VS ChG 40	~40 mm Ø x ~40 mm	
SCRM 661/4	48 mm x 42 mm x 12 mm	
SCRM 656/9	48 mm x 42 mm x 12 mm	
11X C7N	0.0159	0.0097	0.0137	.	.	.	0.025	0.0106	0.025	.	.	0.066	(0.003)	40 mm Ø x 15 mm	
Y 2863-2	.	0.0025	30 mm Ø x 30 mm	
VS ChG 37	~40 mm Ø x ~40 mm	
SCRM 673	0.044	40 mm x 37 mm x 10 mm	
CZ 20034 11b	0.005	0.0032	0.007	0.007	0.011	.	.	(0.005)	0.007	40 mm Ø x 18 mm	
VS ChG 38	~40 mm Ø x ~40 mm	
CZ 02033 5b	.	0.014	0.020	40 mm Ø x 18 mm	
VS ChL2/1	~38 mm Ø x ~38 mm	
CZ 20034 11a	0.005	0.0018	0.011	0.017	0.013	.	.	(0.005)	0.007	40 mm Ø x 18 mm	
SCRM 652/4	48 mm x 42 mm x 12 mm	
DSZU CH07	.	(0.13)	.	(10)	.	(0.01)	~35 mm x ~35 mm	
CZ 02033 5a	40 mm Ø x 18 mm	
CZ 02033 5c	.	0.0078	0.007	(0.002)	(0.010)	.	(0.009)	40 mm Ø x 18 mm	
SCRM 675	0.035	40 mm x 37 mm x 10 mm	
SCRM 655/4	48 mm x 42 mm x 12 mm	
11X C4R	0.0050	0.0086	0.0144	Ag: 0.008	0.008	0.0078	0.019	0.015	0.021	.	.	0.120	0.0031	~40 mm Ø x ~12 mm	
CKD 242A	0.015	0.008	(0.015)	(0.00)	0.000	.	(0.012)	0.007	.	(0.08)	(0.007)	.	(0.000)	37mm x 37mm x 18 or 20mm	
Y 2863-1	.	0.0024	30 mm Ø x 30 mm	

Number	As	B	Bi	Ca*	Ce	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
--------	----	---	----	-----	----	----	---	----	----	----	----	---	----	-------

Table with columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Mo, Pb, Sn, Ti, V, Mg, N. Rows list various alloy grades like BAS NCRM5, SRM C1292, Y 451052-1, etc., with their respective chemical compositions.

Table with columns: #, Number, C, Ce, Co, Mn, Nb, P, W, S, Zr, Ni, Cr, Al, Mo, Pb, Sn, Ti, V, Mg, N, Units, Other. This table provides additional information including units and other elements for the listed alloy grades.

RM CAST IRON MUSHROOMS CONTINUED ON THE NEXT PAGE

typical analysis

each unit is one pair of 43 mm Ø x 5 mm mushroom discs

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF F019	4.04	1.05	1.05	0.032	0.057
CTIF F012	3.71	1.86	0.44	0.038	0.004	0.77	.	.	0.008	.	.	0.011	.	.	.
CTIF F08	3.6	1.04	0.37	0.107	0.021	0.215	0.30	0.30	.	.	0.005	0.05	0.055	0.014	.
CTIF FCR7	3.59	1.07	0.365	0.099	0.0427	0.704	0.947	33.65	.	.	2.62
CTIF F06	3.49	0.55	0.715	0.87	0.106	0.120	0.128	0.45	.	.	0.202	0.039	0.080	0.110	.
CTIF F010	3.5	0.67	1.05	0.20	0.101	0.114	0.118	0.38	.	.	0.20	.	0.1	0.08	.
CTIF NH3	3.47	0.85	0.175	0.36	0.024	0.031	2.53	1.76	.	.	0.73
CTIF F011	3.45	1.57	0.685	0.052	0.103	0.211	0.235	0.34	.	(0.013)	0.225	0.066	0.078	0.113	.
CTIF F018	3.43	1.24	0.590	1.34	0.136	0.049	0.140	0.170	.	.	0.179	0.046	0.057	0.102	.
CTIF NH7-1	3.43	0.95	0.63	0.035	0.022	0.105	5.53	9.02
CTIF FCR5	3.43	0.35	0.62	0.052	0.0175	1.02	2.69	28.5	.	.	3.27
CTIF FT2-1	3.39	1.415	0.78	0.045	0.095	0.01	0.070	0.030	0.100	0.405	.
CTIF NiMo1	3.22	2.585	0.200	0.0590	(0.0030)	0.376	2.165	0.0353	.	0.0205	0.457	0.0020	0.0190	0.0169	.
CTIF FL7	3.22	2.550	0.100	1.34	0.048	0.351	0.232	0.043	.	.	0.335	0.0291	0.0525	0.0796	.
CTIF FT3	3.2	1.55	0.345	0.063	0.051	0.015	0.092	0.685	0.2	0.016	.
CTIF NH7-2	3.2	1.20	0.91	0.034	0.0120	0.108	5.53	8.87
CTIF F05	3.2	0.7	0.2	1.30	0.027	0.12	0.172	0.3	.	.	0.41	0.109	0.04	0.14	.
CTIF NH9	3.13	1.24	0.65	0.087	0.029	0.203	4.11	11.70	.	.	0.059
CTIF NR Cu1	3.12	1.465	0.172	0.090	0.99	4.95	18.02	0.994	(0.095)
CTIF FL6	3.1	1.4	0.6	0.012	0.18	0.079	1.03	0.167	.	0.028	0.50	0.005	0.15	0.033	.
CTIF FL10	3.1	1.3	0.85	0.323	0.066	0.104	0.10	(0.07)	(0.03)	.	0.0335	0.028	0.045	0.048	(0.02)
CTIF FFA 1	3.090	0.0300	0.100	0.0022	0.0009	0.0622	0.0450	0.0710	.	0.0097	0.0109	.	0.0010	0.0010	.
CTIF NR 8S	3.05	1.41	4.39	0.124	.	0.071	14.20	0.191
CTIF F017	3.01	2.48	0.475	0.470	0.168	(0.006)	0.021	(0.016)	.	0.032	.	0.024	0.032	0.018	.
CTIF FAL 1	3.0	1.0	0.2	0.04	<0.001	0.2	0.06	0.04	2.1	.	0.015	.	0.01	.	.
CTIF NR 3L	2.99	3.05	0.72	0.088	0.052	0.26	21.58	2.97
CTIF NH1	2.98	1.35	0.90	0.060	0.105	1.99	1.38	0.83	.	.	1.45
CTIF NH8	2.98	0.80	0.57	0.052	0.076	0.065	8.16	5.03	.	.	0.125
CTIF NR 3S	2.92	2.91	0.77	0.024	.	0.33	24.63	3.05
CTIF FT1	2.9	2.12	0.71	0.12	0.025	0.012	0.11	0.057	.	.	.	0.067	0.19	0.525	.

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF NR 8L	2.89	1.70	5.19	0.054	0.030	0.075	13.33	0.165
CTIF NH4	2.84	0.49	0.28	0.12	0.022	0.09	3.60	2.46	.	.	0.30
CTIF F04	2.81	1.51	0.64	0.58	0.009	0.31	0.32	0.17	.	.	0.095	0.013	0.075	0.049	.
CTIF FCR2	2.86	1.07	0.740	0.137	0.055	0.135	1.87	11.8	.	.	3.88
CTIF FL5	2.8	2.3	0.4	0.02	(0.005)	0.5	0.05	0.35	.	0.010	0.01	0.07	0.01	0.01	.
CTIF FCR Ni3	2.74	0.69	0.47	0.036	0.011	.	11.05	31.65
CTIF NH6	2.70	2.28	0.355	0.066	0.036	0.115	7.06	6.60	.	.	0.11
CTIF F09	2.7	1.5	0.7	0.02	0.015	0.31	0.355	0.18	.	.	0.13	0.144	0.017	0.022	.
CTIF FL4	2.6	2.91	0.5	0.288	0.137	0.0168	0.061	0.45	.	.	0.090	0.011	0.0296	0.116	.
CTIF NR 1S	2.58	3.02	1.54	0.19	0.0015	0.11	20.60	2.00
CTIF NR 1L	2.50	3.00	1.34	0.125	0.10	0.49	25.87	1.74
CTIF NH2	2.50	1.81	1.04	0.047	0.058	1.02	1.78	1.26	.	.	1.01
CTIF NR Cu2	2.48	2.07	1.078	0.113	0.049	6.50	15.85	2.05
CTIF NR 4S	2.47	4.87	1.71	0.145	.	0.63	18.30	1.50
CTIF FCR4	2.47	1.40	2.05	0.097	0.066	1.32	0.571	24.2	.	.	2.16
CTIF FCR1	2.46	0.48	0.63	0.019	0.007	0.031	1.30	18.71	.	.	1.41
CTIF F07	2.45	0.675	0.70	0.84	0.085	0.125	0.15	0.455	.	.	0.26	.	0.065	0.13	.
CTIF NR 4L	2.41	5.89	1.495	0.155	0.010	0.758	15.90	1.403
CTIF NR 2S	2.32	1.43	0.530	0.062	.	0.210	36.3	0.51
CTIF NH5	2.31	0.31	0.24	0.115	0.04	0.035	4.90	2.85	.	.	0.017
CTIF FL3	2.3	2.1	0.27	0.729	(0.013)	0.102	0.553	0.107	.	.	0.106	0.111	0.05	0.049	.
CTIF NR 4G	2.24	5.60	1.72	0.11	(0.002)	0.64	21.30	1.40
CTIF NR 2G	2.25	1.47	0.380	0.0476	(0.003)	0.232	36.34	0.395
CTIF FL2	2.18	3.61	0.0400	0.049	0.082	0.0497	0.0238	0.440	(0.006)	0.0263	(0.004)	0.140	0.0750	0.201	.
CTIF FL1	2.1	3.2	0.80	0.118	0.0765	0.0195	0.245	0.06	.	(0.022)	0.038	0.305	0.020	0.015	.
CTIF F01	2.02	3.18	0.71	0.112	0.074	0.036	0.120	0.090	.	.	0.032	0.38	0.018	0.019	.
CTIF FCR Ni2	2.02	1.50	0.61	0.185	0.024	.	13.05	29.00
CTIF NR Cu3	1.94	3.12	0.60	0.046	0.016	8.05	13.3	3.50
CTIF NR 6S	1.82	2.44	0.99	0.019	.	0.03	30.75	1.06
CTIF NR 5L	1.77	2.99	1.207	0.037	0.083	0.48	33.89	0.27
CTIF NR 6L	1.76	2.07	0.70	0.031	0.063	0.020	30.37	3.49
CTIF NR 5S	1.67	1.97	1.23	0.035	.	0.50	27.05	0.24
CTIF FCR6	1.44	0.76	1.47	0.201	0.086	0.480	0.188	30.84	.	.	0.455
CTIF FCR Ni1	1.27	1.63	0.71	0.41	0.06	0.02	16.50	26.20

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
--------	---	----	----	---	---	----	----	----	----	----	----	----	----	---	---

CAST IRON MUSHROOMS

CONTINUED FROM THE PREVIOUS PAGE

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF F019	0.0005	.
CTIF F012
CTIF F08
CTIF FCR7
CTIF F06
CTIF F010
CTIF NH3
CTIF F011
CTIF F018	0.0040
CTIF NH7-1
CTIF FCR5
CTIF FT2-1
CTIF NiMo1
CTIF FL7	(0.0266)	(0.010)	.	(0.010)	.	0.0035
CTIF FT3
CTIF NH7-2
CTIF F05
CTIF NH9
CTIF NR Cu1
CTIF FL6	.	0.008
CTIF FL10	(0.022)	.	(0.012)	(0.004)	.	.	(0.018)	(0.002)	(0.032)	(0.001)	(0.029)
CTIF FFA 1	0.0109	0.0125
CTIF NR 8S
CTIF F017
CTIF FAL 1
CTIF NR 3L
CTIF NH1
CTIF NH8
CTIF NR 3S
CTIF FT1

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF NR 8L
CTIF NH4
CTIF F04	last of stock
CTIF FCR2
CTIF FL5	.	(0.002)	.	(0.0005)
CTIF FCR Ni3
CTIF NH6
CTIF F09
CTIF FL4	(0.05)	.	.	(0.003)	.	0.007
CTIF NR 1S
CTIF NR 1L
CTIF NH2
CTIF NR Cu2	(0.0079)
CTIF NR 4S
CTIF FCR4
CTIF FCR1
CTIF F07
CTIF NR 4L
CTIF NR 2S
CTIF NH5
CTIF FL3	0.008
CTIF NR 4G
CTIF NR 2G	0.27
CTIF FL2	.	.	.	(0.0135)
CTIF FL1
CTIF F01	last of stock
CTIF FCR Ni2
CTIF NR Cu3
CTIF NR 6S
CTIF NR 5L
CTIF NR 6L
CTIF NR 5S
CTIF FCR6
CTIF FCR Nil

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
--------	----	---	----	----	----	---	----	----	----	----	----

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
1.0812		ECRM 191-2D	15-5PH		ECRM 273-1D	314		IMZ 166A
1.2344		ECRM 271-1D	15-5PH		IARM 22C	316	17025	BS 316C
1.2367		HRT FE2012-H	17-4PH		13X PH2	316		IARM 5H
1.4435, 1.4436		JK 27B	17-4PH		13X PH17400	316		IARM 5i
1.4765		ECRM 299-1D	17-4PH		BS 17-4PHA	316		NILAB 500HAD
1.5415		HRT FE2012-N	17-4PH		BS 17-4PHB	316		SRM 1155A
1.6587		HRT FE2013-N	17-4PH		SRM C2400	316 H		CT 316
1.7149 20MnCrS5		ECRM 187-2D	17-7PH		13X PH17700	316 H		IARM 339A
1.7160		ECRM 194-1D	17-7PH 25(preceded 17025)		BS 192	316 L		13X 31603
1.8550		ECRM 129-3D	17-7PH 25(preceded 17025)		BS 192A	316 L	17025	BS 316D
1.8519		HRT FE2010-N	17-7PH		IARM 152C	316 L	17025	BS 316E
1.8928		ECRM 194-2D	182FM		BS 150	316 L		CZ SL-2A
1005	17025	BS LC-6	18Cr2Ni12Mn		CT ISO035A	316 L		IARM 163E
1005		ECRM 064-2D	201		BS 191	316 L		SS 466/2
1005		RM Fe 1/4	201		SRM 1297	316 Ti		ECRM 284-2D
1005		SRM 1765	20Cb3		BS 187A	317 L		BS 317L
1005		SRM 1766	20Cb3		CT 20 Cb-3	317 L	25(pre-17025)	BS 9941
1005		SS 111/1	20MoCr4		ECRM 197-1D	317 L	25(pre-17025)	BS 9942
1006		BS XCCS	2101		IARM 292A	317 L		IARM 153C
1008		ECRM 057-2D	21Cr6Ni9Mn		CT ISO129A	318	17025	BS 2205
1009		IMZ 71	2205	17025	BS 2205	321		13X 32100
100C6		IRSID 1747	2205		IARM 212D	321		BS 321C
1010		IMZ 111	2304		IARM 317A	321		BS 85D
1010		IRSID 1665	2507		IARM 301B	321		IARM 6i
1011		IMZ 73	253 MA	25(pre-17025)	BS 253	321		IARM 6J
1016	17025	BS 1016	253 MA		IARM 316A	321		SRM 1171
1017		IMZ 112	254 SMO		13X 31254	321		SS 465/1
1017		IRSID 1664	254 SMO		IARM 302B	321 - Ti		IMZ 152
1018		12X 10180B	254 SMO		NILAB 501HAD	32750		13X NSA13
1018		12X 10180C	255, Duplex		IARM 239B	330		IARM 7C
1018	17025	BS 1018	255, Duplex		IARM 239C	3310		BS 1972
1018	17025	BS 2931B	300M		12X 44220	347		13X 34700
1018		ECRM 087-1D	300M	17025	BS 300	347		BS 347A
1020	17025	BS 1020	300M		IARM 340A	347		BS 347B
1026	17025	BS 1026	301		IARM 289A	347		IARM 8G
1026		IARM 359A	301		IRSID 1819	347		IARM 8H
1030	17025	BS 1030	302		IARM 241D	347		IARM 8i
1030		IARM 209D	302 HQ		IARM 234C	347 H		BS 87F
1033		IRSID 1663	303		13X 30300	348		SRM 1172
1035		BS 1035	303	17025	BS 303	355	17025	BS 355
1035		IRSID 1645	303		CT 303	355		IARM 335A
1035		IARM 360A	303		CZ SP-1A	35MV7		IRSID 1750
1039		IRSID 1637	303 Se		IARM 253A	405		SRM 1295
1040		12X 10400	303 Se		IARM 253B	409 + Cr		NCS HS20743
1040	17025	BS 3941	304		IARM 2H	410	25(pre-17025)	BS 0021
1040		IARM 210D	304 H		13X NSB1	410	17025	BS 410C
1040		IRSID 1657	304 H		CT 304	410		CT 410
1042		IRSID 1656	304 H		SS 468/1	410		CT X23576
1042		NM EN-8	304 H		VS LG61	410 + Mo		ECRM 296-1D
1043		IRSID 1652	304 L	17025	BS 304	410 + Mo		IMZ 161
1045		BS 56E	304 L	17025	BS 304A	410 Cb		CT X68890
1045	17025	BS 56H	304 L	17025	BS 304B	410 H		13X 41001
1045		IARM 200D	304 L		BS SS3951	410, F6NM	25(pre-17025)	BS 0022
1045		IPT 503	304 L		IARM 162D	4130	17025	BS 4130
1050		IARM 254A	304 L		ECRM 287-1D	4130		IARM 143F
1055		NM 3405.01	304 L		ECRM 292-1D	4130		IPT 501
1060		IARM 373A	304 L		IARM 162C	4130		SRM 1225
1069		ECRM 059-2D	304 L		SS 463/1	4140		12X 41400
1078		ECRM 056-2D	305		CT 305	4140	25(pre-17025)	BS 1962
1078		SRM 1224	305		CT X52353	4140		IARM 30H
1090		SS 602/2	305		ECRM 297-1D	4140		IARM 30J
1095		SRM 1227	308		DSZU C017	4140 Bi		BS 4140A
1117	25(preceded 17025)	BS 3993	309		13X 30908	4140 Bi		BS 4140B
1117		BS 65C	309		BS 82D	41L40MOD	17025	BS 70B
1117		IARM 29E	309		BS 82E	41L40MOD		BS 70C
1118		IARM 307A	309		IARM 3E	4150 Bi & S		BS 4150MOD
1140 P		BS 52D	310		13X 31008	4150 S	17025	BS 42
1141		BS 66B	310		BS 83G	4150 S		BS 42A
1141		IARM 348A	310	25(pre-17025)	BS 9841	416		BS 90F
1144	17025	BS 1144	310	25(pre-17025)	BS 9842	416	17025	BS 416
1144	17025	BS 1144A	310		CZ SL-3A	416		CT 416
1144		IARM 199C	310		IARM 4E	416		IARM 10D
11L17	17025	BS 75F	310		IARM 4F	416		SRM 1223
11L17	17025	BS 75G	310		IARM 4G	416 H		13X 41600
1215	17025	BS 66L	310		SS 464/1	416 Se		BS 151
1215		IARM 206B	3115		BS XCCT	41CAD7		IRSID 1749
12L14	17025	BS 74C	314		IMZ 165	41L40	17025	BS 70B
12L14		IARM 183C				41L50	17025	BS 72B
12Mn18Cr		BS 193				42		CT ISO138A
1345		BS XCCV				42		CT ISO139A
13-8PH		13X PH13800				420		BS SS4951
13-8PH		BS 184A				420		BS SS4952
13-8PH		CT X92834				420		ECRM 272-1D
1429		ECRM 058-2D				420		IARM 154B
1513		IMZ 76				420		IARM 154C
1526 MOD		SRM 1269				420		SS 469
1541		IARM 349A				420 F		BS 152
1541		IPT 504				420 F S		IARM 352A
1541		IRSID 1648				422		13X 42200
1544		IRSID 1644				422	17025	BS 422
15-5PH		BS 185A				422		IARM 205D
15-5PH		BS 9621				430		BS 430
15-5PH		BS 9622				430		IARM 11D
						430		NCS HS20742

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
430 F		BS 153	CA6NM		HRT FE2009-H	Invar 42		14X 94100
430 F		BS 154	CA6NM		IARM 327A	ISO 898-1		SS 457/2
430 F S		IARM 355A	CD3MN		13X NSA5		17025	BS 160A
431	17025	BS 431	CD3MN		ECRM 298-1D	KOVAR		IARM 98B
431		BS 92B	CD6MN		VS LG58	L-2, 6150		BS 43A
431		IARM 12C	CF-3		IRSID 1820	L-6	17025	BS 39B
431		HRT FE2010-H	CLA1		IARM 164A	L-6		IARM 43B
431		SRM 1219	CLA11		IARM 180A	LDX2101		13X 32101
4320		BS 3961	CLA5		IARM 168A	LF-2		BS 2931B
4330 MOD		BS 4330V	CLA9		IARM 172A	LF-2	17025	BS LF2B
4330 MOD		IARM 330B	CPM15V	17025	BS PM15	LF-2		ECRM 096-
4340	17025	BS 4340	Custom 450	25(pre-17025)	BS 9811	LF-2		SS 601/2
4340	17025	BS 4340A	Custom 450	25(pre-17025)	BS 9812	LF-2		BS LF3
4340		IARM 31G	Custom 450		CT 450	LF-3		CT M1
440 C		13X 44004	Custom 450		IARM 15B	M-1		IARM 304A
440 C	17025	BS 93F	Custom 455		BS SS1961	M-1		CT M10
440 C		IARM 13D	Custom 455		BS SS1962	M-10		IARM 324A
440 F		BS 155	Custom 455		CT 455	M-10		13X 64152
440 F Se		BS 156	Custom 455		IARM 16C	M-152		IARM 291A
440 F Se		IARM 353A	Custom 465		CT ISOL23A	M-152		CT M2
446		BS 94C	Custom 630		CT 630	M-2		IARM 44C
450		IARM 15C	D-2		BS 37G	M-2		SRM 1157
455		13X 45500	D-2		CT D2	M-2		IARM 320A
446		IARM 14C	D-2		IARM 41D	M-35		IARM 251A
4615		BS 3962	D-3, D-4		ECRM 288-1D	M-4		SS 487/1
4620		BS 4620	D-6	17025	BS D-6	M-42		BS M-47
4620		BS 51F	D6-AC		IARM 299A	M-47	17025	BS M-50
4620		IARM 33D	Duplex		13X NSA9	M-50	17025	IARM 306B
465		13X 46500	Duplex	17025	BS 2205	M-50		CT M7
465		IARM 354A	Duplex		IMZ 163A	M-7		CT 250
4820	17025	BS 4820A	Duplex		IMZ 164	Maraging 250		CT 300
4820		IARM 155F	E52100		BS 2952	Maraging 300		BS 161A
5160		IMZ 116	E52100		BS 53G	MaragingA538C 25(pre17025)		BS PP20
6150		BS 4941	E52100		IARM 49D	Mold Steel	17025	IARM 305B
6150		IARM 34C	E52100		IARM 49E	NIT 135M		BS 68B
6418		BS 6418	E52100 Bi		BS 53MOD	Nitriding 135G		BS 68E
6418		BS 69B	Elect./ Magnetic		SRM 1159	Nitriding 135G 17025		13X NSC6
6526		BS 9-4-30	Electrolytic		SRM 1265A	Nitronic 40		BS 190
709		CT X67975	F-11		BS 45A	Nitronic 40		IARM 19C
800	17025	BS 800	F-11	17025	BS 45B	Nitronic 50		BS 180A
8620		BS 8620A (XRF)	F-2		CT X27081	Nitronic 50	17025	BS 180B
8620	17025	BS 8620E	F-22	17025	BS 46B	Nitronic 50		IARM 17D
8620		BS 8620F	F-22	25(preceeded 17025)	BS 1982	Nitronic 60		13X 21800
8620		IPT 502	F-22		SRM 1270	Nitronic 60		BS 181A
86L20 25(preceeded 17025)		BS 73B	F-22 + Cr		HRT FE2009-N	Nitronic 60		BS 181B
86L20		BS 73C	F-5		BS 47A	Nitronic 60	17025	IARM 214A
86L20		IARM 182B	F-5		BS 47B	NMS 100		IARM 295A
8740	17025	BS 67C	F-5		IARM 37C	NMS 140		IARM 294A
8740		IARM 252C	F-51	17025	BS 2205	NMS J38		BS 35D
8740		IARM 252D	F-9	17025	BS 48B	O-1	17025	CT O1
8740		IARM 252E	F-91	25(preceeded 17025)	BS 9905	O-1		BS 41
8740		IARM 252F	F-91	17025	BS 9905A	O-6	17025	BS 41A
904L		13X NSA12	Ferallium 255	17025	BS 179B	O-6	25(preceeded 17025)	IARM 45A
904L		ECRM 295-1D	Ferallium 255	17025	BS 179C	O-6		IARM 45B
9310		BS 58C	Greek Ascoloy		BS 183A	P-6, HY100		BS 1972
9310		BS 58E	Greek Ascoloy		IARM 20B	P-20		BS 55G
9325	17025	BS 9325A	Greek Ascoloy		IARM 20C	PP-20	17025	BS PP20
9-4-30		IARM 341A	H-10		BS 49	Permendur 2V		IARM 326A
A-10		BS A-10	H-11		ECRM 276-2D	RA330		BS 86F
A-11		BS 10V	H-11		IARM 255A	S-1		BS 33D
A-11	17025	BS A-11	H-11		IARM 255B	S-1		BS 33E
A-106 Gr B		SRM 1228	H-11		IMZ 173	S-1		IARM 46B
A-193 B16		BS 4942	H-13	17025	BS H-13	S-5		BS 38C
A-193 B16	17025	BS 4942A	H-13		CT H13	S-5		IARM 47B
A-2		BS 36D	H-13		IARM 42C	S-7		IARM 259A
A-2		CT A2	H-13		IMZ 174	S-7		SRM 1772
A-2		IARM 39B	H-19	17025	BS H-19	SA213-T22		IMZ 159
A-2		IARM 39C	HC 250+V		SRM C1290	SA213-T22		IMZ 169
A-20		BS 187C	High Perm		CT ISO124A	SA213-T22		BS 20E
A-242		IPT 500	High Perm		CT ISO136A	SAE G2500		IARM 268B
A-242 Mod		SRM C1285	High Perm 49		CT ISO141A	STA 361		14X HS1
A-286		BS 188A	HSLA 100		SRM 1271	T-1		BS 30D
A-286	17025	BS 188B	HY 130		SRM 1226	T-1		IARM 48C
A-286		SRM 1230	HY 80		SRM 1286	T-4		IARM 281A
A-36	17025	BS 2931B	Hy-Tuff		IARM 342A	T-15	17025	BS TS15
A-36		IARM 213C	Invar		14X 93603	VM12		IMZ 196
A-36		IARM 213D	Invar-36 + Se		BS 186A	W-5		14X 72305
A-36		SRM 1767	Invar-36 + Se		IARM 24B	Z30C13		IRSID 1825
A-485-1		BS A485-1				Zeron 100, Duplex		13X NSA8
A-6		BS 40B				Zeron 100, Duplex		IARM 319A
A-6		IARM 40B						
A-6		IARM 40C						
A706-60		IARM 380A						
A706-60		IARM 380B						
A706-80		IARM 381A						
Aermet 100		CT ISO045A						
Aermet 100		IARM 242A						
AL6XN	17025	BS 189A						
AL6XN		IARM 157D						
C-.5Mo		BS 3952						
C-.5Mo		IARM 229B						
C-250		IARM 308A						
C-350		IARM 309A						

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S
1005	<0.06	<0.35	<0.03	<0.05
1006	<0.08	0.25-0.40	<0.03	<0.05
1008	<0.10	0.30-0.50	<0.03	<0.05
1009	<0.15	<0.60	<0.03	<0.05
1010	0.08-0.13	0.30-0.60	<0.03	<0.05
1011	0.09-0.14	0.60-0.90	<0.03	<0.05
1012	0.10-0.15	0.30-0.60	<0.03	<0.05
1013	0.11-0.16	0.50-0.80	<0.03	<0.05
1015	0.13-0.18	0.30-0.60	<0.03	<0.05
1016	0.13-0.18	0.60-0.90	<0.03	<0.05
1017	0.15-0.20	0.30-0.60	<0.03	<0.05
1018	0.15-0.20	0.60-0.90	<0.03	<0.05
1019	0.15-0.20	0.70-1.00	<0.03	<0.05
1020	0.18-0.23	0.30-0.60	<0.03	<0.05
1021	0.18-0.23	0.60-0.90	<0.03	<0.05
1022	0.18-0.23	0.70-1.00	<0.03	<0.05
1023	0.20-0.25	0.30-0.60	<0.03	<0.05
1025	0.22-0.28	0.30-0.60	<0.03	<0.05
1026	0.22-0.28	0.60-0.90	<0.03	<0.05
1029	0.25-0.31	0.60-0.90	<0.03	<0.05
1030	0.28-0.34	0.60-0.90	<0.03	<0.05
1033	0.29-0.36	0.70-1.00	<0.03	<0.05
1034	0.32-0.38	0.50-0.80	<0.03	<0.05
1035	0.32-0.38	0.60-0.90	<0.03	<0.05
1037	0.32-0.38	0.70-1.00	<0.03	<0.05
1038	0.35-0.42	0.60-0.90	<0.03	<0.05
1039	0.37-0.44	0.70-1.00	<0.03	<0.05
1040	0.37-0.44	0.60-0.90	<0.03	<0.05
1042	0.40-0.47	0.60-0.90	<0.03	<0.05
1043	0.40-0.47	0.70-1.00	<0.03	<0.05
1044	0.43-0.50	0.30-0.60	<0.03	<0.05
1045	0.43-0.50	0.60-0.90	<0.03	<0.05
1046	0.43-0.50	0.70-1.00	<0.03	<0.05
1049	0.46-0.53	0.60-0.90	<0.03	<0.05
1050	0.48-0.55	0.60-0.90	<0.03	<0.05
1053	0.48-0.55	0.70-1.00	<0.03	<0.05
1055	0.50-0.60	0.60-0.90	<0.03	<0.05
1059	0.55-0.65	0.50-0.80	<0.03	<0.05
1060	0.55-0.65	0.60-0.90	<0.03	<0.05
1064	0.60-0.70	0.50-0.80	<0.03	<0.05
1065	0.60-0.70	0.60-0.90	<0.03	<0.05
1069	0.65-0.75	0.40-0.70	<0.03	<0.05
1070	0.65-0.75	0.60-0.90	<0.03	<0.05
1074	0.70-0.80	0.50-0.80	<0.03	<0.05
1078	0.72-0.85	0.30-0.60	<0.03	<0.05
1080	0.75-0.88	0.60-0.90	<0.03	<0.05
1084	0.83-0.93	0.60-0.90	<0.03	<0.05
1085	0.80-0.94	0.70-1.00	<0.03	<0.05
1086	0.80-0.93	0.30-0.50	<0.03	<0.05
1090	0.85-0.98	0.60-0.90	<0.03	<0.05
1095	0.90-1.03	0.30-0.50	<0.03	<0.05
Number	C	Mn	P	S

CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si
1513	0.10-0.16	1.10-1.40	<0.03	<0.05	.
1522	0.18-0.24	1.10-1.40	<0.04	<0.05	.
1524	0.19-0.25	1.35-1.65	<0.04	<0.05	.
1526	0.22-0.29	1.10-1.40	<0.04	<0.05	.
1527	0.22-0.29	1.20-1.50	<0.04	<0.05	.
1533	0.30-0.37	1.10-1.40	<0.04	<0.05	.
1534	0.30-0.37	1.20-1.50	<0.04	<0.05	.
1541	0.36-0.44	1.35-1.65	<0.04	<0.05	.
1544	0.40-0.47	0.80-1.10	<0.04	<0.05	.
1545	0.43-0.50	0.80-1.10	<0.04	<0.05	.
1546	0.44-0.52	1.00-1.30	<0.04	<0.05	.
1548	0.44-0.52	1.10-1.40	<0.04	<0.05	.
1552	0.47-0.55	1.20-1.50	<0.04	<0.05	.
1553	0.48-0.55	0.80-1.10	<0.04	<0.05	.
1566	0.60-0.70	0.85-1.15	<0.04	<0.05	.
1570	0.65-0.75	0.80-1.10	<0.04	<0.05	.
1580	0.75-0.88	0.80-1.10	<0.04	<0.05	.
1590	0.85-0.98	0.80-1.10	<0.04	<0.05	.
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30

Number	C	Mn	P	S	Si
--------	---	----	---	---	----

RESULFURIZED STEEL SPECIFICATIONS

Number	C	Mn	P	S
1108	0.08-0.13	0.50-0.80	<0.04	0.08-0.13
1109	0.08-0.13	0.60-0.90	<0.04	0.08-0.13
1110	0.08-0.13	0.30-0.60	<0.04	0.08-0.13
1116	0.14-0.20	1.10-1.40	<0.04	0.16-0.23
1117	0.14-0.20	1.00-1.30	<0.04	0.08-0.13
1118	0.14-0.20	1.30-1.60	<0.04	0.08-0.13
1119	0.14-0.20	1.00-1.30	<0.04	0.24-0.33
1123	0.20-0.27	1.20-1.50	<0.04	0.06-0.09
1132	0.27-0.34	1.35-1.65	<0.04	0.09-0.13
1137	0.32-0.39	1.35-1.65	<0.03	0.08-0.13
1139	0.35-0.43	1.35-1.65	<0.04	0.13-0.20
1140	0.37-0.44	0.70-1.00	<0.03	0.08-0.13
1141	0.37-0.45	1.35-1.65	<0.03	0.08-0.13
1144	0.40-0.48	1.35-1.65	<0.03	0.24-0.33
1145	0.41-0.49	0.70-1.00	<0.04	0.08-0.13
1146	0.42-0.49	0.70-1.00	<0.04	0.08-0.13
1151	0.48-0.55	0.70-1.00	<0.04	0.08-0.13
1152	0.48-0.55	0.70-1.00	<0.04	0.06-0.09
1211	<0.13	0.60-0.90	0.07-0.12	0.10-0.15
1212	<0.13	0.70-1.00	0.07-0.12	0.16-0.23
1213	<0.13	0.70-1.00	0.07-0.12	0.24-0.33
1215	<0.09	0.75-1.05	0.04-0.09	0.26-0.35

Number	C	Mn	P	S
--------	---	----	---	---

These are specifications,
not samples for sale.

LOW ALLOY STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other
1330	0.28-0.33	1.60-1.90	<0.035	<0.04	0.15-0.35
1335	0.33-0.38	1.60-1.90	<0.035	<0.04	0.15-0.35
1340	0.38-0.43	1.60-1.90	<0.035	<0.04	0.15-0.35
1345	0.43-0.48	1.60-1.90	<0.035	<0.04	0.15-0.35
3140	0.38-0.43	0.70-0.90	<0.04	<0.04	0.15-0.35	1.10-1.40	0.55-0.75	.	.	.
4023	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4027	0.25-0.30	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4028	0.25-0.30	0.70-0.90	<0.035	0.035-0.050	0.15-0.35	.	.	0.20-0.30	.	.
4037	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4047	0.45-0.50	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4118	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.08-0.15	.	.
4120	0.18-0.23	0.80-1.20	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.15-0.25	.	.
4121	0.18-0.23	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.45-0.65	0.15-0.25	.	.
4130	0.28-0.33	0.40-0.60	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4135	0.33-0.38	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4137	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4140	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L40	0.38-0.43	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4142	0.40-0.45	0.45-0.65	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4145	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4147	0.45-0.50	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4150	0.48-0.53	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L50	0.48-0.53	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4320	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	0.40-0.60	0.20-0.30	.	.
4340	0.38-0.43	0.60-0.80	<0.035	<0.04	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
4615	0.13-0.18	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4617	0.15-0.20	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4620	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4715	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.70-1.00	0.45-0.65	0.45-0.65	.	.
4720	0.17-0.22	0.50-0.70	<0.035	<0.04	0.15-0.35	0.90-1.20	0.35-0.55	0.15-0.25	.	.
4815	0.13-0.18	0.40-0.60	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
4820	0.18-0.23	0.50-0.70	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
50B46	0.44-0.49	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.20-0.35	.	.	B: 0.0005-0.003
5120	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51L20	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	0.15-0.35	.
5130	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	.
5132	0.30-0.35	0.60-0.80	<0.035	<0.04	0.15-0.35	.	0.75-1.00	.	.	.
5140	0.38-0.43	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5160	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51B60	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	B: >0.0005
6150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	V: >0.15
8615	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8617	0.15-0.20	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8620	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
86L20	0.18-0.21	0.70-0.90	<0.035	0.02-0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	0.15-0.35	.
8622	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8630	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8637	0.35-0.40	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8640	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8645	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8720	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8740	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8822	0.20-0.25	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.30-0.40	.	.
9259	0.56-0.64	0.75-1.00	<0.035	<0.04	0.70-1.10	.	0.45-0.65	.	.	.
9260	0.56-0.64	0.75-1.00	<0.035	<0.04	1.80-2.20
E4340	0.38-0.43	0.65-0.85	<0.025	<0.025	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
E51100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	0.90-1.15	.	.	.
E52100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	1.30-1.60	.	.	.
E9310	0.08-0.13	0.45-0.65	<0.025	<0.025	0.15-0.35	3.00-3.50	1.00-1.40	0.08-0.15	.	.
F-11	0.10-0.20	0.30-0.80	<0.04	<0.04	0.50-1.00	.	1.00-1.50	0.44-0.65	.	.
F-22	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	2.00-2.50	0.90-1.10	.	.
F-5	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	4.00-6.00	0.45-0.65	.	.
F-9	<0.15	0.30-0.60	<0.03	<0.03	0.50-1.0	.	8.00-10.00	0.90-1.10	.	.
F-91	0.08-0.12	0.30-0.60	<0.02	<0.01	0.20-0.50	<0.40	8.00-9.50	0.85-1.05	.	Al: <0.04 N: 0.03-0.07
F-91	continued									Nb: 0.06-0.10 V: 0.18-0.25
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30
LF3	<0.20	<0.90	<0.035	<0.04	0.20-0.35	3.25-3.75
Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other

These are specifications,
not samples for sale.

TOOL STEEL SPECIFICATIONS

* notes optional chemistry

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
A-2	0.95-1.05	<1.00	<0.03	<0.03	<0.50	.	4.75-5.50	.	0.90-1.40	0.15-0.50	.	.
A-4	0.95-1.05	1.80-2.20	<0.03	<0.03	<0.50	.	0.90-2.20	.	0.90-1.40	.	.	.
A-6	0.65-0.75	1.80-2.50	<0.03	<0.03	<0.50	.	0.90-1.20	.	0.90-1.40	.	.	.
A-7	2.00-2.85	<0.80	<0.03	<0.03	<0.50	.	5.00-5.75	.	0.90-1.40	3.90-5.15	0.50-1.50	.
A-8	0.50-0.60	<0.50	<0.03	<0.03	0.75-1.10	.	4.75-5.50	.	1.15-1.65	.	1.00-1.50	.
A-9	0.45-0.55	<0.50	<0.03	<0.03	0.95-1.15	1.25-1.75	4.75-5.50	.	1.30-1.80	0.80-1.40	.	.
A-10	1.25-1.50	1.60-2.10	<0.03	<0.03	1.00-1.50	1.55-2.05	.	.	1.25-1.75	.	.	.
A-11	2.45	0.50	.	.	0.90	.	5.25	.	1.30	9.75	.	.
D-2	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	<1.00	0.70-1.20	<1.10	.	.
D-3	2.00-2.35	<0.60	<0.03	<0.03	<0.60	.	11.00-13.50	.	.	<1.00	<1.00	.
D-4	2.05-2.40	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	.	0.70-1.20	<1.00	.	.
D-5	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	2.50-3.50	0.70-1.20	<1.00	.	.
D-7	2.15-2.50	<0.60	<0.03	<0.03	<0.60	.	11.50-13.50	.	0.70-1.20	3.80-4.40	.	.
H-10	0.35-0.45	0.25-0.70	<0.03	<0.03	0.80-1.20	.	3.00-3.75	.	2.00-3.00	0.25-0.75	.	.
H-11	0.33-0.43	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.60	0.30-0.60	.	.
H-12	0.30-0.40	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.25-1.75	<0.50	1.00-1.70	.
H-13	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.75	0.80-1.20	.	.
H-14	0.35-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	.	.	4.00-5.25	.
H-19	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.00-4.75	4.00-4.50	0.30-0.55	1.75-2.20	3.75-4.50	.
H-21	0.26-0.36	0.15-0.40	<0.03	<0.03	0.15-0.50	.	3.00-3.75	.	.	0.30-0.60	8.50-10.00	.
H-22	0.30-0.40	0.15-0.40	<0.03	<0.03	0.15-0.40	.	1.75-3.75	.	.	0.25-0.50	10.00-11.75	.
H-23	0.25-0.35	0.15-0.40	<0.03	<0.03	0.15-0.60	.	11.00-12.75	.	.	0.75-1.25	11.00-12.75	.
H-24	0.42-0.53	0.15-0.40	<0.03	<0.03	0.15-0.40	.	2.50-3.50	.	.	0.40-0.60	14.00-16.00	.
H-26	0.45-0.55	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-4.50	.	.	0.75-1.25	17.25-19.00	.
H-42	0.55-0.70	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
L-2	0.45-1.00	0.10-0.90	<0.03	<0.03	<0.50	.	0.70-1.20	.	<0.25	0.10-0.30	.	.
L-6	0.65-0.75	0.25-0.80	<0.03	<0.03	<0.50	1.25-2.00	0.60-1.20	.	<0.50	.	.	.
M-1	0.78-0.88	0.15-0.40	<0.03	<0.03	0.20-0.50	.	3.50-4.00	.	8.20-9.20	1.00-1.35	1.40-2.10	.
M-2	0.78-1.05	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
M-3.1	1.00-1.10	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.25-2.75	5.00-6.75	.
M-3.2	1.15-1.25	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.75-3.25	5.00-6.75	.
M-4	1.25-1.40	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.75	.	4.25-5.50	3.75-4.50	5.25-6.50	.
M-6	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	11.00-13.00	4.50-5.50	1.30-1.70	3.75-4.75	.
M-7	0.97-1.05	0.15-0.40	<0.03	<0.03	0.20-0.55	.	3.50-4.00	.	8.20-9.20	1.75-2.25	1.40-2.10	.
M-10	0.84-1.05	0.10-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	7.75-8.50	1.80-2.20	.	.
M-30	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.25	4.50-5.50	7.75-9.00	1.00-1.40	1.30-2.30	.
M-33	0.85-0.92	0.15-0.40	<0.03	<0.03	0.25-0.55	.	3.50-4.00	7.75-8.75	9.00-10.00	1.00-1.35	1.30-2.10	.
M-34	0.85-0.92	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.00	7.75-8.75	7.75-9.20	1.90-2.30	1.40-2.10	.
M-36	0.80-0.90	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	7.75-8.75	4.50-5.50	1.75-2.25	5.50-6.50	.
M-41	1.05-1.15	0.20-0.60	<0.03	<0.03	0.15-0.50	.	3.75-4.50	4.75-5.75	3.25-4.25	1.75-2.25	6.25-7.00	.
M-42	1.05-1.15	0.15-0.40	<0.03	<0.03	0.15-0.65	.	3.50-4.25	7.75-8.75	9.00-10.00	0.95-1.35	1.15-1.85	.
M-46	1.22-1.30	0.20-0.40	<0.03	<0.03	0.40-0.65	.	3.70-4.20	7.80-8.80	8.00-8.50	3.00-3.30	1.90-2.20	.
M-48	1.50	3.75	9.00	5.25	3.10	10.0	.
M-52	0.90	4.00	.	4.00	2.00	1.25	.
M-61	1.60	4.00	.	6.50	5.00	12.0	.
M-62	1.30	3.75	.	10.5	2.00	6.25	.
O-1	0.85-1.00	1.00-1.40	<0.03	<0.03	<0.50	.	0.40-0.60	.	.	<0.30	0.40-0.60	.
O-2	0.85-0.95	1.40-1.80	<0.03	<0.03	<0.50	.	<0.35	.	<0.30	<0.30	.	.
O-6	1.25-1.55	0.30-1.10	<0.03	<0.03	0.55-1.50	.	<0.30	.	0.20-0.30	.	.	.
O-7	1.10-1.30	<1.00	<0.03	<0.03	<0.60	.	0.35-0.85	.	<0.30	<0.40	1.00-2.00	.
P-20	0.28-0.40	0.60-1.00	<0.03	<0.03	0.20-0.80	.	1.40-2.00	.	0.30-0.55	.	.	.
P-21	0.18-0.22	0.20-0.40	<0.03	<0.03	0.20-0.40	4.00-4.25	0.20-0.30	.	.	0.15-0.25	.	Al: 1.05-1.25
P-6	0.05-0.15	0.35-0.70	<0.03	<0.03	0.10-0.40	3.25-3.75	1.25-1.75
S-1	0.40-0.55	0.10-0.40	<0.03	<0.03	0.15-1.20	.	1.00-1.80	.	<0.50	0.15-0.30	1.50-3.00	.
S-2	0.40-0.55	0.30-0.50	<0.03	<0.03	0.90-1.20	.	0.90-1.20	.	0.30-0.60	<0.50	.	.
S-4	0.50-0.65	0.60-0.95	<0.03	<0.03	1.75-2.25	.	<0.35	.	.	<0.35	.	.
S-5	0.50-0.65	0.60-1.00	<0.03	<0.03	1.75-2.25	.	<0.35	.	0.20-1.35	<0.35	.	.
S-6	0.40-0.50	1.20-1.50	<0.03	<0.03	2.00-2.50	.	1.20-1.50	.	0.30-0.50	0.20-0.40	.	.
S-7	0.45-0.55	0.20-0.80	<0.03	<0.03	0.20-1.00	.	3.00-3.50	.	1.30-1.80	0.20-0.30*	.	.
T-1	0.65-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	.	.	0.90-1.30	17.25-18.25	.
T-15	1.50-1.60	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-5.00	4.75-5.25	<1.00	4.50-5.25	11.75-13.00	.
T-4	0.70-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	0.80-1.20	17.50-19.00	.
T-5	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-5.00	7.00-9.50	0.50-1.25	1.80-2.40	17.50-19.00	.
T-6	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	4.00-4.75	11.00-13.00	0.40-1.00	1.50-2.10	18.50-21.00	.
T-8	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	1.80-2.40	13.25-14.75	.
W-1	0.70-1.50	0.10-0.40	<0.025	<0.025	0.10-0.40	<0.20	<0.15	.	<0.10	<0.10	<0.15	Cu: <0.20
W-2	0.85-1.50	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	<0.15	.	<0.10	0.15-0.35	<0.15	Cu: <0.20
W-5	1.05-1.15	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	0.40-0.60	.	<0.10	<0.10	<0.15	Cu: <0.20

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
--------	---	----	---	---	----	----	----	----	----	---	---	-------

These are specifications,
not samples for sale.

STAINLESS AND HIGH ALLOY STEEL SPECIFICATIONS

* notes optional chemistry

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	N	Nb	Other
13-8PH	<0.05	<0.20	<0.01	<0.008	<0.10	.	7.50-8.50	12.25-13.25	2.00-2.50	<0.01	.	Al: 0.90-1.35
15-5PH	<0.07	<1.00	<0.04	<0.03	<1.00	2.50-4.50	3.50-5.50	14.00-15.50	.	.	0.15-0.45	
17-4PH	<0.07	<1.00	<0.04	<0.03	<1.00	3.00-5.00	3.00-5.00	15.00-17.50	.	.	0.15-0.45	
201	<0.15	5.5-7.5	<0.060	<0.03	<1.00	.	3.50-5.50	16.00-18.00	.	<0.25	.	
202	<0.15	7.5-10.0	<0.060	<0.03	<1.00	.	4.00-6.00	17.00-19.00	.	<0.25	.	
301	<0.15	<2.00	<0.045	<0.03	<1.00	.	6.00-8.00	16.00-18.00	.	.	.	
302	<0.15	<2.00	<0.045	<0.03	<1.00	.	8.00-10.00	17.00-19.00	.	.	.	
302B	<0.15	<2.00	<0.045	<0.03	2.00-3.00	.	8.00-10.00	17.00-19.00	.	.	.	
303	<0.15	<2.00	<0.20	>0.15	<1.00	.	8.00-10.00	17.00-19.00	<0.60*	.	.	Zr: <0.60*
304	<0.08	<2.00	<0.045	<0.03	<1.00	.	8.00-10.50	18.00-20.00	.	.	.	
304L	<0.03	<2.00	<0.045	<0.03	<1.00	.	8.00-12.00	18.00-20.00	.	.	.	
305	<0.12	<2.00	<0.045	<0.03	<1.00	.	10.00-13.00	17.00-19.00	.	.	.	
308	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-12.00	19.00-21.00	.	.	.	
309	<0.20	<2.00	<0.045	<0.03	<1.00	.	12.00-15.00	22.00-24.00	.	.	.	
310	<0.25	<2.00	<0.045	<0.03	<1.50	.	19.00-22.00	24.00-26.00	.	.	.	
314	<0.25	<2.00	<0.045	<0.03	1.50-3.00	.	19.00-22.00	23.00-26.00	.	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316L	<0.03	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
321	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-12.00	17.00-19.00	.	.	.	Ti: >5xC
347	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	
348	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	Ta: <0.10
384	<0.08	<2.00	<0.045	<0.03	<1.00	.	17.00-19.00	15.00-17.00	.	.	.	
385	<0.08	<2.00	<0.045	<0.03	<1.00	.	14.00-16.00	11.50-13.50	.	.	.	
403	<0.15	<1.00	<0.04	<0.03	<0.50	.	.	11.50-13.00	.	.	.	
405	<0.08	<1.00	<0.04	<0.03	<1.00	.	.	11.50-14.50	.	.	.	Al: 0.10-0.30
409	<0.08	<1.00	<0.04	<0.01	<1.00	.	<0.50	10.50-11.75	.	.	.	Ti: 6\mtC-0.75
410	<0.15	<1.00	<0.04	<0.03	<1.00	.	.	11.50-13.50	.	.	.	
414	<0.15	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	11.50-13.50	.	.	.	
416	<0.15	<1.25	<0.06	>0.15	<1.00	.	.	12.00-14.00	<0.60*	.	.	Zr: <0.60*
420	>0.15	<1.00	<0.04	<0.03	<1.00	.	.	12.00-14.00	.	.	.	
422	0.20-0.25	<1.00	<0.04	<0.03	<0.75	<0.50	0.50-1.00	11.00-12.50	0.75-1.25	.	.	V: 0.15-0.30
422	continued											W: 0.75-1.25
430	<0.12	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	.	.	.	
430F	<0.12	<1.25	<0.06	>0.15	<1.00	.	.	16.00-18.00	<0.60*	.	.	Zr: <0.60*
431	<0.20	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	15.00-17.00	.	.	.	
440A	0.60-0.75	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440B	0.75-0.95	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440C	0.95-1.20	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
450	<0.05	<1.00	<0.03	<0.03	<1.00	1.25-1.75	5.00-7.00	14.00-16.00	0.50-1.00	.	8\mtC	
455	<0.05	<0.50	<0.04	<0.03	<0.50	1.50-2.50	7.50-9.50	11.00-12.50	<0.50	.	0.10-0.50	Ti: 0.80-1.40
501	>0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
502	<0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
Duplex	<0.05	<3.00	<0.035	<0.03	<1.50	<2.50*	4.00-7.00	18.00-25.00	0.20-5.50	<0.40	.	

These are specifications,
not samples for sale.