

INDEX

- ALLOY LISTING 43
ALLOY SPECIFICATIONS 45
ALLOYED CAST IRON 40
ALUMINUM IN STAINLESS STEEL 19
ALUMINUM IN STEEL 2, 6
ANTIMONY IN STEEL 5
ARSENIC IN STEEL 5
- BISMUTH STEEL 5, 8
BORON IN STAINLESS STEEL 19
BORON IN STEEL
- CALCIUM IN STAINLESS STEEL 19
CALCIUM IN STEEL 6
CARBON STEEL 2, 3, 4
CARBON STEEL SPECIFICATIONS 45
CAST IRON 32, 33, 34, 35, 37, 38, 39, 40, 41, 42
CAST IRON WITH MAGNESIUM 34, 35, 36
COBALT ALLOY 9
COBALT IN STAINLESS STEEL 21
COPPER IN STAINLESS STEEL 20
Cr-Mo STEEL 6, 7
- DUCTILE IRON 33
- EPMA SETS 6
- GRAY IRON 33
- HIGH ALLOY STEEL 31, 32
HIGH ALLOY STEEL SPECIFICATIONS 48
HIGH CHROMIUM CAST IRON 40
- IRON 2
- LEADED STEEL 8
LOW ALLOY STEEL
5, 6, 7, 8, 9, 10, 11, 12, 14, 15, 16
LOW ALLOY STEEL SPECIFICATIONS 46
LOW ALLOY STEEL WITH $0.13\% < C < 0.3\%$ 14
LOW ALLOY STEEL WITH $C < 0.13\%$ 15
LOW ALLOY STEEL WITH $C > 0.3\%$ 11, 12
LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS 13
- MAGNETIC ALLOY 9
MANGANESE STAINLESS STEEL 22
MANGANESE STEEL 8
MARAGING STEEL 21
- NICKEL BINARY 22
NITROGEN IN STEEL 6
NODULAR IRON 33
- PERMENDUR 2V 9
PHOSPHORUS IN STAINLESS STEEL 23
- RESULFURIZED STAINLESS STEEL 23
RESULFURIZED STEEL 9
RESULFURIZED STEEL SPECIFICATIONS 45
- SELENIUM IN STAINLESS STEEL 23
SELENIUM STEEL 5
SET 2, 6, 8, 9, 16, 30, 32
Si-Mo CAST IRON 33
SILICON STEEL 10
SOLUBLE ALUMINUM 2
SOLUBLE BORON 2
STAINLESS STEEL
19, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31
STAINLESS STEEL SPECIFICATIONS 48
STAINLESS STEEL WITH $C < 0.05\%$ 28, 29
STAINLESS STEEL WITH $C > 0.05\%$ 26, 27
STAINLESS STEEL WITH $NI < 5.0\%$ 24, 25
SULFUR IN STAINLESS STEEL 23
- TOOL STEEL 16, 17, 18
TOOL STEEL SPECIFICATIONS 47
TUNGSTEN IN STAINLESS STEEL 21
- WHITE IRON 36
- XRF 2, 6, 8, 9, 16, 30, 32

PURE IRON

= class, where 1 = CRM and 2 = RM

T = total

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	O
1	SRM 1265a	0.0067	0.0057	0.0011	0.0055	0.008	0.0058	0.041	0.007	0.0050	(0.0007)	0.007	.	.
1	BS 50F	0.0064	0.082	0.0066	0.0031	0.016	0.0088	0.016	0.022	0.0017	0.003	0.0023	0.0042	(0.0026)
2	CZ LA-0A	(0.006)	0.045	0.005	0.005	0.0015	0.012	0.028	0.022	(0.0044)	0.0015	0.002	0.0023	.
1	VS RG31	0.0035	0.0010	0.0015	.	0.009	0.010	0.0046	0.0016	0.0003	.	0.0007	.	.
1	IARM 27G	(0.003)	(0.003)	(0.003)	0.0011	(0.07)	0.040	0.045	0.043	(0.002)	(0.0013)	(0.0009)	(0.0003)	0.025
2	TL 1669 *	0.00226	0.0955	0.0137	0.0100	0.0093	0.0217	0.0160	0.0246	0.0011	0.03553T	0.0019	0.0024	.
2	TH 1045D	0.0023	.	.	0.0043	0.0046	.
1	VS RG24/1	0.0022	0.015	0.0027	0.0069	0.017	0.011	0.037	0.037	0.0013	.	0.012	.	.
1	BS LC-6	0.0020	0.469	0.0007	0.0009	0.050	0.0003	0.0057	0.0023	(0.0006)	0.034	0.0021	0.0003	0.0007
1	SRM 1768	0.0010	0.0014	0.0013	0.0003	.	0.0006	0.0014	.	.	0.0024	0.0025	0.002	0.036
1	ECRM 098-1D	0.00051	0.00008	(0.00006)	0.00031	0.00048	.	.	0.00571	0.00085	.	.	0.0024	.
1	ECRM 097-1D	(<0.002)	0.0064	0.0016	0.0022	(<0.01)	0.0020	0.0025	0.0016	(<0.001)	.	0.0037	0.0007	.
1	ECRM 097-2D	.	0.012	0.00538	0.00181	0.00285	0.00793	0.0241	0.0213	0.00370	.	0.0139	0.00294	.

Number	As	B	Mg	Nb	Pb	Sn	Ti	V	W	Units
SRM 1265a	(0.0002)	0.00013	.	.	0.00001	.	(0.0001)	0.0006	.	disc 32 mm Ø x 19 mm
BS 50F	0.0013	(<0.0002)	(<0.0001)	(<0.0002)	(<0.0003)	0.0010	0.0004	(0.0003)	(<0.0050)	disc 35 mm Ø x -7 mm 17025
CZ LA-0A	(0.0015)	.	.	Sb:(0.0007)	(0.001)	(0.001)	0.001	.	.	disc -37 mm Ø x 25 mm
VS RG31	disc -45 mm Ø x -28mm
IARM 27G	(0.0016)	(0.0006)	(0.0002)	(0.002)	(0.002)	(0.001)	<0.005	(0.001)	<0.005	disc 31 mm Ø X 2 or 18 mm
TL 1669 *	0.0017	0.00038	.	0.00046	0.00013	0.0071	0.0504	(0.0006)	.	disc 38 mm Ø x 25 mm
TH 1045D	disc 40 mm Ø x 40 mm
VS RG24/1	0.0010	.	.	disc -45 mm Ø x -28mm
BS LC-6	(<0.0020)	(0.0004)	(0.00003)	(<0.0010)	(<0.0020)	(<0.0020)	0.0006	(<0.0010)	last	disc 39 mm Ø x -7 or -12 mm 17025
SRM 1768	disc 31 mm Ø x 19 mm
ECRM 098-1D	octagon 35 mm Ø x 25 mm
ECRM 097-1D	0.0051	0.0003	.	.	.	(<0.0025)	.	(<0.001)	.	disc 38 mm Ø x 3, 25, or 30 mm
ECRM 097-2D	0.00281	0.00012	Sb:0.00012	Ta:0.00015	Zn:0.00014	0.00043	.	0.00011	0.00386	disc 38 mm Ø x 25 or 30 mm

* TL-1669 also contains in ppm Ca: 1.7, Sb: 4.9, Zn: 2.7

RM CARBON STEEL XRF SET

Part Number: BS CS-10 AVAILABLE INDIVIDUALLY 17025 ~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Co	N	Sn	V
Pure Iron	BS 50F	0.0064	0.082	0.0066	0.0031	0.016	0.0088	0.016	0.022	0.0017	0.003	0.0013	0.0023	0.0042	0.0010	(0.0003)
1008	BS XAAS	0.041	0.430	0.007	0.010	0.045	0.015	0.023	0.020	0.007	0.006	0.005	0.004	0.0037	<0.002	<0.005
1018	BS 2931	0.202	0.75	0.012	0.025	0.23	0.23	0.106	0.154	0.019	0.002	0.007	0.009	0.0119	0.010	0.002
1020	BS 57F	0.196	0.554	0.009	0.027	0.202	0.197	0.070	0.120	0.018	(0.002)	(0.006)	0.007	0.0077	0.008	0.063
1026	BS 4932	0.234	0.76	0.010	0.015	0.25	0.15	0.080	0.144	0.033	(0.001)	(0.005)	0.005	0.0080	0.008	0.060
1035	BS 4931	0.352	0.80	0.011	0.016	0.27	0.217	0.070	0.093	0.024	(0.001)	0.005	0.006	0.0080	0.009	0.058
1040	BS 3941	0.407	0.802	0.016	0.023	0.257	0.053	0.018	0.069	0.0061	0.0019	0.0036	0.0042	0.0069	0.0019	0.0025
1045	BS 56E	0.483	0.72	0.010	0.025	0.24	0.015	0.015	0.021	0.005	0.062	0.0035	0.005	0.0056	(0.0006)	(<0.002)
1095	BS 64C	0.920	0.22	0.015	0.0024	0.22	0.016	0.038	0.261	0.008	(0.005)	.	0.004	0.0084	(0.001)	0.005
1522 (LF2)	BS 2932	0.208	1.20	0.008	0.020	0.186	0.060	0.034	0.077	0.026	0.022	(0.003)	0.004	0.0080	0.005	0.001

CRM CARBON STEEL SET

AVAILABLE IN SET/6 ONLY

38 mm Ø x 30 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Al.Sol	Ti	Ti.Sol	V
NCS HS11719-5	1.19	2.20	0.011	0.013	0.751	0.046	0.164	0.439	0.036	0.034	0.029	0.028	0.0082
NCS HS11719-1	0.963	0.586	0.022	0.010	0.241	0.111	0.206	0.131	0.019	0.017	0.016	0.015	0.035
NCS HS11719-3	0.435	1.14	0.045	0.020	0.163	0.160	0.114	0.086	0.019	0.016	0.024	0.023	0.099
NCS HS11719-4	0.140	1.30	0.084	0.020	0.526	0.276	0.344	0.198	0.160	0.155	0.132	0.128	0.153
NCS HS11719-2	0.042	0.048	0.105	0.0053	0.154	0.411	0.432	0.247	0.296	0.292	0.161	0.154	0.207
NCS HS11719-6	0.0060	0.163	0.0053	0.035	0.014	0.0032	0.013	0.021	0.0021	0.0016	0.0010	(0.0008)	0.363

CRM SOLUBLE ALUMINUM AND SOLUBLE BORON STEEL SET

available in set/6 only as grouped .T = total .S = soluble

37 mm Ø x 30 mm

Number	Al.T	Al.S	B.T	B.S	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo
NCS HS93703-1	0.387	0.381	0.025	0.023	1.08	2.35	0.0057	(0.008)	0.681	0.048	0.028	3.98	0.0047	0.0077
NCS HS93703-2	0.92	0.91	0.0083	0.0080	0.055	0.021	0.027	0.0033	0.827	0.422	1.09	3.09	0.262	1.56
NCS HS93703-3	0.107	0.103	0.0041	0.0037	0.792	1.34	0.013	0.038	1.09	0.532	0.533	2.11	0.488	0.397
NCS HS93703-4	0.083	0.078	0.0050	0.0048	0.475	0.612	0.015	0.015	2.57	0.687	2.01	1.31	0.403	0.977
NCS HS93703-5	(1.29)	(1.27)	0.0017	0.0015	0.651	1.53	0.036	0.0052	0.024	0.236	2.98	0.021	0.094	0.631
NCS HS93703-6	0.64	0.63	0.0033	0.0030	0.246	0.211	0.045	0.0058	0.274	0.092	3.83	0.505	0.145	0.203

Number	As	Bi	Ca	Nb	Pb	Sb	Sn	Ti	V	W	Zr
NCS HS93703-1	0.032	0.0011	0.0009	0.351	0.0016	(0.0001)	0.014	0.473	0.0090	0.293	0.0031
NCS HS93703-2	0.0034	0.0006	0.0010	0.254	0.0008	0.0020	0.0069	0.346	0.376	1.97	0.087
NCS HS93703-3	0.0019	0.0004	0.0010	0.506	0.0007	0.0040	0.054	0.016	0.071	0.755	0.014
NCS HS93703-4	0.056	(0.0002)	(0.0001)	0.167	0.0006	0.0095	0.012	0.035	0.709	1.48	0.069
NCS HS93703-5	0.0064	0.0015	0.0007	0.0057	0.0007	0.010	0.015	0.111	0.231	0.050	0.41
NCS HS93703-6	0.011	(0.0002)	(0.0001)	0.070	0.0011	0.0006	0.017	0.246	0.526	1.04	0.22

CARBON STEEL

CONTINUED ON THE NEXT PAGE

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	B	Ca	Co	Mo
1	IRSID 1660	1.20	0.280	0.014	0.010	0.173	0.059	0.072	(0.026)	(0.009)
1	ECRM 090-1D	1.05	0.226	0.013	0.0095	0.281	0.053	0.053	0.121	0.009
1	SRM 1227	0.97	0.402	0.014	0.026	0.215	0.006	0.007	0.019	0.003	0.003
1	SS 602/2	0.94	0.66	0.023	0.031	0.057	(0.06)	(0.02)	(0.03)	0.096	(0.007)	(0.004)
2	BS 64C	0.920	0.22	0.015	0.0024	0.22	0.016	0.038	0.261	(0.005)	0.004	0.008
2	HRT FE2014-N	0.91	1.97	0.012	(0.004)	0.24	0.01	0.02	0.35	0.016	0.00024	0.01
1	ECRM 056-2D	0.8181	0.5073	0.0103	0.0093	0.2006	0.0129	0.0218	0.0146
1	SRM 1224	0.70	0.41	0.009	0.039	0.173	0.072	0.054	0.071	0.060	0.013
1	VS RG28	0.70	0.84	0.031	0.026	1.161	0.050	0.154	0.135	0.066	0.090
1	VS RG28/1	0.68	0.91	0.031	0.0071	2.36	0.040	0.168	0.194	0.068	0.072	0.104
1	IARM 373A	0.63	0.70	0.0123	0.031	0.22	0.107	0.048	0.096	0.002	.	0.0046	0.0003	0.0005	0.005	0.0176
1	VS UG20/6	0.58	0.473	(0.008)	(0.02)	0.229	0.249	0.360	0.396
1	NM 3405.01	0.57	0.80	0.037	0.048	0.19	.	0.031	0.081
1	SS 435/1	0.52	0.41	0.033	0.031	0.54	.	0.060	0.14
1	SS 435/2	0.49	0.39	0.04	0.042	0.32	.	0.13	0.18	0.011	.
2	BS 56E	0.483	0.72	0.010	0.025	0.24	0.015	0.015	0.021	0.062	.	0.0035	.	(<0.0005)	0.005	0.005
1	IRSID 1636	0.47	0.78	0.029	0.037	0.40	0.135	0.092	(0.060)	(0.007)
1	SS 459/2	0.467	0.909	0.0482	0.0481	0.640	.	.	0.015	(0.013)	.	0.0110	.	.	0.0890	.
1	BS 56H	0.457	0.772	0.0096	0.0234	0.210	0.299	0.154	0.098	0.0009	.	0.0056	0.0002	0.0012	0.0078	0.0419
1	IARM 200D	0.453	0.749	0.0103	0.024	0.225	0.232	0.097	0.109	(0.004)	.	0.0050	.	.	0.007	0.0217
1	VS UG123	0.45	0.552	0.016	0.026	0.216	0.196	0.084	0.111	0.024
1	IRSID 1657	0.445	0.724	0.028	(0.013)	0.274	.	0.048	(0.022)	0.004	.	0.0051	.	.	.	(0.008)
1	IRSID 1648	0.432	1.41	0.031	(0.070)	0.242	0.408	0.65	0.170	(0.04)	.	(0.038)	.	.	.	(0.028)
1	12X 10400A	0.420	0.754	0.0137	0.0305	0.220	0.140	0.0631	0.139	0.0323	.	0.0068	.	.	.	0.0169
1	NM EN-8	0.42	0.82	0.02	0.02	0.21
1	IRSID 1642	0.418	0.929	0.031	(0.031)	0.388	0.097	0.068	(0.035)	(0.020)	.	(0.042)	.	.	.	(0.009)
1	IRSID 1647	0.418	0.701	0.019	(0.027)	0.299	(0.104)	0.093	0.490	(0.060)	(0.0555)
1	IRSID 1646	0.414	0.701	0.020	0.027	0.293	0.104	0.093	0.493	0.056
1	IARM 210D	0.412	0.73	0.0052	0.030	0.230	0.273	0.122	0.096	(0.002)	.	0.0059	0.0004	0.0009	0.007	0.034
1	SS 434/1	0.41	1.49	0.050	0.027	0.31	.	0.044	0.055
1	IARM 349A	0.41	1.49	0.011	0.025	0.192	0.300	0.178	0.189	0.0020	.	0.005	0.0003	0.0015	0.0085	0.059
1	BS 3941	0.407	0.802	0.016	0.023	0.257	0.053	0.018	0.069	0.0019	.	0.0036	(0.0001)	0.0011	0.0042	0.0061
1	IRSID 1652	0.406	0.931	(0.017)	0.040	0.386	0.345	0.190	0.184	.	(0.0013)	0.038	.	.	.	(0.042)
1	IRSID 1637	0.401	0.940	0.030	0.030	0.378	0.097	0.068	(0.033)	0.022	.	0.042	.	.	.	(0.006)
1	SS 605/2	0.400	0.345	0.054	0.015	0.54	(0.06)	(0.05)	(0.06)	0.027	(0.008)	(0.001)
1	IRSID 1644	0.394	0.594	0.021	0.031	0.287	0.265	0.158	0.138	(0.017)
1	ECRM 084-1D	0.391	0.860	0.029	0.029	0.265	0.267	0.154	0.033
1	IRSID 1645	0.388	0.610	0.021	0.030	0.286	0.261	0.157	0.140	0.015	(0.0124)
1	IRSID 1649	0.384	0.930	0.045	(0.047)	0.250	0.418	0.226	0.321	0.004	.	0.037	.	.	.	0.043
1	SS 460/2	0.383	0.616	0.0374	0.0099	0.126	.	.	.	0.024	(0.019)	0.037	0.0027	.	0.0106	.
1	VS RG30	0.38	0.357	.	0.013	0.45	0.161	0.62	3.06	0.50	0.62
1	BS 1035 *	0.36	0.75	0.009	0.027	0.24	0.24	0.13	0.15	<0.005	.	<0.05	<0.005	<0.05	<0.05	0.047
1	IRSID 1655	0.355	1.018	(0.018)	(0.060)	0.443	0.415	0.188	0.157	(0.004)	.	(0.036)	.	.	.	(0.043)
1	IRSID 1663	0.353	0.967	0.0090	0.034	0.235	0.180	0.148	0.206	0.037	.	0.028	.	.	.	0.042
1	VS UG90	0.34	0.286	0.0079	0.012	0.221	0.200	0.265	0.261	0.037	0.032	0.0044	.	.	.	0.046
1	VS UG19/6	0.34	0.274	(0.03)	(0.03)	0.136	0.148	0.262	0.227
1	IARM 360A	0.331	0.733	0.008	0.023	0.260	0.235	0.078	0.113	0.0016	.	0.0060	0.0004	0.0017	0.0067	0.024
1	BS 1030	0.331	0.682	0.0101	0.0299	0.261	0.269	0.078	0.124	0.0014	.	0.0055	0.0003	0.0012	0.0069	0.0182
1	IARM 209D	0.322	0.68	0.0084	0.021	0.268	0.243	0.079	0.137	(0.003)	.	0.0060	0.0002	0.002	0.007	0.037
1	IRSID 1653	0.312	0.962	0.034	(0.039)	0.400	0.453	0.218	0.358	<0.004	.	(0.039)	.	.	.	(0.038)
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	B	Ca	Co	Mo
1	VS RG27	0.30	0.97	0.054	0.0032	0.42	0.188	0.135	1.53	0.88	0.071	0.222
1	IRSID 1654	0.270	0.979	0.036	(0.047)	0.354	0.441	0.241	0.328	.	.	0.040	.	.	.	(0.043)
1	SS 434/2	0.27	1.54	0.06	0.014	0.51	.	0.038	0.24
1	IARM 359A	0.267	0.686	0.0094	0.020	0.233	0.186	0.068	0.121	0.002	.	0.0073	0.0003	0.0013	0.0069	0.023
1	BS 1026	0.260	0.715	0.0171	0.0191	0.268	0.247	0.096	0.163	0.0330	.	0.0100	(0.0002)	0.0017	0.0072	0.0289
1	VS UG94	0.26	0.186	0.0037	0.0026	0.101	0.088	0.178	0.206	0.017	0.0005
1	VS UG18/6	0.242	0.213	(0.003)	(0.003)	0.20	0.063	0.273	0.237
2	HRT FE2016-N	0.23	0.85	0.015	0.011	0.32	0.02	0.15	0.21	0.033
1	BS 1020	0.210	0.568	0.0058	0.0249	0.250	0.184	0.059	0.109	0.0006	.	0.0074	(0.0001)	0.0022	0.0070	0.018
1	IARM 213C	0.201	0.922	0.007	0.025	0.25	0.149	0.068	0.099	0.0019	.	0.0058	0.0003	0.0014	0.0074	0.022
1	IRSID 1664	0.2008	0.472	0.0106	0.0259	0.0616	0.0820	0.0547	0.0707	.	0.0193	0.0115	(0.0002)	(0.0005)	(0.0084)	0.0157
1	VS RG25/1	0.195	0.019	0.008	0.010	0.065	0.100	0.067	0.060	0.067	0.012
1	BS 1018	0.195	0.79	0.012	0.024	0.237	0.130	0.104	0.177	0.029	.	0.0041	(0.0002)	(0.0004)	0.0058	0.044
1	BS LF2E	0.176	1.05	0.007	0.0067	0.209	0.318	0.115	0.138	0.0287	.	0.0052	(0.0002)	0.0010	0.0071	0.0382
1	IARM 28K	0.174	0.80	0.012	0.027	0.291	0.171	0.0638	0.107	(0.0025)	.	(0.005)	0.0005	.	0.0060	0.0210
1	BS 1016	0.172	0.77	0.011	0.030	0.193	0.153	0.107	0.091	0.0200	.	0.0066	(0.0003)	(0.0004)	0.0193	0.040
1	12X 10180C	0.171	0.803	0.0150	0.0200	0.147	0.0500	0.0284	0.0793	0.0198	.	0.0029	.	.	.	0.0047
1	NM 3404.01	0.17	0.66	0.025	0.021	0.19	.	0.007	0.010
1	12X 10180B	0.169	0.722	0.0101	0.0056	0.114	0.0544	0.0333	0.0451	0.043	.	0.0059	.	.	.	0.0062
2	TL 1000	0.1692	1.4281	0.0142	0.0164	0.2258	0.0120	0.0312	0.0635	0.0226	.	(0.0016)	0.00018	0.00039	0.0042	0.0076
1	VS RG25	0.167	0.131	0.014	.	0.084	.	0.046	0.057	0.015	0.0028
1	VS UG124	0.165	1.41	0.019	0.032	0.384	0.020	0.015	0.035	0.039
1	VS UG109	0.161	0.353	0.020	0.0037	0.151	0.082	0.0053	0.048	0.0093
1	BS 2931B	0.159	0.788	0.0108	0.0292	0.207	0.098	0.083	0.080	0.0191	.	0.0033	0.0002	0.0002	0.0056	0.0329
1	IARM 213D	0.158	0.725	0.0120	0.031	0.226	0.207	0.076	0.093	(0.003)	.	(0.006)	(0.0004)	.	0.009	0.0131
1	SS 456/2	0.112	0.220	0.0212	0.0221	0.297	.	.	.	0.0017	(0.0013)	.	0.0015	.	0.0504	.
1	DSZU C041	0.107	1.35	0.0126	0.0055	0.63	0.059	0.040	0.067	0.017	.	0.0033	(0.0004)	0.0024	0.003	0.005
1	SS 432/1	0.102	1.34	0.024	0.039	0.043	.	0.14	0.31
1	SS 601/2	0.102	1.30	0.034	0.024	0.263	(0.04)	(0.03)	(0.14)	0.033	(0.09)	(0.006)
1	VS UG93	0.100	0.140	0.0033	0.0024	0.48	0.028	0.126	0.137	0.15	0.0008
1	VS UG17/6	0.097														

CARBON STEEL CONTINUED FROM THE PREVIOUS PAGE

Number	N	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units
IRSID 1660	37 mm Ø x 30 mm
ECRM 090-1D	0.0146	0.00043	.	0.00239	0.00090	.	.	0.204	.	0.00209	.	36 mm Ø x 25 or 30 mm
SRM 1227	0.002	.	.	.	32 mm Ø x 19 mm
SS 602/2	(0.001)	.	.	(<0.005)	44 mm Ø x 19 mm
BS 64C	0.0084	(<0.003)	.	.	.	(0.001)	(0.002)	0.005	.	.	.	44 mm Ø x ~7 or 19+ mm
HRT FE2014-N	0.0052	0.066	.	.	.	~35mm Ø x 20 mm
ECRM 056-2D	0.002	.	.	.	44 mm Ø x 25 or 30 mm
SRM 1224	.	0.029	0.0041	0.002	.	.	.	32 mm Ø x 19 mm
VS RG28	.	0.041	0.022	0.022	0.006	.	.	~45 mm Ø x ~28 mm
VS RG28/1	.	0.041	0.022	0.035	0.0041	.	.	~45 mm Ø x ~28 mm
IARM 373A	0.0088	0.001	0.002	(0.001)	(0.002)	0.0069	0.0017	0.023	(0.002)	(0.003)	(0.003)	31 mm Ø x 2 or 18 mm
VS UG20/6	~45 mm Ø x ~28 mm
NM 3405.01	40 mm Ø x 20 mm
SS 435/1	.	0.039	38 mm Ø x 19 mm
SS 435/2	.	0.13	38 mm Ø x 19 mm
BS 56E	0.0056	(<0.002)	.	(0.0001)	0.0004	(0.0006)	(0.001)	(<0.002)	.	.	.	44 mm Ø x ~7 or 19+ mm
IRSID 1636	48 mm Ø x 30 mm
SS 459/2	.	0.0102	.	0.0044	0.0121	.	.	0.0585	.	.	(0.074)	38 mm Ø x 19 mm
BS 56H	0.0106	0.0009	0.0025	0.0004	0.0025	0.0124	0.0009	0.0295	0.0007	Ta:0.0011	0.0007	38 mm Ø x ~7 or 19+ mm
IARM 200D	0.009	0.0010	.	.	.	0.0079	(0.0013)	0.0244	(0.003)	.	.	31 mm Ø x 2 or 18 mm
VS UG123	0.0078	0.0019	.	.	.	~45 mm Ø x ~28 mm
IRSID 1657	(0.001)	.	.	.	42 mm Ø x 30 mm
IRSID 1648	0.033	40 mm Ø x 28 mm
12X 10400A	0.0133	0.0127	.	.	.	0.0033	.	~40 mm Ø x ~15 mm
NM EN-8	40 mm Ø x 20 mm
IRSID 1642	(0.002)	.	.	.	45 mm Ø x 30 mm
IRSID 1647	41 mm Ø x 30 mm
IRSID 1646	42 mm Ø x 30 mm
IARM 210D	0.011	0.001	0.0034	0.001	0.002	0.010	0.0104	0.024	(0.002)	.	(0.001)	31 mm Ø x 2 or 18 mm
SS 434/1	.	0.078	38 mm Ø x 19 mm
IARM 349A	0.0100	0.0012	0.003	(0.001)	(0.003)	0.015	0.0013	0.027	0.004	(0.003)	(0.002)	31 mm Ø x 2 or 18 mm
BS 3941	0.0069	0.033	0.0055	0.0010	0.0005	0.0019	0.0017	0.0025	(0.0004)	(0.003)	(0.0003)	41 mm Ø x ~7 or 19+ mm
IRSID 1652	0.030	45 mm Ø x 30 mm
IRSID 1637	(0.002)	.	.	.	45 mm Ø x 30 mm
SS 605/2	(0.001)	.	.	(0.12)	44 mm Ø x 19 mm
IRSID 1644	45 mm Ø x 30 mm
ECRM 084-1D	0.023	38 mm Ø x 25 or 30 mm
IRSID 1645	0.028	45 mm Ø x 30 mm
IRSID 1649	40 mm Ø x 28 mm
SS 460/2	.	0.068	.	0.0005	(0.0006)	.	.	0.0322	.	.	(<0.0005)	38 mm Ø x 19 mm
VS RG30	.	0.139	0.63	0.91	.	.	~45 mm Ø x ~28 mm
BS 1035 *	<0.05	<0.005	<0.05	<0.005	.	<0.05	<0.005	0.028	* Provisional Analysis			40 mm Ø x ~7 or 19+ mm
IRSID 1655	0.046	40 mm Ø x 34 mm
IRSID 1663	0.0143	0.051	44 mm Ø x 30 mm
VS UG90	0.015	.	.	.	0.0011	.	0.039	~47 mm Ø x ~30 mm
VS UG19/6	~45 mm Ø x ~28 mm
IARM 360A	0.0102	0.0015	0.004	(0.001)	0.0023	0.010	0.0010	0.039	(0.001)	(0.003)	(0.001)	31 mm Ø x 2 or 18 mm
BS 1030	0.0107	(0.0004)	0.005	0.0005	0.0024	0.0114	0.0005	0.031	0.0012	.	(0.0002)	38 mm Ø x ~7 or 19+ mm
IARM 209D	0.0107	0.0014	0.005	0.001	0.004	0.012	0.0011	0.042	(0.002)	(0.003)	.	31 mm Ø x 2 or 18 mm
IRSID 1653	0.066	40 mm Ø x 34 mm
VS RG27	0.064	0.170	.	.	~45 mm Ø x ~28 mm
IRSID 1654	0.030	40 mm Ø x 34 mm
SS 434/2	0.010	0.038	38 mm Ø x 19 mm
IARM 359A	0.0094	0.002	0.0044	(0.001)	(0.002)	0.0100	0.0009	0.027	(0.001)	.	(0.001)	31 mm Ø x 2 or 18 mm
BS 1026	0.0083	(0.0004)	0.0031	(0.0002)	0.0019	0.0112	(0.0004)	0.0016	0.0021	.	(0.0002)	38 mm Ø x ~7 or 19+ mm
VS UG94	~40 mm Ø x ~28 mm
VS UG18/6	0.053	(0.001)	.	.	.	~45 mm Ø x ~28 mm
HRT FE2016-N	0.0055	35 mm Ø x 20 mm
BS 1020	0.0109	(0.0003)	0.0046	(0.0002)	(0.0018)	0.0090	(0.0005)	0.0363	(0.0004)	.	(0.0005)	44 mm Ø x ~7 or 19+ mm
IARM 213C	0.0116	0.0011	0.0042	0.0011	0.002	0.0081	0.0010	0.035	(0.002)	(0.006)	(0.0004)	31 mm Ø x 2 mm
IRSID 1664	0.0072	(0.0002)	.	0.0002	0.0012	0.0108	0.0013	(0.0005)	<0.002	(0.0007)	(0.0001)	37 mm Ø x 30 mm
VS RG25/1	.	0.016	0.0110	.	.	.	~45 mm Ø x ~28 mm
BS 1018	0.0079	(0.0006)	0.0014	(0.0006)	(0.001)	0.0099	0.0009	0.0109	0.0014	Fe:98.2	(0.001)	38 mm Ø x ~7 or 19+ mm
BS LF2B	0.0078	(0.0003)	0.0024	(0.0001)	0.0018	0.0092	0.0009	0.0300	0.0027	17025	Fe:97.9	38 mm Ø x ~7 or 19+ mm
IARM 28K	(0.008)	0.0017	(0.005)	.	.	0.0075	(0.0015)	(0.0014)	.	.	.	31 mm Ø x 2 or 18 mm
BS 1016	0.0113	(0.0009)	(0.003)	(0.004)	Fe:98.4	0.013	0.0010	0.0011	(0.0013)	17025	(0.001)	Hexagon ~60 mm Ø x 19+ mm
12X 10180C	0.0052	0.0024	.	.	.	0.0005	.	~40 mm Ø x ~15 mm
NM 3404.01	40 mm Ø x 20 mm last
12X 10180B	0.0071	0.0065	.	.	.	0.0079	.	~40 mm Ø x ~15 mm
TL 1000	(0.0093)	0.0293	.	Mg:(0.00005)	.	(0.00106)	0.0011	(0.0033)	(0.0002)	.	.	36 mm Ø x 20 mm
VS RG25	0.039	.	.	.	~45 mm Ø x ~28 mm
VS UG124	0.0072	0.0043	.	.	.	~45 mm Ø x ~28 mm
VS UG109	0.071	~45 mm Ø x ~25 mm
BS 2931B	0.0076	0.0011	0.0021	(0.00004)	0.0012	0.0062	0.0008	0.0014	0.0007	Mg:0.0001	0.0005	38 mm Ø x ~2mm 17025 last
IARM 213D	(0.008)	(0.0012)	(0.01)	.	(0.0032)	0.0147	0.0011	0.0010	(0.003)	(0.002)	(0.0015)	31 mm Ø x 2 or 18 mm
SS 456/2	.	0.0057	.	0.0189	0.0172	.	.	0.0221	.	.	(0.014)	38 mm Ø x 19 mm
DSZU C041	0.0046	0.0017	.	.	.	0.0038	0.0019	0.003	(0.003)	.	.	40 mm Ø x 25 mm
SS 432/1	.	<0.002	38 mm Ø x 19 mm
SS 601/2	(0.002)	.	.	(<0.005)	44 mm Ø x 19 mm
VS UG93	0.075	0.0008	.	.	.	~40 mm Ø x ~28 mm
VS UG17/6	~45 mm Ø x ~28 mm
SS 433/2	.	0.06	38 mm Ø x 19 mm
IRSID 1661	(0.0005)	(0.0085)	40 mm x 42 mm x 30 mm
VS UG125	0.0112	0.071	0.035	0.074	.	.	~45 mm Ø x ~28 mm
VS UG108	~45 mm Ø x ~25 mm
SRM 1228	<0.001	.	.	.	32 mm Ø x 19 mm
ECRM 057-2D	0.0023	38 mm Ø x 25 or 30 mm
BS XCCS-1	0.0052	(0.001)	.	(0.0006)	(0.0005)	0.0002	0.0015	0.0012	(0.003)	.	0.0006	~40 mm Ø x ~30 mm 17025
VS RG26/1	.	0.0056	0.100	0.0113	.	.	.	~45 mm Ø x ~28 mm
NM PC-1	40 mm Ø x 20 mm
ECRM 083-2D	0.00157	0.00439	.	39 mm Ø x 28 mm
DSZU C03	.	(0.002)	.	(0.009)	(0.003)	0.011	0.002	0.004	(0.009)	(0.0037)	(0.0006)	40 mm Ø x 30 mm
VS RG26	0.121	.	0.0058	.	.	~45 mm Ø x ~28 mm
SS 431/2	0.005	0.004	38 mm Ø x 19 mm
DSZU C040	0.0071	(0.0004)	.	.	.	(0.0001)	0.0010	(0.001)	(0.002)	.	.	40 mm Ø x 25 mm
RM Fe 1/5	0.002	<0.005	.	<0.002	.	0.0008	<0.0005	<0.0005	0.002	.	<0.005	40 mm Ø x 40 mm
VS UG2/5	.	(0.002)	(0.01)	0.005	(0.02)	.	.	~45 mm Ø x ~28 mm
SS 432/2	0.007	0.018	36 mm Ø x 18 mm
SS 111/1	0.0025	44 mm Ø x 19 mm
VS 005	0.0006	0.0004	0.0002	.	.	.	~45 mm Ø x ~25 mm
VS UG2/10	(0.006)	0.0017	0.0070	~45 mm Ø x ~28 mm
VS 003	0.0020	0.0063	~45 mm Ø x ~25 mm
CZ LA-1B	0.003	(0.001)	.	(0.0007)	(0.002)	(0.001)	(0.001)	0.004	0.010	.	(0.002)	~37 mm Ø x 25 mm
IMZ 110A	0.0037	.	.</									

ARSENIC AND ANTIMONY IN STEEL

= Class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	As	Sb	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Sn	Ti
1	VS UG87	0.116	0.0012	0.59	1.18	0.026	0.022	1.25	0.030	0.50	0.260	0.024	0.02	.	0.044	.	0.103
1	12X 12749W	0.071	.	0.132	1.250	0.0257	0.101	0.298	0.311	0.485	0.554	0.004	.	0.436	0.224	0.040	0.031
1	SS 454/1	0.070	.	0.376	0.80	0.061	0.047	0.31	0.051	0.069	0.062	.	.	.	0.20	0.054	0.010
1	IMZ 120	0.065	0.031	0.60	0.40	(0.049)	0.026	0.34	0.10	0.085	0.20	0.033	.	.	.	0.008	.
1	12X 15266V	0.0640	.	0.455	1.240	0.0344	0.0258	0.674	0.226	1.317	3.49	0.526	.	0.286	0.298	0.0082	.
1	IRSID 1656	0.055	.	0.477	0.730	0.027	0.013	0.277	.	(0.048)	(0.017)	(0.002)	.	.	(0.007)	.	.
1	12X 15260W	0.055	.	0.352	2.08	0.0275	0.074	0.485	0.152	0.453	2.98	0.191	.	0.0884	0.098	0.0094	.
1	12X 350B	0.053	.	0.138	0.706	0.029	0.0363	0.672	0.150	0.162	0.392	0.341	.	0.0206	0.149	0.0298	0.099
1	12X 350C *	0.05	.	0.16	0.76	0.03	0.04	0.45	0.20	0.16	0.34	0.29	.	0.032	0.15	0.035	0.075
1	12X 353G	0.0461	0.138	0.111	0.726	0.0099	0.0147	0.207	0.232	0.214	0.701	0.0485	.	0.0240	0.1063	0.113	0.0387
1	12X 12746U	0.049	.	0.0132	1.70	0.0247	0.064	0.183	0.368	0.161	0.182	0.021	.	0.115	0.654	0.202	0.0283
1	12X 358A	0.0393	0.128	0.129	0.709	0.0102	0.0142	0.199	0.250	0.212	0.625	0.0616	.	0.0355	0.108	0.117	0.0453
1	12X 355C	0.0331	0.0796	0.159	0.508	0.0214	0.0241	0.494	0.657	0.0710	0.113	0.1104	.	0.0495	0.1010	0.0564	0.153
1	12X 354B	0.023	.	0.252	5.03	0.0478	0.0105	0.200	0.0679	0.082	0.0487	0.0150	.	0.0237	0.0328	0.0154	0.0248
1	ECRM 055-2D	0.0187	0.00376	0.5199	0.687	0.0102	0.0205	0.3094	0.2089	0.3121	0.3217	.	.	0.0257	0.0960	0.0162	0.00104
1	12X 357C	0.0147	0.0140	0.270	0.220	0.0101	0.0590	0.153	0.265	0.0954	0.094	0.208	.	0.199	0.0105	0.0188	0.0569
1	BS 1030	0.0055	0.0024	0.331	0.682	0.0101	0.0299	0.261	0.269	0.078	0.124	0.0014	.	0.0069	0.0182	0.0114	0.0005
1	VS UG90	0.0044	0.0011	0.34	0.286	0.0079	0.012	0.221	0.200	0.265	0.261	0.037	0.032	.	0.046	.	0.039
1	VS UG89	0.0043	0.0011	0.92	0.76	0.0085	0.01	0.385	0.373	0.51	0.420	0.01	0.007	.	0.044	.	0.012
1	BS 2931B	0.0033	0.0012	0.159	0.788	0.0108	0.0292	0.207	0.098	0.083	0.080	0.0191	.	0.0056	0.0329	0.0062	0.0008
1	VS UG92	0.0027	0.0005	0.69	0.79	0.05	0.0029	1.98	0.111	0.155	0.200	0.091	0.08	.	0.119	.	0.022
1	IRSID 1670	0.0018	.	0.0011	0.3981	0.0128	0.0075	0.0046	0.0134	0.0142	0.0174	0.0479	.	0.0018	0.0009	0.0017	0.0078
1	VS UG88	0.0007	0.0003	0.62	1.26	0.0026	0.0043	1.22	0.171	0.52	0.474	0.01	0.009	.	0.104	.	0.107
1	VS UG91	0.0004	0.00009	0.49	.	0.0038	0.0021	2.23	0.057	0.039	0.064	0.048	0.048	.	0.058	.	0.038
1	SS 458/2	.	0.089	0.198	0.479	0.0281	0.0314	0.504	.	.	.	0.055	0.053	0.198	.	.	.
1	SS 457/2	.	0.050	0.307	0.327	0.0098	0.0448	0.105	.	.	.	0.088	0.084	0.0217	.	.	.

Number	B	Bi	Ca*	Ce*	Mg*	N	Nb	O*	Pb	Se	Ta	V	W	Zn	Zr	Units
VS UG87	0.010	.	.	0.00008	.	.	0.0038	.	.	.	~47 mm Ø x ~30 mm
12X 12749W	0.069	0.034	.	.	~40 mm Ø x ~15 mm
SS 454/1	(0.0001)	.	.	.	0.15	.	.	38 mm Ø x 19 mm last
IMZ 120	0.0115	.	.	0.077	40 mm Ø x 40 mm
12X 15266V	1.438	.	.	.	0.116	0.106	.	.	.	~40 mm Ø x ~15 mm
IRSID 1656	(0.002)	.	.	.	40 mm Ø x 35 mm
12X 15260W	0.254	.	.	.	(0.016)	0.442	.	.	.	~40 mm Ø x ~15 mm
12X 350B	0.0286	0.275	.	.	40 mm Ø x 15 mm
12X 350C *	.	.	* Provisional Analysis			0.012	0.25	.	.	~40 mm Ø x ~15 mm
12X 353G	.	0.0246	.	.	.	0.0027	0.0641	.	0.0179	0.0192	.	0.0189	0.135	.	0.034	~40 mm Ø x ~15 mm
12X 12746U	0.0218	0.0160	0.101	.	.	40 mm Ø x ~20 mm last
12X 358A	.	0.0102	.	.	.	0.0029	0.104	.	0.0052	0.097	.	0.0261	0.123	.	0.0113	~40 mm Ø x ~15 mm
12X 355C	(0.0012)	0.0023	0.023	.	.	0.0395	.	0.1265	0.037	.	0.0192	~40 mm Ø x ~15 mm
12X 354B	0.0027	0.0802	0.0204	0.0248	.	.	~40 mm Ø x ~15 mm
ECRM 055-2D	0.01069	0.00245	0.0166	.	.	38 mm Ø x 25 or 30 mm
12X 357C	0.0102	0.0058	.	.	.	0.0079	0.0051	.	0.0315	(0.004)	.	0.166	0.0194	0.0094	.	~40 mm Ø x ~15 mm
BS 1030	0.0003	.	12	(2)	.	0.0107	(0.0004)	50	0.0005	.	(0.001)	0.031	0.0012	.	(0.0002)	38 mm Ø x ~7 or 19+ mm 17025
VS UG90	0.015	~47 mm Ø x ~30 mm
VS UG89	0.017	0.0043	.	0.0003	.	.	0.021	.	.	.	~47 mm Ø x ~30 mm
BS 2931B	0.0002	.	2	.	1	0.0076	0.0011	21	(0.00004)	.	(0.0004)	0.0014	0.0007	last	0.0005	38 mm Ø x ~2 mm 17025
VS UG92	0.016	0.034	.	0.00017	.	.	0.024	.	.	.	~47 mm Ø x ~30 mm
IRSID 1670	0.0007	.	.	(2)	.	0.0016	(0.0003)	(0.0005)	.	.	.	37 mm Ø x 30 mm
VS UG88	0.020	0.059	.	0.00015	.	.	0.117	.	.	.	~47 mm Ø x ~30 mm
VS UG91	0.010	0.097	.	0.00006	.	.	0.049	.	.	.	~47 mm Ø x ~30 mm
SS 458/2	0.0069	0.0510	.	0.0140	.	.	0.105	.	.	(0.064)	38 mm Ø x 19 mm
SS 457/2	0.0046	0.0174	.	0.0098	.	.	0.153	.	.	0.025	38 mm Ø x 19 mm

BISMUTH AND SELENIUM STEEL

= Class, where 1 = CRM and 2 = RM

BS: 38 mm Ø x ~7 or 19+ mm

CZ: ~39 mm Ø x 25 mm

#	Number	Bi	Se	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	N
2	BS 4140A	0.105	.	0.40	0.84	0.021	0.076	0.21	0.15	0.15	0.97	0.016	0.005	0.010	0.16	0.0098
2	BS 53MOD	0.102	.	1.01	0.36	0.011	0.012	0.26	0.070	0.072	1.37	0.019	0.004	0.007	0.024	0.0086
2	BS 4140B	0.087	.	0.43	0.76	0.027	0.037	0.20	0.006	0.012	0.84	0.036	(0.002)	0.005	0.16	0.0064
2	BS 4150MOD	0.070	.	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.012	0.005	0.012	0.21	0.0087
2	CZ CM-16A	0.039	.	0.355	0.92	0.043	0.033	0.77	0.293	0.72	0.70	0.125	0.058	0.056	0.405	0.015

Number	B	Ca	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr
BS 4140A	.	(0.0003)	.	(0.0025)	(0.001)	.	0.011	(0.003)	0.004	.	.	.
BS 53MOD	.	(0.001)	.	(0.002)	0.0005	.	0.008	.	0.005	.	.	.
BS 4140B	.	(0.0002)	.	(0.002)	0.004	.	(0.002)	0.003	0.005	.	.	.
BS 4150MOD	.	0.0010	.	(0.003)	0.0010	.	0.013	(0.002)	0.008	.	.	.
CZ CM-16A	0.012	0.0006	0.066	.	0.053	0.027	0.025	0.099	0.319	0.141	0.021	0.062

CALCIUM IN STEEL

= Class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Ca	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	V
1	BS HiCal-1	0.0140	0.271	1.00	(0.007)	0.0007	1.29	0.152	3.28	1.55	0.070	.	0.0024	0.379	.	0.0027
1	SS 115	0.0058	0.6224	0.682	0.0123	0.00093	0.2078	.	0.0196	0.0198	0.0527	.	.	.	0.0067	.
1	BS 9325A	0.0039	0.203	0.969	0.0079	0.0045	0.612	0.163	3.29	1.50	0.0056	.	0.0093	0.358	0.0076	(0.0024)
1	SS 116	0.0036	0.617	0.6756	0.0092	0.00176	0.201	.	0.0155	0.0141	0.0587	.	.	.	0.0069	.
1	ECRM 194-1D	0.0026	0.1532	1.188	0.0097	0.0006	0.431	0.0751	0.3417	0.733	0.0837	.	.	0.2857	0.0115	0.0243
1	BS XCCS-1	0.0024	0.0441	0.356	0.0068	0.0022	0.292	0.0143	0.0132	0.0288	0.061	.	0.0017	0.0060	0.0052	0.0012
1	BS 1020	0.0022	0.210	0.568	0.0058	0.0249	0.250	0.184	0.059	0.109	0.0006	.	0.0070	0.018	0.0109	0.0363
2	HRT FE2009-N	0.0020	0.12	0.55	0.010	0.003	0.32	0.08	0.25	2.56	0.030	.	.	1.02	.	0.015
1	IRSID 1665	0.0017	0.1209	0.446	0.0104	0.0135	0.187	0.0469	0.0308	0.0363	.	0.0379	0.0046	0.0047	0.0049	(0.0006)
1	BS 3941	0.0011	0.407	0.802	0.016	0.023	0.257	0.053	0.018	0.069	0.0019	.	0.0042	0.0061	0.0069	0.0025
1	IARM 254A	0.001	0.500	0.78	0.010	0.024	0.211	0.091	0.044	0.050	0.025	.	0.006	0.013	0.0096	0.002
2	BS 4150MOD	0.0010	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.012	.	0.012	0.21	0.0087	0.008
2	BS 4330V	0.0010	0.318	0.91	0.008	0.0009	0.240	0.181	1.91	0.91	0.021	.	0.011	0.475	0.0076	0.094
1	BS 4130	0.0007	0.303	0.541	0.0105	0.0113	0.245	0.221	0.088	0.924	0.0242	.	0.0065	0.168	0.0072	0.0037
2	BS 4942	0.0006	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	(0.004)	.	0.010	0.54	0.0080	0.28
2	BS 2952	0.0003	1.03	0.33	0.013	0.014	0.32	0.106	0.135	1.36	0.024	.	0.007	0.044	0.0084	0.005
1	BS PP20	0.0003	0.382	1.41	0.018	0.0070	0.262	0.119	1.00	1.94	0.0132	.	0.0145	0.212	0.0080	0.066
1	IMZ 111	0.0003	0.106	0.31	0.010	0.039	0.55	0.036	0.23	0.072	0.017	0.007	.	0.084	0.0133	0.022
2	TL 1669	0.00017	0.00226	0.0955	0.0137	0.0100	0.0093	0.0217	0.0160	0.0246	0.03553 (tot)	.	0.0019	0.0011	0.0024	(0.0006)

Number	As	B	Bi	Nb	O	Pb	Sb	Sn	Ti	W	Zr	Other
BS HiCal-1	0.0022	(0.0001)	.	(0.002)	.	(0.0005)	.	(0.0002)	0.0037	(0.0009)	(0.0008)	~38 mm Ø x ~30 mm
SS 115	0.0027	.	.	38 mm Ø x 19 mm
BS 9325A	0.0024	(0.0001)	.	0.0017	.	(0.0003)	Fe: 92.8	(0.0003)	0.0030	0.024	(0.001)	~40 mm Ø x ~30 mm
SS 116	0.00012	.	.	0.00171	.	.	44 mm Ø x 19 mm
ECRM 194-1D	0.0042	0.0020	Disc 33 mm Ø x 33 mm or Block ~38x34x32 mm
BS XCCS-1	0.0024	(0.0004)	.	(0.001)	Fe: 99.2	(0.0006)	(0.0005)	0.0002	0.0015	(0.003)	0.0006	~40 mm Ø x ~30 mm
BS 1020	0.0074	(0.0001)	.	(0.0003)	0.0046	(0.0002)	(0.0018)	0.0090	(0.0005)	(0.0004)	(0.0005)	44 mm Ø x ~7 or 19+ mm
HRT FE2009-N	Zn: 0.004	40 mm Ø x 40 mm
IRSID 1665	0.0067	(0.00032)	.	.	.	(0.0014)	(0.0008)	0.0031	(0.0008)	.	.	37 mm Ø x 30 mm
BS 3941	0.0036	(0.0001)	.	0.033	0.0055	0.0010	0.0005	0.0019	0.0017	(0.0004)	(0.0003)	41 mm Ø x ~7 or 19+ mm
IARM 254A	0.005	0.0002	.	0.001	(0.003)	(0.0003)	.	0.005	0.001	(0.001)	(0.001)	31 mm Ø x 2 mm
BS 4150MOD	0.005	.	0.070	.	(0.003)	0.0010	.	0.013	(0.002)	.	.	38 mm Ø x ~7 or 19+ mm
BS 4330V	0.0018	.	.	0.010	.	.	.	37 mm Ø x ~7 or 19+ mm
BS 4130	0.0048	(0.0002)	.	0.0015	0.0015	(0.00003)	(0.0021)	0.0099	0.0009	0.0011	Mg: 0.0002	38 mm Ø x ~7 or 19+ mm
BS 4942	0.005	.	.	.	(0.0021)	.	.	0.014	.	.	.	38 mm Ø x ~7 or 19+ mm
BS 2952	0.004	.	.	.	(0.002)	.	0.003	0.006	0.003	.	.	44 mm Ø x ~7 or 19+ mm
BS PP20	0.0049	0.00011	.	0.0048	(0.0010)	.	0.0013	0.0069	0.0007	0.0058	.	38 mm Ø x ~7 or 19+ mm
IMZ 111	40 mm Ø x 40 mm
TL 1669	0.0017	0.00038	.	0.00046	.	0.00013	0.00049	0.0071	0.0504	.	(0.00021)	38 mm Ø x 25 mm

CRM Al, Ca, AND N IN LOW ALLOY STEEL

Number	Al	Ca	N	Units
BS 9905	0.017	(0.0001)	0.055	38 mm Ø x ~7 mm
IMZ 133	.	.	0.0360	40 mm Ø x 40 mm
IMZ 131	0.0043	.	0.0333	40 mm Ø x 40 mm
IMZ 135	0.0274	0.0008	0.0238	40 mm Ø x 40 mm
IMZ 169	0.075	.	0.0193	40 mm Ø x 40 mm
IMZ 141	0.0071	.	0.0154	40 mm Ø x 40 mm
IMZ 130	0.0046	0.0024	0.0153	40 mm Ø x 40 mm
IMZ 139	(0.029)	0.0031	0.0113	40 mm Ø x 40 mm
IMZ 132	0.0021	0.0002	0.0097	40 mm Ø x 40 mm
IMZ 137	0.0017	0.00025	0.0083	40 mm Ø x 40 mm
IMZ 140	0.0307	0.0015	0.0083	40 mm Ø x 40 mm
IMZ 138	0.0022	.	0.0063	40 mm Ø x 40 mm
IMZ 134	0.0124	0.0005	.	40 mm Ø x 40 mm
IMZ 136	0.0034	0.00031	.	40 mm Ø x 40 mm

C-Mo and Cr-Mo STEEL XRF SET

= class, where 1 = CRM ISO 17025 and 2 = RM, Set Part Number: BS MOLY-5 AVAILABLE INDIVIDUALLY ~7 mm discs

#	Grade	Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	Sn	V
2	C-.5Mo	4419	BS 3952	0.208	0.546	0.011	0.021	0.264	0.202	0.112	0.105	0.519	0.048	.	(0.0005)	.	.
1	1.25Cr-.5Mo	F-11	BS 45B	0.140	0.502	0.0068	0.017	0.583	0.101	0.136	1.14	0.60	0.030	0.0090	0.0066	0.0069	0.0083
2	2.25Cr-1Mo	F-22	BS 1982	0.128	0.441	0.012	0.026	0.255	0.177	0.197	2.09	0.89	0.021	0.010	0.0097	0.013	0.003
2	5Cr-.5Mo	F-5	BS 47A	0.130	0.44	0.017	0.015	0.27	0.11	0.12	4.22	0.47	0.015	0.011	0.018	0.008	0.016
1	9Cr-1Mo	F-9	BS 48B	0.110	0.365	0.0228	0.0068	0.75	0.070	0.165	8.78	0.949	0.0157	0.0165	0.0088	0.0049	0.033

CRM EPMA SETS

available in sets only, as grouped 4x10x15mm

Number	Cr	Number	Ni
NMIJ 1001-a	5.00	NMIJ 1006-a	5.04
NMIJ 1002-a	14.96	NMIJ 1007-a	10.05
NMIJ 1003-a	19.87	NMIJ 1008-a	20.02
NMIJ 1004-a	29.84	NMIJ 1009-a	39.92
NMIJ 1005-a	39.69	NMIJ 1010-a	60.07

LEADED STEEL

= Class, where 1 = CRM and 2 = RM

OES regularly requires extension of preburn time

#	Number	Pb	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	N	Sn	V
1	BS 74C	0.328	0.077	0.94	0.082	0.294	(0.002)	0.005	0.011	0.019	(<0.002)	0.004	.	0.008	0.0040	(<0.002)	0.0016
1	14X 12144A	0.328	0.0800	1.227	0.0630	0.325	0.0093	0.0106	0.0162	0.0807	0.0034	0.0022	.	0.0089	0.0066	.	.
2	CZ CM-15C	0.29	0.075	1.13	0.063	0.32	0.006	0.141	0.072	0.052	.	.	(0.01)	0.021	.	.	.
1	BS 75G	0.247	0.161	1.08	0.0085	0.114	0.011	0.0300	0.045	0.079	0.0016	0.0028	0.0031	0.0174	0.0030	0.0014	0.0005
2	BS 75F	0.202	0.165	1.05	0.009	0.116	0.004	0.030	0.044	0.080	0.002	.	.	0.018	.	.	.
1	BS 73C *	0.21	0.21	0.84	0.012	0.03	0.28	0.026	0.59	0.58	0.03	0.004	0.003	0.18	0.004	0.004	0.003
1	IARM 182B	0.19	0.21	0.81	0.016	0.037	0.27	0.017	0.47	0.49	0.038	(0.003)	0.006	0.172	0.0040	0.0019	0.004
1	IARM 183C	0.18	0.079	1.06	0.078	0.31	0.004	0.016	0.019	0.055	0.0021	0.003	(0.002)	0.010	0.0049	0.003	0.002
2	BS 72B	0.174	0.497	0.87	0.029	0.029	0.26	0.21	0.169	0.985	0.020	(0.006)	0.012	0.187	0.0081	0.014	0.004
2	BS 73B	0.139	0.200	0.83	0.009	0.030	0.250	0.141	0.416	0.512	0.022	0.004	0.008	0.170	0.0113	0.008	(<0.002)
2	BS 70B	0.135	0.40	0.90	0.009	0.022	0.27	0.13	0.25	1.00	0.024	.	.	0.205	.	.	.
1	BS 70C *	0.13	0.39	0.90	0.01	0.02	0.27	0.12	0.25	0.97	0.02	<0.05	0.009	0.20	<0.05	0.01	0.002

Number	B	Ca	Nb	O	Sb	Ti	W	Zn	Grade	Units
BS 74C	.	.	(<0.005)	12L14	41 mm Ø x ~7 or 19+ mm
14X 12144A		~40 mm Ø x ~15 mm
CZ CM-15C		~39 mm Ø x 25 mm
BS 75G	(0.0002)	(0.0002)	(0.0003)	0.0155	.	(0.0004)	0.0004	.	11L17	41 mm Ø x ~7 or 19+ mm
BS 75F	11L17	40 mm Ø x 12 mm
BS 73C *	<0.005	<0.005	0.005	0.001	0.003	0.002	0.007	.	86L20	38 mm Ø x ~7 or 19+ mm
IARM 182B	(0.0003)	(0.0005)	(0.003)	(0.003)	(0.003)	(0.003)	(0.01)	(0.001)	86L20	31 mm Ø x 2 mm
IARM 183C	0.0011	.	0.0010	0.016	(0.001)	0.0009	(0.002)	0.001	12L14	31 mm Ø x 2 or 18 mm
BS 72B	.	.	(0.001)	.	.	(0.002)	.	.	41L50	37 mm Ø x ~7 or 19+ mm
BS 73B	86L20	41 mm Ø x ~7 or 19+ mm
BS 70B	41L40MOD	41 mm Ø x ~7 or 19+ mm
BS 70C *	<0.005	.	<0.05	<0.05	.	0.002	.	Zr:<0.05	41L40MOD	41 mm Ø x ~7 or 19+ mm

RM LEADED AND BISMUTH STEEL XRF SET

Part Number: BS PB-BI-7

AVAILABLE INDIVIDUALLY

~7 mm discs

17025

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Bi	Pb	Sn	V	N
11L17	BS 75F	0.165	1.05	0.009	0.116	0.004	0.030	0.044	0.080	0.018	0.002	.	0.202	.	.	.
12L14	BS 74B	0.08	0.91	0.087	0.316	0.002	0.006	0.012	0.019	0.008	(0.002)	.	0.34	.	.	.
41L40	BS 70B	0.40	0.90	0.009	0.022	0.27	0.13	0.25	1.00	0.205	0.024	.	0.135	.	.	.
41L50	BS 72B	0.497	0.87	0.029	0.029	0.26	0.21	0.169	0.985	0.187	0.020	.	0.174	0.014	0.004	0.0081
4140 + Bi & S	BS 4140A	0.40	0.84	0.021	0.076	0.21	0.15	0.15	0.97	0.16	0.016	0.105	(0.001)	0.011	0.004	0.0098
4150 + Bi & S	BS 4150 MOD	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.21	0.012	0.070	0.0010	0.013	0.008	0.0087
8620 + Bi & S	BS 8620A	0.184	0.80	0.008	0.079	0.21	0.15	0.44	0.48	0.16	0.016	0.073	(0.001)	0.009	0.004	0.0107

MANGANESE STEEL

14X:~40Øx-15-17mm BS:32Øx-15-17mm CZ:~39Øx25mm DSZU:39Øx20mm ECRM:35Øx25mm IMN:50-56Øx15mm SS 491:50Øx10mm other SS:48x42x12mm VS:~38Øx-18mm

#	Number	Mn	C	P	S	Si	Cu	Ni	Cr	Al	Mo	N	Nb	Sn	V	Other
1	DSZU C013	28.8	0.89	0.025	(0.002)	0.29	0.108	(0.20)	(0.14)	(8.6)	(0.44)	(0.002)	(0.46)	.	(0.1)	.
1	VS LG68	28.8	0.39	(0.02)	0.003	.	0.11	0.20	0.13	8.6	0.46	.	0.46	.	.	.
1	IMZ 199	28.74	0.90	0.022	(0.0006)	0.294	0.110	0.20	0.164	8.65	0.43	.	0.43	.	0.026	B:(0.001) Ti:(0.004)
2	CZ SP-2B	26.1	1.42	0.10	0.009	0.51	0.096	0.32	1.36	0.008	0.38	.	W:0.084	0.32	0.155	Co:0.040 Ti:0.025
1	IRSID 1833	22.57	0.605	0.0345	(0.0005)	0.193	0.030	0.0494	0.268	0.0025	0.0133	0.012	0.0026	0.0043	0.203	As, Co, Pb, and Ti **
1	14X MN1AL	22.08	0.597	0.053	0.0054	0.944	0.178	0.692	1.321	(0.23)	0.499	0.0585	0.096	0.0393	0.0226	Ta:(0.011) Ti:0.0346
1	DSZU C02	20.9	0.39	0.021	0.0072	0.31	0.087	0.303	0.17	(2.9)	(0.3)	(0.013)	.	.	(1.14)	.
1	VS LG67	20.9	0.39	0.020	0.007	0.31	0.090	0.11	0.19	2.88	1.09	.
2	BS 17	19.59	0.63	0.047	0.007	0.21	0.075	0.03	1.46	(0.02)	0.46	.	.	(0.012)	(0.02)	~15mm height
2	BS 17A	19.38	0.588	0.043	0.005	0.22	0.135	0.060	1.37	0.052	0.52	0.038	0.06	0.012	0.016	Co:0.013
1	DSZU C011a	17.4	0.45	0.042	0.008	0.43	0.089	0.11	0.36	(2.8)	(0.014)
1	DSZU C024	16.95	0.88	0.068	0.0100	0.531	0.72	0.66	1.62	(0.004)	0.29	(0.021)	(0.10)	.	0.29	B:(0.003) Ti:(0.006)
1	IMZ 198	16.10	0.44	0.031	0.0090	0.423	0.104	0.058	0.30	2.80	(0.008)	Ti:(0.005)
1	VS LG66	16.1	0.44	0.031	0.010	0.41	0.104	0.059	0.30	2.6
1	DSZU C011	16.09	0.44	0.031	0.0093	0.41	0.105	0.058	0.30	(2.6)	(0.01)	(0.010)
1	14X MN4AC	13.62	0.938	0.073	0.0194	0.900	0.270	1.052	1.983	0.20	0.796	0.0450	0.153	0.0634	0.0332	Ti:0.075
1	SS 495/4	13.11	0.796	0.093	0.0128	0.674	0.0222	1.620	2.223	0.0082	0.266	0.0416	.	.	0.0525	Co:0.0120
1	DSZU C023	13.09	0.79	0.052	0.0062	0.291	0.111	3.15	0.313	(0.006)	(0.02)	(0.018)	(0.02)	.	(0.02)	B:(0.001) Ti:(0.004)
1	DSZU C022	12.89	1.15	0.087	0.0057	0.34	0.103	0.122	0.192	(0.007)	(0.03)	(0.013)	(0.01)	.	(0.03)	B:(0.001) Ti:(0.006)
1	DSZU C010	12.25	1.20	0.082	0.0035	0.49	0.120	0.108	0.187	(0.006)	(0.01)	(0.017)
1	VS LG65	12.2	1.19	0.080	0.0033	0.49	0.119	0.11	0.19	0.006
1	DSZU C021	11.23	1.32	0.035	0.010	0.105	0.32	0.36	0.62	(0.003)	0.096	(0.013)	(0.03)	.	0.124	B:(0.002) Ti:(0.005)
1	SS 493/3	11.15	0.819	0.12	0.009	0.861	0.017	3.24	0.259	0.035	1.04	0.025	.	.	0.025	.
1	14X MN3T	11.03	0.994	0.0386	0.0091	1.00	0.153	0.497	0.749	(0.040)	0.259	0.034	0.407	0.0195	0.0198	.
2	14X 15196S	10.16	1.08	0.037	0.012	1.64	0.22	0.25	0.26	0.13	0.22	.	.	0.10	0.21	last of stock
1	14X MN2R	9.65	0.701	0.0198	0.0098	1.48	0.081	0.530	0.355	0.120	1.546	0.0125	0.294	0.061	0.121	Ti:0.179
2	BS 19A	8.76	1.57	0.092	0.009	1.46	0.51	1.48	3.75	0.057	1.97	0.039	0.040	0.037	0.10	Co:0.014
1	DSZU C020	8.85	0.97	0.024	(0.015)	0.091	0.53	1.36	0.96	(0.004)	0.13	(0.020)	(0.02)	.	0.152	B:(0.002) Ti:(0.003)
1	14X MN5T	8.55	1.377	0.0270	0.0110	1.59	0.421	1.372	3.31	(0.26)	1.91	0.0155	0.021	0.0129	0.0397	Ta:0.005 last
1	14X MN5U	8.78	1.36	0.0552	0.0273	1.47	0.691	2.10	3.18	0.0257	1.93	0.0231	0.102	0.0228	0.0490	Ti:0.93
1	SS 492/3	8.33	1.18	0.0318	0.0093	0.299	0.0211	4.17	1.076	0.131	1.318	0.0225	.	.	(0.004)	Co:0.0048
1	14X MN5V	8.02	1.42	0.057	0.0207	2.27	0.551	3.09	3.28	0.145	2.26	0.0146	0.041	0.0278	0.0810	Ta:(0.004) Ti:0.51
2	CZ CM-9B	2.27	0.17	(0.008)	(0.010)	0.89	0.040	0.023	1.36	0.049	(0.002)	.	(0.06)	(0.003)	(0.006)	+7 informational

* Provisional Analysis

** IRSID 1833 also contains As: 0.0034, Co: 0.0089, Pb: 0.00007, and Ti: 0.0011. Sample size 35 mm Ø x 25 mm.

CRM

MANGANESE STEEL SET

AVAILABLE IN SET/6 ONLY

30 mm Ø x 24 mm

CRM Co/Fe/V **MAGNETIC ALLOY PERMENDUR 2V** analysis listed in mass %

Number	Co	Fe	V	Mn	P	S	Si	Ni	N	Nb	O	Zr	Units
IARM 326A	48.4	49.6	1.94	0.003	0.0013	0.0011	0.029	0.037	0.0004	0.038	0.0082	0.002	31 mm Ø x 2 or 18 mm

RESULFURIZED STEEL

= Class, where 1 = CRM and 2 = RM **OES regularly requires extension of preburn time to analyze correctly**

#	Number	S	C	Mn	P	Si	Cu	Ni	Cr	Al	Co	Mo	N	Sn	Ti	V
1	14X MSFMI1	0.414	0.143	1.155	0.0689	0.404	0.1073	0.147	0.89	(0.08)	0.0509	0.264	0.026	0.0289	.	0.0154
1	IMZ 123	0.38	0.25	1.57	0.030	0.23	0.093	0.057	0.16	(0.032)	.	.	0.0171	(0.007)	.	.
1	ECRM 085-1D	0.336	0.067	0.977	0.062	0.008	0.291	.	.	.	0.019	0.0021
1	BS 66L	0.315	0.065	0.844	0.061	0.002	0.007	0.015	0.026	0.0008	0.0035	0.0012	0.0031	(0.0010)	(<0.0010)	0.0006
1	14X I2130A	0.305	0.0871	1.219	0.061	0.022	0.0201	0.0345	0.0505	0.0024	.	0.0102	0.0097	0.0054	.	.
1	IARM 206B	0.293	0.074	1.01	0.050	0.012	0.113	0.053	0.038	0.0025	0.007	0.018	0.0075	0.0064	0.0008	0.0016
1	IARM 199C	0.281	0.469	1.55	0.0155	0.21	0.193	0.085	0.190	0.0019	0.007	0.0293	0.0070	0.0084	0.0016	(0.0037)
1	IMZ 124	0.28	0.10	0.60	0.082	(0.019)	0.060	0.046	0.11	0.005	.	.	0.0059	0.009	.	.
1	BS 1144A	0.271	0.468	1.43	0.0108	0.214	0.147	0.063	0.076	0.0020	0.0064	0.0154	0.0095	0.0079	(0.0008)	0.0015
1	14X MSFM 2K	0.248	0.272	1.568	0.0491	0.353	0.162	0.235	0.996	0.123	0.104	0.355	0.028	0.0218	.	0.0324
1	BS 1144	0.243	0.483	1.55	0.022	0.262	0.462	0.097	0.193	(0.002)	0.011	0.017	0.0093	0.0113	0.002	0.0039
1	14X MSFM 4A	0.224	0.226	1.141	0.0386	0.469	0.429	6.22	1.69	(0.007)	0.0253	0.974	0.0220	0.0141	.	0.0151
1	IMZ 122	0.21	0.27	1.33	0.073	0.43	0.25	0.25	0.19	(0.027)	.	.	0.0110	0.12	.	.
1	14X 606M36TA	0.196	0.378	1.574	0.0159	0.167	0.179	0.0931	0.163	0.0071	.	0.272	0.0095	0.0103	.	.
1	14X 11390A	0.190	0.420	1.040	0.0342	0.198	0.0395	0.0239	0.0609	0.0026	.	0.0067	0.0042	0.0022	.	.
1	ECRM 058-2D	0.1712	0.424	1.186	0.0098	0.1080	0.261	0.199	0.1211	.	.	0.0589	0.0107	.	.	.
1	14X MSFM3G	0.147	0.438	1.809	0.0297	0.292	0.205	0.161	0.454	(0.18)	0.0494	0.390	0.0206	0.0378	.	0.0199
1	IARM 29E	0.121	0.193	1.19	0.0157	0.239	0.253	0.082	0.105	0.0032	0.008	0.0269	0.0093	0.0109	0.0014	0.0255
1	14X 11170A	0.120	0.154	1.129	0.0133	0.151	0.1101	0.0877	0.1126	0.0023	.	0.0317	0.0112	0.0110	.	.
2	BS 65C	0.115	0.150	1.19	0.007	0.24	0.24	0.063	0.066	(0.002)	(0.007)	0.012	0.0084	.	.	0.002
2	BS 66B	0.112	0.418	1.56	0.018	0.017	0.028	0.032	0.193	(0.001)	0.005	0.019	0.0056	0.0016	(0.001)	0.0014
1	IARM 348A	0.102	0.384	1.46	0.0121	0.270	0.230	0.081	0.123	(0.002)	(0.010)	0.026	(0.010)	0.0112	0.0015	0.0029
1	IARM 307A	0.096	0.163	1.44	0.0113	0.281	0.190	0.197	0.104	0.032	(0.010)	0.045	0.0108	0.0090	0.0015	(0.0028)
1	BS 3993	0.094	0.152	1.16	0.012	0.260	0.111	0.045	0.072	0.002	0.006	0.010	0.0071	0.006	(0.0008)	0.002
1	IMZ I21	0.097	0.39	1.18	0.057	(0.056)	0.032	0.029	0.036	0.016	.	.	0.0125	0.059	.	.
2	BS 52D	0.088	0.436	0.97	0.068	0.18	0.060	0.18	0.16	0.028	0.012	0.09	0.0025	0.004	(0.004)	0.002
1	12X 15253T *	0.083	0.225	1.19	0.090	0.35	0.265	1.00	2.03	0.023	0.27	1.02	.	0.31	.	0.275
2	BS 4150MOD	0.079	0.47	0.90	0.024	0.21	0.19	0.15	1.01	0.012	0.012	0.21	0.0087	0.013	(0.002)	0.008
2	BS 42A	0.078	0.52	1.08	0.012	0.258	0.285	0.147	0.80	0.025	(0.007)	0.195	0.008	.	.	0.004
2	BS 42	0.073	0.516	1.24	0.021	0.235	0.252	0.183	0.67	0.020	0.012	0.190	0.0080	0.012	(0.003)	0.003
1	12X 15217Q	0.073	0.176	0.652	0.058	1.390	0.231	0.864	1.24	(0.021)	0.248	0.358	0.078	0.0737	.	0.662
1	12X 15255Q	0.070	0.351	1.191	0.104	1.02	0.279	0.296	1.509	0.073	0.0502	0.1193	0.027	0.101	0.0377	0.475
1	KUT B2/2	0.064	0.065	1.22	0.087	(0.38)	0.32	1.49	.	0.10	.	1.06	.	.	(0.25)	0.87
1	IMZ 125	(0.057)	0.029	0.95	(0.018)	0.15	0.044	0.023	0.18	(0.007)	.	.	.	0.002	.	.
1	KUT A14	0.052	0.12	0.75	0.041	0.73	0.20	1.32	0.59	(0.01)	0.070	0.25	.	0.10	0.12	0.67
1	KUT B16	0.051	0.16	2.05	0.068	1.95	0.09	3.74	0.26	(0.037)	.	0.11	.	.	0.075	0.53
1	KUT B12	0.048	0.43	0.76	0.028	0.34	0.41	1.62	1.32	0.007	0.011	0.21	.	0.032	0.011	0.026
1	KUT B4	0.043	0.55	1.07	0.047	1.72	0.49
1	IARM 381A	0.043	0.272	1.16	0.013	0.269	0.379	0.185	0.129	0.0023	0.011	0.0341	(0.014)	0.0137	(0.002)	0.0299
1	NM 304	0.033	0.19	0.29	0.093	0.082	.	(0.007)

Number	As	B	Bi	Ca	Nb	O	Pb	Sb	W	Zn	Zr	Units
14X MSFMI1	~40 mm Ø x ~15 mm
IMZ 123	0.033	0.030	0.030	.	.	.	40 mm Ø x 40 mm
ECRM 085-1D	0.0010	0.0073	.	0.0025	.	38 mm Ø x 25 or 30 mm
BS 66L	0.0020	(<0.0003)	.	(<0.0010)	(0.0012)	.	0.0007	0.0021	(<0.0010)	.	.	44 mm Ø x ~7 or 19+ mm 17025
14X I2130A	0.0016	~40 mm Ø x ~15 mm
IARM 206B	0.0045	0.0006	.	.	0.002	0.016	(0.001)	(0.002)	(0.003)	.	(0.002)	31 mm Ø x 2 or 18 mm
IARM 199C	0.0059	0.0012	0.003	(0.0011)	0.0016	0.0037	(0.001)	(0.003)	0.0023	(0.0006)	.	31 mm Ø x 2 or 18 mm
IMZ 124	0.004	(0.002)	0.002	.	.	.	40 mm Ø x 40 mm
BS 1144A	0.0052	(0.0003)	Fe:97.3	(0.0005)	(0.002)	0.0019	(0.0006)	(0.002)	(0.0009)	.	(0.0006)	38 mm Ø x ~7 or 19+ mm 17025
14X MSFM 2K	~40 mm Ø x ~15 mm
BS 1144	0.009	.	.	.	(0.004)	0.0016	(0.001)	.	(0.003)	.	last	38 mm Ø x ~16 or 19 mm 17025
14X MSFM 4A	40 mm Ø x 15 mm
IMZ 122	0.007	(0.020)	0.019	.	.	.	40 mm Ø x 40 mm
14X 606M36TA	0.0085	~40 mm Ø x ~15 mm
14X 11390A	0.0028	~40 mm Ø x ~15 mm
ECRM 058-2D	0.0095	38 mm Ø x 25 or 30 mm
14X MSFM3G	.	0.0043	~40 mm Ø x ~15 mm
IARM 29E	0.0085	0.0007	.	0.0012	0.0024	(0.005)	(0.001)	(0.003)	.	(0.004)	.	31 mm Ø x 2 or 18 mm
14X 11170A	0.0044	0.0011	~40 mm Ø x ~15 mm
BS 65C	37 mm Ø x ~7 or ~32 mm last
BS 66B	.	0.0003	41 mm Ø x ~7 or 19+ mm
IARM 348A	(0.007)	(0.0013)	<0.02	0.0010	0.027	(0.003)	(0.002)	(0.003)	(0.009)	<0.003	(0.003)	31 mm Ø x 2 or 18 mm
IARM 307A	0.008	<0.005	<0.02	<0.0005	(0.002)	(0.003)	(0.002)	<0.004	(0.005)	<0.002	(0.002)	31 mm Ø x 2 or 18 mm
BS 3993	0.004	.	.	(0.0002)	.	(0.0030)	38 mm Ø x ~7 or 19+ mm 25(pre-17025)
IMZ I21	0.002	0.011	0.017	.	.	.	40 mm Ø x 40 mm
BS 52D	(0.002)	44 mm Ø x ~7 or 19+ mm
12X 15253T *	.	* Provisional Analysis	.	.	0.365	Ta:0.006	.	.	0.280	.	.	~40 mm Ø x ~15 mm
BS 4150MOD	0.005	0.070	0.0010	.	.	(0.003)	0.0010	38 mm Ø x ~7 or 19+ mm
BS 42A	37 mm Ø x ~7 or 19+ mm
BS 42	(0.004)	.	.	.	(0.002)	.	.	.	(0.002)	.	.	44 mm Ø x ~7 or 19+ mm 17025
12X 15217Q	0.131	.	.	.	0.121	.	.	40 mm Ø x 15 mm
12X 15255Q	0.0193	.	.	.	0.152	.	.	.	0.150	.	.	~40 mm Ø x ~15 mm
KUT B2/2	30-35 mm Ø x 39 mm
IMZ 125	0.065	0.014	.	.	.	40 mm Ø x 40 mm
KUT A14	0.13	0.004	.	.	0.044	.	.	0.047	.	.	.	30-35 mm Ø x 39 mm
KUT B16	0.11	30-35 mm Ø x 39 mm
KUT B12	0.011	0.0035	.	.	0.022	(0.002)	30-

		SILICON STEEL				# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties									
#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Mo	N	Sn	Ti
2	CZ SST-4A	4.73	0.062	0.376	0.031	0.020	0.111	0.082	0.105	0.514	.	0.019	0.0058	0.025	0.035
3	CZ SP-6A	4.65	0.10	0.38	0.017	0.009	0.12	0.04	0.11	0.32	.	0.01	.	0.01	0.008
1	DSZU C047	3.95	0.975	0.402	0.023	0.0052	0.117	0.78	4.44	0.051	.	0.96	0.0164	0.0090	0.059
3	CZ SST-3A	3.27	0.035	0.221	0.007	0.0093	0.096	0.061	0.043	0.009	.	0.036	0.0088	0.015	0.009
1	SRM 1218	(3.2)	0.0029	0.014	(0.002)	0.0011	0.003	(0.002)	0.006	0.005	.	(0.003)	.	.	(0.004)
3	CZ CM-12A	3.21	0.031	0.172	0.0130	0.0106	0.173	0.030	0.067	0.098	.	0.008	0.0070	<0.01	0.005
1	SRM 1135	3.19	0.027	0.094	0.006	0.026	0.056	0.050	0.022	0.0028	.	0.014	.	0.004	.
2	BS 178	3.08	0.436	0.43	0.016	0.001	0.12	0.21	8.17	(0.007)	.	0.044	0.014	(0.007)	0.014
3	CZ SP-5B	3.07	0.20	1.86	0.108	0.023	0.15	3.00	0.38	0.18	.	0.13	.	0.08	0.35
2	CZ SST-2A	3.07	0.083	0.160	0.026	0.0089	0.205	0.066	0.138	0.010	.	0.054	0.0078	0.055	0.016
1	SRM 1134	2.889	0.0261	0.2751	0.0276	0.0095	0.0707	0.0375	0.0198	(0.329)	.	0.0087	.	0.0034	.
2	CZ SST-1A	2.57	0.072	0.062	0.041	0.0043	0.654	0.155	0.209	0.061	.	(0.002)	0.0059	0.110	0.004
1	VS UG4/9	2.23	0.53	1.28	0.017	0.016	0.099	0.71	0.139	0.023	.	0.117	(0.004)	0.081	0.126
1	VS UG91	2.23	0.49	.	0.0038	0.0021	0.057	0.039	0.064	0.048	0.048	0.058	0.010	.	0.038
1	12X 15251U	2.05	1.017	0.910	0.0253	0.0215	0.1194	0.896	0.612	0.1085	.	0.205	0.0031	0.0108	.
1	VS UG92	1.98	0.69	0.79	0.05	0.0029	0.111	0.155	0.200	0.091	0.08	0.119	0.016	.	0.022
1	KUT T4/1	1.97	0.17	0.23	0.012	0.041	0.16	0.077	0.24	(0.005)
1	12X 15259Q	1.81	0.603	0.401	0.0401	0.0704	0.200	4.02	0.512	0.1488	.	0.407	0.0151	0.053	.
1	ECRM 196-2D	1.808	0.0060	0.364	0.00369	0.00065	0.0057	0.0401	0.0282	0.2167	.	0.0142	0.00178	0.00047	0.00253
1	VS UG4/5	1.80	0.56	1.26	(0.008)	(0.006)	0.098	0.68	0.17	0.010	.	0.087	.	.	0.17
1	NCS HS11751a	1.76	0.574	0.792	0.020	0.014	0.011	0.019	0.024
1	ECRM 186-1D	1.72	0.610	0.870	0.022	0.035	0.281	0.190	0.218	0.014	.	0.048	.	.	.
1	BS 300	1.68	0.410	0.721	0.0046	0.0006	0.118	1.867	0.803	0.099	.	0.370	0.0023	0.0053	0.0096
1	12X 44220A	1.662	0.417	0.874	0.0050	0.0009	0.031	1.89	0.846	0.029	.	0.401	0.0030	0.0019	.
3	CZ CM-2A	1.66	0.20	0.97	0.10	0.012	1.01	1.20	1.50	0.03	.	0.33	.	0.08	0.34
1	VS UG111	1.64	0.52	0.625	0.0028	0.0035	0.065	0.036	0.058	0.049	.	0.039	.	.	0.025
1	VS UG1/9	1.63	0.63	0.84	0.030	0.017	0.020	0.105	0.046	0.027	.	0.135	(0.002)	(0.002)	0.069
1	IARM 340A	1.63	0.414	0.755	0.011	0.001	0.103	1.80	0.84	0.062	.	0.39	0.0020	0.005	0.0098
1	IARM 342A	1.63	0.257	1.37	0.006	0.0051	0.110	1.76	0.38	0.019	.	0.42	0.0102	0.021	0.0028
1	VS UG4/10	1.61	0.695	0.834	0.031	0.0060	0.050	0.156	0.130	0.064	.	0.089	0.0192	.	0.0044
1	KUT B1/1	1.58	0.97	0.205	0.017	0.032	0.14	3.96	1.66
1	12X 15261X	1.513	0.546	0.483	0.090	0.0518	0.308	0.0985	0.496	1.648	.	1.594	.	0.0172	0.385
1	VS UG1/10	1.51	0.51	0.659	0.0053	0.0042	0.096	0.190	0.067	0.015	.	0.051	0.0164	0.0030	0.016
2	CZ LA-2D	1.48	0.065	0.26	0.011	0.052	0.53	2.00	0.135	0.18	.	0.57	0.008	0.085	0.30
1	KUT A11/1	(1.46)	0.043	0.21	0.011	0.0137	0.047	0.04	0.02	0.02	.	1.20	.	0.002	0.17
1	VS UG4/6	1.25	0.59	1.23	(0.003)	0.0008	0.169	0.47	0.400	0.032	.	0.083	(0.0005)	0.017	0.131
1	VS UG87	1.25	0.59	1.18	0.026	0.022	0.030	0.50	0.260	0.024	0.02	0.044	0.010	.	0.103
1	VS UG1/5	1.23	0.62	0.79	(0.02)	(0.03)	(0.01)	0.048	0.069	0.022	.	0.061	.	.	0.045
1	VS UG88	1.22	0.62	1.26	0.0026	0.0043	0.171	0.52	0.474	0.01	0.009	0.104	0.020	.	0.107
1	DSZU C046	1.21	0.785	0.257	0.025	0.0153	0.211	1.47	2.67	0.47	.	0.69	0.0099	0.0033	0.115
2	CZ LA-3E	1.19	0.60	0.70	0.044	0.026	0.22	1.01	0.94	0.061	.	0.32	0.010	0.026	0.135
1	KUT A12	1.19	0.031	0.31	0.014	0.082	0.18	2.43	1.25	0.18	.	0.47	.	.	0.05
2	CZ CM-14B	1.18	0.55	1.63	0.017	0.023	0.36	1.10	1.38	0.26	.	0.400	0.0072	0.040	0.36
2	CZ CM-14A	1.15	0.523	1.58	0.051	0.028	0.30	1.14	1.13	0.063	.	0.395	0.0095	0.027	0.40
1	12X 15258P *	1.01	0.40	1.21	0.067	0.032	0.11	0.50	0.61	0.090	.	0.38	.	0.070	.
1	SS 603/2	0.97	0.79	0.236	0.020	0.056	(0.05)	(0.03)	(0.04)	0.076	.	(0.004)	.	.	.
1	SS 405/2	0.947	0.044	0.903	0.0095	0.058	0.022	0.102	0.206	0.330	.	0.025	(0.011)	.	.
1	SS 113	0.931	0.837	1.207	0.0595	0.0294	0.179	0.0784	1.248	0.0151	.	0.056	0.0109	0.0067	0.0390
1	NCS HS11744	0.825	0.092	1.04	0.014	0.066	0.572	1.94	0.166	0.044	.	0.912	.	0.0041	0.049
1	CKD 188A	0.775	0.332	0.169	0.006	0.033	0.057	0.445	5.11	0.093	0.083	1.28	0.0076	0.005	0.034
1	SS 604/2	0.75	0.199	1.91	0.016	0.072	(0.07)	(0.09)	(0.06)	0.008	.	(0.02)	.	.	.
#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Mo	N	Sn	Ti
Number	As	B	Ca	Co	Nb	O	Pb	Sb	Ta	V	W	Zr	Units		
CZ SST-4A	0.004	0.0006	.	0.012	.	.	0.008	(0.003)	.	0.031	0.026	(0.003)	~37	mm	Ø x 25 mm
CZ SP-6A	0.003	.	.	0.003	0.016	0.02	.	~39	mm	Ø x 25 mm
DSZU C047	0.0077	0.0006	0.0013	0.066	0.021	1.84	1.88	.	40	mm	Ø x 25 mm
CZ SST-3A	(0.003)	0.0019	.	0.038	.	Zn:0.011	0.013	.	.	0.041	0.016	.	~37	mm	Ø x 25 mm
SRM 1218	.	.	.	(0.002)	(0.001)	.	(0.002)	32	mm	Ø x 19 mm
CZ CM-12A	0.003	.	.	0.003	<0.01	.	.	~39	mm	Ø x 25 mm
SRM 1135	<0.01	.	.	31	mm	Ø x 19 mm
BS 178	.	(0.0002)	.	0.018	(0.002)	(0.0020)	.	.	.	0.041	0.017	last	~37	mm	Ø x 19 mm
CZ SP-5B	0.19	0.14	.	0.135	0.09	.	0.09	0.07	.	0.71	0.62	.	~39	mm	Ø x 25 mm
CZ SST-2A	.	0.0089	.	0.022	.	Zn:0.011	0.015	0.008	.	0.024	0.019	0.017	~37	mm	Ø x 25 mm
SRM 1134	31	mm	Ø x 19 mm
CZ SST-1A	(0.002)	0.0003	.	0.005	.	.	(0.002)	(0.002)	.	0.006	.	.	~37	mm	Ø x 25 mm
VS UG4/9	(0.001)	(0.0003)	.	.	(0.001)	.	0.008	.	.	0.054	0.061	.	~45	mm	Ø x 28 mm
VS UG91	0.0004	.	.	.	0.097	.	0.00006	0.00009	.	0.049	.	.	~47	mm	Ø x ~30 mm
12X 15251U	.	.	.	0.228	0.266	0.391	0.0393	.	~40	mm	Ø x ~15 mm
VS UG92	0.0027	.	.	.	0.034	.	0.00017	0.0005	.	0.024	.	.	~47	mm	Ø x ~30 mm
KUT T4/1	30-35	mm	Ø x 39 mm
12X 15259Q	.	.	.	0.141	0.249	0.139	0.49	.	~40	mm	Ø x ~15 mm
ECRM 196-2D	0.00033	0.00014	0.00071	0.0138	Mg:0.00075	0.00368	.	Zn:0.00019	38	mm	Ø x 25 mm
VS UG4/5	.	.	.	0.053	0.054	0.14	.	~45	mm	Ø x ~28 mm
NCS HS11751a	40	mm	Ø x 40 mm
ECRM 186-1D	38	mm	Ø x 25 or 30 mm
BS 300	0.0030	0.0003	0.0008	0.0079	0.0031	(0.0004)	(0.000026)	0.0007	(0.0012)	0.070	0.0009	(0.0002)	38mm	Ø x ~7	or 19+mm Fe:93.8
12X 44220A	0.0026	0.0764	.	.	~38	mm	Ø x ~15 mm
CZ CM-2A	0.11	0.0005	.	0.43	0.48	.									

LOW ALLOY STEEL WITH C > 0.3%				CONTINUED ON THE NEXT PAGE							# = Class, where 1=CRM, 2=RM, 3=RM no uncertainties					
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti
1	VS UG0/6	1.40	0.329	(0.006)	(0.003)	0.221	0.286	0.55	0.73	0.129	(0.002)	(0.01)	0.079	.	.	0.0052
1	CKD 182B	1.39	0.370	0.008	0.006	0.126	0.293	2.82	0.122	0.023	0.017	0.171	0.011	0.0049	0.001	0.004
1	CKD 182C	1.36	0.363	0.009	0.008	0.111	0.294	2.80	0.123	0.028	.	0.171	0.012	0.0049	(0.001)	(0.002)
1	VS UG0/9	1.33	0.208	0.0040	0.0045	0.170	0.307	0.36	0.55	0.139	(0.001)	.	0.024	0.0022	0.041	0.029
1	VS UG0/10	1.321	0.268	0.0090	0.0044	0.244	0.265	0.353	0.596	0.101	.	.	0.052	0.0120	0.0033	0.017
1	VS UG0/5	1.32	(0.2)	(0.01)	(0.007)	(0.2)	0.265	0.351	0.60	0.108	.	.	(0.05)	.	(0.01)	(0.01)
1	SS 402/2	1.311	0.288	0.0161	0.0138	0.111	0.302	0.808	0.652	0.161	.	.	0.140	0.0069	.	.
1	ECRM 035-2D	1.277	0.305	0.0038	0.011	0.216	0.0085	0.0190	0.0104	0.0193	.	.	0.0056	0.0230	.	0.0030
1	IMZ 65/2	1.19	0.27	0.013	0.007	0.13	0.059	0.067	0.079	0.030
1	DSZU C049	1.17	0.237	0.0166	0.0147	0.227	0.069	0.044	0.131	(0.005)	.	(0.003)	(0.002)	(0.007)	.	(0.003)
1	KUT A18	1.16	(1.99)	0.014	0.007	0.15	0.066	0.125	0.90	(0.02)	0.035
1	VS UG9/5	1.10	0.25	(0.01)	(0.007)	0.31	0.125	0.183	0.36	0.017	.	.	0.29	.	(0.002)	0.109
3	CZ CM-5B	1.09	1.28	0.021	0.012	0.39	0.13	0.23	2.07	0.083	.	0.022	0.10	0.0135	0.06	0.05
1	14X 72305A	1.085	0.349	0.0128	0.0028	0.206	0.149	0.089	0.425	0.0049	.	.	0.0231	0.0068	0.021	0.173
1	SRM 1761a	(1.05)	0.679	0.042	0.037	0.182	0.298	1.981	0.222	0.055	.	(0.027)	0.103	(0.0042)	.	.
2	CZ CM-5C	1.04	1.17	0.029	0.021	0.54	0.151	0.42	2.45	0.063	.	0.022	0.132	0.014	0.014	0.031
1	VS UG9/9	1.04	0.310	0.0053	0.021	0.319	0.163	0.242	0.310	0.073	(0.003)	.	0.308	0.0027	0.0046	0.130
1	IMZ 172	1.03	0.71	0.018	0.047	0.21	0.128	0.12	4.47	0.062	.	0.012	0.96	0.0192	.	(0.002)
1	NM PC-5	1.03	0.52	0.073	0.073	0.22	.	.	1.19
1	IARM 49E	1.03	0.364	(0.006)	(0.002)	0.248	0.076	0.043	1.43	0.024	.	(0.006)	0.017	(0.003)	(0.003)	0.0060
2	BS 2952	1.03	0.33	0.013	0.014	0.32	0.106	0.135	1.36	0.024	.	0.007	0.044	0.0084	.	0.003
1	12X 52986A	1.023	0.372	0.0049	0.0011	0.246	0.077	0.0411	1.418	0.0258	(0.002)	.	0.0169	(0.002)	.	.
2	BS 53G	1.02	0.35	0.014	0.015	0.23	0.160	0.090	1.53	0.019	.	0.008	0.034	0.0084	.	(0.002)
1	CKD 184A	1.013	2.23	0.028	(0.01)	0.348	0.089	0.250	2.33	0.022	0.016	0.007	0.016	0.0104	0.013	0.010
1	NILAB 100LA D	1.002	0.333	0.012	0.018	.	0.019	0.027	1.517	0.005	.	0.007	0.012	0.0046	.	0.007
1	IRSID 1747	0.990	0.333	0.0078	0.0068	0.222	0.1243	0.0850	1.501	.	0.0392	0.0110	0.0141	0.0084	(0.00025)	0.0041
1	IARM 324A	0.99	1.01	0.009	0.028	0.163	0.22	0.081	0.42	0.002	.	0.007	0.022	0.0082	0.014	0.0016
1	IARM 49D	0.99	0.39	0.0173	0.0059	0.24	0.120	0.061	1.53	0.018	.	(0.006)	0.016	0.0102	0.0009	0.0020
2	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.017	.	0.010	0.029	0.0060	.	0.003
1	KUT B15	0.98	0.69	0.030	0.031	0.80	0.14	0.15	3.70	0.13	.	.	0.21	1.20	.	(0.32)
1	VS UG75	0.98	0.286	0.0127	0.0089	0.248	0.111	0.201	1.43	(0.03)	.	.	(0.01)	.	(0.01)	(0.001)
2	CZ LA-4C	0.95	1.63	0.021	0.012	0.07	0.056	0.045	1.78	0.048	.	(0.006)	0.008	0.012	0.053	(0.002)
1	12X 19965A	0.936	0.600	0.0196	0.0081	0.247	0.148	0.141	1.713	0.0256	.	.	0.210	0.0087	.	.
1	SS 401/2	0.69	1.72	0.025	0.0078	0.02	0.11	0.19	0.74	0.074	.	0.042	0.495	(0.15)	.	.
1	IMZ 119	0.93	1.15	0.018	0.006	0.16	0.042	0.049	0.062	0.010	0.007	.	.	0.0086	.	(0.0007)
1	VS UG89	0.92	0.76	0.0085	0.01	0.385	0.373	0.51	4.20	0.01	0.007	.	0.044	0.017	0.0043	0.012
1	VS UG110	0.91	0.86	0.0063	0.0050	0.342	0.377	0.491	0.47	0.006	.	.	0.0052	.	.	0.0015
1	VS UG21/6	0.83	0.74	(0.02)	(0.02)	0.312	0.346	0.50	0.50
1	12X LA5C	0.83	0.726	0.0077	0.0261	0.493	0.158	0.484	0.678	0.10	.	0.166	0.305	.	.	.
2	IARM 172A	0.78	0.010	0.007	0.004	1.29	0.40	0.025	3.52	0.39	.	0.006	0.014	0.0004	0.004	0.003
1	SS 403/2	0.750	1.677	0.055	0.0381	0.209	0.221	0.223	0.463	0.0485	.	.	0.088	(0.010)	.	.
1	IMZ 64/2	0.75	0.47	0.012	(0.005)	0.22	0.12	0.081	0.090	0.020
1	ECRM 059-2D	0.721	0.845	0.0246	0.0048	0.288	0.074	0.080	0.040	0.0045	0.00020	.	0.0018	0.0051	.	.
2	CZ CM-1C	0.72	1.73	0.023	0.025	0.31	0.18	0.52	0.47	0.034	.	0.026	0.084	0.009	0.054	0.066
2	CZ CM-4B	0.72	1.50	0.023	0.012	0.80	0.40	1.40	2.23	0.025	.	0.115	0.33	0.013	0.071	0.12
1	SS 404/2	0.696	0.532	0.0479	0.0228	1.121	0.427	0.393	0.774	0.017	(0.004)	.	0.307	0.0089	.	.
1	IMZ 118	0.69	1.72	(0.04)	(0.04)	0.25	0.33	0.19	0.19	(0.014)	.	.	0.058	0.0130	.	.
1	IMZ 116	0.64	0.44	0.025	0.035	0.25	0.33	0.022	0.72	0.025	0.012	.	0.074	0.0150	.	(0.0008)
1	VS UG96	0.60	0.52	0.0046	0.0029	0.290	0.256	0.396	0.399	0.031	.	.	0.0042	.	.	0.0025
1	SRM 1764a	0.592	1.193	0.0210	0.0118	0.0595	0.5178	0.2006	1.468	0.0098	.	(0.012)	0.2007	(0.0023)	0.0416	0.0286
1	DSZU C07	0.589	0.903	0.033	0.037	1.00	0.130	0.263	0.201	0.039	.	0.165	0.377	.	0.091	0.059
1	VS UG119	0.58	0.70	0.012	(0.02)	1.63	0.207	0.142	0.195	0.039	.	.	0.0113	0.0047	.	0.0030
1	12X 10550	0.549	0.685	0.0184	0.0055	0.281	0.0290	0.0247	0.338	0.0325	.	.	0.0086	0.0051	.	.
1	12X LA4B	0.537	0.303	0.0363	0.039	0.335	0.334	0.521	0.499	0.057	.	0.105	0.489	0.0222	.	.
1	12X 61500A	0.530	0.912	0.0104	0.0102	0.240	0.157	0.0976	1.023	(0.007)	0.0067	.	0.0195	.	.	.
2	CZ CM-6A	0.52	0.37	0.016	0.058	0.27	0.05	0.19	0.37	0.02	.	0.03	0.04	0.009	0.028	0.03
2	CZ BO-2B	0.515	0.745	0.0093	0.0016	0.309	0.100	0.057	0.212	0.0196	.	0.0055	0.006	0.004	.	0.0017
1	12X LA3C	0.500	1.693	0.0274	0.0442	0.163	0.213	0.280	0.375	0.0410	.	0.0475	0.303	0.0039	.	.
1	IARM 34C	0.50	0.739	0.0090	0.0011	0.30	0.078	0.085	0.914	0.068	.	0.005	0.022	0.0030	0.004	0.0045
2	BS 43A	0.491	0.811	0.008	0.026	0.252	0.184	0.242	0.93	0.003	.	0.008	0.059	0.0074	.	0.002
2	BS 4941	0.490	0.79	0.012	0.017	0.27	0.106	0.074	0.96	0.024	.	0.008	0.039	0.0076	.	.
1	IMZ 103A	0.49	0.78	0.066	0.051	0.42	0.27	0.57	0.58	0.026	.	0.002	0.18	.	0.040	0.17
1	IMZ 117	0.49	0.77	0.038	0.015	0.34	0.41	0.29	0.94	0.023	0.013	.	0.024	0.0154	0.041	(0.0014)
1	BS 1144	0.483	1.55	0.022	0.243	0.262	0.462	0.097	0.193	(0.002)	.	0.011	0.017	0.0093	(0.004)	0.002
1	IPT 503	0.456	0.682	0.027	0.027	0.218	0.129	0.063	0.160	0.018	.	0.006	0.020	0.0082	.	0.0011
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti
1	SRM C1173	0.453	0.174	0.031	0.092	1.38	0.204	4.04	2.63	.	.	.	1.46	.	.	0.037
1	12X 41450A	0.446	1.011	0.0093	0.0031	0.261	0.1318	0.187	1.194	0.0220	.	.	0.340	.	.	.
2	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.41	0.033	.	0.006	0.007	0.0056	(0.002)	(0.002)
1	12X LA3B	0.439	1.176	0.0												

LOW ALLOY STEEL WITH C > 0.3%							CONTINUED FROM THE PREVIOUS PAGE							
Number	As	B	Ca	Fe	Mg	O	Pb	Sb	Sn	Ta	V	W	Zr	Units
VS UG0/6							(<0.0005)	(<0.0005)	0.0032		0.0046			-45 mm Ø x ~28 mm last
CKD 182B	0.005	0.0003					(0.000)	0.001	0.004	0.000	0.027	0.016	0.001	44 mm Ø x 13 or 25 mm
CKD 182C	(0.005)	0.0003					(0.001)	(0.001)	(0.004)	(0.001)	0.028	0.018	(0.001)	44 mm Ø x 13 or 25 mm
VS UG0/9		(0.0002)					(0.002)		(0.0008)		0.0087	0.074		-45 mm Ø x ~28 mm
VS UG0/10									0.0043		0.0037	(0.006)		-45 mm Ø x ~28 mm
VS UG0/5											(0.01)	(0.01)		-45 mm Ø x ~28 mm
SS 402/2											0.194			38 mm Ø x 19 mm
ECRM 035-2D	0.0017													40 mm Ø x 20 mm
IMZ 65/2														40 mm Ø x 40 mm
DSZU C049	(0.004)	(0.0002)	(0.003)						(0.004)		(0.003)			40 mm Ø x 25 mm
KUT A18	0.003	(0.011)						0.005	0.016		0.10			30-35mm Ø x 39 mm
VS UG9/5											0.19	1.63		-45 mm Ø x ~28 mm
CZ CM-5B	0.018	0.002					0.01	0.006	0.012		0.06	0.03	0.09	-37 mm Ø x 25 mm
12X 72305A									0.0101		0.0545			-40 mm Ø x 15 mm
SRM 1761a	(0.011)	0.0023		(95)				(0.0052)	(0.050)	(0.050)	0.054		0.012	34 mm Ø x 19 mm
CZ CM-5C	0.020	0.0012	(0.0006)				0.009	0.005	0.018		0.106	0.034	(0.07)	-39 mm Ø x 25 mm
VS UG9/9		(0.0002)					(0.002)		(0.001)		0.215	1.60		-45 mm Ø x ~28 mm
IMZ 172									0.010		0.20	0.011		40 mm Ø x 40 mm
NM PC-5														40 mm Ø x 20 mm
IARM 49E	0.0029								0.0065		0.066			31 mm Ø x 2 or 18 mm
BS 2952	0.004		0.0003					0.003	0.006		0.005			44 mm Ø x ~7 or 19+ mm
12X 52986A									0.063		0.065			-38 mm Ø x ~15 mm
BS 53Z	0.004	(0.0001)	(0.0001)						0.007		0.006		(0.13)	44 mm Ø x ~7 or 19+ mm
CKD 184A	0.006	0.0005							0.008	0.000	0.017	(0.001)	(0.002)	44 mm Ø x 13 or 25 mm
NILAB 100LA D	0.004						(0.000)	0.002	0.008		0.004			34 mm Ø x 20 mm
IRSID 1747	0.0170	(0.00015)	(0.00030)		(0.00022)		(0.00025)	(0.0034)	0.0105		0.0046		(0.0001)	37 mm Ø x 30 mm
IARM 324A	0.006	0.0004	0.0009		0.003		(0.002)		0.011		0.0017	(0.003)	(0.001)	31 mm Ø x 2 or 18 mm
IARM 49D	0.004	(0.0004)			0.0008		(0.0004)	0.0016	0.0076	(0.001)	0.0034	(0.004)		31 mm Ø x 2 mm
BS A485-1	0.006					(0.0008)			0.011		0.003			39 mm Ø x ~7 or 19+ mm
KUT B15											(0.33)			30-35mm Ø x 39 mm
VS UG75											(0.006)	(0.02)		-40 mm Ø x ~26 mm
CZ LA-4C	(0.003)	0.0005							(0.006)		(0.010)	0.008		-37 mm Ø x 25 mm
12X 19965A									0.0070		0.0087		Zn:0.0008	-41 mm Ø x ~15 mm
SS 401/2											0.496			38 mm Ø x 19 mm
IMZ 119			(0.0002)								0.006			40 mm Ø x 40 mm
VS UG89	0.0043						0.0003	0.0011			0.021			-47 mm Ø x ~30 mm
VS UG110												0.004		-45 mm Ø x ~25 mm
VS UG21/6														-45 mm Ø x ~28 mm
12X LA5C	0.0085						0.0085		0.0100		0.579		Zn:0.0091	-40 mm Ø x ~15 mm
IARM 172A	(0.005)	0.0003				0.0006	(<0.01)		0.003		0.003	0.038		31 mm Ø x 2 or 18 mm
SS 403/2											0.341			38 mm Ø x 19 mm
IMZ 64/2														40 mm Ø x 40 mm
ECRM 059-2D											0.059			40 mm Ø x 40 mm
CZ CM-1C	0.036	0.0020	0.0007				0.005	0.01	0.012		0.073	0.064	0.051	38 mm Ø x 25 mm 30 mm
CZ CM-4B	0.015	0.017					0.022	0.052	0.028		0.18	0.116	Zn:0.007	-39 mm Ø x 25 mm
SS 404/2			(0.0002)								0.107			38 mm Ø x 19 mm
IMZ 118									0.22		0.076			40 mm Ø x 40 mm
IMZ 116											0.076			40 mm Ø x 40 mm
VS UG96											0.0030			-40 mm Ø x ~28 mm
SRM 1764a	0.0100	(0.0010)		(95.1)					(0.024)	0.0297	0.1063	(0.0016)	(0.0012)	34 mm Ø x 19 mm
DSZU C07	(0.0005)	0.005					(0.0003)	(0.0005)	(0.0026)		0.988	0.140		40 mm Ø x 30 mm last
VS UG119														-45 mm Ø x ~25 mm
12X 10550	0.0059								0.0018				Zn:(0.0016)	-40 mm Ø x ~15 mm
12X LA4B											0.328	0.091		42 mm Ø x 15 mm
12X 61500A									0.0114		0.110		Zn: 0.0055	-38 mm Ø x ~15 mm
CZ CM-6A	0.025	0.015					0.017	0.03	0.017		0.05	0.04	0.04	-39 mm Ø x 25 mm
CZ BO-2B	0.0057		(0.0008)						0.0062		(0.001)	(0.005)		-37 mm Ø x ~25 mm
12X LA3C	0.0301	Zn:(0.004)					(0.004)				0.157		0.0197	-40 mm Ø x ~15 mm
IARM 34C	0.0024	0.0003	(0.0004)			0.0008	(0.0003)	(0.001)	0.0058		0.206	(0.003)	(0.001)	31 mm Ø x 2 or 18 mm
BS 43A									0.011		0.148			41 mm Ø x ~7 or 19+ mm
BS 4941	(0.004)		(0.0002)			0.0017			0.006		0.164			41 mm Ø x ~7 or 19+ mm
IMZ 103A		0.006							(0.005)		0.17			40 mm Ø x 40 mm
IMZ 117			(0.0002)								0.087			40 mm Ø x 40 mm
BS 1144	0.009					0.0016	(0.001)		0.0113		0.0039	(0.003)	last	38 mm Ø x 15 or 19 mm 17025
IPT 503							0.008							35 mm Ø x 20 mm
SRM C1173											0.42			32 mm Ø x 19 mm
12X 41450A	0.0053								0.0090		0.0385			-38 mm Ø x ~15 mm
BS XCCV	0.002					(0.0018)	(<0.0006)	(0.0003)	(0.0004)		(<0.003)		(<0.0002)	36 mm Ø x ~7 or 19+ mm
12X LA3B		0.0015					0.0149			Zn:0.0098	0.157		(0.027)	-40 mm Ø x ~15 mm
NM PC-4														40 mm Ø x 20 mm
IARM 30H	0.0046	(0.0007)	(0.0009)		(0.001)	(0.0016)	(0.0005)	0.0013	0.008		(0.0040)	(0.007)	(0.002)	31 mm Ø x 2 or 18 mm
IARM 305B	(0.006)	0.0006	0.0007		(0.002)	0.0006	(0.0003)	(0.004)	0.011		0.004	(0.004)	0.0011	31 mm Ø x 2 or 18 mm
IARM 252D	0.0053	(0.0002)	(0.001)		(0.0002)	(0.0013)	(0.0004)	0.0024	0.012		0.0022	(0.004)	(0.0013)	31 mm Ø x 2 or 18 mm
BS 4340A	0.0059	(0.0002)	(0.0002)	95.4	0.0004	0.0007	(0.0003)	(0.0018)	0.0081		0.0024	0.0005	0.0016	38 mm Ø x ~7 or 19+ mm 17025
SRM 1173											0.42			32 mm Ø x 19 mm
HRT FE2015-N											0.006			35 mm Ø x 20 mm
BS 4340	0.0043	(0.0002)	0.0005	95.5	(0.0002)	0.0012	(0.0002)	(0.0013)	0.0063		0.0033	0.0012	0.0005	38 mm Ø x ~7 or 19+ mm 17025
IARM 252C	0.004	(0.0001)	(0.0003)			(0.002)	0.001	<0.005	0.007		0.005	<0.005	<0.002	31 mm Ø x 2 mm
BS 4942	0.005		0.0006			(0.0021)			0.004		0.28			38 mm Ø x ~7 or 19+ mm last
IARM 252E	0.0046								0.0075		(0.0028)			31 mm Ø x 2 or 18 mm
BS 1962	0.007		25(pre-17025)		(0.0001)		(0.001)		0.010		0.004			41 mm Ø x ~7 mm
VS UG116														-45 mm Ø x ~25 mm
IARM 252F	(0.006)								0.006		(0.003)	(0.003)		31 mm Ø x 2 or 18 mm
IARM 30J	(0.002)								0.0109		0.0045	(0.005)		31 mm Ø x 2 or 18 mm
BS 67C						(0.0014)			0.010		0.0022			38 mm Ø x ~7 or 19+ mm
SS 114	0.0025	0.0008							0.041		0.0086		0.0051	44 mm Ø x 19 mm
IMZ 55/1A		0.0018							0.017		0.110			40 mm Ø x 20 mm
IARM 31G	(0.004)	0.0004							0.0077		0.0036	(0.004)	(0.0012)	31 mm Ø x 2 or 18 mm
IMZ 63/2														40 mm Ø x 40 mm
SS 225/2														38 mm Ø x 19 mm
IPT 504														36 mm Ø x 20 mm
12X 826M40A	0.0056								0.0085					-38 mm Ø x ~15 mm
DSZU C06	(0.003)	0.003					(0.002)		(0.006)		0.072	0.026	(0.0001)	40 mm Ø x 30 mm
BS 4942A	0.0031	(0.0001)	0.0012	96.8	0.0004	0.0020	(0.0007)	(0.001)	0.0044		0.280	(0.0009)	(0.001)	38 mm Ø x

LOW ALLOY STEEL WITH 0.13 % < C < 0.3 % - CONTINUED ON THE NEXT PAGE #=Class, where 1=CRM and 2=RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
1	SRM 330A	0.299	1.00	(0.005)	(0.001)	0.273	0.074	1.80	0.90	0.045	.	(0.003)	0.0063	0.404	0.0024	0.0039	0.071
1	IARM 1269	0.298	1.35	0.012	0.0061	0.189	0.095	0.108	0.201	0.016	.	.	0.036	0.036	.	.	0.004
1	12X 352D	0.298	0.627	0.066	0.125	0.338	0.144	0.334	0.423	0.146	.	0.0095	0.0504	0.257	.	0.105	0.0584
1	ECRM 086-1D	0.297	0.879	0.024	0.037	0.206	0.320	0.168	0.150	.	.	0.023	.	0.150	.	0.026	.
1	12X 16604A *	0.295	0.455	0.006	0.002	0.240	0.135	1.88	1.92	0.013	.	.	0.040	0.34	0.004	0.006	0.007
2	CZ CM-3A	0.295	0.37	0.016	0.0013	0.27	0.16	1.82	1.87	0.05	.	0.005	0.012	0.33	0.007	0.007	0.007
1	VS UG9/10	0.294	0.616	.	(0.003)	0.235	0.169	0.144	0.170	0.280	.	.	0.282	0.015	0.017	0.007	1.25
2	HRT FE2000-N	0.294	0.49	0.014	0.007	0.30	0.07	1.96	1.99	0.025	.	.	0.012	0.34	.	.	0.017
1	VS RG27/1	0.290	0.74	0.044	0.0043	0.28	0.208	0.142	1.83	1.07	.	.	0.025	0.191	.	.	0.072
1	IMZ 178	0.29	0.65	0.016	0.003	0.28	0.140	2.09	1.26	0.051	.	.	0.015	0.20	0.0160	0.011	0.011
1	SRM 1225	0.274	0.48	0.007	0.014	0.221	.	0.018	0.91	.	.	.	0.166	.	.	.	0.004
1	BS HiCal-1	0.271	1.00	(0.007)	0.0007	1.29	0.152	3.28	1.55	0.070	.	0.0022	0.0024	0.379	.	(0.0002)	0.0027
1	IARM 380A	0.268	1.24	0.021	0.025	0.181	0.265	0.114	0.192	0.0029	.	(0.007)	(0.010)	0.059	(0.012)	0.0117	0.0475
2	RM Fe 2/4	0.26	0.61	0.039	0.016	0.30	0.30	0.68	0.70	(0.001)	.	0.04	0.29	0.47	0.020	0.04	0.46
2	BS 69B	0.258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.024	.	.	0.035	0.39	0.0057	0.006	(0.002)
1	12X 12750U	0.258	0.510	0.0078	0.0053	0.599	0.106	0.786	0.792	0.253	.	.	0.581	0.088	.	0.110	0.102
1	12X 32550A	0.257	1.350	0.0061	0.0054	1.59	0.108	1.750	0.377	0.0178	.	0.0054	.	0.417	0.0101	0.0206	0.0222
1	IARM 195B	0.255	1.84	0.018	0.005	1.16	0.52	1.00	0.216	0.029	.	0.021	0.101	0.052	0.0070	0.084	0.082
2	BS 6418	0.255	1.42	0.010	0.004	1.54	0.11	1.74	0.34	0.027	.	0.0044	0.010	0.42	0.0066	0.006	0.003
1	IARM 380B	0.243	1.27	0.016	0.027	0.238	0.307	0.182	0.153	(0.0021)	.	0.0058	0.014	0.055	(0.013)	0.0132	0.049
1	IMZ 113	0.24	0.50	0.022	0.025	0.10	0.11	0.13	1.25	0.007	0.004	.	.	0.050	0.0154	.	0.039
1	DSZU C043	0.239	2.18	0.054	0.070	0.114	0.50	2.93	0.44	0.071	.	0.0017	0.005	0.146	0.0100	0.0023	0.366
1	12X 722M24A	0.236	0.510	0.0135	0.0199	0.262	0.200	0.208	3.094	0.0187	.	0.0075	.	0.497	.	0.0116	0.0080
1	VS UG6/5	0.232	0.39	(0.006)	(0.008)	0.51	0.257	(0.2)	1.85	(0.4)	.	.	(0.2)	.	.	.	0.34
1	IARM 229B	0.220	0.858	0.0073	0.0106	0.329	0.0153	0.030	0.017	0.025	.	(0.002)	0.0116	0.495	0.0072	0.0012	0.0059
1	ECRM 197-1D	0.219	0.792	0.0073	0.0232	0.275	0.152	0.148	0.451	0.0313	.	0.0083	0.0135	0.402	0.0114	0.0097	.
2	BS 3961	0.215	0.565	0.016	0.022	0.236	0.133	1.67	0.510	0.022	.	.	(0.010)	0.27	0.0079	(0.008)	(0.002)
2	TL 1668	0.2146	1.643	0.0137	0.0012	1.645	0.0108	0.0164	0.0173	0.0371	.	0.0016	0.0031	(0.0014)	0.0043	0.0047	0.0016
1	DSZU C048	0.212	0.467	0.0102	0.0059	0.273	0.262	0.105	0.175	0.0293	.	0.0085	0.015	0.016	(0.011)	0.016	.
1	IPT 502	0.210	0.823	0.018	0.026	0.198	0.121	0.408	0.485	0.024	.	.	0.0083	0.155	0.0069	.	.
1	BS 8620E	0.210	0.800	0.011	0.0238	0.255	0.186	0.564	0.541	0.027	.	0.0044	0.0068	0.223	0.0080	0.011	0.0024
1	BS 8620F *	0.21	0.84	0.009	0.032	0.24	0.23	0.43	0.54	0.04	.	<0.05	<0.05	0.2	<0.05	<0.05	<0.05
1	IARM 33D	0.209	0.593	0.009	0.023	0.207	0.072	1.78	0.139	0.026	.	0.0035	0.008	0.229	0.0053	0.005	0.002
2	BS 3952	0.208	0.546	0.011	0.021	0.264	0.202	0.112	0.105	0.048	.	.	0.519	(0.0005)	.	.	.
1	ECRM 187-2D	0.2038	1.257	0.0066	(0.0300)	0.2111	0.1288	0.1755	1.132	0.0223	.	0.0057	0.0112	0.0623	0.0105	0.0237	0.0122
1	BS 9325A	0.203	0.969	0.0079	0.0045	0.612	0.163	3.29	1.50	0.0056	.	0.0024	0.0093	0.358	0.0076	(0.0003)	(0.0024)
1	BS 4820A	0.203	0.64	0.008	0.014	0.185	0.212	3.28	0.116	0.029	.	0.006	0.008	0.203	0.0076	0.0097	0.0010
1	SRM 1763A	0.202	1.584	0.0123	0.022	0.633	0.042	0.513	0.498	0.0435	.	0.055	0.093	0.490	(0.0045)	(0.011)	0.307
1	VS RG29/1	0.202	0.29	.	0.0090	0.22	1.25	4.71	0.89	0.0050	.	.	0.115	1.01	.	.	0.40
1	VS RG31/1	0.200	0.191	0.0039	0.0058	0.28	0.39	2.12	1.28	0.30	.	.	0.273	0.30	.	.	0.200

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
1	KUT B3	0.20	0.14	(0.012)	0.025	0.53	0.25	.	5.94	1.16
1	VS UG5/5	(0.2)	0.52	(0.005)	(0.03)	0.145	0.37	0.42	1.42	0.19	.	.	.	0.44	.	.	0.29
1	IARM 155F	0.199	0.617	0.008	(0.013)	0.223	0.219	3.36	0.144	0.0356	.	(0.006)	0.012	0.244	(0.005)	0.0084	0.0015
1	12X 86200A	0.198	0.849	0.0110	0.0104	0.299	0.213	0.598	0.602	0.0305	.	0.0051	0.224	0.224	0.0091	0.0100	0.0045
1	12X LA2E	0.195	0.57	0.0241	0.0263	0.678	0.786	0.783	0.813	1.381	.	0.282	0.0306	0.136	0.0173	0.0066	0.0990
1	IMZ 112	0.195	0.43	0.022	0.016	0.27	0.055	0.046	0.034	0.034	0.024	.	.	0.043	0.010	0.15	0.045
1	12X 349D	0.194	0.498	0.0162	0.0232	0.201	0.106	0.289	0.268	0.149	.	0.0096	0.021	0.123	.	0.153	0.0172
1	VS UG8/10	0.192	1.81	0.0064	(0.005)	0.61	0.198	0.348	0.729	0.082	.	.	.	0.030	0.0185	0.0052	.
1	VS UG114	0.190	1.65	0.010	0.0074	0.59	0.173	0.345	1.03	0.146	.	.	.	0.016	.	.	0.0031
2	BS 51F	0.190	0.52	0.016	0.018	0.24	0.231	1.68	0.157	0.021	.	(0.0024)	0.009	0.224	0.0060	0.009	0.003
1	IMZ 162	0.19	1.31	0.021	0.014	0.59	0.077	1.64	0.91	(0.040)	.	.	.	0.52	.	.	0.045
1	VS UG113	0.189	1.55	0.0087	0.0070	0.59	0.185	0.186	1.12	0.263	.	.	.	0.010	.	.	0.0040
2	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.032	.	0.0084	0.012	0.24	0.0078	0.013	(0.0008)
1	ECRM 192-1D	0.1875	1.377	0.0029	0.0010	0.219	0.0453	0.755	0.0717	0.0306	0.0285	.	0.0055	0.482	0.0118	.	.
1	VS UG112	0.186	1.63	0.0065	0.0050	0.60	0.157	0.185	0.98	0.026	.	.	.	0.021	.	.	0.014
1	DSZU C08	0.184	0.756	0.019	0.008	0.389	0.550	(6.6)	2.34	0.011	.	(0.011)	0.062	0.514	.	(0.014)	0.216
2	BS LF3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.017	.	0.006	0.056	0.056	0.0054	0.006	(0.002)
2	HRT FE2012-N	0.18	0.70	0.010	0.008	0.31	0.14	0.13	0.25	0.030	.	.	0.26
1	IMZ 74A	0.179	1.19	0.008	0.010	0.34	0.209	0.130	0.197	0.012	.	.	0.0043	0.047	0.0118	.	0.072
1	12X 19MNV56A	0.174	1.563	0.0114	0.0245	0.357	0.203	0.110	0.1087	0.0101	.	.	.	0.0270	0.0210	0.0214	0.0939
1	ECRM 087-1D	0.174	0.671	0.010	0.046	0.263	0.171	0.118	0.078	.	.	0.024	0.015	0.021	.	0.017	.
1	12X 15180A	0.170	1.196	0.0110	0.0022	0.212	0.141	0.1030	0.118	0.018	.	0.0117	.	0.0231	0.0051	0.0115	.
2	HRT FE2013-N	0.17	0.57	0.013	0.010	0.33	0.09	1.45	1.52	0.026	.	.	0.26
1	ECRM 194-2D	0.1694	1.282	0.0137	0.00049	0.2974	0.0313	0.3316									

LOW ALLOY STEEL WITH 0.13 % < C < 0.3 %

CONTINUED FROM THE PREVIOUS PAGE

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
IARM 330A	0.0003	0.0010	.	.	(0.003)	(0.0009)	(0.0004)	(0.001)	.	0.006	(0.004)	.	0.0015	31 mm Ø x 2 mm
SRM 1269	0.005	32 mm Ø x 19 mm
12X 352D	0.285	0.223	.	.	-40 mm Ø x -15 mm
ECRM 086-1D	38 mm Ø x 25 or 30 mm
12X 16604A *	-40 mm Ø x -15 mm
CZ CM-3A	0.0002	.	.	.	0.006	0.006	0.015	.	.	-39 mm Ø x 25 mm
VS UG9/10	0.163	1.34	.	.	-45 mm Ø x -28 mm
HRT FE2000-N	.	0.0015	0.025	.	.	40 mm Ø x 20 mm
VS RG27/1	0.110	0.170	.	.	-45 mm Ø x -28 mm
IMZ 178	0.105	0.017	.	.	40 mm Ø x 40 mm
SRM 1225	32 mm Ø x 19 mm
BS HiCal-1	(0.0001)	0.0140 [91.9]	(0.0003)	(0.002)	(0.002)	(0.0005)	.	.	.	0.0037	(0.0009)	.	(0.0008)	38 mm Ø x -30 mm 17025
IARM 380A	(0.0020)	(0.009)	.	.	31 mm Ø x 2 or 18 mm
RM Fe 2/4	(0.0027)	<0.001	.	.	(0.011)	.	<0.02	<0.03	.	(0.0065)	0.19	.	<0.02	40 mm Ø x 40 mm
BS 69B	(0.002)	.	.	.	38 mm Ø x ~7 or 19+ mm
12X 12750U	0.111	0.159	0.100	.	.	-40 mm Ø x -15 mm
12X 32550A	-38 mm Ø x -15 mm
IARM 195B	0.0039	0.0002	.	.	0.007	0.0017	0.002	0.011	.	0.002	0.38	.	0.002	31 mm Ø x 18 mm last
BS 6418	0.0012	.	.	.	0.003	.	.	.	57 mm Ø x ~7 or 19+ mm
IARM 380B	(0.0016)	0.0011	(0.003)	.	.	31 mm Ø x 2 or 18 mm
IMZ 113	40 mm Ø x 40 mm
DSZU C043	(0.0005)	0.0005	.	.	0.004	0.046	0.082	.	.	40 mm Ø x 25 mm
12X 722M24A	0.0028	.	-38 mm Ø x -15 mm
VS UG6/5	(0.01)	(0.01)	0.16	.	.	-45 mm Ø x -28 mm
IARM 229B	(0.0006)	(0.0003)	.	.	(0.0019)	(0.0017)	(0.0005)	(0.0006)	(0.003)	0.0019	(0.003)	.	(0.0008)	31 mm Ø x 2 or 18 mm
ECRM 197-1D	0.0005	.	.	.	38 mm Ø x 25 mm
BS 3961	<0.003	.	.	.	44 mm Ø x -7 or 19+ mm
TL 1668	(0.00024)	0.0019	.	(0.0003)	(0.0002)	.	(0.0007)	(0.0003)	.	0.0032	.	0.0008	(0.0003)	37 mm Ø x 25 mm
DSZU C048	.	(0.0017)	40 mm Ø x 25 mm
IPT 502	0.0016	.	.	.	36 mm Ø x 20 mm
BS 8620E	(0.0003)	0.0010	97.2	(0.0003)	(0.002)	0.0016	(0.0008)	0.0015	(0.0004)	0.0016	0.0008	17025	(0.0008)	38 mm Ø x ~7 or 19+ mm
BS 8620F *	.	* Provisional Analysis	<0.0005	<0.05	<0.05	<0.05	<0.005	.	.	<0.05	<0.05	.	<0.005	38 mm Ø x -7 or 19+ mm
IARM 33D	0.0002	(0.0003)	.	.	0.002	0.0013	<0.001	(0.002)	.	0.003	<0.005	.	<0.002	31 mm Ø x 2 or 18 mm
BS 3952	39 mm Ø x ~7 or 19+ mm
ECRM 187-2D	0.00048	39 mm Ø x 28 mm
BS 9325A	(0.0001)	0.0039	92.8	(0.0002)	0.0017	(0.0003)	.	(0.010)	.	0.0030	0.024	17025	(0.001)	-40 mm Ø x -30 mm
BS 4820A	0.0002	0.0003	.	0.0003	(0.002)	0.0011	(0.0002)	0.0024	(0.011)	0.0012	(0.002)	17025	.	38 mm Ø x -7 or 19+ mm
SRM 1763a	0.0054	.	(95.3)	.	0.100	.	.	(0.011)	(0.012)	0.308	(0.002)	.	0.044	34 mm Ø x 19 mm
VS RG29/1	0.044	0.020	0.62	.	.	-45 mm Ø x -28 mm
VS RG31/1	0.21	0.39	.	.	-45 mm Ø x -28 mm

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
KUT B3	1.19	.	.	30-35mm Ø x 39 mm
VS UG5/5	(0.01)	(0.003)	0.38	.	.	-45 mm Ø x -28 mm
IARM 155F	0.0016	(0.003)	.	.	.	0.0020	(0.004)	.	.	31 mm Ø x 2 or 18 mm
12X 86200A	-38 mm Ø x -15 mm
12X LA2E	-40 mm Ø x -15 mm
IMZ 112	0.013	0.010	.	.	.	40 mm Ø x 40 mm
12X 349D	0.101	0.049	.	.	-40 mm Ø x -15 mm last
VS UG8/10	(0.003)	0.0034	.	.	.	-45 mm Ø x -28 mm
VS UG114	0.006	.	.	0.065	-45 mm Ø x -25 mm
BS 51F	(0.0001)	(0.0005)	.	(0.0001)	(0.0005)	0.0020	(0.00007)	(0.0011)	.	(0.0012)	(0.0030)	(0.0002)	.	38 mm Ø x ~7 or 19+ mm
IMZ 162	0.12	.	.	.	40 mm Ø x 40 mm
VS UG113	0.006	0.007	.	0.169	-45 mm Ø x -25 mm
BS 4620	0.00006	0.0001	.	0.0001	0.0001	0.0009	0.0002	0.0024	.	0.0026	0.0009	0.0002	.	38 mm Ø x ~7 or 19+ mm
ECRM 192-1D	-35 mm Ø x -30 mm
VS UG112	0.0028	0.005	.	0.0047	-45 mm Ø x -25 mm
DSZU C08	0.011	.	.	.	0.122	0.060	0.966	(0.003)	(0.006)	40 mm Ø x 30 mm last
BS LF3	0.0001	(0.0001)	.	.	.	0.004	38 mm Ø x ~7 or 19+ mm
HRT FE2012-N	40 mm Ø x 20 mm
IMZ 74A	(0.002)	(0.0004)	.	.	0.041	0.022	.	.	.	43 mm Ø x 20 mm
12X 19MNV56A	-40 mm Ø x -15 mm
ECRM 087-1D	0.0046	38 mm Ø x 25 or 30 mm
12X 15180A	0.0016	.	-40 mm Ø x -20 mm
HRT FE2013-N	34 mm Ø x 20 mm
ECRM 194-2D	0.00155	.	.	.	0.0290	0.00322	.	.	.	39 mm Ø x 28 mm
BS 3962	37 mm Ø x ~7 or 19+ mm
CZ CM-8A	0.004	.	.	.	0.034	(0.001)	0.01	.	.	-39 mm Ø x 25 mm
HRT FE1999-N	0.0002	.	.	.	0.002	0.001	.	.	.	40 mm Ø x 20 mm
BS XCCT	(0.001)	(0.005)	<0.001	(0.0004)	.	(0.002)	.	.	<0.002	36 mm Ø x ~7 or 19+ mm
IMZ 176A	(0.015)	.	.	40 mm Ø x 40 mm
12X 12747U	0.072	0.030	.	.	42 mm Ø x 15 mm
BS 15A	(0.0002)	(0.0005)	.	.	0.041	.	(0.0003)	(0.003)	.	0.008	(0.004)	.	0.022	32 mm Ø x 17 mm last
RM Fe C/2	0.0030	(0.0013)	.	.	0.0073	.	.	0.0190	.	0.0074	0.34	.	0.010	40 mm Ø x 40 mm
ECRM 193-1D	0.0232	(0.0013)	.	.	.	36-41 mm Ø x 28-35 mm
BS 1972	(0.0001)	(0.0002)	.	.	(0.001)	(0.0026)	(0.001)	(0.004)	.	(0.003)	(0.004)	.	.	39 mm Ø x ~7 or 19+ mm
BS 47A	0.002	(0.003)	.	.	.	0.003	.	.	.	38 mm Ø x ~7 or 19+ mm

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
--------	---	----	----	----	----	---	----	----	----	----	---	----	----	-------

LOW ALLOY STEEL WITH C < 0.13 %

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Sn	V
1	IMZ 76	0.129	1.37	0.022	0.011	0.24	0.057	0.33	0.12	0.011	.	.	0.101	.	.	(0.006)
1	VS UG86	0.129	0.217	(0.005)	(0.007)	(0.3)	0.62	1.94	1.52	.	.	.	0.311	.	.	0.327
1	BS 1982	0.128	0.441	0.012	0.026	0.255	0.177	0.197	2.09	0.021	.	0.010	0.89	0.0097	0.013	0.003
1	12X 15256Q	0.123	0.492	0.0125	0.0163	0.190	0.0550	5.33	0.362	0.1300	.	0.493	0.0740	0.0056	0.107	0.619
1	12X 93106A	0.122	0.605	0.0071	0.0103	0.206	0.199	3.255	1.107	0.0246	.	.	0.0879	0.0098	0.0094	0.0029
2	BS 47B	0.122	0.39	0.014	0.022	0.22	0.12	0.105	4.78	0.018	.	.	0.45	0.023	0.006	0.004
1	DSZU C042	0.120	0.562	0.0123	0.0058	0.319	0.131	0.203	0.962	0.023	.	0.009	0.286	0.0100	0.0064	0.178
1	CKD 187C	0.118	0.530	0.035	0.013	0.588	0.041	0.085	3.50	0.038	.	0.071	0.563	(0.0153)	0.014	0.559
1	VS UG115	0.115	0.43	0.0084	0.012	0.227	0.173	1.63	0.81	0.024	.	.	0.0126	0.013	.	.
1	IMZ 71	0.114	0.54	0.018	0.011	0.49	0.88	0.041	0.46	0.014	.	.	0.008	.	.	0.045
1	IMZ 75	0.114	0.37	0.081	0.016	0.58	0.45	0.039	0.41	0.020	.	.	0.015	.	.	(0.007)
1	IMZ 75A	0.112	0.394	0.080	0.016	0.618	0.428	0.041	0.401	0.009	.	0.0037	0.018	0.0024	0.023	0.013
1	SRM 1138a	0.11	0.35	0.035	0.056	0.25	0.09	0.10	0.13	.	.	.	0.05	.	.	0.02
1	BS 9905	0.107	0.333	0.008	0.008	0.327	0.115	0.123	8.22	0.017	.	0.016	0.90	0.055	0.009	0.236
1	VS UG6/10	0.107	0.225	0.0068	0.0067	0.342	0.626	2.04	1.41	0.46	.	.	0.339	0.0156	0.0023	0.194
1	12X 12748U	0.106	0.902	0.0309	0.050	0.221	0.347	0.376	0.401	0.111	.	0.323	0.329	.	0.080	0.0499
1	IPT 500	0.106	0.844	0.016	0.0048	0.282	0.270	0.018	0.612	0.046	.	0.0046	0.0013	0.0092	0.002	0.003
1	12X LA1B	0.104	1.262	0.0090	0.060	0.777	0.0572	0.210	1.026	0.0104	.	0.0144	0.068	0.0144	.	0.448
1	KUT A13	0.104	0.49	0.053	0.073	0.81	0.166	1.93	0.14	0.042	.	0.011	0.91	.	0.060	0.23
1	VS UG6/6	0.104	0.227	(0.007)	(0.007)	0.337	0.616	2.05	1.40	0.47	.	(0.008)	0.34	.	0.0023	0.193
2	BS 58E	0.100	0.63	0.009	0.002	0.29	0.154	3.22	1.40	0.029	.	0.013	0.110	0.0033	0.003	0.006
1	IMZ 175	0.099	0.25	0.016	0.0040	0.22	0.130	3.12	0.515	0.043	.	(0.013)	0.025	0.0099	0.011	0.014
2	BS 58C	0.098	0.57	0.011	0.014	0.29	0.14	3.20	1.29	(0.055)	.	.	0.11	.	(0.012)	.
1	IMZ 73	0.097	0.68	0.019	0.013	0.12	0.17	0.13	0.079	0.010	.	.	0.013	.	.	0.022
1	KUT T3/2	0.09	0.60	0.058	0.033	0.66	0.10	0.11	0.40
1	VS UG5/10	0.088	0.177	0.0067	0.0055	0.135	0.490	1.87	1.51	0.47	.	.	0.049	0.0059	0.0036	0.121
1	IARM 268B	0.087	0.58	0.011	0.035	0.21	0.31	0.127	0.094	0.002	.	0.003	0.033	0.0015	0.010	0.047
1	IMZ 204	0.085	0.36	0.014	0.008	0.40	0.075	0.034	0.111	4.21	.	.	(0.007)	(0.0052)	.	.
1	SRM 1226	0.085	0.274	0.0022	0.0044	0.231	0.125	5.42	0.467	0.054	.	0.029	0.446	.	(0.003)	0.0018
1	NCS HS20747	0.083	0.967	0.02	0.015	0.472
1	DSZU C050	0.082	1.21	0.040	0.065	0.287	0.304	0.118	0.075	(0.008)	.	.	0.48	.	(0.004)	0.007
1	IMZ 72	0.081	0.31	0.092	0.012	0.34	0.27	0.039	0.52	0.013	.	.	0.006	.	.	(0.002)
1	NCS HS20745	0.068	0.813	0.1	0.024	0.33	0.297	0.022
1	VS UG117	0.064	1.41	0.012	0.021	0.60	0.214	0.072	0.129	0.018	.	.	(0.005)	0.0085	.	.
1	SRM 1271	0.064	0.73	0.005	0.0013	0.334	1.48	3.34	0.552	0.020	.	.	0.543	.	.	0.003
1	SRM C1285	0.058	0.332	0.072	0.020	0.36	0.37	1.17	0.80	.	.	0.036	0.164	.	0.035	0.150
1	SRM 1767	0.052	0.022	0.0031	0.0090	0.026	0.0014	0.002	0.0015	0.004	.	0.0050	0.020	0.0008	0.006	0.033
2	CZ CM-7A	0.05	1.17	0.011	0.016	0.56	0.09	0.05	0.10	0.13	.	0.007	0.015	0.01	0.008	0.012
1	CKD 183E	0.049	1.76	0.009	0.013	1.03	0.575	1.10	0.205	0.149	.	0.119	0.036	0.0040	0.053	(0.004)
1	SS 421	(0.049)	(0.11)	(0.012)	(0.027)	(0.07)	(0.028)	.	.	(<0.02)
1	12X 15252Q	0.0478	0.818	0.0213	0.0580	0.265	0.154	2.03	0.887	0.074	.	0.154	0.248	.	0.0448	0.330
1	VS UG82	0.046	1.83	(0.003)	(0.004)	0.334	0.056	0.201	0.59	.	.	.	0.93	.	.	0.56
1	VS UG97	0.041	0.59	0.0036	0.0025	0.194	0.0040	0.0048	0.0080	0.51	.	.	0.019	.	.	(0.001)
1	SRM 1766	0.015	0.067	0.002	0.0024	0.010	0.015	0.021	0.024	0.012	.	0.0020	0.0035	0.0033	0.0010	0.009
1	KUT B20	0.008	0.09	0.012	0.013	0.005	0.034	0.038	0.03	(0.01)	.	(<0.01)	(<0.01)	.	(0.003)	(<0.005)
1	SRM 1765	0.006	0.144	0.0052	0.0038	(0.004)	0.0013	0.154	0.051	(0.006)	.	0.0012	<0.005	0.0010	0.002	0.0040
1	NCS HS15749	0.0045	0.247	0.010	0.0054	1.54	.	0.050	0.050	0.048	(0.0008)
1	DSZU C01	0.004	0.049	0.002	0.002	0.014	0.008	0.530	0.040	0.004	.	0.217	0.124	.	.	(0.003)
2	IARM 168A	0.003	0.12	0.030	0.064	0.46	0.009	2.32	0.004	0.19	.	0.003	0.69	0.0002	0.003	0.004
1	CKD 180B	(0.003)	0.047	0.004	0.0038	0.001	0.006	0.018	0.013	(0.001)	.	0.003	0.001	(0.0028)	0.0011	0.000
1	ECRM 064-2D	0.0026	0.1641	.	.	0.0065	0.0077	0.0115	.	.	.	0.0027	0.00077	0.0026	0.00051	0.00015

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Sn	V
	Number	As	B	Ca	Ce	Fe	Nb	O	Pb	Sb	Ti	W	Zr	Units		
	IMZ 76	.	(0.001)	.	.	.	0.068	.	.	.	(0.003)	40 mm Ø x 40 mm
	VS UG86	40 mm Ø x 28 mm
	BS 1982	0.007	(0.003)	0.0017	(0.0003)	0.002	(0.001)	25(pre-17025)			39 mm Ø x ~7 or 19+mm	
	12X 15256Q	0.0509	0.101	.	.	.	40 mm Ø x ~15 mm
	12X 93106A	0.0050	38 mm Ø x ~15 mm
	BS 47B	0.004	(0.004)	38 mm Ø x ~7 or 19+mm
	DSZU C042	0.0073	0.00023	0.0010	.	.	0.0025	.	.	.	0.0018	(0.006)	.	.	.	40 mm Ø x 25 mm
	CKD 187C	(0.007)	0.0006	0.0010	Ta: 0.016	.	0.028	.	(0.003)	0.023	0.110	0.67	0.011	.	.	44 mm Ø x 13 or 25 mm
	VS UG115	0.0014	45 mm Ø x ~25 mm
	IMZ 71	.	(0.002)	.	.	.	(0.005)	.	.	.	(0.002)	.	.	(0.002)	.	40 mm Ø x 40 mm
	IMZ 75	0.024	.	last	.	.	40 mm Ø x 40 mm
	IMZ 75A	.	0.0021	.	.	.	0.024	.	.	.	0.023	38 mm Ø x 20 mm
	SRM 1138a	32 mm Ø x 13 mm
	BS 9905	0.007	(0.0004)	(0.0001)	25(pre-17025)	0.076	0.0021	(0.0002)	(0.002)	(0.002)	(0.002)	0.003	.	.	.	38 mm Ø x ~7 mm last
	VS UG6/10	0.128	0.41	.	.	.	45 mm Ø x ~28 mm
	12X 12748U	0.129	0.105	0.0464	.	.	.	40 mm Ø x ~15 mm
	IPT 500	0.0020	0.008	.	.	.	0.0014	34 mm Ø x 18 mm
	12X LA1B	0.0212	40 mm Ø x ~15 mm
	KUT A13	0.070	(0.002)	0.024	0.11	30-35mm Ø x 39 mm
	VS UG6/6	(0.002)	(0.0005)	.	0.125	0.39	.	.	.	45 mm Ø x ~28 mm
	BS 58E	0.003	(0.0002)	(0.0002)	.	.	.	0.0008	.	.	(0.002)	38 mm Ø x ~7 or 19+mm
	IMZ 175	(0.019)	.	.	.	40 mm Ø x 40 mm

RM LOW ALLOY STEEL XRF SETPart Number: BS LAS-24 Set of 24 samples, each 35 - 45 mm Ø x 7 mm discs **17025**

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
300M	BS 4340M	0.414	0.74	0.004	<0.001	1.65	0.134	1.78	0.78	0.35	0.076	0.007	.	0.013	0.0020	0.009	0.056
1345	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.007	0.033	0.0023	.	0.006	0.0056	(0.0004)	(<0.003)
3115	BS XCCT	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.020	0.006	0.004	.	0.017	0.0076	(0.002)	0.031
4130	BS 3932	0.321	0.54	0.016	0.018	0.33	0.200	0.19	1.00	0.229	0.020	0.004	0.0043	0.011	0.0070	0.012	0.005
4140	BS 1962	0.41	0.94	0.007	0.011	0.242	0.224	0.16	1.05	0.229	0.018	0.007	.	0.008	0.0095	0.010	0.004
4150 + S	BS 42	0.516	1.24	0.021	0.073	0.235	0.252	0.183	0.67	0.190	0.020	(0.004)	.	0.012	0.0080	0.012	0.003
4330	BS 4330V	0.318	0.91	0.008	0.0009	0.240	0.181	1.91	0.91	0.475	0.021	.	0.0010	0.011	0.0076	0.010	0.094
4340	BS 60E	0.408	0.70	0.012	0.024	0.26	0.153	1.73	0.86	0.249	0.024	0.007	0.0010	0.009	0.0087	0.009	0.004
4615	BS 51E	0.15	0.59	0.010	0.021	0.28	0.22	1.75	0.14	0.21	0.028	.	.	0.035	0.0086	0.010	(0.0011)
4620	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.24	0.032	(0.0084)	(0.0001)	0.012	0.0078	0.013	(0.0008)
4820	BS 4820	0.188	0.57	0.010	0.025	0.25	0.11	3.29	0.12	0.21	0.020	0.005	0.0046	0.008	0.0079	(0.008)	(0.002)
6150	BS 43A	0.491	0.811	0.008	0.026	0.252	0.184	0.242	0.93	0.059	0.003	.	.	0.008	0.0074	0.011	0.148
8620	BS 1931	0.194	0.84	0.007	0.018	0.235	0.116	0.42	0.50	0.168	0.021	0.007	(0.0008)	0.012	0.0079	0.007	0.002
8822	BS 8822	0.228	0.92	0.011	0.025	0.26	0.17	0.47	0.52	0.34	0.022	0.007	(0.0004)	0.019	0.0085	0.011	0.003
8740	BS 67B	0.40	0.94	0.007	0.020	0.23	0.19	0.53	0.51	0.22	0.024	.	.	0.011	0.0078	0.009	(0.002)
9310	BS 58D	0.127	0.45	0.010	0.005	0.32	0.156	3.02	1.35	0.14	0.042	.	.	0.009	0.0147	0.012	0.005
9325	BS 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.31	0.030	(0.004)	0.0049	0.010	0.0089	0.009	0.004
P-20	BS 55E	0.307	0.72	0.014	0.024	0.60	0.032	0.053	1.66	0.40	(0.004)	.	.	(0.005)	0.0096	0.002	0.019
AMS 6418	BS 69B	0.2258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.39	0.024	.	.	0.035	0.0057	0.006	(0.002)
A193	BS 4942	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	0.54	(0.004)	0.005	0.0006	0.010	0.0080	0.014	0.28
A485-1	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.029	0.017	0.006	.	0.010	0.0060	0.011	0.003
E52100	BS 53E	1.08	0.37	0.007	0.012	0.24	0.11	0.26	1.45	0.10	0.003	.	.	0.011	0.0086	0.005	0.004
Nitriding	BS 68C	0.38	0.60	0.018	0.008	0.305	0.178	0.166	1.77	0.36	1.06	(0.004)	(0.0002)	0.011	0.0045	0.008	0.007
LF 3	BS LF 3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.056	0.017	0.006	(0.0001)	0.056	0.0054	0.006	(0.002)

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
-------	--------	---	----	---	---	----	----	----	----	----	----	----	----	----	---	----	---

RM TOOL STEEL XRF SETPart Number: BS TS-18 AVAILABLE INDIVIDUALLY **17025** ~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
A-2	BS 36C	0.96	0.46	0.023	0.027	0.31	0.18	0.19	5.01	0.99	.	(0.04)	0.11	0.03	.
A-10	BS A-10	1.41	1.75	0.016	0.022	1.15	0.16	1.82	0.24	1.53	0.006	<0.005	(0.004)	(0.010)	.
D-2	BS 37D	1.54	0.28	0.021	0.015	0.29	0.063	0.21	11.07	1.09	.	0.16	0.80	0.07	0.016
H-10	BS 49	0.36	0.33	0.014	0.015	0.92	0.072	0.20	3.51	2.41	0.004	0.31	0.62	2.00	0.0186
H-11	BS TH11	0.423	0.31	0.016	0.005	0.88	0.041	0.11	5.04	1.27	.	(0.01)	0.46	(0.008)	.
H-12	BS TH12	0.372	0.40	0.020	0.005	0.92	0.064	0.16	5.02	1.41	.	1.06	0.62	0.07	.
H-13	BS 34D	0.395	0.38	0.017	0.005	1.06	0.049	0.10	5.15	1.24	.	0.10	0.94	0.031	.
L-6	BS 39B	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	0.17	(0.011)	.	(0.01)	(0.02)	.
M-1	BS TM1	0.86	0.23	0.007	0.012	0.46	0.054	0.057	3.72	8.4	.	1.7	1.05	0.45	.
M-2	BS 32C	0.84	0.29	(0.018)	0.0010	0.29	0.13	0.35	3.98	4.85	(0.02)	6.3	2.03	0.31	.
O-1	BS 35D	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.035	(0.005)	0.46	0.181	0.012	.
O-6	BS 41	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	0.23	(0.007)	0.035	0.046	.	.
S-1	BS 33E	0.49	0.29	0.022	0.005	0.20	0.038	0.08	1.25	0.045	.	2.75	0.19	0.006	.
S-5	BS 38C	0.60	0.81	0.011	0.012	2.08	0.26	0.24	0.28	0.41	0.015	0.004	0.214	0.036	0.0081
S-7	BS TS7	0.529	0.70	0.016	0.010	0.27	0.05	0.10	3.18	1.34	.	0.19	0.35	0.043	.
T-1	BS 30D	0.745	0.348	0.029	0.0010	0.301	0.116	0.191	3.93	0.342	0.0123	17.73	1.077	0.101	0.0168
	BS 10V	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	1.30	<0.002	0.013	9.50	0.009	0.064
HP9-4-30	BS 9-4-30	0.30	0.22	0.008	<0.001	0.06	0.09	7.25	1.00	1.00	0.004	0.01	0.085	4.40	0.0015

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
-------	--------	---	----	---	---	----	----	----	----	----	----	---	---	----	---

TOOL STEEL

CONTINUED ON THE NEXT PAGE

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	W	Al
1	BS PM15	3.54	0.416	0.0198	0.0127	0.912	0.142	0.203	5.33	0.0330	1.22	0.111	0.0029	14.79	0.109	0.0025
1	BS 10V	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	0.009	1.30	0.064	.	9.50	0.013	<0.002
1	DSZU C070	2.43	0.38	0.021	0.054	0.79	0.130	0.153	5.57	0.053	1.28	.	.	9.39	0.029	.
1	BS A-11	2.42	0.507	0.023	0.123	0.98	0.092	0.25	5.21	0.044	1.25	0.110	0.0019	9.24	(0.080)	0.0054
1	DSZU C082	2.32	0.33	0.029	0.014	0.36	0.118	0.239	12.24	0.035	1.11	.	.	4.02	0.17	.
1	ECRM 288-1D	2.08	0.292	0.024	(0.0012)	0.260	0.060	0.298	12.00	0.018	1.03	0.0151	.	0.055	(0.68)	0.012
1	DSZU C080	1.68	0.31	0.025	0.020	1.89	0.120	0.162	5.06	0.028	0.39	.	.	5.12	3.40	.
1	BS 37G	1.663	0.326	0.021	0.0007	0.352	0.044	0.152	11.77	0.0166	0.78	0.0310	0.0025	0.70	0.034	0.0060
1	BS TS15	1.64	0.27	(0.017)	0.067	0.357	0.065	(0.18)	4.12	4.87	0.45	0.045	0.0016	4.81	11.6	0.0032
1	ECRM 274-1D	1.563	0.397	0.0148	0.0096	1.057	0.0281	0.077	8.036	(0.0230)	1.4551	0.0769	(0.0011)	4.010	0.0087	(0.0025T)
2	CT D2	1.53	0.48	0.013	0.005	0.40	0.04	0.10	11.46	0.02	0.75	.	.	0.89	<0.01	.
1	IARM 41D	1.519	0.256	0.021	0.012	0.256	0.047	0.114	11.5	(0.020)	0.74	0.0152	(0.003)	0.77	0.034	0.014
1	BS 41A	1.50	0.93	0.004	0.001	0.97	0.034	0.17	0.20	0.006	0.19	0.0077	0.004	(0.003)	<0.003	0.010
1	IARM 45B	1.42	0.90	0.010	0.008	0.92	0.018	0.024	0.061	0.004	0.24	0.0080	0.002	(0.003)	(0.004)	0.010
2	BS 41	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	.	0.23	.	.	0.046	0.035	(0.007)
2	BS A-10	1.41	1.75	0.016	0.022	1.15	0.016	1.82	0.24	(0.010)	1.53	.	.	(0.004)	<0.005	0.006
1	IARM 251A	1.398	0.33	0.014	0.058	0.58	0.13	0.131	4.1	0.129	5.16	0.044	0.003	3.9	5.5	0.01
1	IARM 45A	1.39	0.88	0.014	0.012	1.02	0.049	0.11	0.13	0.004	0.25	0.0079	0.003	0.005	.	0.011
1	DSZU C073	1.32	0.23	0.019	0.013	0.27	0.112	0.198	3.97	8.31	4.97	.	.	2.82	6.40	.
1	CT X27081	1.32	0.20	0.004	0.001	0.24	0.026	0.031	0.052	.	0.008	.	.	.	3.39	.
1	DSZU C072	1.30	0.29	0.024	0.019	0.19	0.106	0.192	4.25	0.011	5.39	.	.	3.59	6.33	.
3	CZ HS-2A	1.24	0.27	0.024	0.017	0.24	0.08	0.21	4.15	9.9	3.75	.	0.003	3.4	9.3	0.035
1	DSZU C077	1.16	0.19	0.030	0.024	0.40	0.142	0.271	4.07	7.73	3.05	.	.	2.04	12.17	.
1	DSZU C075	1.16	0.16	0.021	0.015	0.47	0.120	0.202	3.10	8.03	4.06	.	.	2.10	9.27	.
1	BS M-47	1.14	0.20	0.020	0.002	0.464	0.080	0.17	3.72	4.99	9.24	0.0219	(0.004)	1.23	1.36	(0.002)
1	IMZ 102/3	1.11	0.15	0.014	(0.0045)	1.06	0.13	0.021	1.59	.	0.43	.	.	(0.012)	.	0.017
1	DSZU C074	1.10	0.16	0.023	0.020	0.16	0.141	0.158	3.93	5.08	5.21	.	.	1.94	6.47	.
1	DSZU C071	1.06	0.20	0.020	0.028	0.38	0.162	0.149	3.77	8.10	9.67	.	.	1.07	1.74	.
1	SS 487/1	1.02	0.26	0.022	0.029	0.18	.	(0.14)	3.91	7.95	9.41	.	.	1.14	1.80	0.006
1	DSZU C081	1.01	0.32	0.017	0.011	1.10	0.124	0.207	7.78	0.029	2.13	.	.	0.25	0.05	.
2	CT M7	1.00	0.29	0.012	0.003	0.34	0.066	0.10	3.60	0.015	8.49	.	.	2.02	1.78	.
1	JK 49D	(1)	(0.4)	(0.02)	(0.01)	(0.5)	(0.1)	(0.2)	(5)	(0.3)	(3)	1.89	.	(9)	(4)	.
1	IARM 39B	0.99	0.54	0.017	0.003	0.35	0.10	0.14	4.79	0.014	1.01	0.0096	0.003	0.22	(0.026)	0.006
1	IARM 39C	0.99	0.45	0.019	0.007	0.28	0.077	0.144	4.99	0.013	0.97	0.011	0.0029	0.21	0.011	0.017
2	BS 36D	0.97	0.68	0.021	0.007	0.27	0.060	0.089	5.25	0.010	0.96	0.0108	.	0.29	0.028	0.010
2	CT A2	0.95	0.72	0.010	0.004	0.40	0.06	0.10	5.13	.	1.05	.	.	0.22	.	.
1	SS 485/1	0.94	0.41	0.043	0.039	0.30	.	(0.14)	4.02	4.97	0.66	.	.	1.02	17.8	(0.006)
1	IARM 320A	0.93	0.33	0.021	(0.0015)	0.36	0.091	0.204	4.22	4.90	4.79	(0.014)	0.0032	1.76	6.01	0.023
2	CT O1	0.91	1.27	0.009	0.004	0.36	0.05	0.06	0.49	.	0.07	.	.	0.25	0.51	.
1	ECRM 290-1D	0.91	0.24	0.016	0.016	0.08	0.081	0.33	4.18	5.12	4.81	0.0325	.	1.92	6.24	.
2	CT M10	0.88	0.27	0.016	0.004	0.30	0.061	0.14	3.97	0.012	7.89	.	.	1.99	0.008	.
2	BS 35D	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.012	0.035	.	(0.003)	0.181	0.46	(0.005)
1	IARM 304A	0.857	0.260	0.019	0.0016	0.36	0.14	0.133	3.55	0.278	8.04	0.034	0.002	1.23	1.65	0.009
2	14X 14946D	0.85	0.53	0.051	0.048	0.46	0.25	1.06	5.06	0.44	0.21	.	.	1.03	16.9	.
2	BS 32D	0.85	0.30	0.027	0.022	0.25	0.039	0.053	4.14	0.010	4.92	0.018	.	1.82	6.15	0.018
1	IARM 306B	0.84	0.24	0.006	(0.001)	0.21	0.058	0.095	4.12	0.010	4.2	0.0049	(0.002)	0.98	(0.01)	0.08
1	SRM 1157	0.836	0.34	0.011	0.004	0.18	0.088	0.228	4.36	0.028	4.86	.	.	1.82	6.28	.
1	BS M-50	0.834	0.244	0.0066	0.0009	(0.205)	0.064	0.074	4.28	0.0151	4.29	0.0057	(0.0018)	0.99	0.0052	0.073
2	14X 14948C	0.83	0.65	0.011	0.017	0.26	0.04	0.29	4.04	0.16	0.14	.	.	0.65	18.8	.
2	CT M2	0.82	0.33	0.012	0.004	0.27	0.06	0.25	4.03	0.05	4.96	.	.	1.81	6.47	.
1	IARM 44C	0.82	0.301	0.027	0.004	0.31	0.12	0.132	4.04	0.247	5.02	0.033	0.004	1.91	6.0	0.05
2	14X 14890K	0.81	0.58	(0.012)	0.028	0.69	0.09	0.08	3.60	0.32	5.59	.	.	1.99	5.30	.
2	CT M1	0.80	0.30	0.012	0.005	0.22	0.087	0.12	3.91	.	8.22	.	.	1.05	1.58	.
1	IARM 48C	0.77	0.39	0.029	0.018	0.45	0.13	0.204	4.24	0.22	0.17	0.0165	(0.006)	1.27	17.5	0.017
1	BS 30D	0.745	0.348	0.029	0.010	0.301	0.116	0.191	3.93	0.101	0.342	0.0168	(0.0189)	1.077	17.73	0.0123
1	IARM 281A	0.74	0.30	0.015	0.019	0.29	0.096	0.15	3.89	4.8	0.49	0.0064	0.004	0.90	17.6	0.007
1	SS 486/1	0.74	0.21	0.029	0.021	0.27	.	(0.06)	4.54	0.08	5.20	.	.	1.82	5.80	(0.005)
1	IARM 40C	0.72	1.91	0.014	0.012	0.32	0.142	0.255	0.99	0.010	1.27	0.0083	0.008	0.010	0.009	0.019
1	14X HS1C	0.72	0.29	0.018	0.020	0.23	0.07	0.28	4.00	0.25	0.36	0.023	.	1.04	17.2	.
3	CZ HS-1A	0.72	0.28	0.023	0.011	0.28	0.08	0.14	4.15	4.7	0.06	.	.	1.33	17.5	0.03
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	W	Al
1	IARM 43B	0.711	0.56	0.008	0.013	0.251	0.180	1.39	0.651	0.012	0.206	0.0093	0.0047	0.0035	<0.005	0.021
2	BS 40B	0.71	2.28	0.020	0.006	0.35	0.076	0.089	1.18	0.020	1.07	0.0076	0.002	0.10	0.11	0.002
3	CZ CM-10A	0.694	1.00	0.040	0.022	0.817	0.31	2.38	5.48	0.114	1.234	.	0.0189	0.908	0.96	0.086
1	DSZU C076	0.69	0.18	0.024	0.022	0.58	0.120	0.213	5.75	13.88	4.29	.	.	2.03	9.81	.
1	SS 481/1	0.68	0.25	0.023	0.022	0.15	.	(0.09)	3.40	0.31	0.28	.	.	0.56	14.0	.
1	IARM 40B	0.68	1.98	0.012	0.003	0.39	0.050	0.096	1.04	0.015	1.22	0.0107	0.003	0.014	0.013	(0.006)
2	BS 39B	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	(0.02)	0.17	.	.	(0.01)	.	(0.011)
1	SS 482/1	0.67	0.26	0.027	0.027	0.14	(0.16)	0.29	3.95	0.29	0.40	.	.	1.04	17.8	.
1	DSZU C078	0.67	0.22	0.022	0.019	0.117										

ALUMINUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Al	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	Ti	V
1	ECRM 299-1D	5.33	0.172	22.32	0.0154	0.2678	0.0152	0.00022	0.299	0.0382	0.0187	0.0186	0.0198	.	0.1289	0.0329
1	IMZ 158	1.56	0.24	25.51	0.091	1.34	0.015	0.007	2.23	0.097	.	0.025	.	.	0.12	0.078
1	13X PH17700A	1.172	6.98	16.88	0.0732	0.496	0.0181	0.0008	0.551	0.146	0.0464	0.340	0.0192	0.0201	0.051	0.0390
1	BS 192	1.17	7.11	16.44	0.074	0.835	0.025	0.0005	0.387	0.412	0.104	0.430	0.0290	0.168	0.076	0.124
2	CT X92834	1.14	8.32	12.57	0.035	0.044	0.003	0.003	0.019	0.030	0.030	2.20	.	0.001	0.019	<0.004
1	13X PH13800A	1.075	8.04	12.53	0.0386	0.0332	0.0064	0.0030	0.081	0.0449	0.0220	2.10	0.0041	.	0.0122	0.0188
2	BS 184A	1.00	8.34	12.66	0.035	0.06	0.007	0.001	0.080	0.041	0.036	2.20	0.0045	(0.006)	0.051	0.014
1	BS 192A	0.98	7.01	16.44	0.066	0.768	0.021	<0.002	0.300	0.334	0.114	0.28	0.029	0.208	0.083	0.077
1	IARM 152C	0.94	7.30	16.99	0.072	0.74	0.024	0.0006	0.263	0.316	0.113	0.36	0.0172	0.012	0.098	0.072

Number	As	B	Ca	O	Sn	Ta	W	Zr	Units
ECRM 299-1D	0.0054	0.0002	0.1775	40 mm Ø x 25 mm
IMZ 158	40 mm Ø x 40 mm
13X PH17700A	.	0.0033	.	.	0.0055	.	0.009	.	~38 mm Ø x ~15 mm
BS 192	(0.005)	(0.0003)	0.0007	0.0014	0.008	(0.001)	0.05	.	38 mm Ø x ~7 or 19+ mm
CT X92834	.	0.0009	.	.	0.002	.	.	<0.001	30-35 mm Ø x x ~19 mm
13X PH13800A	0.0051	.	.	.	~38 mm Ø x ~15 mm
BS 184A	.	(0.0004)	(0.0003)	(0.0003)	(0.002)	.	0.032	.	38 mm Ø x ~7 or 19+ mm
BS 192A	(0.0035)	(0.0003)	(0.0006)	(0.0006)	0.008	.	0.048	.	38 mm Ø x ~7 or 19+ mm
IARM 152C	(0.004)	0.0029	(0.0005)	(0.001)	0.007	(0.005)	0.026	.	31 mm Ø x 2 or 18 mm

CRM BORON IN STAINLESS STEEL

35 mm x 45 mm x 16 mm

Number	B	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Ti	V	W
DSZU C61	2.14	(0.073)	(0.38)	(0.003)	(0.005)	(0.41)	(0.09)	(0.95)	(17.8)	(0.04)	(0.24)	(0.75)	(0.19)	(0.22)
DSZU C60	1.42	(0.058)	(0.50)	(0.002)	(0.006)	(0.35)	(0.01)	(0.51)	(11.9)	(0.11)	(0.37)	(2.70)	(0.41)	(0.20)
DSZU C62	1.15	(0.065)	(0.31)	(0.010)	(0.024)	(0.32)	(0.24)	(0.84)	(14.4)	(0.59)	(0.16)	(3.36)	(0.18)	(0.14)
DSZU C63	1.05	(0.070)	(0.27)	(0.014)	(0.006)	(0.30)	(0.39)	(0.48)	(11.3)	(0.25)	(0.09)	(0.70)	(0.08)	(0.10)

CALCIUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Ca	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	V	W
1	BS Ca304-4 *	0.008	8.8	18.3	0.092	0.80	0.021	0.007	0.91	0.14	0.001	0.004	0.06	0.06	0.07	<0.05
2	BS CA304-1	0.0045	8.57	18.30	0.045	1.06	0.026	0.016	0.71	0.34	0.20	0.34	0.083	0.026	0.09	0.04
1	13X 14923A	0.0044	0.452	11.26	0.205	0.501	0.0197	0.0031	0.330	0.0563	0.0207	0.819	0.0321	0.005	0.295	.
1	ECRM 379-1D	0.0033	30.83	26.79	0.0121	1.804	0.0166	0.0006	0.393	0.984	0.0390	3.290	0.0550	(0.0028)	0.0663	(0.0091)
1	13X 31603C	0.0029	10.03	16.83	0.023	1.879	0.0263	0.0245	0.350	0.306	0.148	2.02	0.080	0.0197	0.0895	0.0427
2	BS 193	0.0020	1.82	18.48	0.104	12.11	0.018	0.002	0.66	0.088	0.028	0.21	0.37	0.014	0.107	(0.007)
2	BS SS4952	0.0019	0.23	13.15	0.347	0.41	0.016	0.003	0.66	0.045	0.030	0.049	0.027	0.004	0.089	(0.007)
2	BS 82E	0.0014	12.49	22.38	0.062	1.61	0.027	0.001	0.58	0.26	0.12	0.31	0.072	0.062	0.064	0.041
1	BS 9942	0.0014	13.55	18.21	0.021	1.84	0.025	0.006	0.49	0.305	0.086	3.30	0.071	0.005	0.072	0.032
1	BS 9842	0.0010	20.02	24.19	0.059	1.50	0.025	0.0016	0.99	0.147	0.237	0.111	0.037	0.026	0.075	0.011
1	ECRM 272-1D	0.00090	0.2445	11.927	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.0145	0.0030	0.0508	0.0028	0.0167	.
2	BS 94C	0.0008	0.43	25.90	0.057	0.45	0.024	0.002	0.62	0.056	0.042	0.20	0.065	0.032	0.12	(0.03)
2	BS 82D	0.0007	14.12	22.40	0.058	1.85	0.020	0.009	0.63	0.16	0.042	0.144	0.070	0.053	0.087	0.028
2	BS 87F	0.0007	10.12	17.30	0.055	1.64	0.024	0.025	0.67	0.28	0.17	0.29	0.037	0.57	0.13	0.050
2	BS SS3951	0.0005	9.18	18.17	0.014	1.56	0.023	0.031	0.61	0.22	0.16	0.303	0.077	0.085	0.067	0.040

Number	Al	As	B	O	Pb	Sb	Sn	Ti	Zn	Units	
BS Ca304-4 *	<0.05	<0.05	0.004	0.01	* Provisional Analysis					.	~38 mm Ø x ~38mm
BS CA304-1	0.003	(0.003)	0.0006	0.0041	.	(0.0020)	0.010	0.028	.	38 mm Ø x ~5 mm last, sides not parallel	
13X 14923A	0.003	0.004	.	.	~40 mm Ø x ~15 mm	
ECRM 379-1D	(0.00246)	(0.0018)	0.00190	(0.0027)	(0.000038)	0.00057	0.0021	(0.0014)	.	38 or 45 mm Ø x 25 mm	
13X 31603C	(0.005)	0.0053	.	.	.	~30 mm Ø x ~20 mm	
BS 193	(0.003)	.	0.0007	(0.004)	.	.	0.004	0.003	.	32 mm Ø x ~7 or 19+ mm	
BS SS4952	0.003	0.002	(0.0004)	0.005	.	.	0.004	0.002	.	38 mm Ø x ~7 or 19+ mm	
BS 82E	0.006	.	0.0024	.	.	.	0.006	0.003	.	38 mm Ø x ~7 or 19+ mm	
BS 9942	0.004	(0.004)	0.0014	(0.0023)	.	.	0.006	(0.002)	.	44 mm Ø x ~7 or 19+ mm	
BS 9842	0.014	(0.002)	0.0025	(0.0044)	.	.	0.005	0.003	.	38 mm Ø x ~7 or 19+ mm	
ECRM 272-1D	0.0046	0.0116	0.0018	.	.	0.0007	.	0.00096	0.0031	38 mm Ø x 25 or 30 mm	
BS 94C	0.004	.	(0.0005)	0.0061	.	.	0.006	.	.	44 mm Ø x ~7 or 19+ mm	
BS 82D	(0.002)	.	0.0040	0.007	.	.	0.004	0.005	.	38 mm Ø x ~7 or ~11 mm last	
BS 87F	0.004	0.005	(0.0006)	0.005	.	.	0.004	0.004	.	41 mm Ø x ~7 or 19+ mm	
BS SS3951	0.002	.	(0.0006)	0.0075	.	.	0.007	(0.002)	.	41 mm Ø x ~7 or 19+ mm	

MARAGING STEEL AND COBALT IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	Co	Mo	Ni	Cr	C	Mn	P	S	Si	Cu	Al	B	N	Nb	Ti
1	IARM 326A	48.4	(0.002)	0.037	(0.002)	(0.002)	0.003	0.0013	0.0011	0.029	(0.002)	(0.003)	(0.001)	0.0004	0.038	(0.002)
2	CT ISO070A	29.00	0.006	24.47	5.54	0.014	0.015	0.003	<0.001	0.32	0.010	0.47	0.0038	.	4.63	0.82
1	IMZ 521	20.25	4.84	8.63	0.040	0.015	0.039	0.0031	0.0058	0.072	0.027	.	.	0.0113	.	.
1	IMZ 522	18.72	6.45	11.47	0.022	0.0088	0.032	(0.003)	0.0043	0.048	0.019	.	.	0.0045	(0.008)	0.54
1	IMZ 520	17.66	4.92	10.10	0.242	0.011	0.070	0.0043	0.019	0.094	0.080	.	(0.001)	0.0105	(0.008)	(0.007)
1	IARM 98B	17.0	0.010	29.4	0.012	0.007	0.18	0.002	0.0007	0.17	0.028	0.07	0.001	0.0024	0.002	0.03
1	IMZ 523	14.44	6.67	15.94	0.048	0.0098	0.051	(0.004)	0.0039	0.043	0.059	.	.	0.0037	(0.008)	0.70
1	IARM 242A	13.5	1.21	11.1	3.00	0.24	0.018	0.002	0.0004	0.02	0.007	0.004	(0.0005)	0.0003	0.004	0.009
2	CT ISO045A	13.39	1.18	11.38	3.12	0.228	0.002	0.001	0.0004	<0.010	0.006	0.004	.	.	.	0.005
1	IARM 309A	12.3	4.71	18.4	0.053	0.0059	0.018	0.004	0.0006	0.020	0.023	0.11	0.0032	0.0010	0.004	1.47
1	IMZ 524	12.25	4.95	13.75	0.085	0.012	0.68	(0.004)	0.004	0.13	0.024	.	.	0.0038	(0.007)	0.85
1	DSZU C093	12.08	3.79	15.80	0.42	0.013	0.32	(0.006)	(0.007)	(0.10)	(0.12)	0.17	.	.	.	1.56
1	BS 161A	9.22	4.82	18.40	0.12	0.004	0.031	0.004	0.0007	0.032	0.22	0.14	0.0023	(0.002)	(0.004)	0.65
2	CT 300	9.07	4.97	18.51	0.034	0.005	0.032	0.005	0.004	0.030	0.047	0.12	0.0020	.	.	0.69
1	13X 14934Q	9.03	4.22	17.60	0.388	0.0254	0.254	0.024	0.0288	0.502	.	0.15	.	0.0132	.	0.694
1	DSZU C091	8.07	4.98	18.20	0.12	0.035	0.092	(0.006)	(0.011)	(0.09)	(0.12)	0.05	.	.	.	0.81
1	IARM 308A	7.80	4.78	18.53	0.023	0.003	0.019	0.004	0.0005	0.014	0.018	0.097	0.0029	0.0013	0.003	0.46
1	ECRM 285-2D	7.76	4.99	18.07	0.0236	0.0018	0.0168	0.0053	0.0025	0.0117	0.0094	0.1067	0.0009	0.0007	.	0.520
2	CT 250	7.54	4.88	18.44	0.008	0.002	0.006	0.003	0.002	0.008	0.008	0.058	0.0024	.	.	0.41
1	13X 14935T	7.17	5.61	18.96	0.745	0.0105	0.494	0.036	0.055	0.441	.	(0.007)	.	0.0102	.	0.106
3	DSZU C55	6.5	1.25	2.34	14.1	0.23	0.69	0.033	0.023	0.70	.	.	.	0.11	0.29	.
3	DSZU C53	5.9	1.88	0.96	15.0	0.10	0.54	0.050	0.031	0.25	0.12	.
3	DSZU C54	5.3	1.45	1.95	18.4	0.07	0.55	0.040	0.020	0.54	.	.	.	0.13	0.41	.
1	DSZU C092	5.21	5.50	20.12	0.23	0.015	0.27	(0.006)	(0.009)	(0.10)	(0.16)	(0.006)	.	.	.	(0.008)
3	DSZU C51	4.7	0.72	1.78	11.0	0.20	0.40	0.017	0.036	0.24	.	.	.	0.090	0.12	.
3	DSZU C52	3.8	1.17	1.55	11.6	0.14	0.37	0.020	0.028	0.17	0.31	.
1	BS 85D	0.97	0.59	9.98	17.09	0.048	1.69	0.024	0.024	0.54	0.45	0.13	(0.001)	(0.02)	0.062	0.48

Number	As	Ca	Fe	Mg	O	Sb	Sn	Ta	V	W	Zr	Units
IARM 326A	<0.005	.	49.6	(0.001)	0.0082	.	<0.001	(0.01)	1.94	(0.001)	0.002	31 mm Ø x 2 or 18 mm
CT ISO070A	.	.	34.66	<0.01	0.043	<0.01	.	30-35 mm Ø x ~16 mm
IMZ 521	(0.002)	.	3.97	5.23	.	38 mm Ø x 20 mm
IMZ 522	(0.001)	.	2.21	2.25	.	38 mm Ø x 20 mm
IMZ 520	(0.002)	.	4.03	4.90	.	38 mm Ø x 20 mm
IARM 98B	<0.002	<0.0005	52.9	0.0040	0.0021	.	0.002	<0.05	(0.003)	(0.02)	<0.01	31 mm Ø x 2 or 18 mm OES is last
IMZ 523	(0.001)	.	2.01	1.87	.	38 mm Ø x 20 mm
IARM 242A	0.0006	.	(0.001)	0.008	0.01	<0.01	.	31 mm Ø x 2 or 18 mm
CT ISO045A	.	.	70.70	30-35 mm Ø x ~19 mm
IARM 309A	0.0005	.	(0.001)	(0.006)	0.01	0.01	0.008	31 mm Ø x 2 or 18 mm
IMZ 524	(0.003)	3.02	1.84	.	38 mm Ø x 20 mm
DSZU C093	~40 mm Ø x 17 mm
BS 161A	(0.002)	(0.0008)	25(pre-17025)	(0.0004)	(0.0004)	.	(0.0015)	(0.03)	0.031	(0.008)	(0.002)	38 mm Ø x ~7 or 19+ mm
CT 300	30-35 mm Ø x ~16 mm
13X 14934Q	40 mm Ø x 15 mm
DSZU C091	~40 mm Ø x 17 mm
IARM 308A	0.0005	.	0.001	<0.01	0.01	0.01	0.01	31 mm Ø x 2 or 18 mm
ECRM 285-2D	0.0050	38 mm Ø x 25 or 30 mm
CT 250	30-35 mm Ø x ~19 mm
13X 14935T	40 mm Ø x 15 mm
DSZU C55	0.16	1.1	.	42 mm Ø x 25 mm
DSZU C53	0.25	0.58	.	42 mm Ø x 25 mm
DSZU C54	0.40	0.62	.	42 mm Ø x 25 mm
DSZU C092	~40 mm Ø x 17 mm
DSZU C51	0.08	0.32	.	42 mm Ø x 25 mm
DSZU C52	0.03	0.95	.	42 mm Ø x 25 mm
BS 85D	(0.01)	0.0004	[67.8]	.	(0.002)	(0.001)	0.0062	(0.001)	0.132	(0.07)	(0.004)	38 mm Ø x ~7 or 19+ mm 17025

TUNGSTEN IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	W	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	Ti	V
1	VS LG57	4.24	25.2	13.70	0.016	0.52	0.011	0.0023	0.56	0.080	.	0.401	.	.	1.81	0.65
1	13X 14219K	4.17	12.66	21.46	0.0997	0.482	0.0401	0.0456	1.504	0.138	0.0475	0.169	.	0.140	.	0.0188
1	13X 14212S *	3.72	8.76	21.8	0.12	0.15	0.034	0.037	2.5	0.6	0.11	0.52	0.007	0.56	.	0.12
1	IARM 20B	3.52	1.94	12.42	0.18	0.35	0.019	0.004	0.40	0.069	0.030	0.32	0.0434	0.010	0.004	0.17
1	13X 14211Q	3.24	12.55	25.70	0.064	0.766	0.0157	0.0146	1.64	0.161	0.071	0.325	.	0.161	0.220	.
1	VS LG59	3.08	35.1	15.81	0.073	1.15	0.011	0.0083	0.63	0.083	.	0.094	.	0.106	1.12	0.273
1	113X 14215L	3.02	15.86	22.89	0.136	1.110	0.0050	0.0068	0.596	0.0110	0.0057	0.0048	.	0.0196	.	0.0480
2	BS 183A	2.60	1.85	12.14	0.172	0.35	0.016	0.0040	0.37	0.093	0.036	0.12	0.0256	0.006	0.002	0.090
1	IARM 20C	2.59	1.93	12.15	0.18	0.30	0.018	0.007	0.35	0.060	0.031	0.12	0.0222	0.010	(0.003)	0.086
1	IMZ 161	1.05	0.55	12.90	0.074	0.29	0.023	0.023	0.65	0.56	.	1.10	.	.	.	0.33

Number	Al	As	B	Ca	O	Sb	Sn	Units
VS LG57	0.151	~47 mm Ø x ~30 mm
13X 14219K	~40 mm Ø x ~15 mm
13X 14212S *	~40 mm Ø x ~15 mm
IARM 20B	0.006	.	.	.	0.0056	.	0.005	31 mm Ø x 2 mm
13X 14211Q	(0.11)	~40 mm Ø x ~15 mm
VS LG59	0.079	~47 mm Ø x ~30 mm
13X 14215L	~40 mm Ø x ~15 mm
BS 183A	0.002	(0.002)	(<0.0005)	0.0020	0.0065	(0.001)	0.003	38 mm Ø x ~7 or 19+ mm
IARM 20C	(0.004)	.	.	.	0.0068	.	0.004	31 mm Ø x 2 or 18 mm
IMZ 161	40 mm Ø x 40 mm

MANGANESE STAINLESS STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

* Provisional Analysis

# Number	Mn	Ni	Cr	C	P	S	Si	Cu	Mo	Al	Co	N	Nb	V	W
1 IARM 294A	21.6	2.9	19.7	0.017	0.026	0.0028	0.43	0.34	1.8	(0.01)	0.021	0.78	(0.03)	0.046	(0.01)
1 IARM 295A	19.7	1.84	18.0	0.021	0.028	0.0041	0.36	0.113	0.97	(0.01)	0.021	0.62	0.018	0.046	0.016
1 ECRM 294-1D	18.68	0.429	17.98	0.0657	0.0271	0.00031	0.283	0.0242	0.0861	(0.0095)	0.0288	0.566	(0.00117)	0.0694	(0.00114)
1 IARM 214A	18.3	2.33	12.36	0.018	0.033	0.002	1.00	0.36	0.44	(0.002)	0.021	0.27	0.23	0.04	0.02
1 VS RG20/1	15.77	0.673	14.35	0.064	(0.02)	(0.01)	0.81	0.265	0.089	.	.	.	0.175	0.166	0.007
1 VS RG22/1	13.41	3.94	13.25	0.054	(0.02)	(0.008)	0.63	0.358	0.121	.	.	.	0.38	0.125	0.137
2 BS 193	12.11	1.82	18.48	0.104	0.018	0.002	0.66	0.088	0.21	(0.003)	0.028	0.37	0.014	0.107	(0.007)
2 CT ISO035A	12.04	1.81	18.48	0.102	0.023	0.002	0.59	0.17	0.28	<0.004	0.037	0.33	0.004	0.058	0.002
1 IARM 296A	10.6	1.71	11.2	0.074	0.027	0.002	0.38	0.12	0.60	(0.005)	0.018	0.23	0.043	0.056	(0.01)
1 13X NSC3Z	10.15	2.96	23.02	0.895	.	0.0110	1.28	0.100	0.060	0.105	.	0.498	2.81	0.110	.
2 BS 190	9.72	6.74	19.57	0.022	0.015	0.001	0.46	0.072	0.15	(0.004)	0.044	0.255	(0.004)	0.11	0.015
2 CT ISO129A	9.31	6.86	19.62	0.030	0.002	<0.001	0.40	0.152	0.25	0.014	0.102	0.264	0.025	0.144	0.03
1 IARM 19C *	9.02	6.40	19.51	0.012	0.027	0.0007	0.31	0.45	0.40	0.007	0.087	0.32	0.028	0.090	0.037
1 13X NSC6A	8.85	6.52	20.47	0.0266	0.0049	0.0055	0.523	0.0064	(0.002)	(0.009)	.	0.235	.	0.0052	.
1 VS RG23/1	8.74	1.98	18.5	0.045	(0.02)	(0.004)	0.49	0.099	0.401	.	.	.	0.24	0.69	0.3
1 13X NSC2P	8.70	4.20	21.98	0.560	.	0.0117	0.997	1.026	0.850	.	.	0.341	2.21	0.321	0.062
2 BS 181A	8.16	8.15	16.52	0.071	0.019	0.001	4.03	0.18	0.21	0.022	0.072	0.148	0.017	0.094	0.04
1 BS 181B	8.07	8.18	16.17	0.070	0.021	0.0009	3.94	0.206	0.173	0.0119	0.044	0.158	0.026	0.044	0.016
1 13X 21800A	8.00	8.32	16.81	0.0765	0.032	0.0011	4.03	0.431	0.325	0.012	0.0943	0.125	0.007	0.0619	.
1 13X NSC4F	7.97	7.03	32.58	0.513	.	0.0071	1.52	0.162	1.390	0.119	0.218	0.942	2.41	0.219	0.204
1 SRM 1297	7.11	5.34	16.69	0.066	0.038	0.0033	0.397	0.442	0.331	.	0.127	.	.	0.080	.
1 13X NSC1P	6.53	5.06	18.76	0.316	.	0.0097	0.788	0.391	0.196	.	.	0.0877	1.499	0.501	0.100
1 VS RG21/1	6.39	7.52	15.53	0.169	(0.02)	(0.008)	1.95	0.17	0.88	.	.	.	0.48	1.71	(0.2)
3 CZ SL-5A	5.8	4.94	11.7	0.37	0.021	0.014	0.36	2.90	4.12	0.035	0.26	.	0.20	0.21	0.78
2 BS 191	5.71	5.34	16.33	0.098	0.024	0.023	3.73	0.33	0.36	(0.002)	0.11	0.117	0.024	0.083	0.033
1 VS RG19/1	5.63	17.73	24.5	0.064	(0.02)	(0.009)	0.90	(0.2)	0.166	.	.	.	0.108	0.407	0.206
1 13X NSA4B	5.55	17.62	23.85	0.115	0.0302	0.0095	0.519	0.595	4.32	0.0048	.	0.446	0.154	.	.
1 13X NSA10A	5.23	12.98	20.67	0.0180	0.0206	0.0007	0.375	0.170	2.636	.	0.060	0.342	0.143	0.151	(0.061)
2 BS 180A	5.05	13.19	21.09	0.018	0.012	0.001	0.32	0.067	2.04	0.012	0.039	0.334	0.20	0.20	0.02
1 IARM 292A	5.0	1.47	21.35	0.030	0.018	0.001	0.75	0.29	0.097	0.010	0.031	0.245	0.009	0.084	0.01
1 BS 180B	4.65	11.9	21.5	0.022	0.017	0.0008	0.46	0.201	2.20	(0.007)	0.111	0.315	0.131	0.149	0.050
2 HRT FE2017-H	4.43	15.45	20.15	0.015	0.022	0.002	0.34	0.21	3.17	.	.	0.311	0.131	.	.
1 13X NSA5A	4.27	9.52	20.73	0.063	(0.010)	0.0212	0.281	0.098	2.32	(0.012)	.	0.340	0.574	.	.
1 IARM 17D	4.15	11.83	21.06	0.041	0.026	0.0018	0.416	0.412	1.52	0.0032	0.23	0.311	0.14	0.118	0.056
1 13X NSC7A	3.80	7.41	23.63	0.410	0.0155	0.0091	0.803	0.144	0.448	(0.096)	0.308	0.337	0.509	0.123	0.052
1 13X NSC5B	2.22	4.34	22.10	0.558	.	0.0155	1.19	0.787	(0.009)	0.21	.	0.296	2.38	0.0461	.

Number	As	B	Ca	O	Pb	Sb	Sn	Ta	Te	Ti	Zr	Units
IARM 294A	.	(0.003)	.	(0.003)	.	.	(0.006)	(0.003)	.	(0.002)	(0.002)	31 mm Ø x 2 or 18 mm
IARM 295A	.	0.002	.	(0.003)	.	.	0.004	.	.	0.0019	(0.001)	31 mm Ø x 2 or 18 mm
ECRM 294-1D	0.0037	(<0.00005)	(0.00026)	.	(0.000128)	(0.00053)	(0.0014)	.	(<0.00008)	(0.0008)	(0.0001)	40 mm Ø x 20 mm
IARM 214A	.	(0.001)	.	0.0026	.	.	0.008	.	.	0.002	.	31 mm Ø x 2 or 18 mm
VS RG20/1	0.093	.	-45 mm Ø x ~30 mm
VS RG22/1	0.33	.	-45 mm Ø x ~30 mm
BS 193	.	0.0007	0.0020	(0.004)	.	.	0.004	.	.	0.003	.	32 mm Ø x ~7 or 19+ mm
CT ISO035A	.	Fe: 65.91	.	.	(<0.0001)	.	0.003	.	.	0.001	<0.001	30-35 mm Ø x ~19 mm
IARM 296A	.	(0.001)	.	(0.003)	.	.	0.007	.	.	(0.002)	.	31 mm Ø x 2 or 18 mm
13X NSC3Z	-40 mm Ø x ~15 mm
BS 190	.	0.0005	.	0.0045	.	.	0.003	.	.	0.002	.	38 mm Ø x ~7 or 19+ mm
CT ISO129A	.	Fe: 62.62	30-35 mm Ø x ~16 mm
IARM 19C *	(0.004)	0.0011	.	0.003	.	.	0.0061	0.005	.	0.003	.	31 mm Ø x 2 or 18 mm
13X NSC6A	40 mm Ø x 13 mm HIP
VS RG23/1	0.21	.	-45 mm Ø x ~30 mm
13X NSC2P	-40 mm Ø x ~12 mm
BS 181A	.	0.0009	.	0.0010	.	.	0.005	.	.	0.007	last	38 mm Ø x ~7 or 19+ mm
BS 181B	(0.002)	(0.0008)	(0.001)	0.0010	(0.0005)	(0.0007)	(0.004)	Fe:62.9	17025	0.0051	(0.0004)	38 mm Ø x ~7 or 19+ mm
13X 21800A	.	(0.001)	-38 mm Ø x ~15 mm
13X NSC4F	-40 mm Ø x ~15 mm
SRM 1297	32 mm Ø x 19 mm
13X NSC1P	-40 mm Ø x ~15 mm
VS RG21/1	0.18	.	-45 mm Ø x ~30 mm
CZ SL-5A	0.005	0.004	0.07	.	0.004	.	-39 mm Ø x 25 mm
BS 191	.	(0.0006)	.	0.002	.	.	(0.006)	0.002	.	0.012	.	38 mm Ø x ~7 or 19+ mm
VS RG19/1	0.14	.	-45 mm Ø x ~30 mm
13X NSA4B	-40 mm Ø x ~15 mm
13X NSA10A	.	0.0031	-38 mm Ø x ~15 mm
BS 180A	.	(0.0023)	.	0.003	.	.	(0.002)	.	.	(0.002)	.	37 mm Ø x ~7 or 19+ mm
IARM 292A	.	0.0011	.	0.0024	.	.	0.004	(0.006)	.	0.005	.	31 mm Ø x 2 or 18 mm
BS 180B	(0.004)	0.0011	0.0009	0.0043	17025	(0.0007)	0.0040	(0.003)	Fe:58.5	(0.005)	(0.0009)	38 mm Ø x ~7 or 19+ mm
HRT FE2017-H	30 mm x 30 mm x 10 mm
13X NSA5A	-40 mm Ø x ~14 mm
IARM 17D	0.005	0.001	(0.002)	0.003	(0.0002)	(0.001)	0.0044	(0.003)	.	0.010	(0.002)	31 mm Ø x 2 or 18 mm
13X NSC7A	-40 mm Ø x ~13 mm
13X NSC5B	-40 mm Ø x ~15 mm

CRM NICKEL BINARIES

analysis listed in mass %

-40 mm Ø x ~15 mm

Number	Ni	C	Mn	P	S	Si	Cu	Cr	Al	Co	N	Mg	Mo	Nb	Ti	W
14X FeNi50C *	51.4	0.025	.	0.015	0.14	0.15	0.09	0.07	0.30	0.42
14X FeNi45C *	45.0	0.005	.	0.03	0.003	0.75	0.085	0.07	0.95	0.6
14X 94100A	41.00	0.0055	0.443	0.0051	0.0027	0.103	0.0628	0.0265	0.0208	0.0016	0.0021	0.0053	(0.01)	0.0011	0.0017	.
14X FeNi35D	34.17	0.035	0.303	0.0400	0.146	0.255	0.0363	0.409	(0.004)	0.400
14X FeNi20B	20.06	0.0137	0.0284	0.010	0.0089	1.12	0.074	0.102	0.018	0.994
14X FeNi10A	10.12	0.095	0.272	0.015	0.027	0.061	0.029	0.070	0.025	.	0.0055
14X FeNi8A	8.10	0.097	0.330	0.015	0.029	0.097	0.030	0.250	0.029	.	0.0061
14X FeNi6A	6.08	0.100	0.330	0.0155	0.028	0.075	0.028	0.073	0.025	.	0.0055

SULFUR AND PHOSPHORUS IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	S	P	Ni	Cr	C	Mn	Si	Cu	Al	Co	Mo	N	Nb	Ti	V
2	CT 416	0.36	0.018	0.24	13.15	0.088	0.52	0.63	0.004	.	0.019	0.065	0.020	.	.	0.025
1	IARM 10D	0.334	0.0178	0.291	12.42	0.110	1.11	0.475	0.192	(0.0027)	0.0187	0.148	0.0241	0.0027	0.0015	0.051
2	BS 150	0.33	0.020	0.19	18.61	0.048	1.71	0.43	0.042	0.002	0.024	1.97	0.029	0.003	.	0.054
1	SRM 1223	0.329	0.018	0.232	12.64	0.127	1.08	0.327	0.081	.	.	0.053	.	.	.	0.068
2	BS 90F	0.328	0.023	0.30	13.01	0.085	0.53	0.58	0.12	(0.006)	0.021	0.14	0.037	0.011	.	0.076
1	BS 303	0.326	0.028	8.17	17.23	0.044	1.80	0.415	0.627	0.0019	0.071	0.410	0.023	0.008	0.017	0.056
1	13X 30300A	0.312	0.0205	8.60	17.62	0.041	1.83	0.422	0.025	.	0.0255	0.334	0.034	.	.	0.091
2	CT 303	0.31	0.029	9.08	17.78	0.070	1.64	0.58	0.49	.	0.16	0.41	.	.	.	0.044
1	IARM 355A	0.31	0.0186	0.427	17.81	0.0274	0.47	0.435	0.083	0.0016	0.047	0.337	0.0439	0.0095	0.0020	0.038
2	BS 154	0.302	0.027	0.25	17.58	0.030	0.40	1.26	0.063	(0.002)	0.019	0.31	0.039	0.005	.	0.046
2	13X 12549K	0.29	0.092	1.26	11.70	0.16	0.34	0.43	0.10	.	0.52	1.49	.	.	0.23	.
2	BS 153	0.280	0.018	0.140	17.38	0.026	0.41	0.53	0.052	0.002	0.017	0.30	0.021	0.002	(0.004)	0.045
2	BS 152	0.275	0.022	0.14	13.41	0.320	0.36	0.44	0.050	(0.002)	0.015	0.061	0.020	0.006	.	0.051
3	CZ SP-1A	0.26	0.024	8.6	17.7	0.047	1.87	0.33	0.52	0.004	0.095	0.42	.	0.012	0.02	0.058
1	13X 12548M	0.219	0.027	1.075	12.96	0.188	0.577	0.425	0.230	.	0.353	1.318	0.0500	0.586	.	.
1	IARM 352A	0.21	0.0182	0.269	13.11	0.341	1.13	0.357	0.148	(0.0025)	(0.016)	0.38	0.029	(0.012)	0.0015	0.028
1	13X 43020A	0.189	0.0246	0.517	16.07	0.147	1.439	0.415	0.0687	0.0047	0.0191	0.226	0.0212	0.0102	.	0.0542
1	IMZ 154	0.16	0.040	9.86	17.71	0.076	2.18	0.89	0.33	(0.16)	0.105	2.58	.	.	1.00	0.073
2	BS 155	0.145	0.014	0.13	16.64	1.00	0.35	0.40	0.035	(0.001)	0.019	0.46	0.032	0.002	.	0.10
1	13X 12536S	0.136	0.052	12.07	15.30	0.149	0.406	0.865	0.065	0.049	0.298	2.54	0.062	.	0.105	.
1	13X 8110L	0.068	0.052	4.62	12.30	0.750	0.446	0.812	0.344	(0.071)	0.31	2.81	0.0286	.	0.0108	0.211
1	13X 12535BE	0.0591	0.0400	14.79	16.95	0.229	0.342	1.407	0.130	0.194	0.146	4.09	0.029	.	0.625	0.252
1	SRM C1154a	0.051	0.06	13.08	19.31	0.100	1.44	0.53	0.44	.	0.38	0.068	.	.	.	0.135
1	13X 19003C	0.046	0.0382	12.46	18.99	0.047	1.138	0.497	0.171	.	0.105	2.50	0.077	0.120	.	0.0486
1	VS LG58	0.0280	0.0135	4.26	23.4	0.48	0.99	0.292	0.388	.	.	2.41	.	0.214	0.039	0.264
1	VS LG60	0.0205	0.028	19.86	21.8	0.020	2.31	0.289	0.027	0.040	.	3.62	.	.	0.83	0.229
2	13X 19004B	0.014	0.069	17.9	22.8	0.066	1.96	0.36	0.022	.	.	3.62	.	0.18	.	.
1	13X 18004B	0.0191	0.068	12.67	21.57	0.099	1.400	1.21	0.050	0.011	0.211	0.601	0.061	0.749	.	0.161

Number	Ag	As	B	O	Pb	Sn	Ta	W	Units
CT 416	0.0002	.	.	.	<0.001	0.005	.	.	30-35 mm Ø x ~16 mm
IARM 10D	.	(0.007)	(0.002)	(0.005)	.	0.010	.	(0.005)	31 mm Ø x 2 or 18 mm
BS 150	.	.	.	0.012	.	(0.003)	.	0.01	35 mm Ø x ~7 or 19+ mm
SRM 1223	32 mm Ø x 19 mm
BS 90F	.	.	.	0.011	.	0.005	.	0.032	38 mm Ø x ~7 or 19+ mm
BS 303	.	.	0.0013	0.0058	.	0.0091	.	0.023	44 mm Ø x ~7 or 19+ mm 17025
13X 30300A	.	.	0.0035	~40 mm Ø x ~15 mm
CT 303	0.0003	.	.	.	0.001	0.007	.	.	30-35 mm Ø x ~16 mm
IARM 355A	.	(0.004)	(0.0011)	(0.010)	(0.0002)	(0.005)	.	(0.018)	31 mm Ø x 2 or 18 mm
BS 154	.	.	.	0.008	.	(0.005)	.	(0.01)	38 mm Ø x ~7 or 19+ mm
13X 12549K	40 mm Ø x 15 mm
BS 153	.	(0.004)	.	.	(0.001)	0.002	.	(0.002)	35 mm Ø x ~7 or 19+ mm
BS 152	0.003	.	<0.01	41 mm Ø x ~7 or 19+ mm
CZ SP-1A	.	0.006	0.0007	.	.	0.01	.	0.03	~39 mm Ø x 25 mm
13X 12548M	Sb:0.022	.	.	0.031	40 mm Ø x 15 mm
IARM 352A	.	(0.005)	(0.0007)	(0.005)	.	0.0046	.	(0.005)	31 mm Ø x 2 or 18 mm
13X 43020A	.	.	(0.0032)	0.0108	~40 mm Ø x ~15 mm
IMZ 154	40 mm Ø x 40 mm
BS 155	.	.	.	0.0048	.	(0.003)	.	.	36 mm Ø x ~7 or 19+ mm
13X 12536S	.	.	0.0274	.	.	0.018	0.091	.	~40 mm Ø x ~15 mm
13X 8110L	.	0.074	0.989	~40 mm Ø x ~15 mm
13X 12535BE	.	.	0.0051	.	.	0.0194	(0.020)	.	~40 mm Ø x ~15 mm
SRM C1154a	0.017	.	.	.	32 mm Ø x 19 mm
13X 19003C	(0.005)	.	~40 mm Ø x ~15 mm
VS LG58	0.21	~47 mm Ø x ~30 mm
VS LG60	0.115	~47 mm Ø x ~30 mm
13X 19004B	40 mm Ø x 15 mm
13X 18004B	~40 mm Ø x ~15 mm

SELENIUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Se	Ni	Cr	C	Mn	P	S	Si	Cu	Al	Co	Mo	N	Nb	Ti
2	BS 151	0.328	0.24	13.19	0.090	0.41	0.021	0.018	0.65	0.11	(0.002)	0.018	0.088	0.022	0.005	(<0.003)
2	BS 186A	0.229	35.86	0.16	0.040	0.72	0.008	0.0053	0.19	0.016	(0.001)	0.028	0.0032	0.0026	(<0.002)	(<0.003)
1	IARM 253A	0.21	9.17	17.90	0.041	1.50	0.140	0.0089	0.50	0.223	0.003	0.088	0.348	0.0373	0.016	0.002
1	IARM 24B	0.19	35.86	0.121	0.053	0.82	0.009	0.0010	0.28	0.052	0.002	0.036	0.011	0.0017	<0.01	0.002
1	IARM 353A	0.17	0.265	17.01	0.98	0.95	0.019	0.025	0.49	0.13	0.0018	0.032	0.50	0.027	(0.011)	0.0015
2	CT ISO124A	0.167	48.07	0.079	0.011	0.73	0.007	0.006	0.40	0.015	.	0.012	0.009	.	.	.
2	BS 156	0.142	0.35	16.87	1.06	1.15	0.022	0.007	0.47	0.09	(<0.002)	0.047	0.50	0.041	0.005	0.001
1	IARM 253B	0.13	9.11	17.64	0.051	1.61	0.13	0.011	0.46	0.44	(0.004)	0.145	0.59	0.031	0.021	0.0027

Number	B	Fe	O	Sn	Ta	V	W	Zr	Units
BS 151	.	.	0.009	0.005	.	0.046	0.010	.	50 mm Ø x ~7 or 19+ mm
BS 186A	.	.	.	(0.002)	.	0.0012	(0.01)	.	38 mm Ø x ~7 or 19+ mm
IARM 253A	0.0003	.	0.009	0.01	.	0.106	0.10	.	31 mm Ø x 2 or 18 mm
IARM 24B	(0.001)	62.6	0.003	0.0018	<0.005	<0.005	<0.04	<0.005	31 mm Ø x 2 or 18 mm
IARM 353A	(0.0006)	.	(0.005)	0.0056	(0.004)	0.116	0.041	(0.002)	31 mm Ø x 2 or 18 mm
CT ISO124A	.	50.65	30-35 mm Ø x ~19 mm
BS 156	.	.	0.0045	(0.004)	.	0.13	0.11	.	41 mm Ø x ~7 or 19+ mm
IARM 253B	0.0007	.	0.007	(0.012)	(0.003)	0.092	(0.05)	.	31 mm Ø x 2 or 18 mm

STAINLESS STEEL WITH NI < 5.0 %

CONTINUED ON THE NEXT PAGE

= Class, 1=CRM, 2=RM, and 3=RM with no uncertainties analysis listed in mass % except * which is mg/Kg ** Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	14X HS10A	1.710	0.134	0.0135	0.0099	0.660	0.0605	0.146	14.83	0.0866	1.679	(0.001)	.	.	1.142	1.75
3	CZ SL-4A	1.38	2.85	0.038	0.017	2.28	0.75	2.04	26.3	0.11	0.92	.	1.11	0.8	0.54	0.35
2	BS 156	1.06	1.15	0.022	0.007	0.47	0.09	0.35	16.87	0.047	0.50	0.041	0.005	0.001	0.13	0.11
1	BS 93F	1.047	0.59	0.0266	(0.0025)	0.49	0.132	0.187	16.72	0.021	0.46	0.051	0.0029	0.0012	0.057	0.0016
1	13X 44004A	1.052	0.346	0.0214	0.0178	0.363	0.0548	0.207	16.74	0.0188	0.462	0.0247	.	.	0.076	0.030
1	IARM 13D	1.040	0.697	0.0195	0.0012	0.614	0.184	0.256	16.36	0.0212	0.488	0.0492	0.0074	0.0035	0.058	0.046
2	BS 155	1.00	0.35	0.014	0.045	0.40	0.035	0.13	16.64	0.019	0.46	0.032	0.002	.	0.10	.
1	NCS HS41752	0.97	0.46	0.023	0.0016	0.48	0.082	0.192	17.61	.	0.057	.	.	.	0.088	.
1	ECRM 291-1D	0.90	0.81	0.017	0.0088	0.91	0.071	0.56	17.15	0.0233	2.10	0.1142	.	.	0.39	.
1	VS LG40/1	0.66	0.318	(0.02)	(0.006)	0.289	(0.15)	0.271	13.67	.	0.039	.	.	.	0.038	.
1	VS LG39/1	0.406	0.64	(0.02)	(0.007)	0.94	(0.12)	0.42	13.11	.	0.136	.	.	.	0.135	.
1	13X 14122A	0.356	0.480	0.0177	0.0021	0.449	0.066	0.632	15.91	0.0224	0.955	0.0290	0.006	.	0.101	0.004
1	IARM 154B	0.35	0.405	0.017	0.0004	0.45	0.087	0.223	12.20	0.020	0.079	0.020	0.003	0.002	0.067	0.010
2	BS SS4952	0.347	0.41	0.016	0.003	0.66	0.045	0.23	13.15	0.030	0.049	0.027	0.004	0.002	0.089	(0.007)
1	IARM 154C	0.339	0.423	0.0174	0.0043	0.37	0.120	0.215	12.41	0.016	0.036	0.054	0.014	0.0015	0.043	(0.005)
2	BS SS4951	0.333	0.58	0.016	0.0012	0.62	0.033	0.15	13.55	0.013	0.009	0.0127	0.006	0.002	0.032	.
2	BS 152	0.320	0.36	0.022	0.275	0.44	0.050	0.14	13.41	0.015	0.061	0.020	0.006	.	0.051	<0.01
1	TRSID 1825	0.305	0.650	0.019	0.022	0.336	0.100	0.308	12.90	0.026	0.052	.	.	.	0.052	.
1	ECRM 272-1D	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.2445	11.927	0.0245	0.0030	0.0508	0.0028	0.00096	0.0167	.
1	SS 469	0.279	0.598	0.015	0.020	0.421	(0.02)	0.246	11.93	(0.01)	(0.02)	.
1	VS LG38/1	0.255	0.73	(0.02)	(0.01)	0.81	(0.16)	0.551	11.75	.	0.344	.	.	.	0.190	.
1	IMZ 168	0.24	1.36	0.019	0.012	1.12	0.093	0.17	13.91	(0.019)	0.026	(0.057)	.	(0.003)	0.053	.
1	13X 12547M	0.238	1.191	0.0441	0.0746	0.344	0.531	1.492	17.49	0.302	1.009	0.099	0.347	.	0.1021	.
1	IARM 205D	0.232	0.736	0.0209	0.0028	0.257	0.122	0.841	12.18	0.043	1.002	0.0484	0.013	0.0022	0.319	1.07
1	BS 422	0.232	0.640	0.0169	0.0013	0.404	0.080	0.676	11.25	0.0293	0.896	0.050	0.045	0.0011	0.274	0.95
1	SS 472	0.227	1.02	0.032	0.029	1.05	(0.02)	1.95	15.82	(0.02)	0.661	.	.	.	(0.02)	.
1	13X 42200A	0.220	0.651	0.0182	0.0012	0.314	0.136	0.738	11.41	0.0114	1.042	0.0585	0.0203	.	0.246	1.177
1	NCS HS41749	0.21	0.39	0.023	0.012	0.56	1.15	1.52	12.27	.	0.158	.	.	.	0.074	.
1	13X 42000A	0.208	0.679	0.0241	0.0253	0.496	0.202	0.295	12.56	0.0161	0.0398	0.0273	.	.	0.046	.
1	13X 14923A	0.205	0.501	0.0197	0.0031	0.330	0.0563	0.452	11.26	0.0207	0.819	0.0321	0.005	.	0.295	.
1	VS LG41/1	0.200	0.91	(0.02)	(0.008)	0.64	(0.12)	1.53	15.90	.	0.277	.	.	.	0.303	.
1	IMZ 171	0.195	0.42	0.020	0.014	0.21	0.116	0.59	11.44	0.024	1.23	0.057	.	(0.001)	0.26	.
1	NCS HS41748	0.194	0.62	0.016	0.011	0.54	0.008	0.077	12.70	.	0.010	.	.	.	0.048	.
2	HRT FE2015-H	0.19	0.52	0.021	0.002	0.37	0.07	0.25	12.87	.	0.07	0.045	.	.	0.055	.
1	13X 12548M	0.188	0.577	0.027	0.219	0.425	0.230	1.075	12.96	0.353	1.318	0.0500	0.586	.	.	0.031
2	HRT FE2010-H	0.18	0.60	0.024	0.004	0.39	0.08	1.94	15.95	0.023	0.13	.	.	.	0.044	0.024
1	SS 70	0.18	0.38	0.024	0.020	0.35	(0.06)	0.40	16.35
1	IARM 20B	0.18	0.35	0.019	0.004	0.40	0.069	1.94	12.42	0.030	0.32	0.0434	0.010	0.004	0.17	3.52
1	IARM 20C	0.18	0.30	0.018	0.007	0.35	0.060	1.93	12.15	0.031	0.12	0.0222	0.010	(0.003)	0.086	2.59
1	IMZ 167	0.175	1.16	0.016	0.0025	0.755	0.106	0.16	13.07	(0.021)	0.024	0.053	.	(0.002)	0.054	.
1	13X 41800A **	0.175	0.335	0.017	0.0005	0.32	0.105	2.05	12.3	0.036	0.07	0.029	0.004	.	0.021	2.80
1	SS 473	0.172	0.494	0.019	0.030	0.604	(0.02)	(0.06)	9.06	(0.01)	0.95	.	.	.	(0.02)	.
2	ES 183A	0.17	0.85	0.016	0.040	0.39	0.093	1.85	11.14	0.035	0.299	0.0256	0.006	0.002	0.090	2.60
1	13X 15024X	0.166	0.610	0.0284	0.0294	0.750	0.332	2.95	14.55	0.1059	0.299	0.0156	0.099	.	0.150	0.039
1	13X 43100A	0.166	0.378	0.0199	0.0050	0.535	0.134	2.10	16.39	0.0239	0.0768	0.075	0.006	.	0.0577	0.004
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
2	13X 12549K	0.16	0.34	0.092	0.29	0.43	0.10	1.26	11.70	0.52	1.49	.	0.23	.	.	.
1	IARM 12C	0.155	0.55	0.022	0.0032	0.34	0.33	2.23	15.78	0.048	0.125	0.056	0.020	(0.002)	0.040	0.015
1	SS 470	0.153	0.235	0.024	0.035	0.335	(0.02)	0.369	17.68	(0.02)	(0.02)	.
2	BS 92B	0.150	0.42	0.021	0.003	0.42	0.13	2.12	15.92	0.04	0.17	0.073	(0.006)	.	0.07	0.02
1	SRM 1219	0.149	0.42	0.026	0.001	0.545	0.162	2.16	15.64	.	0.164	0.078	.	.	.	0.056
1	BS 431	0.146	0.579	0.0232	0.0047	0.393	0.282	2.25	15.8	0.050	0.092	0.049	0.034	0.0007	0.062	0.012
1	IARM 335A	0.138	0.85	0.016	0.0005	0.374	0.086	4.27	15.30	0.053	2.72	0.085	0.015	(0.002)	0.094	0.008
1	BS 355	0.138	0.862	0.0171	0.0003	0.374	0.173	4.18	15.43	0.053	2.73	0.081	0.0103	0.0007	0.106	0.0069
1	13X 41001A	0.136	0.464	0.0142	0.0037	0.298	0.056	0.0939	12.06	0.0143	0.0102	0.0316	.	.	0.079	.
1	NCS HS28747	0.132	0.453	0.027	0.0068	0.502	0.126	1.79	16.24	0.051	0.153	0.030	.	(0.002)	0.075	.
1	13X 12540M	0.131	0.800	0.051	0.0512	0.805	0.181	4.975	27.44	0.109	0.993	0.054	0.107	.	0.210	0.097
1	BS 410C	0.131	0.381	0.0206	0.0051	0.366	0.084	0.352	12.78	0.0185	0.055	0.039	0.0056	0.0006	0.042	0.0131
1	BS 0021	0.128	0.420	0.021	0.008	0.354	0.040	0.100	12.00	0.015	0.016	0.029	(0.001)	(0.003)	0.029	0.005
1	IARM 10C	0.128	0.35	0.018	0.002	0.329	0.081	0.24	12.25	0.022	0.053	0.015	0.003	0.002	0.024	0.011
1	SRM 1223	0.127	1.08	0.018	0.329	0.327	0.081	0.232	12.64	.	0.053	.	.	.	0.068	.
1	ECRM 296-1D	0.1166	0.676	0.0178	0.0026	0.242	0.1498	2.790	11.82	0.0218	1.700	0.0214	.	.	0.363	.
1	BS 416	0.116	0.64	0.0237	0.35	0.232	0.154	0.371	13.41	0.0241	0.030	0.043	(0.006)	0.0012	0.100	0.0034
1	13X 15035U	0.115	0.674	0.0415	0.0456	0.636	0.204	2.38	14.00	0.199	0.399	0.0584	0.500	.	0.160	0.048
1	13X 64152A	0.114	0.666	0.0123	0.0020	0.224	0.0622	2.50	11.34	0.0185	1.567	0.0339	.	.	0.275	.
1	13X 41600A	0.111	0.627	0.0253	0.302	0.442	0.160	0.331	13.23	0.0216	0.0499	0.0245	0.0053	.	0.0888	(0.003)
1	13X 12533Z	0.110	0.812	0.0149	0.0156	0.440	0.131	5.06	18.80	0.0299	1.05	0.073	.	0.147	0.181	.
1	IARM 291A	0.11	0.71	0.016	0.009	0.230	0.060	2.62	11.3	0.021	1.61	0.035	0.022	0.0011	0.29	(0.01)
2	CT 410	0.11	0.48	0.015	0.023	0.27	0.079	0.34	12.04	0.023	0.053	0.036	0.001	0.001	0.025	0.004
1	IMZ 156	0.101	0.84	0.031	0.008	1.11	0.071	0.64	16.96	(0.033)	0.035	.	.	(0.032)	0.073	.
1	SS 471	0.095	0.417	0.018	0.023	0.326	(0.02)	0.96	23.85	(0.02)	(0.03)	.
1	IMZ 158	0.091	1.34	0.015	0.007	2.23	0.097	0.24	25.51	.	0.025	.	.	.	0.12	0.078
2	BS 151	0.090	0.41	0.021	0.018	0.65	0.11	0.24	13.19	0.018	0.088	0.022	0.005	(0.003)	0.046	0.010
1	13X 15023W **	0.09	1.76	0.01	0.005	0.35	0.03	0.96	11.2	0.05	0.98	0.01	1.43	.	0.03	0.039
1	13X 14742A	0.084	0.714	0.0214	0.0008	0.910	0.1267	0.449	17.60	0.0186	0.0968	0.0209	0.0202	0.0051	0.0463	.
2	BS 90F	0.085	0.53	0.023	0.328	0.58										

STAINLESS STEEL WITH C > 0.05 %

CONTINUED ON THE NEXT PAGE

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	KUT S24	0.65	0.94	0.062	0.036	0.76	0.12	9.19	10.28	.	0.41	.	1.65	0.27	.	.
1	VS LG76	0.445	0.342	0.021	0.0076	0.455	0.098	13.39	13.77	.	0.263	0.031	.	0.020	0.041	2.38
1	VS LG74	0.373	0.962	0.024	0.0049	2.49	0.093	23.66	18.30	0.031	0.104	0.030	.	0.030	.	0.052
1	KUT S21	0.37	0.19	0.017	0.021	1.26	0.11	22.3	3.99	.	4.12	.	.	0.50	.	.
2	CZ CM-19A	0.361	0.783	0.0440	0.0182	1.588	0.986	15.27	13.12	0.222	1.023	(0.021)	0.091	0.254	1.235	0.311
1	VS LG79	0.313	1.28	0.017	0.0036	0.703	0.065	8.72	19.23	.	1.18	.	0.47	.	0.049	1.16
2	CZ SP-3C	0.30	0.43	0.026	0.011	0.84	0.185	5.31	16.42	0.041	0.26	.	(0.04)	(0.17)	0.19	0.12
1	DSZU C016	0.281	3.26	0.0192	0.0174	1.16	0.054	7.47	21.9	.	0.52	0.010	.	0.72	0.036	0.014
3	CZ SP-3B	0.27	0.29	0.023	0.008	0.72	0.62	5.65	15.1	0.02	0.24	.	.	0.13	0.10	0.12
1	KUT S19	0.26	0.32	0.010	0.021	2.32	0.19	12.8	7.00	.	0.11	.	0.81	0.048	.	.
1	SRM C1153a	0.225	0.544	0.030	0.019	1.00	0.226	8.76	16.70	0.127	0.24	.	.	.	0.176	.
1	VS LG34/5	0.222	0.362	0.010	0.019	0.80	0.269	9.54	17.32	.	0.266	.	.	0.138	0.195	0.33
1	13X 18001B	0.207	0.463	0.0090	0.0786	0.203	0.149	6.13	15.92	0.0231	0.816	0.0347	0.612	.	0.0996	.
1	KUT H6/1	0.20	0.49	0.021	0.024	0.67	0.10	0.15	18.9	0.10	.	(0.12)
2	CZ SP-3D	0.171	0.34	0.021	0.015	0.71	0.73	5.36	16.44	0.033	0.25	.	(0.04)	0.088	0.11	0.12
2	13X NSB1D	0.17	0.44	.	.	0.58	.	10.0	19.1	.	0.11	0.04
1	IARM 339A	0.16	1.71	0.004	0.009	0.64	0.021	12.9	17.0	0.007	2.79	0.0060	(0.005)	(0.002)	0.007	(0.0119)
2	13X NSA3J	0.16	1.07	.	.	0.57	.	12.0	16.1	.	2.8	0.20
1	13X 18002D	0.159	0.722	0.0245	0.0487	0.352	0.116	7.92	17.77	0.0514	0.209	0.072	1.531	.	0.0542	.
2	13X 12540L	0.15	0.44	.	.	1.05	.	5.17	27.88	.	0.54
2	CZ CM-18A	0.143	1.792	0.0182	0.0119	0.903	2.393	20.44	20.59	0.097	2.282	0.0848	.	.	0.113	0.097
1	SS 468/1	0.143	1.70	0.014	0.020	1.41	.	8.90	17.96	0.018
1	SRM C1152a	0.142	0.95	0.023	0.0064	0.64	0.097	10.86	17.76	0.22	0.44	.	.	.	0.033	.
1	VS LG32/5	0.138	0.54	0.0057	0.039	0.185	0.019	7.10	19.75	.	0.110	.	0.0032	0.008	0.92	0.317
1	IARM 289A	0.126	1.67	0.006	0.0019	0.58	0.016	7.12	17.0	0.054	(0.005)	.	0.008	0.028	0.01	0.01
1	IARM 241D	0.125	1.94	(0.003)	0.0023	1.00	0.242	8.98	18.12	0.022	(0.02)	(0.008)	0.028	0.018	0.031	(0.012)
1	DSZU C018	0.125	1.09	0.0268	0.0099	0.53	0.163	9.33	17.54	.	0.189	0.009	.	0.54	0.048	0.066
1	13X NSB3G	0.121	0.632	.	.	0.471	.	9.26	15.22	.	0.630	0.198
1	KUT H5	0.12	0.48	0.017	(0.003)	0.70	0.22	0.20	21.8	0.03	.	0.10
2	13X 17001B	0.114	1.73	0.080	0.016	0.34	0.037	6.05	14.89	0.15	0.12	0.040	0.76	.	.	.
1	13X 18003C	0.113	1.000	0.0545	0.0245	0.805	0.0433	10.08	19.56	0.100	0.401	0.090	1.042	.	0.0750	.
1	IRSID 1819	0.112	0.903	0.023	0.0112	0.616	0.064	7.10	17.31	0.117	0.110	0.0288
1	13X 17002E	0.112	0.801	0.0409	0.0250	0.486	0.1012	7.87	17.45	0.0702	0.204	0.061	0.487	.	0.0587	.
1	NCS HS28743	0.110	0.841	0.024	0.0082	0.780	0.089	18.02	23.71	0.102	0.115	0.057	0.016	(0.003)	0.077	.
1	IMZ 166A	0.108	1.99	0.019	0.005	2.51	0.025	21.93	25.53	0.030	(0.025)	.	.	0.003	0.038	.
1	13X 14828A *	0.108	1.53	0.027	0.007	2.17	0.41	11.2	19.4	0.145	0.300	0.037	0.016	.	0.081	0.015
1	VS LG81	0.104	0.29	0.0121	0.0014	0.231	0.088	22.5	11.51	.	1.22	.	0.004	2.93	0.040	0.012
1	VS LG77	0.101	0.34	0.0149	0.0021	0.44	0.116	4.32	15.67	.	0.020	0.054	0.109	.	0.022	0.006
1	IMZ 164	0.100	1.77	0.019	0.002	0.82	0.26	6.75	20.96	0.035	3.48	0.249	0.049	(0.003)	0.053	(0.025)
2	13X 17003A	0.10	0.85	0.037	0.035	0.78	0.08	11.9	11.89	0.07	0.27	.	0.34	.	.	.
1	VS LG73	0.098	1.26	0.019	0.0073	0.570	0.140	17.74	22.60	0.247	0.061	0.0319	.	0.0022	.	0.102
1	KUT S20	0.097	1.50	0.011	0.025	1.80	0.44	18.2	2.06	.	3.15	.	1.22	(0.01)	.	.
1	VS LG80	0.097	0.709	0.025	0.0029	2.15	0.166	19.38	24.7	.	0.086	0.064	.	0.015	0.032	0.029
2	BS 253	0.094	0.58	0.018	<0.001	1.81	0.14	10.89	20.68	0.15	0.21	0.146	0.017	0.005	0.050	0.03
1	IARM 234C	0.092	1.93	0.0090	(0.0027)	0.88	3.41	9.00	18.15	0.034	0.012	(0.01)	0.053	0.026	0.055	(0.006)
1	SS 462	0.092	0.74	0.010	0.018	0.46	.	12.53	12.37
1	13X 12537T	0.0889	1.116	0.0382	0.0206	1.151	0.248	10.71	20.43	0.1520	3.05	0.048	0.102	0.273	0.0908	.
1	DSZU C015	0.087	0.420	0.0118	0.059	0.214	0.070	12.15	15.36	.	0.89	0.020	.	0.177	0.021	0.023
1	SS 464/1	0.086	0.791	0.020	0.028	0.57	.	20.05	25.39	0.054
1	IMZ 165	0.082	0.98	0.017	0.007	1.42	0.040	19.01	23.28	0.029	0.025	0.105	.	(0.002)	0.042	.
1	SS 467/1	0.082	0.788	0.018	0.019	0.52	.	9.21	18.09	.	.	.	0.99	.	.	.
1	VS LG35/5	0.078	0.81	0.042	0.0094	1.01	0.066	8.23	18.44	.	0.39	.	.	0.73	0.041	0.107
1	13X 17001C	0.0769	1.543	0.055	0.0134	0.215	0.0161	6.31	14.83	0.0979	0.0967	.	0.546	.	.	.
1	KUT S26	0.076	0.99	0.027	0.026	0.67	0.14	3.31	18.9	.	2.59	.	0.07	0.11	.	.
1	NCS HS41750	0.075	1.43	0.031	0.012	0.33	0.276	6.35	16.31	.	0.107	0.058	.	(0.001)	0.064	.
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	ECRM 270-1D	0.0742	0.540	0.0196	0.0007	1.517	0.1076	10.86	20.88	0.0685	0.2099	0.1417	.	(0.0019)	0.0256	(0.0244)
1	VS LG78	0.074	1.60	0.017	0.0017	0.58	0.053	35.4	14.71	.	0.061	0.0062	0.004	1.31	0.020	3.16
1	BS 192	0.074	0.835	0.025	0.0005	0.387	0.412	7.11	16.44	0.104	0.430	0.0290	0.168	0.076	0.124	0.05
2	BS 83G	0.073	1.66	0.024	0.004	0.56	0.114	19.15	24.50	0.153	0.085	0.026	0.061	(0.003)	0.077	0.007
1	VS LG72	0.072	1.32	.	0.0050	0.334	0.306	12.4	16.36	0.090	2.07	0.0073	.	0.57	.	0.077
1	13X 12534X	0.0716	0.589	0.0192	0.0086	0.811	0.0586	8.50	17.71	0.0602	2.04	.	0.201	0.348	0.110	0.010
1	IARM 316A	0.070	0.61	0.023	0.0011	1.50	0.19	10.81	21.07	0.118	0.250	0.16	(0.003)	(0.002)	0.042	0.022
1	VS LG63	0.068	0.356	0.010	0.0050	0.285	0.024	22.15	10.13	.	1.65	.	0.113	2.98	0.086	0.43
1	KUT S25	0.067	1.90	0.045	0.015	1.49	0.07	13.8	15.6	.	1.77	.	0.07	0.46	.	.
2	CT 305	0.067	1.85	0.025	0.022	1.55	0.29	11.95	18.58	0.22	0.45	.	.	.	0.078	.
1	SRM 1171	0.067	1.81	(0.019)	(0.013)	0.536	0.1205	11.18	17.50	(0.097)	0.167	.	.	0.346	.	(0.012)
1	BS 9841	0.067	1.69	0.024	0.024	0.54	0.356	19.55	24.30	0.116	0.57	0.064	0.070	(0.002)	0.070	0.06
1	SS 465/1	0.066	1.380	0.021	0.012	0.405	0.098	9.24	17.31	0.053	0.092	.	.	0.40	0.102	.
1	BS 192A	0.066	0.768	0.021	<0.002	0.300	0.334	7.01	16.44	0.114	0.28	0.029	0.208	0.083	0.077	0.048
1	IMZ 152	0.065														

STAINLESS STEEL WITH C > 0.05 %

CONTINUED FROM THE PREVIOUS PAGE

Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units
KUT S24													30-35 mm Ø x 18 or 40 mm
VS LG76	0.034												~45 mm Ø x ~28 mm
VS LG74	0.035												~45 mm Ø x ~28 mm
KUT S21													30-35 mm Ø x 18 or 40 mm
CZ CM-19A	0.0788		(0.091)		(0.0036)					0.0283			~37 mm Ø x ~25 mm
VS LG79	0.059												~45 mm Ø x ~28 mm
CZ SP-3C	0.095	(0.03)	1.67							(0.02)			~39 mm Ø x 25 mm
DSZU C016	0.007				0.0004								40 mm Ø x 25 mm
CZ SP-3B	0.08		0.88							0.01			~39 mm Ø x 25 mm
KUT S19													30-35 mm Ø x 18 or 40 mm
SRM C1153a								0.006					32 mm Ø x 19 mm
VS LG34/5	0.029												~38 mm Ø x ~25 mm
13X 18001B	0.0157												~40 mm Ø x ~15 mm
KUT H6/1													30-35 mm Ø x 18 or 40 mm
CZ SP-3D	0.037	(0.03)	2.45							(0.04)			~39 mm Ø x 25 mm
13X NSB1D													40 mm Ø x 15 mm
IARM 339A	0.004	(0.001)	0.0006		0.0014		0.016			(0.002)	(0.005)	(0.003)	31 mm Ø x 2 or 18 mm
13X NSA3J													40 mm Ø x 15 mm
13X 18002D	0.0617												~40 mm Ø x ~15 mm
13X 12540L													40 mm Ø x 15 mm
CZ CM-18A	0.0344												~37 mm Ø x ~25 mm
SS 468/1													38 mm Ø x 19 mm
SRM C1152a								0.0047					32 mm Ø x 19 mm
VS LG32/5	0.156		0.0003				0.0104			(0.002)	<0.005		~38 mm Ø x ~25 mm
IARM 289A	0.01												31 mm Ø x 2 mm
IARM 241D	0.022	(0.001)	0.0016		(0.0012)		(0.005)	(0.0003)		(0.0022)	(0.007)	(0.005)	31 mm Ø x 2 or 18 mm
DSZU C018	0.086				0.0003								40 mm Ø x 25 mm
13X NSB3G	0.08							0.006					42 mm Ø x 15 mm
KUT H5													30-35 mm Ø x 18 or 40 mm
13X 17001B	0.01		0.008							0.030			~40 mm Ø x ~15 mm last
13X 18003C	0.0292												~40 mm Ø x ~15 mm
IRSID 1819			(0.0004)										47 mm x 47 mm x 30 mm
13X 17002E	(0.030)		0.0012								(0.012)		~40 mm Ø x ~15 mm
NCS HS28743	0.0056	0.0042						0.0004		0.0025			38 mm Ø x 15 mm
IMZ 166A	0.036	(0.0026)								(0.0035)			40 mm Ø x 40 mm
13X 14828A *	0.008	* Provisional Analysis			0.001					0.012			~40 mm Ø x ~15 mm
VS LG81	0.409												~45 mm Ø x ~28 mm
VS LG77													~45 mm Ø x ~28 mm
IMZ 164	0.040	(0.005)						(0.002)		(0.003)			40 mm Ø x 40 mm
13X 17003A													40 mm Ø x 15 mm
VS LG73													~45 mm Ø x ~28 mm
KUT S20													30-35 mm Ø x 18 or 40 mm
VS LG80	0.025												~45 mm Ø x ~28 mm
BS 253	0.016	0.005				0.044				0.006	25(pre-17025)		38 mm Ø x ~7 or 19+ mm
IARM 234C	0.035	(0.001)	0.0023		(0.0017)		(0.005)	(0.001)		0.0017	(0.003)	(0.006)	31 mm Ø x 2 or 18 mm
SS 462		0.007						0.0005					38 mm Ø x 19 mm
13X 12537T	(0.062)		0.0029							0.0401	0.0194		~40 mm Ø x ~15 mm
DSZU C015	(0.008)				0.0017								40 mm Ø x 25 mm
SS 464/1		(0.003)						0.0004					38 mm Ø x 19 mm
IMZ 165	0.038	(0.003)						(0.001)		0.003			40 mm Ø x 40 mm
SS 467/1		0.004						0.004			0.0017		38 mm Ø x 19 mm
VS LG35/5	0.087												~38 mm Ø x ~25 mm
13X 17001C	0.0312		0.0085								0.0124		~40 mm Ø x ~15 mm
KUT S26													30-35 mm Ø x 18 or 40 mm
NCS HS41750	0.009												38 mm Ø x 35 mm
Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units
ECRM 270-1D	(0.0023)	(0.0034)	Ce: 0.0487	La: 0.0154					(0.0007)	(0.0035)		(0.002)	38 mm Ø x 25 mm
VS LG78	0.15												~45 mm Ø x ~28 mm
BS 192	1.17	(0.005)	(0.0003)		0.0007		0.0014	25(pre-17025)		0.008	(0.001)		38 mm Ø x ~7 or 19+ mm
BS 83G	(0.004)		(0.001)				0.0064			0.003			38 mm Ø x ~7 or 19+ mm
VS LG72	0.089												~45 mm Ø x ~28 mm
13X 12534X	0.0485		(0.0003)								0.031		~40 mm Ø x ~15 mm
IARM 316A	0.006	0.007	(0.0003)		0.0017	0.064	0.0052	(0.0001)		0.006	(0.003)		31 mm Ø x 2 or 18 mm
VS LG63	0.45												~47 mm Ø x ~30 mm
KUT S25													30-35 mm Ø x 18 or 40 mm
CT 305													30-35 mm Ø x ~16 mm
SRM 1171													31 mm Ø x 19 mm
BS 9841	<(0.006)	(0.003)	0.0026	25(pre-17025)			(0.011)	(0.001)	(0.006)	0.006		(0.002)	44 mm Ø x ~7 or 19+ mm
SS 465/1	0.026		0.0006					<(0.001)					38 mm Ø x 19 mm
BS 192A	0.98	(0.0035)	(0.0003)		(0.0006)		(0.0006)			0.008	25(pre-17025)		38 mm Ø x ~7 or 19+ mm
IMZ 152													40 mm Ø x 40 mm
13X 12853L *	0.17		0.002	* Provisional Analysis							0.03		~40 mm Ø x ~15 mm
VS LG71	0.072												~45 mm Ø x ~28 mm
IARM 7C	0.017		0.0027				0.0021	(0.0001)		0.0020	(0.002)	(0.001)	31 mm Ø x 2 or 18 mm Mg:15ppm
CT 304								<0.001		0.017			30-35 mm Ø x ~16 mm Ag: 7ppm
BS 82E	0.006		0.0024		0.0014					0.006			38 mm Ø x ~7 or 19+ mm
13X 31008A													~38 mm Ø x ~15 mm
KUT H7/1													30-35 mm Ø x 18 or 40 mm
CT 316								0.001		0.006			30-35 mm Ø x ~19 mm Ag: 5ppm
VS LG36/5	0.080												~38 mm Ø x ~25 mm
CT X52353													30-35 mm Ø x ~16 mm last
13X NSB2D													40 mm Ø x 15 mm
BS 9842	0.014	(0.002)	0.0025		0.0010		(0.0044)			0.005	25(pre-17025)		38 mm Ø x ~7 or 19+ mm
BS 82D	(0.002)		0.0040		0.0007		0.007			0.004	last		38 mm Ø x ~7 or ~11 mm
13X 30908A	0.0035		0.0027		(0.0005)								~38 mm Ø x ~15 mm
SRM 1172											<0.001		32 mm Ø x 19 mm
VS LG82	0.076												~45 mm Ø x ~28 mm
IARM 3E	0.0045	(0.005)	(0.0005)		0.0015		0.0048	(0.0003)	(0.0013)	0.007	(0.005)	0.0018	31 mm Ø x 2 or 18 mm
BS 87F	0.004	0.005	(0.0006)		0.0007		0.005			0.004			41 mm Ø x ~7 or 19+ mm
13X 19001B													40 mm Ø x 15 mm
BS 86F	(0.007)	(0.003)	0.0026		(0.001)			(0.001)		0.004			44 mm Ø x ~7 or 19+ mm
DSZU C017	0.28				0.0031								40 mm Ø x 25 mm
BS 347B	0.002	(0.003)	0.0036		(0.0005)		0.005			0.006	<(0.004)		38 mm Ø x ~7 or 19+ mm
BS 347A	(0.002)	(0.003)	(0.0004)		(0.0002)		0.0047			0.007	<(0.004)		38 mm Ø x 19+ mm
IARM 2H	0.0034	0.007	0.0005		(0.0021)		0.007		(0.0018)	0.011	0.006	(0.003)	31 mm Ø x 2 or 18 mm
BS 188A	0.19		0.0065				0.0012	<0.001		0.002			38 mm Ø x ~7 mm last of stock
Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units

STAINLESS STEEL WITH C < 0.05 % CONTINUED ON THE NEXT PAGE
 # = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties analysis listed in mass %

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	ECRM 269-1D	0.0499	1.262	0.0313	0.0010	0.441	0.366	8.044	18.150	0.1116	0.397	0.0460	0.0242	0.0006	0.0991	0.0306
1	IARM BH *	0.049	1.81	0.0250	(0.002)	0.40	0.192	9.08	17.14	0.083	0.237	0.027	0.48	0.0027	0.049	(0.016)
1	IARM 61	0.049	1.76	0.0208	(0.023)	0.31	0.202	9.20	17.76	0.052	0.133	(0.013)	(0.018)	0.60	0.048	(0.023)
1	IARM 5i	0.049	1.443	0.0279	0.033	0.433	0.487	10.04	16.67	0.185	0.207	0.048	0.0133	0.0025	0.064	0.182
1	ECRM 289-1D	0.0489	1.016	0.0114	0.0027	0.531	.	24.68	14.63	0.065	1.102	.	.	2.01	0.260	.
1	IMZ 150A	0.048	1.35	0.0064	0.0095	0.59	0.090	12.75	18.89	0.125	0.12	.	0.0026	0.021	(0.027)	0.11
1	IARM 4F	0.047	1.17	0.0195	0.0015	0.494	0.146	20.1	24.5	0.067	0.142	0.056	0.007	0.0031	0.146	0.012
1	13X 32100A	0.0463	1.52	0.0298	0.0011	0.498	0.415	9.32	17.39	0.105	0.282	0.0115	0.0191	0.376	0.106	0.021
1	BS 188B	0.046	0.247	0.016	(0.0007)	0.266	0.120	24.81	14.32	0.274	1.30	0.0021	0.099	2.20	0.264	0.043
1	IARM 4G	0.0454	1.36	0.027	0.0008	0.430	0.320	19.2	24.9	0.085	0.580	0.058	0.008	0.029	0.092	0.017
1	IARM 6J	0.045	1.52	0.028	(0.002)	0.62	0.383	9.00	17.74	0.191	0.387	0.0109	0.010	0.34	0.081	0.026
1	BS 303	0.044	1.80	0.028	0.326	0.415	0.627	8.17	17.23	0.071	0.410	0.023	0.008	0.017	0.056	0.023
1	IARM 4E	0.044	1.07	0.0224	0.0006	0.514	0.234	20.18	24.25	0.066	0.32	0.038	0.024	(0.003)	0.052	0.046
3	CZ SL-3A	0.043	1.73	0.024	0.002	0.53	0.22	19.6	24.6	0.06	0.38	0.065	0.013	0.003	0.066	0.03
1	KUT S15	0.043	0.38	(0.02)	0.013	0.26	1.54	3.90	16.7	.	2.46	.	0.64	.	.	.
1	IARM 8i	0.0424	1.395	0.0352	0.0118	0.38	0.441	9.01	17.08	0.301	0.416	0.052	0.60	(0.008)	0.057	0.060
1	13X 14216P	0.0424	0.663	0.0048	0.0070	1.566	0.231	12.06	23.44	0.248	0.209	0.0152	0.248	.	0.0722	2.25
1	IARM 8G	0.042	1.468	0.0327	0.0126	0.36	0.390	9.02	17.20	0.162	0.359	0.046	0.53	0.0024	0.062	0.032
1	VS LG70	0.042	0.834	0.042	0.0020	0.382	0.062	9.17	17.10	0.209	0.096	0.0134	.	0.305	.	0.053
1	NILAB 500HA D	0.041	1.541	0.024	0.012	0.720	0.182	11.00	16.93	0.139	2.73	0.1154	0.023	.	0.074	.
1	13X 12538J	0.04	0.78	.	.	0.64	.	6.07	23.72	.	1.53
1	NCS HS41751	0.039	1.81	0.035	0.200	0.353	0.124	8.12	17.22	.	0.044	0.064	.	(0.001)	0.121	.
1	NCS HS28741	0.039	1.07	0.037	0.016	0.425	0.399	8.19	18.31	0.208	0.027	0.069	.	(0.002)	0.106	.
2	BS 321C	0.037	1.72	0.025	0.022	0.58	0.28	10.58	17.16	0.048	0.30	0.0082	0.008	0.38	0.079	(0.03)
1	IRSID 1821	0.037	1.72	(0.025)	(0.004)	0.542	0.058	10.42	17.04	0.266	2.04	0.0125	.	0.297	.	.
1	13X 14207L *	0.037	0.58	0.006	0.005	1.4	0.18	12.3	19.6	0.01	0.57	0.010	0.26	.	.	3.0
1	ECRM 292-1D	0.0367	1.744	0.0175	0.0055	0.402	0.0391	10.09	18.00	0.0255	0.0464	0.0640	0.571	.	.	.
1	13X 66286A	0.036	1.172	0.0173	(0.0006)	0.216	0.195	25.21	15.00	0.083	1.190	0.0040	.	1.92	0.264	0.098
2	BS 184A	0.035	0.06	0.007	0.001	0.080	0.041	8.34	12.66	0.036	2.20	0.0045	(0.006)	0.051	0.014	0.032
1	IARM 21C	0.035	0.051	0.007	0.0038	0.042	0.047	8.18	12.39	0.021	2.11	0.0045	0.007	0.012	0.013	(0.01)
1	SS 462/1	0.0345	0.722	0.0053	0.0041	0.463	0.0112	12.85	11.898	.	0.0304
1	SFM C1151a	0.034	2.37	0.017	0.038	0.29	0.385	7.25	22.59	0.033	0.79	.	.	.	0.040	.
1	B13X 31400A *	0.033	1.60	0.025	0.0005	2.28	0.21	18.8	24.3	0.133	0.24	0.029	0.02	.	0.095	0.013
1	BS 9812	0.031	0.485	0.018	0.004	0.43	1.65	6.61	14.82	0.110	0.76	0.0195	0.645	(0.005)	0.088	0.025
1	IMZ I53A	0.030	1.49	0.021	0.0073	0.13	0.102	13.56	16.45	0.015	2.61	0.107	0.034	0.036	0.020	.
2	HRT FE2014-H	0.027	1.91	0.023	(0.002)	0.39	0.25	9.92	17.16	.	0.41	(0.018)	.	0.31	0.09	0.018
2	BS 317L	0.027	1.17	0.029	0.0034	0.67	0.23	13.53	18.16	0.14	3.07	0.056	.	.	.	4.14
1	VS LG75	0.027	0.228	0.0046	0.0026	0.29	0.217	7.92	18.20	0.190	0.052	0.044	.	1.76	.	0.013
1	BS 9811	0.027	0.380	0.016	0.0010	0.36	1.63	6.55	14.87	0.055	0.744	0.0196	0.62	(0.003)	0.086	0.013
1	SFM I155a	0.0260	1.593	0.0271	(0.0020)	0.521	0.2431	12.471	17.803	0.225	2.188	(0.0428)	0.0082	0.0039	0.0725	0.0809

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
2	HRT FE2013-H	0.026	0.61	0.022	0.005	0.38	0.13	6.20	25.71	.	3.63	0.28	.	.	0.05	.
1	13X 32900A	0.0251	1.478	0.0276	0.0269	0.556	0.354	5.57	24.91	0.0724	1.310	0.097	.	0.0139	0.0938	0.017
1	13X NSA8A	0.0240	0.656	0.0216	0.0008	(0.40)	0.903	6.29	25.93	0.0374	3.60	0.239	(0.004)	.	0.060	0.586
1	IARM 162D	0.0240	1.82	0.0296	0.0271	0.570	0.52	8.15	18.31	0.074	0.573	0.097	0.0090	0.013	0.063	0.028
1	IARM 153C	0.0225	1.60	0.0289	0.0288	0.349	0.442	11.10	18.22	0.251	3.00	0.086	0.015	0.004	0.058	0.043
1	ECRM 297-1D	0.0223	0.897	0.0137	0.0101	0.344	0.204	12.33	18.37	0.0413	0.290	0.0152	(0.0089)	0.0072	0.0535	(0.0057)
1	NCS HS28746	0.021	1.87	0.031	0.0009	0.510	0.340	8.24	17.19	0.191	0.069	0.011	.	0.184	0.096	.
1	BS 9942	0.021	1.84	0.025	0.006	0.49	0.305	13.55	18.21	0.086	3.30	0.071	0.005	(0.002)	0.072	0.032
1	BS 9941	0.021	1.78	0.027	0.024	0.33	0.424	13.68	18.48	0.178	3.24	0.036	0.015	(0.002)	0.062	0.068
1	IRSID 1820	0.021	1.61	(0.021)	0.0079	0.428	0.045	9.07	19.51	0.151	0.115	0.064
1	NCS HS28742	0.021	0.940	0.034	0.0028	0.414	0.043	8.11	18.2	0.216	0.025	0.059	.	0.006	0.089	.
1	IARM 301B	0.0206	0.807	0.0251	0.0010	0.419	0.192	7.01	25.06	0.055	3.75	0.297	0.020	(0.003)	0.070	0.050
1	13X 3043A	0.020	1.495	0.029	0.025	0.298	0.217	7.92	18.20	0.101	0.193	0.084	(0.019)	.	0.113	0.018
1	13X NSA9A	0.020	1.593	0.0246	(0.0008)	0.476	0.242	5.46	22.59	0.071	3.10	0.156	0.012	.	0.070	(0.024)
1	SS 463/1	0.019	1.400	0.025	0.019	0.270	0.276	10.20	18.46	0.116	0.265	0.063
1	BS 2205	0.0199	1.029	0.0227	0.0005	0.564	0.196	5.27	22.92	0.041	3.26	0.169	0.0052	0.0019	0.0560	0.0309
1	13X NSAI2A	0.0192	1.272	0.0267	0.0007	0.492	1.485	24.84	19.63	0.090	4.20	0.0662	0.0088	.	0.0660	0.047
1	BS 304A	0.019	1.706	0.0402	0.0188	0.56	0.548	8.20	18.17	0.126	0.28	0.072	0.014	(0.0005)	0.067	0.042
1	IARM 212D	0.019	1.21	0.024	0.0007	0.34	0.125	5.53	22.60	0.049	3.27	0.182	(0.009)	(0.002)	0.063	0.014
1	113X NSAI3A *	0.019	0.75	0.025	0.0005	0.24	0.155	6.75	25.35	0.033	3.70	0.275	0.025	.	0.072	0.030
1	BS 316D	0.0185	1.400	0.0294	0.0189	0.278	0.409	10.38	16.76	0.294	2.05	0.042	0.0277	(0.002)	0.074	0.072
1	BS 316E	0.0183	1.413	0.0295	0.0214	0.268	0.408	10.43	16.70	0.287	2.06	0.042	0.0282	(0.002)	0.074	0.067
1	IARM 162C	0.0181	1.45	0.032	0.024	0.25	0.44	8.68	18.07	0.158	0.34	0.074	0.011	0.0012	0.076	0.043
1	13X FV520BA	0.0181	0.655	0.0221	0.0016	0.342	1.462	5.29	13.73	0.030	1.334	0.0197	0.301	.	0.080	0.020
2	HRT FE2000-H	0.018	2.02	0.022	(0.003)	0.36	0.15	5.98	22.15	0.048	3.27	0.				

STAINLESS STEEL WITH C < 0.05 %
analysis listed in mass %

CONTINUED FROM THE PREVIOUS PAGE

Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
ECRM 269-1D		0.0061						0.0099		35 mm Ø x 25 mm
IARM 8H *	(0.005)		(0.0002)		* Provisional Analysis			(0.008)	(0.01)	31 mm Ø x 2 or 18 mm
IARM 6I	0.084	(0.005)	0.0034	(0.0004)	0.0012			(0.0060)		31 mm Ø x 2 or 18 mm
IARM 5I	0.004	0.006	0.0006	(0.0016)	0.0057	(0.0001)	(0.0019)	0.0077	(0.005)	31 mm Ø x 2 or 18 mm
ECRM 289-1D	0.199		0.0044					0.111		38 mm Ø x 30 mm
IMZ 150A	0.022									40 mm Ø x 40 mm
IARM 4F	0.015	(0.003)	(0.0012)	(0.002)	(0.004)		(0.001)	(0.005)	(0.007)	31 mm Ø x 2 or 18 mm
I3X 32100A	0.0247		0.0025					0.0115		~38 mm Ø x ~15 mm
BS 188B	0.168	0.0045	0.0047	(0.00003)	0.0006	(0.0001)	(0.0006)	0.0051		38 mm Ø x ~7 or 19+ mm Fe: 55.8 17025
IARM 4G	0.008	(0.005)	0.0032	(0.001)	(0.003)	(0.0005)	(0.001)	0.008	(0.008)	31 mm Ø x 2 or 18 mm
IARM 6J	0.0195		0.0024		(0.001)			(0.009)	(0.01)	31 mm Ø x 2 or 18 mm
BS 303	0.0019		0.0013	(0.0015)	0.0058		(0.002)	0.0091		44 mm Ø x ~7 or 19+ mm 17025 Fe:[70.7]
IARM 4E	0.004	(0.005)	0.0011		0.0021			0.0060	0.005	31 mm Ø x 2 or 18 mm
CZ SL-3A	0.007		0.002					0.006		~39 mm Ø x 25 mm
KUT S15										30-35 mm Ø x 18 or 40 mm
IARM 8I	(0.0030)		(0.0005)		(0.004)			(0.012)		31 mm Ø x 2 or 18 mm
I3X 14216P										~40 mm Ø x ~15 mm
IARM 8G	0.0030	(0.007)	(0.0005)	(0.0005)	(0.003)			0.0107	(0.004)	31 mm Ø x 2 or 18 mm
VS LG70	0.029									~45 mm Ø x ~28 mm
NILAB 500HA D										38 mm Ø x 20 mm
I3X 12538J										40 mm Ø x 15 mm
NCS HS41751	(0.004)					(0.001)				38 mm Ø x 35 mm
NCS HS28741		0.0035				0.0001		0.0051		38 mm Ø x 35 mm
BS 321C	0.044	(0.004)	(0.0005)	(0.0001)	(0.0011)			0.006		38 mm Ø x ~7, ~11, or 12 mm last
IRSID 1821										47 mm x 47 mm x 30 mm
I3X 14207L *		* Provisional Analysis							0.08	~40 mm Ø x ~15 mm
ECRM 292-1D	(0.002)	(0.008)		(0.0006)					(0.001)	38 mm Ø x 25 or 30 mm
I3X 66286A	0.193		0.0044							~40 mm Ø x ~15 mm
BS 184A	1.00		(0.0004)	(0.0003)	(0.0003)			(0.002)	(0.002)	38 mm Ø x ~7 or 19+ mm
IARM 21C	1.07		0.0004		0.0004			0.005	(0.002)	31 mm Ø x 2 or 18 mm
SS 462/1										38 mm Ø x 19 mm
SRM C1151a						0.0039				32 mm Ø x 19 mm
I3X 31400A *	0.021			0.0025	* Provisional Analysis					~40 mm Ø x ~15 mm
BS 9812	(0.002)	(0.005)	(0.0003)	0.0012	(0.007)			0.004		50 mm Ø x ~7 or 19+ mm 25(pre-17025)
IMZ 153A	0.036									38 mm Ø x 20 mm
HRT FE2014-H										35mm Ø x 20 mm
BS 317L	(0.005)	(0.003)	0.0013	(0.001)	0.007			0.005		37 mm Ø x ~7 or 19+ mm
VS LG75	0.113									~45 mm Ø x ~28 mm
BS 9811	(0.003)	(0.003)	(0.0003)	0.0014	(0.0060)			0.004		38 mm Ø x ~7 or 19+ mm 25(pre-17025)
SRM I155a	<0.01	(0.007)	(0.002)		(0.003)	<0.005		(0.0069)		32 mm Ø x 19 mm

Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
HRT FE2013-H										40 mm Ø x 20 mm last of stock
I3X 32900A	0.007		0.0028	0.0033						~40 mm Ø x ~15 mm
I3X NSA8A										~44 mm Ø x ~15 mm
IARM 162D	(0.0026)	0.0072	0.0027	(0.003)	0.005		(0.0019)	0.0102	(0.005)	31 mm Ø x 2 or 18 mm
IARM 153C	(0.003)	0.0061	0.0009	(0.0026)	0.006	(0.001)	(0.002)	0.010	(0.006)	31 mm Ø x 2 or 18 mm
ECRM 297-1D	0.0195	0.0040	1.146	(0.0002)						40 mm Ø x 30 mm
NCS HS28746	0.086	0.0032				0.0002		0.0065		38 mm Ø x 35 mm
BS 9942	0.004	(0.004)	0.0014	0.0014	(0.0023)			0.006		44 mm Ø x ~7 or 19+ mm 25(pre-17025)
BS 9941	0.004	(0.010)	0.0025	(0.0003)	(0.0058)			0.007		38 mm Ø x ~7 or 19+ mm 25(pre-17025)
IRSID I820			(0.0013)							47 mm x 47 mm x 30 mm
NCS HS28742		0.0025				0.0001		(0.0001)		38 mm Ø x 35 mm
IARM 301B	0.005	(0.004)	0.0024	(0.0009)	0.0069	(0.0003)	(0.0006)	0.0051	(0.003)	31 mm Ø x 2 or 18 mm
I3X 30403A										~40 mm Ø x ~15 mm
I3X NSA9A										40 mm Ø x ~15 mm
SS 463/1			0.0022							38 mm Ø x 19 mm
BS 2205	0.0080	0.0059	0.0016	0.0014	0.0034	(0.0001)	0.0010	0.0050	17025	38 mm Ø x ~7 or 19+ mm Fe:[67.0] Mg:(0.0004) Zr:(0.006)
I3X NSA12A	0.0169		0.0020							~40 mm Ø x ~15 mm
BS 304A	0.0028	(0.007)	(0.0005)		0.0061	(0.0001)	(0.002)	0.0096	last	38 mm Ø x ~7, ~11, ~15 or 19 mm 17025 Fe:[70.1]
IARM 212D	(0.005)	(0.01)	0.001	(0.001)	0.0034	(0.001)		(0.003)	(0.003)	31 mm Ø x 2 mm
I3X NSA13A *	0.007		0.0028							~40 mm Ø x ~15 mm
BS 316D	(0.002)	0.0048	0.0038	(0.0008)	0.0039	(0.0003)	(0.002)	0.0080	last	38 mm Ø x ~7, ~12, ~17 or 19 mm 17025 Fe: 68.1
BS 316E	0.0027	0.0045	0.0036	(0.0006)	0.0039	(0.0002)	(0.002)	0.0082		38 mm Ø x ~7 or 19+ mm 17025 Fe:[68.1]
IARM I62C	0.004	(0.006)	(0.001)	(0.001)	0.005	(0.001)		0.011	last	31 mm Ø x 18 mm
I3X FV520BA										~40 mm Ø x ~15 mm
HRT FE2000-H			0.0013							40 mm Ø x 20 mm
BS 304	0.0022	(0.005)	(0.0005)	(0.001)	0.0083	(0.0003)	(0.002)	0.0116		38 mm Ø x ~7 or 19+ mm 17025 Fe:[70.5]
VS LG33/5	0.024									~38 mm Ø x ~25 mm
NCS HS28745		0.0055				0.0001		0.0073		38 mm Ø x 35 mm
BS 304B	0.0036	0.0051	(0.0004)	0.0009	0.0038	(0.0008)		0.0057		38 mm Ø x ~7 or 19+ mm 17025 Fe: 69.6
IARM 239C *	0.007	(0.004)	0.0014					(0.003)	(0.004)	31 mm Ø x 2 or 18 mm
BS 179C	0.0078	0.0034	0.0015	(0.0003)	0.0038	(0.0002)	0.0005	0.0018	(0.0006)	38 mm Ø x ~7 or 19+ mm 17025 Fe:[61.6]
BS 179E	0.0070	0.0036	0.0015	(0.0004)	0.0037	(0.0002)	0.0005	0.0019	(0.0006)	38 mm Ø x 19+ mm 17025 Fe:[61.5]
ECRM 287-1D	0.023		0.924							38 mm Ø x 25 or 30 mm
I3X 34700A	(0.021)		0.0008							~38 mm Ø x ~15 mm
I3X NSA11A										~38 mm Ø x ~15 mm
CZ SL-2A	0.005	0.008	0.002					0.01		~39 mm Ø x 25 mm
IARM 319A	(0.010)	(0.004)	0.0020		0.0025			0.0055	(0.002)	31 mm Ø x 2 mm
ECRM 298-1D	0.0285		0.0021			0.00008				38 mm Ø x 25 mm Fe: 63.38
SS 466/2	0.0018	0.0020	0.0039							38 mm Ø x 19 mm
BS SS3951	0.002		(0.0006)	0.0005	0.0075			0.007		41 mm Ø x ~7 or 19+ mm
IARM 163E *	0.0039	(0.008)	0.0019	(0.002)	0.007		(0.002)	0.012		31 mm Ø x 2 mm * Provisional Analysis, last
HRT FE2016-H										30 mm Ø x 20 mm
SS 461/1	0.069									38 mm Ø x 19 mm
BS SS1961	0.067	0.004	0.0022		(0.002)			0.004		38 mm Ø x 12 mm last
JK 27B			0.00072	0.0022				0.0068		~37 mm Ø x 25 mm
BS SS1962	0.062	0.002	0.0018		(0.001)			0.004		38 mm Ø x ~7 or 19+ mm
IARM 354A	(0.05)	(0.002)	0.0023	(0.0003)	(0.0012)	(0.004)	(0.0002)	(0.002)		31 mm Ø x 2 or 18 mm
CT ISO123A	0.027		0.0021							30-35 mm Ø x ~16 mm Fe: 74.72
I3X 46500A *	0.067		0.0016							~32 mm Ø x ~20 mm
ECRM 284-3D		0.00131	0.00020					0.00074		39 mm Ø x 28 mm

Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
--------	----	----	---	----	---	----	----	----	----	-------

STAINLESS STEEL XRF SETS

AVAILABLE IN SETS OR INDIVIDUALLY

-7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	V	W
SET BS SS-17															
15-5PH	BS 185A	0.033	0.49	0.022	0.002	0.38	3.41	4.43	14.46	0.026	0.30	0.027	0.32	0.048	(0.014)
17-4PH	BS 17-4PHA	0.018	0.85	0.023	0.022	0.40	3.30	4.69	15.40	0.072	0.34	0.022	0.204	0.043	
17-7PH	BS 192	0.075	0.84	0.025	0.001	0.38	0.41	7.10	16.42	0.104	0.42	0.029	0.17	0.13	0.04
253 MA	BS 253	0.094	0.58	0.018	<0.001	1.81	0.14	10.89	20.68	0.15	0.21	0.146	0.017	0.050	0.03
255	BS 179C	0.0164	0.878	0.0236	0.0003	0.373	1.53	6.10	25.9	0.0386	3.34	0.236	0.009	0.080	0.056
2205 (318)															
	BS 2205	0.0199	1.029	0.0227	0.0005	0.564	0.196	5.27	22.92	0.041	3.26	0.169	0.0052	0.0560	0.0309
303	BS 303	0.044	1.80	0.028	0.326	0.415	0.627	8.17	17.23	0.071	0.410	0.023	0.008	0.056	0.023
304 L	BS 81F	0.026	1.35	0.023	0.012	0.36	0.19	10.06	18.15	0.21	0.41	0.069		0.078	0.037
309	BS 82D	0.058	1.85	0.020	0.009	0.63	0.16	14.12	22.40	0.042	0.144	0.070	0.053	0.087	0.028
310	BS 83G	0.073	1.66	0.024	0.004	0.56	0.114	19.15	24.50	0.153	0.085	0.026	0.061	0.077	0.007
316 L	BS 316D	0.0185	1.400	0.0294	0.0189	0.278	0.409	10.38	16.76	0.294	2.05	0.042	0.0277	0.074	0.072
317 L	BS 317L	0.027	1.17	0.029	0.0014	0.67	0.23	13.53	18.16	0.14	3.07	0.056	0.031	0.09	0.018
321	BS 85D	0.048	1.69	0.024	0.024	0.54	0.45	9.98	17.09	0.97	0.59	(0.02)	0.062	0.132	(0.07)
330	BS 86F	0.054	1.30	0.021	0.0011	1.22	0.23	34.99	18.74	0.098	0.24	0.035	0.19	0.061	(0.03)
347	BS 347B	0.051	1.57	0.028	0.026	0.51	0.15	9.16	17.24	0.05	0.38	0.056	0.71	0.04	(0.005)
PH13-8 Mo															
	BS 355	0.136	0.862	0.0171	0.0003	0.374	0.173	4.18	15.43	0.053	2.73	0.081	0.0103	0.106	0.0069
	BS 184A	0.035	0.06	0.007	0.001	0.080	0.041	8.34	12.66	0.036	2.20	0.0045	(0.006)	0.014	0.032
SET BS 400-SS-16															
182PM	BS 150	0.048	1.71	0.020	0.33	0.43	0.042	0.19	18.61	0.024	1.97	0.029	0.003	0.054	0.01
410	BS 410C	0.131	0.381	0.0206	0.0051	0.366	0.084	0.352	12.78	0.0185	0.055	0.039	0.0056	0.0006	0.0131
416	BS 90F	0.085	0.53	0.023	0.328	0.58	0.12	0.30	13.01	0.021	0.14	0.037	0.011	0.076	0.032
416 Se	BS 151	0.090	0.41	0.021	0.018	0.65	0.11	0.24	13.19	0.018	0.088	0.022	0.005	0.046	0.010
420	BS 98	0.309	0.48	0.019	0.0014	0.72	0.098	0.21	13.35	0.020	0.034	0.0181	0.003	0.075	0.009
420F	BS 152	0.32	0.36	0.022	0.275	0.44	0.050	0.14	13.41	0.015	0.061	0.020	0.006	0.051	<0.01
422	BS 97	0.216	0.71	0.021	0.0004	0.39	0.066	0.76	11.82	0.041	1.05	0.030	0.007	0.21	0.95
430	BS 91E	0.066	0.42	0.017	0.002	0.52	0.05	0.17	16.58	0.02	0.035	0.032	(0.004)	0.09	0.01
430F	BS 153	0.026	0.41	0.018	0.280	0.53	0.052	0.140	17.38	0.017	0.30	0.021	0.002	0.045	(0.002)
431	BS 92B	0.150	0.42	0.021	0.003	0.42	0.13	2.12	15.92	0.04	0.17	0.073	(0.006)	0.07	0.02
440C	BS 93E	1.02	0.52	0.022	0.0010	0.90	0.12	0.35	17.33	0.048	0.50	0.0359	0.005	0.24	0.11
440F	BS 155	1.00	0.35	0.014	0.145	0.40	0.035	0.13	16.64	0.019	0.46	0.032	0.002	0.10	
440F Se	BS 156	1.06	1.15	0.022	0.007	0.47	0.09	0.35	16.87	0.047	0.50	0.041	0.005	0.13	0.11
446	BS 94C	0.057	0.45	0.024	0.002	0.62	0.056	0.43	25.90	0.042	0.20	0.065	0.032	0.12	(0.03)
450	BS 95A	0.035	0.58	0.026	0.004	0.46	1.50	6.42	14.72	0.081	0.73	0.0255	0.55	0.052	0.02
455	BS 96A	0.009	0.04	0.007	0.004	0.06	2.07	8.38	11.62	0.03	0.021	.	0.26	0.07	.

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	V	W
Number															
		Al	B	Ca	Se	Sn	Ti								
SET BS SS-17															
	BS 185A	0.002	0.0017	(0.0002)	.	0.007	(0.001)	Ta: (0.002)							
	BS 17-4PHA		0.0016	.	.										
	BS 192	1.15	(0.0004)	0.0007	.	0.009	0.078	Ce: 0.044 As: 0.005							
	BS 253	0.016	.	.	.	0.006	0.005	As: 0.0034 O: 0.0038 Sb: 0.0005 17025							
	BS 179C	0.0078	0.0015	(0.0003)	.	0.0018	(0.0005)	As: 0.0059 Fe: [67.0] O: 0.0034 Sb: 0.0010 17025							
	BS 2205	0.0080	0.0016	0.0014	.	0.0050	0.0019	As: 0.0059 Fe: [67.0] O: 0.0034 Sb: 0.0010 17025							
	BS 303	0.0019	0.0013	(0.0015)	.	0.0091	0.017	O: (0.0064) 17025							
	BS 81F	(0.003)	0.0026	(0.0004)	.	0.007	0.003								
	BS 82D	(0.002)	0.0040	0.0007	.	0.004	0.005								
	BS 83G	(0.004)	(0.001)	0:0.0064	.	0.003	(0.003)								
	BS 316D	(0.002)	0.0038	(0.0008)	0:0.0039	0.0080	(0.002)	As: 0.0048 Fe: 68.1 17025							
	BS 317L	(0.005)	0.0013	(0.001)	.	0.005									
	BS 85D	0.13	(0.001)	0.0004	.	0.0062	0.48	17025							
	BS 86F	(0.007)	0.0026	(0.001)	.	0.004	(0.006)								
	BS 347B	0.002	0.0036	(0.0005)	.	0.006	(0.002)								
	BS 355	0.0192	0.0039	(0.0002)	.	0.0038	0.0007	O: 0.0020							
	BS 184A	1.00	(0.0004)	(0.0003)	.	(0.002)	0.051								
SET BS 400-SS-16															
	BS 150	0.002	.	.	.	(0.003)	(0.002)								
	BS 410C	0.0079	(0.0001)	0.0022	.	0.0023	0.0006	17025							
	BS 90F	(0.006)	.	.	.	0.005	(0.002)								
	BS 151	(0.002)	.	.	0.328	0.005	(<0.003)								
	BS 98	0.003	.	(0.0005)	.	0.006	0.002								
	BS 152	(0.002)	.	.	.	0.003	(0.002)								
	BS 97	0.018	.	.	.	(0.003)	(0.002)								
	BS 91E	(0.004)	.	0.0008	.	0.004	(0.002)								
	BS 153	(0.004)	.	.	.	0.002	(0.004)								
	BS 92B	(0.002)	.	(0.0009)	.	0.006	(0.002)								
	BS 93E	0.009	.	.	.	0.003	0.007								
	BS 155	(0.001)	.	.	.	(0.003)	(0.002)								
	BS 156	(<0.002)	.	.	0.142	(0.004)	0.001								
	BS 94C	0.004	.	0.0008	.	0.006									
	BS 95A	0.002	0.0010	0.0008	.	0.008	(0.003)								
	BS 96A	0.08	(0.0017)	.	.	.	1.18								

Number	Al	B	Ca	Se	Sn	Ti
--------	----	---	----	----	----	----

RM HIGH ALLOY STEEL XRF SET

Part Number: BS HAS-12

AVAILABLE INDIVIDUALLY

~7 mm discs

Number Grade	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	B	Co	N	Nb	Sn	Ti	V	W	O
BS 189A AL6XN CRM	0.0147	0.639	0.019	(0.001)	0.30	0.184	23.8	20.4	6.04	0.0129	(0.0002)	0.100	0.198	(0.13)	0.0035	0.0065	0.054	0.037	0.0024
BS 179A Alloy 255	0.017	1.04	0.021	0.001	0.44	1.94	5.84	25.45	3.24	(0.009)	(0.001)	0.58	0.184	0.030	0.005	0.006	0.070	(0.2)	.
BS 183 Greek Ascology	0.16	0.43	0.020	0.013	0.33	0.068	2.00	12.81	0.35	.	.	0.029	.	(0.003)	(0.0016)	0.003	0.12	2.77	.
BS 186A Invar 36	0.040	0.72	0.008	0.0053	0.19	0.016	35.86	0.16	0.0032	(0.001)	.	0.028	0.0026	(<0.002)	(0.002)	(<0.003)	0.0012	(0.01)	.
BS 187A Carp. 20Cb3	0.022	0.52	0.017	0.0025	0.26	3.10	33.06	19.75	2.06	(0.009)	0.0022	0.32	0.0157	0.57	0.003	(0.002)	0.10	(0.02)	.
BS 188A A-286	0.050	0.139	0.015	0.0049	0.15	0.099	24.61	14.04	1.10	0.19	0.0065	0.18	0.0029	0.050	0.002	2.21	0.24	0.055	.
BS 190 Nitronic® 40	0.022	9.72	0.015	0.001	0.46	0.072	6.74	19.57	0.15	(0.004)	0.0005	0.044	0.255	(0.004)	0.003	0.002	0.11	0.015	0.0045
BS 180A Nitronic® 50	0.018	5.05	0.012	0.001	0.32	0.067	13.19	21.09	2.04	0.012	(0.0024)	0.039	0.334	0.20	(0.002)	(0.002)	0.20	0.02	0.003
BS 181A Nitronic® 60	0.071	8.16	0.019	0.001	4.03	0.18	8.15	16.52	0.21	0.022	0.0009	0.072	0.148	0.017	0.005	0.007	0.094	0.04	0.0010
BS 193 18Cr-12Mn	0.104	12.11	0.018	0.002	0.66	0.088	1.82	18.48	0.21	(0.003)	0.0007	0.028	0.37	0.014	0.004	0.003	0.107	(0.007)	.
BS 182 17Cr-15Mn	0.037	15.09	0.022	(0.003)	0.46	0.56	1.11	16.67	0.99	.	.	0.032	(0.40)	(0.005)	(0.003)	(0.003)	0.059	(0.01)	.
BS 191 16Cr-6Mn-4Si	0.098	5.71	0.024	0.023	3.66	0.33	5.34	16.33	0.36	(0.002)	(0.0006)	0.11	0.117	0.024	(0.006)	0.012	0.083	0.033	.

Number Grade	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	B	Co	N	Nb	Sn	Ti	V	W	O
--------------	---	----	---	---	----	----	----	----	----	----	---	----	---	----	----	----	---	---	---

CRM CAST IRON SETS AVAILABLE IN SETS ONLY, as grouped

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Sn	Ti	V	Ce	La	Mg	N
30 mm Ø x 28 mm																	
NCS HS11712a-6	4.02	1.41	0.021	0.026	0.163	1.83	1.89	0.112	0.019	0.726	0.057	0.238	0.509	<0.0001	<0.0001	0.104	0.013
NCS HS11712a-7	3.94	1.38	0.085	0.0048	0.918	1.10	1.37	1.05	0.214	0.168	0.134	0.114	0.390	<0.0001	<0.0001	0.056	0.0063
NCS HS11712a-5	3.52	0.311	0.420	0.019	1.17	0.389	1.03	0.766	.	0.629	0.013	0.161	0.324	<0.0001	<0.0001	0.021	0.0047
NCS HS11712a-4	3.16	0.462	0.396	0.017	1.96	0.921	0.778	1.40	0.0073	0.428	0.024	0.065	0.166	<0.0001	<0.0001	0.025	0.0073
NCS HS11712a-2	2.22	0.301	0.043	0.058	2.44	0.458	0.341	2.13	0.060	0.087	0.044	0.065	0.055	0.0010	0.010	0.0085	0.024
NCS HS11712a-3	2.55	0.878	0.071	0.045	1.50	0.641	0.519	0.417	0.034	0.354	0.021	0.027	0.085	0.027	0.0061	0.024	0.024
NCS HS11712a-1	1.75	0.080	0.580	0.119	3.40	0.025	0.030	2.48	0.248	0.031	0.0031	0.038	0.021	<0.0001	<0.0001	0.0006	0.015
30 mm Ø x 30 mm																	
NCS HS19701-7	4.13	2.06	0.306	0.111	1.85	.	0.026	0.157	.	.	0.043	0.399	0.821
NCS HS19701-6	3.93	1.46	0.168	0.124	0.99	.	0.094	0.387	.	(0.112)	0.0018	0.105	0.506
NCS HS19701-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	(0.68)	0.0022	0.066	0.335
NCS HS19701-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	(0.031)	0.0017	0.030	0.158
NCS HS19701-3	3.29	1.22	0.045	0.056	0.689	.	0.046	0.030	.	.	0.009	0.043	0.071
NCS HS19701-2	2.99	0.329	0.033	0.038	0.937	.	0.194	0.080	.	.	0.024	0.216	0.044
NCS HS19701-1	2.46	0.072	0.011	0.019	0.099	.	0.183	0.511	.	.	0.005	0.0059	0.0090

CRM CAST IRON SET AVAILABLE IN SET ONLY 37 mm x 37 mm x ~20mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Ce	La	Mg	Mo	Sb	Sn	Ti	V
CKD 241	1.71	0.136	0.006	0.14	3.20	0.021	0.014	0.684	.	.	.	0.60	0.13	0.004	0.001	0.092
CKD 242	2.21	0.045	0.040	0.033	2.88	0.045	0.024	0.026	.	.	.	1.20	0.007	0.008	0.314	0.43
CKD 243	2.23	0.385	0.162	0.085	2.44	0.175	0.080	0.378	.	.	.	0.263	0.082	0.111	0.013	0.258
CKD 244	2.60	0.665	0.024	0.019	2.11	0.295	0.36	0.274	0.014	0.005	0.033	0.053	(0.003)	0.177	0.033	0.004
CKD 245	2.78	1.36	0.40	0.049	1.60	0.063	0.165	0.168	.	.	0.004	0.106	0.048	0.074	0.074	0.058
CKD 246	2.82	0.302	0.60	0.022	0.62	1.38	0.043	1.20	(0.01)	0.003	0.010	0.005	0.003	0.005	(0.001)	0.002
CKD 247	3.12	1.01	0.095	0.005	1.16	0.815	0.42	0.054	0.048	0.022	0.037	0.015	0.002	0.038	0.058	0.008
CKD 248	3.41	0.245	0.050	0.006	1.81	0.117	0.70	0.022	0.023	0.014	0.064	0.003	0.012	0.015	0.170	0.171
CKD 249	3.75	0.127	0.25	0.008	0.34	0.485	1.42	0.093	0.077	0.025	0.056	0.013	0.004	0.004	0.096	0.024
Number	Al	As	B	Bi	Ca	Co	Fe	Nb	Nd	Pb	Pr	Se	Te	W	Zn	Zr
CKD 241	0.003	0.003	(0.001)	.	.	0.002	(93.23)	0.002	.	0.003	.	.	.	0.001	.	0.001
CKD 242	0.075	0.007	0.007	0.013	.	0.002	(92.55)	0.007	.	0.020	.	.	0.024	0.011	(0.001)	.
CKD 243	0.012	0.08	0.009	.	.	0.022	(93.03)	0.024	.	(0.04)	.	0.050	.	0.026	(0.016)	.
CKD 244	0.070	0.041	0.084	.	(0.003)	0.047	(92.95)	0.004	(0.004)	0.002	(0.002)	.	.	0.055	0.018	0.034
CKD 245	0.020	0.006	0.008	0.007	.	0.004	(92.89)	.	.	0.015	.	0.034	0.029	0.021	.	0.002
CKD 246	0.006	0.005	.	.	(0.002)	0.008	(92.92)	0.001	(0.003)	(0.0003)	(0.001)	.	.	0.007	.	.
CKD 247	0.013	0.009	(0.01)	.	(0.005)	0.092	(92.82)	0.057	(0.012)	0.002	(0.006)	.	(0.017)	(0.005)	0.013	0.007
CKD 248	0.045	0.019	0.036	0.004	(0.003)	0.016	(92.96)	0.005	(0.005)	0.012	(0.002)	0.003	0.004	(0.003)	0.015	0.015
CKD 249	0.059	0.018	0.018	0.006	(0.002)	0.011	(92.94)	0.035	(0.02)	0.023	(0.009)	0.004	(0.004)	(0.01)	0.004	0.040

These CKD sets may contain 1 or more replacement pieces from later batches.

RM GRAY IRON as cast (not chill cast) CONTAINS FREE GRAPHITE **OES regularly requires extension of preburn time to analyze correctly**

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	Sb	Sn	Ti	V	mm Ø x mm H
BS 20G	3.33	0.58	0.028	0.029	3.02	0.54	0.38	0.086	0.008	0.004	0.022	0.19	(<0.001)	0.12	0.012	0.018	47 x 19+
BS 20W	3.27	0.62	0.045	0.036	2.64	0.29	0.082	0.092	0.004	0.004	0.005	0.054	(<0.001)	0.086	0.015	0.007	47 x 13
BS 20R	3.25	0.62	0.047	0.034	2.72	0.35	0.096	0.094	0.005	0.004	0.006	0.053	(<0.001)	0.104	0.015	0.007	47 x 19+
BS 20E	3.24	0.80	0.042	0.044	2.29	0.23	0.156	0.088	0.006	(0.003)	0.006	0.042	(<0.002)	0.093	0.017	0.007	47 x 19+
BS 20P	3.22	0.63	0.032	0.044	2.62	0.067	0.143	0.079	0.008	(0.004)	0.018	0.033	(<0.001)	0.099	0.018	0.017	44 x 19+

DUCTILE / NODULAR IRON

= Class, where 1 = CRM and 2 = RM * Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Ce	Co	Mg	Mo	Ti	V
1	SCRM 666/12	3.599	0.106	.	.	1.763	0.0581	1.709	0.102	.	.	.	0.0838	0.0979	0.1069	0.0486
1	SCRM 667/13	3.04	0.222	.	.	2.866	0.497	1.303	0.294	.	0.110	.	0.070	.	.	0.103
1	BS 285BL *	3.4	0.73	0.047	0.01	1.9	0.32	1.4	1.0	0.017	.	0.004	0.056	0.24	0.043	0.12
1	BS 285BK *	3.4	0.74	0.047	0.01	1.9	0.32	1.4	1.0	0.02	.	0.003	0.055	0.24	0.043	0.12
1	BS 285BJ *	3.5	0.73	0.047	0.01	1.9	0.32	1.4	1.0	0.017	.	0.004	0.054	0.24	0.043	0.12
1	BS 285BI *	3.4	0.73	0.047	0.01	1.9	0.32	1.4	1.0	0.017	.	0.003	0.053	0.24	0.04	0.12
1	BS 285BH *	3.4	0.73	0.047	0.01	1.9	0.32	1.4	1.0	0.017	.	0.003	0.052	0.24	0.043	0.12
1	BS 285BG *	3.4	0.73	0.047	0.01	1.9	0.32	1.4	1.0	0.016	.	0.004	0.051	0.24	0.042	0.12
1	BS 285BF *	3.4	0.73	0.047	0.013	1.9	0.32	1.4	1.05	0.016	.	0.003	0.050	0.24	0.042	0.12
1	BS 285BE *	3.4	0.73	0.048	0.013	1.9	0.32	1.4	1.0	0.016	.	0.003	0.049	0.24	0.04	0.12
1	BS 285BD *	3.4	0.73	0.047	0.013	1.9	0.32	1.4	1.0	0.016	.	0.003	0.048	0.24	0.04	0.12
1	BS 285BC *	3.4	0.7	0.05	0.01	1.9	0.3	1.4	1.0	0.01	.	0.003	0.047	0.2	0.04	0.1
1	BS 285BB *	3.4	0.7	0.05	0.01	1.9	0.3	1.4	1.0	0.01	.	0.004	0.046	0.2	0.04	0.1
1	BS 291EH	3.23	0.478	0.0192	0.0120	2.07	0.234	0.099	0.015	0.048	.	(0.0027)	0.046	0.0076	0.0158	0.0082
1	SCRM 670/20	3.576	0.367	.	0.0110	2.261	0.959	0.892	0.505	.	0.0105	.	0.0454	0.0198	0.110	0.0261
1	BS 285BA *	3.5	0.7	0.05	0.01	1.9	0.3	1.4	1.0	0.01	.	0.004	0.045	0.2	0.04	0.1
1	BS 291EG	3.21	0.479	0.0192	0.0118	2.07	0.232	0.099	0.015	0.048	.	(0.0032)	0.045	0.0075	0.0158	0.0082
1	BS 291EF	3.22	0.479	0.0190	0.0118	2.077	0.235	0.100	0.015	0.048	.	(0.0032)	0.044	0.0075	0.0156	0.0082
1	BS 291EE	3.24	0.480	0.0190	0.0119	2.08	0.234	0.099	0.015	0.047	.	(0.0033)	0.043	0.0075	0.0157	0.0082
1	BS 291ED	3.24	0.479	0.0189	0.0119	2.08	0.235	0.099	0.014	0.047	.	(0.0037)	0.042	0.0075	0.0155	0.0082
1	BS 291EC	3.23	0.478	0.0190	0.0125	2.09	0.234	0.099	0.014	0.046	.	(0.0048)	0.041	0.0074	0.0159	0.0083
1	BS 291EB	3.25	0.477	0.0189	0.012	2.09	0.234	0.099	0.015	0.046	.	(0.0040)	0.040	0.0075	0.0159	0.0082
1	BS 286AF	3.24	0.740	0.201	0.0162	2.03	0.341	1.360	0.165	(0.009)	.	(0.004)	0.037	0.258	0.054	0.151
1	BS 286AE	3.24	0.740	0.201	0.0162	2.03	0.341	1.360	0.165	(0.009)	.	(0.004)	0.036	0.258	0.054	0.151
1	SRM C1137a	2.86	0.52	0.087	0.017	1.15	0.192	2.17	0.643	(0.007)	0.016	.	0.032	0.86	(0.04)	0.019
1	BAS SIMO 1/4	2.57	0.329	0.031	0.010	3.95	0.027	0.017	0.913	0.024	.	0.014	0.028	0.699	0.007	0.008
1	BAS SIMO 2/2	2.14	0.434	0.025	0.007	4.75	0.010	0.0189	0.856	0.013	0.006	0.0029	0.026	0.484	0.005	0.009
1	SCRM 669/14	2.955	0.526	.	.	2.201	0.194	0.473	0.214	.	0.0415	.	0.0224	0.0550	0.0499	0.532
1	SCRM 668/13	3.724	0.712	.	.	1.400	0.751	0.097	0.962	.	0.0245	.	0.0116	0.0193	0.091	0.193
1	SRM C2424	2.68	0.268	0.041	0.024	3.37	0.125	0.061	0.13	(<0.01)	0.0046	(0.05)	0.006	0.019	0.050	0.083

Number	As	B	Ca	Fe	La	Nb	Pb	Sn	W	Zr	Units
SCRM 666/12	48 mm x 42 mm x 12 mm
SCRM 667/13	48 mm x 42 mm x 12 mm
BS 285BL *	<0.005	0.008	0.001	90.5	.	0.004	<0.005	0.001	0.06	0.006	-35 mm Ø x 30 mm
BS 285BK *	<0.005	0.008	0.001	90.5	.	0.004	<0.005	0.001	0.06	0.006	-35 mm Ø x 30 mm
BS 285BJ *	<0.005	0.008	0.001	90.5	.	0.004	0.001	0.001	0.06	0.006	-35 mm Ø x 30 mm
BS 285BI *	<0.005	0.008	0.001	90.5	.	0.004	<0.005	<0.005	0.06	0.005	-35 mm Ø x 30 mm
BS 285BH *	<0.005	0.008	0.001	90.5	.	0.004	<0.005	<0.005	0.06	0.005	-35 mm Ø x 30 mm
BS 285BG *	<0.005	0.008	0.001	90.5	.	0.004	<0.005	<0.005	0.06	0.005	-35 mm Ø x 30 mm
BS 285BF *	<0.005	0.008	0.001	90.5	.	0.004	<0.005	0.002	0.06	0.005	-35 mm Ø x 30 mm
BS 285BE *	<0.005	0.008	0.001	90.5	.	0.004	<0.005	0.002	0.06	0.005	-35 mm Ø x 30 mm
BS 285BD *	<0.005	0.008	0.001	90.5	.	0.004	<0.005	0.002	0.06	0.005	-35 mm Ø x 30 mm
BS 285BC *	<0.005	0.008	<0.005	90	.	0.004	<0.005	0.002	0.06	0.006	-35 mm Ø x 30 mm
BS 285BB *	0.002	0.008	<0.005	90	.	0.004	<0.005	0.002	0.06	0.006	-35 mm Ø x 30 mm
BS 291EH	0.0003	0.0055	0.0010	93.6	.	0.0032	0.0004	0.0481	(0.0031)	0.0024	-35 mm Ø x -30 mm
SCRM 670/20	48 mm x 42 mm x 12 mm
BS 285BA *	<0.005	0.008	<0.005	90	.	0.004	<0.005	<0.005	0.06	0.005	-35 mm Ø x 30 mm
BS 291EG	(0.0005)	0.0055	0.0010	93.6	.	0.0033	0.0004	0.0482	(0.0030)	0.0024	-35 mm Ø x -30 mm
BS 291EF	(0.0005)	0.0055	0.0010	93.6	.	0.0033	0.0005	0.0480	(0.0031)	0.0023	-35 mm Ø x -30 mm
BS 291EE	0.0003	0.0055	0.0009	93.6	.	0.0034	0.0004	0.0480	(0.0030)	0.0023	-35 mm Ø x -30 mm
BS 291ED	(0.0005)	0.0055	0.0010	93.6	.	0.0033	0.0004	0.0480	(0.0029)	0.0022	-35 mm Ø x -30 mm
BS 291EC	(0.0006)	0.0055	0.0010	93.6	.	0.0034	(0.0004)	0.0481	(0.0033)	0.0023	-35 mm Ø x -30 mm
BS 291EB	(0.0007)	0.0055	0.0009	93.6	.	0.0032	(0.0004)	0.0480	(0.0031)	0.0022	-35 mm Ø x -30 mm
BS 286AF	(0.01)	0.0085	(0.001)	[91.4]	.	(0.003)	.	(0.004)	(0.008)	(0.007)	-35 mm Ø x -30 mm
BS 286AE	(0.01)	0.0085	(0.001)	[91.4]	.	(0.003)	.	(0.004)	(0.008)	(0.007)	-35 mm Ø x -30 mm
SRM C1137a	32 mm Ø x 19 mm
BAS SIMO 1/4	0.002	0.046	.	.	48 mm x 42 mm x 12 mm
BAS SIMO 2/2	0.039	0.038	.	.	48 mm x 42 mm x 12 mm
SCRM 669/14	48 mm x 42 mm x 12 mm
SCRM 668/13	48 mm x 42 mm x 12 mm
SRM C2424	.	(0.002)	.	.	0.0011	32 mm Ø x 19 mm

RM Si-Mo CAST IRON

BAS SIMO: 48 mm x 42 mm x 12 mm block

CTIF: each unit = one pair 43 mm Ø x 5 mm discs

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Ti	V	Co	As	Sn	Ce	Mg
CTIF SiMo-3	3.18	0.61	0.053	(0.0006)	4.02	0.0325	0.066	0.110	0.604	1.15	0.0176	0.0171	0.0296	.	.	.	0.013
CTIF SiMo-1	2.98	0.365	0.013	(0.0015)	4.03	0.035	0.065	0.036	0.752	.	(0.018)	(0.018)	(0.03)	.	.	.	0.019
CTIF SiMo-5	2.94	0.439	0.0282	.	4.31	0.0121	0.194	0.032	0.841	.	0.010	(0.0095)	(0.013)
CTIF SiMo-2	(2.85)	0.335	0.0260	(0.001)	3.85	0.036	(0.061)	0.038	1.04	1.51	(0.016)	(0.017)	(0.030)	.	.	.	0.072
BAS SIMO 1/3	2.70	0.333	0.040	0.007	4.07	0.028	0.030	0.899	0.776	0.026	0.007	0.007	0.013	0.047	0.048	.	0.036
CTIF SiMo-4	2.70	0.280	0.0211	(0.0015)	4.												

CAST IRON WITH MAGNESIUM - continued on the next page

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	CZ 20034 17b	4.38	0.501	0.089	0.0040	0.178	0.111	2.34	0.200	0.009	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17a	4.30	0.494	0.115	0.0034	0.170	0.082	2.38	0.200	0.007	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17c	4.08	0.503	0.104	0.0033	0.150	0.037	2.32	0.178	0.007	.	(0.002)	(0.003)	0.043	0.030	0.015	0.076
1	Y 2863-11	4.03	0.61	0.613	0.026	0.79	0.96	0.46	1.65	0.0075	0.94	0.29	0.079
1	CZ SPL17 43A	3.98	1.322	0.190	0.008	1.63	0.385	0.411	0.032	(0.04)	.	0.024	0.017	0.045	0.152	0.065	0.152
1	CZ SPL17 42A	3.94	0.764	0.294	0.0040	1.94	0.199	0.492	0.145	(0.06)	.	0.087	0.039	0.010	0.021	0.126	0.093
1	Y 451045	3.90	0.12	0.023	0.0027	2.29	0.022	0.45	0.028	0.033	0.0030	0.016	0.0014
1	CZ 02033 2g	3.78	0.096	0.125	0.009	1.10	0.88	0.650	0.027	0.036	(0.004)	0.019	0.013	0.012	(0.002)	0.029	0.017
1	Y 2863-12	3.77	0.158	0.053	0.057	0.150	0.55	0.192	2.31	0.0024	0.44	0.030	0.229
1	CZ 02033 2f	3.77	0.091	0.159	0.009	1.23	0.89	0.658	0.022	0.053	.	0.024	0.018	(0.003)	(0.002)	0.021	0.010
1	Y 4510251-16	3.75	0.39	0.034	0.012	1.69	0.423	0.60	0.52	0.050	.	0.061	0.034	.	0.203	0.036	0.198
1	VS ChG 25	3.74	0.68	0.0090	0.0035	1.46	0.79	0.38	0.25	0.037	.	0.009	.	.	0.253	0.017	0.086
1	Y 451047	3.73	2.35	0.51	0.0036	2.02	1.98	3.57	1.58	0.060	0.050	0.40	0.018
1	SCRM 668/13	3.724	0.712	.	.	1.400	0.751	0.097	0.962	0.0116	.	.	0.0245	.	0.0193	0.091	0.193
1	CZ 02033 3c	3.68	0.333	0.026	0.007	2.15	0.421	0.040	0.100	0.006	(0.005)	0.024	0.013	0.026	0.490	0.021	0.016
1	SCRM 666/12	3.599	0.106	.	.	1.763	0.0581	1.709	0.102	0.0838	0.0979	0.1069	0.0486
1	SCRM 670/20	3.576	0.367	.	0.0110	2.261	0.959	0.892	0.505	0.0454	.	.	0.0105	.	0.0198	0.110	0.0261
1	CZ 20034 15a	3.54	0.051	0.054	0.0029	1.68	1.322	0.661	0.070	0.031	.	0.026	0.026	0.027	0.005	0.034	0.014
1	CZ SPL17 31A	3.54	0.041	0.025	0.006	2.10	0.005	0.538	0.019	0.070	.	0.005	(0.004)	0.022	0.004	0.007	0.008
1	11X SG1A	3.53	0.278	0.0363	0.0095	2.96	0.0194	0.042	0.0299	0.040	.	0.0187	.	.	.	0.0150	.
1	CZ 20034 15b	3.52	0.048	0.054	0.0031	1.66	1.322	0.681	0.067	0.037	.	0.029	0.021	0.027	0.004	0.025	0.013
1	CZ SPL17 34A	3.48	0.980	0.105	0.008	2.29	0.230	0.493	0.102	0.026	.	0.010	0.008	0.025	0.072	0.044	0.073
1	11X SG2A	3.48	0.297	0.0353	0.0075	3.03	0.0245	0.0263	0.0304	0.055	.	0.0238	.	.	.	0.0146	.
1	Y 451042	3.47	0.71	0.043	0.012	2.11	0.35	1.39	1.02	0.023	0.22	0.029	0.15
1	CZ 02033 2e	3.47	0.168	0.106	0.010	1.03	0.89	0.620	0.043	0.038	(0.006)	0.025	0.017	0.005	(0.002)	0.039	0.026
1	CZ 20034 15c	3.47	0.060	0.054	0.0028	1.68	1.123	0.728	0.078	0.040	.	0.010	0.030	0.026	(0.002)	0.036	0.019
1	CZ SPL17 32A	3.39	0.288	0.037	0.007	2.74	0.306	0.015	0.060	0.024	.	0.029	(0.004)	(0.002)	0.116	0.044	0.005
1	CZ 02033 3b	3.38	0.260	0.012	0.012	1.74	0.400	0.049	0.235	0.012	.	0.026	0.006	0.012	0.456	0.023	0.009
1	CZ SPL17 40A	3.38	0.042	0.021	0.0035	1.98	0.010	0.045	0.031	0.007	.	0.096	0.012	0.027	0.005	0.015	0.014
1	VS ChG 28	3.29	0.414	0.025	0.015	2.22	1.29	0.166	0.127	0.010	.	0.015	.	.	0.0024	0.0041	0.0020
1	CZ 20034 14a	3.29	0.218	0.0115	0.0103	2.25	0.578	0.021	0.042	0.015	.	0.009	0.009	0.005	0.633	0.018	0.013
1	CZ 20034 14b	3.26	0.240	0.0115	0.0096	2.34	0.640	0.020	0.042	0.015	.	0.012	0.012	0.005	0.635	0.021	0.012
1	BS 286AF	3.24	0.740	0.201	0.0162	2.03	0.341	1.360	0.165	0.037	.	(0.009)	.	(0.004)	0.258	0.054	0.151
1	BS 286AE	3.24	0.740	0.201	0.0162	2.03	0.341	1.360	0.165	0.036	.	(0.009)	.	(0.004)	0.258	0.054	0.151
1	CZ 02033 3d	3.24	0.317	0.008	0.006	2.12	0.396	0.025	0.236	0.016	.	0.055	0.006	0.014	0.453	0.016	0.072
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	CZ 02033 1f	3.23	0.693	0.043	0.005	2.68	0.018	0.373	0.035	0.070	(0.007)	0.073	0.036	0.024	0.182	0.041	0.014
1	CZ 02033 1g	3.22	0.701	0.036	0.007	2.53	0.027	0.357	0.044	0.050	.	0.062	0.023	0.010	0.185	0.054	0.019
1	CZ 20034 13c	3.15	0.704	0.0261	0.0044	2.23	0.089	1.299	0.124	0.064	.	0.022	0.011	0.024	0.360	0.015	0.043
1	CZ 02033 1e	3.15	0.718	0.037	0.006	2.72	0.012	0.367	0.037	0.044	.	0.058	0.027	0.022	0.185	0.046	0.015
1	CZ 02033 1c	3.15	0.674	0.064	0.010	2.36	0.035	0.367	0.051	0.019	.	0.033	0.009	.	0.197	0.036	0.019
1	CZ 20034 14c	3.14	0.275	0.0162	0.0081	2.49	0.585	0.030	0.045	0.017	.	0.007	0.019	0.009	0.646	0.018	0.013
1	CKD 247C (U)	3.13	0.99	0.099	0.0033	1.29	0.84	0.503	0.029	0.053	(0.007)	0.041	0.058	0.097	0.024	0.057	0.010
1	CZ 20034 13a	3.13	0.691	0.0244	0.0046	2.19	0.021	1.266	0.122	0.053	.	0.017	0.011	0.024	0.364	0.014	0.048
1	CZ 20034 13b	3.12	0.692	0.0243	0.0041	2.12	0.021	1.313	0.125	0.054	.	0.019	0.011	0.024	0.364	0.012	0.048
1	CKD 247B	3.09	1.05	0.098	0.0034	1.20	0.822	0.437	0.041	0.056	(0.008)	0.043	0.053	0.095	0.023	0.067	0.013
1	VS ChG 24	3.05	0.245	0.260	0.0048	2.50	0.100	0.87	0.031	0.015	.	0.007	.	.	0.031	0.060	0.0067
1	Y 2863-9	3.04	1.43	0.049	0.015	1.53	0.269	1.59	0.72	0.043	1.38	0.212	0.41
1	VS ChM5/1	3.04	0.311	0.056	0.016	1.37	.	.	.	0.045	.	0.013
1	SCRM 667/13	3.04	0.222	.	.	2.866	0.497	1.303	0.294	0.070	.	.	0.110	.	.	.	0.103
1	VS ChM6/1	3.03	0.54	0.055	0.0074	2.75	.	.	.	0.072	.	0.022
1	VS ChM9/1	3.02	0.83	0.055	0.0034	3.39	.	.	.	0.105	.	0.041
1	CZ SPL17 36A	3.02	0.057	0.026	0.010	2.13	0.007	0.011	0.014	0.012	.	(0.003)	0.0007	(0.004)	0.004	0.021	0.021
1	VS ChM13	2.96	1.05	0.043	0.009	2.98	0.062	1.65	0.273	0.09	.	0.065	.	.	.	0.018	0.0096
1	SCRM 669/14	2.955	0.526	.	.	2.201	0.194	0.473	0.214	0.0224	.	.	0.0415	.	0.0550	0.0499	0.532
1	CKD 245B(U)	2.95	1.38	0.42	0.035	1.59	0.081	0.194	0.197	0.003	(0.017)	0.038	(0.00)	0.007	0.115	0.110	0.055
1	CKD 245A	2.94	1.38	0.41	0.039	1.58	0.076	0.161	0.166	0.003	(0.018)	0.019	(0.00)	0.003	0.114	0.087	0.073
1	VS ChG 26	(2.9)	0.126	0.123	0.0041	2.98	0.014	1.52	0.050	0.044	.	0.038	.	.	0.075	0.0026	0.040
1	VS ChM10	2.89	0.43	0.067	0.017	1.13	0.082	0.85	0.067	0.024	.	0.005	.	.	.	0.028	0.079
1	SRM C1137a	2.86	0.52	0.087	0.017	1.15	0.192	2.17	0.643	0.032	.	(0.007)	0.016	.	0.86	(0.04)	0.019
1	CZ SPL17 33A	2.75	0.710	0.060	0.007	3.10	0.730	0.389	0.239	0.021	.	0.054	0.026	0.015	0.220	0.130	0.356
1	CKD 246B	2.73	0.354	0.66	0.020	0.76	1.39	0.065	1.16	0.016	(0.00)	0.101	0.007	0.012	0.009	0.014	0.013
1	SRM C2424	2.68	0.268	0.041	0.024	3.37	0.125	0.061	0.13	0.006	.	(<0.01)	0.0046	(0.05)	0.019	0.050	0.083
1	VS ChM9	2.61	1.28	0.075	0.021	1.59	0.095	0.38	0.083	0.011	.	0.016	.	.	.	0.027	0.068
1	VS ChM11	2.26	0.77	0.032	0.011	2.32	0.067	1.75	0.122	0.066	.	0.035	.	.	.	0.014	0.0044
1	Y 2863-7	1.98	3.42	0.067	0.0061	3.10	0.089	4.47	0.150	0.050	.	.	0.019	.	0.052	0.060	0.87

BS: 28-34 mm Ø x 17-35 mm

CKD 24x: 37 mm x 37 mm x ~15-20 mm

SCRM: 48 mm x 42 mm x 12 mm

VS: ~40 mm Ø x ~40 mm

CZ: 40 mm Ø x 18 mm

SRM: 32 mm Ø x 19 mm

Y: 30 mm Ø x 30 mm

RM CAST IRON WITH YOUR CHOICE OF MAGNESIUM LEVELS each unit: 2 pcs mushroom 43 mm Ø x 5 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Al	Ce	Co	Sn	Ti	V	Zn	Other
CTIF 6134	3.70	0.25	0.030	<0.01	1.60	0.020	2.00	0.040	*	.	<0.03
CTIF 8532	3.7	0.288	0.05	.	2.6	0.0443	0.888	0.04	*	.	<0.025	.	0.0303	0.02	0.07	.	.
CTIF 6135	3.6	0.38	0.0130	(0.003)	0.9	0.0219	1.98	0.04	*	(0.006)	.	0.037	.	0.007	0.0155	.	.
CTIF 4500	3.38	0.60	0.059	(0.002)	1.97	.	1.45	0.014	*	0.033	0.023	0.065
CTIF 5781	3.35	0.26	0.030	(0.0025)	2.50	0.0061	0.83	0.040	*	.	.	(0.004)	.	0.0208	0.0150	.	.
CTIF 4497	3.12	0.605	0.043	(<0.002)	2.66	0.048	1.90	0.040	*	.	.	.	0.094	0.031	0.44	.	.
CTIF 7160	3.1	0.57	0.05	(0.001)	2.4	0.08	1.0	(0.1)	*	(0.02)	0.02	0.09	.	0.013	0.018	.	As: 0.009
CTIF 5037	3.04	0.76	0.043	(0.0025)	3.40	.	0.64	0.014	*	0.029	.	.	.
CTIF 3601B	3.0	0.35	0.037	(0.005)	2.1	0.019	1.08	0.029	*	.	<0.01	.	.	0.016	(0.005)	<0.05	Pb:(<0.002)
CTIF 8018	3.0	0.7	0.07	(0.0015)	3.0	0.08	0.127	0.09	*	0.02	(<0.02)	.	0.07	0.06	0.39	.	Sb:(0.01)
CTIF 6736	2.8	0.65	0.012	(0.002)	1.6	0.0258	1.7	0.03	*	0.008	(0.03)	.	.
CTIF 5783	2.55	0.2	0.0266	(0.003)	2.3	0.110	1.23	0.05	*	.	.	0.0074	.	0.015	0.0127	.	As: 0.0016

Magnesium level available in the below samples. X = available

For Mg Range	Order Suffix	3601B	4497	4500	5037	5781	5783	6134	6135	6736	7160	8018	8532
<0.005	<0.005	X	.	.	.	X	X	X	.
0.005 - 0.009	0.005	X	.	.	X	X	X	.	.	X	.	X	X
0.010 - 0.014	0.01	.	.	.	X	X	X	.	.	X	X	X	X
0.015 - 0.024	0.02	X	.	.	X	X	X	.	X	X	X	X	X
0.025 - 0.034	0.03	.	.	.	X	.	X	.	X	X	X	X	X
0.035 - 0.044	0.04	.	.	.	X	.	X	.	X	X	X	X	X
0.045 - 0.054	0.05	.	.	.	X	.	X	.	X	X	X	X	X
0.055 - 0.064	0.06	.	X	X	.	.	X	.	X	X	X	X	X
0.065 - 0.074	0.07	.	X	X	.	.	X	.	X	X	X	X	.
0.075 - 0.084	0.08	.	X	X	.	.	X	X	X	X	X	X	.
0.085 - 0.094	0.09	.	X	X	.	.	X	X	X	X	X	X	.
0.095 - 0.104	0.10	X	X	X	X	X	X	.
0.105 - 0.114	0.11	X	X	X	X	X	.
0.115 - 0.124	0.12	X	X	X	X	X	.
0.125 - 0.134	0.13	X	X	X	X	X	.
0.135 - 0.144	0.14	X	.	.	X	.	.
0.145 - 0.154	0.15	X	.	.
0.155 - 0.164	0.16	X	.	.
0.165 - 0.174	0.17	X	.	.
0.175 - 0.184	0.18	X	.	.

The above cast iron samples can be ordered with your choice of Magnesium. Examples:
 to order CTIF 6736 with Mg 0.035 - 0.044 then order as part number CTIF 6736 0.04
 to order CTIF 8018 with trace Mg, order as part number CTIF 8018 <0.005

CRM WHITE IRON analysis listed in mass %

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	Nb	Ti	V
BS WI-2	3.61	0.80	0.22	0.056	0.52	0.0124	0.254	0.229	0.0118	0.219	0.128	0.089	0.215
SRM CII45	2.92	0.187	0.215	0.191	0.271	0.46	0.62	0.63	0.058	0.48	.	0.012	0.112
VS Chg 8/6	(2.7)	1.51	0.040	0.013	3.93	.	.	(0.2)	(0.3)
VS Chg 10/6	(2.7)	0.86	0.103	0.0072	2.86	.	.	(0.2)	(0.3)
VS Chg 11/6	(2.7)	0.312	0.23	0.039	1.79	.	.	(0.2)	(0.3)
VS Chg 9/6	(2.7)	0.155	0.38	0.071	0.80	.	.	(0.2)	(0.3)
BS WI-1	1.75	0.24	0.051	0.114	1.90	0.027	0.053	0.048	0.0074	0.0103	0.027	0.020	0.008

17025

17025

Number	Al	As	B	Bi	Ca	Fe	Mg	Pb	Sb	Sn	W	Zr	Units
BS WI-2	0.0192	0.0016	0.0008	.	(0.00013)	[93.6]	(0.0002)	0.013	0.023	0.0042	0.023	0.0045	~35 mm Ø x ~30 mm
SRM CII45	(0.04)	(0.03)	(0.02)	(<0.01)	.	.	.	0.0012	(0.04)	(0.10)	.	(0.002)	32 mm Ø x 19 mm
VS Chg 8/6	.	(0.003-0.006)	~38 mm Ø x ~38 mm
VS Chg 10/6	.	(0.003-0.006)	~38 mm Ø x ~38 mm
VS Chg 11/6	.	(0.003-0.006)	~38 mm Ø x ~38 mm
VS Chg 9/6	.	(0.003-0.006)	~38 mm Ø x ~38 mm
BS WI-1	0.075	0.0067	0.0032	.	0.0005	[95.5]	0.0009	0.115	.	0.0081	0.185	0.0034	~35 mm Ø x ~30 mm

CAST IRON WITH C > 2.75%

CONTINUED ON THE NEXT PAGE

= Class, 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	CZ SPL17 35A	4.55	0.096	0.024	0.011	0.078	0.004	0.024	0.022	(0.002)	0.023	0.003	.	(0.002)	(0.002)	0.009	.
1	CZ 02033 4e	4.45	0.034	0.023	0.006	0.090	0.005	0.049	0.030	(0.003)	0.033	0.002	.	(0.001)	(0.011)	0.015	.
1	SCRM 672/1	4.322	0.474	0.198	0.036	0.143	0.100	0.083	0.0186	0.0102	0.139	0.117	.	0.0047	0.0373	0.0988	.
1	CZ 02033 4d	4.19	0.112	0.050	0.041	0.259	0.084	0.063	0.056	0.007	(0.003)	0.024	.	(0.001)	0.009	0.012	0.009
1	SCRM 659/9	4.174	1.010	0.0215	0.0372	1.361
1	Y 2582-7	4.13	2.06	0.306	0.111	1.85	.	0.026	0.157	0.399	0.821	.
2	BS CC-14 (4.04)	(0.01)	0.016	0.003	0.64	0.021	0.074	0.031	0.006	0.036	(0.003)	.	.	0.002	0.004	0.021	.
1	DSZU CH04	4.01	1.77	0.074	0.018	0.73	0.55	0.273	0.100	0.014	(0.05)	(0.004)	(0.005)	(0.002)	0.025	(0.004)	.
1	DSZU CH05	3.99	2.23	0.119	0.039	0.46	0.61	0.85	1.63	(0.002)	(0.07)	0.109	(0.3)	(0.01)	0.070	0.200	.
1	CZ 02033 4b	3.95	0.145	0.041	0.046	0.252	0.062	0.023	0.049	0.003	0.005	0.005	.	0.001	0.006	0.004	0.008
1	Y 2582-6	3.93	1.46	0.168	0.124	0.99	.	0.094	0.387	.	.	(0.112)	.	.	0.105	0.506	.
1	VS ChG 2/9	3.93	0.456	0.513	0.078	0.387	0.082	.	0.060	0.080	0.049	.
1	DSZU CH06	3.88	0.85	0.050	0.050	0.28	1.03	1.23	(2.8)	0.025	(0.07)	0.29	(0.05)	(0.03)	0.33	0.205	.
1	CZ 20034 16c	3.87	1.311	0.173	0.0243	0.95	0.345	0.376	0.332	0.004	0.006	0.195	.	0.125	0.057	0.027	0.017
1	CZ 20034 16a	3.80	1.292	0.171	0.0266	1.00	0.332	0.390	0.374	0.007	0.010	0.203	.	0.125	0.0763	0.021	0.019
1	CZ 20034 16b	3.78	1.327	0.170	0.0236	1.00	0.332	0.388	0.378	0.007	0.010	0.202	.	0.121	0.070	0.029	0.020
1	VS ChG 32	3.74	1.90	0.061	0.018	0.60	0.171	.	0.031	.	.	0.113	.	0.060	0.040	0.294	.
1	SCRM 674/1	3.71	1.437	0.0180	0.078	0.484	.	0.161	0.0296	0.0061	0.0066	0.0497	.	0.0164	0.0131	0.0125	.
1	Y 2582-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	.	(0.031)	.	.	0.030	0.158	.
1	CZ SPL17 39A	3.70	0.812	0.160	0.045	1.90	0.298	0.032	0.488	0.008	(0.002)	0.203	.	(0.003)	(0.074)	0.232	0.035
1	Y 451043	3.69	0.49	0.063	0.049	1.50	0.34	0.23	0.47	.	.	0.22	.	.	.	0.11	.
1	11X HPCSA	3.68	1.028	0.246	0.223	1.175	.	.	1.42
1	Y 2582-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	.	(0.68)	.	.	0.066	0.335	.
1	VS ChG 1/9	3.61	1.12	0.184	0.038	1.13	0.041	.	0.017	0.014	0.006	.
1	CZ 02033 7b	3.61	0.304	0.021	0.020	1.82	0.036	1.28	0.536	0.022	0.050	0.96	.	.	0.015	0.007	.
1	CZ 02033 7c	3.55	0.389	0.028	0.026	1.73	0.016	1.26	0.542	0.040	0.048	0.966	.	(0.004)	0.026	0.067	.
1	DSZU CH03	3.54	0.40	0.023	0.034	0.57	0.194	0.187	0.612	0.035	(0.05)	(0.019)	(0.010)	(0.004)	0.059	0.009	.
1	VS ChG 3/9	3.54	0.387	0.037	0.053	0.516	0.123	.	0.100	0.125	0.096	.
1	VS ChG 27	3.53	1.21	0.044	0.029	1.82	0.348	0.022	0.162	0.008	.	0.147	.	0.115	0.056	0.160	.
1	SCRM 660/10	3.522	0.398	0.143	0.1089	1.719
1	VS ChG 5/9	3.51	0.60	0.104	0.036	0.84	0.037	.	0.307	(0.1)	0.441	.
1	11X C10C	3.48	0.696	0.103	0.050	2.10	1.54	2.673	0.302	0.104	.	0.335	.	0.0458	0.0709	0.0589	.
1	Y 2863-5	3.47	0.78	0.564	0.070	0.89	0.365	0.62	1.53	.	.	0.67	.	.	0.133	0.129	.
1	11X C2U	3.414	1.203	0.268	0.093	1.081	0.1085	1.702	0.882	0.053	0.226	0.111	(0.030)	0.046	0.094	0.314	.
1	CZ SPL17 41A	3.41	0.512	0.199	0.068	1.92	0.151	0.104	0.125	(0.003)	0.031	0.041	.	0.066	0.048	0.011	(0.001)
1	CZ 02033 8c	3.41	0.408	0.168	0.058	1.93	0.158	0.102	0.125	0.004	0.030	0.041	.	0.067	0.022	0.015	.
1	11X C3AB	3.408	0.447	0.451	0.201	0.849	0.295	3.20	2.02	0.0090	0.241	0.216	(0.19)	0.209	0.040	0.692	0.0389
1	VS ChL1/1	3.39	0.53	0.048	0.029	1.32	0.344	0.410	0.264	.	0.017	0.036	.	.	0.061	0.073	.
1	CZ SPL17 38A	3.39	0.401	0.067	0.036	2.37	0.510	0.306	0.141	0.034	0.021	0.101	0.008	0.032	0.012	0.061	0.028
1	11X HPC3J	3.38	1.287	2.01	0.0473	1.63	.	2.18	1.48	.	.	0.120
1	VS ChG 1/5	3.38	1.09	0.160	0.029	1.04	(0.04)	.	(0.08)	0.005	0.050	.
1	VS ChG 35	3.34	1.23	0.102	0.021	0.617	0.090	2.15	0.233	.	.	0.027	.	.	0.022	0.043	.
1	KUT 120	3.34	0.59	0.059	0.18	1.84
1	NCS HS11783	3.33	0.756	0.083	0.090	1.73	0.666	0.304	0.386	.	.	0.238	.	0.066	0.057	0.174	.
1	SCRM 658/11	3.278	0.502	0.177	0.067	1.933
1	Y 2863-3	3.32	1.27	0.115	0.049	2.27	0.62	2.01	0.49	.	.	0.313	.	.	0.176	0.45	.
1	KUT 121	3.32	0.61	0.135	0.17	(1.86)
1	KUT 205	3.32	0.80	0.025	(0.010)	1.88	0.81	0.61	0.64	.	.	1.79	.	(0.035)	.	.	.
1	KUT 206	3.32	0.75	0.027	(0.010)	1.84	1.01	0.21	0.12	.	.	2.14	.	(0.107)	.	.	.
1	KUT 122	3.31	0.61	0.22	0.20	1.72
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	KUT 123	3.30	0.69	0.31	0.074	(1.87)
1	NCS HS11784	3.30	0.528	0.78	0.031	2.68	0.015	0.024	0.812	(0.0012)	.	0.142	(0.0012)	0.0005	0.084	0.020	.
1	Y 2582-3	3.29	1.22	0.045	0.056	0.689	.	0.046	0.030	0.043	0.071	.
1	11X HPC1H	3.29	0.620	0.808	0.0035	3.27	.	.	1.056	.	.	0.060
1	SCRM 665/4	3.25	0.24	1.09	0.053	1.66	.	.	(1)
1	11X C9D	3.24	1.886	0.069	0.0260	1.462	0.581	2.79	1.206	0.051	0.1301	0.155	0.0766	0.040	(0.062)	0.359	0.009
1	VS ChG 4/9	3.24	1.42	0.030	0.024	0.455	0.199	.	0.155	0.10	0.169	.
2	BAS NCRM3	3.24	0.67	0.125	0.090	0.29	1.21	3.64	3.95	.	.	0.78	.	.	.	0.02	.
1	11X HPC1G	3.22	0.499	0.75	0.0311	2.60	0.042	0.014	0.061	.	.	0.0048	.	.	0.027	0.0079	.
1	NCS HS11782	3.21	1.09	0.088	0.035	1.64
1	KUT 125	3.20	0.73	0.70	0.019	(1.87)
1	VS ChG 31	3.19	0.97	0.047	0.043	1.60	0.281	.	0.156	.	.	0.0069	.	0.013	0.0063	0.0035	.
1	NCS HS11785	3.19	0.482	0.79	0.030	2.52	0.021	0.031	0.817	(0.0030)	.	0.139	(0.0009)	0.0010	0.076	0.018	.
1	DSZU CH02	3.18	1.09	0.007	0.0116	1.35	0.038	0.658	0.59	0.026	(0.06)	0.224	(0.4)	(0.014)	0.161	(0.005)	.
1	VS ChM 12	3.17	1.00	0.030	0.007	3.10	0.062	1.65	0.039	0.050	0.013	0.0027	.
1	SCRM 671/1	3.165	0.811	0.108	0.0503	0.868	.	0.0627	0.0609	0.030	0.098	0.0259	.	0.0103	0.0407	0.0122	.
1	KUT 126	3.16	0.81	1.41	0.016	1.90
1	KUT 202	3.16	0.81	0.024	(0.010)	1.77	0.24	2.07	2.36	.	.	0.44	.	(0.21)	.	.	.
1	KUT 204	3.15	0.80	0.023	(0.009)	1.79	0.64	1.09	1.22	.	.	1.38	.	(0.215)	.	.	.
1	CZ 02033 6a	3.14	1.22	0.077	0.032	3.37	0.225	0.023	1.40	0.022	.</						

CAST IRON WITH C > 2.75%

CONTINUED FROM THE PREVIOUS PAGE

analysis in mass % except * = mg/kg

Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
CZ SPL17 35A	.	(0.0002)	0.0036	(0.002)	.	.	.	(0.005)	.	40 mm Ø x 18 mm
CZ 02033 4e	.	.	(0.002)	(0.002)	40 mm Ø x 18 mm
SCRM 672/1	0.0079	40 mm x 37 mm x 10 mm
CZ 02033 4d	(0.012)	(0.0001)	(0.002)	0.007	40 mm Ø x 18 mm
SCRM 659/9	48 mm x 42 mm x 12 mm
Y 2582-7	0.043	30 mm Ø x 30 mm
BS CC-14	(<0.001)	(0.0003)	(<0.0005)	11	(0.002)	(0.0007)	(0.024)	.	0.0002	(0.001)	.	0.005	(0.003)	(0.002)	32 mm Ø x 17 mm last
DSZU CH04	.	(0.0007)	.	(7)	.	.	(0.0001)	.	(0.007)	.	.	.	(<0.0002)	.	~30 mm x ~35 mm
DSZU CH05	.	(0.03)	.	(20)	.	.	(0.001)	~30 mm x ~35 mm
CZ 02033 4b	0.004	(0.001)	40 mm Ø x 18 mm
Y 2582-6	0.0018	30 mm Ø x 30 mm
VS ChG 2/9	(0.003)	~38 mm Ø x ~38 mm
DSZU CH06	.	(0.02)	.	(10)	0.1	.	~35 mm x ~35 mm
CZ 20034 16c	(0.003)	0.020	0.015	0.010	.	.	0.015	(0.002)	40 mm Ø x 18 mm
CZ 20034 16a	0.005	0.018	0.006	0.011	.	.	0.019	(0.002)	40 mm Ø x 18 mm
CZ 20034 16b	0.005	0.018	0.007	0.011	.	.	0.019	(0.002)	40 mm Ø x 18 mm
VS ChG 32	.	.	0.361	~35 mm Ø x ~20 mm
SCRM 674/1	40 mm x 37 mm x 10 mm
Y 2582-4	0.0017	30 mm Ø x 30 mm
CZ SPL17 39A	.	0.0195	0.008	0.0037	0.017	0.037	40 mm Ø x 18 mm
Y 451043	0.12	30 mm Ø x 30 mm last
11X HPC5A	40 mm Ø x 17 mm
Y 2582-5	0.0022	30 mm Ø x 30 mm
VS ChG 1/9	(0.003)	~38 mm Ø x ~38 mm
CZ 02033 7b	0.045	.	40 mm Ø x 18 mm
CZ 02033 7c	.	0.0008	(0.002)	(0.006)	0.037	.	40 mm Ø x 18 mm
DSZU CH03	(0.004)	(0.001)	.	(20)	.	.	(0.0001)	.	(0.01)	.	.	.	(0.006)	.	~30 mm x ~35 mm
VS ChG 3/9	(0.003)	~38 mm Ø x ~38 mm
VS ChG 27	0.029	~40 mm Ø x ~40 mm
SCRM 660/10	48 mm x 42 mm x 12 mm
VS ChG 5/9	(0.003)	~38 mm Ø x ~38 mm
11X C10C	0.0200	0.0050	0.0095	.	.	0.327	.	~40 mm Ø x ~15 mm
Y 2863-5	.	0.060	0.158	.	30 mm Ø x 30 mm
11X C2U	0.0288	0.0213	0.0055	.	.	.	0.0110	0.023	0.104	0.0199	.	.	0.062	.	~40 mm Ø x ~15 mm
CZ SPL17 41A	.	(0.0004)	(0.007)	.	.	.	0.0070	0.010	0.016	.	.	.	0.012	.	40 mm Ø x 18 mm
CZ 02033 8c	(0.006)	.	0.009	0.008	0.014	.	.	.	40 mm Ø x 18 mm
11X C3AB	0.098	0.0054	0.0144	0.0095	0.022	0.245	0.0193	.	0.0520	.	~40 mm Ø x ~15 mm last
VS ChL1/1	~38 mm Ø x ~38 mm
CZ SPL17 38A	.	0.0027	(0.002)	0.0100	(0.003)	0.018	.	.	(0.005)	.	40 mm Ø x 18 mm
11X HPC3J	~40 mm Ø x ~15 mm
VS ChG 1/5	(0.002)	~40 mm Ø x ~40 mm last
VS ChG 35	~40 mm Ø x ~40 mm
KUT 120	30 x 30 x 13 mm
NCS HS11783	0.0085	0.142	31 mm Ø x 28 mm
SCRM 658/11	48 mm x 42 mm x 12 mm
Y 2863-3	.	0.056	30 mm Ø x 30 mm
KUT 121	30 x 30 x 13 mm
KUT 205	30 x 30 x 13 mm
KUT 206	30 x 30 x 13 mm
KUT 122	30 x 30 x 13 mm
Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
KUT 123	30 x 30 x 13 mm
NCS HS11784	0.0041	.	0.0083	0.0002	0.0007	31 mm Ø x 28 mm
Y 2582-3	0.009	30 mm Ø x 30 mm
11X HPC1H	~40 mm Ø x ~15 mm
SCRM 665/4	48 mm x 42 mm x 12 mm
11X C9D	0.068	0.0049	0.0052	0.149	.	0.011	0.304	.	~40 mm Ø x ~15 mm
VS ChG 4/9	(0.003)	~38 mm Ø x ~38 mm
BAS NCRM3	40 mm x 37 mm x 10 mm
11X HPC1G	40 mm Ø x 15 mm
NCS HS11782	0.0065	31 mm Ø x 28 mm
KUT 125	30 x 30 x 13 mm
VS ChG 31	.	.	0.068	~35 mm Ø x ~20 mm
NCS HS11785	0.0049	.	0.013	0.0002	0.0005	31 mm Ø x 28 mm
DSZU CH02	.	(0.016)	.	(10)	.	.	(0.002)	~35 mm Ø x ~18 mm
VS ChM 12	(0.08)	~38 mm Ø x ~38 mm
SCRM 671/1	40 mm x 37 mm x 12 mm
KUT 126	30 x 30 x 13 mm
KUT 202	30 x 30 x 13 mm
KUT 204	30 x 30 x 13 mm
CZ 02033 6a	0.056	40 mm Ø x 18 mm
KUT 127	30 x 30 x 13 mm
CZ 02033 6c	.	0.0024	(0.003)	0.044	.	0.007	.	40 mm Ø x 18 mm
CZ 02033 7a	0.022	.	40 mm Ø x 18 mm
SCRM 653/4	48 mm x 42 mm x 12 mm last
CZ SPL17 37A	.	0.0124	(0.002)	0.0089	(0.002)	.	.	.	0.026	.	40 mm Ø x 18 mm
VS ChG 30	.	.	0.082	~35 mm Ø x ~20 mm
BAS NCRM1	40 mm x 37 mm x 10 mm
VS ChL3/1	~38 mm Ø x ~38 mm
DSZU CH08	.	(0.08)	.	(10)	~35 mm x ~35 mm
VS ChG 39	~40 mm Ø x ~40 mm
BS CC-11	0.006	0.0012	(<0.0005)	2	(0.001)	(0.001)	(0.013)	.	0.0007	0.14	.	(0.002)	(0.002)	(0.002)	32 mm Ø x 17 mm last
BAS LARM2	0.044	.	.	.	0.008	.	.	.	0.007	40 mm x 37 mm x 10 mm
BAS LARM4	0.008	.	.	.	0.018	40 mm x 37 mm x 10 mm
BAS LARM1	.	0.006	0.011	.	0.005	40 mm x 37 mm x 10 mm
BAS LARM5	0.018	0.0012	0.0010	0.0005	40 mm x 37 mm x 10 mm last
BAS LARM3	0.092	0.003	0.022	40 mm x 37 mm x 10 mm
Y 2863-4	.	0.041	30 mm Ø x 30 mm
BAS LARM5/1	.	0.0016	0.0012	<0.001	40 mm x 37 mm x 10 mm
BAS NCRM2	40 mm x 37 mm x 10 mm
KUT 124	30 x 30 x 13 mm
CZ 02033 6b	0.049	40 mm Ø x 18 mm
SCRM 662/4	48 mm x 42 mm x 12 mm
VS ChG 36	~40 mm Ø x ~40 mm
SCRM 657/8	48 mm x 42 mm x 12 mm
CZ 20034 12b	0.024	0.047	0.006	0.009	0.046	.	.	0.007	(0.002)	40 mm Ø x 18 mm
SRM C1145a	(0.03)	(0.02)	0.0012	(0.04)	.	.	.	(0.002)	32 mm Ø x 19 mm
11X C1R	0.0141	0.0357	0.011	0.0091	0.005	0.046	0.0050	.	0.100	0.0030	~40 mm Ø x ~15 mm
VS ChG34	.	.	0.223	~35 mm Ø x ~20 mm
SCRM 664/4	48 mm x 42 mm x 12 mm
CZ 20034 12a	0.022	0.036	0.005								

CAST IRON WITH C < 2.75%

= Class, 1 = CRM and 2 = RM

analysis in mass % except * = mg/kg

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	11X C5Y *	2.75	0.75	0.09	0.09	1.9	0.42	1.2	0.94	0.06	0.045	0.53	0.015	0.03	0.09	0.075	0.01
1	VS ChL4/1	2.69	1.37	0.054	0.027	1.99	0.161	0.725	0.92	.	0.017	0.116	.	.	0.11	0.258	.
1	SRM C1291	2.67	1.14	0.028	0.032	1.34	0.26	4.34	2.78	.	.	0.32	.	.	.	0.031	.
1	VS ChG 6/9	2.65	0.83	0.54	0.027	0.53	0.34	.	0.241	0.028	0.130	.
1	DSZU CH01	2.61	0.258	0.012	0.0045	1.95	0.097	0.072	0.88	0.079	(0.06)	0.070	(0.010)	(0.05)	0.132	0.134	.
1	VS ChG 40	2.59	1.56	0.059	0.019	1.60	0.98	1.61	1.47	.	.	0.229	.	.	0.18	0.325	.
1	11X C8V *	2.58	0.40	1.0	0.21	1.60	0.31	0.28	0.145	0.085	0.130	0.15	0.02	0.105	0.24	0.063	0.006
1	SRM 661/4	2.56	0.30	0.84	0.068	2.96	.	.	(1)
1	SRM 656/9	2.537	0.820	0.060	0.108	2.504
1	11X C7N	2.51	1.942	0.0266	0.0101	0.829	0.075	0.0303	0.507	0.0127	0.0335	0.071	0.051	0.0114	0.022	0.036	0.0226
1	Y 2863-2	2.50	1.83	0.069	0.026	3.14	0.020	3.73	0.136	.	.	0.096	.	.	0.066	0.61	.
1	VS ChG 37	2.49	0.92	0.038	0.046	2.03	0.512	0.90	0.82	.	.	0.55	.	.	0.092	0.227	.
1	SRM 673	2.47	0.133	0.328	0.006	1.72	0.023	0.147	0.037	0.028	0.053	0.006	.	0.0191	0.072	0.059	0.0004
1	SRM 673/1	2.455	0.123	0.317	0.0112	1.702	.	0.103	0.0423	0.0287	0.053	0.0092	.	0.0206	0.0718	0.052	.
1	CZ 20034 11b	2.44	0.382	0.271	0.140	3.67	0.130	0.082	1.178	0.067	0.005	1.144	.	0.074	0.041	0.182	.
1	VS ChG 38	2.43	0.302	0.386	0.084	2.30	1.20	0.162	1.98	.	.	0.046	.	.	0.105	0.119	.
1	CZ 02033 5b	2.42	0.812	0.033	0.073	1.32	0.031	0.188	0.061	0.062	.	0.089	.	.	0.007	0.005	.
1	VS ChL2/1	2.38	1.03	0.054	0.023	0.55	0.97	0.114	0.077	.	0.013	0.012	.	.	0.009	0.050	.
1	CZ 20034 11a	2.37	0.343	0.271	0.163	3.31	0.086	0.084	1.219	0.046	0.005	1.130	.	0.070	0.028	0.184	.
1	SRM 652/4	2.34	1.19	0.071	0.129	0.878	.	.	(1)
1	DSZU CH07	2.33	1.36	0.090	0.064	3.01	0.35	0.403	0.34	0.036	.	0.66	(0.08)	(0.07)	0.150	0.52	.
1	CZ 02033 5a	2.30	0.804	0.035	0.100	1.26	0.014	0.096	0.054	0.060	.	0.100	.	.	0.008	0.005	.
1	CZ 02033 5c	2.30	0.704	0.027	0.091	1.40	0.013	0.188	0.085	0.103	0.013	0.104	.	(0.002)	0.008	0.054	.
1	SRM 675	1.92	1.81	0.045	0.072	1.29	0.012	0.210	0.080	0.007	0.023	0.034	.	0.0062	0.007	0.178	0.0006
1	SRM 655/4	1.90	0.44	0.180	0.076	2.110	.	.	(1)
1	11X C4R	1.86	0.493	0.108	0.098	2.92	0.345	2.02	1.531	0.040	0.0316	0.101	0.0373	0.0102	0.080	0.0208	0.0083
1	CKD 242A	1.84	0.060	0.039	0.036	3.06	0.055	0.039	0.029	0.036	0.002	1.13	0.013	0.010	0.19	0.37	(0.00)
1	Y 2863-1	1.78	2.41	0.021	0.009	3.62	0.022	4.77	0.031	.	.	0.038	0.0052	.	0.068	1.13	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
---	--------	---	----	---	---	----	----	----	----	----	----	----	----	----	----	---	----

Number	As	B	Bi	Ca*	Ce	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
11X C5Y *	0.02	0.005	* Provisional Analysis				0.01	0.005	0.03	0.006	.	0.005	0.001	~40 mm Ø x ~15 mm
VS ChL4/1	~38 mm Ø x ~38 mm
SRM C1291	32 mm Ø x 19 mm
VS ChG 6/9	(0.003)	~38 mm Ø x ~38 mm
DSZU CH01	.	(0.03)	.	(10)	.	(0.0005)	(0.02)	.	~30 mm x ~35 mm
VS ChG 40	~40 mm Ø x ~40 mm
11X C8V *	0.078	0.035	0.01	* Provisional Analysis				.	0.065	0.020	0.005	0.026	~40 mm Ø x ~15 mm	
SRM 661/4	48 mm x 42 mm x 12 mm
SRM 656/9	48 mm x 42 mm x 12 mm
11X C7N	0.0159	0.0097	0.0137	.	.	.	0.025	0.0106	0.025	.	.	0.066	(0.003)	40 mm Ø x 15 mm
Y 2863-2	.	0.0025	30 mm Ø x 30 mm
VS ChG 37	~40 mm Ø x ~40 mm
SRM 673	0.044	40 mm x 37 mm x 10 mm
SRM 673/1	40 mm x 37 mm x 10 mm
CZ 20034 11b	0.005	0.0032	0.007	0.007	0.011	.	.	(0.005)	0.007	40 mm Ø x 18 mm
VS ChG 38	~40 mm Ø x ~40 mm
CZ 02033 5b	.	0.014	0.020	40 mm Ø x 18 mm
VS ChL2/1	~38 mm Ø x ~38 mm
CZ 20034 11a	0.005	0.0018	0.011	0.017	0.013	.	.	(0.005)	0.007	40 mm Ø x 18 mm
SRM 652/4	48 mm x 42 mm x 12 mm
DSZU CH07	.	(0.13)	.	(10)	.	(0.01)	~35 mm x ~35 mm
CZ 02033 5a	40 mm Ø x 18 mm
CZ 02033 5c	.	0.0078	0.007	(0.002)	(0.010)	.	(0.009)	40 mm Ø x 18 mm
SRM 675	0.035	40 mm x 37 mm x 10 mm
SRM 655/4	48 mm x 42 mm x 12 mm
11X C4R	0.0050	0.0086	0.0144	Ag: 0.008	.	0.0078	0.019	0.015	0.021	.	.	0.120	0.0031	~40 mm Ø x ~12 mm
CKD 242A	0.015	0.008	(0.015)	(0.00)	0.000	.	(0.012)	0.007	.	(0.08)	(0.007)	(0.000)	(0.000)	37mm x 37mm x 18 or 20mm
Y 2863-1	.	0.0024	30 mm Ø x 30 mm

Number	As	B	Bi	Ca*	Ce	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
--------	----	---	----	-----	----	----	---	----	----	----	----	---	----	-------

#	Number	ALLOYED CAST IRON					# = Class, where 1 = CRM and 2 = RM						Pb	Sn	Ti	V	Mg	N
		C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo							
2	BAS NCRM5	3.70	0.27	0.025	0.015	1.15	0.204	6.74	10.44	.	0.10	0.06	.	.
1	SRM C1292	3.47	0.55	0.049	0.016	0.59	0.36	5.04	11.4	.	0.25	.	.	.	0.041	.	.	
2	BAS CRRM5/2	3.43	0.30	0.029	0.018	0.20	0.22	0.36	30.35	0.15	0.63	.	.	0.009	0.11	.	.	
1	Y 451052-1	3.31	1.54	0.369	0.0047	0.098	0.449	2.57	1.17	.	1.47	.	.	.	0.952	.	.	
1	BS PM15	3.54	0.416	0.0198	0.0127	0.912	0.142	0.203	5.33	0.0025	1.22	(0.00001)	0.0034	0.0029	14.79	(0.0002)	0.111	
1	Y 451052-7	3.13	0.201	0.024	0.116	2.48	0.154	0.129	31.26	.	0.086	.	.	0.033	0.087	.	.	
1	11X 15309S	3.05	1.506	0.040	0.086	1.398	0.505	0.919	23.26	.	0.249	.	.	0.0156	0.056	.	.	
1	SRM C1290	3.04	0.66	0.030	0.013	0.971	0.065	0.917	30.5	.	(0.041)	.	.	.	0.442	.	.	
1	Y TSK205	3.03	0.16	0.041	0.088	1.65	0.35	0.37	30.35	.	0.22	.	.	.	0.077	.	0.108	
1	Y 451054-2	3.00	1.42	0.133	0.016	0.56	0.324	1.43	7.23	.	2.48	.	.	0.015	0.88	.	.	
1	NCS HS11788	2.97	1.62	0.191	0.010	3.29	0.51	17.77	2.56	(0.0023)	0.0013	.	0.0003	0.043	0.017	.	.	
1	Y 451052-2	2.96	1.24	0.211	0.0077	0.491	1.57	1.99	9.75	.	2.17	.	.	0.300	0.669	.	.	
2	BAS NIRM5/1	2.95	1.01	0.103	0.005	1.50	0.21	21.7	0.51	0.055	.	
2	BAS CRRM4/2	2.93	0.58	0.049	0.042	0.45	0.53	0.58	21.93	<0.005	1.15	.	.	0.008	0.11	.	.	
2	11X 20003K	2.91	1.53	0.174	0.007	3.03	0.52	17.8	2.53	
1	11X S/1 Cr3J	2.91	0.861	0.072	0.023	1.07	9.01	14.53	1.61	
2	11X 20001J	2.90	0.58	0.005	0.143	1.01	0.01	21.4	1.50	
2	11X S/2 Cr1E	2.83	1.68	0.31	0.011	2.85	0.02	16.5	2.48	
1	11X 0331-1J	2.82	1.646	0.069	0.13	2.50	7.59	12.43	0.607	0.122	0.120	0.0327	0.0439	0.1099	.	.	.	
2	BAS NIRM2/1	2.81	2.08	0.129	0.010	1.50	5.98	13.95	1.48	0.050	.	
1	Y 451054-3	2.73	1.09	0.105	0.036	0.99	0.451	1.20	12.97	.	2.08	.	.	0.045	0.66	.	.	
1	VS ChG45	(2.7)	1.01	0.096	0.047	2.96	0.040	0.60	32.65	.	0.198	.	.	0.011	0.111	.	.	
2	11X 20002J	2.67	1.06	0.060	0.045	2.04	0.30	20.0	2.03	
2	BAS NCRM4	2.66	0.40	0.203	0.012	2.13	0.68	5.34	7.94	.	0.57	.	.	.	0.11	.	.	
1	NCS HS11787	2.65	1.08	0.067	0.037	2.07	0.306	19.84	1.98	(0.085)	0.0014	.	0.0054	0.022	0.0096	.	.	
1	11X 0331-2K	2.64	1.272	0.049	0.119	2.32	6.47	14.26	1.025	0.191	0.0644	0.0205	0.0205	0.14	0.0158	.	.	
2	11X S/3 Cr1D	2.61	0.7	0.046	0.011	2.52	0.19	31.7	0.15	
1	Y TSK201	2.56	1.07	0.253	0.023	0.66	1.53	2.44	10.14	.	2.56	.	.	.	0.42	.	0.029	
1	11X 15295R	2.52	0.491	0.0504	0.0413	0.589	0.197	0.304	27.53	0.19	0.391	(0.015)	0.047	.	0.201	.	.	
2	BAS NIRM3	2.51	0.51	0.208	0.096	2.21	1.00	17.8	2.43	
2	BAS NIRM6	2.44	4.00	0.217	0.062	2.43	0.10	26.7	1.07	.	0.45	
1	Y 451052-3	2.40	1.06	0.115	0.015	0.821	0.953	1.55	13.30	.	0.869	.	.	0.171	0.482	.	.	
2	BAS CRRM3/2	2.37	0.92	0.073	0.087	1.21	1.09	1.35	18.78	0.102	1.58	.	.	0.015	0.042	.	.	
1	Y 451054-4	2.31	0.725	0.071	0.046	1.40	0.739	0.914	17.60	.	1.44	.	.	0.084	0.46	.	.	
1	11X 15294V	2.29	0.467	0.093	0.031	0.399	0.134	0.649	30.82	(0.177)	0.325	0.0084	0.0560	.	0.117	.	.	
1	CKD 251	2.25	1.97	0.015	0.015	1.14	0.38	19.7	1.07	(0.02)	0.12	(0.009)	(0.01)	(0.005)	(0.02)	0.022	.	
1	Y TSK200	2.11	0.82	0.319	0.022	0.17	1.86	3.22	4.97	.	3.50	.	.	.	0.60	.	0.021	
2	BAS NIRM1	2.05	6.72	0.055	0.005	3.15	0.20	11.80	0.246	0.021	.	
2	BAS NIRM7	2.05	0.71	0.058	0.020	3.05	0.52	32.9	3.53	.	0.99	0.019	.	
1	Y 451052-4	2.00	0.803	0.090	0.025	1.16	0.738	1.07	18.28	.	0.598	.	.	0.087	0.380	.	.	
2	BAS NIRM4	1.97	2.37	0.051	0.008	3.03	0.52	20.2	3.56	0.014	.	
1	NCS HS11789	1.97	1.08	0.048	0.076	2.58	6.39	17.80	2.51	0.061	0.062	0.015	0.014	0.011	0.0093	.	.	
2	BAS CRRM2/1	1.92	1.11	0.097	0.079	1.18	1.59	1.61	14.13	0.054	2.44	.	.	0.070	0.063	.	.	
2	BAS CRRM1/1	1.83	1.45	0.132	0.099	1.53	2.01	2.03	11.18	0.117	3.05	.	.	0.096	0.040	.	.	
1	Y 451054-5	1.83	0.466	0.043	0.091	1.80	0.904	0.517	23.40	.	0.739	.	.	0.068	0.26	.	.	
1	Y TSK202	1.81	1.16	0.201	0.057	2.00	1.10	1.91	15.42	.	2.20	.	.	.	0.33	.	0.075	
1	Y 451052-5	1.48	0.579	0.041	0.058	1.37	0.583	0.708	22.55	.	0.359	.	.	0.056	0.314	.	.	
2	BAS NIRM8/2	1.45	1.58	0.105	0.014	5.61	0.23	35.3	2.47	.	0.77	0.033	.	
1	Y 451054-6	1.45	0.254	0.024	0.123	2.38	1.15	0.216	28.96	0.084	0.13	.	.	
2	BAS NIRM8/1	1.34	1.60	0.109	0.010	5.42	0.23	35.2	2.34	.	0.75	0.043	.	
1	VS ChG44	1.24	0.87	(1.2)	0.076	1.50	2.27	0.175	25.44	.	0.035	.	.	0.104	0.079	.	.	
1	Y TSK203	1.23	0.68	0.117	0.044	0.46	0.75	1.55	19.93	.	1.58	.	.	.	0.22	.	0.094	
1	Y 451052-6	1.16	0.302	0.033	0.086	1.44	0.845	0.289	25.76	.	0.150	.	.	0.019	0.146	.	.	
1	Y TSK204	0.91	0.34	0.078	0.063	1.00	0.53	0.97	25.37	.	0.95	.	.	.	0.14	.	0.114	

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
	Number	Ce	Co	Nb	W	Zr	Units					Other					
	BAS NCRM5	40 mm x 37 mm x 10 mm										
	SRM C1292	32 mm Ø x 19 mm										
	BAS CRRM5/2	48 mm x 42 mm x 12 mm										
	Y 451052-1	B:0.177	.	0.018	0.015	.	30 mm Ø x 30 mm										
	BS PM15	.	0.0330	0.014	0.109	(0.0005)	38 mm Ø x 19+ mm					17025 Fe:[73.0] As:0.0040 N:0.111 O:0.0129					
	Y 451052-7	B:0.015	.	0.010	0.175	.	30 mm Ø x 30 mm										
	11X 15309S	.	0.032	0.0192	0.015	.	~40 mm Ø x ~15 mm										
	SRM C1290	32 mm Ø x 19 mm										
	Y TSK205	35 mm Ø x 30 mm										
	Y 451054-2	30 mm Ø x 30 mm										
	NCS HS11788	B:0.0008	(0.0063)	.	(0.0002)	.	31 mm Ø x 28 mm					As: 0.014					
	Y 451052-2	B:0.142	.	0.182	1.99	.	30 mm Ø x 30 mm										
	BAS NIRM5/1	0.016	.	0.15	.	.	48 mm x 42 mm x 12 mm										
	BAS CRRM4/2	48 mm x 42 mm x 12 mm										
	11X 20003K	40 mm Ø x 15 mm										
	11X S/1 Cr3J	~40 mm Ø x ~15 mm										
	11X 20001K	40 mm Ø x 15 mm										
	11X S/2 Cr1E	40 mm Ø x 15 mm										
	11X 0331-1J	.	0.1117	0.149	.	.	~40 mm Ø x ~15 mm										
	BAS NIRM2/1	0.015	48 mm x 42 mm x 12 mm										
	Y 451054-3	30 mm Ø x 30 mm										
	VS ChG45	~35 mm Ø x ~17 mm										
	11X 20002J	40 mm Ø x 15 mm										
	BAS NCRM4	40 mm x 37 mm x 10 mm										
	NCS HS11787	B:0.0007	(0.0054)	.	(0.0002)	.	31 mm Ø x 28 mm					As: 0.0075					
	11X 0331-2K	.	0.161	0.104	.	.	~40 mm Ø x ~15 mm										
	11X S/3 Cr1D	40 mm Ø x ~12 mm										
	Y TSK201	35 mm Ø x 30 mm										
	11X 15295R	.	1.510	(0.036)	0.195	.	~40 mm Ø x ~15 mm										
	BAS NIRM3	0.007	.	0.09	.	.	40 mm x 37 mm x 10 mm										
	BAS NIRM6	0.003	40 mm x 37 mm x 10 mm										
</																	

RM CAST IRON MUSHROOMS CONTINUED ON THE NEXT PAGE

typical analysis

each unit is one pair of 43 mm Ø x 5 mm mushroom discs

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF F019	4.04	1.05	1.05	0.032	0.057
CTIF F012	3.71	1.86	0.44	0.038	0.004	0.77	.	.	0.008	.	.	0.011	.	.	.
CTIF F08	3.6	1.04	0.37	0.107	0.021	0.215	0.30	0.30	.	.	0.005	0.05	0.055	0.014	.
CTIF FCR7	3.59	1.07	0.365	0.099	0.0427	0.704	0.947	33.65	.	.	2.62
CTIF F06	3.49	0.55	0.715	0.87	0.106	0.120	0.128	0.45	.	.	0.202	0.039	0.080	0.110	.
CTIF F010	3.5	0.67	1.05	0.20	0.101	0.114	0.118	0.38	.	.	0.20	.	0.1	0.08	.
CTIF NH3	3.47	0.85	0.175	0.36	0.024	0.031	2.53	1.76	.	.	0.73
CTIF F011	3.45	1.57	0.685	0.052	0.103	0.211	0.235	0.34	.	(0.013)	0.225	0.066	0.078	0.113	.
CTIF F018	3.43	1.24	0.590	1.34	0.136	0.049	0.140	0.170	.	.	0.179	0.046	0.057	0.102	.
CTIF NH7-1	3.43	0.95	0.63	0.035	0.022	0.105	5.53	9.02
CTIF FCR5	3.43	0.35	0.62	0.052	0.0175	1.02	2.69	28.5	.	.	3.27
CTIF FT2-1	3.39	1.415	0.78	0.045	0.095	0.01	0.070	0.030	0.100	0.405	.
CTIF NiMo1	3.22	2.585	0.200	0.0590	(0.0030)	0.376	2.165	0.0353	.	0.0205	0.457	0.0020	0.0190	0.0169	.
CTIF FL7	3.22	2.550	0.100	1.34	0.048	0.351	0.232	0.043	.	.	0.335	0.0291	0.0525	0.0796	.
CTIF FT3	3.2	1.55	0.345	0.063	0.051	0.015	0.092	0.685	0.2	0.016	.
CTIF NH7-2	3.2	1.20	0.91	0.034	0.0120	0.108	5.53	8.87
CTIF F05	3.2	0.7	0.2	1.30	0.027	0.12	0.172	0.3	.	.	0.41	0.109	0.04	0.14	.
CTIF NH9	3.13	1.24	0.65	0.087	0.029	0.203	4.11	11.70	.	.	0.059
CTIF NR Cu1	3.12	1.465	0.172	0.090	0.99	4.95	18.02	0.994	(0.095)
CTIF FL6	3.1	1.4	0.6	0.012	0.18	0.079	1.03	0.167	.	0.028	0.50	0.005	0.15	0.033	.
CTIF FL10	3.1	1.3	0.85	0.323	0.066	0.104	0.10	(0.07)	(0.03)	.	0.0335	0.028	0.045	0.048	(0.02)
CTIF FFA 1	3.090	0.0300	0.100	0.0022	0.0009	0.0622	0.0450	0.0710	.	0.0097	0.0109	.	0.0010	0.0010	.
CTIF NR 8S	3.05	1.41	4.39	0.124	0.071	14.20	0.191
CTIF F017	3.01	2.48	0.475	0.470	0.168	(0.006)	0.021	(0.016)	.	0.032	.	0.024	0.032	0.018	.
CTIF FAL 1	3.0	1.0	0.2	0.04	<0.001	0.2	0.06	0.04	2.1	.	0.015	.	0.01	.	.
CTIF NR 3L	2.99	3.05	0.72	0.088	0.052	0.26	21.58	2.97
CTIF NH1	2.98	1.35	0.90	0.060	0.105	1.99	1.38	0.83	.	.	1.45
CTIF NH8	2.98	0.80	0.57	0.052	0.076	0.065	8.16	5.03	.	.	0.125
CTIF NR 3S	2.92	2.91	0.77	0.024	0.025	0.33	24.63	3.05
CTIF FT1	2.9	2.12	0.71	0.12	0.025	0.012	0.11	0.057	.	.	.	0.067	0.19	0.525	.

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF NR 8L	2.89	1.70	5.19	0.054	0.030	0.075	13.33	0.165
CTIF NH4	2.84	0.49	0.28	0.12	0.022	0.09	3.60	2.46	.	.	0.30
CTIF F04	2.81	1.51	0.64	0.58	0.009	0.31	0.32	0.17	.	.	0.095	0.013	0.075	0.049	.
CTIF FCR2	2.86	1.07	0.740	0.137	0.055	0.135	1.87	11.8	.	.	3.88
CTIF FL5	2.8	2.3	0.4	0.02	(0.005)	0.5	0.05	0.35	.	0.010	0.01	0.07	0.01	0.01	.
CTIF FCR Ni3	2.74	0.69	0.47	0.036	0.011	.	11.05	31.65
CTIF NH6	2.70	2.28	0.355	0.066	0.036	0.115	7.06	6.60	.	.	0.11
CTIF F09	2.7	1.5	0.7	0.02	0.015	0.31	0.355	0.18	.	.	0.13	0.144	0.017	0.022	.
CTIF FL4	2.6	2.91	0.5	0.288	0.137	0.0168	0.061	0.45	.	.	0.090	0.011	0.0296	0.116	.
CTIF NR 1S	2.58	3.02	1.54	0.19	0.0015	0.11	20.60	2.00
CTIF NR 1L	2.50	3.00	1.34	0.125	0.10	0.49	25.87	1.74
CTIF NH2	2.50	1.81	1.04	0.047	0.058	1.02	1.78	1.26	.	.	1.01
CTIF NR Cu2	2.48	2.07	1.078	0.113	0.049	6.50	15.85	2.05
CTIF NR 4S	2.47	4.87	1.71	0.145	0.066	0.63	18.30	1.50
CTIF FCR4	2.47	1.40	2.05	0.097	0.066	1.32	0.571	24.2	.	.	2.16
CTIF FCR1	2.46	0.48	0.63	0.019	0.007	0.031	1.30	18.71	.	.	1.41
CTIF F07	2.45	0.675	0.70	0.84	0.085	0.125	0.15	0.455	.	.	0.26	.	0.065	0.13	.
CTIF NR 4L	2.41	5.89	1.495	0.155	0.010	0.758	15.90	1.403
CTIF NR 2S	2.32	1.43	0.530	0.062	0.0210	0.210	36.3	0.51
CTIF NH5	2.31	0.31	0.24	0.115	0.04	0.035	4.90	2.85	.	.	0.017
CTIF FL3	2.3	2.1	0.27	0.729	(0.013)	0.102	0.553	0.107	.	.	0.106	0.111	0.05	0.049	.
CTIF NR 4G	2.24	5.60	1.72	0.11	(0.002)	0.64	21.30	1.40
CTIF NR 2G	2.25	1.47	0.380	0.0476	(0.003)	0.232	36.34	0.395
CTIF FL2	2.18	3.61	0.0400	0.049	0.082	0.0497	0.0238	0.440	(0.006)	0.0263	(0.004)	0.140	0.0750	0.201	.
CTIF FL1	2.1	3.2	0.80	0.118	0.0765	0.0195	0.245	0.06	.	(0.022)	0.038	0.305	0.020	0.015	.
CTIF FCR Ni2	2.02	1.50	0.61	0.185	0.024	.	13.05	29.00
CTIF NR Cu3	1.94	3.12	0.60	0.046	0.016	8.05	13.3	3.50
CTIF NR 6S	1.82	2.44	0.99	0.019	0.03	0.03	30.75	1.06
CTIF NR 5L	1.77	2.99	1.207	0.037	0.083	0.48	33.89	0.27
CTIF NR 6L	1.76	2.07	0.70	0.031	0.063	0.020	30.37	3.49
CTIF NR 5S	1.67	1.97	1.23	0.035	.	0.50	27.05	0.24
CTIF FCR6	1.44	0.76	1.47	0.201	0.086	0.480	0.188	30.84	.	.	0.455
CTIF FCR Ni1	1.27	1.63	0.71	0.41	0.06	0.02	16.50	26.20

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
--------	---	----	----	---	---	----	----	----	----	----	----	----	----	---	---

CAST IRON MUSHROOMS

CONTINUED FROM THE PREVIOUS PAGE

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF F019	0.0005	.
CTIF F012
CTIF F08
CTIF FCR7
CTIF F06
CTIF F010
CTIF NH3
CTIF F011
CTIF F018	0.0040
CTIF NH7-1
CTIF FCR5
CTIF FT2-1
CTIF NiMo1
CTIF FL7	(0.0266)	(0.010)	.	(0.010)	.	0.0035
CTIF FT3
CTIF NH7-2
CTIF F05
CTIF NH9
CTIF NR Cu1
CTIF FL6	.	0.008
CTIF FL10	(0.022)	.	(0.012)	(0.004)	.	.	(0.018)	(0.002)	(0.032)	(0.001)	(0.029)
CTIF FFA 1	0.0109	0.0125
CTIF NR 8S
CTIF F017
CTIF FAL 1
CTIF NR 3L
CTIF NH1
CTIF NH8
CTIF NR 3S
CTIF FT1

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF NR 8L
CTIF NH4
CTIF F04	last of stock
CTIF FCR2
CTIF FL5	.	(0.002)	.	(0.0005)
CTIF FCR Ni3
CTIF NH6
CTIF F09
CTIF FL4	(0.05)	.	.	(0.003)	.	0.007
CTIF NR 1S
CTIF NR 1L
CTIF NH2
CTIF NR Cu2	(0.0079)
CTIF NR 4S
CTIF FCR4
CTIF FCR1
CTIF F07
CTIF NR 4L
CTIF NR 2S
CTIF NH5
CTIF FL3	0.008
CTIF NR 4G
CTIF NR 2G	0.27
CTIF FL2	.	.	.	(0.0135)
CTIF FL1
CTIF FCR Ni2
CTIF NR Cu3
CTIF NR 6S
CTIF NR 5L
CTIF NR 6L
CTIF NR 5S
CTIF FCR6
CTIF FCR Nil

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
--------	----	---	----	----	----	---	----	----	----	----	----

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
1.0812		ECRM 191-2D	15-5PH		BS 9622	314		IMZ 166A
1.2344		ECRM 271-1D	15-5PH		ECRM 273-1D	316	17025	BS 316C
1.2367		HRT FE2012-H	15-5PH		IARM 22C	316		IARM 5H
1.4435, 1.4436		JK 27B	17-4PH		13X PH2	316		IARM 5i
1.4765		ECRM 299-1D	17-4PH		13X PH17400	316		NILAB 500HAD
1.5415		HRT FE2012-N	17-4PH		BS 17-4PHA	316		SRM 1155A
1.6587		HRT FE2013-N	17-4PH		BS 17-4PHB	316 H		CT 316
1.7149 20MnCrS5		ECRM 187-2D	17-4PH		SRM C2400	316 H		IARM 339A
1.7160		ECRM 194-1D	17-7PH		13X PH17700	316 L		13X 31603
1.8550		ECRM 129-3D	17-7PH 25(preceded 17025)		BS 192	316 L	17025	BS 316D
1.8519		HRT FE2010-N	17-7PH 25(preceded 17025)		BS 192A	316 L	17025	BS 316E
1.8928		ECRM 194-2D	17-7PH		IARM 152C	316 L		CZ SL-2A
1005	17025	BS LC-6	182FM		BS 150	316 L		IARM 163E
1005		ECRM 064-2D	18Cr2Ni12Mn		CT ISO035A	316 L		SS 466/2
1005		RM Fe 1/5	201		BS 191	316 Ti		ECRM 284-2D
1005		SRM 1765	201		SRM 1297	317 L		BS 317L
1005		SRM 1766	20Cb3		BS 187A	317 L	25(pre-17025)	BS 9941
1005		SS 111/1	20Cb3		CT 20 Cb-3	317 L	25(pre-17025)	BS 9942
1006		BS XCCS-1	20MoCr4		ECRM 197-1D	317 L		IARM 153C
1008		ECRM 057-2D	2101		IARM 292A	318	17025	BS 2205
1009		IMZ 71	21Cr6Ni9Mn		CT ISO129A	321		13X 32100
100C6		IRSID 1747	2205	17025	BS 2205	321		BS 321C
1010		IMZ 111	2205		IARM 212D	321	17025	BS 85D
1010		IRSID 1665	2304		IARM 317A	321		IARM 6i
1011		IMZ 73	2507		IARM 301B	321		IARM 6J
1016	17025	BS 1016	253 MA	25(pre-17025)	BS 253	321		SRM 1171
1017		IMZ 112	253 MA		IARM 316A	321		SS 465/1
1017		IRSID 1664	254 SMO		13X 31254	321 - Ti		IMZ 152
1018		12X 10180B	254 SMO		IARM 302B	32750		13X NSA13
1018		12X 10180C	254 SMO		NILAB 501HAD	330		IARM 7C
1018	17025	BS 1018	255, Duplex		IARM 239B	3310		BS 1972
1018	17025	BS 2931B	255, Duplex		IARM 239C	347		13X 34700
1018		ECRM 087-1D	300M		12X 44220	347		BS 347A
1018		IARM 28K	300M	17025	BS 300	347		BS 347B
1020	17025	BS 1020	300M		IARM 340A	347		IARM 8G
1026	17025	BS 1026	301		IARM 289A	347		IARM 8H
1026		IARM 359A	301		IRSID 1819	347		IARM 8i
1030	17025	BS 1030	302		IARM 241D	347 H		BS 87F
1030		IARM 209D	302 HQ		IARM 234C	348		SRM 1172
1033		IRSID 1663	303		13X 30300	355	17025	BS 355
1035		BS 1035	303	17025	BS 303	355		IARM 335A
1035		IRSID 1645	303		CT 303	35MV7		IRSID 1750
1035		IARM 360A	303		CZ SP-1A	405		SRM 1295
1039		IRSID 1637	303 Se		IARM 253A	409 + Cr		NCS HS20743
1040		12X 10400	303 Se		IARM 253B	410	25(pre-17025)	BS 0021
1040	17025	BS 3941	304		IARM 2H	410	17025	BS 410C
1040		IARM 210D	304 H		13X NSB1	410		CT 410
1040		IRSID 1657	304 H		CT 304	410 + Mo		ECRM 296-1D
1042		IRSID 1656	304 H		SS 468/1	410 + Mo		IMZ 161
1042		NM EN-8	304 L	17025	BS 304	410 H		13X 41001
1043		IRSID 1652	304 L	17025	BS 304A	410, F6NM	25(pre-17025)	BS 0022
1045		BS 56E	304 L	17025	BS 304B	4130	17025	BS 4130
1045	17025	BS 56H	304 L		BS SS3951	4130		IARM 143F
1045		IARM 200D	304 L		IARM 162D	4130		IPT 501
1045		IPT 503	304 L		ECRM 287-1D	4130		SRM 1225
1050		IARM 254A	304 L		ECRM 292-1D	4140		12X 41400
1055		NM 3405.01	304 L		IARM 162C	4140	25(pre-17025)	BS 1962
1060		IARM 373A	304 L		SS 463/1	4140		IARM 30H
1069		ECRM 059-2D	305		CT 305	4140		IARM 30J
1078		ECRM 056-2D	305		CT X52353	4140 Bi		BS 4140A
1078		SRM 1224	305		ECRM 297-1D	4140 Bi		BS 4140B
1090		SS 602/2	308		DSZU C017	41L40MOD	17025	BS 70B
1095		SRM 1227	309		13X 30908	41L40MOD		BS 70C
1117 25(preceded 17025)		BS 3993	309		BS 82D	4150 Bi & S		BS 4150MOD
1117		BS 65C	309		BS 82E	4150 S	17025	BS 42
1117		IARM 29E	309		IARM 3E	4150 S		BS 42A
1118		IARM 307A	310		13X 31008	416		BS 90F
1140 P		BS 52D	310		BS 83G	416	17025	BS 416
1141		BS 66B	310	25(pre-17025)	BS 9841	416		CT 416
1141		IARM 348A	310	25(pre-17025)	BS 9842	416		IARM 10D
1144	17025	BS 1144	310		CZ SL-3A	416		SRM 1223
1144	17025	BS 1144A	310		IARM 4E	416 H		13X 41600
1144		IARM 199C	310		IARM 4F	416 Se		BS 151
11L17	17025	BS 75F	310		IARM 4G	41CAD7		IRSID 1749
11L17	17025	BS 75G	310		SS 464/1	41L40	17025	BS 70B
1215	17025	BS 66L	3115		BS XCCT	41L50	17025	BS 72B
1215		IARM 206B	314		IMZ 165	42		CT ISO138A
12L14	17025	BS 74C				42		CT ISO139A
12L14		IARM 183C				420		BS SS4951
12Mn18Cr		BS 193				420		BS SS4952
1345		BS XCCV				420		ECRM 272-1D
13-8PH		13X PH13800				420		IARM 154B
13-8PH		BS 184A				420		IARM 154C
13-8PH		CT X92834				420		SS 469
1429		ECRM 058-2D				420 F		BS 152
1513		IMZ 76				420 F S		IARM 352A
1526 MOD		SRM 1269				422		13X 42200
1541		IARM 349A				422	17025	BS 422
1541		IPT 504				422		IARM 205D
1541		IRSID 1648				430	17025	BS 430
1544		IRSID 1644				430		IARM 11D
15-5PH		BS 185A				430		NCS HS20742
15-5PH		BS 9621				430 F		BS 153
						430 F		BS 154

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
430 F S		IARM 355A	CD3MN		13X NSA5	Invar 42		14X 94100
431	17025	BS 431	CD3MN		ECRM 298-1D	ISO 898-1		SS 457/2
431		BS 92B	CD6MN		VS LG58	KOVAR	17025	BS 160A
431		IARM 12C	CF-3		IRSID 1820	KOVAR		IARM 98B
431		HRT FE2010-H	CLA1		IARM 164A	L-2, 6150		BS 43A
431		SRM 1219	CLA11		IARM 180A	L-6	17025	BS 39B
4320		BS 3961	CLA5		IARM 168A	L-6		IARM 43B
4330 MOD		BS 4330V	CLA9		IARM 172A	LDX2101		13X 32101
4330 MOD		IARM 330B	CPM15V	17025	BS PM15	LF-2		BS 2931B
4340	17025	BS 4340	Custom 450	25(pre-17025)	BS 9811	LF-2	17025	BS LF2B
4340	17025	BS 4340A	Custom 450	25(pre-17025)	BS 9812	LF-2		SS 601/2
4340		IARM 31G	Custom 450		CT 450	LF-3		BS LF3
440 C		13X 44004	Custom 450		IARM 15B	M-1		CT M1
440 C	17025	BS 93F	Custom 455		BS SS1961	M-1		IARM 304A
440 C		IARM 13D	Custom 455		BS SS1962	M-10		CT M10
440 F		BS 155	Custom 455		CT 455	M-10		IARM 324A
440 F Se		BS 156	Custom 455		IARM 16C	M-152		13X 64152
440 F Se		IARM 353A	Custom 465		CT ISO123A	M-152		IARM 291A
446		BS 94C	Custom 630		CT 630	M-2		CT M2
450		IARM 15C	D-2		BS 37G	M-2		IARM 44C
455		13X 45500	D-2		CT D2	M-2		SRM 1157
446		IARM 14C	D-2		IARM 41D	M-35		IARM 320A
4615		BS 3962	D-3, D-4		ECRM 288-1D	M-4		IARM 251A
4620		BS 4620	D-6	17025	BS D-6	M-42		SS 487/1
4620		BS 51F	D6-AC		IARM 299A	M-47	17025	BS M-47
4620		IARM 33D	Duplex		13X NSA9	M-50	17025	BS M-50
465		13X 46500	Duplex	17025	BS 2205	M-50		IARM 306B
465		IARM 354A	Duplex		IMZ 163A	M-7		CT M7
4820	17025	BS 4820A	Duplex		IMZ 164	Maraging 250		CT 250
4820		IARM 155F	E52100		BS 2952	Maraging 300		CT 300
5160		IMZ 116	E52100		BS 53G	MaragingA538C	25(pre17025)	BS 161A
6150		BS 4941	E52100		IARM 49D	Mold Steel	17025	BS PP20
6150		IARM 34C	E52100		IARM 49E	NIT 135M		IARM 305B
6418		BS 6418	E52100 Bi		BS 53MOD	Nitriding 135G		BS 68B
6418		BS 69B	Elect./ Magnetic		SRM 1159	Nitriding 135G	17025	BS 68E
6526		BS 9-4-30	Electrolytic		SRM 1265a	Nitronic 40		13X NSC6
709		CT X67975	F-11		BS 45A	Nitronic 40		BS 190
800	17025	BS 800	F-11	17025	BS 45B	Nitronic 40		IARM 19C
8620		BS 8620A (XRF)	F-11		IARM 35L	Nitronic 50		BS 180A
8620	17025	BS 8620E	F-2		CT X27081	Nitronic 50	17025	BS 180B
8620		BS 8620F	F-22	17025	BS 46B	Nitronic 50		IARM 17D
8620		IPT 502	F-22	25(preceeded 17025)	BS 1982	Nitronic 60		13X 21800
86L20 25(preceeded 17025)		BS 73B	F-22		IARM 36C	Nitronic 60		BS 181A
86L20		BS 73C	F-22		SRM 1270	Nitronic 60	17025	BS 181B
86L20		IARM 182B	F-22 + Cr		HRT FE2009-N	NMS 100		IARM 214A
8740	17025	BS 67C	F-5		BS 47A	NMS 140		IARM 295A
8740		IARM 252C	F-5		BS 47B	NMS J38		IARM 294A
8740		IARM 252D	F-5		IARM 37C	O-1	17025	BS 35D
8740		IARM 252E	F-51	17025	BS 2205	O-1		CT O1
8740		IARM 252F	F-9	17025	BS 48B	O-6	17025	BS 41
904L		13X NSA12	F-91	25(preceeded 17025)	BS 9905	O-6	25(preceeded 17025)	BS 41A
904L		ECRM 295-1D	F-91	17025	BS 9905A	O-6		IARM 45A
9310		BS 58C	Ferallium 255	17025	BS 179B	O-6		IARM 45B
9310		BS 58E	Ferallium 255	17025	BS 179C	P-6, HY100		BS 1972
9325	17025	BS 9325A	Greek Ascoloy		BS 183A	P-20		BS 55G
9-4-30		IARM 341A	Greek Ascoloy		IARM 20B	PP-20	17025	BS PP20
A-10		BS A-10	Greek Ascoloy		IARM 20C	Permendur 2V		IARM 326A
A-11		BS 10V	H-10		BS 49	RA330		BS 86F
A-11	17025	BS A-11	H-11		ECRM 276-2D	S-1		BS 33D
A-106 Gr B		SRM 1228	H-11		IARM 255A	S-1		BS 33E
A-193 B16		BS 4942	H-11		IARM 255B	S-1		IARM 46B
A-193 B16	17025	BS 4942A	H-11		IMZ 173	S-5		BS 38C
A-2		BS 36D	H-13	17025	BS H-13	S-5		IARM 47B
A-2		CT A2	H-13		CT H13	S-7		IARM 259A
A-2		IARM 39B	H-13		IARM 42C	S-7		SRM 1772
A-2		IARM 39C	H-13		IMZ 174	SA213-T22		IMZ 159
A-20		BS 187C	H-19	17025	BS H-19	SA213-T22		IMZ 160
A-242		IPT 500	HC 250+V		SRM C1290	SA213-T22		IMZ 169
A-242 Mod		SRM C1285	High Perm		CT ISO124A	SAE G2500		BS 20E
A-286		BS 188A	High Perm		CT ISO136A	STA 361		IARM 268B
A-286	17025	BS 188B	High Perm 49		CT ISO141A	T-1		14X HS1
A-286		SRM 1230	HSLA 100		SRM 1271	T-1	17025	BS 30D
A-36	17025	BS 2931B	HY 130		SRM 1226	T-1		IARM 48C
A-36		IARM 213C	HY 80		SRM 1286	T-4		IARM 281A
A-36		IARM 213D	Hy-Tuff		IARM 342A	T-15	17025	BS TS15
A-36		SRM 1767	Invar		14X 93603	VMI2		IMZ 196
A-485-1		BS A485-1	Invar-36 + Se		BS 186A	W-5		14X 72305
A-6		BS 40B	Invar-36 + Se		IARM 24B	Z30C13		IRSID 1825
A-6		IARM 40B				Zeron 100, Duplex		13X NSA8
A-6		IARM 40C				Zeron 100, Duplex		IARM 319A
A706-60		IARM 380A						
A706-60		IARM 380B						
A706-80		IARM 381A						
Aermet 100		CT ISO045A						
Aermet 100		IARM 242A						
AL6XN	17025	BS 189A						
AL6XN		IARM 157D						
C-.5Mo		BS 3952						
C-.5Mo		IARM 229B						
C-250		IARM 308A						
C-350		IARM 309A						
CA6NM		HRT FE2009-H						
CA6NM		IARM 327A						

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S
1005	<0.06	<0.35	<0.03	<0.05
1006	<0.08	0.25-0.40	<0.03	<0.05
1008	<0.10	0.30-0.50	<0.03	<0.05
1009	<0.15	<0.60	<0.03	<0.05
1010	0.08-0.13	0.30-0.60	<0.03	<0.05
1011	0.09-0.14	0.60-0.90	<0.03	<0.05
1012	0.10-0.15	0.30-0.60	<0.03	<0.05
1013	0.11-0.16	0.50-0.80	<0.03	<0.05
1015	0.13-0.18	0.30-0.60	<0.03	<0.05
1016	0.13-0.18	0.60-0.90	<0.03	<0.05
1017	0.15-0.20	0.30-0.60	<0.03	<0.05
1018	0.15-0.20	0.60-0.90	<0.03	<0.05
1019	0.15-0.20	0.70-1.00	<0.03	<0.05
1020	0.18-0.23	0.30-0.60	<0.03	<0.05
1021	0.18-0.23	0.60-0.90	<0.03	<0.05
1022	0.18-0.23	0.70-1.00	<0.03	<0.05
1023	0.20-0.25	0.30-0.60	<0.03	<0.05
1025	0.22-0.28	0.30-0.60	<0.03	<0.05
1026	0.22-0.28	0.60-0.90	<0.03	<0.05
1029	0.25-0.31	0.60-0.90	<0.03	<0.05
1030	0.28-0.34	0.60-0.90	<0.03	<0.05
1033	0.29-0.36	0.70-1.00	<0.03	<0.05
1034	0.32-0.38	0.50-0.80	<0.03	<0.05
1035	0.32-0.38	0.60-0.90	<0.03	<0.05
1037	0.32-0.38	0.70-1.00	<0.03	<0.05
1038	0.35-0.42	0.60-0.90	<0.03	<0.05
1039	0.37-0.44	0.70-1.00	<0.03	<0.05
1040	0.37-0.44	0.60-0.90	<0.03	<0.05
1042	0.40-0.47	0.60-0.90	<0.03	<0.05
1043	0.40-0.47	0.70-1.00	<0.03	<0.05
1044	0.43-0.50	0.30-0.60	<0.03	<0.05
1045	0.43-0.50	0.60-0.90	<0.03	<0.05
1046	0.43-0.50	0.70-1.00	<0.03	<0.05
1049	0.46-0.53	0.60-0.90	<0.03	<0.05
1050	0.48-0.55	0.60-0.90	<0.03	<0.05
1053	0.48-0.55	0.70-1.00	<0.03	<0.05
1055	0.50-0.60	0.60-0.90	<0.03	<0.05
1059	0.55-0.65	0.50-0.80	<0.03	<0.05
1060	0.55-0.65	0.60-0.90	<0.03	<0.05
1064	0.60-0.70	0.50-0.80	<0.03	<0.05
1065	0.60-0.70	0.60-0.90	<0.03	<0.05
1069	0.65-0.75	0.40-0.70	<0.03	<0.05
1070	0.65-0.75	0.60-0.90	<0.03	<0.05
1074	0.70-0.80	0.50-0.80	<0.03	<0.05
1078	0.72-0.85	0.30-0.60	<0.03	<0.05
1080	0.75-0.88	0.60-0.90	<0.03	<0.05
1084	0.83-0.93	0.60-0.90	<0.03	<0.05
1085	0.80-0.94	0.70-1.00	<0.03	<0.05
1086	0.80-0.93	0.30-0.50	<0.03	<0.05
1090	0.85-0.98	0.60-0.90	<0.03	<0.05
1095	0.90-1.03	0.30-0.50	<0.03	<0.05
Number	C	Mn	P	S

CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si
1513	0.10-0.16	1.10-1.40	<0.03	<0.05	.
1522	0.18-0.24	1.10-1.40	<0.04	<0.05	.
1524	0.19-0.25	1.35-1.65	<0.04	<0.05	.
1526	0.22-0.29	1.10-1.40	<0.04	<0.05	.
1527	0.22-0.29	1.20-1.50	<0.04	<0.05	.
1533	0.30-0.37	1.10-1.40	<0.04	<0.05	.
1534	0.30-0.37	1.20-1.50	<0.04	<0.05	.
1541	0.36-0.44	1.35-1.65	<0.04	<0.05	.
1544	0.40-0.47	0.80-1.10	<0.04	<0.05	.
1545	0.43-0.50	0.80-1.10	<0.04	<0.05	.
1546	0.44-0.52	1.00-1.30	<0.04	<0.05	.
1548	0.44-0.52	1.10-1.40	<0.04	<0.05	.
1552	0.47-0.55	1.20-1.50	<0.04	<0.05	.
1553	0.48-0.55	0.80-1.10	<0.04	<0.05	.
1566	0.60-0.70	0.85-1.15	<0.04	<0.05	.
1570	0.65-0.75	0.80-1.10	<0.04	<0.05	.
1580	0.75-0.88	0.80-1.10	<0.04	<0.05	.
1590	0.85-0.98	0.80-1.10	<0.04	<0.05	.
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30

Number	C	Mn	P	S	Si
--------	---	----	---	---	----

RESULFURIZED STEEL SPECIFICATIONS

Number	C	Mn	P	S
1108	0.08-0.13	0.50-0.80	<0.04	0.08-0.13
1109	0.08-0.13	0.60-0.90	<0.04	0.08-0.13
1110	0.08-0.13	0.30-0.60	<0.04	0.08-0.13
1116	0.14-0.20	1.10-1.40	<0.04	0.16-0.23
1117	0.14-0.20	1.00-1.30	<0.04	0.08-0.13
1118	0.14-0.20	1.30-1.60	<0.04	0.08-0.13
1119	0.14-0.20	1.00-1.30	<0.04	0.24-0.33
1123	0.20-0.27	1.20-1.50	<0.04	0.06-0.09
1132	0.27-0.34	1.35-1.65	<0.04	0.09-0.13
1137	0.32-0.39	1.35-1.65	<0.03	0.08-0.13
1139	0.35-0.43	1.35-1.65	<0.04	0.13-0.20
1140	0.37-0.44	0.70-1.00	<0.03	0.08-0.13
1141	0.37-0.45	1.35-1.65	<0.03	0.08-0.13
1144	0.40-0.48	1.35-1.65	<0.03	0.24-0.33
1145	0.41-0.49	0.70-1.00	<0.04	0.08-0.13
1146	0.42-0.49	0.70-1.00	<0.04	0.08-0.13
1151	0.48-0.55	0.70-1.00	<0.04	0.08-0.13
1152	0.48-0.55	0.70-1.00	<0.04	0.06-0.09
1211	<0.13	0.60-0.90	0.07-0.12	0.10-0.15
1212	<0.13	0.70-1.00	0.07-0.12	0.16-0.23
1213	<0.13	0.70-1.00	0.07-0.12	0.24-0.33
1215	<0.09	0.75-1.05	0.04-0.09	0.26-0.35

Number	C	Mn	P	S
--------	---	----	---	---

These are specifications,
not samples for sale.

LOW ALLOY STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other
1330	0.28-0.33	1.60-1.90	<0.035	<0.04	0.15-0.35
1335	0.33-0.38	1.60-1.90	<0.035	<0.04	0.15-0.35
1340	0.38-0.43	1.60-1.90	<0.035	<0.04	0.15-0.35
1345	0.43-0.48	1.60-1.90	<0.035	<0.04	0.15-0.35
3140	0.38-0.43	0.70-0.90	<0.04	<0.04	0.15-0.35	1.10-1.40	0.55-0.75	.	.	.
4023	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4027	0.25-0.30	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4028	0.25-0.30	0.70-0.90	<0.035	0.035-0.050	0.15-0.35	.	.	0.20-0.30	.	.
4037	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4047	0.45-0.50	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4118	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.08-0.15	.	.
4120	0.18-0.23	0.80-1.20	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.15-0.25	.	.
4121	0.18-0.23	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.45-0.65	0.15-0.25	.	.
4130	0.28-0.33	0.40-0.60	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4135	0.33-0.38	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4137	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4140	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L40	0.38-0.43	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4142	0.40-0.45	0.45-0.65	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4145	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4147	0.45-0.50	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4150	0.48-0.53	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L50	0.48-0.53	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4320	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	0.40-0.60	0.20-0.30	.	.
4340	0.38-0.43	0.60-0.80	<0.035	<0.04	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
4615	0.13-0.18	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4617	0.15-0.20	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4620	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4715	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.70-1.00	0.45-0.65	0.45-0.65	.	.
4720	0.17-0.22	0.50-0.70	<0.035	<0.04	0.15-0.35	0.90-1.20	0.35-0.55	0.15-0.25	.	.
4815	0.13-0.18	0.40-0.60	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
4820	0.18-0.23	0.50-0.70	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
50B46	0.44-0.49	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.20-0.35	.	.	B: 0.0005-0.003
5120	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51L20	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	0.15-0.35	.
5130	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	.
5132	0.30-0.35	0.60-0.80	<0.035	<0.04	0.15-0.35	.	0.75-1.00	.	.	.
5140	0.38-0.43	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5160	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51B60	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	B: >0.0005
6150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	V: >0.15
8615	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8617	0.15-0.20	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8620	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
86L20	0.18-0.21	0.70-0.90	<0.035	0.02-0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	0.15-0.35	.
8622	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8630	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8637	0.35-0.40	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8640	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8645	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8720	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8740	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8822	0.20-0.25	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.30-0.40	.	.
9259	0.56-0.64	0.75-1.00	<0.035	<0.04	0.70-1.10	.	0.45-0.65	.	.	.
9260	0.56-0.64	0.75-1.00	<0.035	<0.04	1.80-2.20
E4340	0.38-0.43	0.65-0.85	<0.025	<0.025	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
E51100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	0.90-1.15	.	.	.
E52100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	1.30-1.60	.	.	.
E9310	0.08-0.13	0.45-0.65	<0.025	<0.025	0.15-0.35	3.00-3.50	1.00-1.40	0.08-0.15	.	.
F-11	0.10-0.20	0.30-0.80	<0.04	<0.04	0.50-1.00	.	1.00-1.50	0.44-0.65	.	.
F-22	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	2.00-2.50	0.90-1.10	.	.
F-5	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	4.00-6.00	0.45-0.65	.	.
F-9	<0.15	0.30-0.60	<0.03	<0.03	0.50-1.0	.	8.00-10.00	0.90-1.10	.	.
F-91	0.08-0.12	0.30-0.60	<0.02	<0.01	0.20-0.50	<0.40	8.00-9.50	0.85-1.05	.	Al: <0.04 N: 0.03-0.07
F-91	continued									Nb: 0.06-0.10 V: 0.18-0.25
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30
LF3	<0.20	<0.90	<0.035	<0.04	0.20-0.35	3.25-3.75
Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other

These are specifications,
not samples for sale.

TOOL STEEL SPECIFICATIONS

* notes optional chemistry

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
A-2	0.95-1.05	<1.00	<0.03	<0.03	<0.50	.	4.75-5.50	.	0.90-1.40	0.15-0.50	.	.
A-4	0.95-1.05	1.80-2.20	<0.03	<0.03	<0.50	.	0.90-2.20	.	0.90-1.40	.	.	.
A-6	0.65-0.75	1.80-2.50	<0.03	<0.03	<0.50	.	0.90-1.20	.	0.90-1.40	.	.	.
A-7	2.00-2.85	<0.80	<0.03	<0.03	<0.50	.	5.00-5.75	.	0.90-1.40	3.90-5.15	0.50-1.50	.
A-8	0.50-0.60	<0.50	<0.03	<0.03	0.75-1.10	.	4.75-5.50	.	1.15-1.65	.	1.00-1.50	.
A-9	0.45-0.55	<0.50	<0.03	<0.03	0.95-1.15	1.25-1.75	4.75-5.50	.	1.30-1.80	0.80-1.40	.	.
A-10	1.25-1.50	1.60-2.10	<0.03	<0.03	1.00-1.50	1.55-2.05	.	.	1.25-1.75	.	.	.
A-11	2.45	0.50	.	.	0.90	.	5.25	.	1.30	9.75	.	.
D-2	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	<1.00	0.70-1.20	<1.10	.	.
D-3	2.00-2.35	<0.60	<0.03	<0.03	<0.60	.	11.00-13.50	.	.	<1.00	<1.00	.
D-4	2.05-2.40	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	.	0.70-1.20	<1.00	.	.
D-5	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	2.50-3.50	0.70-1.20	<1.00	.	.
D-7	2.15-2.50	<0.60	<0.03	<0.03	<0.60	.	11.50-13.50	.	0.70-1.20	3.80-4.40	.	.
H-10	0.35-0.45	0.25-0.70	<0.03	<0.03	0.80-1.20	.	3.00-3.75	.	2.00-3.00	0.25-0.75	.	.
H-11	0.33-0.43	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.60	0.30-0.60	.	.
H-12	0.30-0.40	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.25-1.75	<0.50	1.00-1.70	.
H-13	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.75	0.80-1.20	.	.
H-14	0.35-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	.	.	4.00-5.25	.
H-19	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.00-4.75	4.00-4.50	0.30-0.55	1.75-2.20	3.75-4.50	4.00-5.25
H-21	0.26-0.36	0.15-0.40	<0.03	<0.03	0.15-0.50	.	3.00-3.75	.	.	0.30-0.60	8.50-10.00	.
H-22	0.30-0.40	0.15-0.40	<0.03	<0.03	0.15-0.40	.	1.75-3.75	.	.	0.25-0.50	10.00-11.75	.
H-23	0.25-0.35	0.15-0.40	<0.03	<0.03	0.15-0.60	.	11.00-12.75	.	.	0.75-1.25	11.00-12.75	.
H-24	0.42-0.53	0.15-0.40	<0.03	<0.03	0.15-0.40	.	2.50-3.50	.	.	0.40-0.60	14.00-16.00	.
H-26	0.45-0.55	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-4.50	.	.	0.75-1.25	17.25-19.00	.
H-42	0.55-0.70	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
L-2	0.45-1.00	0.10-0.90	<0.03	<0.03	<0.50	.	0.70-1.20	.	<0.25	0.10-0.30	.	.
L-6	0.65-0.75	0.25-0.80	<0.03	<0.03	<0.50	1.25-2.00	0.60-1.20	.	<0.50	.	.	.
M-1	0.78-0.88	0.15-0.40	<0.03	<0.03	0.20-0.50	.	3.50-4.00	.	8.20-9.20	1.00-1.35	1.40-2.10	.
M-2	0.78-1.05	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
M-3.1	1.00-1.10	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.25-2.75	5.00-6.75	.
M-3.2	1.15-1.25	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.75-3.25	5.00-6.75	.
M-4	1.25-1.40	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.75	.	4.25-5.50	3.75-4.50	5.25-6.50	.
M-6	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	11.00-13.00	4.50-5.50	1.30-1.70	3.75-4.75	.
M-7	0.97-1.05	0.15-0.40	<0.03	<0.03	0.20-0.55	.	3.50-4.00	.	8.20-9.20	1.75-2.25	1.40-2.10	.
M-10	0.84-1.05	0.10-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	7.75-8.50	1.80-2.20	.	.
M-30	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.25	4.50-5.50	7.75-9.00	1.00-1.40	1.30-2.30	.
M-33	0.85-0.92	0.15-0.40	<0.03	<0.03	0.25-0.55	.	3.50-4.00	7.75-8.75	9.00-10.00	1.00-1.35	1.30-2.10	.
M-34	0.85-0.92	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.00	7.75-8.75	7.75-9.20	1.90-2.30	1.40-2.10	.
M-36	0.80-0.90	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	7.75-8.75	4.50-5.50	1.75-2.25	5.50-6.50	.
M-41	1.05-1.15	0.20-0.60	<0.03	<0.03	0.15-0.50	.	3.75-4.50	4.75-5.75	3.25-4.25	1.75-2.25	6.25-7.00	.
M-42	1.05-1.15	0.15-0.40	<0.03	<0.03	0.15-0.65	.	3.50-4.25	7.75-8.75	9.00-10.00	0.95-1.35	1.15-1.85	.
M-46	1.22-1.30	0.20-0.40	<0.03	<0.03	0.40-0.65	.	3.70-4.20	7.80-8.80	8.00-8.50	3.00-3.30	1.90-2.20	.
M-48	1.50	3.75	9.00	5.25	3.10	10.0	.
M-52	0.90	4.00	.	4.00	2.00	1.25	.
M-61	1.60	4.00	.	6.50	5.00	12.0	.
M-62	1.30	3.75	.	10.5	2.00	6.25	.
O-1	0.85-1.00	1.00-1.40	<0.03	<0.03	<0.50	.	0.40-0.60	.	.	<0.30	0.40-0.60	.
O-2	0.85-0.95	1.40-1.80	<0.03	<0.03	<0.50	.	<0.35	.	<0.30	<0.30	.	.
O-6	1.25-1.55	0.30-1.10	<0.03	<0.03	0.55-1.50	.	<0.30	.	0.20-0.30	.	.	.
O-7	1.10-1.30	<1.00	<0.03	<0.03	<0.60	.	0.35-0.85	.	<0.30	<0.40	1.00-2.00	.
P-20	0.28-0.40	0.60-1.00	<0.03	<0.03	0.20-0.80	.	1.40-2.00	.	0.30-0.55	.	.	.
P-21	0.18-0.22	0.20-0.40	<0.03	<0.03	0.20-0.40	4.00-4.25	0.20-0.30	.	.	0.15-0.25	.	Al: 1.05-1.25
P-6	0.05-0.15	0.35-0.70	<0.03	<0.03	0.10-0.40	3.25-3.75	1.25-1.75
S-1	0.40-0.55	0.10-0.40	<0.03	<0.03	0.15-1.20	.	1.00-1.80	.	<0.50	0.15-0.30	1.50-3.00	.
S-2	0.40-0.55	0.30-0.50	<0.03	<0.03	0.90-1.20	.	.	.	0.30-0.60	<0.50	.	.
S-4	0.50-0.65	0.60-0.95	<0.03	<0.03	1.75-2.25	.	<0.35	.	.	<0.35	.	.
S-5	0.50-0.65	0.60-1.00	<0.03	<0.03	1.75-2.25	.	<0.35	.	0.20-1.35	<0.35	.	.
S-6	0.40-0.50	1.20-1.50	<0.03	<0.03	2.00-2.50	.	1.20-1.50	.	0.30-0.50	0.20-0.40	.	.
S-7	0.45-0.55	0.20-0.80	<0.03	<0.03	0.20-1.00	.	3.00-3.50	.	1.30-1.80	0.20-0.30*	.	.
T-1	0.65-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	.	.	0.90-1.30	17.25-18.25	.
T-15	1.50-1.60	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-5.00	4.75-5.25	<1.00	4.50-5.25	11.75-13.00	.
T-4	0.70-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	0.80-1.20	17.50-19.00	.
T-5	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-5.00	7.00-9.50	0.50-1.25	1.80-2.40	17.50-19.00	.
T-6	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	4.00-4.75	11.00-13.00	0.40-1.00	1.50-2.10	18.50-21.00	.
T-8	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	1.80-2.40	13.25-14.75	.
W-1	0.70-1.50	0.10-0.40	<0.025	<0.025	0.10-0.40	<0.20	<0.15	.	<0.10	<0.10	<0.15	Cu: <0.20
W-2	0.85-1.50	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	<0.15	.	<0.10	0.15-0.35	<0.15	Cu: <0.20
W-5	1.05-1.15	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	0.40-0.60	.	<0.10	<0.10	<0.15	Cu: <0.20
Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other

These are specifications,
not samples for sale.

STAINLESS AND HIGH ALLOY STEEL SPECIFICATIONS

* notes optional chemistry

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	N	Nb	Other
13-8PH	<0.05	<0.20	<0.01	<0.008	<0.10	.	7.50-8.50	12.25-13.25	2.00-2.50	<0.01	.	Al: 0.90-1.35
15-5PH	<0.07	<1.00	<0.04	<0.03	<1.00	2.50-4.50	3.50-5.50	14.00-15.50	.	.	0.15-0.45	
17-4PH	<0.07	<1.00	<0.04	<0.03	<1.00	3.00-5.00	3.00-5.00	15.00-17.50	.	.	0.15-0.45	
201	<0.15	5.5-7.5	<0.060	<0.03	<1.00	.	3.50-5.50	16.00-18.00	.	<0.25	.	
202	<0.15	7.5-10.0	<0.060	<0.03	<1.00	.	4.00-6.00	17.00-19.00	.	<0.25	.	
301	<0.15	<2.00	<0.045	<0.03	<1.00	.	6.00-8.00	16.00-18.00	.	.	.	
302	<0.15	<2.00	<0.045	<0.03	<1.00	.	8.00-10.00	17.00-19.00	.	.	.	
302B	<0.15	<2.00	<0.045	<0.03	2.00-3.00	.	8.00-10.00	17.00-19.00	.	.	.	
303	<0.15	<2.00	<0.20	>0.15	<1.00	.	8.00-10.00	17.00-19.00	<0.60*	.	.	Zr: <0.60*
304	<0.08	<2.00	<0.045	<0.03	<1.00	.	8.00-10.50	18.00-20.00	.	.	.	
304L	<0.03	<2.00	<0.045	<0.03	<1.00	.	8.00-12.00	18.00-20.00	.	.	.	
305	<0.12	<2.00	<0.045	<0.03	<1.00	.	10.00-13.00	17.00-19.00	.	.	.	
308	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-12.00	19.00-21.00	.	.	.	
309	<0.20	<2.00	<0.045	<0.03	<1.00	.	12.00-15.00	22.00-24.00	.	.	.	
310	<0.25	<2.00	<0.045	<0.03	<1.50	.	19.00-22.00	24.00-26.00	.	.	.	
314	<0.25	<2.00	<0.045	<0.03	1.50-3.00	.	19.00-22.00	23.00-26.00	.	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316L	<0.03	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
321	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-12.00	17.00-19.00	.	.	.	Ti: >5xC
347	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	
348	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	Ta: <0.10
384	<0.08	<2.00	<0.045	<0.03	<1.00	.	17.00-19.00	15.00-17.00	.	.	.	
385	<0.08	<2.00	<0.045	<0.03	<1.00	.	14.00-16.00	11.50-13.50	.	.	.	
403	<0.15	<1.00	<0.04	<0.03	<0.50	.	.	11.50-13.00	.	.	.	
405	<0.08	<1.00	<0.04	<0.03	<1.00	.	.	11.50-14.50	.	.	.	Al: 0.10-0.30
409	<0.08	<1.00	<0.04	<0.01	<1.00	.	<0.50	10.50-11.75	.	.	.	Ti: 6\mtC-0.75
410	<0.15	<1.00	<0.04	<0.03	<1.00	.	.	11.50-13.50	.	.	.	
414	<0.15	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	11.50-13.50	.	.	.	
416	<0.15	<1.25	<0.06	>0.15	<1.00	.	.	12.00-14.00	<0.60*	.	.	Zr: <0.60*
420	>0.15	<1.00	<0.04	<0.03	<1.00	.	.	12.00-14.00	.	.	.	
422	0.20-0.25	<1.00	<0.04	<0.03	<0.75	<0.50	0.50-1.00	11.00-12.50	0.75-1.25	.	.	V: 0.15-0.30
422	continued											W: 0.75-1.25
430	<0.12	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	.	.	.	
430F	<0.12	<1.25	<0.06	>0.15	<1.00	.	.	16.00-18.00	<0.60*	.	.	Zr: <0.60*
431	<0.20	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	15.00-17.00	.	.	.	
440A	0.60-0.75	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440B	0.75-0.95	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440C	0.95-1.20	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
450	<0.05	<1.00	<0.03	<0.03	<1.00	1.25-1.75	5.00-7.00	14.00-16.00	0.50-1.00	.	8\mtC	
455	<0.05	<0.50	<0.04	<0.03	<0.50	1.50-2.50	7.50-9.50	11.00-12.50	<0.50	.	0.10-0.50	Ti: 0.80-1.40
501	>0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
502	<0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
Duplex	<0.05	<3.00	<0.035	<0.03	<1.50	<2.50*	4.00-7.00	18.00-25.00	0.20-5.50	<0.40	.	

These are specifications,
not samples for sale.