

INDEX

BISMUTH 1

HARD LEAD 4

SILVER 12, 13

SILVER ALLOYS 13

CADMIUM 1

JEWELRY 12

CHROMIUM 2

TIN 5, 14, 15, 16

COBALT 2

TITANIUM 16, 17, 18

LEAD 3, 4, 5, 6

FUSIBLE ALLOY 1

XRF 3, 4, 16, 21

MAGNESIUM 7, 8, 9, 10, 11

GOLD 12, 13

ZAMAK 20

RoHS MONITOR 19

ZINC 19, 20, 21, 22, 23

RM BISMUTH BASE and FUSIBLE SOLDER ALLOYS

95X: ~40 mm Ø x ~15 mm

NF: 37 mm Ø x 12 mm

| Number | Bi | Cd | In | Pb | Sn | Ag | Al | As | Au | Co | Cu | Fe | Hg | Ni | Sb | Zn | Other |
|--------------|-------|--------|--------|--------|-------|--------|----------|--------|--------|--------|--------|----------|----------|--------|-------|--------|--------------|
| 95X BIS40P1A | 57.4 | 0.0050 | 0.0164 | 0.043 | 42.3 | 0.035 | . | 0.0101 | . | . | 0.0670 | (0.001) | . | . | 0.092 | 0.011 | |
| 95X 174A | 57.1 | 0.0089 | 26.08 | 0.082 | 16.70 | 0.0075 | . | . | . | . | 0.0030 | . | . | . | 0.086 | 0.037 | Melt 'C: 79 |
| 95X 255A | 55.7 | 0.0065 | 0.010 | 43.7 | 0.24 | 0.0019 | . | . | . | . | 0.045 | . | . | . | 0.32 | 0.035 | Melt 'C: 124 |
| 95X BIS40P2A | 55.25 | 0.0008 | 0.0049 | 0.020 | 44.66 | 0.005 | 0.0021 | 0.0019 | 0.0006 | 0.0012 | 0.0026 | 0.0013 | (0.0016) | 0.0020 | 0.005 | 0.0016 | Ge: (0.0005) |
| NF 64-7 | Rem | . | 0.003 | 0.076 | 45.0 | 1.25 | . | 0.006 | 0.011 | 0.026 | 0.004 | . | . | 0.005 | 0.26 | . | |
| NF 64-6 | Rem | . | 0.007 | 0.26 | 43.1 | 0.70 | . | 0.018 | 0.035 | 0.039 | 0.11 | . | . | 0.042 | 0.11 | . | |
| NF 64-5 | Rem | . | 0.098 | 0.006 | 42.6 | 0.99 | . | . | . | . | 0.076 | . | . | . | 0.078 | . | |
| NF 64-4 | Rem | . | 0.075 | 0.052 | 42.0 | 0.40 | . | 0.010 | 0.006 | <0.001 | <0.001 | 0.006 | . | 0.025 | 0.053 | . | |
| NF 64-3 | Rem | . | 0.049 | 0.025 | 41.4 | 0.20 | . | 0.005 | . | . | 0.049 | . | . | 0.072 | 0.026 | . | |
| NF 64-1 | Rem | . | 0.010 | 0.098 | 41.0 | 0.006 | . | 0.0006 | . | . | 0.026 | . | . | 0.093 | 0.001 | . | |
| NF 64-2 | Rem | . | 0.024 | 0.012 | 40.5 | 0.052 | . | 0.001 | . | . | 0.15 | . | . | 0.011 | 0.013 | . | |
| 95X 158 | 50.2 | 9.6 | 0.006 | 27.0 | 13.5 | 0.002 | . | . | . | . | 0.048 | . | . | . | 0.057 | 0.044 | Melt 'C: 70 |
| 95X BISS0P1A | 49.8 | 0.022 | . | . | 50.0 | . | . | . | . | . | . | 0.051 | . | 0.025 | . | 0.006 | |
| 95X BISS0P3A | 49.8 | 0.015 | . | . | 48.6 | 1.50 | . | 0.073 | 0.0025 | . | . | 0.003 | . | . | . | 0.002 | |
| 95X BISS0P2A | 49.6 | . | . | . | 50.3 | 0.090 | 0.005 | 0.002 | 0.015 | . | . | 0.007 | . | . | . | . | |
| 95X 136A | 48.8 | 0.0092 | 21.49 | 18.0 | 12.05 | 0.0056 | . | . | . | . | 0.0028 | . | . | . | 0.022 | 0.031 | Melt 'C: 58 |
| 95X 117A | 45.3 | 4.95 | 18.72 | 23.1 | 8.02 | 0.0043 | . | . | . | . | 0.010 | . | . | . | 0.010 | 0.0056 | Melt 'C: 47 |
| 95X BIS70P1A | 29.6 | . | 0.040 | . | 69.1 | 1.10 | <0.001 | 0.025 | 0.0004 | . | . | 0.010 | . | . | . | . | |
| 95X BIS70P2A | 32.8 | . | 0.049 | . | 65.0 | 2.01 | <0.001 | . | . | . | . | . | . | 0.029 | . | 0.001 | |
| 95X PBS40P1A | 13.8 | 0.0043 | 0.005 | (43.6) | 42.6 | 0.011 | (0.0006) | 0.005 | . | . | 0.025 | (0.0006) | . | . | 0.016 | 0.0010 | |

RM CADMIUM ALLOY

| Number | Cd | Sn | Units |
|-----------|---------|-------|-----------------|
| 95X SC34A | (65.99) | 34.05 | 40 mm Ø x 15 mm |
| 95X SC36A | (63.98) | 36.09 | 40 mm Ø x 15 mm |

CRM CADMIUM SETS

AVAILABLE IN SETS ONLY, AS GROUPED

| Number | As | Cu | Ni | Pb | Sb | Sn | Tl | Set Size |
|------------------|-----------|--------|---------|--------|---------|---------|--------|-----------------|
| KZ 030101-03 - 1 | . | 0.0023 | 0.0010 | 0.0060 | . | . | 0.0011 | |
| KZ 030101-03 - 2 | . | 0.0039 | 0.0018 | 0.011 | . | . | 0.0021 | |
| KZ 030101-03 - 3 | . | 0.0068 | 0.00044 | 0.022 | . | . | 0.0047 | 40 mm Ø x 30 mm |
| KZ 030101-03 - 4 | . | 0.013 | 0.0043 | 0.047 | . | . | 0.0091 | |
| KZ 030101-03 - 5 | . | 0.024 | 0.011 | 0.12 | . | . | 0.023 | |
| IMN K1 | (0.00030) | . | 0.0086 | . | 0.0064 | 0.0061 | . | |
| IMN K2 | 0.0012 | . | 0.018 | . | 0.0038 | 0.0032 | . | |
| IMN K3 | 0.0010 | . | 0.063 | . | 0.0010 | 0.00065 | . | 40 mm Ø x 25 mm |
| IMN K4 | 0.0056 | . | 0.11 | . | 0.0011 | 0.00091 | . | |
| IMN K5 | 0.0014 | . | 0.0054 | . | 0.00017 | . | . | |

CRM CHROMIUM ALLOY

~40 mm Ø x ~15 mm

| Number | Cr | C | Co | Cu | Fe | Mn | Mo | N | Nb | Ni | P | S | Si | W |
|-------------|------|--------|--------|--------|-------|-------|--------|-------|--------|-------|--------|--------|-------|--------|
| 219X 20500C | 51.0 | 0.0212 | 0.0110 | 0.0101 | 1.515 | 0.299 | 0.0103 | 0.199 | 0.0117 | 45.46 | 0.0048 | 0.0137 | 1.288 | 0.0086 |

COBALT BASE ALLOYS

= class, where 1 = CRM and 2 = rm analysis listed in mass %

| # | Number | Cr | Fe | Mn | Mo | Nb | Ni | W | Al | C | Cu | P | S | Si | Ti | Co |
|---|-------------|---------|--------|--------|---------|----------|-------|---------|---------|---------|---------|----------|-----------|-------|---------|-------|
| 1 | 112X 14943H | 31.00 | 0.763 | 1.008 | 7.96 | 0.099 | 0.151 | 0.051 | (0.13) | 0.190 | 0.203 | 0.0043 | 0.0197 | 0.201 | 0.005 | . |
| 1 | IARM 95D | 29.9 | 0.84 | 1.47 | 0.954 | 0.024 | 2.99 | 3.98 | 0.080 | 1.06 | 0.009 | 0.0053 | (0.0003) | 0.64 | (0.009) | 57.9 |
| 1 | ECRM 378-1D | 28.22 | 0.606 | 0.0579 | 0.053 | . | 0.617 | 4.43 | . | 1.181 | . | (0.0023) | 0.0055 | 1.172 | . | 63.52 |
| 2 | BS 173 | 27.5 | 0.19 | 0.76 | 5.62 | (0.002) | 0.14 | . | (0.04) | 0.046 | (0.008) | (0.003) | 0.001 | 0.61 | (0.004) | 65.0 |
| 2 | CT ISO074A | 27.12 | (0.93) | 0.78 | 5.47 | . | 0.150 | <0.01 | . | 0.089 | 0.005 | 0.002 | 0.002 | 0.59 | . | 64.87 |
| 1 | IMZ 188 | 26.44 | 1.14 | 0.68 | 0.42 | 0.045 | 10.76 | 7.46 | (0.005) | 0.526 | 0.025 | 0.011 | (0.0002) | 0.69 | (0.007) | 51.64 |
| 1 | 119X COB1H | 24.62 | 15.15 | 0.514 | 0.413 | 0.405 | 22.14 | 11.99 | 0.055 | 0.0520 | 0.0607 | 0.0192 | 0.0099 | 0.493 | . | . |
| 1 | IMZ 186 | 23.14 | 0.10 | . | . | . | 10.22 | 7.17 | 0.28 | 0.59 | . | . | . | . | 0.19 | Rem |
| 2 | BS 172A | 21.85 | 1.76 | 0.77 | 0.30 | 0.09 | 23.7 | 14.0 | 0.08 | 0.098 | 0.027 | (0.011) | (<0.0005) | 0.37 | . | . |
| 2 | BS 171B | 20.5 | 1.82 | 1.90 | 0.65 | 0.046 | 10.68 | 15.1 | 0.08 | 0.087 | 0.035 | 0.008 | <0.001 | 0.29 | . | . |
| 2 | 111X 12671J | 20.5 | 1.45 | 0.61 | . | 1.95 | 0.88 | 11.8 | . | . | . | . | . | 0.51 | . | . |
| 1 | SRM 1242 | 20.0 | 1.80 | 1.58 | . | (<0.005) | 9.78 | 15.1 | (<0.01) | 0.126 | 0.0010 | 0.002 | 0.0007 | 0.016 | . | 51.5 |
| 1 | IARM 326A | (0.002) | 49.6 | 0.003 | (0.002) | 0.038 | 0.037 | (0.001) | (0.003) | (0.002) | (0.002) | 0.0013 | 0.0011 | 0.029 | (0.002) | 48.4 |

| Number | B | La | Mg | N | O | Pb | Sn | Ta | V | Zr | Units |
|-------------|-----------|-------|----------|--------|---------|-----------|----------|---------|---------|----------|---------------------------------|
| 112X 14943H | 0.0045 | . | . | 0.0284 | . | . | . | (0.014) | 0.009 | . | ~40 mm Ø x ~15 mm |
| IARM 95D | 0.0015 | . | (0.0002) | 0.0417 | 0.0009 | (0.00001) | (0.0001) | (0.03) | 0.0100 | (0.001) | 31 mm Ø x 2 mm last |
| ECRM 378-1D | . | . | . | . | . | . | . | . | . | . | 40 mm Ø x 20 mm |
| BS 173 | (0.001) | . | . | 0.190 | (0.002) | . | . | . | (0.01) | . | 35 mm Ø x ~7 or 19+ mm |
| CT ISO074A | (<0.0010) | . | . | 0.17 | . | . | . | . | 0.005 | . | 30-35 mm Ø x ~16 mm |
| IMZ 188 | 0.0009 | . | . | . | . | . | . | (0.011) | (0.011) | (0.0004) | 1/4 of 75 mm Ø cylinder x 20 mm |
| 119X COB1H | . | . | . | 0.093 | . | . | . | . | . | . | ~40 mm Ø x ~15 mm |
| IMZ 186 | (0.007) | . | . | . | . | . | . | 3.78 | . | 0.40 | 1/4 of 78 mm Ø cylinder x 30 mm |
| BS 172A | (0.003) | 0.045 | (0.001) | . | . | . | . | (0.024) | 0.007 | . | 38 mm Ø x ~7 or 19+ mm |
| BS 171B | . | . | . | . | . | . | . | . | (0.02) | . | 38 mm Ø x ~7 or 19+ mm |
| 111X 12671J | . | . | . | . | . | . | . | . | . | . | 40 mm Ø x 15 mm last |
| SRM 1242 | (<0.0001) | . | (<0.001) | 0.026 | . | (<0.0001) | (<0.001) | (<0.01) | 0.005 | (<0.01) | 43 mm Ø x 20 mm |
| IARM 326A | (0.001) | . | (0.001) | 0.0004 | 0.0082 | . | <0.001 | (0.01) | 1.94 | 0.002 | 31 mm Ø x 2 or 18 mm |

Need a larger size?
Most BS items are
available in any height.

LEAD

= class, where 1 = CRM and 2 = RM analysis listed in mass %

| # | Number | Ag | As | Bi | Cd | Cu | Ni | Sb | Se | Sn | Te | Zn |
|---|------------|-----------|------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| 1 | 83X PR1K | 0.1029 | 0.0338 | 0.0508 | 0.074 | 0.0465 | (0.0004) | 0.0100 | 0.0008 | 0.016 | 0.0058 | (0.002) |
| 1 | 83X PR4H | 0.0114 | 0.0003 | 0.0150 | 0.0081 | 0.0454 | 0.0029 | 0.0050 | (0.004) | . | 0.0229 | . |
| 1 | SRM C2417 | 0.010 | 0.011 | 0.010 | (<0.0002) | 0.010 | (<0.0005) | 0.010 | . | (<0.010) | (<0.0005) | (<0.0005) |
| 1 | 83X PR11A | 0.0030 | 0.0095 | 0.0117 | 0.0008 | 0.0551 | 0.0011 | 0.497 | (0.0001) | 0.119 | . | . |
| 1 | 83X PR12A | 0.0030 | (0.0003) | 0.0119 | 0.0011 | 0.0353 | 0.0009 | 0.0011 | (0.0002) | 0.0005 | . | . |
| 2 | 83X PR9-1A | 0.003 | . | . | 0.0004 | . | . | . | . | 0.054 | . | 0.0007 |
| 2 | 83X PR9-2A | 0.003 | . | . | 0.0004 | . | . | . | . | 0.015 | . | 0.0002 |
| 1 | 83X PR3G | 0.0029 | 0.0011 | 0.144 | 0.0462 | 0.0694 | 0.0116 | 0.0888 | 0.0166 | 0.0417 | 0.0039 | (0.0007) |
| 1 | 83X CU06A | 0.0019 | (0.0001) | 0.0134 | (0.00006) | 0.0554 | 0.0003 | (0.0008) | (0.0005) | (0.0004) | (0.0002) | (0.0003) |
| 1 | BCR 287A | 0.00152 | <0.0000003 | 0.00673 | 0.000036 | 0.000098 | 0.0000024 | 0.0000040 | <0.000005 | <0.000005 | <0.00002 | <0.00001 |
| 1 | 83X PR5G/2 | 0.0110 | 0.0003 | 0.0086 | 0.00029 | 0.00058 | (0.00017) | 0.0006 | 0.0004 | (0.0007) | 0.0003 | (0.00016) |
| 1 | SRM C2418 | 0.0007 | (<0.0001) | (<0.0005) | 0.0003 | (<0.0001) | (<0.0005) | (<0.0001) | . | (<0.0005) | (<0.0005) | (<0.0005) |
| 2 | BCS 210e * | 0.0001 | . | 0.0008 | . | 0.0006 | <0.001 | <0.002 | . | <0.002 | . | <0.005 |
| 1 | BCR 286A | 0.0000015 | <0.0000002 | 0.00215 | 0.0000125 | 0.000149 | 0.0000041 | 0.000010 | <0.000005 | <0.000005 | <0.00001 | <0.00001 |
| 1 | ERM-EB107 | . | . | . | 0.00261 | . | . | . | . | . | . | . |
| 1 | ERM-EB108 | . | . | . | 0.00260 | . | . | . | . | . | . | . |

| Number | Al | Au | Ca | Fe | Hg | In | Mn | Na | Pt | S | Ti | Tl | Units |
|------------|-----------|----------|-----------|-----------|----------|----------|-----------|----------|----|----------|-------|----------|--------------------------|
| 83X PR1K | (0.0003) | 0.0019 | . | . | . | 0.0080 | . | . | . | . | . | . | ~40 mm Ø x ~15 mm |
| 83X PR4H | . | 0.0021 | . | . | 0.019 | . | . | . | . | . | . | 0.0021 | ~40 mm Ø x ~15 mm |
| SRM C2417 | (<0.0001) | . | (<0.0001) | (<0.0003) | . | . | (<0.0003) | . | . | . | . | . | 50 mm Ø x 16 mm |
| 83X PR11A | . | . | . | (0.0003) | . | . | . | . | . | 0.009 | . | 0.0042 | ~40 mm Ø x ~15 mm |
| 83X PR12A | . | . | . | (0.0003) | . | . | . | . | . | (0.0002) | . | 0.0051 | ~40 mm Ø x ~15 mm |
| 83X PR9-1A | 0.0001 | Ba:0.033 | 0.096 | . | Li:0.004 | . | Mg:0.006 | 0.015 | . | . | . | . | ~40 mm Ø x ~15 mm |
| 83X PR9-2A | 0.0001 | Ba:0.015 | 0.046 | . | Li:0.002 | . | Mg:0.002 | 0.007 | . | . | . | . | ~40 mm Ø x ~15 mm |
| 83X PR3G | . | 0.0036 | . | . | 0.0008 | 0.0093 | . | (0.0038) | . | . | . | 0.0033 | ~40 mm Ø x ~15 mm |
| 83X CU06A | . | . | . | . | . | . | . | . | . | 0.0011 | . | . | ~40 mm Ø x ~15 mm |
| BCR 287A | . | . | . | . | . | . | . | . | . | . | . | 0.000073 | 60 mm x 60 mm x 12 mm |
| 83X PR5G/2 | . | . | . | . | (0.0001) | (0.0001) | . | . | . | . | . | (0.0001) | ~40 mm Ø x ~15 mm |
| SRM C2418 | (<0.0001) | . | (<0.0005) | (<0.0005) | . | . | (<0.0005) | . | . | . | . | . | 50 mm Ø x 16 mm |
| BCS 210e * | <0.001 | . | . | 0.0005 | . | . | <0.001 | . | . | . | 0.001 | . | 500 g (10.5 x 2 x 2 cms) |
| BCR 286A | . | . | . | . | . | . | . | . | . | . | . | 0.00025 | 60 mm x 60 mm x 12 mm |
| ERM-EB107 | . | . | . | . | 0.00113 | . | . | . | . | . | . | . | 40 mm Ø x 40 mm |
| ERM-EB108 | . | . | . | . | 0.00083 | . | . | . | . | . | . | . | 40 mm Ø x 40 mm |

** BCS 210e has a certified melting point of 327.3 °C and Pb: 99.996

CRM REFINED LEAD SET

available in SET/7 ONLY

analysis listed in mg/kg

40 mm Ø x 27 mm

| Number | Ag | As | Bi | Ca | Cd | Cu | Fe | In | Mn | Ni | Sb | Se | Sn | Te | Tl | Zn |
|----------|------|--------|------|--------|------|------|-------|--------|--------|------|------|------|------|------|------|-------|
| IMN PL 1 | 193 | 3.6 | 729 | . | . | 7.3 | 4.5 | (64.3) | (0.20) | 136 | 15.4 | . | 3.0 | 145 | 569 | 6.0 |
| IMN PL 2 | 97.0 | 2.6 | 460 | . | 218 | 14.9 | 4.4 | (6.4) | (0.17) | 159 | 7.2 | 33.3 | 2.6 | 349 | 228 | (1.7) |
| IMN PL 3 | 17.0 | 2.5 | 101 | (3.4) | 15.7 | 105 | (2.4) | 5.9 | (0.60) | 39.4 | 8.0 | 2.7 | 2.1 | 235 | 26.4 | 1.8 |
| IMN PL 4 | 10.3 | 345 | 59.9 | . | 5.1 | 197 | . | . | . | 8.5 | 3.4 | 2.7 | . | 23.6 | 21.5 | . |
| IMN PL 5 | 27.3 | 159 | 296 | . | . | 9.1 | . | 287 | . | 6.7 | 572 | . | 13.7 | 13.6 | 135 | . |
| IMN PL 6 | 64.3 | 318 | 48.3 | (81.1) | 623 | 4.7 | (2.0) | 104 | (0.50) | 5.5 | 310 | . | 7.6 | 8.2 | 494 | . |
| IMN PL 7 | 151 | (74.3) | 61.7 | . | 53.2 | 6.8 | . | . | . | . | 77.7 | . | 26.3 | 270 | 99.2 | 3.5 |

LEAD BINARY

available individually

typical analysis

cast typical analysis

40 mm Ø x 15 mm

| Class | Number | Sn | As | Pb | Sb | Units | Class | Number | Sb | Ag | As | Bi | Mg |
|-------|-----------|-------|------|----------|------|-----------------|----------------|-----------------------|-----------------|-------|----------|--------|-------|
| CRM | 91X S63P | 63.30 | . | SOLD OUT | . | 40 mm Ø x 15 mm | CRM | 81X PA12.5D | 12.72 | . | . | . | . |
| RM | 91X S50PE | 50.0 | . | Rem | . | 40 mm Ø x 15 mm | CRM | 81X PA10.0C | 9.60 | . | . | . | . |
| RM | 91X S40PD | 40.0 | . | Rem | . | 40 mm Ø x 15 mm | CRM | 81X PA7.0D | 7.02 | . | SOLD OUT | . | . |
| RM | 91X S30P | 30.0 | . | SOLD OUT | . | 40 mm Ø x 15 mm | CRM | 81X PA3.5E | 3.49 | . | . | . | . |
| RM | NF 23 | 30.0 | . | SOLD OUT | . | 37 mm Ø x 12 mm | CRM | 81X PA2.0D | 1.996 | . | SOLD OUT | . | . |
| RM | NF 22 | 25.0 | . | Rem | . | 37 mm Ø x 12 mm | CRM | 81X PA1.0C | 0.989 | . | . | . | . |
| RM | NF 20 | 15.2 | . | Rem | . | 37 mm Ø x 12 mm | CRM | 81X PA0.5C | 0.481 | . | . | . | . |
| RM | NF 19 | 12.0 | . | Rem | . | 37 mm Ø x 12 mm | RM | 81X PAs1A | (0.02) | . | 1.25 | (0.03) | . |
| CRM | 91X S10PD | 10.07 | . | Rem | . | 40 mm Ø x 15 mm | RM | 81X PMg1A | . | . | . | . | 1.15 |
| RM | NF 18 | 9.80 | . | Rem | . | 37 mm Ø x 12 mm | RM | 81X PMg2A | . | . | . | . | 0.173 |
| RM | NF 17 | 6.80 | . | Rem | . | 37 mm Ø x 12 mm | RM | 81X PMg3A | . | . | . | . | 0.023 |
| RM | NF 16 | 3.00 | . | Rem | . | 37 mm Ø x 12 mm | RM | 82X PAG0.9A | . | 0.903 | . | . | . |
| RM | NF 35 | 0.97 | 0.94 | Rem | 14.0 | 37 mm Ø x 12 mm | RM | 82X PAG0.7A | . | 0.733 | . | . | . |

LEAD ALLOYS

CONTINUED FROM THE PREVIOUS PAGE

* Provisional Analysis

| Number | Al | Au | Hg | In | Mg | Mn | Na | Pd | S | Se | Tl | Units |
|---------------|-----------|----------|---------|-----------|-----------|-----------|----------|--------|-----------|----------|----------|-----------------------------|
| 91X S63PR3G | . | 0.169 | (0.038) | 0.0097 | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 91X S63PJ | (0.0003) | (0.0005) | . | 0.0064 | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 91X S63PR2K | 0.0005 | 0.082 | . | 0.0157 | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 91X S63Bi1A | (0.0015) | 0.074 | . | 0.0067 | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 91X S62AG2A | (0.0011) | 0.0020 | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 91X S63PR1G | . | 0.0348 | (0.015) | 0.0308 | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 91X S63PR0B | . | 0.0148 | 0.004 | 0.0048 | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 91X S40PR2D | . | . | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| SRM 1131 | . | . | . | . | . | . | . | . | . | . | . | Disc 32 mm Ø x 19 mm |
| 91X S40PR1B | . | . | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm last |
| 93X S30APR3C | . | . | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 91X S30PR3C | . | 0.0063 | . | 0.0085 | . | . | . | . | . | . | . | Disc 40 mm Ø x ~12 mm |
| 93X S30APR2C | . | . | . | 0.0199 | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 91X S30PR2C | <0.0005 | 0.0017 | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 93X S30APR1C | . | . | . | 0.0094 | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 86X PSS4C * | . | . | . | 0.020 | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 86X PSS4B | . | . | . | 0.0174 | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 85X S5BCA | . | 0.0079 | . | 0.209 | . | . | . | . | (0.0008) | (0.0029) | 0.0196 | Disc 40 mm Ø x 15 mm |
| 86X PSS3B | . | . | . | 0.0111 | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 91X S10PR1C | . | . | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 86X PSS2B | . | . | . | 0.0059 | . | . | . | 0.0049 | . | . | . | Disc 40 mm Ø x 15 mm |
| SRM 1132 | . | . | . | . | . | . | . | . | . | . | . | Disc 32 mm Ø x 19 mm |
| 86X PSS1B | . | . | . | 0.0074 | . | . | . | 0.0023 | . | . | . | Disc 40 mm Ø x 15 mm |
| 84X BA9C | 0.0207 | . | . | . | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 85X SSCHA | . | . | . | . | . | . | . | . | 0.0035 | (0.015) | last | Disc 40 mm Ø x ~11-13 mm |
| 85X Psn2C | . | . | . | Co:0.0004 | . | . | . | . | (0.0009) | 0.0042 | . | Disc ~40 mm Ø x ~15 mm |
| BAM EBI06 | . | . | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 40 mm |
| 84X BA13B | 0.0363 | . | . | . | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 84X BA12C | 0.0158 | . | . | . | 0.00074 | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| BAM EBI05 | . | . | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 40 mm |
| 84X BA11B | 0.0207 | . | . | . | . | . | . | . | . | . | . | Disc ~38 mm Ø x ~15 mm |
| BAM EBI04 | . | . | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 40 mm |
| 85X ANTHF | . | . | . | Co:0.0006 | . | . | . | . | 0.0026 | 0.014 | . | Disc ~40 mm Ø x ~15 mm |
| BAM EBI02a | 0.0124 | . | . | (<0.0002) | (<0.0001) | . | (0.0004) | . | (<0.0003) | . | 0.00302 | Disc 40 mm Ø x 40 mm |
| 84X BA14A | 0.0188 | . | . | . | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 84X BA15A | 0.0161 | . | . | . | . | . | . | . | . | . | . | Disc ~38 mm Ø x ~15 mm |
| 84X BA1K | 0.0336 | . | . | . | . | . | . | . | . | . | . | Disc ~39 mm Ø x ~15 mm |
| 85X HRHH | . | . | . | . | . | . | . | . | (0.0022) | 0.0375 | . | Disc 40 mm Ø x 15 mm |
| 83X PR8D | . | 0.0106 | 0.086 | 0.293 | . | . | . | . | . | (0.0003) | . | Disc ~40 mm Ø x ~15 mm |
| 84X BA7B | 0.0085 | . | . | . | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 84X BA2D | 0.0183 | . | . | . | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 82X PAG6.0RA | <0.001 | . | . | 0.008 | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 85X MS2XA | . | . | . | . | . | . | . | . | (0.0002) | 0.0334 | . | Disc ~38 mm Ø x ~15 mm |
| 84X BA20B | 0.065 | . | . | . | . | . | . | . | . | . | . | Disc ~38 mm Ø x ~15 mm |
| 84X BA8D | 0.0359 | . | . | . | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| Number | Al | Au | Hg | In | Mg | Mn | Na | Pd | S | Se | Tl | Units |
| 84X BA3D | 0.0043 | . | . | . | 0.00038 | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| SRM C2415a | Pb: (96) | . | . | . | . | . | . | . | (0.0061) | 0.01005 | . | Disc 40 mm Ø x 18 mm |
| BAM EBI01a | 0.0227 | . | . | . | (0.0009) | . | (0.0004) | . | (<0.0003) | . | 0.00102 | Disc 40 mm Ø x 40 mm |
| 85X P5b5E | . | . | . | . | . | . | . | . | 0.018 | 0.014 | . | Disc ~38 mm Ø x ~15 mm |
| 85X P5b12B | . | . | . | . | . | . | . | . | <0.001 | 0.0004 | . | Disc 40 mm Ø x 15 mm |
| L21.02 | . | . | . | . | . | . | . | . | . | . | . | Block 50 mm x 50 mm x 20 mm |
| 82X PAG3.5RD | 0.0015 | . | . | 0.037 | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 85X S744A | . | . | . | . | . | . | . | . | 0.0028 | 0.0253 | . | Disc ~40 mm Ø x ~15 mm |
| 84X BA23B | 0.0569 | . | . | . | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 85X 0494 Pb3D | . | . | . | . | . | . | . | . | 0.0185 | 0.049 | . | Disc ~40 mm Ø x ~15 mm |
| 85X P5b5F | . | . | . | . | . | . | . | . | 0.0056 | 0.0077 | . | Disc ~40 mm Ø x ~15 mm |
| BAM EBI03 | . | . | . | . | . | . | . | . | . | 0.0180 | 0.00152 | Disc 40 mm Ø x 30 mm |
| 84X BA21B | 0.0125 | . | . | . | . | . | . | . | . | . | . | Disc ~39 mm Ø x ~15 mm |
| 85X P5b3J | . | . | . | . | . | . | . | . | (0.0008) | 0.0317 | . | Disc ~40 mm Ø x ~15 mm |
| 83X PR9A | 0.0138 | 0.200 | . | Li:0.066 | 0.054 | . | 0.077 | . | . | . | . | Disc ~40 mm Ø x ~15 mm last |
| 84X BA22B | 0.074 | . | . | . | . | . | . | . | . | . | . | Disc ~38 mm Ø x ~15 mm |
| 85X 0494 Pb2C | . | . | . | . | . | . | . | . | 0.0052 | 0.0272 | . | Disc ~40 mm Ø x ~15 mm |
| 85X CADHC * | . | . | . | . | . | . | . | . | . | 0.01 | . | Disc ~40 mm Ø x ~15 mm |
| 83X PR2G | . | 0.0005 | 0.003 | 0.0010 | . | . | 0.0013 | . | (0.0006) | 0.0005 | (0.0017) | Disc ~40 mm Ø x ~15 mm |
| 85X P5b10B | . | . | . | . | . | . | . | . | <0.001 | 0.0020 | . | Disc 40 mm Ø x 15 mm |
| SRM C2416 | (<0.0001) | . | . | . | . | (<0.0005) | . | . | 0.0015 | . | . | Disc 50 mm Ø x 16 mm |
| 82X PAG2.5RD | . | . | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 85X M2A | . | . | . | . | . | . | . | . | (0.0008) | 0.0247 | . | Disc ~38 mm Ø x ~15 mm |
| 85X 2.5LAA | . | . | . | . | . | . | . | . | . | 0.0006 | . | Disc ~40 mm Ø x ~15 mm |
| 85X P5b6A | . | . | . | . | . | . | . | . | . | 0.0018 | . | Disc ~40 mm Ø x ~15 mm |
| 85X 0494 Pb1A | . | . | . | . | . | . | . | . | . | 0.004 | . | Disc 40 mm Ø x 15 mm |
| 85X SB28A | . | . | . | . | . | . | . | . | 0.0010 | 0.0223 | . | Disc ~38 mm Ø x ~15 mm |
| 84X BA4C | 0.0015 | . | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x ~15 mm last |
| 85X N35A | . | . | . | . | . | . | . | . | 0.007 | 0.0004 | . | Disc ~38 mm Ø x ~15 mm |
| 85X P5b8B | . | . | . | . | . | . | . | . | 0.005 | 0.0022 | . | Disc 40 mm Ø x 15 mm |
| 82X PAG1.5RE | . | . | . | . | . | . | . | . | . | . | . | Disc 40 mm Ø x 15 mm |
| 85X A16A | . | . | . | . | . | . | . | . | (0.0003) | 0.0218 | . | Disc ~38 mm Ø x ~15 mm |
| 85X SM31A | . | . | . | . | . | . | . | . | 0.0003 | 0.0183 | . | Disc ~38 mm Ø x ~15 mm |
| 85X CADLB | . | . | . | . | . | . | . | . | . | . | . | Disc ~40 mm Ø x ~15 mm |
| 85X SASHA | . | . | . | . | . | . | . | . | (0.0005) | . | . | Disc 40 mm Ø x ~15 mm |
| 85X CADLA | . | . | . | . | . | . | . | . | . | (0.0011) | . | Disc 40 mm Ø x ~15 mm |
| 85X YUMA | . | . | . | . | . | . | . | . | 0.0062 | 0.0008 | . | Disc ~40 mm Ø x ~15 mm |
| 85X 0616 Pb1C | . | . | 0.0010 | . | . | . | . | . | . | 0.0087 | . | Disc ~40 mm Ø x ~15 mm |
| Number | Al | Au | Hg | In | Mg | Mn | Na | Pd | S | Se | Tl | Units |

MAGNESIUM

= class, where 1 = CRM and 2 = RM

61X: not for Glow Discharge

| # | Number | Al | Cu | Fe | Mn | Ni | Pb | Si | Zn | Ag | Be |
|---|---------------|---------|---------|----------|--------|-----------|----------|--------|--------|--------|----------|
| 1 | 58A ST4360 | (1.06) | 0.025 | 0.02 | 0.148 | 0.0052 | 0.018 | 0.02 | 0.025 | . | . |
| 1 | 58A ST4320 | (0.531) | 0.0077 | 0.027 | 0.085 | 0.011 | 0.037 | 0.062 | 0.047 | . | . |
| 1 | NCS HS49725-2 | (0.531) | 0.0077 | 0.027 | 0.085 | 0.011 | 0.037 | 0.062 | 0.047 | . | . |
| 1 | 58A ST4340 | 0.262 | 0.014 | 0.0069 | 0.023 | 0.0044 | 0.012 | 0.034 | 0.019 | . | . |
| 1 | NCS HS49725-4 | 0.262 | 0.014 | 0.0069 | 0.023 | 0.0044 | 0.012 | 0.034 | 0.019 | . | . |
| 1 | 61X MgP3A | 0.096 | 0.0296 | 0.014 | 0.0135 | 0.0049 | 0.0148 | 0.046 | 0.0196 | 0.0125 | <0.0001 |
| 1 | 63X MgE1E | (0.088) | 0.0503 | 0.0014 | 0.860 | 0.0162 | 0.011 | 0.052 | 0.083 | 0.0195 | (0.0002) |
| 1 | 61X MgP2A | 0.065 | 0.0109 | 0.0061 | 0.0118 | 0.0029 | 0.0061 | 0.031 | 0.0122 | 0.003 | <0.0001 |
| 2 | 58A ZH1120 | 0.063 | 0.037 | 0.012 | 0.062 | 0.012 | 0.0073 | 0.037 | 0.038 | . | . |
| 2 | 58A ZH1130 | 0.055 | 0.017 | 0.015 | 0.039 | 0.007 | 0.0035 | 0.055 | 0.02 | . | . |
| 1 | 61X MgP4A | 0.0247 | 0.0108 | (0.0044) | 0.0100 | 0.0028 | 0.0066 | 0.037 | 0.0158 | 0.0203 | <0.0001 |
| 1 | 58A ST4330 | 0.017 | 0.0087 | 0.0083 | 0.019 | 0.0021 | 0.0067 | 0.023 | 0.012 | . | . |
| 1 | NCS HS49725-3 | 0.017 | 0.0087 | 0.0083 | 0.019 | 0.0021 | 0.0067 | 0.023 | 0.012 | . | . |
| 2 | 58A ZH1140 | 0.017 | 0.0054 | 0.0044 | 0.011 | 0.0007 | 0.0013 | 0.0027 | 0.0058 | . | . |
| 2 | 58A ZH1160 | 0.011 | 0.0016 | 0.0071 | 0.016 | 0.0004 | 0.0025 | 0.019 | 0.004 | . | . |
| 1 | NCS HS49725-1 | 0.011 | 0.0012 | 0.0028 | 0.017 | 0.00035 | 0.0052 | 0.011 | 0.011 | . | . |
| 1 | 58A ST4370 | 0.0082 | 0.0039 | 0.0055 | 0.017 | 0.0013 | 0.0067 | 0.03 | 0.013 | . | . |
| 1 | NCS HS49725-7 | 0.0082 | 0.0039 | 0.0055 | 0.017 | 0.0013 | 0.0067 | 0.030 | 0.013 | . | . |
| 2 | 58A ZH1150 | 0.0062 | 0.0003 | 0.0015 | 0.0054 | (0.0001) | (0.0005) | 0.0024 | 0.0046 | . | . |
| 1 | NCS HS49725-5 | 0.0059 | 0.00063 | 0.0022 | 0.0060 | (0.00033) | 0.0020 | 0.0063 | 0.0079 | . | . |
| 2 | 58A ZH1110 | 0.0052 | 0.062 | 0.0054 | 0.092 | 0.0041 | 0.012 | 0.015 | 0.058 | . | . |
| 1 | 58A ST4310b | 0.005 | 0.00097 | 0.0087 | 0.022 | 0.00026 | (0.0011) | 0.012 | 0.0012 | . | . |

| Number | Ca | Cd | Ce | Cl | La | Na | Sn | Ti | Zr | ~mm Ø x ~mm H |
|---------------|--------|--------|--------|----------|--------|----------|--------|-----------|----------|----------------|
| 58A ST4360 | . | . | . | . | . | . | . | 0.0025 | . | 45 x 25 |
| 58A ST4320 | . | . | . | . | . | . | . | (0.00018) | . | 45 x 25 |
| NCS HS49725-2 | . | . | . | . | . | . | . | (0.00018) | . | 45 x 25 |
| 58A ST4340 | . | . | . | . | . | . | . | 0.0012 | . | 45 x 25 |
| NCS HS49725-4 | . | . | . | . | . | . | . | 0.0012 | . | 45 x 25 |
| 61X MgP3A | 0.053 | 0.0154 | 0.0055 | . | 0.0038 | . | 0.0154 | . | (0.0014) | 40 x 20 |
| 63X MgE1E | . | 0.0017 | . | . | . | . | 0.0053 | . | . | 50x20 or 40x15 |
| 61X MgP2A | 0.0138 | 0.0063 | 0.0019 | . | 0.0014 | . | 0.0073 | . | (0.0007) | 40 x 20 |
| 58A ZH1120 | . | . | . | (0.0023) | . | (0.0002) | . | . | . | ~49 x ~34 |
| 58A ZH1130 | . | . | . | (0.0027) | . | (0.0003) | . | . | . | ~49 x ~34 |
| 61X MgP4A | 0.028 | 0.0071 | 0.0041 | . | 0.0030 | . | 0.0067 | . | 0.030 | 40 x 20 |
| 58A ST4330 | . | . | . | . | . | . | . | (0.0008) | . | 45 x 25 |
| NCS HS49725-3 | . | . | . | . | . | . | . | 0.000062 | . | 45 x 25 |
| 58A ZH1140 | . | . | . | (0.0015) | . | (0.0003) | . | . | . | ~49 x ~34 |
| 58A ZH1160 | . | . | . | (0.0018) | . | (0.0001) | . | . | . | ~49 x ~34 |
| NCS HS49725-1 | . | . | . | . | . | . | . | 0.00027 | . | 45 x 25 |
| 58A ST4370 | . | . | . | . | . | . | . | (0.00010) | . | 45 x 25 |
| NCS HS49725-7 | . | . | . | . | . | . | . | (0.00010) | . | 45 x 25 |
| 58A ZH1150 | . | . | . | (0.0011) | . | (0.0001) | . | . | . | ~49 x ~34 |
| NCS HS49725-5 | . | . | . | . | . | . | . | 0.000072 | . | 45 x 25 |
| 58A ZH1110 | . | . | . | (0.0018) | . | (0.0004) | . | . | . | ~49 x ~34 |
| 58A ST4310b | . | . | . | . | . | . | . | 0.00026 | . | 45 x 25 |

MAGNESIUM with RARE EARTHS

= class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

| # | Number | Ag | Al | Be* | Ca | Cd* | Ce | Cu | Fe | Gd | La | Mn | Nd | Ni |
|---|-------------|--------|---------------|-----|----------|-----|--------------|--------|--------|-------|--------|--------|--------------|--------|
| 1 | 67X MgK3A | . | 4.56 | 7 | . | . | 0.83 | 0.0017 | 0.0024 | 0.038 | 0.374 | 0.516 | 0.175 | 0.0016 |
| 1 | 67X MgK2A | . | 3.84 | 25 | . | . | 0.70 | 0.0041 | 0.0016 | 0.053 | 0.34 | 0.534 | 0.125 | 0.0033 |
| 1 | 64X MgQ9A | . | 2.14 | 15 | . | . | 0.111 | 0.0104 | 0.0069 | . | 0.083 | 0.068 | 0.114 | 0.0020 |
| 1 | 66X MgD1B | . | 0.147 | . | . | . | 0.065 | 0.066 | 0.0029 | . | 0.031 | 0.125 | 0.064 | 0.0162 |
| 1 | 61X MgP5A | 0.0342 | 0.119 | 18 | . | 292 | 0.049 | 0.092 | 0.0048 | . | 0.0382 | 0.201 | 0.0446 | 0.0176 |
| 1 | 61X MgP6A | 0.0043 | 0.0449 | . | (0.0008) | 25 | 0.0209 | 0.0067 | 0.0041 | . | 0.0137 | 0.0125 | 0.0238 | 0.0025 |
| 2 | AA C7548 | . | 0.004 | . | . | . | 2.66 | 0.022 | . | . | . | 0.035 | . | 0.001 |
| 2 | AA C7594 | . | 0.003 | . | . | . | 3.22 | 0.080 | . | . | . | 0.033 | . | 0.001 |
| 2 | AA C7546 | . | 0.003 | . | . | . | 1.63 | 0.058 | . | . | . | 0.039 | . | 0.004 |
| 2 | AA C7514 | . | 0.002 | . | . | . | 2.47 | 0.12 | . | . | . | 0.012 | . | 0.002 |
| 2 | AA C7489 | . | 0.001 | . | . | . | 2.57 | 0.004 | . | . | . | 0.012 | . | 0.015 |
| 2 | AA E1273 | . | 0 | . | . | . | 1.86 | 0.022 | . | . | . | 0.041 | . | 0.002 |
| 2 | AA E1272 | . | 0 | . | . | . | 1.79 | 0.026 | . | . | . | 0.045 | . | 0.003 |
| 1 | 58A ST5280 | . | . | . | . | . | 4.16 | . | . | . | . | . | . | . |
| 1 | 58A ST5290 | . | . | . | . | . | 3.37 | . | . | . | . | . | . | . |
| 1 | 58A ST5260 | . | . | . | . | . | 2.79 | . | . | . | . | . | . | . |
| 1 | 58A ST5250 | . | . | . | . | . | 1.54 | 0.133 | . | . | . | 0.214 | . | 0.005 |
| 1 | 58A ST5240 | . | . | . | . | . | 1.47 | 0.051 | . | . | . | 0.062 | . | 0.084 |
| 1 | 58A ST5230 | . | . | . | . | . | 1.28 | 0.068 | 0.0041 | . | . | 0.067 | . | 0.0011 |
| 1 | 58A ST5220 | . | . | . | . | . | 0.826 | 0.054 | 0.0033 | . | . | 0.093 | . | 0.0009 |
| 1 | 58A ST5210 | . | . | . | . | . | 0.149 | 0.0092 | 0.0027 | . | . | 0.15 | . | 0.001 |
| 1 | 58A ST10350 | . | . | . | . | . | . | . | . | . | . | . | 3.55 | . |
| 1 | 58A ST10360 | . | . | . | . | . | . | . | . | . | . | . | 3.38 | . |
| 1 | 58A ST10340 | . | . | . | . | . | . | . | . | . | . | . | 2.6 | . |
| 1 | 58A ST10330 | . | . | . | . | . | . | . | . | . | . | . | 2.28 | . |
| 1 | 58A ST10320 | . | . | . | . | . | . | . | . | . | . | . | 0.71 | . |
| 1 | 58A ST10310 | . | . | . | . | . | . | . | . | . | . | . | 0.429 | . |
| 2 | AA D1075 | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 2 | AA D1073 | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 2 | AA D1072 | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 2 | AA D1074 | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 1 | 58A ST9460 | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 1 | 58A ST9450 | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 1 | 58A ST9440 | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 1 | 58A ST9430 | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 1 | 58A ST9420 | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 1 | 58A ST9410 | . | . | . | . | . | . | . | . | . | . | . | . | . |

| # | Number | Ag | Al | Be* | Ca | Cd* | Ce | Cu | Fe | Gd | La | Mn | Nd | Ni |
|-----|---------|--------|-------|-------|----------|--------|--------------|-------|--------|----------------|----|----|----|----|
| 67X | MgK3A | . | 0.069 | . | 0.068 | . | . | 0.050 | . | 50x20 or 40x15 | . | . | . | . |
| 67X | MgK2A | . | 0.053 | . | 0.057 | . | . | 0.132 | . | 50x20 or 40x15 | . | . | . | . |
| 64X | MgQ9A | 0.0096 | . | . | (0.37) | 0.0076 | . | 0.243 | . | 40 x 15 | . | . | . | . |
| 66X | MgD1B | 0.026 | . | . | (0.073) | 0.026 | . | 1.19 | . | 40 x 15 | . | . | . | . |
| 61X | MgP5A | 0.0357 | . | . | 0.094 | 0.0352 | 0.0132 | 0.099 | . | 40 x 15 | . | . | . | . |
| 61X | MgP6A | 0.0120 | . | . | 0.044 | 0.0091 | 0.0375 | 0.010 | . | 50x20 or 40x15 | . | . | . | . |
| AA | C7548 | . | . | (4.8) | 0.002 | . | . | . | 0.16 | 62 x 6 | . | . | . | . |
| AA | C7594 | . | . | (6.0) | 0.002 | . | . | . | 0.31 | 62 x 6 | . | . | . | . |
| AA | C7546 | . | . | (3.0) | 0.001 | . | . | . | 0.34 | 62 x 6 | . | . | . | . |
| AA | C7514 | . | . | (4.7) | 0.002 | . | . | . | 0.42 | 62 x 6 | . | . | . | . |
| AA | C7489 | . | . | (5.0) | 0.002 | . | . | . | 0.46 | 62 x 6 | . | . | . | . |
| AA | E1273 | . | . | (3.6) | 0.0 | . | . | 2.87 | 0.54 | 62 x 6 | . | . | . | . |
| AA | E1272 | . | . | (3.3) | 0.0 | . | . | 2.58 | 0.54 | 62 x 6 | . | . | . | . |
| 58A | ST5280 | . | . | . | . | . | . | 3.52 | 0.63 | 45 x 25 | . | . | . | . |
| 58A | ST5290 | . | . | . | . | . | . | 4.37 | 0.81 | 45 x 25 | . | . | . | . |
| 58A | ST5260 | . | . | . | . | . | . | 4.36 | (1.03) | 45 x 25 | . | . | . | . |
| 58A | ST5250 | . | . | . | . | . | . | 1.46 | . | 45 x 25 | . | . | . | . |
| 58A | ST5240 | . | . | . | . | . | . | 2.69 | . | 45 x 25 | . | . | . | . |
| 58A | ST5230 | . | . | . | (0.0047) | . | . | 3.63 | . | 45 x 25 | . | . | . | . |
| 58A | ST5220 | . | . | . | (0.0056) | . | . | 4.58 | . | 45 x 25 | . | . | . | . |
| 58A | ST5210 | . | . | . | . | . | . | 5.59 | . | 45 x 25 | . | . | . | . |
| 58A | ST10350 | . | . | . | . | . | . | . | . | 45 x 25 | . | . | . | . |
| 58A | ST10360 | . | . | . | . | . | . | . | . | 45 x 25 | . | . | . | . |
| 58A | ST10340 | . | . | . | . | . | . | . | . | 45 x 25 | . | . | . | . |
| 58A | ST10330 | . | . | . | . | . | . | . | . | 45 x 25 | . | . | . | . |
| 58A | ST10320 | . | . | . | . | . | . | . | . | 45 x 25 | . | . | . | . |
| 58A | ST10310 | . | . | . | . | . | . | . | . | 45 x 25 | . | . | . | . |
| AA | D1075 | . | . | (3.7) | . | . | . | (2.7) | 0.64 | 62 x 6 | . | . | . | . |
| AA | D1073 | . | . | (3.7) | . | . | . | 3.23 | (0.6) | 62 x 6 | . | . | . | . |
| AA | D1072 | . | . | (3.4) | . | . | . | 2.02 | (0.5) | 62 x 6 | . | . | . | . |
| AA | D1074 | . | . | (3.4) | . | . | . | (2.7) | 0.42 | 62 x 6 | . | . | . | . |
| 58A | ST9460 | . | . | . | . | . | 6.69 | . | . | 45 x 25 | . | . | . | . |
| 58A | ST9450 | . | . | . | . | . | 4.3 | . | . | 45 x 25 | . | . | . | . |
| 58A | ST9440 | . | . | . | . | . | 3.52 | . | . | 45 x 25 | . | . | . | . |
| 58A | ST9430 | . | . | . | . | . | 2.02 | . | . | 45 x 25 | . | . | . | . |
| 58A | ST9420 | . | . | . | . | . | 1.78 | . | . | 45 x 25 | . | . | . | . |
| 58A | ST9410 | . | . | . | . | . | 0.527 | . | . | 45 x 25 | . | . | . | . |

| Number | Pb | Pr | R.E. | Si | Sn | Y | Zn | Zr | ~mm Ø x ~mm H |
|--------|----|----|------|----|----|---|----|----|---------------|
|--------|----|----|------|----|----|---|----|----|---------------|

MAGNESIUM with ALUMINUM

| # | Number | Al | Be | Ca | Cd | Cu | Fe | Mn | Ni | Pb | Si | Sn | Zn |
|---|---------------|--------|-----------|----------|---------|--------|----------|---------|----------|--------|---------|--------|--------|
| 1 | 58A ST2150 | 11.52 | (0.0023) | . | . | 0.295 | (0.020) | (0.68) | 0.018 | . | 0.176 | . | 0.217 |
| 1 | 65X MgA15A | 10.67 | 0.0062 | (0.0014) | 0.0034 | 0.0273 | 0.010 | 0.067 | 0.0026 | 0.0051 | 0.034 | 0.0021 | 0.348 |
| 2 | 58A ZH2050M | 10.4 | 0.0007 | . | . | 0.307 | 0.0081 | (0.71) | 0.019 | . | 0.41 | . | 0.201 |
| 2 | AA D3738 | 10.38 | . | . | . | 0.031 | . | 0.21 | 0.004 | . | 0.085 | . | 0.32 |
| 1 | 64X MgQ3A | 8.66 | 0.0041 | . | . | 0.0349 | 0.0090 | 0.206 | 0.0032 | 0.0022 | (0.083) | 0.0019 | 0.0039 |
| 1 | 65X MgA5A | 8.00 | 0.0013 | (0.014) | 0.0035 | 0.0195 | 0.006 | 0.401 | 0.0201 | 0.042 | 0.110 | 0.0124 | 0.411 |
| 1 | 58A ST1240 | 7.33 | 0.00015 | . | . | 0.02 | 0.015 | 0.182 | (0.0015) | . | 0.27 | . | 0.171 |
| 1 | 64X MgQ4A | 6.50 | 0.00029 | . | . | 0.310 | 0.0040 | 0.183 | 0.0068 | 0.0322 | (0.067) | 0.0282 | 0.188 |
| 1 | 58A ST1250 | 6.29 | (0.0010) | . | . | 0.02 | (0.016) | 0.428 | (0.0068) | . | 0.286 | . | 0.271 |
| 1 | 58A ST1210 | 6.1 | (0.0020) | . | . | 0.0029 | (0.039) | 0.92 | 0.0012 | . | 0.034 | . | 0.056 |
| 1 | 58A ST2000a | 5.96 | (0.00024) | . | . | 0.0035 | 0.007 | 0.02 | 0.00094 | . | 0.097 | . | 0.0068 |
| 1 | 58A ST3320 | 5.82 | 0.00018 | . | . | 0.0016 | 0.0077 | 0.095 | 0.0012 | . | 1.54 | . | 0.128 |
| 1 | NCS HS49724-2 | 5.82 | 0.00018 | . | . | 0.0016 | 0.0077 | 0.095 | 0.0012 | . | 1.54 | . | 0.128 |
| 1 | 64X MgQ5A | 5.76 | 0.0013 | . | . | 0.0072 | 0.0043 | 0.276 | 0.0010 | 0.0056 | 0.052 | 0.0050 | 0.047 |
| 1 | 58A ST1260 | 4.56 | 0.0009 | . | . | 0.013 | 0.025 | (0.65) | 0.0025 | . | 0.241 | . | 0.106 |
| 1 | 64X MgQ2A | 4.53 | 0.0013 | . | . | 0.0151 | 0.0041 | 0.378 | 0.0061 | 0.0107 | 0.051 | 0.0107 | 0.107 |
| 1 | 58A ST3340 | 4.37 | 0.0009 | . | . | 0.103 | 0.022 | 0.33 | 0.0038 | . | 1.22 | . | 0.25 |
| 1 | NCS HS49724-4 | 4.37 | 0.0009 | . | . | 0.103 | 0.022 | 0.33 | 0.0038 | . | 1.22 | . | 0.25 |
| 1 | 65X MgA17A | 4.20 | . | 0.021 | 0.0049 | 0.0215 | 0.0069 | 0.203 | 0.0141 | 0.009 | 0.33 | 0.0050 | 0.128 |
| 1 | 64X MgQ7A | 4.20 | 0.00042 | . | . | 0.0167 | 0.0028 | (0.434) | 0.0053 | 0.0126 | (1.05) | 0.0096 | 0.0607 |
| 1 | 65X MgB4C | 3.86 | 0.0033 | 0.0010 | 0.00016 | 0.0183 | (0.009) | 0.031 | 0.0003 | 0.0037 | 0.037 | 0.0050 | 0.333 |
| 1 | 58A ST3310 | 3.69 | 0.00011 | . | . | 0.0084 | 0.007 | 0.59 | 0.0012 | . | 0.54 | . | 0.102 |
| 1 | NCS HS49724-1 | 3.69 | 0.00011 | . | . | 0.0084 | 0.0070 | 0.59 | 0.0012 | . | 0.54 | . | 0.102 |
| 1 | 58A ST3350 | 2.58 | 0.0012 | . | . | 0.039 | 0.033 | 0.23 | 0.014 | . | 1.83 | . | 0.152 |
| 1 | NCS HS49724-5 | 2.58 | 0.0012 | . | . | 0.039 | 0.033 | 0.23 | 0.014 | . | 1.83 | . | 0.152 |
| 1 | 58A ST1220 | 2.55 | 0.0009 | . | . | 0.0081 | 0.0089 | 0.338 | 0.0008 | . | 0.173 | . | 0.237 |
| 2 | AA C8209 | 2.55 | . | . | . | 0.012 | (0.02) | 0.15 | 0.001 | . | 0.058 | . | 0.18 |
| 1 | 64X MgQ6A | 2.31 | 0.0007 | . | . | 0.0045 | (0.004) | (0.260) | 0.0026 | 0.0060 | (0.97) | 0.0055 | 0.072 |
| 2 | AA C8211 | 2.07 | . | . | . | 0.033 | (0.02) | 0.20 | 0.007 | . | 0.090 | . | 0.23 |
| 1 | 58A ST3330 | 1.09 | (0.0005) | . | . | 0.016 | (0.0034) | (0.50) | (0.0013) | . | 0.68 | . | 0.339 |
| 1 | NCS HS49724-3 | 1.09 | (0.0005) | . | . | 0.16 | (0.0034) | (0.50) | (0.0013) | . | 0.68 | . | 0.339 |
| 1 | 64X MgQ1A | 1.083 | 0.00036 | . | . | 0.084 | 0.0034 | 0.377 | 0.0041 | 0.020 | 0.062 | 0.0195 | 0.235 |
| 1 | NCS HS49725-6 | (1.06) | . | . | . | 0.025 | 0.020 | 0.148 | 0.0052 | 0.018 | 0.020 | . | 0.025 |
| 1 | 64X MgQ8A | 1.03 | 0.00015 | . | . | 0.0019 | 0.0018 | 0.700 | 0.0004 | 0.0008 | 0.045 | 0.0022 | 0.044 |

| # | Number | Al | Be | Ca | Cd | Cu | Fe | Mn | Ni | Pb | Si | Sn | Zn |
|---|---------------|--------|--------|-------|----------|--------|----------|--------|----------------|----|----|----|----|
| | Number | Ag | Ce | Hg | La | Sr | Ti | Zr | ~mm Ø x ~mm H | | | | |
| | 58A ST2150 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 65X MgA15A | 0.030 | 0.0069 | 0.011 | 0.0048 | . | . | . | 50x20 or 40x15 | | | | |
| | 58A ZH2050M | . | . | . | . | . | . | . | ~49 x ~34 | | | | |
| | AA D3738 | . | . | . | . | . | . | . | 62 x 6 | | | | |
| | 64X MgQ3A | . | . | . | . | . | . | . | 50x20 or 40x15 | | | | |
| | 65X MgA5A | 0.0050 | . | . | . | 0.0004 | (0.001) | . | 50x20 or 40x15 | | | | |
| | 58A ST1240 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 64X MgQ4A | . | . | . | . | . | . | . | 50x20 or 40x15 | | | | |
| | 58A ST1250 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 58A ST1210 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 58A ST2000a | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 58A ST3320 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | NCS HS49724-2 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 64X MgQ5A | . | . | . | . | . | . | . | 40 x 15 | | | | |
| | 58A ST1260 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 64X MgQ2A | . | . | . | . | . | . | . | 50x20 or 40x15 | | | | |
| | 58A ST3340 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | NCS HS49724-4 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 65X MgA17A | 0.0064 | . | . | . | . | . | . | 50x20 or 40x15 | | | | |
| | 64X MgQ7A | . | . | . | . | . | . | . | 50x20 or 40x15 | | | | |
| | 65X MgB4C | 0.0046 | 0.0003 | . | (0.0001) | . | (0.0008) | <0.001 | 40 x 18 | | | | |
| | 58A ST3310 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | NCS HS49724-1 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 58A ST3350 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | NCS HS49724-5 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 58A ST1220 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | AA C8209 | . | . | . | . | . | . | . | 62 x 6 | | | | |
| | 64X MgQ6A | . | . | . | . | . | . | . | 50x20 or 40x15 | | | | |
| | AA C8211 | . | . | . | . | . | . | . | 62 x 6 | | | | |
| | 58A ST3330 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | NCS HS49724-3 | . | . | . | . | . | . | . | 45 x 25 | | | | |
| | 64X MgQ1A | . | . | . | . | . | . | . | 50x20 or 40x15 | | | | |
| | NCS HS49725-6 | . | . | . | . | . | 0.0025 | . | 45 x 25 | | | | |
| | 64X MgQ8A | . | . | . | . | . | . | . | 50x20 or 40x15 | | | | |
| | Number | Ag | Ce | Hg | La | Sr | Ti | Zr | ~mm Ø x ~mm H | | | | |

MAGNESIUM with ALUMINUM and ZINC

= class, where 1 = CRM and 2 = RM ##: not for Glow Discharge

| # | Number | Al | Zn | Be | Ca | Cd | Cu | Fe | Mn | Ni | Pb | Si | Sn |
|---|--------------|-------|-------|-----------|----------|--------|---------|---------|--------|---------|--------|---------|--------|
| 1 | 65X MgA21A | 12.37 | 5.11 | 0.0006 | . | . | 0.0020 | 0.0140 | 0.0777 | 0.0010 | 0.0048 | 0.028 | 0.0063 |
| 1 | 65X MgA23A | 9.72 | 0.543 | 0.0026 | . | . | 0.0153 | 0.0083 | 0.130 | 0.0011 | 0.0020 | 0.0270 | 0.0026 |
| 1 | 58A ST2160 | 9.07 | 0.98 | 0.0029 | . | . | 0.0098 | 0.039 | 0.61 | 0.0036 | . | 0.43 | . |
| 2 | 58A ZH2040M | 9.0 | 0.46 | 0.0013 | . | . | 0.222 | 0.01 | 0.57 | 0.015 | . | 0.285 | . |
| 1 | 65X MgA19A | 8.97 | 2.17 | 0.00025 | . | . | 0.0426 | 0.0085 | 0.322 | 0.0065 | 0.049 | 0.196 | 0.049 |
| 1 | 65X MgA22A | 8.60 | 0.882 | 0.0005 | . | . | 0.0783 | 0.0054 | 0.40 | 0.0057 | 0.0039 | (0.086) | 0.0032 |
| 2 | AA SM183-B | (8.0) | (3.0) | . | . | . | . | . | (0.2) | 0.005 | . | . | . |
| 2 | AA SM183-C | (8.0) | (3.0) | . | . | . | . | . | (0.2) | 0.005 | . | . | . |
| 2 | AA SM183-D | (8.0) | (3.0) | . | . | . | . | . | (0.2) | 0.005 | . | . | . |
| 2 | AA C3731G | 7.54 | 2.60 | . | . | . | 0.011 | . | 0.12 | 0.012 | . | 0.091 | . |
| 1 | 65X MgA13A | 7.45 | 0.925 | (0.010) | 0.0064 | 0.0055 | 0.125 | (0.008) | 0.092 | 0.0039 | 0.0085 | 0.022 | 0.043 |
| 2 | 58A ZH2030M | 6.97 | 0.71 | 0.0017 | . | . | 0.151 | 0.018 | 0.374 | 0.0096 | . | 0.183 | . |
| 1 | 58A ST2130 | 6.96 | 1.94 | 0.001 | . | . | 0.164 | 0.023 | 0.231 | (0.013) | . | 0.28 | . |
| 1 | 65X MgA16A | 6.78 | 4.03 | 0.0011 | 0.0024 | 0.0066 | 0.099 | 0.0073 | 0.271 | 0.0057 | 0.050 | 0.023 | 0.028 |
| 1 | 65X MgA18A | 6.75 | 0.502 | 0.00051 | . | . | 0.052 | 0.0081 | 0.192 | 0.0074 | 0.0244 | 0.043 | 0.0114 |
| 2 | AA SM145 | (6.7) | (2.4) | 0.003 | . | . | . | . | . | . | . | . | . |
| 1 | 58A ST2120a | 6.40 | 2.50 | 0.0004 | . | . | 0.080 | 0.008 | 0.35 | 0.0060 | . | 0.12 | . |
| 1 | 65X MgA20A | 5.87 | 1.32 | 0.0018 | . | . | 0.013 | 0.008 | 0.067 | 0.0025 | 0.0075 | 0.052 | 0.032 |
| 1 | 65X MgA12A | 5.68 | 3.18 | (0.0036) | 0.037 | 0.0121 | 0.266 | 0.0053 | 0.198 | 0.0148 | 0.010 | 0.0142 | 0.0021 |
| 1 | 65X MgAlJ ## | 5.45 | 1.26 | 0.006 | 0.029 | 0.013 | 0.221 | 0.021 | 0.060 | 0.021 | 0.012 | 0.20 | 0.072 |
| 2 | 58A ZH2020M | 5.06 | 0.95 | 0.0022 | . | . | 0.085 | 0.028 | 0.256 | 0.0047 | . | 0.10 | . |
| 1 | 58A ST2110a | 4.45 | 4.1 | (0.00015) | . | . | 0.00072 | 0.0029 | 0.077 | 0.00042 | . | 0.019 | . |
| 1 | 65X MgA11A | 3.63 | 1.59 | 0.0021 | 0.102 | 0.0014 | 0.0496 | 0.0048 | 0.044 | 0.0134 | 0.0190 | 0.022 | 0.093 |
| 1 | 65X MgB3C | 3.38 | 0.711 | 0.0019 | (0.0033) | 0.0025 | 0.022 | 0.0028 | 0.277 | 0.0027 | 0.0023 | 0.042 | 0.0017 |
| 2 | AA C7574 | 3.36 | (1.0) | . | . | . | . | . | (0.4) | . | . | . | . |
| 2 | 58A ZH2010M | 3.04 | 1.21 | 0.0032 | . | . | 0.0096 | 0.035 | 0.082 | 0.0006 | . | 0.037 | . |
| 2 | AA C7640 | (3.0) | 0.76 | . | . | . | . | . | (0.4) | . | . | . | . |
| 2 | AA C7641 | (3.0) | 1.36 | . | . | . | . | . | . | . | . | . | . |
| 2 | AA C7643 | (3.0) | (1.0) | . | . | . | 0.026 | . | 0.32 | 0.005 | . | 0.14 | . |
| 1 | 65X MgB2D | 2.81 | 1.047 | 0.0014 | (0.010) | 0.0103 | 0.065 | 0.0032 | 0.526 | 0.0043 | 0.0053 | (0.088) | 0.0052 |
| 1 | 65X MgB2C | 2.67 | 0.95 | 0.0008 | 0.011 | 0.0114 | 0.113 | (0.010) | 0.333 | 0.0027 | 0.0036 | 0.069 | 0.0047 |
| 2 | AA C7639 | 2.39 | (1.0) | . | . | . | . | . | (0.4) | . | . | . | . |
| 1 | 65X MgB1E | 1.90 | 1.60 | 0.0008 | (0.067) | 0.076 | 0.051 | 0.0027 | 0.770 | 0.0020 | 0.0095 | 0.069 | 0.0098 |
| 1 | 58A ST1270 | 1.36 | 0.492 | 0.0033 | . | . | 0.01 | 0.0049 | 0.13 | 0.01 | . | 0.065 | . |

| # | Number | Al | Zn | Be | Ca | Cd | Cu | Fe | Mn | Ni | Pb | Si | Sn |
|---|--------|----|----|----|----|----|----|----|----|----|----|----|----|
|---|--------|----|----|----|----|----|----|----|----|----|----|----|----|

| Number | Ag | Ce | Hg | La | Ti | Zr | ~mm Ø x ~mm H |
|--------------|----------|----------|---------|----------|---------|----------|----------------|
| 65X MgA21A | . | . | . | . | . | . | 50x20 or 40x15 |
| 65X MgA23A | . | . | . | . | . | . | 50x20 or 40x15 |
| 58A ST2160 | . | . | . | . | . | . | 45 x 25 |
| 58A ZH2040M | . | . | . | . | . | . | ~49 x ~34 |
| 65X MgA19A | . | . | . | . | . | . | 50x20 or 40x15 |
| 65X MgA22A | . | . | . | . | . | . | 40 x 15 |
| AA SM183-B | . | . | . | . | . | . | 62 x 6 |
| AA SM183-C | . | . | . | . | . | . | 62 x 6 |
| AA SM183-D | . | . | . | . | . | . | 62 x 6 |
| AA C3731G | . | . | . | . | . | . | 62 x 6 |
| 65X MgA13A | 0.0074 | 0.0024 | (0.033) | 0.0021 | . | . | 50x20 or 40x15 |
| 58A ZH2030M | . | . | . | . | . | . | ~49 x ~34 |
| 58A ST2130 | . | . | . | . | . | . | 45 x 25 |
| 65X MgA16A | 0.0035 | 0.0017 | 0.005 | 0.0012 | . | . | 50x20 or 40x15 |
| 65X MgA18A | . | . | . | . | . | . | 50x20 or 40x15 |
| AA SM145 | . | . | . | . | . | . | 62 x 6 |
| 58A ST2120a | . | . | . | . | . | . | 45 x 40 |
| 65X MgA20A | . | . | . | . | . | . | 50x20 or 40x15 |
| 65X MgA12A | 0.0128 | 0.0009 | (0.016) | 0.0007 | . | . | 50x20 or 40x15 |
| 65X MgAlJ ## | 0.012 | 0.009 | . | 0.007 | (0.005) | (0.0015) | 45 x 20 |
| 58A ZH2020M | . | . | . | . | . | . | ~49 x ~34 |
| 58A ST2110a | . | . | . | . | . | . | 45 x 25 |
| 65X MgA11A | (0.0002) | (0.0005) | 0.006 | (0.0005) | . | . | 50x20 or 40x15 |
| 65X MgB3C | 0.0028 | . | . | . | . | . | 50x20 or 40x15 |
| AA C7574 | . | . | . | . | . | . | 62 x 6 |
| 58A ZH2010M | . | . | . | . | . | . | ~49 x ~34 |
| AA C7640 | . | . | . | . | . | . | 62 x 6 |
| AA C7641 | . | . | . | . | . | . | 62 x 6 |
| AA C7643 | . | . | . | . | . | . | 62 x 6 |
| 65X MgB2D | 0.0099 | . | . | . | . | . | 50x20 or 40x15 |
| 65X MgB2C | 0.0098 | 0.0009 | . | 0.0007 | 0.0003 | <0.001 | 40 x 15 |
| AA C7639 | . | . | . | . | . | . | 62 x 6 |
| 65X MgB1E | 0.0300 | . | . | . | . | . | 50x20 or 40x15 |
| 58A ST1270 | . | . | . | . | . | . | 45 x 25 |

| Number | Ag | Ce | Hg | La | Ti | Zr | ~mm Ø x ~mm H |
|--------|----|----|----|----|----|----|---------------|
|--------|----|----|----|----|----|----|---------------|

MAGNESIUM with MANGANESE

= class, where 1 = CRM and 2 = RM

| # | Number | Mn | Al | Cu | Fe | Ni | Pb | Si | Sn | Zn | Ag | Ca | Cd | ~mm Ø x ~mm H |
|---|-----------|-------|---------|--------|--------|---------|--------|--------|--------|--------|--------|----------|--------|----------------|
| 2 | AA C8096 | 1.88 | (0.1) | (0.04) | . | (0.003) | . | (0.05) | . | (0.1) | . | . | . | 62 x 6 |
| 1 | 63X MgE2B | 1.76 | 0.045 | 0.0203 | 0.0019 | 0.0035 | 0.0020 | 0.019 | 0.0026 | 0.0243 | 0.0089 | (0.0016) | 0.0009 | 40 x 15 |
| 2 | AA SMD3A | 1.69 | 0.08 | 0.032 | . | 0.002 | . | 0.034 | . | 0.058 | . | . | . | 62 x 6 |
| 1 | 63X MgE3C | 1.62 | (0.056) | 0.0072 | 0.0005 | 0.0028 | 0.0046 | 0.014 | 0.006 | 0.0101 | 0.0041 | . | 0.0046 | 50x20 or 40x15 |
| 2 | AA C8095 | (1.6) | 0.17 | 0.012 | . | 0.005 | . | 0.052 | . | 0.029 | . | . | . | 62 x 6 |
| 2 | AA C8016 | (1.3) | 0.03 | 0.070 | . | 0.011 | . | 0.064 | . | 0.11 | . | . | . | 62 x 6 |
| 2 | AA C7857 | 1.07 | (0.1) | (0.03) | . | (0.001) | . | (0.05) | . | (0.1) | . | . | . | 62 x 6 |

CRM MAGNESIUM with STRONTIUM

| Class | Number | Sr | Units |
|-------|------------|--------|-----------------|
| CRM | 58A ST8240 | 0.028 | 45 mm Ø x 25 mm |
| CRM | 58A ST8220 | 0.015 | 45 mm Ø x 25 mm |
| CRM | 58A ST8230 | 0.0066 | 45 mm Ø x 25 mm |
| CRM | 58A ST8210 | 0.0014 | 45 mm Ø x 25 mm |

MAGNESIUM with ZINC

= class, where 1 = CRM and 2 = RM

| # | Number | Zn | Ag | Al | Be | Ca | Cu | Fe | Mn | Ni | Pb | Si | Sn | Sr | Zr | ~mm Ø x ~mm H |
|---|------------|-------|--------|---------|----------|----------|--------|---------|-------|---------|--------|--------|--------|-----------|--------|----------------|
| 1 | 58A ST5310 | 7.20 | . | 0.0040 | . | . | 1.64 | 0.0110 | 0.967 | 0.0020 | . | 0.025 | . | . | . | 45 x 35 |
| 1 | 66X MgC4C | 6.81 | 0.0074 | 0.039 | (0.0001) | (<0.001) | 0.0024 | 0.006 | 0.166 | 0.0009 | 0.0030 | 0.06 | 0.021 | (0.00014) | <0.001 | 50x20 or 40x15 |
| 1 | 58A ST7320 | 6.68 | . | (0.036) | . | . | 3.45 | 0.0069 | 0.361 | 0.00024 | . | 0.066 | . | . | . | 45 x 25 |
| 1 | 66X MgC5A | 6.61 | . | 0.072 | . | . | 0.0286 | 0.0008 | 1.17 | 0.0111 | 0.0281 | 0.026 | 0.0051 | . | . | 50x20 or 40x15 |
| 1 | 66X MgD5A | 6.25 | 0.044 | 0.040 | <0.0005 | (0.030) | 2.88 | 0.008 | 0.307 | 0.0120 | 0.097 | 0.134 | 0.104 | . | . | 50x20 or 40x15 |
| 1 | 58A ST5120 | 6.15 | . | . | . | . | . | . | . | . | . | 0.0015 | . | . | 0.2 | 45 x 25 |
| 1 | 58A ST5130 | 6.08 | . | . | . | . | . | . | . | 0.025 | . | . | . | . | 0.36 | 45 x 25 |
| 1 | 58A ST7330 | 6.01 | . | 0.205 | . | . | 2.76 | 0.019 | 0.57 | 0.055 | . | 0.144 | . | . | . | 45 x 25 |
| 1 | 58A ST7340 | 5.52 | . | 0.148 | . | . | 3.71 | (0.019) | 0.25 | 0.018 | . | 0.332 | . | . | . | 45 x 25 |
| 1 | 58A ST7350 | 4.76 | . | 0.106 | . | . | 4.17 | 0.016 | 0.133 | 0.0022 | . | 0.215 | . | . | . | 45 x 25 |
| 1 | 58A ST5110 | 4.71 | . | . | . | . | . | . | . | . | . | . | . | . | 0.17 | 45 x 25 |
| 2 | AA C7510 | 3.04 | . | . | 0.11 | . | 0.019 | . | . | 0.001 | . | . | . | . | . | 62 x 6 |
| 2 | AA SM176 | (3.0) | . | 0.19 | . | . | (0.03) | . | (0.2) | . | . | (0.1) | . | . | . | 62 x 6 |
| 2 | AA SM175 | (2.0) | . | 0.21 | . | . | (0.03) | . | (0.2) | . | . | (0.1) | . | . | . | 62 x 6 |

RM JEWELRY INDIVIDUAL XRF SAMPLES

analysis listed in mass % FLX 0740: 2mm Ø mounted in 36mm Ø x 10mm others: 3mm Ø mounted in 36mm Ø x 10mm

| Number | Ag | Au | Cu | Fe | Ir | Ni | Pd | Pt | Rh | Ru | W | Zn |
|----------|--------------|--------------|--------------|-------|-------|-------|--------------|--------------|--------------|-------|------|-----------------|
| FLX 0720 | . | 99.99 | 0.002 | . | 0.002 | . | 0.002 | 0.002 | 0.002 | . | . | . |
| FLX 1404 | . | 99.69 | . | . | . | . | . | . | . | . | . | Co: 0.310 |
| FLX 0701 | 4.59 | 91.76 | 3.65 | . | . | . | . | . | . | . | . | . |
| FLX 0702 | 4.60 | 90.12 | 5.28 | . | . | . | . | . | . | . | . | . |
| FLX 1405 | . | 81.89 | . | . | . | 18.11 | . | . | . | . | . | . |
| FLX 0743 | . | 80.07 | 1.12 | . | . | 14.35 | . | . | . | . | . | 4.46 |
| FLX 1402 | 5.16 | 76.37 | 10.29 | . | . | . | . | . | . | . | . | 8.18 |
| FLX 0703 | 4.18 | 75.14 | 4.93 | . | . | . | 15.75 | . | . | . | . | . |
| FLX 0708 | . | 75.12 | 17.47 | . | . | 5.81 | . | . | . | . | . | 1.60 |
| FLX 0726 | 10.16 | 75.11 | 14.73 | . | . | . | . | . | . | . | . | . |
| FLX 0728 | 4.79 | 75.1 | 20.11 | . | . | . | . | . | . | . | . | . |
| FLX 0727 | 8.98 | 75.07 | 15.95 | . | . | . | . | . | . | . | . | . |
| FLX 0724 | 15.07 | 75.05 | 9.88 | . | . | . | . | . | . | . | . | . |
| FLX 0725 | 12.54 | 75.03 | 12.43 | . | . | . | . | . | . | . | . | . |
| FLX 0705 | 10.09 | 75.03 | 4.83 | . | . | . | 10.05 | . | . | . | . | . |
| FLX 0704 | 2.75 | 75.03 | 9.74 | . | . | . | 12.48 | . | . | . | . | . |
| FLX 0707 | 2.75 | 75.02 | 15.13 | . | . | 5.04 | . | . | . | . | . | 2.06 |
| FLX 0706 | 13.13 | 75.0 | 5.42 | . | . | . | 6.45 | . | . | . | . | . |
| FLX 1302 | 15.16 | 59.13 | 17.31 | . | . | . | . | . | . | . | . | 8.40 |
| FLX 0710 | 30.94 | 59.06 | 3.48 | . | . | . | 6.52 | . | . | . | . | . |
| FLX 0709 | 21.93 | 59.02 | 4.05 | . | . | . | 15.0 | . | . | . | . | . |
| FLX 0903 | 4.32 | 58.69 | 36.99 | . | . | . | . | . | . | . | . | . |
| FLX 0738 | 19.7 | 58.65 | 19.22 | . | . | . | . | . | . | . | . | 2.43 |
| FLX 0904 | 13.77 | 58.65 | 27.58 | . | . | . | . | . | . | . | . | . |
| FLX 0905 | 25.06 | 58.64 | 14.92 | . | . | . | . | . | . | . | . | 1.38 |
| FLX 0715 | . | 58.64 | 26.18 | . | . | 6.09 | . | . | . | . | . | 9.09 |
| FLX 0736 | 33.01 | 58.61 | 7.89 | . | . | . | . | . | . | . | . | 0.49 |
| FLX 0712 | 27.36 | 58.59 | 4.05 | . | . | . | 10.0 | . | . | . | . | . |
| FLX 0735 | 6.65 | 58.58 | 31.08 | . | . | . | . | . | . | . | . | 3.69 |
| FLX 0739 | 33.39 | 58.53 | 8.08 | . | . | . | . | . | . | . | . | . |
| FLX 0729 | 29.42 | 58.52 | 12.06 | . | . | . | . | . | . | . | . | . |
| FLX 0711 | 10.72 | 58.49 | 26.47 | . | . | . | . | . | . | . | . | 4.32 |
| FLX 0713 | 4.84 | 58.47 | 24.91 | . | . | 8.39 | . | . | . | . | . | 3.39 |
| FLX 0714 | . | 58.44 | 41.31 | . | . | . | . | . | . | . | . | 0.25 |
| FLX 0744 | 26.84 | 55.37 | 10.09 | . | . | . | 6.49 | . | . | . | . | 1.21 |
| FLX 0737 | 6.15 | 38.35 | 46.89 | . | . | . | . | . | . | . | . | 8.61 |
| FLX 1301 | 45.83 | 37.63 | 12.67 | . | . | . | . | . | . | . | . | 3.87 |
| FLX 0716 | 15.09 | 37.63 | 37.97 | . | . | . | . | . | . | . | . | 9.31 |
| FLX 0731 | 54.31 | 37.52 | 8.17 | . | . | . | . | . | . | . | . | . |
| FLX 0732 | 58.75 | 33.71 | 7.54 | . | . | . | . | . | . | . | . | . |
| FLX 0734 | 6.3 | 33.65 | 50.28 | . | . | . | . | . | . | . | . | 9.77 |
| FLX 1401 | 33.00 | 33.61 | 33.36 | . | . | . | . | . | . | . | . | 0.030 |
| FLX 0718 | 6.21 | 33.56 | 49.69 | . | . | . | . | . | . | . | . | 10.54 |
| FLX 0717 | 11.92 | 33.52 | 41.04 | . | . | . | . | . | . | . | . | 13.52 |
| FLX 1403 | 5.90 | 29.36 | 53.80 | 0.010 | . | 0.200 | 0.030 | 0.010 | . | . | . | 10.68 Cd: 0.010 |
| FLX 0721 | 99.97 | . | 0.008 | . | 0.005 | . | 0.005 | 0.007 | 0.005 | . | . | . |
| FLX 0719 | 99.94 | . | 0.06 | . | . | . | . | . | . | . | . | . |
| FLX 0730 | 93.56 | . | 6.44 | . | . | . | . | . | . | . | . | . |
| FLX 1303 | 92.76 | . | 4.92 | . | . | . | . | . | . | . | . | 2.32 |
| FLX 0733 | 83.75 | . | 16.25 | . | . | . | . | . | . | . | . | . |
| FLX 1406 | 34.98 | . | 6.50 | . | . | . | 58.52 | . | . | . | . | . |
| FLX 0742 | 0.005 | . | 99.99 | 0.005 | . | . | . | . | . | . | . | . |
| FLX 0740 | . | . | 0.005 | 0.09 | . | . | . | . | 99.90 | 0.005 | . | . |
| FLX 0723 | . | . | 0.01 | 0.01 | . | . | 99.96 | 0.01 | 0.01 | . | . | . |
| FLX 0722 | . | . | . | . | 0.02 | . | 0.02 | 99.95 | 0.01 | . | . | . |
| FLX 0741 | . | . | 4.16 | . | . | . | . | 95.84 | . | . | 4.63 | . |
| FLX 0902 | . | . | . | . | . | . | . | 95.37 | . | . | . | . |
| FLX 0901 | . | . | . | . | . | . | . | 95.23 | . | 4.77 | . | . |
| FLX 1202 | . | . | . | . | 10.0 | . | . | 90.0 | . | . | . | . |
| FLX 1201 | . | . | . | . | 25.0 | . | . | 75.0 | . | . | . | . |
| Number | Ag | Au | Cu | Fe | Ir | Ni | Pd | Pt | Rh | Ru | W | Zn |

RM LARGER JEWELRY SAMPLES

16 mm Ø mounted in 36mm Ø x 10mm

| Number | Ag | Au | Cu | Ni | Pd | Zn |
|--------------|------|------------------|-----------------|------------------|-----------------|-------|
| FLX 0720-16 | . | 99.99 | 0.002 | . | . | . |
| FLX 0720-16a | . | 99.99 | . | . | . | . |
| FLX 0743-16 | . | 80.15 | 1.05 | 14.53 | 4.27 | . |
| FLX 0704-16c | 3.05 | 75.08 | 9.37 | . | 12.5 | . |
| FLX 0715-16 | . | 59.12 | 25.15 | 6.54 | . | 9.19 |
| FLX 0715-16a | 9.05 | 59.10 | 25.74 | 6.11 | . | . |
| FLX 0738-16 | 19.8 | 58.58 | 21.1 | . | . | 0.52 |
| FLX 0744-16 | 26.8 | 55.68 | 9.43 | . | 6.57 | 1.52 |
| FLX 0732-16 | 57.1 | 33.46 | 9.44 | . | . | . |
| FLX 0734-16a | 7.09 | 33.41 | 48.82 | . | . | 10.68 |

Ir, Pd, Pt, Rh: 0.002

last of stock

<- THIS ONE SOLD OUT

last of stock

CRM GOLD ALLOYS

analysis listed in mass % ~16 mm disc mounted in acrylic 40 mm Ø x 5 mm

| Number | Alloy | Ag | Au | Cu | Ni | Zn |
|-----------|-------------|-------|-------|-------|------|-------|
| ERM-EB508 | Yellow Gold | 24.90 | 75.12 | . | . | . |
| ERM-EB507 | White Gold | 3.02 | 75.10 | 14.69 | 4.99 | 2.107 |
| ERM-EB506 | Rose Gold | 3.90 | 58.56 | 35.65 | . | 1.891 |

SILVER

analysis listed in mg/kg 131X PAG: RM, 34 Ø x 12mm 131X PAG: RM, 25 Ø x 3mm IMN SH: CRM 40 Ø x ~15-20mm IMN SJ: 40 mm Ø x ~15-20 mm

| Number | Cu | Al | As | Au | Bi | Cd | Fe | Ga | In | Ir | Mn | Ni | P | Pb | Pd | Pt | Rh | Sb | Se | Si | Sn | Te | Tl | Zn |
|------------|-------|----|------|------|------|------|------|----|------|------|------|------|---|------|------|------|----|------|------|----|-----|------|--------|-------|
| 131X ACP1B | 815 | . | 145 | 521 | 523 | 377 | 57 | . | . | . | 404 | 276 | . | 420 | 332 | 505 | . | 485 | 299 | . | 505 | 435 | . | 502 |
| 131X PAG2A | 400 | 2 | 8 | 20 | 12 | 5 | 7 | 15 | . | 0.02 | 10 | 9 | 2 | 12 | 180 | 10 | 2 | 12 | 10 | 4 | 14 | 15 | . | 40 |
| IMN SJ2 | 306.0 | . | 41.3 | 35.4 | 47.4 | 21.2 | 26.4 | . | 49.2 | . | 46.1 | 49.7 | . | 82.5 | 41.5 | 44.4 | . | 81.2 | 45.7 | . | . | 43.0 | 40.5 | 135.1 |
| 131X AGP2B | 193 | . | 29 | 114 | 96 | 56 | (20) | . | . | . | 49 | 57 | . | 75 | 105 | 112 | . | 107 | 65 | . | 95 | 90 | . | 109 |
| 131X PAG1A | 75 | 8 | 12 | 120 | 40 | 35 | 5 | 60 | . | 0.02 | 35 | 25 | 4 | 40 | 180 | 35 | <1 | 50 | 35 | 30 | 40 | 120 | . | 50 |
| 131X AGP3B | 66 | . | 6 | 26 | 12 | 6 | (11) | . | . | . | 3 | 12 | . | 12 | 16 | 23 | . | 21 | 16 | . | 22 | 18 | . | 34 |
| IMN SH3 | 59.0 | . | 11.0 | 7.7 | 9.2 | 9.6 | 11.3 | . | 8.7 | . | 27.3 | 29.7 | . | 44.9 | 25.7 | 25.4 | . | 48.6 | 8.7 | . | . | 25.7 | 25.8 | 43.8 |
| 131X AGP4B | 41 | . | 3 | 9 | 7 | 2 | (23) | . | . | . | 3 | 6 | . | 5 | 7 | 7 | . | 12 | 6 | . | 6 | 5 | . | 20 |
| IMN SJ1 | 15.3 | . | 1.8 | 4.9 | 1.4 | 2.2 | 2.1 | . | 1.4 | . | 6.5 | 2.6 | . | 7.2 | 2.0 | 1.2 | . | 1.5 | 1.2 | . | . | 1.6 | (0.70) | 382.6 |

RM SILVER ALLOYS

analysis in mass %

| Number | Ag | Au | Cu | Pb | Zn | Units |
|--------------|-------|-------|-------|-------|------|-------------------|
| 132X AGB100C | 99.94 | . | 0.009 | . | . | -40 mm Ø x ~10 mm |
| 132X AGB100A | 99.89 | . | 0.136 | . | . | -40 mm Ø x ~10 mm |
| 132X AGB100B | 99.84 | . | 0.012 | . | . | -40 mm Ø x ~10 mm |
| 132X AGB94A | 93.98 | . | 5.83 | . | . | -40 mm Ø x ~10 mm |
| 132X AGB93B | 92.70 | . | 7.27 | . | . | -40 mm Ø x ~10 mm |
| 132X 925Zn1B | 92.70 | . | 6.09 | . | 1.39 | 25 mm Ø x 3 mm |
| 132X 925Zn3B | 92.64 | . | 4.53 | . | 2.88 | 25 mm Ø x 3 mm |
| 132X AGB90A | 90.16 | . | 9.56 | . | . | -40 mm Ø x ~10 mm |
| 132X AGB90B | 89.73 | . | 10.24 | . | . | -40 mm Ø x ~10 mm |
| 132X AGB88B | 88.12 | . | 11.87 | . | . | -40 mm Ø x ~10 mm |
| 132X AGB87B | 87.13 | . | 12.67 | . | . | -40 mm Ø x ~10 mm |
| 132X AGB85C | 84.87 | . | 15.09 | . | . | -40 mm Ø x ~10 mm |
| 132X AGB75B | 75.20 | . | 24.75 | . | . | -40 mm Ø x ~10 mm |
| 132X AGB75C | 75.11 | . | 24.53 | . | . | -40 mm Ø x ~10 mm |
| 133X AGQ3C | rem | 1.975 | 9.612 | 0.921 | . | 25 mm Ø x 3 mm |
| 133X AGQ2C | rem | 0.978 | 5.808 | 0.469 | . | 25 mm Ø x 3 mm |
| 133X AGQ1C | rem | 0.251 | 2.532 | 0.245 | . | 25 mm Ø x 3 mm |

RM SILVER ALLOYS

analysis in mass %

| Number | Au | Bi | Cu | Pb | Sb | Se | Si | Sn | Zn | Al | As | Cd | Co | Cr | Fe | Ge | In |
|-------------|-------|--------|--------|-------|-------|--------|--------|-------|-------|----------|--------|--------|--------|--------|---------|--------|--------|
| 133X AGA1A | 1.48 | 0.194 | 19.95 | 0.207 | 0.050 | 0.0169 | . | 0.291 | 0.211 | 0.0096 | 0.0255 | 0.0165 | 0.0406 | . | 0.039 | 0.0107 | 0.0037 |
| 133X AGA2A | 0.507 | 0.113 | 10.00 | 1.02 | 0.192 | 0.0078 | . | 0.520 | 0.502 | 0.0019 | 0.0144 | 0.0113 | 0.0163 | . | 0.027 | 0.0047 | 0.0065 |
| 133X AGA3A | 0.258 | 0.048 | 4.91 | 1.89 | 0.459 | 0.0044 | . | 0.921 | 0.816 | (0.0020) | 0.0080 | 0.0042 | 0.0050 | . | (0.015) | 0.0045 | 0.0134 |
| 131X AgSe2A | . | 0.0790 | 0.1333 | . | . | 0.0465 | 0.0039 | . | . | 0.0043 | . | . | . | 0.0037 | 0.0022 | . | . |
| 131X AgSe1A | . | 0.0304 | . | . | . | 0.0162 | . | . | . | . | . | . | . | . | 0.0023 | . | . |

| Number | Mn | Ni | Pd | Pt | Te | Units |
|-------------|--------|--------|--------|--------|--------|-------------------|
| 133X AGA1A | 0.0061 | 0.0118 | 0.0054 | 0.0067 | 0.0271 | ~25 mm Ø x ~3 mm |
| 133X AGA2A | 0.0115 | 0.0264 | 0.0076 | 0.0114 | 0.0098 | ~25 mm Ø x ~3 mm |
| 133X AGA3A | 0.0098 | 0.0450 | 0.0156 | 0.0256 | 0.0054 | ~25 mm Ø x ~3 mm |
| 131X AgSe2A | . | . | . | . | . | -40 mm Ø x ~10 mm |
| 131X AgSe1A | . | . | . | . | . | -40 mm Ø x ~10 mm |

TIN

= class, where 1 = CRM and 2 = RM

analysis listed in mass %

* Provisional Analysis

| # | Number | Ag | Al | As | Au | Bi | C | Cd | Co | Cr | Cu | Fe | Ga | Ge | Hg | In |
|---|------------|---------------|----------|---------------|--------|----------|-------|---------|----------|-----------|----------|-----------|--------|--------|---------|----------|
| 2 | BCS 192g | . | . | . | . | . | 0.001 | . | . | . | 0.00007 | 0.0002 | . | . | . | . |
| 1 | 71X SR3F | 0.050 | (0.0014) | 0.097 | 0.0145 | 0.123 | . | 0.100 | . | . | 0.121 | 0.0203 | 0.0339 | . | 0.115 | 0.104 |
| 1 | 71X SR2F | 0.0305 | 0.0022 | 0.0070 | 0.0077 | 0.0403 | . | 0.0351 | 0.0064 | 0.0031 | 0.116 | 0.0133 | . | 0.009 | 0.141 | 0.0597 |
| 1 | 71X SR1F * | 0.012 | . | 0.003 | 0.002 | 0.010 | . | 0.011 | . | . | 0.002 | 0.007 | . | 0.011 | 0.018 | 0.010 |
| 1 | 71X SR0C | 0.0024 | 0.0414 | 0.00053 | 0.0012 | 0.0029 | . | 0.0024 | 0.00040 | . | 0.0073 | 0.0040 | 0.0054 | 0.0021 | 0.0099 | 0.0088 |
| 1 | SRM 1727 | . | . | (<0.0100) | . | (0.0008) | . | . | (0.0002) | . | (0.0004) | (0.0020) | . | . | . | (0.0020) |
| 1 | SRM 1728 | 0.4591 | . | . | . | (0.0128) | . | 0.00582 | (0.0057) | (0.00012) | 3.06 | 0.0111 | . | . | 0.01198 | (0.0031) |
| 1 | SRM 1729 | (<0.0075) | (0.0460) | . | . | 0.01147 | . | . | . | . | (0.0024) | (0.00141) | . | . | . | . |

| Number | Ni | P | Pb | S | Sb | Se | Si | Sn | Te | Tl | Zn | Melt °C | Units |
|------------|-----------|----------|----------|---------|-----------|--------|----------|--------|--------|-------|----------|---------|----------------------------|
| BCS 192g | 0.00005 | . | 0.00007 | . | . | . | . | 99.997 | . | . | 0.00006 | 231.9 | 300 g block or 100 g chips |
| 71X SR3F | 0.0371 | . | 0.306 | . | 0.128 | 0.0031 | . | . | 0.070 | . | 0.054 | . | ~40 mm Ø x ~15 mm |
| 71X SR2F | 0.0183 | (0.007) | 0.151 | . | 0.074 | . | . | . | 0.0246 | 0.005 | 0.0058 | . | ~40 mm Ø x ~15 mm |
| 71X SR1F * | 0.007 | . | 0.026 | . | 0.018 | 0.005 | . | . | 0.001 | . | 0.020 | . | ~40 mm Ø x ~15 mm |
| 71X SR0C | 0.0025 | 0.0004 | 0.0457 | . | 0.0055 | 0.0006 | . | . | 0.0021 | . | 0.0053 | . | ~40 mm Ø x ~15 mm |
| SRM 1727 | (0.0003) | . | 0.003326 | . | (0.0040) | . | . | . | . | . | . | . | 30 mm x 30 mm x 30 mm |
| SRM 1728 | 0.00817 | (0.0010) | 0.0544 | 0.00349 | (0.0087) | . | (0.0045) | (96.3) | . | . | (0.0156) | . | 39 mm Ø x 15 mm |
| SRM 1729 | (0.00022) | . | 0.000311 | . | (0.00964) | . | (0.0020) | (96.9) | . | . | 0.0518 | . | 39 mm Ø x 15 mm |

RM

TIN - LOW ALLOY

37 mm Ø x 12 mm

| Number | Ag | Al | As | Bi | Cd | Co | Cu | Fe | In | Ni | Pb | Sb | Sn | Zn |
|---------|-------|-------|--------|-------|--------|-------|------|--------|-------|-------|------|-------|-----|--------|
| NF 54-1 | 0.005 | 0.005 | <0.1 | 0.002 | 0.0002 | 0.002 | 0.01 | <0.1 | 0.005 | 0.002 | 0.03 | 0.005 | Rem | <0.1 |
| NF 54-2 | 0.01 | 0.01 | <0.1 | 0.005 | 0.0005 | 0.005 | 0.05 | <0.1 | 0.01 | 0.005 | 0.15 | 0.01 | Rem | <0.1 |
| NF 54-3 | 0.03 | 0.03 | <0.5 | 0.01 | 0.001 | 0.01 | 0.15 | <0.1 | 0.02 | 0.01 | 0.40 | 0.02 | Rem | <0.1 |
| NF 54-4 | 0.06 | . | <0.5 | 0.02 | 0.005 | 0.02 | 0.30 | <0.1 | 0.04 | 0.02 | 0.70 | 0.04 | Rem | <0.1 |

RM

BISMUTH AND SULPHUR IN TIN

certified analysis in bold, rest is informational composition

37 mm Ø x 12 mm

| Number | Bi | S | Ag | Al | As | Au | Cd | Cu | Fe | In | Ni | P | Pb | Sb | Sn | Zn |
|---------|-------------|--------------------------------|-------|----------|---------|----------|----------|-------|----------|-------|----------|---------|-------|-------|-----|----------|
| NF 60-4 | 3.99 | <0.001 | 0.001 | <0.001 | <0.01 | <0.001 | <0.001 | 0.001 | <0.001 | 0.005 | <0.001 | <0.01 | Rem | 0.005 | 60 | <0.001 |
| NF 60-3 | 3.00 | <0.001 | 0.001 | <0.001 | <0.01 | <0.001 | <0.001 | 0.001 | <0.001 | 0.005 | <0.001 | <0.01 | Rem | 0.005 | 60 | <0.001 |
| NF 60-2 | 2.39 | <0.001 | 0.001 | <0.001 | <0.01 | <0.001 | <0.001 | 0.001 | <0.001 | 0.005 | <0.001 | <0.01 | Rem | 0.005 | 60 | <0.001 |
| NF 60-1 | 2.01 | <0.001 | 0.001 | <0.001 | <0.01 | <0.001 | <0.001 | 0.001 | <0.001 | 0.005 | <0.001 | <0.01 | Rem | 0.005 | 60 | <0.001 |
| NF 59-5 | 0.008 | 0.020 | 3.98 | <0.001 | <0.01 | <0.001 | <0.001 | 0.51 | 0.005 | 0.006 | 0.001 | <0.01 | 0.056 | 0.023 | Rem | 0.001 |
| NF 59-4 | 0.008 | 0.0085 | 3.98 | <0.001 | <0.01 | <0.001 | <0.001 | 0.51 | 0.005 | 0.006 | 0.001 | <0.01 | 0.056 | 0.023 | Rem | 0.001 |
| NF 59-3 | 0.008 | 0.0048 | 3.98 | <0.001 | <0.01 | <0.001 | <0.001 | 0.51 | 0.005 | 0.006 | 0.001 | <0.01 | 0.056 | 0.023 | Rem | 0.001 |
| NF 59-2 | 0.008 | 0.0007 | 3.98 | <0.001 | <0.01 | <0.001 | <0.001 | 0.51 | 0.005 | 0.006 | 0.001 | <0.01 | 0.056 | 0.023 | Rem | 0.001 |
| NF 59-1 | 0.008 | <0.0006 | 3.98 | <0.001 | <0.01 | <0.001 | <0.001 | 0.51 | 0.005 | 0.006 | 0.001 | <0.01 | 0.056 | 0.023 | Rem | 0.001 |

CRM

SPECIALTY TIN BASE LOW-LEAD and LEAD-FREE SOLDERS

analysis listed in mass %

~40 mm Ø x ~15 mm

| Number | Ag | Al | As | Au | Bi | Cd | Co | Cu | Fe | Ge | Hg | In | Ni | P | Pb | S | Sb | Se | Zn |
|-----------|-------|-----------|--------|----------|--------|---------|----------|--------|----------|--------|--------|--------|--------|-----------|--------|------|------------------------------|----------|----------|
| 74X CA5B | 4.09 | (0.0014) | 0.0125 | 0.0091 | 0.0050 | 0.0023 | . | 1.189 | 0.0021 | . | 0.0030 | 0.0129 | 0.0149 | (0.011) | 0.044 | . | 0.124 | (0.0004) | (0.0019) |
| 74X CA7B | 4.02 | Cr:0.0045 | 0.0085 | . | 0.0102 | 0.0059 | (0.0018) | 0.347 | 0.007 | . | 0.049 | 0.0053 | 0.0315 | . | 0.107 | . | 0.0194 | . | 0.0501 |
| 74X AB1A | 3.58 | . | 0.0280 | 0.0010 | 0.997 | 0.0199 | 0.0032 | 0.0285 | 0.0435 | . | . | 0.0262 | 0.0036 | . | 0.0353 | . | 0.0111 | . | . |
| 74X CA2C* | 3.45 | 0.002 | 0.015 | . | 0.030 | 0.003 | 0.003 | 0.78 | (0.002) | 0.015 | 0.005 | 0.006 | 0.033 | . | 0.055 | . | * Provisional Analysis 0.001 | | |
| 74X CA4C | 3.01 | 0.0005 | 0.0076 | . | 0.0608 | 0.0018 | 0.0052 | 0.545 | 0.0052 | . | 0.0054 | 0.0057 | 0.0872 | Cr:0.0094 | 0.0800 | . | 0.0709 | (0.0007) | (0.0055) |
| 74X CA3B | 2.98 | 0.0010 | 0.0039 | 0.007 | 0.0156 | 0.00045 | . | 0.0869 | 0.006 | 0.0093 | . | 0.0042 | 0.0077 | 0.031 | 0.0491 | . | 0.0266 | . | 0.0009 |
| 74X HAG | 2.80 | (0.002) | 0.0032 | . | 0.0639 | 0.0018 | . | 0.629 | 0.0029 | . | . | 0.0090 | 0.0133 | (0.0009) | 0.077 | . | 2.10 | (0.0008) | 2.73 |
| 74X CA8B | 2.47 | . | 0.0144 | . | 0.0172 | 0.0101 | 0.0202 | 0.950 | 0.0043 | 0.0020 | 0.101 | 0.0062 | 0.0020 | 0.010 | 0.084 | . | 0.0180 | . | . |
| 74X CA9A | 1.002 | 0.0007 | 0.0173 | 0.0025 | 0.0364 | 0.0015 | . | 0.097 | 0.0085 | 0.0049 | . | 0.0165 | 0.0039 | 0.011 | 0.038 | . | 0.076 | . | 0.0010 |
| 74X EF | 0.667 | (0.0012) | 0.0092 | . | 0.0099 | 0.0003 | . | 2.94 | 0.0008 | . | . | 0.0074 | 0.0069 | (0.0012) | 0.0248 | . | 0.0168 | 0.0008 | (0.0054) |
| 74X AMF | 0.496 | (0.0012) | 0.0038 | . | 0.190 | 0.0061 | . | 3.07 | (0.0006) | . | . | 0.0082 | 0.0260 | (0.0016) | 0.126 | . | 1.064 | (0.0013) | (0.0055) |
| 74X CALB | 0.440 | 0.0262 | . | 0.0053 | 0.0131 | 0.0071 | . | 0.682 | . | . | . | . | . | . | 0.077 | . | 0.0169 | . | . |
| 74X CA6B | 0.305 | (0.0003) | 0.0133 | 0.0050 | 0.0098 | 0.0005 | . | 0.602 | 0.0120 | . | 0.0039 | 0.0243 | 0.0246 | (0.001) | 0.0287 | . | (0.01) | (0.0005) | (0.0005) |
| 74X WSA | 0.298 | (0.0007) | 0.0105 | (0.0002) | 0.0063 | 0.00140 | . | 4.58 | (0.0036) | . | . | 0.0032 | 0.0048 | 0.0122 | 0.037 | . | 1.49 | . | 0.0009 |
| 74X HNF | 0.160 | 0.0011 | 0.016 | . | 0.042 | 0.0046 | . | 4.12 | 0.0020 | . | . | 0.0052 | 0.195 | (0.001) | 0.0050 | . | 0.038 | 0.0024 | 0.0068 |
| 74X HNE | 0.143 | 0.005 | 0.010 | . | 0.122 | 0.0057 | . | 3.82 | 0.010 | . | . | . | 0.185 | (0.002) | 0.0404 | last | 0.037 | 0.0016 | (0.0009) |
| 74X OAA | 0.100 | (0.0007) | 0.080 | (0.0001) | 1.065 | 0.00063 | . | 3.41 | 0.007 | . | . | 0.0034 | 0.0025 | 0.0072 | 0.128 | . | 0.0098 | . | (0.002) |
| 74X HBG | 0.086 | (0.0026) | 0.045 | . | 0.038 | 0.0103 | . | 4.49 | 0.0138 | . | . | 0.0179 | 1.22 | (0.002) | 0.056 | . | 4.81 | 0.0038 | (0.02) |
| 74X GE2A | 0.079 | 0.068 | . | . | . | 0.0086 | . | 0.713 | . | 0.479 | . | . | 0.031 | . | 0.0467 | . | . | . | . |
| 74X GE1A | 0.052 | 0.065 | . | . | . | 0.0059 | . | 0.662 | . | 0.046 | . | . | 0.0289 | . | 0.0339 | . | . | . | . |
| 74X TCF | 0.039 | (0.001) | 0.024 | . | 0.106 | 0.0150 | . | 4.99 | 0.0031 | . | . | 0.0215 | 0.0167 | (0.002) | 0.183 | . | 0.124 | 0.0473 | 0.004 |
| 74X BZ1A | 0.004 | 0.0021 | 0.0119 | . | 3.03 | 0.0012 | . | 0.026 | 0.011 | . | . | . | 0.0097 | . | 0.0238 | . | 0.031 | . | 8.27 |

RM TIN - SILVER ALLOYS 37 mm Ø x 12 mm

| Number | Ag | Bi | Cu | Ge | Hg | In | Ni | P | Pb | Sb | Sn | Zn |
|---------|-------|-------|-------|-------|--------|--------|--------|-------|--------|-------|-------|---------|
| NF 46-3 | 5.0 # | 0.25 | 0.030 | | | | | | 0.21 | 0.059 | Rem | (0.017) |
| NF 56-5 | 4.49 | 0.029 | 0.54 | | 0.0024 | | | 0.006 | 0.26 | | Rem | |
| NF 56-6 | 4.24 | 0.096 | 0.80 | | 0.009 | | | 0.012 | 0.024 | | Rem | |
| NF 46-2 | 4.1 | 0.095 | 0.096 | | | | | | 0.059 | 0.11 | Rem | (0.007) |
| NF 57-2 | 4.01 | | 0.46 | | 0.0002 | | | 0.006 | <0.001 | | Rem | |
| NF 56-2 | 3.77 | 0.50 | 0.60 | | 0.0004 | | | 0.009 | 0.051 | | Rem | |
| NF 56-3 | 3.53 | | 0.4 | | 0.014 | | | 0.003 | 0.009 | 0.50 | Rem | |
| NF 56-4 | 3.26 | 0.20 | 0.30 | | 0.0045 | | | 0.021 | 0.22 | | Rem | |
| NF 46-1 | 3.1 | 0.05 | 0.19 | | | | | | 0.043 | 0.205 | Rem | (0.015) |
| NF 57-1 | 3.00 | 0.004 | 0.49 | | 0.0016 | | | 0.004 | 0.076 | | Rem | |
| NF 9-1 | 3.00 | 0.048 | 0.073 | | | | | | Rem | 0.51 | 59.90 | |
| NF 61-4 | 2.58 | | | | | | | | Rem | | 62.0 | |
| NF 63-6 | 2.56 | | 0.50 | 0.042 | | <0.001 | 0.0073 | | 0.009 | | Rem | |
| NF 56-1 | 2.54 | 0.006 | 0.91 | | 0.018 | | | 0.020 | 0.10 | | Rem | |
| NF 61-3 | 2.33 | | | | | | | | Rem | | 62.0 | |
| NF 9-2 | 2.00 | 0.093 | 0.040 | | | | | | Rem | 0.38 | 61.90 | |
| NF 61-2 | 1.81 | | | | | | | | Rem | | 62.0 | |
| NF 61-1 | 1.54 | | | | | | | | Rem | | 62.0 | |
| NF 63-4 | 1.50 | | 0.194 | 0.025 | | 0.027 | 0.12 | | 0.012 | | Rem | |
| NF 63-3 | 1.18 | | 0.53 | 0.005 | | 0.053 | 0.066 | | 0.024 | | Rem | |
| NF 63-2 | 1.02 | | 0.104 | 0.052 | | 0.005 | 0.027 | | 0.18 | | Rem | |
| NF 63-5 | 1.01 | | 0.51 | 0.010 | | 0.11 | 0.065 | | 0.018 | | Rem | |
| NF 9-3 | 1.00 | 0.25 | 0.010 | | | | | | Rem | 0.23 | 63.60 | |
| NF 63-1 | 0.74 | | 0.077 | 0.079 | | 0.200 | 0.068 | | 0.009 | | Rem | |
| NF 58-3 | 0.51 | 0.077 | 0.59 | | 0.0043 | | | 0.010 | 0.040 | | Rem | |
| NF 58-1 | 0.32 | 0.12 | 0.69 | | 0.0003 | | | 0.001 | 0.085 | | Rem | |
| NF 58-2 | 0.21 | 0.095 | 0.79 | | 0.0024 | | | 0.006 | 0.008 | | Rem | |

CRM TIN BASE SETS available in sets only, as grouped

| Number | Ag | Al | As | Au | Bi | Cd | Cu | Fe | In | Ni | Pb | Sb | Sn | Zn |
|-----------|--------|----------|----------|--------|--------|---------|--------|----------|--------|--------|--------|--------|-------|----------|
| IMN LBA 1 | 0.632 | | 0.0459 | 0.0115 | 0.230 | 0.00085 | 0.282 | 0.0195 | 0.208 | 0.0055 | 0.228 | 0.0517 | Rem | 0.0032 |
| IMN LBA 2 | 0.697 | (0.0029) | 0.0314 | 0.0259 | 0.175 | 0.0052 | 0.487 | 0.0182 | 0.127 | 0.0107 | 0.319 | 0.0979 | Rem | 0.0047 |
| IMN LBA 3 | 0.0971 | 0.0022 | 0.0239 | 0.0468 | 0.0989 | 0.0039 | 0.885 | 0.0057 | 0.0949 | 0.0224 | 0.141 | 0.142 | Rem | 0.0020 |
| IMN LBA 4 | 0.0976 | 0.0061 | (0.0086) | 0.0632 | 0.0364 | 0.0058 | 1.21 | 0.0114 | 0.0503 | 0.0320 | 0.0862 | 0.457 | Rem | 0.0006 |
| IMN LBA 5 | 0.214 | | (0.0090) | 0.691 | 0.325 | 0.0053 | 0.763 | 0.0098 | 0.0228 | 0.0346 | 0.0579 | 0.286 | Rem | (0.0009) |
| IMN LCA 1 | 0.210 | <0.0012 | 0.0494 | 0.0677 | 0.269 | 0.0093 | | | 0.141 | | 0.229 | 0.490 | Rem | |
| IMN LCA 2 | 0.158 | | 0.0864 | 0.0542 | 0.146 | 0.0073 | 2.67 | 0.0155 | 0.0610 | 0.0210 | 0.0773 | 0.138 | Rem | 0.0016 |
| IMN LCA 3 | 0.107 | (0.0011) | 0.0285 | 0.0260 | 0.100 | 0.0025 | 3.53 | 0.0143 | 0.0081 | 0.0102 | 0.137 | 0.101 | Rem | 0.0042 |
| IMN LCA 4 | 0.0545 | (0.0023) | 0.0145 | 0.0100 | 0.0403 | 0.0115 | 4.51 | 0.0101 | 0.0442 | 0.0056 | 0.0890 | 0.0479 | Rem | 0.0103 |
| IMN LCA 5 | 0.221 | | 0.0386 | 0.0670 | 0.263 | 0.0006 | 1.52 | 0.0295 | 0.0533 | 0.0315 | 0.232 | 0.458 | Rem | 0.0011 |
| IMN L89 1 | | | 0.019 | | 0.012 | 0.19 | 3.20 | 0.18 | | 0.010 | 0.072 | 5.66 | Rem | 0.099 |
| IMN L89 2 | | | 0.037 | | 0.026 | 0.091 | 4.15 | 0.086 | | 0.031 | 0.13 | 6.39 | Rem | 0.059 |
| IMN L89 3 | | | 0.065 | | 0.052 | 0.041 | 3.49 | 0.058 | | 0.090 | 0.29 | 7.41 | Rem | 0.042 |
| IMN L89 4 | | | 0.12 | | 0.099 | 0.021 | 2.81 | 0.028 | | 0.16 | 0.52 | 8.14 | Rem | 0.020 |
| IMN L89 5 | | | 0.18 | | 0.20 | 0.011 | 2.12 | 0.013 | | 0.33 | 1.11 | 8.86 | Rem | |
| IMN L89 6 | | | 0.029 | | 0.014 | 0.19 | 4.51 | 0.17 | | 0.014 | 0.20 | 8.03 | Rem | 0.096 |
| IMN LA 1 | | | 0.012 | | 0.014 | 1.41 | 2.45 | 0.012 | | 0.011 | 3.18 | 6.79 | Rem | 0.0016 |
| IMN LA 2 | | | 0.092 | | 0.033 | 0.88 | 3.84 | 0.018 | | 0.094 | 2.17 | 7.81 | Rem | |
| IMN LA 3 | | | 0.24 | | 0.059 | 0.50 | 8.13 | 0.059 | | 0.28 | 1.19 | 10.22 | Rem | 0.0095 |
| IMN LA 4 | | | 0.43 | | 0.085 | 0.096 | 6.95 | 0.080 | | 0.45 | 0.41 | 11.66 | Rem | |
| IMN LA 5 | | | 0.54 | | 0.099 | 0.011 | 5.45 | 0.096 | | 0.53 | 0.070 | 13.58 | Rem | 0.020 |
| IMN L 1 | | | 0.051 | | 0.17 | 0.0020 | 0.11 | | | | Rem | 0.52 | 56.06 | 0.00093 |
| IMN L 2 | | | 0.034 | | 0.11 | 0.0043 | 0.075 | (0.011) | | | Rem | 0.35 | 59.09 | 0.0019 |
| IMN L 3 | | | 0.092 | | 0.22 | 0.0065 | 0.034 | (0.023) | | | Rem | 0.14 | 60.18 | 0.0064 |
| IMN L 4 | | | 0.017 | | 0.055 | 0.0080 | 0.013 | (0.0085) | | | Rem | 0.079 | 62.81 | 0.0011 |
| IMN L 5 | | | 0.0035 | | 0.014 | 0.0097 | 0.0037 | | | | Rem | 0.011 | 64.96 | 0.0056 |

CRM TITANIUM

* Provisional Analysis

= class, where 1 = CRM and 2 = RM

| # | Number | Al | B | C | Co | Cr | Cu | Fe | H | Mn | Mo | N | Nb | Ni | O |
|---|-------------|---------|----------|---------|---------|---------|---------|--------|----------|---------|---------|----------|----------|----------|--------|
| 1 | IARM 311A | 0.32 | | 0.009 | | 0.013 | 0.0013 | 0.060 | 0.0021 | 0.0013 | 0.0012 | 0.012 | (0.002) | 0.014 | 0.083 |
| 1 | BCR 090 | (0.074) | 0.00282 | | 0.0501 | 0.0533 | 0.0513 | 0.0563 | | 0.0314 | 0.0488 | | (0.0492) | 0.0667 | |
| 1 | BS T-81 | 0.0664 | 0.0082 | 0.0161 | 0.0395 | 0.0294 | 0.0244 | 0.1144 | 0.0035 | 0.0404 | 0.0279 | 0.0037 | 0.0191 | 0.0090 | 0.0669 |
| 1 | BS T-4A | 0.040 | | 0.014 | | 0.026 | (0.001) | 0.19 | (0.0027) | 0.003 | 0.0006 | 0.005 | | 0.014 | (0.37) |
| 1 | IARM 312B | 0.018 | (0.001) | 0.0092 | (0.002) | 0.010 | (0.003) | 0.072 | 0.0004 | (0.001) | (0.003) | 0.007 | (0.001) | 0.019 | 0.128 |
| 1 | IARM 303B * | (0.015) | <0.001 | 0.035 | <0.002 | 0.0018 | (0.002) | 0.120 | (0.0008) | (0.001) | (0.002) | 0.017 | (0.006) | (0.0013) | 0.176 |
| 1 | IARM 361A | (0.013) | (0.0005) | (0.012) | (0.002) | 0.008 | (0.003) | 0.095 | (0.0027) | (0.005) | 0.288 | (0.006) | (0.004) | 0.88 | 0.15 |
| 1 | IARM 312A | 0.006 | | 0.004 | (0.001) | (0.002) | (0.002) | 0.028 | 0.0049 | (0.001) | (0.002) | 0.0023 | | (0.002) | 0.066 |
| 1 | BS T-2A | 0.005 | | (0.007) | | 0.018 | (0.001) | 0.156 | (0.0020) | 0.003 | 0.002 | (0.0044) | | 0.021 | (0.12) |
| 1 | IARM 174C | (0.003) | | 0.0057 | (0.001) | 0.009 | 0.0015 | 0.28 | 0.0027 | 0.0019 | 0.002 | 0.004 | (0.004) | 0.007 | 0.34 |

BCR: HIP; 090A: 40mm Ø x 20mm; 090B: ~25g of 0.2g cubes

BS: 38-40 Ø x ~7, 12, or 19mm

IARM: 31mm Ø x 2 or 18mm

| Number | P | Pd | Ru | S | Si | Sn | V | W | Y | Zr | Grade |
|-------------|----------|----------|----------|----------|---------|---------|----------|----------|----------|----------|-----------|
| IARM 311A | | | | | 0.005 | 0.0020 | 0.004 | (0.002) | (0.0002) | 0.012 | BT1-0 |
| BCR 090 | | | | | | (0.071) | (0.057) | (0.050) | | (0.0436) | |
| BS T-81 | | 0.0398 | 0.0310 | | 0.0474 | 0.0155 | 0.0186 | 0.0372 | 0.0017 | 0.0163 | Ti Cp 17 |
| BS T-4A | (0.001) | | | (0.0004) | 0.011 | 0.005 | (0.001) | <0.002 | | <0.002 | Ti Cp 1 |
| IARM 312B | (0.0002) | (0.0005) | (0.0001) | (0.0008) | (0.006) | (0.004) | 0.009 | (0.0005) | (0.001) | 0.0014 | Ti Cp 4.1 |
| IARM 303B * | | 0.13 | <0.01 | <0.002 | (0.006) | (0.006) | (0.0023) | <0.002 | <0.001 | (0.0028) | Ti Cp 7 |
| IARM 361A | (0.003) | (0.002) | (0.0006) | (0.004) | (0.012) | (0.004) | (0.006) | (0.003) | (0.0004) | (0.0016) | Ti Cp 12 |
| IARM 312A | | (0.004) | | (0.001) | 0.006 | 0.0012 | (0.002) | | (0.0004) | (0.001) | Ti Cp 4.1 |
| BS T-2A | | | (0.0004) | 0.002 | 0.006 | 0.006 | <0.002 | <0.002 | | <0.003 | Ti Cp 1 |
| IARM 174C | | | (0.0005) | (0.006) | 0.023 | 0.023 | (0.002) | | (0.0004) | (0.003) | Ti CP 1.4 |

17025 last
2mm only, last

CRM TITANIUM SETS available in SETS ONLY, as grouped

| Number | Al | C | Fe | Mo | Si | Sn | V | Zr | Units |
|---------------|------|-------|-------|------|-------|------|------|------|-----------------|
| 58A HC03001 | 4.51 | . | . | 2.69 | . | 1.36 | . | 5.35 | 35 mm Ø x 35 mm |
| 58A HC03002 | 5.31 | . | . | 2.4 | . | 1.71 | . | 4.59 | |
| 58A HC03003 | 6.05 | . | . | 2.0 | . | 2.04 | . | 3.93 | |
| 58A HC03004 | 6.94 | . | . | 1.76 | . | 2.32 | . | 3.32 | |
| 58A HC03005 | 7.78 | . | . | 1.42 | . | 2.72 | . | 2.83 | |
| 58A SY03009-1 | 3.9 | 0.158 | 0.39 | . | 0.277 | . | 5.65 | . | 36 mm Ø x 25 mm |
| 58A SY03009-2 | 4.67 | 0.119 | 0.314 | . | 0.196 | . | 5.01 | . | |
| 58A SY03009-3 | 5.38 | 0.095 | 0.239 | . | 0.115 | . | 3.41 | . | |
| 58A SY03009-4 | 6.48 | 0.051 | 0.143 | . | 0.054 | . | 4.46 | . | |
| 58A SY03009-5 | 6.78 | 0.023 | 0.131 | . | 0.085 | . | 3.85 | . | |

TITANIUM ALLOYS, chart 1 of 2

= class, where 1 = CRM and 2 = RM analysis listed in mass % * Provisional Analysis

| # | Number | Al | V | C | Cr | Cu | Fe | H | N | O | Mn | Mo | Ni | Si | Sn | Zr |
|---|-------------|------|-------|---------|----------|----------|-------|----------|---------|---------|---------|---------|---------|---------|---------|---------|
| 1 | IARM 269B | 7.86 | 1.03 | (0.014) | (0.0014) | (0.0023) | 0.071 | 0.007 | (0.006) | 0.090 | 0.0071 | 0.98 | (0.001) | (0.025) | 0.008 | (0.002) |
| 1 | 58A ZB03002 | 6.54 | 3.61 | 0.014 | . | . | 0.066 | . | 0.016 | . | . | . | <0.003 | 0.024 | . | . |
| 1 | 58A CP03005 | 6.46 | 5.1 | 0.01 | 0.02 | 0.0099 | 0.231 | . | . | . | 0.0064 | . | . | 0.031 | 0.001 | 0.018 |
| 2 | CT 6AL4V | 6.39 | 4.01 | . | . | . | 0.14 | . | . | . | . | . | . | . | . | . |
| 1 | IARM 175D | 6.39 | 3.99 | 0.008 | 0.014 | 0.002 | 0.23 | 0.0027 | 0.030 | 0.177 | (0.003) | 0.0030 | 0.016 | 0.008 | 0.007 | (0.002) |
| 1 | SRM 654b | 6.34 | 4.31 | . | 0.025 | 0.008 | 0.23 | (0.002) | . | (0.17) | . | 0.013 | 0.028 | 0.045 | 0.023 | 0.008 |
| 1 | 58A SY03005 | 6.24 | 4.08 | 0.013 | . | . | 0.047 | . | . | . | . | . | . | 0.024 | . | . |
| 1 | BCR 089 | 5.97 | 3.976 | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 1 | IARM 176C | 5.95 | 4.00 | 0.012 | 0.011 | 0.002 | 0.14 | 0.0034 | (0.005) | 0.110 | 0.0011 | (0.004) | 0.012 | 0.017 | (0.005) | 0.0023 |
| 1 | 58A CP03004 | 5.88 | 1.61 | 0.017 | 0.028 | 0.0085 | 0.074 | . | . | . | 0.027 | 3.58 | . | 0.059 | 0.0085 | 0.024 |
| 1 | IARM 314B | 5.57 | 5.04 | 0.010 | 3.08 | 0.002 | 0.39 | 0.0057 | 0.0045 | 0.130 | (0.001) | 4.88 | 0.0044 | 0.041 | 0.022 | (0.002) |
| 1 | IARM 178D | 5.49 | 5.47 | 0.028 | 0.031 | 0.52 | 0.550 | 0.0016 | 0.017 | 0.17 | (0.003) | 0.10 | 0.067 | 0.053 | 1.84 | 0.026 |
| 1 | IARM 178C | 5.44 | 5.41 | 0.022 | 0.014 | 0.61 | 0.66 | 0.0025 | 0.011 | 0.168 | 0.002 | 0.012 | 0.013 | 0.045 | 1.98 | 0.0038 |
| 1 | 58A CP03003 | 5.21 | 4.89 | 0.014 | 0.997 | . | 1.01 | . | . | . | . | 4.87 | . | 0.038 | . | 0.02 |
| 1 | IARM 344A | 3.15 | 15.3 | 0.011 | 3.09 | (0.002) | 0.20 | (0.015) | 0.005 | 0.107 | (0.003) | 0.004 | 0.011 | (0.03) | 3.09 | (0.002) |
| 1 | 58A SY03003 | 3.14 | 14.98 | 0.01 | 2.84 | . | 0.05 | (0.001) | (0.02) | (0.013) | . | . | . | . | 3.17 | . |
| 1 | 58A SY03004 | 3.13 | 2.82 | 0.01 | . | . | 0.042 | (0.001) | (0.01) | (0.1) | . | . | . | . | . | . |
| 1 | SRM 1128 | 3.06 | 15.13 | 0.011 | 2.96 | . | 0.134 | . | . | . | . | . | . | . | 3.04 | . |
| 1 | IARM 261E | 3.05 | 2.51 | 0.012 | 0.016 | 0.0025 | 0.18 | (0.0005) | 0.006 | 0.084 | (0.001) | 0.003 | 0.018 | 0.007 | 0.005 | (0.003) |
| 1 | IARM 261C | 3.05 | 2.46 | 0.011 | 0.014 | 0.003 | 0.180 | 0.001 | 0.005 | 0.085 | (0.003) | 0.004 | 0.016 | 0.007 | 0.006 | 0.003 |
| 1 | IARM 344B * | 3.03 | 14.7 | 0.0095 | 2.91 | (0.0024) | 0.118 | 0.007 | (0.016) | 0.118 | (0.003) | (0.006) | 0.021 | (0.03) | 3.01 | (0.002) |
| 1 | IARM 261D | 3.02 | 2.50 | 0.011 | 0.016 | 0.0028 | 0.185 | (0.0005) | 0.0051 | 0.083 | (0.002) | 0.003 | 0.018 | 0.008 | 0.005 | 0.003 |
| 1 | IARM 261A | 3.00 | 2.48 | 0.007 | 0.013 | (0.002) | 0.19 | 0.0023 | 0.007 | 0.10 | 0.0011 | (0.003) | 0.006 | 0.012 | 0.008 | (0.002) |
| 1 | IARM 261B | 2.98 | 2.23 | 0.011 | 0.016 | 0.003 | 0.19 | (0.001) | 0.004 | 0.083 | (0.003) | 0.004 | 0.023 | 0.008 | 0.004 | (0.002) |

| # | Number | Al | V | C | Cr | Cu | Fe | H | N | O | Mn | Mo | Ni | Si | Sn | Zr |
|---|-------------|----------|-----------|---------|---------|----------|---------------|----------|----------|--------|---------|----------|----------------------|----|----|----|
| | Number | B | Co | Nb | P | Pd | Ru | S | Ta | Ti | W | Y | Units | | | |
| | IARM 269B | (<0.001) | (<0.0005) | (0.004) | (0.003) | (<0.005) | (0.004) | (0.003) | (<0.005) | (89.9) | (0.001) | (<0.001) | 31 mm Ø x 2 or 18 mm | | | |
| | 58A ZB03002 | . | . | . | . | . | . | . | . | . | . | . | 40 mm Ø x 30 mm | | | |
| | 58A CP03005 | . | . | . | . | . | . | . | . | . | . | . | 40 mm Ø x 35 mm | | | |
| | CT 6AL4V | . | . | . | . | . | . | . | . | . | . | . | 30-35 mm Ø x ~19 mm | | | |
| | IARM 175D | (0.0008) | . | (0.008) | . | . | . | . | . | (89.2) | (0.002) | (0.001) | 31 mm Ø x 2 or 18 mm | | | |
| | SRM 654b | . | . | . | . | . | . | (0.001) | . | . | . | . | 31 mm Ø x 19 mm | | | |
| | 58A SY03005 | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm | | | |
| | BCR 089 | . | . | . | . | . | . | . | . | . | . | . | 40 mm Ø x 20 mm | | | |
| | IARM 176C | . | (0.001) | (0.005) | . | (0.004) | last of stock | . | . | 89.8 | . | (0.0001) | 31 mm Ø x 2 mm last | | | |
| | 58A CP03004 | . | . | . | . | . | . | . | . | . | . | . | 40 mm Ø x 35 mm | | | |
| | IARM 314B | (0.001) | (0.004) | 0.009 | (0.001) | (0.003) | . | (0.001) | (0.002) | . | (0.003) | (0.001) | 31 mm Ø x 2 or 18 mm | | | |
| | IARM 178D | (0.001) | 0.005 | (0.01) | (0.002) | (0.003) | (0.001) | (0.001) | (0.001) | (85.8) | (0.001) | (0.001) | 31 mm Ø x 2 or 18 mm | | | |
| | IARM 178C | 0.0010 | (0.003) | <0.01 | (0.003) | (0.003) | (0.002) | (0.002) | <0.002 | (85.8) | . | (0.001) | 31 mm Ø x 2 mm | | | |
| | 58A CP03003 | . | . | . | . | . | . | . | . | . | . | . | 40 mm Ø x 35 mm | | | |
| | IARM 344A | 0.0011 | (0.001) | (0.005) | (0.002) | (0.001) | . | (0.001) | (0.001) | (74.9) | (0.003) | <0.001 | 31 mm Ø x 2 or 18 mm | | | |
| | 58A SY03003 | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 30 mm | | | |
| | 58A SY03004 | . | . | . | . | . | . | . | . | . | . | <0.001 | 36 mm Ø x 30 mm | | | |
| | SRM 1128 | . | . | . | . | . | . | . | . | . | . | . | 35 mm Ø x 19 mm | | | |
| | IARM 261E | 0.0003 | (0.0004) | (0.005) | <0.003 | (0.002) | (0.001) | (0.001) | . | (94.1) | (0.001) | (0.001) | 31 mm Ø x 2 or 18 mm | | | |
| | IARM 261C | 0.0004 | (0.005) | (0.003) | (0.003) | (0.002) | (0.001) | (0.001) | . | (94.1) | (0.001) | (0.0004) | 31 mm Ø x 2 or 18 mm | | | |
| | IARM 344B * | <0.001 | <0.004 | (0.003) | <0.003 | <0.03 | <0.02 | <0.003 | <0.04 | (76.0) | <0.03 | <0.006 | 31 mm Ø x 2 or 18 mm | | | |
| | IARM 261D | 0.0003 | <0.001 | (0.003) | <0.004 | (0.002) | (0.0005) | (0.001) | (0.0005) | (94.2) | (0.001) | (0.0005) | 31 mm Ø x 2 or 18 mm | | | |
| | IARM 261A | . | . | . | . | . | . | (0.001) | . | . | . | . | 31 mm Ø x 2 mm | | | |
| | IARM 261B | 0.0004 | <0.004 | (0.002) | (0.004) | . | (0.001) | (0.0004) | . | (94.4) | (0.003) | (0.0004) | 31 mm Ø x 2 or 18 mm | | | |

TITANIUM ALLOYS, chart 2 of 2

= class, where 1 = CRM and 2 = RM analysis listed in mass % * Provisional Analysis

| # | Number | Al | V | C | Cr | Fe | H | Mn | Mo | N | Nb | O | Si | Sn | Ti | Zr |
|---|---------------|---------|---------|---------|---------|--------|----------|----------|----------|----------|----------|--------|---------|---------|--------|----------|
| 1 | SRM 2062 | 30.31 | . | . | . | . | . | . | . | . | 10.78 | . | . | . | 53.92 | . |
| 1 | 58A SY03008-6 | 7.64 | . | 0.12 | . | 0.369 | . | . | 2.27 | . | . | . | 0.446 | . | . | 0.63 |
| 1 | 58A SY03001-6 | 7.15 | . | 0.0098 | . | 0.051 | . | . | 2.0 | . | 2.02 | . | 0.253 | . | . | 1.01 |
| 1 | 58A SY03008-5 | 7.05 | . | 0.093 | . | 0.325 | . | . | 2.54 | . | . | . | 0.389 | . | . | 0.83 |
| 1 | 58A SY03008-4 | 6.61 | . | 0.081 | . | 0.301 | . | . | 2.83 | . | . | . | 0.354 | . | . | 1.21 |
| 1 | 58A SY03001-5 | 6.45 | . | 0.02 | . | 0.122 | . | . | 1.49 | . | 2.46 | . | 0.202 | . | . | 1.54 |
| 1 | 58A ZB03001 | 6.38 | . | 0.0074 | . | 0.08 | . | . | 3.22 | 0.01 | . | . | 0.26 | . | . | 1.75 |
| 1 | 58A SY03008-3 | 6.25 | . | 0.069 | . | 0.288 | . | . | 3.46 | . | . | . | 0.298 | . | . | 1.6 |
| 1 | IARM 300E * | 6.16 | (0.03) | 0.008 | 0.007 | 0.17 | (0.001) | (<0.02) | 0.0028 | 0.0059 | 6.85 | 0.180 | 0.017 | (0.005) | (86.5) | (<0.02) |
| 1 | 58A SY03007 | 6.14 | . | 0.061 | . | 0.253 | . | . | 3.25 | . | . | . | 0.298 | . | . | 1.64 |
| 1 | IARM 300B | 6.09 | (0.004) | 0.0081 | 0.0174 | 0.175 | 0.0025 | (0.006) | 0.0013 | 0.0030 | 6.84 | 0.171 | 0.016 | (0.004) | (86.3) | (0.013) |
| 1 | IARM 300D | 6.06 | (0.03) | (0.010) | (0.006) | 0.183 | (0.001) | (<0.005) | 0.0019 | (0.005) | 6.82 | 0.166 | (0.021) | (0.005) | (86.7) | (0.005) |
| 1 | IARM 336B | 6.04 | (0.004) | 0.006 | (0.001) | 0.132 | 0.0029 | . | 6.16 | 0.0016 | . | 0.101 | 0.020 | 2.04 | . | 4.12 |
| 1 | 58A SY03001-4 | 6.03 | . | 0.049 | . | 0.187 | . | . | 1.02 | . | 2.76 | . | 0.149 | . | . | 1.93 |
| 1 | 101X Ti2A | 6.02 | . | 0.016 | 0.0054 | 0.053 | 0.0076 | . | 2.08 | 0.0053 | . | 0.143 | 0.110 | 2.05 | . | 3.97 |
| 1 | 58A SY03002 | 5.99 | . | 0.01 | 1.22 | 0.05 | (0.001) | . | 2.89 | (0.01) | 1.97 | (0.13) | 0.067 | 2.24 | . | 1.99 |
| 1 | IARM 300C | 5.97 | 0.030 | (0.010) | 0.008 | 0.181 | (0.0006) | (0.003) | 0.0023 | 0.0061 | 6.80 | 0.174 | 0.018 | (0.006) | (86.7) | (0.005) |
| 1 | IARM 300A | 5.96 | (0.005) | 0.007 | 0.0097 | 0.191 | (0.0018) | 0.0012 | 0.0009 | 0.0033 | 6.86 | 0.162 | 0.018 | (0.007) | 86.71 | (0.003) |
| 1 | IARM 336A | 5.9 | 0.005 | 0.005 | (0.002) | 0.115 | 0.0022 | . | 6.16 | 0.0015 | . | 0.102 | 0.019 | 2.03 | . | 3.92 |
| 1 | IARM 337A | 5.60 | (0.003) | 0.008 | 2.01 | 0.114 | 0.005 | . | 2.05 | 0.0017 | (0.004) | 0.104 | 0.14 | 1.96 | . | 1.89 |
| 1 | 58A SY03008-2 | 5.59 | . | 0.049 | . | 0.233 | . | . | 3.79 | . | . | . | 0.242 | . | . | 1.96 |
| 1 | 58A SY03001-3 | 5.55 | . | 0.06 | . | 0.246 | . | . | 0.595 | . | 3.3 | . | 0.1 | . | . | 2.31 |
| 1 | IARM 271A | 5.28 | 0.09 | 0.026 | 0.016 | 0.31 | 0.013 | (0.002) | 0.011 | 0.012 | . | 0.16 | 0.021 | 2.49 | . | 0.015 |
| 1 | IARM 271B | 5.21 | 0.057 | 0.0128 | 0.010 | 0.196 | 0.0139 | 0.0036 | 0.0063 | 0.013 | (0.005) | 0.155 | (0.010) | 2.52 | (91.9) | 0.059 |
| 1 | IARM 345A | 5.12 | 0.005 | 0.010 | 3.89 | 0.121 | 0.0040 | 0.0009 | 4.09 | 0.0025 | (0.002) | 0.120 | 0.013 | 1.99 | (82.8) | 1.90 |
| 1 | 58A SY03001-2 | 5.1 | . | 0.084 | . | 0.313 | . | . | 0.297 | . | 3.63 | . | 0.043 | . | . | 2.74 |
| 1 | 58A SY03001-1 | 4.62 | . | 0.124 | . | 0.347 | . | . | 0.103 | . | 3.94 | . | 0.007 | . | . | 2.94 |
| 1 | 58A SY03008-1 | 4.59 | . | 0.015 | . | 0.189 | . | . | 4.74 | . | . | . | 0.149 | . | . | 2.45 |
| 1 | IARM 280A | 4.11 | 0.023 | 0.005 | 0.0055 | 0.044 | 0.0015 | (0.002) | 4.01 | 0.0014 | (0.001) | 0.19 | 0.47 | 2.07 | . | (0.002) |
| 1 | IARM 367A | 2.02 | (0.005) | (0.014) | 0.012 | 0.064 | 0.0030 | 1.61 | (0.0023) | 0.0074 | (<0.01) | 0.105 | (0.011) | 0.0019 | (96.1) | (0.003) |
| 1 | BS T-81 17025 | 0.0664 | 0.0186 | 0.0161 | 0.0294 | 0.1144 | 0.0035 | 0.0404 | 0.0279 | 0.0037 | 0.0191 | 0.0669 | 0.0474 | 0.0155 | . | 0.0163 |
| 1 | BS T-4A 17025 | 0.040 | (0.001) | 0.014 | 0.026 | 0.19 | (0.0027) | 0.003 | 0.0006 | 0.005 | . | (0.37) | 0.011 | 0.005 | . | <0.002 |
| 1 | BS T-2A 17025 | 0.005 | <0.002 | (0.007) | 0.018 | 0.156 | (0.002) | 0.003 | 0.002 | (0.0044) | . | (0.12) | 0.002 | 0.006 | . | <0.003 |
| 2 | BS T-22 | 0.004 | 0.50 | 0.005 | 1.22 | 1.19 | . | 2.02 | 1.15 | (0.01) | . | (0.09) | (0.02) | 0.019 | . | <(0.01) |
| 2 | BS T-24 | 0.002 | 1.22 | 0.005 | 0.54 | 0.54 | . | 4.7 | 0.51 | 0.006 | . | (0.09) | (0.01) | 0.019 | . | (0.001) |
| 1 | BCR 090A | (0.074) | (0.057) | . | 0.0533 | 0.0563 | . | 0.0314 | 0.0488 | . | (0.0492) | . | . | (0.071) | . | (0.0436) |
| 1 | SRM 643 | . | . | . | . | . | . | 11.6 | . | . | . | . | . | . | . | . |
| 1 | SRM 642 | . | . | . | . | . | . | 9.0 | . | . | . | . | . | . | . | . |
| 1 | SRM 641 | . | . | . | . | . | . | 6.6 | . | . | . | . | . | . | . | . |

| # | Number | Al | V | C | Cr | Fe | H | Mn | Mo | N | Nb | O | Si | Sn | Ti | Zr |
|---|--------|----|---|---|----|----|---|----|----|---|----|---|----|----|----|----|
|---|--------|----|---|---|----|----|---|----|----|---|----|---|----|----|----|----|

| Number | B | Co | Cu | Mg | Ni | P | Pb | Pd | Ru | S | Sb | Ta | W | Y | Units |
|---------------|----------|----------|---------|----------|---------|----------|-----------|----------|----------|----------|-----------|----------|----------|-----------|------------------------|
| SRM 2062 | . | . | . | . | . | . | . | . | . | . | . | . | 4.38 | . | 24 mm Ø x 2 mm |
| 58A SY03008-6 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| 58A SY03001-6 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| 58A SY03008-5 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| 58A SY03008-4 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| 58A SY03001-5 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| 58A ZB03001 | . | . | . | . | <0.005 | . | <0.001 | . | . | . | . | . | . | . | 40 mm Ø x 30 mm |
| 58A SY03008-3 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| IARM 300E * | (<0.002) | (0.004) | (<0.02) | (<0.001) | 0.011 | (<0.001) | (<0.0001) | (<0.001) | (<0.01) | (<0.001) | (<0.001) | (0.006) | (<0.002) | (0.003) | 31 mm Ø x 2 or 18 mm |
| 58A SY03007 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| IARM 300B | (0.0012) | (0.002) | (0.014) | . | 0.012 | . | . | (0.005) | . | (0.001) | . | (0.005) | . | . | 31 mm Ø x 2 or 18 mm |
| IARM 300D | (0.001) | (0.004) | (0.003) | (<0.001) | 0.013 | (<0.002) | (<0.0005) | (<0.005) | (<0.001) | (0.001) | (0.0004) | (0.005) | (<0.002) | (0.003) | 31 mm Ø x 2 or 18 mm |
| IARM 336B | (0.001) | (0.002) | (0.002) | . | (0.002) | (0.002) | . | . | . | (0.002) | . | . | (0.005) | (0.0002) | 31 mm Ø x 2 or 18 mm |
| 58A SY03001-4 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| 101X Ti2A | . | . | (0.003) | . | 0.0073 | . | . | . | . | . | . | . | . | 0.0002 | 40 mm Ø x 13 mm last |
| 58A SY03002 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 30 mm |
| IARM 300C | (0.0006) | (0.001) | (0.003) | (<0.001) | (0.014) | (<0.001) | (<0.0001) | (<0.005) | . | (0.0005) | (0.0005) | (0.005) | (<0.002) | (0.002) | 31 mm Ø x 2 or 18 mm |
| IARM 300A | (0.0008) | (0.001) | 0.0039 | (0.0004) | 0.0081 | (0.001) | . | (0.002) | (<0.02) | 0.0008 | . | (0.004) | (<0.002) | (0.0004) | 31 mm Ø x 2 or 18 mm |
| IARM 336A | (0.001) | (0.002) | (0.002) | . | (0.002) | . | . | . | . | (0.002) | . | . | (0.004) | (0.0003) | 31 mm Ø x 2 or 18 mm |
| IARM 337A | (0.001) | 0.0011 | (0.002) | . | 0.011 | . | . | . | . | (0.001) | . | . | (0.003) | (0.0004) | 31 mm Ø x 2 or 18 mm |
| 58A SY03008-2 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| 58A SY03001-3 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| IARM 271A | . | . | 0.004 | . | 0.035 | (0.002) | . | . | . | (0.002) | . | . | . | . | 31 mm Ø x 2 mm |
| IARM 271B | (0.0012) | (0.001) | 0.0068 | (0.001) | 0.0089 | (0.011) | . | (0.011) | (0.003) | (0.001) | . | (0.0104) | (0.0021) | (0.00018) | 31 mm Ø x 2 or 18 mm |
| IARM 345A | (0.001) | (0.002) | (0.002) | . | 0.015 | (0.002) | . | (0.002) | . | (0.001) | . | (0.003) | (0.002) | (0.0003) | 31 mm Ø x 2 or 18 mm |
| 58A SY03001-2 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| 58A SY03001-1 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| 58A SY03008-1 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 36 mm Ø x 25 mm |
| IARM 280A | . | (0.002) | 0.003 | . | 0.012 | . | . | (0.002) | . | (0.001) | . | . | . | (0.0003) | 31 mm Ø x 2 or 18 mm |
| IARM 367A | (<0.001) | (<0.002) | (0.002) | (<0.001) | (0.013) | (<0.005) | (<0.001) | (<0.01) | (<0.01) | (0.0012) | (<0.0005) | (<0.005) | (<0.002) | (<0.001) | 31 mm Ø x 2 or 18 mm |
| BS T-81 17025 | 0.0082 | 0.0395 | 0.0244 | . | 0.0090 | . | . | 0.0398 | 0.0310 | . | . | . | 0.0372 | 0.0017 | 40 mm Ø x ~7 or 19+ mm |
| BS T-4A 17025 | . | . | (0.001) | . | 0.014 | (0.001) | . | . | . | (0.0004) | . | . | <0.002 | . | 38 mm Ø x ~7 or 19+ mm |
| BS T-2A 17025 | . | . | (0.001) | . | 0.021 | . | . | . | . | (0.0004) | . | . | <0.002 | . | 38 mm Ø x 12 or 19 mm |
| BS T-22 | . | . | 0.04 | . | 0.008 | . | . | . | . | (0.002) | . | . | 0.51 | . | 32 mm Ø x ~7 or 19+ mm |
| BS T-24 | . | . | 0.020 | . | (0.007) | . | . | . | . | (0.002) | . | . | 0.37 | . | 32 mm Ø x ~7 or 19+ mm |
| BCR 090A | 0.00282 | 0.0501 | 0.0513 | . | 0.0667 | . | . | . | . | . | . | . | (0.050) | . | 40 mm Ø x 20 mm |
| SRM 643 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 32 mm Ø x 19 mm |
| SRM 642 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 32 mm Ø x 19 mm |
| SRM 641 | . | . | . | . | . | . | . | . | . | . | . | . | . | . | 32 mm Ø x 19 mm |

| Number | B | Co | Cu | Mg | Ni | P | Pb | Pd | Ru | S | Sb | Ta | W | Y | Units |
|--------|---|----|----|----|----|---|----|----|----|---|----|----|---|---|-------|
|--------|---|----|----|----|----|---|----|----|----|---|----|----|---|---|-------|

ZINC

= class, where 1 = CRM and 2 = RM analysis listed in mass % Trace = informational values such as (<0.001) or lower

| # | Number | Pb | Al | Cd | Cu | Fe | In | Mg | Mn | Ni | Sb | Sn | Tl |
|---|-----------|----------|-------------|------------|------------|------------|-----------|------------|---------|------------|-----------|------------|------------|
| 1 | 41X Z6A | 0.031 | 0.0096 | 0.0093 | 0.0088 | (0.002) | 0.0228 | <0.0005 | 0.0002 | 0.0002 | . | 0.0038 | . |
| 1 | 41X Z5N | 0.0286 | 0.0243 | 0.0165 | 0.0109 | 0.0262 | 0.0057 | 0.0107 | 0.0049 | 0.0051 | 0.0054 | 0.0063 | 0.0068 |
| 1 | ERM-EB325 | 0.0142 | . | 0.00947 | 0.00475 | 0.00561 | . | . | . | . | . | 0.00461 | 0.00368 |
| 1 | 41X Z11A | 0.0077 | 0.0261 | 0.0155 | 0.0116 | 0.0019 | 0.0345 | . | . | . | 0.0026 | 0.0072 | (0.0010) |
| 1 | 41X Z4L | 0.00584 | 0.0065 | 0.00437 | 0.00326 | 0.0148 | 0.00304 | 0.00331 | 0.00286 | 0.00320 | 0.00340 | 0.00221 | 0.00277 |
| 1 | 41X Z3M | 0.00502 | 0.00158 | 0.00327 | 0.00345 | 0.00605 | 0.00233 | (0.00034) | 0.00524 | 0.00209 | 0.00167 | 0.00297 | 0.00210 |
| 2 | BS SP-5 | 0.005 | 0.0003 | <0.0004 | <0.001 | <0.001 | . | <0.002 | . | . | <0.001 | 0.0010 | . |
| 1 | ERM-EB323 | 0.00486 | . | 0.000651 | 0.00189 | 0.00113 | . | . | . | . | . | 0.00187 | 0.00108 |
| 1 | BCR 327 | 0.004094 | . | 0.03014 | (0.000056) | 0.01440 | . | . | . | . | . | . | . |
| 1 | BCR 326 | 0.003070 | Trace | 0.02030 | 0.01048 | 0.02648 | . | . | . | . | . | . | . |
| 2 | BS SP-A | 0.003 | 0.051 | . | <0.0005 | 0.011 | . | . | . | . | 0.099 | <0.001 | . |
| 1 | 41X Z1Q | 0.00276 | (0.00011) | 0.00120 | 0.00116 | 0.00282 | 0.00026 | (0.00010) | 0.00047 | 0.00014 | (0.00024) | 0.00051 | 0.00028 |
| 1 | ERM-EB324 | 0.00261 | . | 0.00489 | 0.000987 | 0.00585 | . | . | . | . | . | 0.00098 | 0.00199 |
| 2 | BCS 194e | 0.002 | . | . | 0.001 | . | . | . | . | . | . | . | . |
| 1 | BAM M601 | 0.00157 | <0.00005 | 0.000055 | 0.000189 | 0.000220 | <0.000005 | . | . | . | . | . | 0.000225 |
| 1 | ERM-EB322 | 0.00150 | . | 0.001508 | 0.000589 | 0.00191 | . | . | . | . | . | 0.00056 | 0.000528 |
| 1 | SRM 683 | 0.00111 | . | 0.00011 | 0.00059 | 0.00022 | Trace | . | Trace | . | . | (0.000002) | (0.00002) |
| 1 | SRM 631 | (0.001) | 0.50 | 0.0002 | 0.0013 | 0.005 | 0.0023 | Trace | 0.00015 | Trace | . | 0.0001 | . |
| 1 | BCR 321 | 0.000485 | <0.00007 | (0.000023) | (0.000097) | (0.000222) | <0.00002 | . | . | . | . | <0.00005 | 0.000078 |
| 1 | SRM 682 * | . | (<0.000003) | (0.00001) | 0.0000042 | (0.00001) | . | (<0.00001) | Trace | (<0.00001) | . | (0.000002) | (<0.00002) |

| Number | Ag | Bi | Cr | Ga | Ge | Hg | Si | Zn | Melt °C | Units |
|-----------|------------|---------|-------------|----------|----------|----------|------------|-------|---------|---------------------------------------|
| 41X Z6A | . | 0.0122 | (0.0001) | . | . | . | . | . | . | 50 mm Ø x 20 mm |
| 41X Z5N | . | 0.0056 | . | . | . | 0.0050 | . | . | . | ~50 mm Ø x 20 mm |
| ERM-EB325 | . | . | . | . | . | . | . | . | . | 60 mm Ø x 30 mm |
| 41X Z11A | . | 0.0189 | . | . | . | (0.0009) | . | . | . | 50 mm Ø x 20 mm |
| 41X Z4L | . | 0.00319 | . | . | . | 0.0025 | . | . | . | 50 mm Ø x 20 mm |
| 41X Z3M | . | 0.00315 | . | . | . | 0.00289 | . | . | . | ~50 mm Ø x ~20 mm |
| BS SP-5 | . | . | . | . | . | . | . | . | . | 37 mm Ø x 12 mm |
| ERM-EB323 | . | . | . | . | . | . | . | . | . | 60 mm Ø x 30 mm |
| BCR 327 | . | . | . | . | . | . | . | . | . | 80 mm Ø x 20 mm |
| BCR 326 | . | . | . | . | . | . | . | . | . | 80 mm Ø x 20 mm |
| BS SP-A | . | . | . | . | . | . | . | . | . | 38 mm Ø x 14 mm last of stock |
| 41X Z1Q | . | 0.00030 | . | . | . | 0.00034 | . | . | . | ~50 mm Ø x ~20 mm |
| ERM-EB324 | . | . | . | . | . | . | . | . | . | 60 mm Ø x 30 mm |
| BCS 194e | . | . | . | . | . | . | . | 99.99 | 419.5 | 300 g(4.5 x 3.5 x 3 cms) |
| BAM M601 | . | . | . | . | . | . | . | . | . | 45 mm Ø x 30 mm |
| ERM-EB322 | . | . | . | . | . | . | . | . | . | 60 mm Ø x 30 mm |
| SRM 683 | 0.00013 | . | . | Trace | . | . | . | . | . | Cylinder segment 57mm Ø x 25mm x 19mm |
| SRM 631 | Trace | . | 0.0001 | (0.0002) | (0.0002) | . | . | . | . | 45 mm x 45 mm x 19 mm |
| BCR 321 | . | . | . | . | . | . | . | . | . | 80 mm Ø x 20 mm |
| SRM 682 * | (0.000002) | . | (<0.000006) | . | . | . | (<0.00005) | . | . | Cylinder segment 57mm Ø x 25mm x 19mm |

* SRM 682 has trace informational B, Be, C, Ca, Cl, F, K, Li, N, and Nb.

CRM ZINC SETS

available in sets only, as grouped

| Number | Al | Cd | Cu | Fe | Pb | Sn | Ti | Zn | Units |
|----------|---------|---------|-----------|-----------|---------|---------|---------|-----|-----------------------|
| IMN ZA 1 | . | 0.0042 | (0.0032) | 0.00167 | 0.025 | 0.0038 | . | Rem | Rods 10 mm Ø x 100 mm |
| IMN ZA 2 | . | 0.0029 | 0.0013 | 0.0061 | 0.011 | 0.0012 | . | Rem | |
| IMN ZA 3 | . | 0.00092 | 0.00011 | 0.00078 | 0.0028 | 0.00036 | . | Rem | |
| IMN ZA 4 | . | 0.00049 | 0.00032 | 0.00040 | 0.0016 | 0.00011 | . | Rem | |
| IMN ZE 1 | 0.012 | 0.0019 | 0.011 | 0.020 | 0.018 | 0.0018 | . | Rem | Discs 40 mm Ø x 25 mm |
| IMN ZE 2 | 0.0035 | 0.0031 | (0.00037) | 0.0052 | 0.0078 | 0.0074 | . | Rem | |
| IMN ZE 3 | 0.025 | 0.0050 | 0.0032 | . | 0.0052 | 0.015 | . | Rem | |
| IMN ZE 4 | . | 0.00023 | 0.013 | (0.00035) | 0.0012 | 0.0017 | . | Rem | |
| IMN ZE 5 | 0.0011 | 0.0060 | 0.0049 | 0.011 | 0.0004 | 0.00045 | . | Rem | |
| IMN ZL 1 | 0.0190 | 0.0365 | 0.342 | 0.00072 | 0.00498 | 0.0364 | 0.00745 | Rem | Discs 40 mm Ø x 25 mm |
| IMN ZL 2 | 0.0119 | 0.0241 | 0.573 | 0.0174 | 0.00923 | 0.0420 | 0.114 | Rem | |
| IMN ZL 3 | 0.00388 | 0.00492 | 0.201 | 0.00496 | 0.0247 | 0.00788 | 0.238 | Rem | |
| IMN ZL 4 | 0.0497 | 0.0115 | 0.114 | 0.00879 | 0.0351 | 0.0114 | 0.394 | Rem | |
| IMN ZL 5 | 0.0518 | 0.00085 | 0.0115 | 0.0299 | 0.0363 | 0.0011 | 0.598 | Rem | |

CRM ZINC RoHS MONITOR

cast 50 mm Ø x 20 mm

| Number | Cd | Cr | Hg | Pb |
|-----------|--------|---------|--------|--------|
| 41X ZSC6A | 0.215 | <0.0002 | 0.029 | 0.0077 |
| 41X ZSC3A | 0.119 | 0.0148 | 0.0021 | 0.0273 |
| 41X ZSC1A | 0.0288 | 0.0039 | 0.026 | 0.0621 |
| 41X ZSC4A | 0.0131 | 0.0299 | 0.050 | 0.156 |
| 41X ZSC2A | 0.0016 | 0.0036 | 0.0053 | 0.111 |

CRM ZAMAK (MAZAK) SPECIFICATIONS AND SUGGESTED SAMPLES

42X, 43X: ~50 mm Ø x ~15-20 mm BAM: 39 mm Ø x 39 mm BCR: 80 mm Ø x 20 mm SRM: 44 mm x 44 mm x 19 mm

| Number | Al | Cu | Mg | Ni | Cd | Cr | Fe | Mn | Pb | Sn |
|----------------|----------------|------------------|--------------------|-------------------|------------------|----------|------------------|----------|------------------|------------------|
| Zamak 2 | 3.9-4.3 | 2.6-2.9 | 0.025-0.05 | . | <0.003 | . | <0.075 | . | <0.004 | <0.002 |
| 43X Z7A | 3.68 | 3.14 | 0.062 | 0.0005 | 0.00092 | 0.0003 | 0.029 | 0.0025 | 0.0058 | 0.0031 |
| 43X Z6B | 4.51 | 2.85 | 0.0238 | 0.0027 | 0.0031 | 0.0005 | 0.024 | 0.0022 | 0.004 | 0.0052 |
| 43X Z4C | 4.79 | 2.69 | 0.0480 | 0.0258 | 0.0033 | . | 0.0017 | 0.0153 | 0.0062 | 0.0030 |
| Zamak 5 | 3.9-4.3 | 0.75-1.25 | 0.030-0.06 | . | <0.003 | . | <0.075 | . | <0.004 | <0.002 |
| Zamak 6 | 3.9-4.3 | 0.75-1.25 | <0.05 | . | <0.003 | . | <0.075 | . | <0.004 | <0.002 |
| 43X Z3M | 3.40 | 1.499 | 0.114 | 0.0062 | 0.0109 | 0.0046 | (0.042) | 0.0013 | 0.0077 | 0.0058 |
| BCR 360 | 3.427 | 1.234 | 0.0705 | 0.0267 | 0.00595 | . | . | . | 0.00739 | 0.00330 |
| 43X Z2P * | 4.05 | 1.03 | 0.062 | 0.010 | 0.0033 | . | 0.0015 | 0.016 | 0.0055 | 0.0035 |
| SRM 630 | 4.30 | 0.976 | 0.030 | 0.0027 | 0.0048 | 0.0031 | 0.023 | 0.0106 | 0.0083 | 0.0040 |
| ERM-EB602 | 4.08 | 0.812 | 0.0415 | 0.00025 | 0.00011 | . | 0.00073 | . | 0.00195 | 0.00010 |
| BCR 361 | 4.068 | 0.798 | . | . | (0.000080) | . | 0.001034 | . | 0.000531 | 0.00463 |
| 43X Z1K | 4.50 | 0.717 | 0.0256 | 0.0010 | 0.0014 | 0.0007 | 0.0070 | 0.0014 | 0.0038 | 0.0019 |
| SRM 628 | 4.59 | 0.611 | 0.0094 | 0.030 | 0.0040 | 0.0087 | 0.066 | 0.0091 | 0.0045 | 0.0017 |
| BCR 357 | 4.227 | 0.5849 | 0.0273 | 0.000982 | 0.000283 | . | 0.00257 | . | 0.00138 | 0.000351 |
| 43X Z1J | 4.50 | 0.501 | 0.0145 | 0.0010 | 0.00037 | 0.0009 | 0.0058 | 0.0005 | 0.0017 | (0.0007) |
| Zamak 3 | 3.9-4.3 | <0.10 | 0.025-0.05 | . | <0.003 | . | <0.075 | . | <0.004 | <0.002 |
| Zamak 7 | 3.9-4.3 | <0.10 | 0.010-0.020 | 0.005-0.02 | <0.002 | . | <0.075 | . | <0.004 | <0.001 |
| BCR 356 | 4.434 | 0.3944 | 0.01323 | 0.000343 | 0.000073 | . | 0.00315 | . | 0.000987 | (0.000032) |
| 42X Z6B | 3.67 | 0.238 | 0.177 | 0.00030 | 0.0039 | 0.0034 | 0.008 | 0.0157 | 0.0093 | 0.0057 |
| 42X Z12A | 4.717 | 0.156 | 0.0488 | 0.0413 | 0.00277 | 0.00063 | 0.0457 | 0.0483 | 0.0079 | 0.0022 |
| 42X Z3J | 3.84 | 0.135 | 0.0503 | 0.0071 | 0.0065 | . | 0.0145 | 0.0090 | 0.0068 | 0.0048 |
| SRM 627 | 3.88 | 0.132 | 0.031 | 0.0029 | 0.0051 | 0.0038 | 0.023 | 0.014 | 0.0082 | 0.0042 |
| 42X Z5M | 4.33 | 0.111 | 0.0508 | 0.041 | 0.0013 | (0.0002) | (0.05) | 0.0049 | 0.0030 | 0.0012 |
| BCR 355 | 3.443 | 0.1035 | 0.0786 | 0.0268 | 0.00581 | . | . | . | 0.00569 | 0.00291 |
| 42X Z4J | 3.55 | 0.063 | 0.058 | 0.0177 | 0.0076 | . | 0.012 | 0.0077 | 0.0113 | 0.0060 |
| SRM 626 | 3.56 | 0.056 | 0.020 | 0.047 | 0.0016 | 0.0395 | 0.103 | 0.048 | 0.0022 | 0.0012 |
| SRM 625 | 3.06 | 0.034 | 0.070 | 0.0184 | 0.0007 | 0.0128 | 0.036 | 0.031 | 0.0014 | 0.0006 |
| BCR 354 | 3.726 | 0.03123 | 0.0602 | 0.00831 | 0.00297 | . | . | . | 0.00308 | 0.00141 |
| 42X Z2K | 3.79 | 0.0300 | 0.0146 | 0.0155 | 0.0017 | (0.0001) | 0.0055 | 0.0274 | 0.0029 | 0.0011 |
| BCR 352 | 4.150 | 0.003126 | 0.02830 | 0.000674 | 0.000288 | . | . | . | (0.00064) | 0.00030 |
| BCR 351 | 4.355 | 0.001213 | 0.01310 | (0.00019) | (0.000021) | . | . | . | 0.000450 | <0.0001 |
| Zamak 8 | 7.8-9.0 | 0.70-1.40 | 0.015-0.030 | <0.02 | <0.005 | . | <0.1 | . | <0.005 | <0.003 |
| 43X Z14E | 8.05 | 1.13 | 0.0133 | 0.0066 | 0.0083 | 0.0047 | 0.031 | 0.0050 | 0.015 | 0.0054 |
| 43X Z14F | 7.98 | 1.238 | 0.0123 | 0.0058 | 0.00567 | 0.0037 | 0.0025 | (0.0003) | 0.0019 | 0.0005 |

| Number | Be | Bi | Ce | In | La | Sb | Si | Ti | Tl |
|----------------|--------|----------|---------|------------|---------|----------|-----------------|----------|----------------------|
| Zamak 2 | . | . | . | . | . | . | . | . | . |
| 43X Z7A | 0.0194 | (0.0009) | . | . | . | 0.0016 | . | 0.067 | . |
| 43X Z6B | . | 0.0054 | . | . | . | 0.0044 | . | . | . |
| 43X Z4C | . | 0.0113 | . | . | . | (0.0023) | (0.0012) | . | . |
| Zamak 5 | . | . | . | . | . | . | . | . | . |
| Zamak 6 | . | . | . | . | . | . | . | . | . |
| 43X Z3M | . | 0.0092 | . | . | . | 0.0029 | . | . | . |
| BCR 360 | . | . | . | 0.00298 | . | . | . | . | 0.00259 |
| 43X Z2P * | . | 0.004 | . | Ag: 0.011 | . | 0.0013 | . | * | Provisional Analysis |
| SRM 630 | . | . | . | . | . | 0.022 | . | . | . |
| ERM-EB602 | . | . | . | . | . | 0.00114 | 0.00048 | . | . |
| BCR 361 | . | . | . | (<0.00002) | . | . | . | . | 0.00374 |
| 43X Z1K | . | 0.0015 | . | . | . | 0.0007 | . | . | . |
| SRM 628 | . | . | . | . | . | . | 0.008 | . | . |
| BCR 357 | . | . | . | 0.000330 | . | . | . | . | 0.000276 |
| 43X Z1J | . | 0.0031 | . | . | . | 0.0016 | (0.0037) | 0.0014 | . |
| | | | | | | | | | last of stock |
| Zamak 3 | . | . | . | . | . | . | . | . | . |
| Zamak 7 | . | . | . | . | . | . | . | . | . |
| BCR 356 | . | . | . | <0.00002 | . | . | . | . | 0.000079 |
| 42X Z6B | . | . | (0.012) | 0.00191 | (0.011) | 0.0169 | (0.010) | . | 0.0021 |
| 42X Z12A | . | . | 0.0116 | 0.0068 | 0.0084 | 0.0070 | . | . | 0.0076 |
| 42X Z3J | . | . | 0.0032 | . | 0.0013 | 0.0006 | (0.0018) | . | . |
| SRM 627 | . | . | . | . | . | . | 0.021 | . | . |
| 42X Z5M | . | . | 0.0328 | . | 0.0026 | . | . | 0.0017 | . |
| BCR 355 | . | . | . | 0.00246 | . | . | . | . | 0.002325 |
| 42X Z4J | . | . | 0.020 | 0.0016 | 0.020 | (0.0029) | . | . | (0.0025) |
| SRM 626 | . | . | . | . | . | . | 0.042 | . | . |
| SRM 625 | . | . | . | . | . | . | 0.017 | . | . |
| BCR 354 | . | . | . | 0.00098 | . | . | . | . | 0.001101 |
| 42X Z2K | . | . | 0.0055 | 0.0047 | 0.0150 | 0.0010 | 0.0011 | . | . |
| BCR 352 | . | . | . | 0.000302 | . | . | . | . | 0.00032 |
| BCR 351 | . | . | . | <0.00002 | . | . | . | . | 0.000074 |
| Zamak 8 | . | . | . | . | . | . | <0.03 | . | . |
| 43X Z14E | . | 0.0096 | . | . | . | 0.0089 | 0.016 | 0.0014 | . |
| 43X Z14F | . | 0.0106 | . | . | . | 0.0105 | (<0.001) | (0.0001) | . |

CRM ZAMAK SET

SOLD IN SET/4 ONLY

40 mm Ø x 25 mm

| Number | Al | Cd | Cu | Fe | Mg | Ni | Pb | Si | Sn |
|----------|------|---------|----------|--------|---------|---------|--------|----------|---------|
| IMN ZG 1 | 3.07 | 0.00048 | 1.34 | 0.0083 | 0.074 | 0.0067 | 0.009 | 0.036 | 0.0068 |
| IMN ZG 2 | 3.56 | 0.0049 | 0.72 | . | 0.048 | 0.0025 | 0.0065 | 0.024 | 0.0048 |
| IMN ZG 3 | 4 | 0.0028 | 0.11 | 0.011 | 0.028 | 0.001 | 0.0033 | 0.01 | 0.00067 |
| IMN ZG 4 | 4.64 | 0.011 | (0.0089) | 0.016 | 0.00055 | 0.00042 | 0.0013 | (0.0047) | 0.0021 |

ZINC BINARY AND TERNARY SAMPLES

= class, where 1 = CRM and 2 = RM analysis listed in mass % cast

| # | Number | Al | Mg | Mn | Pb | Sb | Units |
|---|-----------|--------|------|------|----------|------|-----------------|
| 1 | SRM 1742 | 0.7917 | . | . | (0.0029) | . | 50 mm Ø x 12 mm |
| 1 | SRM 1741 | 0.5242 | . | . | 0.1571 | . | 50 mm Ø x 12 mm |
| 1 | SRM 1740 | 0.4177 | . | . | 0.0691 | . | 50 mm Ø x 12 mm |
| 1 | SRM 1738 | 0.1014 | . | . | 0.0101 | . | 50 mm Ø x 12 mm |
| 2 | 41X ZMg1A | . | 1.13 | . | . | . | 40 mm Ø x 15 mm |
| 1 | 41X ZMn1A | . | . | 1.07 | . | . | 50 mm Ø x 20 mm |
| 2 | 41X ZSb1A | . | . | . | . | 1.03 | 40 mm Ø x 15 mm |
| 2 | 41X ZSb4A | . | . | . | . | 3.78 | 40 mm Ø x 15 mm |
| 2 | 41X ZSb8A | . | . | . | . | 7.68 | 40 mm Ø x 15 mm |

RM ZINC - ALUMINUM - ANTIMONY ALLOYS

cast some Sb segregation in below series, last of stock 40 mm Ø x 15 mm

| Number | Al | Sb | Bi | Cd | Cu | Fe | Mg | Pb | Sn |
|---------|------|-----|-------|-------|-------|-------|--------|-------|-------|
| 44X Z5A | 20.4 | 5.2 | 0.004 | 0.001 | 0.001 | 0.010 | <0.001 | 0.010 | 0.003 |
| 44X Z4A | 20.3 | 6.7 | 0.016 | 0.011 | 0.007 | 0.011 | 0.008 | 0.032 | 0.018 |

CRM ZINC ALLOY SETS

available in SETS ONLY, as grouped

~40 mm Ø x ~25 mm

| Number | Al | Bi | Cd | Cu | Fe | Mg | Mn | Ni | Pb | Sb | Sn | Ti | Zn |
|----------|--------|--------|---------|-------|---------|--------|--------|----|--------|--------|---------|--------|-----|
| IMN ZK 1 | 11.789 | 0.200 | 0.0021 | 1.538 | . | 0.0009 | . | . | 0.0031 | 0.127 | 0.00085 | . | . |
| IMN ZK 2 | 10.572 | 0.169 | 0.0031 | 3.119 | . | 0.0040 | 0.0137 | . | 0.0121 | 0.102 | 0.0015 | . | . |
| IMN ZK 3 | 9.767 | 0.102 | 0.0071 | 3.996 | . | 0.0307 | . | . | 0.0226 | 0.0674 | 0.00267 | . | . |
| IMN ZK 4 | 8.371 | 0.0188 | 0.0121 | 5.487 | . | 0.0640 | . | . | 0.0334 | 0.0121 | 0.00491 | . | . |
| IMN ZK 5 | 6.476 | 0.0020 | 0.0207 | 6.663 | . | 0.0410 | 0.589 | . | 0.0507 | 0.0025 | 0.0065 | . | . |
| IMN ZF 1 | 0.018 | . | 0.0041 | 0.013 | 0.020 | . | . | . | 0.0012 | . | 0.013 | 0.0014 | Rem |
| IMN ZF 2 | 0.011 | . | 0.0055 | 0.46 | 0.011 | . | . | . | 0.0082 | . | 0.0077 | 0.11 | Rem |
| IMN ZF 3 | 0.0033 | . | . | 0.098 | 0.0018 | . | . | . | . | . | 0.0022 | 0.021 | Rem |
| IMN ZF 4 | 0.0058 | . | 0.00053 | 0.86 | 0.00045 | . | . | . | 0.0091 | . | 0.0017 | 0.20 | Rem |
| IMN ZF 5 | . | . | 0.0088 | 0.011 | 0.0081 | . | . | . | 0.026 | . | . | 0.013 | Rem |

| CRM | ZINC ALLOYS, chart 1 of 2 | | | | | | | | | | | | | |
|---------------|-----------------------------------|---------|---------|----------|--------------------------------|----------|---------|---------|----------------------------|--------|---------|----------|-----------|----------|
| | X: ~50 mm \emptyset x ~15-20 mm | | | | CAN: 50 mm \emptyset x 12 mm | | | | SRM: 44 mm x 44 mm x 19 mm | | | | | |
| Number | Al | Bi | Cd | Cr | Cu | Fe | Mg | Mn | Ni | Pb | Sb | Si | Sn | Ti |
| 43X Z23E | 30.7 | . | 0.0042 | 0.0147 | 3.22 | 0.055 | 0.0242 | 0.0090 | 0.0236 | 0.0112 | . | 0.077 | 0.0115 | 0.0045 |
| CAN NZA-1 | 28.70 | . | 0.00098 | . | 1.51 | 0.046 | 0.020 | . | . | 0.0030 | . | . | 0.0069 | . |
| 43X Z22D | 27.4 | . | 0.0043 | 0.0010 | 2.11 | 0.068 | 0.0099 | 0.0057 | 0.0101 | 0.0053 | . | 0.019 | 0.0020 | 0.0073 |
| CAN NZA-4 | 26.65 | . | 0.0029 | . | 2.45 | 0.027 | 0.0106 | . | . | 0.0101 | . | . | 0.0087 | . |
| CAN NZA-3 | 25.99 | . | 0.0064 | . | 2.00 | 0.066 | 0.0049 | . | . | 0.0045 | . | . | 0.0034 | . |
| 43X Z21D | 23.9 | . | 0.0010 | . | 2.68 | 0.0067 | 0.0142 | 0.0022 | 0.0021 | 0.0087 | . | 0.0191 | 0.0007 | . |
| CAN NZA-2 | 23.81 | . | 0.0047 | . | 3.00 | 0.021 | 0.029 | . | . | 0.0076 | . | . | 0.0045 | . |
| 43X GALF5A | 15.03 | . | 0.0080 | . | 0.0114 | (0.072) | 0.0016 | . | . | 0.0084 | . | . | 0.0081 | . |
| CAN NZA-7 | 13.17 | . | 0.00020 | . | 0.212 | (0.016) | 0.052 | . | . | 0.0136 | . | . | 0.0116 | . |
| 42X Z16A | 12.28 | . | 0.0045 | 0.0007 | 0.235 | 0.033 | 0.105 | 0.0028 | 0.0039 | 0.0090 | . | 0.011 | 0.0034 | . |
| 43X Z11F | 11.12 | 0.0046 | 0.0175 | (0.0003) | 0.335 | 0.015 | 0.0357 | 0.0032 | 0.0014 | 0.0202 | 0.0009 | 0.0013 | 0.0145 | . |
| CAN NZA-5 | 10.85 | . | 0.0095 | . | 1.04 | (0.016) | 0.021 | . | . | 0.0012 | . | . | 0.0017 | . |
| 43X GALF4A | 10.71 | . | 0.0108 | . | 2.470 | 0.074 | 0.0062 | . | . | 0.0122 | . | . | 0.0110 | . |
| 43X Z12E | 10.38 | 0.0021 | 0.0045 | 0.0008 | 0.791 | 0.037 | 0.0287 | 0.0026 | 0.0033 | 0.0041 | 0.0032 | (0.002) | 0.0017 | 0.0050 |
| 42X Z15A | 9.99 | . | 0.0023 | 0.0003 | 0.0028 | 0.026 | 0.0026 | 0.0037 | 0.0017 | 0.0074 | 0.0006 | . | 0.0006 | . |
| 43X Z13E | 9.01 | 0.0014 | 0.0072 | 0.0004 | 1.113 | 0.0045 | 0.0198 | 0.0025 | 0.0036 | 0.0086 | 0.0020 | (0.0012) | 0.0035 | . |
| 43X GALF3A | 8.37 | . | 0.0018 | . | 0.507 | 0.018 | 0.0099 | . | . | 0.0032 | . | . | 0.0025 | . |
| CAN NZA-6 | 7.54 | . | 0.0147 | . | 3.17 | (0.0105) | 0.00037 | . | . | 0.0809 | . | . | 0.0051 | . |
| 43X Z15C | 7.36 | (0.005) | 0.0030 | 0.0024 | 1.54 | . | 0.0022 | 0.0020 | 0.0019 | 0.0060 | (0.005) | (0.007) | 0.004 | 0.002 |
| 42X Z8A | 7.03 | . | 0.0003 | (0.0002) | 0.0215 | . | 0.0033 | 0.0014 | 0.0019 | 0.0025 | . | 0.013 | (0.0023) | (0.0001) |
| 42X Z9A | 5.58 | . | 0.0054 | . | 0.0070 | . | 0.0464 | 0.0006 | (0.0003) | 0.0021 | . | (0.004) | (0.00035) | 0.020 |
| 43X GALF2A | 5.40 | . | 0.0043 | . | 0.0585 | 0.032 | 0.0504 | . | . | 0.0050 | . | . | 0.0040 | . |
| SRM 629 | 5.15 | . | 0.0155 | 0.0008 | 1.50 | 0.017 | 0.094 | 0.0017 | 0.0075 | 0.0135 | . | 0.078 | 0.012 | . |
| 42X Z10A * | 4.90 | . | 0.0032 | . | 0.31 | 0.0008 | 0.0021 | 0.018 | 0.010 | 0.006 | <0.001 | . | 0.0035 | . |
| 43X GALF1A | 4.68 | . | 0.0499 | . | 4.39 | 0.061 | 0.0999 | . | . | 0.0505 | . | . | 0.0514 | . |
| 42X Z7B | 4.39 | . | 0.030 | (0.0001) | 0.0249 | 0.027 | 0.0095 | 0.0045 | 0.0067 | 0.0097 | . | 0.006 | 0.012 | . |
| 42X Z7C | 4.39 | . | 0.030 | (0.0001) | 0.0249 | 0.027 | 0.0095 | 0.0045 | 0.0067 | 0.0097 | . | 0.006 | 0.012 | (0.0001) |
| 43X SC4A | 4.35 | . | 0.0058 | 0.009 | 1.122 | 0.022 | 0.093 | 0.044 | 0.0249 | 0.0064 | . | 0.022 | 0.0056 | . |
| 43X Z10A | 3.99 | . | 0.0014 | 0.00027 | 2.97 | 0.007 | 0.0403 | 0.0050 | 0.0036 | 0.0046 | . | 0.009 | 0.0012 | . |
| 43X SC1A | 3.75 | . | 0.0011 | 0.0082 | 1.903 | 0.073 | 0.740 | 0.0201 | 0.0161 | 0.0150 | . | 0.022 | 0.0082 | . |
| 43X SC2A | 3.41 | . | 0.0018 | 0.023 | 4.80 | 0.046 | 0.498 | 0.0183 | 0.0096 | 0.0097 | . | 0.0133 | 0.0031 | . |
| 42X Z11A | 3.19 | . | 0.0020 | 0.0016 | 0.093 | (0.036) | 0.0329 | 0.0196 | 0.0241 | 0.0058 | 0.0047 | . | 0.0017 | . |
| 43X Z9A | 3.17 | 0.0033 | 0.0034 | 0.0034 | 4.82 | 0.073 | 0.0472 | 0.0108 | 0.0027 | 0.0078 | 0.0033 | . | 0.0020 | 0.0012 |
| 43X Z5B | 3.164 | 0.0148 | 0.0030 | . | 5.92 | 0.10 | 0.0144 | 0.0061 | 0.0056 | 0.0029 | 0.065 | . | (0.0004) | . |
| 43X SC3A | 3.14 | . | 0.0028 | 0.0108 | 3.03 | 0.018 | 0.257 | 0.0337 | 0.0261 | 0.0066 | . | 0.022 | 0.0078 | . |
| 43X Z8A | 2.51 | . | 0.00090 | 0.00024 | 0.481 | (0.0017) | 0.00155 | 0.00021 | 0.00033 | 0.0027 | . | . | (0.0005) | . |
| 41X 0336Zn2M | 1.55 | 0.0099 | 0.145 | . | 0.354 | (0.01) | 0.099 | 0.0212 | 0.0137 | 0.486 | 0.0007 | . | 0.038 | . |
| 41X 0336Zn2N* | 1.00 | 0.0044 | 0.150 | Co:0.019 | 0.215 | 0.028 | 0.057 | 0.023 | 0.0047 | 0.49 | 0.0018 | . | 0.056 | . |

| Number | Al | Bi | Cd | Cr | Cu | Fe | Mg | Mn | Ni | Pb | Sb | Si | Sn | Ti |
|----------------|--------|------------------------|--------|--------|--------|----------|---------|-------|-----------------------------|---------------|----|----|----|----|
| 43X Z23E | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| CAN NZA-1 | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X Z22D | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| CAN NZA-4 | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| CAN NZA-3 | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X Z21D | . | (0.0004) | . | . | . | . | . | . | . | . | . | . | . | . |
| CAN NZA-2 | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X GALF5A | . | . | . | 0.0041 | . | 0.0019 | . | . | . | . | . | . | . | . |
| CAN NZA-7 | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 42X Z16A | . | . | . | . | 0.0051 | . | (0.003) | . | . | . | . | . | . | . |
| 43X Z11F | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| CAN NZA-5 | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X GALF4A | . | . | . | 0.079 | . | 0.041 | . | . | . | . | . | . | . | . |
| 43X Z12E | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 42X Z15A | . | . | . | . | 0.0024 | . | . | . | . | . | . | . | . | . |
| 43X Z13E | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X GALF3A | . | . | . | 0.0152 | . | 0.0076 | . | . | . | . | . | . | . | . |
| CAN NZA-6 | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X Z15C | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 42X Z8A | . | . | . | 0.0081 | . | 0.0079 | . | . | . | . | . | . | . | . |
| 42X Z9A | . | . | . | 0.0047 | . | 0.0044 | . | 0.011 | . | . | . | . | . | . |
| 43X GALF2A | . | . | . | 0.0318 | . | 0.0158 | . | . | . | . | . | . | . | . |
| SRM 629 | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 42X Z10A * | . | * Provisional Analysis | . | . | 0.0022 | . | <0.001 | . | . | . | . | . | . | . |
| 43X GALF1A | . | . | . | 0.0569 | . | 0.0284 | . | . | . | . | . | . | . | . |
| 42X Z7B | . | . | . | 0.072 | . | 0.061 | . | . | . | . | . | . | . | . |
| 42X Z7C | . | . | . | 0.09 | . | 0.08 | . | . | . | . | . | . | . | . |
| 43X SC4A | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X Z10A | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X ZSC1A | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X SC2A | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 42X Z11A | . | . | . | 0.0014 | 0.0037 | (0.0009) | 0.0047 | . | . | . | . | . | . | . |
| 43X Z9A | . | . | 0.0010 | . | . | . | . | . | . | . | . | . | . | . |
| 43X Z5B | 0.0254 | (0.0005) | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X ZSC3A | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 43X Z8 | . | . | . | . | . | . | . | . | . | . | . | . | . | . |
| 41X 0336Zn2M | 0.0102 | 0.0009 | . | . | . | . | 0.0012 | . | ~50 mm \emptyset x ~15 mm | last of stock | . | . | . | . |
| 41X 0336Zn2N * | 0.014 | * Provisional Analysis | . | . | . | . | 0.0016 | . | . | . | . | . | . | . |

| Number | Ag | As | Be | Ce | In | La | Tl | Zr |
|----------------|--------|------------------------|--------|--------|--------|----------|---------|-----------------------------|
| 43X Z23E | . | . | . | . | . | . | . | . |
| CAN NZA-1 | . | . | . | . | . | . | . | . |
| 43X Z22D | . | . | . | . | . | . | . | . |
| CAN NZA-4 | . | . | . | . | . | . | . | . |
| CAN NZA-3 | . | . | . | . | . | . | . | . |
| 43X Z21D | . | (0.0004) | . | . | . | . | . | . |
| CAN NZA-2 | . | . | . | . | . | . | . | . |
| 43X GALF5A | . | . | . | 0.0041 | . | 0.0019 | . | . |
| CAN NZA-7 | . | . | . | . | . | . | . | . |
| 42X Z16A | . | . | . | . | 0.0051 | . | (0.003) | . |
| 43X Z11F | . | . | . | . | . | . | . | . |
| CAN NZA-5 | . | . | . | . | . | . | . | . |
| 43X GALF4A | . | . | . | 0.079 | . | 0.041 | . | . |
| 43X Z12E | . | . | . | . | . | . | . | . |
| 42X Z15A | . | . | . | . | 0.0024 | . | . | . |
| 43X Z13E | . | . | . | . | . | . | . | . |
| 43X GALF3A | . | . | . | 0.0152 | . | 0.0076 | . | . |
| CAN NZA-6 | . | . | . | . | . | . | . | . |
| 43X Z15C | . | . | . | . | . | . | . | . |
| 42X Z8A | . | . | . | 0.0081 | . | 0.0079 | . | . |
| 42X Z9A | . | . | . | 0.0047 | . | 0.0044 | . | 0.011 |
| 43X GALF2A | . | . | . | 0.0318 | . | 0.0158 | . | . |
| SRM 629 | . | . | . | . | . | . | . | . |
| 42X Z10A * | . | * Provisional Analysis | . | . | 0.0022 | . | <0.001 | . |
| 43X GALF1A | . | . | . | 0.0569 | . | 0.0284 | . | . |
| 42X Z7B | . | . | . | 0.072 | . | 0.061 | . | . |
| 42X Z7C | . | . | . | 0.09 | . | 0.08 | . | . |
| 43X SC4A | . | . | . | . | . | . | . | . |
| 43X Z10A | . | . | . | . | . | . | . | . |
| 43X ZSC1A | . | . | . | . | . | . | . | . |
| 43X SC2A | . | . | . | . | . | . | . | . |
| 42X Z11A | . | . | . | 0.0014 | 0.0037 | (0.0009) | 0.0047 | . |
| 43X Z9A | . | . | 0.0010 | . | . | . | . | . |
| 43X Z5B | 0.0254 | (0.0005) | . | . | . | . | . | . |
| 43X ZSC3A | . | . | . | . | . | . | . | . |
| 43X Z8 | . | . | . | . | . | . | . | . |
| 41X 0336Zn2M | 0.0102 | 0.0009 | . | . | . | . | 0.0012 | ~50 mm \emptyset x ~15 mm |
| 41X 0336Zn2N * | 0.014 | * Provisional Analysis | . | . | . | . | 0.0016 | last of stock |

CRM ZINC ALLOYS, chart 2 of 2

41X CGL: 42 - 48 mm Ø x 20 mm other X: ~45--50 mm Ø x ~20 mm

| Number | Al | Bi | Cd | Cr | Cu | Fe | Mg | Mn | Ni | Pb | Sb | Si | Sn | Ti |
|----------------|--------|----------|----------|----------|----------|--------|---------|----------|----------|--------|---------|----|----------|----------|
| 41X GLV10A | 0.969 | 0.0031 | 0.0030 | . | 0.0073 | 0.0051 | 0.0040 | 0.0062 | 0.0022 | 0.0066 | 0.0009 | . | 0.0062 | . |
| 41X GLV9A | 0.547 | 0.0019 | 0.0028 | . | 0.0037 | 0.0039 | 0.0014 | 0.0027 | 0.0009 | 0.0043 | 0.0048 | . | 0.0028 | . |
| 41X GLV4E | 0.503 | 0.0047 | 0.0013 | 0.00104 | 0.0246 | (0.01) | 0.0025 | 0.164 | 0.0078 | 0.0058 | 0.0235 | . | 0.0035 | . |
| 41X GLV11A | 0.463 | 0.0009 | 0.0010 | . | 0.0017 | 0.0027 | 0.0009 | 0.0008 | 0.0008 | 0.0057 | 0.168 | . | 0.0009 | . |
| 41X 4380 Zn4D | 0.446 | 0.0101 | 0.086 | 0.0029 | 0.0284 | 0.017 | 0.118 | 0.0092 | 0.0172 | 0.310 | 0.0156 | . | 0.0416 | (0.0003) |
| 41X GLV6B | 0.441 | 0.0254 | 0.0051 | 0.0007 | 0.0371 | 0.0020 | . | 0.00235 | 0.0007 | 0.097 | 0.0122 | . | 0.0155 | . |
| 41X GLV7A | 0.399 | (0.0108) | 0.00056 | 0.0010 | 0.023 | . | . | 0.0025 | 0.0060 | 0.082 | 0.0031 | . | (0.0006) | . |
| 41X 0336 Zn3K | 0.336 | . | 0.341 | . | 0.353 | 0.0456 | 0.147 | 0.0106 | 0.0022 | 0.0282 | . | . | 0.127 | . |
| 41X GLV3C | 0.326 | 0.0031 | 0.0183 | 0.0003 | 0.0332 | 0.0014 | 0.0014 | 0.0185 | 0.0335 | 0.0249 | 0.0555 | . | 0.0031 | . |
| 41X 4380 Zn9A | 0.295 | 0.00046 | 0.0032 | 0.0015 | 0.0416 | 0.0113 | 0.0153 | 0.0018 | 0.0009 | 0.0139 | 0.0060 | . | 0.0008 | . |
| 41X CGLF | 0.28 | . | (0.0015) | . | (0.0005) | . | . | . | . | 0.046 | . | . | (<0.001) | . |
| 41X GLV1E * | 0.28 | 0.004 | 0.009 | . | 0.019 | 0.001 | 0.002 | . | 0.002 | 0.018 | 0.001 | . | 0.005 | . |
| 41X 4380 Zn7D | 0.277 | . | 0.0156 | . | 0.0133 | 0.0018 | 0.0029 | 0.0036 | 0.0120 | 1.18 | 0.086 | . | 0.0036 | 0.0065 |
| 41X GLV8A | 0.263 | 0.0005 | 0.0003 | 0.0012 | 0.0139 | 0.0062 | 0.0012 | 0.0012 | 0.0006 | 0.0037 | 0.0057 | . | 0.0005 | . |
| 41X GLV8B | 0.258 | 0.0006 | 0.0004 | (0.0001) | 0.0111 | 0.0080 | 0.0009 | 0.0035 | 0.0023 | 0.0039 | 0.0062 | . | 0.0005 | . |
| 41X 4380 Zn8D | 0.232 | 0.0156 | 0.0097 | (0.0001) | 0.0208 | 0.0074 | 0.0054 | 0.0081 | 0.0445 | 0.700 | 0.0151 | . | 0.0177 | 0.0020 |
| 41X GLV2C | 0.0905 | 0.0158 | 0.0037 | 0.0015 | 0.0057 | 0.0155 | 0.0006 | 0.0218 | 0.0053 | 0.0248 | 0.0049 | . | 0.0097 | . |
| 41X 2951 Zn3A | 0.078 | . | 0.0062 | 0.184 | 1.89 | . | 0.0164 | 0.0018 | 0.0010 | 0.0065 | . | . | (0.006) | 0.133 |
| 41X GLV2A | 0.068 | 0.017 | 0.0025 | . | 0.0052 | 0.048 | . | . | 0.0070 | 0.214 | 0.006 | . | 0.003 | . |
| 41X Zn1BiA | 0.050 | 0.502 | 0.0020 | . | 0.0132 | 0.0133 | . | . | 2.02 | 0.0187 | . | . | 0.154 | . |
| 41X 4380 Zn1D | 0.039 | 0.0021 | 0.394 | 0.0007 | 0.178 | 0.0276 | 0.0032 | 0.0006 | 0.0058 | 0.0618 | 0.0019 | . | 0.0510 | 0.0004 |
| 41X 0336 Zn5A | 0.035 | (0.001) | 0.056 | . | 0.023 | . | <0.0005 | (0.0001) | (0.0005) | 0.91 | 0.008 | . | 0.21 | . |
| 41X 2951 Zn2A | 0.032 | . | 0.0037 | 0.142 | 1.37 | . | 0.0123 | 0.0011 | 0.0027 | 0.0040 | . | . | (0.0015) | 0.209 |
| 41X 2951 Zn1A | 0.029 | . | 0.0005 | 0.083 | 0.79 | . | 0.0029 | 0.0013 | 0.0038 | 0.0042 | . | . | (0.0007) | 0.278 |
| 41X 4380 Zn6D | 0.0260 | 0.0047 | 0.0466 | 0.0064 | 0.0327 | 0.0307 | 0.0044 | 0.200 | 0.0073 | 0.427 | (0.002) | . | 0.101 | 0.0029 |
| 41X 4380 Zn5C | 0.0215 | 0.0308 | 0.0571 | 0.0075 | 0.071 | . | 0.00165 | 0.035 | 0.00147 | 0.140 | 0.0061 | . | 0.0101 | 0.339 |
| 41X 4380 Zn3C | 0.0203 | 0.0103 | 0.0950 | 0.0029 | 0.073 | . | 0.0220 | 0.0180 | 0.0120 | 0.180 | 0.0046 | . | 0.080 | 0.125 |
| 41X 0336 Zn1L | 0.0177 | . | 0.0067 | . | 0.0088 | 0.0106 | 0.0062 | 0.0102 | 0.0009 | 1.007 | . | . | 0.0051 | . |
| 41X 4380 Zn2C | 0.0153 | 0.0076 | 0.284 | 0.0027 | 0.0288 | . | 0.0243 | 0.0087 | 0.0023 | 0.268 | 0.0093 | . | 0.0021 | 0.0251 |
| 41X GLV5B | 0.0139 | 0.0098 | 0.0136 | . | 0.0103 | 0.0443 | 0.0014 | . | 0.0025 | 0.0166 | 0.148 | . | 0.0172 | . |
| 41X Zn12A | 0.0135 | 0.0050 | 0.0010 | . | 0.0056 | 0.0061 | . | . | 1.97 | 0.0172 | . | . | 0.141 | . |
| 41X 4380 Zn10A | 0.0004 | . | 0.0007 | 0.117 | 0.0022 | 0.49 | 0.184 | . | 0.063 | 0.0043 | 0.0005 | . | 0.0014 | . |

| Number | Al | Bi | Cd | Cr | Cu | Fe | Mg | Mn | Ni | Pb | Sb | Si | Sn | Ti |
|--------|----|----|----|----|----|----|----|----|----|----|----|----|----|----|
|--------|----|----|----|----|----|----|----|----|----|----|----|----|----|----|

| Number | Ag | As | Co | In | Tl |
|--------|----|----|----|----|----|
|--------|----|----|----|----|----|

| | | | | | |
|----------------|--------|------------------------|----------|---------|---------------|
| 41X GLV10A | . | . | 0.0002 | . | . |
| 41X GLV9A | . | . | 0.0005 | . | . |
| 41X GLV4E | . | 0.0002 | 0.0061 | . | . |
| 41X GLV11A | . | . | (0.0001) | . | Sr:(0.0004) |
| 41X 4380 Zn4D | . | . | 0.0018 | . | . |
| 41X GLV6B | . | . | 0.0061 | . | V:<0.0005 |
| 41X GLV7A | . | 0.0016 | . | . | . |
| 41X 0336 Zn3K | . | 0.0003 | . | . | . |
| 41X GLV3C | . | 0.0036 | 0.0034 | . | . |
| 41X 4380 Zn9A | . | . | . | . | . |
| 41X CGLF | . | . | (0.001) | (0.001) | last of stock |
| 41X GLV1E * | . | * Provisional Analysis | . | . | . |
| 41X 4380 Zn7D | . | . | . | . | . |
| 41X GLV8A | . | . | . | . | . |
| 41X GLV8B | . | . | . | . | . |
| 41X 4380 Zn8D | 0.0140 | . | . | . | . |
| 41X GLV2C | . | 0.0017 | 0.0055 | . | . |
| 41X 2951 Zn3A | . | . | . | . | . |
| 41X GLV2A | . | <0.001 | . | . | last of stock |
| 41X Zn1BiA | . | . | . | . | . |
| 41X 4380 Zn1D | 0.0012 | . | . | . | . |
| 41X 0336 Zn5A | . | . | . | . | . |
| 41X 2951 Zn2A | . | . | . | . | . |
| 41X 2951 Zn1A | . | . | . | . | . |
| 41X 4380 Zn6D | 0.0030 | . | 0.0091 | . | . |
| 41X 4380 Zn5C | . | . | . | . | . |
| 41X 4380 Zn3C | . | . | . | . | . |
| 41X 0336 Zn1L | . | 0.0008 | . | . | . |
| 41X 4380 Zn2C | . | . | . | . | . |
| 41X GLV5B | . | 0.00044 | 0.0011 | . | . |
| 41X Zn12A | . | . | . | . | . |
| 41X 4380 Zn10A | . | . | . | . | . |

| Number | Ag | As | Co | In | Tl |
|--------|----|----|----|----|----|
|--------|----|----|----|----|----|