

INDEX

BISMUTH 1

HARD LEAD 4

SILVER 12, 13

SILVER ALLOYS 13

CADMIUM 1

JEWELRY 12

CHROMIUM 2

TIN 5, 14, 15, 16

COBALT 2

TITANIUM 16, 17, 18

LEAD 3, 4, 5, 6

FUSIBLE ALLOY 1

XRF 3, 4, 16, 21

MAGNESIUM 7, 8, 9, 10, 11

GOLD 12, 13

ZAMAK 20

RoHS MONITOR 19

ZINC 19, 20, 21, 22, 23

RM BISMUTH BASE and FUSIBLE SOLDER ALLOYS

95X: ~40 mm Ø x ~15 mm NF: 37 mm Ø x 12 mm

Number	Bi	Cd	In	Pb	Sn	Ag	Al	As	Au	Co	Cu	Fe	Hg	Ni	Sb	Zn	Other
95X BIS40P1A	57.4	0.0050	0.0164	0.043	42.3	0.035	.	0.0101	.	.	0.0670	(0.001)	.	.	0.092	0.011	
95X 174A	57.1	0.0089	26.08	0.082	16.70	0.0075	0.0030	.	.	.	0.086	0.037	Melt °C: 79
95X 255A	55.7	0.0065	0.010	43.7	0.24	0.0019	0.045	.	.	.	0.32	0.035	Melt °C: 124
95X BIS40P2A	55.25	0.0008	0.0049	0.020	44.66	0.005	0.0021	0.0019	0.0006	0.0012	0.0026	0.0013	(0.0016)	0.0020	0.005	0.0016	Ge: (0.0005)
NF 64-7	Rem	.	0.003	0.076	45.0	1.25	.	0.006	0.011	0.026	0.004	.	.	0.005	0.26	.	
NF 64-6	Rem	.	0.007	0.26	43.1	0.70	.	0.018	0.035	0.039	0.11	.	.	0.042	0.11	.	
NF 64-5	Rem	.	0.098	0.006	42.6	0.99	0.076	.	.	.	0.078	.	
NF 64-4	Rem	.	0.075	0.052	42.0	0.40	.	0.010	<0.001	<0.001	0.006	.	.	0.025	0.053	.	
NF 64-3	Rem	.	0.049	0.025	41.4	0.20	.	0.005	.	.	0.049	.	.	0.072	0.026	.	
NF 64-1	Rem	.	0.010	0.098	41.0	0.006	.	0.0006	.	.	0.026	.	.	0.093	0.001	.	
NF 64-2	Rem	.	0.024	0.012	40.5	0.052	.	0.001	.	.	0.15	.	.	0.011	0.013	.	
95X 158	50.2	9.6	0.006	27.0	13.5	0.002	0.048	.	.	.	0.057	0.044	Melt °C: 70
95X BISS0P1A	49.8	0.022	.	.	50.0	0.051	.	0.025	.	0.006	
95X BISS0P3A	49.8	0.015	.	.	48.6	1.50	.	0.073	0.0025	.	.	0.003	.	.	.	0.002	
95X BISS0P2A	49.6	.	.	.	50.3	0.090	0.005	0.002	0.015	.	.	0.007	
95X 136A	48.8	0.0092	21.49	18.0	12.05	0.0056	0.0028	.	.	.	0.022	0.031	Melt °C: 58
95X 117A	45.3	4.95	18.72	23.1	8.02	0.0043	0.010	.	.	.	0.010	0.0056	Melt °C: 47
95X BIS70P1A	29.6	.	0.040	.	69.1	1.10	<0.001	0.025	0.0004	.	.	0.010	
95X BIS70P2A	32.8	.	0.049	.	65.0	2.01	<0.001	0.029	.	0.001	
95X PBS40P1A	13.8	0.0043	0.005	(43.6)	42.6	0.011	(0.0006)	0.005	.	.	0.025	(0.0006)	.	.	0.016	0.0010	

RM CADMIUM ALLOY

Number	Cd	Sn	Units
95X SC34A	(65.99)	34.05	40 mm Ø x 15 mm
95X SC36A	(63.98)	36.09	40 mm Ø x 15 mm

CRM CADMIUM SETS

AVAILABLE IN SETS ONLY, AS GROUPED

Number	As	Cu	Ni	Pb	Sb	Sn	Tl	Set Size
KZ 030101-03 - 1	.	0.0023	0.0010	0.0060	.	.	0.0011	
KZ 030101-03 - 2	.	0.0039	0.0018	0.011	.	.	0.0021	
KZ 030101-03 - 3	.	0.0068	0.00044	0.022	.	.	0.0047	40 mm Ø x 30 mm
KZ 030101-03 - 4	.	0.013	0.0043	0.047	.	.	0.0091	
KZ 030101-03 - 5	.	0.024	0.011	0.12	.	.	0.023	
IMN K1	(0.00030)	.	0.0086	.	0.0064	0.0061	.	
IMN K2	0.0012	.	0.018	.	0.0038	0.0032	.	
IMN K3	0.0010	.	0.063	.	0.0010	0.00065	.	40 mm Ø x 25 mm
IMN K4	0.0056	.	0.11	.	0.0011	0.00091	.	
IMN K5	0.0014	.	0.0054	.	0.00017	.	.	

CRM CHROMIUM ALLOY ~40 mm Ø x ~15 mm

Number	Cr	C	Co	Cu	Fe	Mn	Mo	N	Nb	Ni	P	S	Si	W
219X 20500C	51.0	0.0212	0.0110	0.0101	1.515	0.299	0.0103	0.199	0.0117	45.46	0.0048	0.0137	1.288	0.0086

COBALT BASE ALLOYS

= class, where 1 = CRM and 2 = rm analysis listed in mass %

#	Number	Cr	Fe	Mn	Mo	Nb	Ni	W	Al	C	Cu	P	S	Si	Ti	Co
1	112X 14943H	31.00	0.763	1.008	7.96	0.099	0.151	0.051	(0.13)	0.190	0.203	0.0043	0.0197	0.201	0.005	.
1	IARM Co6B-18	30.7	2.68	1.48	0.020	(0.014)	2.59	3.92	(0.07)	1.02	(0.015)	.	(<0.0010)	0.61	(0.007)	57.0
1	ECRM 378-1D	28.22	0.606	0.0579	0.053	.	0.617	4.43	.	1.181	.	(0.0023)	0.0055	1.172	.	63.52
2	BS 173	27.5	0.19	0.76	5.62	(0.002)	0.14	.	(0.04)	0.046	(0.008)	(0.003)	0.001	0.61	(0.004)	65.0
2	CT ISO074A	27.12	(0.93)	0.78	5.47	.	0.150	<0.01	.	0.089	0.005	0.002	0.002	0.59	.	64.87
1	IMZ 188	26.44	1.14	0.68	0.42	0.045	10.76	7.46	(0.005)	0.526	0.025	0.011	(0.0002)	0.69	(0.007)	51.64
1	119X COB1H	24.62	15.15	0.514	0.413	0.405	22.14	11.99	0.055	0.0520	0.0607	0.0192	0.0099	0.493	.	.
1	IMZ 186	23.14	0.10	.	.	.	10.22	7.17	0.28	0.59	0.19	Rem
2	BS 172A	21.85	1.76	0.77	0.30	0.09	23.7	14.0	0.08	0.098	0.027	(0.011)	(<0.0005)	0.37	.	.
2	BS 171B	20.5	1.82	1.90	0.65	0.046	10.68	15.1	0.08	0.087	0.035	0.008	<0.001	0.29	.	.
2	111X 12671J	20.5	1.45	0.61	.	1.95	0.88	11.8	0.51	.	.
1	IARM CoElgiloy-18	20.4	12.6	2.36	8.6	(0.006)	15.9	(0.008)	(0.011)	0.008	(0.005)	0.0019	(0.0018)	0.05	(0.004)	40.4
1	SRM 1242	20.0	1.80	1.58	.	(<0.005)	9.78	15.1	(<0.01)	0.126	0.0010	0.002	0.0007	0.016	.	51.5
1	IARM 326A	(0.002)	49.6	0.003	(0.002)	0.038	0.037	(0.001)	(0.003)	(0.002)	(0.002)	0.0013	0.0011	0.029	(0.002)	48.4

#	Number	Cr	Fe	Mn	Mo	Nb	Ni	W	Al	C	Cu	P	S	Si	Ti	Co	
	Number	B	La	Mg	N	O	Pb	Sn	Ta	V	Zr	Units					
	112X 14943H	0.0045	.	.	0.0284	.	.	.	(0.014)	0.009	.	.	~40 mm Ø x ~15 mm				
	IARM Co6B-18	.	.	.	0.017	0.011	.	.	31 mm Ø x 2 or 18 mm				
	ECRM 378-1D	40 mm Ø x 20 mm				
	BS 173	(0.001)	.	.	0.190	(0.002)	.	.	.	(0.01)	.	.	35 mm Ø x ~7 or 19+ mm				
	CT ISO074A	(<0.0010)	.	.	0.17	0.005	.	.	30-35 mm Ø x ~16 mm				
	IMZ 188	0.0009	(0.011)	(0.011)	(0.0004)	1/4 of 75 mm Ø cylinder x 20 mm					
	119X COB1H	.	.	.	0.093	~40 mm Ø x ~15 mm				
	IMZ 186	(0.007)	3.78	.	0.40	1/4 of 78 mm Ø cylinder x 30 mm					
	BS 172A	(0.003)	0.045	(0.001)	(0.024)	0.007	.	38 mm Ø x ~7 or 19+ mm					
	BS 171B	(0.02)	.	38 mm Ø x ~7 or 19+ mm					
	IARM CoElgiloy-18	(0.002)	.	.	0.0034	0.009	.	.	(0.01)	(0.009)	.	31 mm Ø x 2 or 18 mm					
	111X 12671J	40 mm Ø x 15 mm last					
	SRM 1242	(<0.0001)	.	(<0.001)	0.026	.	(<0.0001)	(<0.001)	(<0.01)	0.005	(<0.01)	43 mm Ø x 20 mm					
	IARM 326A	(0.001)	.	(0.001)	0.0004	0.0082	.	<0.001	(0.01)	1.94	0.002	31 mm Ø x 2 mm					

Number	B	La	Mg	N	O	Pb	Sn	Ta	V	Zr	Units
--------	---	----	----	---	---	----	----	----	---	----	-------

Need a larger size?
Most BS items are
available in any height.

LEAD

= class, where 1 = CRM and 2 = RM analysis listed in mass %

#	Number	Ag	As	Bi	Cd	Cu	Ni	Sb	Se	Sn	Te	Zn
1	83X PR1K	0.1029	0.0338	0.0508	0.074	0.0465	(0.0004)	0.0100	0.0008	0.016	0.0058	(0.002)
1	83X PR4H	0.0114	0.0003	0.0150	0.0081	0.0454	0.0029	0.0050	(0.004)	.	0.0229	.
1	SRM C2417	0.010	0.011	0.010	(<0.0002)	0.010	(<0.0005)	0.010	.	(<0.010)	(<0.0005)	(<0.0005)
1	83X PR11A	0.0030	0.0095	0.0117	0.0008	0.0551	0.0011	0.497	(0.0001)	0.119	.	.
1	83X PR12A	0.0030	(0.0003)	0.0119	0.0011	0.0353	0.0009	0.0011	(0.0002)	0.0005	.	.
2	83X PR9-1A	0.003	.	.	0.0004	0.054	.	0.0007
1	83X PR3G	0.0029	0.0011	0.144	0.0462	0.0694	0.0116	0.0888	0.0166	0.0417	0.0039	(0.0007)
1	83X CU06A	0.0019	(0.0001)	0.0134	(0.00006)	0.0554	0.0003	(0.0008)	(0.0005)	(0.0004)	(0.0002)	(0.0003)
1	BCR 287A	0.00152	<0.0000003	0.00673	0.000036	0.000098	0.0000024	0.0000040	<0.000005	<0.000005	<0.00002	<0.00001
1	83X PR5G/2	0.0110	0.0003	0.0086	0.00029	0.00058	(0.00017)	0.0006	0.0004	(0.0007)	0.0003	(0.00016)
1	SRM C2418	0.0007	(<0.0001)	(<0.0005)	0.0003	(<0.0001)	(<0.0005)	(<0.0001)	.	(<0.0005)	(<0.0005)	(<0.0005)
2	BCS 210e *	0.0001	.	0.0008	.	0.0006	<0.001	<0.002	.	<0.002	.	<0.005
1	BCR 286A	0.0000015	<0.0000002	0.00215	0.0000125	0.000149	0.0000041	0.000010	<0.000005	<0.000005	<0.00001	<0.00001
1	ERM-EB107	.	.	.	0.00261
1	ERM-EB108	.	.	.	0.00260

Number	Al	Au	Ca	Fe	Hg	In	Mn	Na	Pt	S	Ti	Tl	Units
83X PR1K	(0.0003)	0.0019	.	.	.	0.0080	~40 mm Ø x ~15 mm
83X PR4H	.	0.0021	.	.	0.019	0.0021	~40 mm Ø x ~15 mm
SRM C2417	(<0.0001)	.	(<0.0001)	(<0.0003)	.	.	(<0.0003)	50 mm Ø x 16 mm
83X PR11A	.	.	.	(0.0003)	0.009	.	0.0042	~40 mm Ø x ~15 mm
83X PR12A	.	.	.	(0.0003)	(0.0002)	.	0.0051	~40 mm Ø x ~15 mm
83X PR9-1A	0.0001	Ba:0.033	0.096	.	Li:0.004	.	Mg:0.006	0.015	~40 mm Ø x ~15 mm
83X PR3G	.	0.0036	.	.	0.0008	0.0093	.	(0.0038)	.	.	.	0.0033	~40 mm Ø x ~15 mm
83X CU06A	0.0011	.	.	~40 mm Ø x ~15 mm
BCR 287A	0.000073	60 mm x 60 mm x 12 mm
83X PR5G/2	(0.0001)	(0.0001)	(0.0001)	~40 mm Ø x ~15 mm
SRM C2418	(<0.0001)	.	(<0.0005)	(<0.0005)	.	.	(<0.0005)	50 mm Ø x 16 mm
BCS 210e *	<0.001	.	.	0.0005	.	.	<0.001	.	.	.	0.001	.	500 g(10.5 x 2 x 2 cms)
BCR 286A	0.00025	60 mm x 60 mm x 12 mm
ERM-EB107	0.00113	40 mm Ø x 40 mm
ERM-EB108	0.00083	40 mm Ø x 40 mm

** BCS 210e has a certified melting point of 327.3 °C and Pb: 99.996

CRM REFINED LEAD SET

available in SET/7 ONLY

analysis listed in mg/kg

40 mm Ø x 27 mm

Number	Ag	As	Bi	Ca	Cd	Cu	Fe	In	Mn	Ni	Sb	Se	Sn	Te	Tl	Zn
IMN PL 1	193	3.6	729	.	.	7.3	4.5	(64.3)	(0.20)	136	15.4	.	3.0	145	569	6.0
IMN PL 2	97.0	2.6	460	.	218	14.9	4.4	(6.4)	(0.17)	159	7.2	33.3	2.6	349	228	(1.7)
IMN PL 3	17.0	2.5	101	(3.4)	15.7	105	(2.4)	5.9	(0.60)	39.4	8.0	2.7	2.1	235	26.4	1.8
IMN PL 4	10.3	345	59.9	.	5.1	197	.	.	.	8.5	3.4	2.7	.	23.6	21.5	.
IMN PL 5	27.3	159	296	.	.	9.1	.	287	.	6.7	572	.	13.7	13.6	135	.
IMN PL 6	64.3	318	48.3	(81.1)	623	4.7	(2.0)	104	(0.50)	5.5	310	.	7.6	8.2	494	.
IMN PL 7	151	(74.3)	61.7	.	53.2	6.8	77.7	.	26.3	270	99.2	3.5

LEAD BINARY

available individually

typical analysis

cast typical analysis

40 mm Ø x 15 mm

Class	Number	Sn	As	Pb	Sb	Units	Class	Number	Sb	Ag	As	Bi	Mg
CRM	91X S63P	63.30	.	SOLD OUT	.	40 mm Ø x 15 mm	CRM	81X PA12.5D	12.72
RM	91X S50PE	50.0	.	Rem	.	40 mm Ø x 15 mm	CRM	81X PA10.0C	9.60
RM	91X S40PD	40.0	.	Rem	.	40 mm Ø x 15 mm	CRM	81X PA7.0D	7.02	.	SOLD OUT	.	.
RM	91X S30P	30.0	.	SOLD OUT	.	40 mm Ø x 15 mm	CRM	81X PA3.5E	3.49
RM	NF 23	30.0	.	SOLD OUT	.	37 mm Ø x 12 mm	CRM	81X PA2.0D	1.996	.	SOLD OUT	.	.
RM	NF 22	25.0	.	Rem	.	37 mm Ø x 12 mm	CRM	81X PA1.0C	0.989
RM	NF 20	15.2	.	Rem	.	37 mm Ø x 12 mm	CRM	81X PA0.5C	0.481
RM	NF 19	12.0	.	Rem	.	37 mm Ø x 12 mm	RM	81X PAs1A	(0.02)	.	1.25	(0.03)	.
CRM	91X S10PD	10.07	.	Rem	.	40 mm Ø x 15 mm	RM	81X PMg1A	1.15
RM	NF 18	9.80	.	Rem	.	37 mm Ø x 12 mm	RM	81X PMg2A	0.173
RM	NF 17	6.80	.	Rem	.	37 mm Ø x 12 mm	RM	81X PMg3A	0.023
RM	NF 16	3.00	.	Rem	.	37 mm Ø x 12 mm	RM	82X PAG0.9A	.	0.903	.	.	.
RM	NF 35	0.97	0.94	Rem	14.0	37 mm Ø x 12 mm	RM	82X PAG0.7A	.	0.733	.	.	.

LEAD AND TIN ALLOYS CONTINUED ON THE NEXT PAGE

= class, where 1 = CRM and 2 = rm

analysis listed in mass %

* Provisional Analysis

#	Number	Sn	Sb	Ag	As	Bi	Ca	Cd	Cu	Fe	Ni	Te	Zn
1	91X S63PR3G	64.01	0.243	0.0193	0.0264	0.254	.	0.0009	0.101	0.0078	0.0085	0.0068	0.0061
1	91X S63PJ	62.96	0.011	0.0170	(0.0006)	0.0056	.	(0.0001)	0.0156	0.0015	0.0003	(0.0002)	(0.0003)
1	91X S63PR2K	61.84	0.531	0.0528	0.0094	0.175	.	0.0089	0.0841	0.0053	0.0027	0.0036	0.0032
1	91X S63Bi1A	61.9	0.470	0.0592	(<0.002)	0.597	.	0.0095	0.105	0.0204	0.0131	0.0012	(0.0022)
1	91X S62AG2A	61.68	0.347	2.03	0.022	0.168	.	0.0016	0.069	0.0065	(0.0016)	.	0.0011
1	91X S63PR1G	61.45	0.052	0.0061	0.0064	0.0588	.	0.0045	0.214	(0.0016)	0.0060	0.0047	(0.0021)
1	91X S63PROB	60.03	0.0182	0.0097	0.0094	0.0084	.	0.0097	0.0202	(0.0024)	0.0018	0.0034	<0.0005
1	91X S50PR4B	53.06	0.132	0.0704	0.0364	0.114	.	0.0123	1.184	0.0028	0.0171	.	0.032
1	91X S40PR2D	40.68	0.596	0.086	0.010	0.154	.	0.0046	0.085	0.0096	0.0050	.	0.0275
1	SRM 1131	39.3	0.43	0.01	0.01	0.06	.	.	0.011	.	0.012	.	.
2	91X S40PR1B	39.0	0.05	0.005	0.005	0.05	.	0.001	0.20	0.015	0.001	.	0.002
1	93X S30APR3C	33.0	0.96	0.021	0.018	0.28	.	0.009	0.008	0.003	0.010	.	0.0053
1	91X S30PR3C	30.88	0.269	0.024	0.0126	0.294	.	0.0115	0.102	0.0016	0.0269	.	(0.003)
1	93X S30APR2C	30.68	1.80	0.049	0.0178	0.168	.	0.0061	0.062	0.0026	0.042	0.0102	0.028
1	91X S30PR2C	30.17	0.619	0.060	0.028	0.158	.	0.0060	0.095	0.009	0.0077	.	0.016
1	93X S30APR1C	28.58	2.54	0.0144	0.010	0.059	.	0.0014	0.192	(0.012)	0.0010	.	(0.0004)
1	86X PSS4C	10.22	16.18	0.0279	0.202	0.119	.	0.0575	0.113	0.0012	0.0005	0.0071	0.0156
1	85X SSB3C	9.70	2.14	0.456	0.075	0.413	.	0.455	.	.	.	0.0037	.
1	86X PSS3B	9.39	14.13	0.0140	0.409	0.0273	.	0.0170	0.489	0.0025	0.0009	0.0050	0.0030
1	91X S10PR1C	9.10	0.0278	0.0078	0.0045	0.0277	.	0.0029	0.0097	(0.0016)	0.0006	.	<0.001
1	86X PSS2B	7.00	8.04	0.0179	1.43	0.0646	.	0.066	0.127	(0.0012)	0.0165	.	0.031
1	SRM 1132	5.84	10.26	.	0.057	0.052	.	.	0.054	<0.001	0.003	.	.
1	86X PSS1B	4.29	11.54	0.0049	0.554	0.195	.	0.0057	0.0249	0.0018	0.0100	.	0.0030
1	84X BA9C	2.94	(0.005)	0.0023	(0.0005)	0.0145	0.118	0.0011	0.0021	.	(0.0001)	(0.0003)	0.0017
1	85X S5CHA	2.64	5.52	0.0134	0.208	0.0441	.	0.0040	0.177	(0.002)	0.010	0.0070	0.0007
1	85X P5Sn2C	2.06	0.0239	0.0048	0.0048	0.0154	.	0.00065	0.0128	(0.0002)	0.00025	0.0045	(0.0004)
1	BAM EB106	1.72	.	(0.00323)	.	(0.0135)	0.0782
1	84X BA13B	1.685	0.0018	0.0076	0.0004	0.0082	0.0725	0.00140	0.0010	.	.	.	0.0079
1	84X BA12C	1.460	0.0029	0.0051	(0.0001)	0.0146	0.0647	0.00122	0.00137	.	.	.	0.00323
1	BAM EB105	1.43	.	0.00321	.	0.0133	0.0595
1	84X BA11B	1.289	(0.005)	0.0025	0.0006	0.0159	0.0546	0.0006	0.0017	.	.	.	0.0006
1	BAM EB104	1.27	.	(0.00293)	.	(0.0126)	0.0530
1	85X ANTHF	1.25	6.25	0.0070	0.183	0.0194	.	0.0039	0.0070	(0.0004)	0.0045	0.0067	0.0005
1	BAM EB102a	1.01	(0.0004)	0.0170	(<0.0002)	0.00737	0.0635	.	0.00013	(<0.0002)	.	(<0.00011)	(<0.00005)
1	84X BA14A	0.959	(0.0017)	0.0103	(0.0004)	0.0162	0.076	0.0015	0.0016	.	(0.0002)	(0.0002)	0.0057
1	84X BA15A	0.941	0.0047	0.0095	0.00053	0.0140	0.0865	0.0013	0.0011	.	.	.	0.0062
1	84X BAK	0.888	0.0009	0.0098	0.0005	0.0146	0.120	0.0014	(0.0013)	.	(0.0001)	(0.0003)	0.0068
1	85X HRRH	0.851	1.106	0.236	0.721	0.0996	.	0.0066	0.073	.	0.0012	0.0023	.
1	83X PR8D	0.604	0.257	0.497	0.134	1.18	.	0.199	0.0448	.	0.0008	0.0014	0.0004
1	84X BA7B	0.594	0.0022	0.0015	(0.0004)	0.0140	0.0391	0.0004	0.0020	.	(0.0003)	(0.0002)	0.0024
1	84X BA2D	0.544	(0.0027)	0.0044	0.0004	0.0230	0.0756	0.0040	(0.0023)	.	(0.0004)	(0.0003)	0.0273
1	85X MS2XA	0.392	1.367	0.0043	0.176	0.0188	.	0.0002	0.0277	(0.0001)	0.0004	.	0.0003
1	84X BA20B	0.370	0.0038	0.0295	.	0.0144	0.368	0.0051	0.0435
1	84X BA8D	0.325	0.0043	0.0035	0.0005	0.0147	0.136	0.00043	0.0008	.	0.0002	(0.00024)	0.0018
1	84X BA3D	0.324	(0.006)	0.0062	(<0.0005)	0.0351	0.0212	0.0047	0.0061	.	(0.0001)	(<0.0005)	0.0032

#	Number	Sn	Sb	Ag	As	Bi	Ca	Cd	Cu	Fe	Ni	Te	Zn
1	SRM C2415a	0.3058	2.981	0.00762	0.1865	0.0507	.	0.00497	0.1022	.	0.00436	0.01034	.
1	BAM EB101a	0.294	(<0.00012)	0.00290	(<0.0002)	0.0165	0.136	(<0.0002)	0.00243	(<0.0002)	(<0.00006)	(<0.0003)	0.00010
1	85X PSb5E	0.285	4.51	0.00177	0.149	0.0134	.	0.00163	0.0493	.	0.00146	0.0029	0.00057
1	85X PSb12B	0.270	11.50	0.0019	0.071	0.0310	.	0.00053	0.330	.	0.0033	0.0056	0.071
2	L21.02	0.27	0.0003	0.008	.	0.01	0.03	<0.0002	0.0013	.	<0.0002	.	0.0016
1	82X PAG3.5RD	0.25	0.106	3.54	0.020	0.290	.	0.0027	0.073	<0.001	.	.	(0.0004)
1	85X S744A	0.237	1.532	0.0046	0.125	0.0182	.	0.00033	0.0366	(<0.001)	0.00053	.	0.00020
1	84X BA23B	0.237	0.0061	0.0024	.	0.0134	1.052	0.00012	0.0026
1	85X 0494 Pb3D	0.221	2.99	0.0186	0.245	0.126	.	.	0.0974	0.0005	.	0.0155	.
1	85X PSb5F	0.207	4.69	0.00382	0.221	0.0267	.	0.00107	0.0361	.	0.00176	0.0007	0.0009
1	BAM EB103	0.183	1.64	0.0066	0.097	0.0158	.	0.000020	0.00097	.	0.00302	.	.
1	84X BA21B	0.162	0.0028	0.0102	.	0.0173	0.552	0.0007	0.0155
1	83X PR9A	0.153	.	0.0049	.	.	0.556	0.00073	0.0045
1	85X PSb3K *	0.14	2.25	0.004	0.27	0.021	.	0.0025	0.030	.	0.002	0.0045	.
1	84X BA22B	0.128	0.0022	0.0044	.	0.0138	0.799	0.0018	0.0053
1	85X 0494 Pb2C	0.124	1.928	0.0279	0.102	0.0387	.	.	0.0227	(<0.001)	.	0.00382	.
1	85X CADHC	0.115	1.89	0.0093	0.0918	0.0138	.	2.01	0.013	0.0010	0.0007	0.0035	(0.0004)
1	83X PR2G	0.0948	0.0499	0.055	0.0233	0.0404	.	0.0020	0.0309	.	0.0006	0.0100	0.0005
1	85X PSb10B	0.090	10.0	0.0020	0.127	0.0410	.	0.0018	0.169	.	0.0027	0.0037	0.015
1	SRM C2416	0.09	0.79	0.0044	0.056	0.10	(<0.001)	(<0.0002)	0.065	(<0.0005)	(<0.0005)	(<0.0005)	(<0.0005)
1	82X PAG2.5RD	0.082	0.25	2.21	0.010	0.13	.	.	0.26	.	.	.	0.002
1	85X M2A	0.071	1.847	0.0016	0.259	0.0141	.	0.0003	0.0281	(0.0002)	0.0005	.	(0.0001)
1	85X 2.5LAA	0.068	2.48	0.0017	0.334	0.0142	.	(0.0002)	0.0372	.	0.0005	0.0004	0.0002
1	85X PSb6A	0.065	6.51	0.0459	0.111	0.0270	.	0.00460	0.0651	.	0.00213	0.0108	(0.0002)
1	85X 0494 Pb1A	0.051	0.95	.	0.049	0.0017	.	.	0.012
1	85X SB28A	0.051	2.87	0.00248	0.162	0.0140	.	(0.0001)	0.0035	(0.00015)	0.0012	.	(0.0001)
1	84X BA4C	0.0480	0.0078	0.0020	(0.0027)	0.0260	0.0014	0.0092	0.0064	.	(0.0004)	0.0205	0.0065
1	85X N35A	0.044	3.42	0.0011	0.201	0.0130	.	0.00013	0.0246	(0.0001)	0.00058	.	0.00013
1	85X PSb8B	0.041	8.04	0.0049	0.0352	0.0178	.	0.0010	0.0169	.	0.0016	0.0043	<0.001
1	82X PAG1.5RE	0.038	0.39	1.55	0.006	0.062	.	.	0.27	.	.	.	0.004
1	85X A16A	0.0356	1.57	0.0297	0.0503	0.0165	.	0.00014	0.0006	(0.0001)	0.0006	.	0.00011
1	85X SM31A	0.0274	2.98	0.0009	0.0581	0.0114	.	(0.0001)	0.0084	(0.0001)	0.0006	.	0.00015
1	85X CADLB	0.0182	2.00	0.0132	0.102	0.0489	.	1.22	0.0384	0.0008	0.0002	(<0.001)	(0.011)
1	85X SASHA	0.0130	1.54	0.0016	0.683	0.0602	.	0.00024	0.0245	.	0.0005	0.0006	.

LEAD ALLOYS CONTINUED FROM THE PREVIOUS PAGE

* Provisional Analysis

Number	Al	Au	Hg	In	Mg	Mn	Na	Pd	S	Se	Tl	Units
91X S63PR3G	.	0.169	(0.038)	0.0097	Disc 40 mm Ø x 15 mm
91X S63PJ	(0.0003)	(0.0005)	.	0.0064	Disc ~40 mm Ø x ~15 mm
91X S63PR2K	0.0005	0.082	.	0.0157	Disc ~40 mm Ø x ~15 mm
91X S63Bi1A	(0.0015)	0.074	.	0.0067	Disc 40 mm Ø x 15 mm
91X S62AG2A	(0.0011)	0.0020	Disc 40 mm Ø x 15 mm
91X S63PR1G	.	0.0348	(0.015)	0.0308	Disc 40 mm Ø x 15 mm
91X S63PR0B	.	0.0148	0.004	0.0048	Disc 40 mm Ø x 15 mm
91X S40PR2D	Disc 40 mm Ø x 15 mm
SRM 1131	Disc 32 mm Ø x 19 mm
91X S40PR1B	Disc 40 mm Ø x 15 mm last
93X S30APR3C	Disc 40 mm Ø x 15 mm
91X S30PR3C	.	0.0063	.	0.0085	Disc 40 mm Ø x ~12 mm
93X S30APR2C	.	.	.	0.0199	Disc 40 mm Ø x 15 mm
91X S30PR2C	<0.0005	0.0017	Disc 40 mm Ø x 15 mm
93X S30APR1C	.	.	.	0.0094	Disc 40 mm Ø x 15 mm
86X PSS4C	.	.	.	0.0194	Disc ~40 mm Ø x ~15 mm
86X PSS4B	.	.	.	0.0174	Disc ~40 mm Ø x ~15 mm
85X SBCA	.	0.0079	.	0.209	(0.0008)	(0.0029)	0.0196	Disc 40 mm Ø x 15 mm
86X PSS3B	.	.	.	0.0111	Disc ~40 mm Ø x ~15 mm
91X S10PR1C	Disc 40 mm Ø x 15 mm
86X PSS2B	.	.	.	0.0059	.	.	.	0.0049	.	.	.	Disc 40 mm Ø x 15 mm
SRM 1132	Disc 32 mm Ø x 19 mm
86X PSS1B	.	.	.	0.0074	.	.	.	0.0023	.	.	.	Disc 40 mm Ø x 15 mm
84X BA9C	0.0207	Disc ~40 mm Ø x ~15 mm
85X SSCHA	0.0035	(0.015)	last	Disc 40 mm Ø x ~11-13 mm
85X Psn2C	.	.	.	Co:0.0004	(0.0009)	0.0042	.	Disc ~40 mm Ø x ~15 mm
BAM EBI06	Disc 40 mm Ø x 40 mm
84X BA13B	0.0363	Disc ~40 mm Ø x ~15 mm
84X BA12C	0.0158	.	.	.	0.00074	Disc ~40 mm Ø x ~15 mm
BAM EBI05	Disc 40 mm Ø x 40 mm
84X BA11B	0.0207	Disc ~38 mm Ø x ~15 mm
BAM EBI04	Disc 40 mm Ø x 40 mm
85X ANTHF	.	.	.	Co:0.0006	0.0026	0.014	.	Disc ~40 mm Ø x ~15 mm
BAM EBI02a	0.0124	.	.	(<0.0002)	(<0.0001)	.	(0.0004)	.	(<0.0003)	.	0.00302	Disc 40 mm Ø x 40 mm
84X BA14A	0.0188	Disc ~40 mm Ø x ~15 mm
84X BA15A	0.0161	Disc ~38 mm Ø x ~15 mm
84X BA1K	0.0336	Disc ~39 mm Ø x ~15 mm
85X HRHH	(0.0022)	0.0375	.	Disc 40 mm Ø x 15 mm
83X PR8D	.	0.0106	0.086	0.293	(0.0003)	.	Disc ~40 mm Ø x ~15 mm
84X BA7B	0.0085	Disc ~40 mm Ø x ~15 mm
84X BA2D	0.0183	Disc ~40 mm Ø x ~15 mm
85X MS2XA	(0.0002)	0.0334	.	Disc ~38 mm Ø x ~15 mm
84X BA20B	0.065	Disc ~38 mm Ø x ~15 mm
84X BA8D	0.0359	Disc ~40 mm Ø x ~15 mm
84X BA3D	0.0043	.	.	.	0.00038	Disc ~40 mm Ø x ~15 mm
Number	Al	Au	Hg	In	Mg	Mn	Na	Pd	S	Se	Tl	Units
SRM C2415a	Pb:(96)	(0.0061)	0.01005	.	Disc 40 mm Ø x 18 mm
BAM EBI01a	0.0227	.	.	.	(0.0009)	.	(0.0004)	.	(<0.0003)	.	0.00102	Disc 40 mm Ø x 40 mm
85X Psb5E	0.018	0.014	.	Disc ~38 mm Ø x ~15 mm
85X Psb12B	<0.001	0.0004	.	Disc 40 mm Ø x 15 mm
L21.02	Block 50 mm x 50 mm x 20 mm
82X PAG3.5RD	0.0015	.	.	0.037	Disc 40 mm Ø x 15 mm
85X S744A	0.0028	0.0253	.	Disc ~40 mm Ø x ~15 mm
84X BA23B	0.0569	Disc ~40 mm Ø x ~15 mm
85X 0494 Pb3D	0.0185	0.049	.	Disc ~40 mm Ø x ~15 mm
85X Psb5F	0.0056	0.0077	.	Disc ~40 mm Ø x ~15 mm
BAM EBI03	0.0180	0.00152	Disc 40 mm Ø x 30 mm
84X BA21B	0.0125	Disc ~39 mm Ø x ~15 mm
83X PR9A	0.0138	0.200	.	Li:0.066	0.054	.	0.077	Disc ~40 mm Ø x ~15 mm last
85X Psb3K *	0.010	0.038	.	Disc ~40 mm Ø x ~15 mm
84X BA22B	0.074	Disc ~38 mm Ø x ~15 mm
85X 0494 Pb2C	0.0052	0.0272	.	Disc ~40 mm Ø x ~15 mm
85X CADHC	Disc ~40 mm Ø x ~15 mm
83X PR2G	.	0.0005	0.003	0.0010	.	.	0.0013	.	(0.0006)	0.0005	(0.0017)	Disc ~40 mm Ø x ~15 mm
85X Psb10B	<0.001	0.0020	.	Disc 40 mm Ø x 15 mm
SRM C2416	(<0.0001)	(<0.0005)	.	.	0.0015	.	.	Disc 50 mm Ø x 16 mm
82X PAG2.5RD	Disc 40 mm Ø x 15 mm
85X M2A	(0.0008)	0.0247	.	Disc ~38 mm Ø x ~15 mm
85X 2.5LAA	0.0006	.	Disc ~40 mm Ø x ~15 mm
85X Psb6A	0.0018	.	Disc ~40 mm Ø x ~15 mm
85X 0494 Pb1A	0.004	.	Disc 40 mm Ø x 15 mm
85X SB28A	0.0010	0.0223	.	Disc ~38 mm Ø x ~15 mm
84X BA4C	0.0015	Disc 40 mm Ø x ~15 mm last
85X N35A	0.007	0.0004	.	Disc ~38 mm Ø x ~15 mm
85X Psb8B	0.005	0.0022	.	Disc 40 mm Ø x 15 mm
82X PAG1.5RE	Disc 40 mm Ø x 15 mm
85X A16A	(0.0003)	0.0218	.	Disc ~38 mm Ø x ~15 mm
85X SM31A	0.0003	0.0183	.	Disc ~38 mm Ø x ~15 mm
85X CADLB	Disc ~40 mm Ø x ~15 mm
85X SASHA	(0.0005)	.	.	Disc 40 mm Ø x ~15 mm
85X CADLA	(0.0011)	.	Disc 40 mm Ø x ~15 mm
85X YUMA	0.0062	0.0008	.	Disc ~40 mm Ø x ~15 mm
85X 0616 Pb1C	.	.	0.0010	0.0087	.	Disc ~40 mm Ø x ~15 mm
Number	Al	Au	Hg	In	Mg	Mn	Na	Pd	S	Se	Tl	Units

MAGNESIUM

= class, where 1 = CRM and 2 = RM

61X: not for Glow Discharge

#	Number	Al	Cu	Fe	Mn	Ni	Pb	Si	Zn	Ag	Be
1	58A ST4360	(1.06)	0.025	0.02	0.148	0.0052	0.018	0.02	0.025	.	.
1	58A ST4320	(0.531)	0.0077	0.027	0.085	0.011	0.037	0.062	0.047	.	.
1	NCS HS49725-2	(0.531)	0.0077	0.027	0.085	0.011	0.037	0.062	0.047	.	.
1	58A ST4340	0.262	0.014	0.0069	0.023	0.0044	0.012	0.034	0.019	.	.
1	NCS HS49725-4	0.262	0.014	0.0069	0.023	0.0044	0.012	0.034	0.019	.	.
1	61X MgP3A	0.096	0.0296	0.014	0.0135	0.0049	0.0148	0.046	0.0196	0.0125	<0.0001
1	63X MgE1E	(0.088)	0.0503	0.0014	0.860	0.0162	0.011	0.052	0.083	0.0195	(0.0002)
1	61X MgP2A	0.065	0.0109	0.0061	0.0118	0.0029	0.0061	0.031	0.0122	0.003	<0.0001
2	58A ZH1120	0.063	0.037	0.012	0.062	0.012	0.0073	0.037	0.038	.	.
2	58A ZH1130	0.055	0.017	0.015	0.039	0.007	0.0035	0.055	0.02	.	.
1	61X MgP4A	0.0247	0.0108	(0.0044)	0.0100	0.0028	0.0066	0.037	0.0158	0.0203	<0.0001
1	NCS HS49725-3	0.017	0.0087	0.0083	0.019	0.0021	0.0067	0.023	0.012	.	.
2	58A ZH1140	0.017	0.0054	0.0044	0.011	0.0007	0.0013	0.0027	0.0058	.	.
2	58A ZH1160	0.011	0.0016	0.0071	0.016	0.0004	0.0025	0.019	0.004	.	.
1	NCS HS49725-1	0.011	0.0012	0.0028	0.017	0.00035	0.0052	0.011	0.011	.	.
1	58A ST4370	0.0082	0.0039	0.0055	0.017	0.0013	0.0067	0.03	0.013	.	.
1	NCS HS49725-7	0.0082	0.0039	0.0055	0.017	0.0013	0.0067	0.030	0.013	.	.
2	58A ZH1150	0.0062	0.0003	0.0015	0.0054	(0.0001)	(0.0005)	0.0024	0.0046	.	.
1	NCS HS49725-5	0.0059	0.00063	0.0022	0.0060	(0.00033)	0.0020	0.0063	0.0079	.	.
2	58A ZH1110	0.0052	0.062	0.0054	0.092	0.0041	0.012	0.015	0.058	.	.
1	58A ST4310b	0.005	0.00097	0.0087	0.022	0.00026	(0.0011)	0.012	0.0012	.	.

Number	Ca	Cd	Ce	Cl	La	Na	Sn	Ti	Zr	~mm Ø x ~mm H
58A ST4360	0.0025	.	45 x 25
58A ST4320	(0.00018)	.	45 x 25
NCS HS49725-2	(0.00018)	.	45 x 25
58A ST4340	0.0012	.	45 x 25
NCS HS49725-4	0.0012	.	45 x 25
61X MgP3A	0.053	0.0154	0.0055	.	0.0038	.	0.0154	.	(0.0014)	40 x 20
63X MgE1E	.	0.0017	0.0053	.	.	50x20 or 40x15
61X MgP2A	0.0138	0.0063	0.0019	.	0.0014	.	0.0073	.	(0.0007)	40 x 20
58A ZH1120	.	.	.	(0.0023)	.	(0.0002)	.	.	.	~49 x ~34
58A ZH1130	.	.	.	(0.0027)	.	(0.0003)	.	.	.	~49 x ~34
61X MgP4A	0.028	0.0071	0.0041	.	0.0030	.	0.0067	.	0.030	40 x 20
NCS HS49725-3	0.000062	.	45 x 25
58A ZH1140	.	.	.	(0.0015)	.	(0.0003)	.	.	.	~49 x ~34
58A ZH1160	.	.	.	(0.0018)	.	(0.0001)	.	.	.	~49 x ~34
NCS HS49725-1	0.00027	.	45 x 25
58A ST4370	(0.00010)	.	45 x 25
NCS HS49725-7	(0.00010)	.	45 x 25
58A ZH1150	.	.	.	(0.0011)	.	(0.0001)	.	.	.	~49 x ~34
NCS HS49725-5	0.000072	.	45 x 25
58A ZH1110	.	.	.	(0.0018)	.	(0.0004)	.	.	.	~49 x ~34
58A ST4310b	0.00026	.	45 x 25

MAGNESIUM with RARE EARTHS

= class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Ag	Al	Be*	Ca	Cd*	Ce	Cu	Fe	Gd	La	Mn	Nd	Ni
1	67X MgK3A	.	4.56	7	.	.	0.83	0.0017	0.0024	0.038	0.374	0.516	0.175	0.0016
1	67X MgK2A	.	3.84	25	.	.	0.70	0.0041	0.0016	0.053	0.34	0.534	0.125	0.0033
1	64X MgQ9A	.	2.14	15	.	.	0.111	0.0104	0.0069	.	0.083	0.068	0.114	0.0020
1	66X MgD1B	.	0.147	.	.	.	0.065	0.066	0.0029	.	0.031	0.125	0.064	0.0162
1	61X MgP5A	0.0342	0.119	18	.	292	0.049	0.092	0.0048	.	0.0382	0.201	0.0446	0.0176
1	61X MgP6A	0.0043	0.0449	.	(0.0008)	25	0.0209	0.0067	0.0041	.	0.0137	0.0125	0.0238	0.0025
2	AA C7548	.	0.004	.	.	.	2.66	0.022	.	.	.	0.035	.	0.001
2	AA C7514	.	0.002	.	.	.	2.47	0.12	.	.	.	0.012	.	0.002
2	AA C7489	.	0.001	.	.	.	2.57	0.004	.	.	.	0.012	.	0.015
2	AA E1273	.	0	.	.	.	1.86	0.022	.	.	.	0.041	.	0.002
2	AA E1272	.	0	.	.	.	1.79	0.026	.	.	.	0.045	.	0.003
1	58A ST5280	4.16
1	58A ST5290	3.37
1	58A ST5260	2.79
1	58A ST5250	1.54	0.133	.	.	.	0.214	.	0.005
1	58A ST5240	1.47	0.051	.	.	.	0.062	.	0.084
1	58A ST5230	1.28	0.068	0.0041	.	.	0.067	.	0.0011
1	58A ST5220	0.826	0.054	0.0033	.	.	0.093	.	0.0009
1	58A ST5210	0.149	0.0092	0.0027	.	.	0.15	.	0.001
1	58A ST10350	3.55	.
2	AA D1075
2	AA D1073
2	AA D1072
2	AA D1074
1	58A ST9460	Ni
1	58A ST9450
1	58A ST9440

#	Number	Ag	Al	Be*	Ca	Cd*	Ce	Cu	Fe	Gd	La	Mn	Nd	Ni
---	--------	----	----	-----	----	-----	----	----	----	----	----	----	----	----

Number	Pb	Pr	R.E.	Si	Sn	Y	Zn	Zr	~mm Ø x ~mm H
--------	----	----	------	----	----	---	----	----	---------------

67X MgK3A	.	0.069	.	0.068	.	.	0.050	.	50x20 or 40x15
67X MgK2A	.	0.053	.	0.057	.	.	0.132	.	50x20 or 40x15
64X MgQ9A	0.0096	.	.	(0.37)	0.0076	.	0.243	.	40 x 15
66X MgD1B	0.026	.	.	(0.073)	0.026	.	1.19	.	40 x 15
61X MgP5A	0.0357	.	.	0.094	0.0352	0.0132	0.099	.	40 x 15

61X MgP6A	0.0120	.	.	0.044	0.0091	0.0375	0.010	.	50x20 or 40x15
AA C7548	.	.	(4.8)	0.002	.	.	0.16	.	62 x 6
AA C7514	.	.	(4.7)	0.002	.	.	0.42	.	62 x 6
AA C7489	.	.	(5.0)	0.002	.	.	0.46	.	62 x 6
AA E1273	.	.	(3.6)	0.0	.	.	2.87	0.54	62 x 6

AA E1272	.	.	(3.3)	0.0	.	.	2.58	0.54	62 x 6
58A ST5280	3.52	0.63	45 x 25
58A ST5290	4.37	0.81	45 x 25
58A ST5260	4.36	(1.03)	45 x 25
58A ST5250	1.46	.	45 x 25

58A ST5240	2.69	.	45 x 25
58A ST5230	.	.	.	(0.0047)	.	.	3.63	.	45 x 25
58A ST5220	.	.	.	(0.0056)	.	.	4.58	.	45 x 25
58A ST5210	5.59	.	45 x 25
58A ST10350	45 x 25

AA D1075	.	.	(3.7)	.	.	.	(2.7)	0.64	62 x 6
AA D1073	.	.	(3.7)	.	.	.	3.23	(0.6)	62 x 6
AA D1072	.	.	(3.4)	.	.	.	2.02	(0.5)	62 x 6
AA D1074	.	.	(3.4)	.	.	.	(2.7)	0.42	62 x 6
58A ST9460	6.69	.	.	45 x 25

58A ST9450	4.3	.	.	45 x 25
58A ST9440	3.52	.	.	45 x 25

Number	Pb	Pr	R.E.	Si	Sn	Y	Zn	Zr	~mm Ø x ~mm H
--------	----	----	------	----	----	---	----	----	---------------

MAGNESIUM with ALUMINUM

#	Number	Al	Be	Ca	Cd	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn
1	58A ST2150	11.52	(0.0023)	.	.	0.295	(0.020)	(0.68)	0.018	.	0.176	.	0.217
1	65X MgA15A	10.67	0.0062	(0.0014)	0.0034	0.0273	0.010	0.067	0.0026	0.0051	0.034	0.0021	0.348
2	58A ZH2050M	10.4	0.0007	.	.	0.307	0.0081	(0.71)	0.019	.	0.41	.	0.201
2	AA D3738	10.38	.	.	.	0.031	.	0.21	0.004	.	0.085	.	0.32
1	64X MgQ3A	8.66	0.0041	.	.	0.0349	0.0090	0.206	0.0032	0.0022	(0.083)	0.0019	0.0039
1	58A ST25051	8.31	0.0007	.	.	0.008	0.0029	0.146	0.0009	.	0.011	.	0.656
1	65X MgA5A	8.00	0.0013	(0.014)	0.0035	0.0195	0.006	0.401	0.0201	0.042	0.110	0.0124	0.411
1	58A ST1240	7.33	0.00015	.	.	0.02	0.015	0.182	(0.0015)	.	0.27	.	0.171
1	64X MgQ4A	6.50	0.00029	.	.	0.310	0.0040	0.183	0.0068	0.0322	(0.067)	0.0282	0.188
1	58A ST2000a	5.96	(0.00024)	.	.	0.0035	0.007	0.02	0.00094	.	0.097	.	0.0068
1	58A ST3320	5.82	0.00018	.	.	0.0016	0.0077	0.095	0.0012	.	1.54	.	0.128
1	NCS HS49724-2	5.82	0.00018	.	.	0.0016	0.0077	0.095	0.0012	.	1.54	.	0.128
1	64X MgQ5A	5.76	0.0013	.	.	0.0072	0.0043	0.276	0.0010	0.0056	0.052	0.0050	0.047
1	58A ST1260	4.56	0.0009	.	.	0.013	0.025	(0.65)	0.0025	.	0.241	.	0.106
1	64X MgQ2A	4.53	0.0013	.	.	0.0151	0.0041	0.378	0.0061	0.0107	0.051	0.0107	0.107
1	58A ST3340	4.37	0.0009	.	.	0.103	0.022	0.33	0.0038	.	1.22	.	0.25
1	NCS HS49724-4	4.37	0.0009	.	.	0.103	0.022	0.33	0.0038	.	1.22	.	0.25
1	65X MgA17A	4.20	.	0.021	0.0049	0.0215	0.0069	0.203	0.0141	0.009	0.33	0.0050	0.128
1	64X MgQ7A	4.02	0.00042	.	.	0.0167	0.0028	(0.434)	0.0053	0.0126	(1.05)	0.0096	0.0607
1	65X MgB4C	3.86	0.0033	0.0010	0.00016	0.0183	(0.009)	0.031	0.0003	0.0037	0.037	0.0050	0.333
1	58A ST3310	3.69	0.00011	.	.	0.0084	0.007	0.59	0.0012	.	0.54	.	0.102
1	NCS HS49724-1	3.69	0.00011	.	.	0.0084	0.0070	0.59	0.0012	.	0.54	.	0.102
1	58A ST3350	2.58	0.0012	.	.	0.039	0.033	0.23	0.014	.	1.83	.	0.152
1	NCS HS49724-5	2.58	0.0012	.	.	0.039	0.033	0.23	0.014	.	1.83	.	0.152
1	58A ST1220	2.55	0.0009	.	.	0.0081	0.0089	0.338	0.0008	.	0.173	.	0.237
2	AA C8209	2.55	.	.	.	0.012	(0.02)	0.15	0.001	.	0.058	.	0.18
1	64X MgQ6A	2.31	0.0007	.	.	0.0045	(0.004)	(0.260)	0.0026	0.0060	(0.97)	0.0055	0.072
1	58A ST3330	1.09	(0.0005)	.	.	0.016	(0.0034)	(0.50)	(0.0013)	.	0.68	.	0.339
1	NCS HS49724-3	1.09	(0.0005)	.	.	0.16	(0.0034)	(0.50)	(0.0013)	.	0.68	.	0.339
1	64X MgQ1A	1.083	0.00036	.	.	0.084	0.0034	0.377	0.0041	0.020	0.062	0.0195	0.235
1	NCS HS49725-6	(1.06)	.	.	.	0.025	0.020	0.148	0.0052	0.018	0.020	.	0.025
1	64X MgQ8A	1.03	0.00015	.	.	0.0019	0.0018	0.700	0.0004	0.0008	0.045	0.0022	0.044

#	Number	Al	Be	Ca	Cd	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn
	Number	Ag	Ce	Hg	La	Sr	Ti	Zr	~mm Ø	x	~mm H		
	65X MgA15A	0.030	0.0069	0.011	0.0048	.	.	.	50x20	or	40x15		
	58A ZH2050M	~49	x	~34		
	AA D3738	62	x	6		
	64X MgQ3A	50x20	or	40x15		
	58A ST25051	45	x	30		
	65X MgA5A	0.0050	.	.	.	0.0004	(0.001)	.	50	x	20		
	58A ST1240	45	x	25		
	64X MgQ4A	50x20	or	40x15		
	58A ST1210	45	x	25		
	58A ST2000a	45	x	25		
	58A ST3320	45	x	25		
	NCS HS49724-2	45	x	25		
	64X MgQ5A	40	x	15		
	58A ST1260	45	x	25		
	64X MgQ2A	50x20	or	40x15		
	58A ST3340	45	x	25		
	NCS HS49724-4	45	x	25		
	65X MgA17A	0.0064	50x20	or	40x15		
	64X MgQ7A	50x20	or	40x15		
	65X MgB4C	0.0046	0.0003	.	(0.0001)	.	(0.0008)	<0.001	40	x	18		
	58A ST3310	45	x	25		
	NCS HS49724-1	45	x	25		
	58A ST3350	45	x	25		
	NCS HS49724-5	45	x	25		
	58A ST1220	45	x	25		
	AA C8209	62	x	6		
	64X MgQ6A	50x20	or	40x15		
	58A ST3330	45	x	25		
	NCS HS49724-3	45	x	25		
	64X MgQ1A	50x20	or	40x15		
	NCS HS49725-6	0.0025	.	45	x	25		
	64X MgQ8A	50x20	or	40x15		
	Number	Ag	Ce	Hg	La	Sr	Ti	Zr	~mm Ø	x	~mm H		

MAGNESIUM with ALUMINUM and ZINC

= class, where 1 = CRM and 2 = RM ##: not for Glow Discharge

#	Number	Al	Zn	Be	Ca	Cd	Cu	Fe	Mn	Ni	Pb	Si	Sn
1	65X MgA21A	12.37	5.11	0.0006	.	.	0.0020	0.0140	0.0777	0.0010	0.0048	0.028	0.0063
1	65X MgA23A	9.72	0.543	0.0026	.	.	0.0153	0.0083	0.130	0.0011	0.0020	0.0270	0.0026
1	58A ST2160	9.07	0.98	0.0029	.	.	0.0098	0.039	0.61	0.0036	.	0.43	.
2	58A ZH2040M	9.0	0.46	0.0013	.	.	0.222	0.01	0.57	0.015	.	0.285	.
1	65X MgA19A	8.97	2.17	0.00025	.	.	0.0426	0.0085	0.322	0.0065	0.049	0.196	0.049
1	65X MgA22A	8.60	0.882	0.0005	.	.	0.0783	0.0054	0.40	0.0057	0.0039	(0.086)	0.0032
2	AA SM183-B	(8.0)	(3.0)	(0.2)	0.005	.	.	.
2	AA SM183-C	(8.0)	(3.0)	(0.2)	0.005	.	.	.
2	AA SM183-D	(8.0)	(3.0)	(0.2)	0.005	.	.	.
1	65X MgA13A	7.45	0.925	(0.010)	0.0064	0.0055	0.125	(0.008)	0.092	0.0039	0.0085	0.022	0.043
2	58A ZH2030M	6.97	0.71	0.0017	.	.	0.151	0.018	0.374	0.0096	.	0.183	.
1	65X MgA16A	6.78	4.03	0.0011	0.0024	0.0066	0.099	0.0073	0.271	0.0057	0.050	0.023	0.028
1	65X MgA18A	6.75	0.502	0.00051	.	.	0.052	0.0081	0.192	0.0074	0.0244	0.043	0.0114
2	AA SM145	(6.7)	(2.4)	0.003
1	58A ST2120a	6.40	2.50	0.0004	.	.	0.080	0.008	0.35	0.0060	.	0.12	.
1	65X MgA20A	5.87	1.32	0.0018	.	.	0.013	0.008	0.067	0.0025	0.0075	0.052	0.032
1	65X MgA12A	5.68	3.18	(0.0036)	0.037	0.0121	0.266	0.0053	0.198	0.0148	0.010	0.0142	0.0021
1	65X MgA1J ##	5.45	1.26	0.006	0.029	0.013	0.221	0.021	0.060	0.021	0.012	0.20	0.072
2	58A ZH2020M	5.06	0.95	0.0022	.	.	0.085	0.028	0.256	0.0047	.	0.10	.
1	58A ST2110a	4.45	4.1	(0.00015)	.	.	0.00072	0.0029	0.077	0.00042	.	0.019	.
1	65X MgA11A	3.63	1.59	0.0021	0.102	0.0014	0.0496	0.0048	0.044	0.0134	0.0190	0.022	0.093
1	65X MgB3C	3.38	0.711	0.0019	(0.0033)	0.0025	0.022	0.0028	0.277	0.0027	0.0023	0.042	0.0017
2	AA C7574	3.36	(1.0)	(0.4)
2	58A ZH2010M	3.04	1.21	0.0032	.	.	0.0096	0.035	0.082	0.0006	.	0.037	.
2	AA C7640	(3.0)	0.76	(0.4)
2	AA C7641	(3.0)	1.36
2	AA C7643	(3.0)	(1.0)	.	.	.	0.026	.	0.32	0.005	.	0.14	.
1	65X MgB2D	2.81	1.047	0.0014	(0.010)	0.0103	0.065	0.0032	0.526	0.0043	0.0053	(0.088)	0.0052
1	65X MgB2C	2.67	0.95	0.0008	0.011	0.0114	0.113	(0.010)	0.333	0.0027	0.0036	0.069	0.0047
2	AA C7639	2.39	(1.0)	(0.4)
1	65X MgB1E	1.90	1.60	0.0008	(0.067)	0.076	0.051	0.0027	0.770	0.0020	0.0095	0.069	0.0098
1	58A ST1270	1.36	0.492	0.0033	.	.	0.01	0.0049	0.13	0.01	.	0.065	.

#	Number	Al	Zn	Be	Ca	Cd	Cu	Fe	Mn	Ni	Pb	Si	Sn
---	--------	----	----	----	----	----	----	----	----	----	----	----	----

Number	Ag	Ce	Hg	La	Ti	Zr	~mm Ø x ~mm H
65X MgA21A	50x20 or 40x15
65X MgA23A	50x20 or 40x15
58A ST2160	45 x 25
58A ZH2040M	~49 x ~34
65X MgA19A	50x20 or 40x15
65X MgA22A	40 x 15
AA SM183-B	62 x 6
AA SM183-C	62 x 6
AA SM183-D	62 x 6
65X MgA13A	0.0074	0.0024	(0.033)	0.0021	.	.	50x20 or 40x15
58A ZH2030M	~49 x ~34
65X MgA16A	0.0035	0.0017	0.005	0.0012	.	.	50x20 or 40x15
65X MgA18A	50x20 or 40x15
AA SM145	62 x 6
58A ST2120a	45 x 40
65X MgA20A	50x20 or 40x15
65X MgA12A	0.0128	0.0009	(0.016)	0.0007	.	.	50x20 or 40x15
65X MgA1J ##	0.012	0.009	.	0.007	(0.005)	(0.0015)	45 x 20
58A ZH2020M	~49 x ~34
58A ST2110a	45 x 25
65X MgA11A	(0.0002)	(0.0005)	0.006	(0.0005)	.	.	50x20 or 40x15
65X MgB3C	0.0028	50x20 or 40x15
AA C7574	62 x 6
58A ZH2010M	~49 x ~34
AA C7640	62 x 6
AA C7641	62 x 6
AA C7643	62 x 6
65X MgB2D	0.0099	50x20 or 40x15
65X MgB2C	0.0098	0.0009	.	0.0007	0.0003	<0.001	40 x 15
AA C7639	62 x 6
65X MgB1E	0.0300	50x20 or 40x15
58A ST1270	45 x 25

Number	Ag	Ce	Hg	La	Ti	Zr	~mm Ø x ~mm H
--------	----	----	----	----	----	----	---------------

MAGNESIUM with MANGANESE

= class, where 1 = CRM and 2 = RM

#	Number	Mn	Al	Cu	Fe	Ni	Pb	Si	Sn	Zn	Ag	Ca	Cd	~mm Ø x ~mm H
2	AA C8096	1.88	(0.1)	(0.04)	.	(0.003)	.	(0.05)	.	(0.1)	.	.	.	62 x 6
1	63X MgE2B	1.76	0.045	0.0203	0.0019	0.0035	0.0020	0.019	0.0026	0.0243	0.0089	(0.0016)	0.0009	40 x 15
2	AA SMD3A	1.69	0.08	0.032	.	0.002	.	0.034	.	0.058	.	.	.	62 x 6
1	63X MgE3C	1.62	(0.056)	0.0072	0.0005	0.0028	0.0046	0.014	0.006	0.0101	0.0041	.	0.0046	50x20 or 40x15
2	AA C8095	(1.6)	0.17	0.012	.	0.005	.	0.052	.	0.029	.	.	.	62 x 6
2	AA C8016	(1.3)	0.03	0.070	.	0.011	.	0.064	.	0.11	.	.	.	62 x 6
2	AA C7857	1.07	(0.1)	(0.03)	.	(0.001)	.	(0.05)	.	(0.1)	.	.	.	62 x 6

MAGNESIUM with ZINC

= class, where 1 = CRM and 2 = RM

#	Number	Zn	Ag	Al	Be	Ca	Cu	Fe	Mn	Ni	Pb	Si	Sn	Sr	Zr	~mm Ø x ~mm H
1	58A ST5310	7.20	.	0.0040	.	.	1.64	0.0110	0.967	0.0020	.	0.025	.	.	.	45 x 35
1	66X MgC4C	6.81	0.0074	0.039	(0.0001)	(<0.001)	0.0024	0.006	0.166	0.0009	0.0030	0.06	0.021	(0.00014)	<0.001	50x20 or 40x15
1	58A ST7320	6.68	.	(0.036)	.	.	3.45	0.0069	0.361	0.00024	.	0.066	.	.	.	45 x 25
1	66X MgC5A	6.61	.	0.072	.	.	0.0286	0.0008	1.17	0.0111	0.0281	0.026	0.0051	.	.	50x20 or 40x15
1	66X MgD5A	6.25	0.044	0.040	<0.0005	(0.030)	2.88	0.008	0.307	0.0120	0.097	0.134	0.104	.	.	50x20 or 40x15
1	58A ST7330	6.01	.	0.205	.	.	2.76	0.019	0.57	0.055	.	0.144	.	.	.	45 x 25
1	58A ST7340	5.52	.	0.148	.	.	3.71	(0.019)	0.25	0.018	.	0.332	.	.	.	45 x 25
1	58A ST7350	4.76	.	0.106	.	.	4.17	0.016	0.133	0.0022	.	0.215	.	.	.	45 x 25
2	AA C7510	3.04	.	.	0.11	.	0.019	.	.	0.001	62 x 6
2	AA SML76	(3.0)	.	0.19	.	.	(0.03)	.	(0.2)	.	.	(0.1)	.	.	.	62 x 6
2	AA SML75	(2.0)	.	0.21	.	.	(0.03)	.	(0.2)	.	.	(0.1)	.	.	.	62 x 6

RM JEWELRY INDIVIDUAL XRF SAMPLES

analysis listed in mass % FLX 0740: 2mm Ø mounted in 36mm Ø x 10mm others: 3mm Ø mounted in 36mm Ø x 10mm

Number	Ag	Au	Cu	Fe	Ir	Ni	Pd	Pt	Rh	Ru	W	Zn
FLX 0720	.	99.99	0.002	.	0.002	.	0.002	0.002	0.002	.	.	.
FLX 1404	.	99.69	Co: 0.310
FLX 0701	4.59	91.76	3.65
FLX 0702	4.60	90.12	5.28
FLX 1405	.	81.89	.	.	.	18.11
FLX 0743	.	80.07	1.12	.	.	14.35	4.46
FLX 1402	5.16	76.37	10.29	8.18
FLX 0703	4.18	75.14	4.93	.	.	.	15.75
FLX 0708	.	75.12	17.47	.	.	5.81	1.60
FLX 0726	10.16	75.11	14.73
FLX 0728	4.79	75.1	20.11
FLX 0727	8.98	75.07	15.95
FLX 0724	15.07	75.05	9.88
FLX 0725	12.54	75.03	12.43
FLX 0705	10.09	75.03	4.83	.	.	.	10.05
FLX 0704	2.75	75.03	9.74	.	.	.	12.48
FLX 0707	2.75	75.02	15.13	.	.	5.04	2.06
FLX 0706	13.13	75.0	5.42	.	.	.	6.45
FLX 1302	15.16	59.13	17.31	8.40
FLX 0710	30.94	59.06	3.48	.	.	.	6.52
FLX 0709	21.93	59.02	4.05	.	.	.	15.0
FLX 0903	4.32	58.69	36.99
FLX 0738	19.7	58.65	19.22	2.43
FLX 0904	13.77	58.65	27.58
FLX 0905	25.06	58.64	14.92	1.38
FLX 0715	.	58.64	26.18	.	.	6.09	9.09
FLX 0736	33.01	58.61	7.89	0.49
FLX 0712	27.36	58.59	4.05	.	.	.	10.0
FLX 0735	6.65	58.58	31.08	3.69
FLX 0739	33.39	58.53	8.08
FLX 0729	29.42	58.52	12.06
FLX 0711	10.72	58.49	26.47	4.32
FLX 0713	4.84	58.47	24.91	.	.	8.39	3.39
FLX 0714	.	58.44	41.31	0.25
FLX 0744	26.84	55.37	10.09	.	.	.	6.49	1.21
FLX 0737	6.15	38.35	46.89	8.61
FLX 1301	45.83	37.63	12.67	3.87
FLX 0716	15.09	37.63	37.97	9.31
FLX 0731	54.31	37.52	8.17
FLX 0732	58.75	33.71	7.54
FLX 0734	6.3	33.65	50.28	9.77
FLX 1401	33.00	33.61	33.36	0.030
FLX 0718	6.21	33.56	49.69	10.54
FLX 0717	11.92	33.52	41.04	13.52
FLX 1403	5.90	29.36	53.80	0.010	.	0.200	0.030	0.010	.	.	.	10.68 Cd: 0.010
FLX 0721	99.97	.	0.008	.	0.005	.	0.005	0.007	0.005	.	.	.
FLX 0719	99.94	.	0.06
FLX 0730	93.56	.	6.44
FLX 1303	92.76	.	4.92	2.32
FLX 0733	83.75	.	16.25
FLX 1406	34.98	.	6.50	.	.	.	58.52
FLX 0742	0.005	.	99.99	0.005
FLX 0740	.	.	0.005	.	0.09	.	.	.	99.90	0.005	.	.
FLX 0723	.	.	0.01	0.01	.	.	99.96	0.01	0.01	.	.	.
FLX 0722	0.02	.	0.02	99.95	0.01	.	.	.
FLX 0741	.	.	4.16	95.84
FLX 0902	95.37	.	.	4.63	.
FLX 0901	95.23	.	4.77	.	.
FLX 1202	10.0	.	.	90.0
FLX 1201	25.0	.	.	75.0
Number	Ag	Au	Cu	Fe	Ir	Ni	Pd	Pt	Rh	Ru	W	Zn

RM LARGER JEWELRY SAMPLES

16 mm Ø mounted in 36mm Ø x 10mm

Number	Ag	Au	Cu	Ni	Pd	Zn
FLX 0720-16	.	99.99	0.002	.	.	.
FLX 0720-16a	.	99.99
FLX 0704-16c	3.05	75.08	9.37	.	12.5	.
FLX 0715-16a	9.05	59.10	25.74	6.11	.	.
FLX 0738-16	19.8	58.58	21.1	.	.	0.52
FLX 0744-16	26.8	55.68	9.43	.	6.57	1.52
FLX 0732-16	57.1	33.46	9.44	.	.	.
FLX 0734-16a	7.09	33.41	48.82	.	.	10.68

Ir, Pd, Pt, Rh: 0.002
last of stock

CRM GOLD ALLOYS

analysis listed in mass % ~16 mm disc mounted in acrylic 40 mm Ø x 5 mm

Number	Alloy	Ag	Au	Cu	Ni	Zn
ERM-EB508	Yellow Gold	24.90	75.12	.	.	.
ERM-EB507	White Gold	3.02	75.10	14.69	4.99	2.107
ERM-EB506	Rose Gold	3.90	58.56	35.65	.	1.891

SILVER

analysis listed in mg/kg 131X PAG: RM, 34 Ø x 12mm 131X PAG: RM, 25 Ø x 3mm IMN SH: CRM 40 Ø x ~15-20mm IMN SJ: 40 mm Ø x ~15-20 mm

Number	Cu	Al	As	Au	Bi	Cd	Fe	Ga	In	Ir	Mn	Ni	P	Pb	Pd	Pt	Rh	Sb	Se	Si	Sn	Te	Tl	Zn
131X ACP1B	815	.	145	521	523	377	57	.	.	.	404	276	.	420	332	505	.	485	299	.	505	435	.	502
131X PAG2A	400	2	8	20	12	5	7	15	.	0.02	10	9	2	12	180	10	2	12	10	4	14	15	.	40
IMN SJ2	306.0	.	41.3	35.4	47.4	21.2	26.4	.	49.2	.	46.1	49.7	.	82.5	41.5	44.4	.	81.2	45.7	.	.	43.0	40.5	135.1
131X AGP2B	193	.	29	114	96	56	(20)	.	.	.	49	57	.	75	105	112	.	107	65	.	95	90	.	109
131X PAG1A	75	8	12	120	40	35	5	60	.	0.02	35	25	4	40	180	35	<1	50	35	30	40	120	.	50
131X AGP3B	66	.	6	26	12	6	(11)	.	.	.	3	12	.	12	16	23	.	21	16	.	22	18	.	34
IMN SH3	59.0	.	11.0	7.7	9.2	9.6	11.3	.	8.7	.	27.3	29.7	.	44.9	25.7	25.4	.	48.6	8.7	.	.	25.7	25.8	43.8
131X AGP4B	41	.	3	9	7	2	(23)	.	.	.	3	6	.	5	7	7	.	12	6	.	6	5	.	20
IMN SJ1	15.3	.	1.8	4.9	1.4	2.2	2.1	.	1.4	.	6.5	2.6	.	7.2	2.0	1.2	.	1.5	1.2	.	.	1.6	(0.70)	382.6

RM SILVER ALLOYS

analysis in mass %

Number	Ag	Au	Cu	Pb	Zn	Units
132X AGB100C	99.94	.	0.009	.	.	-40 mm Ø x ~10 mm
132X AGB100A	99.89	.	0.136	.	.	-40 mm Ø x ~10 mm
132X AGB100B	99.84	.	0.012	.	.	-40 mm Ø x ~10 mm
132X AGB94A	93.98	.	5.83	.	.	-40 mm Ø x ~10 mm
132X AGB93B	92.70	.	7.27	.	.	-40 mm Ø x ~10 mm
132X 925Zn1B	92.70	.	6.09	.	1.39	25 mm Ø x 3 mm
132X 925Zn3B	92.64	.	4.53	.	2.88	25 mm Ø x 3 mm
132X AGB90A	90.16	.	9.56	.	.	-40 mm Ø x ~10 mm
132X AGB90B	89.73	.	10.24	.	.	-40 mm Ø x ~10 mm
132X AGB88B	88.12	.	11.87	.	.	-40 mm Ø x ~10 mm
132X AGB87B	87.13	.	12.67	.	.	-40 mm Ø x ~10 mm
132X AGB85C	84.87	.	15.09	.	.	-40 mm Ø x ~10 mm
132X AGB75B	75.20	.	24.75	.	.	-40 mm Ø x ~10 mm
132X AGB75C	75.11	.	24.53	.	.	-40 mm Ø x ~10 mm
133X AGQ3C	rem	1.975	9.612	0.921	.	25 mm Ø x 3 mm
133X AGQ2C	rem	0.978	5.808	0.469	.	25 mm Ø x 3 mm
133X AGQ1C	rem	0.251	2.532	0.245	.	25 mm Ø x 3 mm

RM SILVER ALLOYS

analysis in mass %

Number	Au	Bi	Cu	Pb	Sb	Se	Si	Sn	Zn	Al	As	Cd	Co	Cr	Fe	Ge	In
133X AGA1A	1.48	0.194	19.95	0.207	0.050	0.0169	.	0.291	0.211	0.0096	0.0255	0.0165	0.0406	.	0.039	0.0107	0.0037
133X AGA2A	0.507	0.113	10.00	1.02	0.192	0.0078	.	0.520	0.502	0.0019	0.0144	0.0113	0.0163	.	0.027	0.0047	0.0065
133X AGA3A	0.258	0.048	4.91	1.89	0.459	0.0044	.	0.921	0.816	(0.0020)	0.0080	0.0042	0.0050	.	(0.015)	0.0045	0.0134
131X AgSe2A	.	0.0790	0.1333	.	.	0.0465	0.0039	.	.	0.0043	.	.	.	0.0037	0.0022	.	.
131X AgSe1A	.	0.0304	.	.	.	0.0162	0.0023	.	.

Number	Mn	Ni	Pd	Pt	Te	Units
133X AGA1A	0.0061	0.0118	0.0054	0.0067	0.0271	~25 mm Ø x ~3 mm
133X AGA2A	0.0115	0.0264	0.0076	0.0114	0.0098	~25 mm Ø x ~3 mm
133X AGA3A	0.0098	0.0450	0.0156	0.0256	0.0054	~25 mm Ø x ~3 mm
131X AgSe2A	-40 mm Ø x ~10 mm
131X AgSe1A	-40 mm Ø x ~10 mm

TIN

= class, where 1 = CRM and 2 = RM

analysis listed in mass %

* Provisional Analysis

Table with columns: #, Number, Ag, Al, As, Au, Bi, C, Cd, Co, Cr, Cu, Fe, Ga, Ge, Hg, In. Rows include BCS 192g and SRM 1727-1729.

Table with columns: Number, Ni, P, Pb, S, Sb, Se, Si, Sn, Te, Tl, Zn, Melt °C, Units. Rows include BCS 192g, SRM 1727-1729 and units like 300 g block or 100 g chips.

RM

TIN - LOW ALLOY

37 mm Ø x 12 mm

Table with columns: Number, Ag, Al, As, Bi, Cd, Co, Cu, Fe, In, Ni, Pb, Sb, Sn, Zn. Rows include NF 54-1 to 54-4.

RM

BISMUTH AND SULPHUR IN TIN

certified analysis in bold, rest is informational composition

37 mm Ø x 12 mm

Table with columns: Number, Bi, S, Ag, Al, As, Au, Cd, Cu, Fe, In, Ni, P, Pb, Sb, Sn, Zn. Rows include NF 60-1 to 60-4 and NF 59-1 to 59-5.

CRM

SPECIALTY TIN BASE LOW-LEAD and LEAD-FREE SOLDERS

analysis listed in mass %

~40 mm Ø x ~15 mm

Table with columns: Number, Ag, Al, As, Au, Bi, Cd, Co, Cu, Fe, Ge, Hg, In, Ni, P, Pb, S, Sb, Se, Zn. Rows include 74X CA5B to 74X BZ1A.

RM TIN - SILVER ALLOYS 37 mm Ø x 12 mm

Number	Ag	Bi	Cu	Ge	Hg	In	Ni	P	Pb	Sb	Sn	Zn
NF 46-3	5.0 #	0.25	0.030						0.21	0.059	Rem	(0.017)
NF 56-5	4.49	0.029	0.54		0.0024			0.006	0.26		Rem	
NF 56-6	4.24	0.096	0.80		0.009			0.012	0.024		Rem	
NF 46-2	4.1	0.095	0.096						0.059	0.11	Rem	(0.007)
NF 57-2	4.01		0.46		0.0002			0.006	<0.001		Rem	
NF 56-2	3.77	0.50	0.60		0.0004			0.009	0.051		Rem	
NF 56-3	3.53		0.4		0.014			0.003	0.009	0.50	Rem	
NF 56-4	3.26	0.20	0.30		0.0045			0.021	0.22		Rem	
NF 46-1	3.1	0.05	0.19						0.043	0.205	Rem	(0.015)
NF 57-1	3.00	0.004	0.49		0.0016			0.004	0.076		Rem	
NF 9-1	3.00	0.048	0.073						Rem	0.51	59.90	
NF 61-4	2.58								Rem		62.0	
NF 63-6	2.56		0.50	0.042		<0.001	0.0073		0.009		Rem	
NF 56-1	2.54	0.006	0.91		0.018			0.020	0.10		Rem	
NF 61-3	2.33								Rem		62.0	
NF 9-2	2.00	0.093	0.040						Rem	0.38	61.90	
NF 61-2	1.81								Rem		62.0	
NF 61-1	1.54								Rem		62.0	
NF 63-4	1.50		0.194	0.025		0.027	0.12		0.012		Rem	
NF 63-3	1.18		0.53	0.005		0.053	0.066		0.024		Rem	
NF 63-2	1.02		0.104	0.052		0.005	0.027		0.18		Rem	
NF 63-5	1.01		0.51	0.010		0.11	0.065		0.018		Rem	
NF 9-3	1.00	0.25	0.010						Rem	0.23	63.60	
NF 63-1	0.74		0.077	0.079		0.200	0.068		0.009		Rem	
NF 58-3	0.51	0.077	0.59		0.0043			0.010	0.040		Rem	
NF 58-1	0.32	0.12	0.69		0.0003			0.001	0.085		Rem	
NF 58-2	0.21	0.095	0.79		0.0024			0.006	0.008		Rem	

CRM TIN BASE SETS available in sets only, as grouped

Number	Ag	Al	As	Au	Bi	Cd	Cu	Fe	In	Ni	Pb	Sb	Sn	Zn
IMN LBA 1	0.632		0.0459	0.0115	0.230	0.00085	0.282	0.0195	0.208	0.0055	0.228	0.0517	Rem	0.0032
IMN LBA 2	0.697	(0.0029)	0.0314	0.0259	0.175	0.0052	0.487	0.0182	0.127	0.0107	0.319	0.0979	Rem	0.0047
IMN LBA 3	0.0971	0.0022	0.0239	0.0468	0.0989	0.0039	0.885	0.0057	0.0949	0.0224	0.141	0.142	Rem	0.0020
IMN LBA 4	0.0976	0.0061	(0.0086)	0.0632	0.0364	0.0058	1.21	0.0114	0.0503	0.0320	0.0862	0.457	Rem	0.0006
IMN LBA 5	0.214		(0.0090)	0.691	0.325	0.0053	0.763	0.0098	0.0228	0.0346	0.0579	0.286	Rem	(0.0009)
IMN LCA 1	0.210	<0.0012	0.0494	0.0677	0.269	0.0093			0.141		0.229	0.490	Rem	
IMN LCA 2	0.158		0.0864	0.0542	0.146	0.0073	2.67	0.0155	0.0610	0.0210	0.0773	0.138	Rem	0.0016
IMN LCA 3	0.107	(0.0011)	0.0285	0.0260	0.100	0.0025	3.53	0.0143	0.0081	0.0102	0.137	0.101	Rem	0.0042
IMN LCA 4	0.0545	(0.0023)	0.0145	0.0100	0.0403	0.0115	4.51	0.0101	0.0442	0.0056	0.0890	0.0479	Rem	0.0103
IMN LCA 5	0.221		0.0386	0.0670	0.263	0.0006	1.52	0.0295	0.0533	0.0315	0.232	0.458	Rem	0.0011
IMN L89 1			0.019		0.012	0.19	3.20	0.18		0.010	0.072	5.66	Rem	0.099
IMN L89 2			0.037		0.026	0.091	4.15	0.086		0.031	0.13	6.39	Rem	0.059
IMN L89 3			0.065		0.052	0.041	3.49	0.058		0.090	0.29	7.41	Rem	0.042
IMN L89 4			0.12		0.099	0.021	2.81	0.028		0.16	0.52	8.14	Rem	0.020
IMN L89 5			0.18		0.20	0.011	2.12	0.013		0.33	1.11	8.86	Rem	
IMN L89 6			0.029		0.014	0.19	4.51	0.17		0.014	0.20	8.03	Rem	0.096
IMN LA 1			0.012		0.014	1.41	2.45	0.012		0.011	3.18	6.79	Rem	0.0016
IMN LA 2			0.092		0.033	0.88	3.84	0.018		0.094	2.17	7.81	Rem	
IMN LA 3			0.24		0.059	0.50	8.13	0.059		0.28	1.19	10.22	Rem	0.0095
IMN LA 4			0.43		0.085	0.096	6.95	0.080		0.45	0.41	11.66	Rem	
IMN LA 5			0.54		0.099	0.011	5.45	0.096		0.53	0.070	13.58	Rem	0.020
IMN L 1			0.051		0.17	0.0020	0.11				Rem	0.52	56.06	0.00093
IMN L 2			0.034		0.11	0.0043	0.075	(0.011)			Rem	0.35	59.09	0.0019
IMN L 3			0.092		0.22	0.0065	0.034	(0.023)			Rem	0.14	60.18	0.0064
IMN L 4			0.017		0.055	0.0080	0.013	(0.0085)			Rem	0.079	62.81	0.0011
IMN L 5			0.0035		0.014	0.0097	0.0037				Rem	0.011	64.96	0.0056

CRM TITANIUM * Provisional Analysis # = class, where 1 = CRM and 2 = RM

#	Number	Al	B	C	Co	Cr	Cu	Fe	H	Mn	Mo	N	Nb	Ni	O
1	IARM 311A	0.32		0.009		0.013	0.0013	0.060	0.0021	0.0013	0.0012	0.012	(0.002)	0.014	0.083
1	BCR 090	(0.074)	0.00282		0.0501	0.0533	0.0513	0.0563		0.0314	0.0488		(0.0492)	0.0667	
1	BS T-81	0.0664	0.0082	0.0161	0.0395	0.0294	0.0244	0.1144	0.0035	0.0404	0.0279	0.0037	0.0191	0.0090	0.0669
1	BS T-4A	0.040		0.014		0.026	(0.001)	0.19	(0.0027)	0.003	0.0006	0.005		0.014	(0.37)
1	IARM 312B	0.018	(0.001)	0.0092	(0.002)	0.010	(0.003)	0.072	0.0004	(0.001)	(0.003)	0.007	(0.001)	0.019	0.128
1	IARM 303B *	(0.015)	<0.001	0.035	<0.002	0.0018	(0.002)	0.120	(0.0008)	(0.001)	(0.002)	0.017	(0.006)	(0.0013)	0.176
1	IARM 361A	(0.013)	(0.0005)	(0.012)	(0.002)	0.008	(0.003)	0.095	(0.0027)	(0.005)	0.288	(0.006)	(0.004)	0.88	0.15
1	IARM 312A	0.006		0.004	(0.001)	(0.002)	(0.002)	0.028	0.0049	(0.001)	(0.002)	0.0023		(0.002)	0.066
1	BS T-2A	0.005		(0.007)		0.018	(0.001)	0.156	(0.0020)	0.003	0.002	(0.0044)		0.021	(0.12)

BCR: HIP; 090A: 40mm Ø x 20mm; 090B: ~25g of 0.2g cubes BS: 38-40 Ø x ~7, 12, or 19mm IARM: 31mm Ø x 2 or 18mm

Number	P	Pd	Ru	S	Si	Sn	V	W	Y	Zr	Grade
IARM 311A					0.005	0.0020	0.004	(0.002)	(0.0002)	0.012	BT1-0
BCR 090						(0.071)	(0.057)	(0.050)		(0.0436)	
BS T-81		0.0398	0.0310		0.0474	0.0155	0.0186	0.0372	0.0017	0.0163	Ti Cp 17
BS T-4A	(0.001)			(0.0004)	0.011	0.005	(0.001)	<0.002		<0.002	Ti Cp 1
IARM 312B	(0.002)	(0.005)	(0.001)	(0.0008)	(0.006)	(0.004)	0.009	(0.0005)	(0.001)	0.0014	Ti CP 4.1
IARM 303B *		0.13	<0.01	<0.002	(0.006)	(0.006)	(0.0023)	<0.002	<0.001	(0.0028)	Ti Cp 7
IARM 361A	(0.003)	(0.002)	(0.006)	(0.004)	(0.012)	(0.004)	(0.006)	(0.0027)	(0.003)	(0.0016)	Ti Cp 12
IARM 312A		(0.004)		(0.001)	0.006	0.0012	(0.002)		(0.0004)	(0.001)	Ti CP 4.1
BS T-2A				(0.0004)	0.002	0.006	<0.002	<0.002		<0.003	Ti Cp 1

 last 18mm only
 17025 last 12mm only

CRM TITANIUM SETS available in SETS ONLY, as grouped

Number	Al	C	Fe	Mo	Si	Sn	V	Zr	Units
58A HCO3001	4.51	.	.	2.69	.	1.36	.	5.35	35 mm Ø x 35 mm
58A HCO3002	5.31	.	.	2.4	.	1.71	.	4.59	
58A HCO3003	6.05	.	.	2.0	.	2.04	.	3.93	
58A HCO3004	6.94	.	.	1.76	.	2.32	.	3.32	
58A HCO3005	7.78	.	.	1.42	.	2.72	.	2.83	
58A SY03009-1	3.9	0.158	0.39	.	0.277	.	5.65	.	36 mm Ø x 25 mm
58A SY03009-2	4.67	0.119	0.314	.	0.196	.	5.01	.	
58A SY03009-3	5.38	0.095	0.239	.	0.115	.	3.41	.	
58A SY03009-4	6.48	0.051	0.143	.	0.054	.	4.46	.	
58A SY03009-5	6.78	0.023	0.131	.	0.085	.	3.85	.	

TITANIUM ALLOYS, chart 1 of 2

= class, where 1 = CRM and 2 = RM analysis listed in mass % * Provisional Analysis

#	Number	Al	V	C	Cr	Cu	Fe	H	N	O	Mn	Mo	Ni	Si	Sn	Zr
1	IARM 269B	7.86	1.03	(0.014)	(0.0014)	(0.0023)	0.071	0.007	(0.006)	0.090	0.0071	0.98	(0.001)	(0.025)	0.008	(0.002)
1	58A ZB03002	6.54	3.61	0.014	.	.	0.066	.	0.016	.	.	.	<0.003	0.024	.	.
1	IARM Ti64-18	6.52	4.08	(0.034)	(0.013)	.	0.19	(0.0031)	(0.025)	0.181	.	(0.004)	0.011	(0.011)	(0.003)	.
1	58A CP03005	6.46	5.1	0.01	0.02	0.0099	0.231	.	.	.	0.0064	.	.	0.031	0.001	0.018
2	CT 6AL4V	6.39	4.01	.	.	.	0.14
1	IARM 175D	6.39	3.99	0.008	0.014	0.002	0.23	0.0027	0.030	0.177	(0.003)	0.0030	0.016	0.008	0.007	(0.002)
1	SRM 654b	6.34	4.31	.	0.025	0.008	0.23	(0.002)	.	(0.17)	.	0.013	0.028	0.045	0.023	0.008
1	58A SY03005	6.24	4.08	0.013	.	.	0.047	0.024	.	.
1	IARM Ti64ELI-18	6.11	4.01	0.033	(0.004)	(0.002)	0.167	(0.0021)	(0.006)	0.118	(0.0014)	.	(0.003)	(0.014)	(0.022)	.
1	BCR 089	5.97	3.976
1	58A CP03004	5.88	1.61	0.017	0.028	0.0085	0.074	.	.	.	0.027	3.58	.	0.059	0.0085	0.024
1	IARM 178D	5.49	5.47	0.028	0.031	0.52	0.550	0.0016	0.017	0.17	(0.003)	0.10	0.067	0.053	1.84	0.026
1	58A CP03003	5.21	4.89	0.014	0.997	.	1.01	4.87	.	0.038	.	0.02
1	IARM Ti1023-18	3.31	9.75	(0.032)	(0.016)	(0.006)	1.98	(0.002)	(0.005)	0.109	(0.0024)	(0.003)	0.009	(0.018)	.	.
1	IARM 344A	3.15	15.3	0.011	3.09	(0.002)	0.20	(0.015)	0.005	0.107	(0.003)	0.004	0.011	(0.03)	3.09	(0.002)
1	58A SY03003	3.14	14.98	0.01	2.84	.	0.05	(0.001)	(0.02)	(0.013)	3.17	.
1	58A SY03004	3.13	2.82	0.01	.	.	0.042	(0.001)	(0.01)	(0.1)
1	SRM 1128	3.06	15.13	0.011	2.96	.	0.134	3.04	.
1	IARM 261E	3.05	2.51	0.012	0.016	0.0025	0.18	(0.0005)	0.006	0.084	(0.001)	0.003	0.018	0.007	0.005	(0.003)
1	IARM 261C	3.05	2.46	0.011	0.014	0.003	0.180	0.001	0.005	0.085	(0.003)	0.004	0.016	0.007	0.006	0.003
1	IARM 344B *	3.03	14.7	0.0095	2.91	(0.0024)	0.118	0.007	(0.016)	0.118	(0.003)	(0.006)	0.021	(0.03)	3.01	(0.002)
1	IARM 261D	3.02	2.50	0.011	0.016	0.0028	0.185	(0.0005)	0.0051	0.083	(0.002)	0.003	0.018	0.008	0.005	0.003
1	IARM 261A	3.00	2.48	0.007	0.013	(0.002)	0.19	0.0023	0.007	0.10	0.0011	(0.003)	0.006	0.012	0.008	(0.002)
1	IARM 261B	2.98	2.23	0.011	0.016	0.003	0.19	(0.001)	0.004	0.083	(0.003)	0.004	0.023	0.008	0.004	(0.002)

#	Number	Al	V	C	Cr	Cu	Fe	H	N	O	Mn	Mo	Ni	Si	Sn	Zr
	Number	B	Co	Nb	P	Pd	Ru	S	Ta	Ti	W	Y	Units			
	IARM 269B	(<0.001)	(<0.0005)	(0.004)	(0.003)	(<0.005)	(0.004)	(0.003)	(<0.005)	(89.9)	(0.001)	(<0.001)	31 mm Ø x 2 or 18 mm			
	58A ZB03002	40 mm Ø x 30 mm			
	IARM Ti64-18	(89.0)	.	.	31 mm Ø x 2 or 18 mm			
	58A CP03005	40 mm Ø x 35 mm			
	CT 6AL4V	30-35 mm Ø x ~19 mm			
	IARM 175D	(0.0008)	.	(0.008)	(89.2)	(0.002)	(0.001)	31 mm Ø x 2 mm last			
	SRM 654b	(0.001)	31 mm Ø x 19 mm			
	58A SY03005	36 mm Ø x 25 mm			
	IARM Ti64ELI-18	(89.7)	.	.	31 mm Ø x 2 or 18 mm			
	BCR 089	40 mm Ø x 20 mm			
	58A CP03004	40 mm Ø x 35 mm			
	IARM 178D	(0.001)	0.005	(0.01)	(0.002)	(0.003)	(0.001)	(0.001)	(0.001)	(85.8)	(0.001)	(0.001)	31 mm Ø x 2 or 18 mm			
	58A CP03003	40 mm Ø x 35 mm			
	IARM Ti1023-18	84.8	.	.	31 mm Ø x 2 or 18 mm			
	IARM 344A	0.0011	(0.001)	(0.005)	(0.002)	(0.001)	.	(0.001)	(0.001)	(74.9)	(0.003)	<0.001	31 mm Ø x 2 or 18 mm			
	58A SY03003	36 mm Ø x 30 mm			
	58A SY03004	<0.001	36 mm Ø x 30 mm			
	SRM 1128	35 mm Ø x 19 mm			
	IARM 261E	0.0003	(0.0004)	(0.005)	<0.003	(0.002)	(0.001)	(0.001)	.	(94.1)	(0.001)	(0.001)	31 mm Ø x 2 or 18 mm			
	IARM 261C	0.0004	(0.005)	(0.003)	(0.003)	(0.002)	(0.001)	(0.001)	.	(94.1)	(0.001)	(0.0004)	31 mm Ø x 2 or 18 mm			
	IARM 344B *	<0.001	<0.004	(0.003)	<0.003	<0.03	<0.02	<0.003	<0.04	(76.0)	<0.03	<0.006	31 mm Ø x 2 or 18 mm			
	IARM 261D	0.0003	<0.001	(0.003)	<0.004	(0.002)	(0.0005)	(0.001)	(0.0005)	(94.2)	(0.001)	(0.0005)	31 mm Ø x 2 or 18 mm			
	IARM 261A	(0.001)	31 mm Ø x 2 mm			
	IARM 261B	0.0004	<0.004	(0.002)	(0.004)	.	(0.001)	(0.0004)	.	(94.4)	(0.003)	(0.0004)	31 mm Ø x 2 or 18 mm			

TITANIUM ALLOYS, chart 2 of 2

= class, where 1 = CRM and 2 = RM analysis listed in mass % * Provisional Analysis

Table with columns: #, Number, Al, V, C, Cr, Fe, H, Mn, Mo, N, Nb, O, Si, Sn, Ti, Zr. Rows list various titanium alloy standards and their chemical compositions.

Table with columns: #, Number, Al, V, C, Cr, Fe, H, Mn, Mo, N, Nb, O, Si, Sn, Ti, Zr. Continuation of the titanium alloy standards table.

Table with columns: Number, B, Co, Cu, Mg, Ni, P, Pb, Pd, Ru, S, Sb, Ta, W, Y, Units. Rows list various titanium alloys and their mechanical properties/units.

Table with columns: Number, B, Co, Cu, Mg, Ni, P, Pb, Pd, Ru, S, Sb, Ta, W, Y, Units. Continuation of the titanium alloy table.

ZINC

= class, where 1 = CRM and 2 = RM analysis listed in mass % Trace = informational values such as (<0.001) or lower

#	Number	Pb	Al	Cd	Cu	Fe	In	Mg	Mn	Ni	Sb	Sn	Tl
1	41X Z6A	0.031	0.0096	0.0093	0.0088	(0.002)	0.0228	<0.0005	0.0002	0.0002	.	0.0038	.
1	41X Z5N	0.0286	0.0243	0.0165	0.0109	0.0262	0.0057	0.0107	0.0049	0.0051	0.0054	0.0063	0.0068
1	ERM-EB325	0.0142	.	0.00947	0.00475	0.00561	0.00461	0.00368
1	41X Z11A	0.0077	0.0261	0.0155	0.0116	0.0019	0.0345	.	.	.	0.0026	0.0072	(0.0010)
1	41X Z4L	0.00584	0.0065	0.00437	0.00326	0.0148	0.00304	0.00331	0.00286	0.00320	0.00340	0.00221	0.00277
1	41X Z3M	0.00502	0.00158	0.00327	0.00345	0.00605	0.00233	(0.00034)	0.00524	0.00209	0.00167	0.00297	0.00210
2	BS SP-5	0.005	0.0003	<0.0004	<0.001	<0.001	.	<0.002	.	.	<0.001	0.0010	.
1	ERM-EB323	0.00486	.	0.000651	0.00189	0.00113	0.00187	0.00108
1	BCR 327	0.004094	.	0.03014	(0.000056)	0.01440
1	BCR 326	0.003070	Trace	0.02030	0.01048	0.02648
2	BS SP-A	0.003	0.051	.	<0.0005	0.011	0.099	<0.001	.
1	41X Z1Q	0.00276	(0.00011)	0.00120	0.00116	0.00282	0.00026	(0.00010)	0.00047	0.00014	(0.00024)	0.00051	0.00028
1	ERM-EB324	0.00261	.	0.00489	0.000987	0.00585	0.00098	0.00199
2	BCS 194e	0.002	.	.	.	0.001
1	BAM M601	0.00157	<0.00005	0.000055	0.000189	0.000220	<0.000005	0.000225
1	ERM-EB322	0.00150	.	0.001508	0.000589	0.00191	0.00056	0.000528
1	SRM 683	0.00111	.	0.00011	0.00059	0.00022	Trace	.	Trace	.	.	(0.000002)	(0.00002)
1	SRM 631	(0.001)	0.50	0.0002	0.0013	0.005	0.0023	Trace	0.00015	Trace	.	0.0001	.
1	BCR 321	0.000485	<0.00007	(0.000023)	(0.000097)	(0.000222)	<0.00002	<0.00005	0.000078
1	SRM 682 *	.	(<0.000003)	(0.00001)	0.0000042	(0.00001)	.	(<0.00001)	Trace	(<0.00001)	.	(0.000002)	(<0.00002)

Number	Ag	Bi	Cr	Ga	Ge	Hg	Si	Zn	Melt °C	Units
41X Z6A	.	0.0122	(0.0001)	50 mm Ø x 20 mm
41X Z5N	.	0.0056	.	.	.	0.0050	.	.	.	~50 mm Ø x 20 mm
ERM-EB325	60 mm Ø x 30 mm
41X Z11A	.	0.0189	.	.	.	(0.0009)	.	.	.	50 mm Ø x 20 mm
41X Z4L	.	0.00319	.	.	.	0.0025	.	.	.	50 mm Ø x 20 mm
41X Z3M	.	0.00315	.	.	.	0.00289	.	.	.	~50 mm Ø x ~20 mm
BS SP-5	37 mm Ø x 12 mm
ERM-EB323	60 mm Ø x 30 mm
BCR 327	80 mm Ø x 20 mm
BCR 326	80 mm Ø x 20 mm
BS SP-A	38 mm Ø x 14 mm last of stock
41X Z1Q	.	0.00030	.	.	.	0.00034	.	.	.	~50 mm Ø x ~20 mm
ERM-EB324	60 mm Ø x 30 mm
BCS 194e	99.99	419.5	300 g(4.5 x 3.5 x 3 cms)
BAM M601	45 mm Ø x 30 mm
ERM-EB322	60 mm Ø x 30 mm
SRM 683	0.00013	.	.	Trace	Cylinder segment 57mm Ø x 25mm x 19mm
SRM 631	Trace	.	0.0001	(0.0002)	(0.0002)	45 mm x 45 mm x 19 mm
BCR 321	80 mm Ø x 20 mm
SRM 682 *	(0.000002)	.	(<0.000006)	.	.	.	(<0.00005)	.	.	Cylinder segment 57mm Ø x 25mm x 19mm

* SRM 682 has trace informational B, Be, C, Ca, Cl, F, K, Li, N, and Nb.

CRM ZINC SETS

available in sets only, as grouped

Number	Al	Cd	Cu	Fe	Pb	Sn	Ti	Zn	Units
IMN ZA 1	.	0.0042	(0.0032)	0.00167	0.025	0.0038	.	Rem	Rods 10 mm Ø x 100 mm
IMN ZA 2	.	0.0029	0.0013	0.0061	0.011	0.0012	.	Rem	
IMN ZA 3	.	0.00092	0.00011	0.00078	0.0028	0.00036	.	Rem	
IMN ZA 4	.	0.00049	0.00032	0.00040	0.0016	0.00011	.	Rem	
IMN ZE 1	0.012	0.0019	0.011	0.020	0.018	0.0018	.	Rem	Discs 40 mm Ø x 25 mm
IMN ZE 2	0.0035	0.0031	(0.00037)	0.0052	0.0078	0.0074	.	Rem	
IMN ZE 3	0.025	0.0050	0.0032	.	0.0052	0.015	.	Rem	
IMN ZE 4	.	0.00023	0.013	(0.00035)	0.0012	0.0017	.	Rem	
IMN ZE 5	0.0011	0.0060	0.0049	0.011	0.0004	0.00045	.	Rem	
IMN ZL 1	0.0190	0.0365	0.342	0.00072	0.00498	0.0364	0.00745	Rem	Discs 40 mm Ø x 25 mm
IMN ZL 2	0.0119	0.0241	0.573	0.0174	0.00923	0.0420	0.114	Rem	
IMN ZL 3	0.00388	0.00492	0.201	0.00496	0.0247	0.00788	0.238	Rem	
IMN ZL 4	0.0497	0.0115	0.114	0.00879	0.0351	0.0114	0.394	Rem	
IMN ZL 5	0.0518	0.00085	0.0115	0.0299	0.0363	0.0011	0.598	Rem	

CRM ZINC RoHS MONITOR

cast 50 mm Ø x 20 mm

Number	Cd	Cr	Hg	Pb
41X ZSC6A	0.215	<0.0002	0.029	0.0077
41X ZSC3A	0.119	0.0148	0.0021	0.0273
41X ZSC1A	0.0288	0.0039	0.026	0.0621
41X ZSC4A	0.0131	0.0299	0.050	0.156
41X ZSC2A	0.0016	0.0036	0.0053	0.111

CRM ZAMAK (MAZAK) SPECIFICATIONS AND SUGGESTED SAMPLES

42X, 43X: ~50 mm Ø x ~15-20 mm BAM: 39 mm Ø x 39 mm BCR: 80 mm Ø x 20 mm SRM: 44 mm x 44 mm x 19 mm

Number	Al	Cu	Mg	Ni	Cd	Cr	Fe	Mn	Pb	Sn
Zamak 2	3.9-4.3	2.6-2.9	0.025-0.05	.	<0.003	.	<0.075	.	<0.004	<0.002
43X Z7A	3.68	3.14	0.062	0.0005	0.00092	0.0003	0.029	0.0025	0.0058	0.0031
43X Z6B	4.51	2.85	0.0238	0.0027	0.0031	0.0005	0.024	0.0022	0.004	0.0052
43X Z4C	4.79	2.69	0.0480	0.0258	0.0033	.	0.0017	0.0153	0.0062	0.0030
Zamak 5	3.9-4.3	0.75-1.25	0.030-0.06	.	<0.003	.	<0.075	.	<0.004	<0.002
Zamak 6	3.9-4.3	0.75-1.25	<0.05	.	<0.003	.	<0.075	.	<0.004	<0.002
43X Z3M	3.40	1.499	0.114	0.0062	0.0109	0.0046	(0.042)	0.0013	0.0077	0.0058
BCR 360	3.427	1.234	0.0705	0.0267	0.00595	.	.	.	0.00739	0.00330
43X Z2P	4.07	1.019	0.0614	0.0100	0.0031	.	0.0013	0.0162	0.0048	0.0033
SRM 630	4.30	0.976	0.030	0.0027	0.0048	0.0031	0.023	0.0106	0.0083	0.0040
ERM-EB602	4.08	0.812	0.0415	0.00025	0.00011	.	0.00073	.	0.00195	0.00010
BCR 361	4.068	0.798	.	.	(0.00080)	.	0.001034	.	0.000531	0.00463
43X Z1K	4.50	0.717	0.0256	0.0010	0.0014	0.0007	0.0070	0.0014	0.0038	0.0019
SRM 628	4.59	0.611	0.0094	0.030	0.0040	0.0087	0.066	0.0091	0.0045	0.0017
BCR 357	4.227	0.5849	0.0273	0.000982	0.000283	.	0.00257	.	0.00138	0.000351
43X Z1J	4.50	0.501	0.0145	0.0010	0.00037	0.0009	0.0058	0.0005	0.0017	(0.0007)
Zamak 3	3.9-4.3	<0.10	0.025-0.05	.	<0.003	.	<0.075	.	<0.004	<0.002
Zamak 7	3.9-4.3	<0.10	0.010-0.020	0.005-0.02	<0.002	.	<0.075	.	<0.002	<0.001
BCR 356	4.434	0.3944	0.01323	0.000343	0.000073	.	0.00315	.	0.000987	(0.000032)
42X Z6B	3.67	0.238	0.177	0.00030	0.0039	0.0034	0.008	0.0157	0.0093	0.0057
42X Z12A	4.717	0.156	0.0488	0.0413	0.00277	0.00063	0.0457	0.0483	0.0079	0.0022
42X Z3J	3.84	0.135	0.0503	0.0071	0.0065	.	0.0145	0.0090	0.0068	0.0048
SRM 627	3.88	0.132	0.031	0.0029	0.0051	0.0038	0.023	0.014	0.0082	0.0042
42X Z5M	4.33	0.111	0.0508	0.041	0.0013	(0.0002)	(0.05)	0.0049	0.0030	0.0012
BCR 355	3.443	0.1035	0.0786	0.0268	0.00581	.	0.0017	.	0.00569	0.00291
42X Z4J	3.55	0.063	0.058	0.0177	0.0076	.	0.012	0.0077	0.0113	0.0060
SRM 626	3.56	0.056	0.020	0.047	0.0016	0.0395	0.103	0.048	0.0022	0.0012
SRM 625	3.06	0.034	0.070	0.0184	0.0007	0.0128	0.036	0.031	0.0014	0.0006
BCR 354	3.726	0.03123	0.0602	0.00831	0.00297	.	.	.	0.00308	0.00141
42X Z2K	3.79	0.0300	0.0146	0.0155	0.0017	(0.0001)	0.0055	0.0274	0.0029	0.0011
BCR 352	4.150	0.003126	0.02830	0.000674	0.000288	.	.	.	(0.00064)	0.00030
BCR 351	4.355	0.001213	0.01310	(0.00019)	(0.00021)	.	.	.	0.000450	<0.0001
Zamak 8	7.8-9.0	0.70-1.40	0.015-0.030	<0.02	<0.005	.	<0.1	.	<0.005	<0.003
43X Z14F	7.98	1.238	0.0123	0.0058	0.00567	0.0037	0.0025	(0.0003)	0.0019	0.0005

Number	Be	Bi	Ce	In	La	Sb	Si	Ti	Tl
Zamak 2
43X Z7A	0.0194	(0.0009)	.	.	.	0.0016	.	0.067	.
43X Z6B	.	0.0054	.	.	.	0.0044	.	.	.
43X Z4C	.	0.0113	.	.	.	(0.0023)	(0.0012)	.	.
Zamak 5
Zamak 6
43X Z3M	.	0.0092	.	.	.	0.0029	.	.	.
BCR 360	.	.	.	0.00298	0.00259
43X Z2P Ag:0.0098	.	0.0038	.	.	.	0.0012	.	.	.
SRM 630	0.022	.	.
ERM-EB602	0.00114	0.00048	.
BCR 361	.	.	.	(<0.00002)	0.00374
43X Z1K	.	0.0015	.	.	.	0.0007	.	.	.
SRM 628	0.008	.	.
BCR 357	.	.	.	0.000330	0.000276
43X Z1J	.	0.0031	.	.	.	0.0016	(0.0037)	0.0014	.
Zamak 3
Zamak 7
BCR 356	.	.	.	<0.00002	0.000079
42X Z6B	.	.	(0.012)	0.00191	(0.011)	0.0169	(0.010)	.	0.0021
42X Z12A	.	.	0.0116	0.0068	0.0084	0.0070	.	.	0.0076
42X Z3J	.	.	0.0032	.	0.0013	0.0006	(0.0018)	.	.
SRM 627	0.021	.	.
42X Z5M	.	.	0.0328	.	0.0026	.	.	0.0017	.
BCR 355	.	.	.	0.00246	0.002325
42X Z4J	.	.	0.020	0.0016	0.020	(0.0029)	.	.	(0.0025)
SRM 626	0.042	.	.
SRM 625	0.017	.	.
BCR 354	.	.	.	0.00098	0.0150	0.0010	0.0011	.	0.001101
42X Z2K	.	.	0.0055	0.0047
BCR 352	.	.	.	0.000302	0.00032
BCR 351	.	.	.	<0.00002	0.000074
Zamak 8	<0.03	.	.
43X Z14F	.	0.0106	.	.	.	0.0105	(<0.001)	(0.0001)	.

CRM ZAMAK SET

SOLD IN SET/4 ONLY

40 mm Ø x 25 mm

Number	Al	Cd	Cu	Fe	Mg	Ni	Pb	Si	Sn
IMN ZG 1	3.07	0.00048	1.34	0.0083	0.074	0.0067	0.009	0.036	0.0068
IMN ZG 2	3.56	0.0049	0.72	.	0.048	0.0025	0.0065	0.024	0.0048
IMN ZG 3	4.00	0.0028	0.11	0.011	0.028	0.001	0.0033	0.01	0.00067
IMN ZG 4	4.64	0.011	(0.0089)	0.016	0.00055	0.00042	0.0013	(0.0047)	0.0021

ZINC BINARY AND TERNARY SAMPLES

= class, where 1 = CRM and 2 = RM analysis in mass % cast

#	Number	Al	Mn	Pb	Sb	Units
1	SRM 1742	0.7917	.	(0.0029)	.	50 mm Ø x 12 mm
1	SRM 1741	0.5242	.	0.1571	.	50 mm Ø x 12 mm
1	SRM 1740	0.4177	.	0.0691	.	50 mm Ø x 12 mm
1	SRM 1738	0.1014	.	0.0101	.	50 mm Ø x 12 mm
2	41X ZMg1A	40 mm Ø x 15 mm
1	41X ZMn1A	.	1.07	.	.	50 mm Ø x 20 mm
2	41X ZSb1A	.	.	.	1.03	40 mm Ø x 15 mm
2	41X ZSb4A	.	.	.	3.78	40 mm Ø x 15 mm
2	41X ZSb8A	.	.	.	7.68	40 mm Ø x 15 mm

RM ZINC - ALUMINUM - ANTIMONY ALLOYS

cast some Sb segregation in below series, last of stock 40 mm Ø x 15 mm

Number	Al	Sb	Bi	Cd	Cu	Fe	Mg	Pb	Sn
44X Z5A	20.4	5.2	0.004	0.001	0.001	0.010	<0.001	0.010	0.003
44X Z4A	20.3	6.7	0.016	0.011	0.007	0.011	0.008	0.032	0.018

CRM ZINC ALLOY SETS

available in SETS ONLY, as grouped

~40 mm Ø x ~25 mm

Number	Al	Bi	Cd	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Sn	Ti	Zn
IMN ZK 1	11.789	0.200	0.0021	1.538	.	0.0009	.	.	0.0031	0.127	0.00085	.	.
IMN ZK 2	10.572	0.169	0.0031	3.119	.	0.0040	0.0137	.	0.0121	0.102	0.0015	.	.
IMN ZK 3	9.767	0.102	0.0071	3.996	.	0.0307	.	.	0.0226	0.0674	0.00267	.	.
IMN ZK 4	8.371	0.0188	0.0121	5.487	.	0.0640	.	.	0.0334	0.0121	0.00491	.	.
IMN ZK 5	6.476	0.0020	0.0207	6.663	.	0.0410	0.589	.	0.0507	0.0025	0.0065	.	.
IMN ZF 1	0.018	.	0.0041	0.013	0.020	.	.	.	0.0012	.	0.013	0.0014	Rem
IMN ZF 2	0.011	.	0.0055	0.46	0.011	.	.	.	0.0082	.	0.0077	0.11	Rem
IMN ZF 3	0.0033	.	.	0.098	0.0018	0.0022	0.021	Rem
IMN ZF 4	0.0058	.	0.00053	0.86	0.00045	.	.	.	0.0091	.	0.0017	0.20	Rem
IMN ZF 5	.	.	0.0088	0.011	0.0081	.	.	.	0.026	.	.	0.013	Rem

CRM														
ZINC ALLOYS, chart 1 of 2														
X: ~50 mm Ø x ~15-20 mm CAN: 50 mm Ø x 12 mm SRM: 44 mm x 44 mm x 19 mm														
Number	Al	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Si	Sn	Ti
43X Z23E	30.7	.	0.0042	0.0147	3.22	0.055	0.0242	0.0090	0.0236	0.0112	.	0.077	0.0115	0.0045
CAN NZA-1	28.70	.	0.00098	.	1.51	0.046	0.020	.	.	0.0030	.	.	0.0069	.
43X Z22D	27.4	.	0.0043	0.0010	2.11	0.068	0.0099	0.0057	0.0101	0.0053	.	0.019	0.0020	0.0073
CAN NZA-4	26.65	.	0.0029	.	2.45	0.027	0.0106	.	.	0.0101	.	.	0.0087	.
CAN NZA-3	25.99	.	0.0064	.	2.00	0.066	0.0049	.	.	0.0045	.	.	0.0034	.
43X Z21D	23.9	.	0.0010	.	2.68	0.0067	0.0142	0.0022	0.0021	0.0087	.	0.0191	0.0007	.
CAN NZA-2	23.81	.	0.0047	.	3.00	0.021	0.029	.	.	0.0076	.	.	0.0045	.
43X GALF5A	15.03	.	0.0080	.	0.0114	(0.072)	0.0016	.	.	0.0084	.	.	0.0081	.
CAN NZA-7	13.17	.	0.00020	.	0.212	(0.016)	0.052	.	.	0.0136	.	.	0.0116	.
42X Z16A	12.28	.	0.0045	0.0007	0.235	0.033	0.105	0.0028	0.0039	0.0090	.	0.011	0.0034	.
43X Z11F	11.12	0.0046	0.0175	(0.0003)	0.335	0.015	0.0357	0.0032	0.0014	0.0202	0.0009	0.0013	0.0145	.
CAN NZA-5	10.85	.	0.0095	.	1.04	(0.016)	0.021	.	.	0.0012	.	.	0.0017	.
43X GALF4A	10.71	.	0.0108	.	2.470	0.074	0.0062	.	.	0.0122	.	.	0.0110	.
43X Z12E	10.38	0.0021	0.0045	0.0008	0.791	0.037	0.0287	0.0026	0.0033	0.0041	0.0032	(0.002)	0.0017	0.0050
42X Z15A	9.99	.	0.0023	0.0003	0.0028	0.026	0.0026	0.0037	0.0017	0.0074	0.0006	.	0.0006	.
43X Z13E	9.01	0.0014	0.0072	0.0004	1.113	0.0045	0.0198	0.0025	0.0036	0.0086	0.0020	(0.0012)	0.0035	.
43X GALF3A	8.37	.	0.0018	.	0.507	0.018	0.0099	.	.	0.0032	.	.	0.0025	.
CAN NZA-6	7.54	.	0.0147	.	3.17	(0.0105)	0.00037	.	.	0.0809	.	.	0.0051	.
43X Z15C	7.36	(0.005)	0.0030	0.0024	1.54	.	0.0022	0.0020	0.0019	0.0060	(0.005)	(0.007)	0.004	0.002
42X Z8A	7.03	.	0.0003	(0.0002)	0.0215	.	0.0033	0.0014	0.0019	0.0025	.	0.013	(0.0023)	(0.0001)
42X Z9A	5.58	.	0.0054	.	0.0070	.	0.0464	0.0006	(0.0003)	0.0021	.	(0.004)	(0.00035)	0.020
43X GALF2A	5.40	.	0.0043	.	0.0585	0.032	0.0504	.	.	0.0050	.	.	0.0040	.
SRM 629	5.15	.	0.0155	0.0008	1.50	0.017	0.094	0.0017	0.0075	0.0135	.	0.078	0.012	.
42X Z10A *	4.90	.	0.0032	.	0.31	0.0008	0.0021	0.018	0.010	0.006	<0.001	.	0.0035	.
43X GALF1A	4.68	.	0.0499	.	4.39	0.061	0.0999	.	.	0.0505	.	.	0.0514	.
42X Z7B	4.39	.	0.030	(0.0001)	0.0249	0.027	0.0095	0.0045	0.0067	0.0097	.	0.006	0.012	.
42X Z7C	4.39	.	0.030	(0.0001)	0.0249	0.027	0.0095	0.0045	0.0067	0.0097	.	0.006	0.012	(0.0001)
43X SC4A	4.35	.	0.0058	0.009	1.122	0.022	0.093	0.044	0.0249	0.0064	.	0.022	0.0056	.
43X Z10A	3.99	.	0.0014	0.00027	2.97	0.007	0.0403	0.0050	0.0036	0.0046	.	0.009	0.0012	.
43X SC1A	3.75	.	0.0011	0.0082	1.903	0.073	0.740	0.0201	0.0161	0.0150	.	0.022	0.0082	.
43X SC2A	3.41	.	0.0018	0.023	4.80	0.046	0.498	0.0183	0.0096	0.0097	.	0.0133	0.0031	.
42X Z11A	3.19	.	0.0020	0.0016	0.093	(0.036)	0.0329	0.0196	0.0241	0.0058	0.0047	.	0.0017	.
43X Z9A	3.17	0.0033	0.0034	0.0034	4.82	0.073	0.0472	0.0108	0.0027	0.0078	0.0033	.	0.0020	0.0012
43X Z5B	3.164	0.0148	0.0030	.	5.92	0.10	0.0144	0.0061	0.0056	0.0029	0.065	.	(0.0004)	.
43X SC3A	3.14	.	0.0028	0.0108	3.03	0.018	0.257	0.0337	0.0261	0.0066	.	0.022	0.0078	.
43X Z8A	2.51	.	0.00090	0.00024	0.481	(0.0017)	0.00155	0.00021	0.00033	0.0027	.	.	(0.0005)	.
41X 0336 Zn2N	1.000	0.0043	0.147	.	0.216	0.0283	0.0568	0.0227	0.0047	0.492	0.0019	.	0.0547	.
Number	Al	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Si	Sn	Ti
Number	Ag	As	Be	Ce	In	La	Tl	Zr						
43X Z23E						
CAN NZA-1						
43X Z22D						
CAN NZA-4						
CAN NZA-3						
43X Z21D	.	(0.0004)						
CAN NZA-2						
43X GALF5A	.	.	.	0.0041	.	0.0019	.	.						
CAN NZA-7						
42X Z16A	0.0051	.	(0.003)	.						
43X Z11F						
CAN NZA-5						
43X GALF4A	.	.	.	0.079	.	0.041	.	.						
43X Z12E						
42X Z15A	0.0024	.	.	.						
43X Z13E						
43X GALF3A	.	.	.	0.0152	.	0.0076	.	.						
CAN NZA-6						
43X Z15C						
42X Z8A	.	.	.	0.0081	.	0.0079	.	.						
42X Z9A	.	.	.	0.0047	.	0.0044	.	0.011						
43X GALF2A	.	.	.	0.0318	.	0.0158	.	.						
SRM 629						
42X Z10A *	.	Provisional Analysis	.	.	0.0022	.	<0.001	.						
43X GALF1A	.	.	.	0.0569	.	0.0284	.	.						
42X Z7B	.	.	.	0.072	.	0.061	.	last						
42X Z7C	.	.	.	0.09	.	0.08	.	.						
43X SC4A						
43X Z10A						
43X ZSC1A						
43X SC2A						
42X Z11A	.	.	.	0.0014	0.0037	(0.0009)	0.0047	.						
43X Z9A						
43X Z5B	0.0254	(0.0005)						
43X ZSC3A						
43X Z8						
41X 0336 Zn2N	0.0131	0.0016	.						
Number	Ag	As	Be	Ce	In	La	Tl	Zr						

CRM ZINC ALLOYS, chart 2 of 2 41X CGL: 42 - 48 mm Ø x 20 mm other X: ~45--50 mm Ø x ~20 mm

Number	Al	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Si	Sn	Ti
41X GLV10A	0.969	0.0031	0.0030	.	0.0073	0.0051	0.0040	0.0062	0.0022	0.0066	0.0009	.	0.0062	.
41X GLV9A	0.547	0.0019	0.0028	.	0.0037	0.0039	0.0014	0.0027	0.0009	0.0043	0.0048	.	0.0028	.
41X GLV4E	0.503	0.0047	0.0013	0.00104	0.0246	(0.01)	0.0025	0.164	0.0078	0.0058	0.0235	.	0.0035	.
41X GLV11A	0.463	0.0009	0.0010	.	0.0017	0.0027	0.0009	0.0008	0.0008	0.0057	0.168	.	0.0009	.
41X 4380 Zn4D	0.446	0.0101	0.086	0.0029	0.0284	0.017	0.118	0.0092	0.0172	0.310	0.0156	.	0.0416	(0.0003)
41X GLV6B	0.441	0.0254	0.0051	0.0007	0.0371	0.0020	.	0.00235	0.0007	0.097	0.0122	.	0.0155	.
41X GLV7A	0.399	(0.0108)	0.00056	0.0010	0.023	.	.	0.0025	0.0060	0.082	0.0031	.	(0.0006)	.
41X 0336 Zn3K	0.336	.	0.341	.	0.353	0.0456	0.147	0.0106	0.0022	0.0282	.	.	0.127	.
41X GLV3C	0.326	0.0031	0.0183	0.0003	0.0332	0.0014	0.0014	0.0185	0.0335	0.0249	0.0555	.	0.0031	.
41X 4380 Zn9A	0.295	0.00046	0.0032	0.0015	0.0416	0.0113	0.0153	0.0018	0.0009	0.0139	0.0060	.	0.0008	.
41X GLV1E	0.285	0.0045	0.0087	.	0.0188	(0.0008)	0.0021	.	0.0021	0.0175	0.0016	.	0.0049	.
41X CGLF	0.28	.	(0.0015)	.	(0.0005)	0.046	.	.	(<0.001)	.
41X 4380 Zn7D	0.277	.	0.0156	.	0.0133	0.0018	0.0029	0.0036	0.0120	1.18	0.086	.	0.0036	0.0065
41X GLV8A	0.263	0.0005	0.0003	0.0012	0.0139	0.0062	0.0012	0.0012	0.0006	0.0037	0.0057	.	0.0005	.
41X GLV8B	0.258	0.0006	0.0004	(0.0001)	0.0111	0.0080	0.0009	0.0035	0.0023	0.0039	0.0062	.	0.0005	.
41X 4380 Zn8D	0.232	0.0156	0.0097	(0.0001)	0.0208	0.0074	0.0054	0.0081	0.0445	0.700	0.0151	.	0.0177	0.0020
41X GLV2C	0.0905	0.0158	0.0037	0.0015	0.0057	0.0155	0.0006	0.0218	0.0053	0.0248	0.0049	.	0.0097	.
41X 2951 Zn3A	0.078	.	0.0062	0.184	1.89	.	0.0164	0.0018	0.0010	0.0065	.	.	(0.006)	0.133
41X GLV2A	0.068	0.017	0.0025	.	0.0052	0.048	.	.	0.0070	0.214	0.006	.	0.003	.
41X ZNiBiA	0.050	0.502	0.0020	.	0.0132	0.0133	.	.	2.02	0.0187	.	.	0.154	.
41X 4380 Zn1D	0.039	0.0021	0.394	0.0007	0.178	0.0276	0.0032	0.0006	0.0058	0.0618	0.0019	.	0.0510	0.0004
41X 0336 Zn5A	0.035	(0.001)	0.056	.	0.023	.	<0.0005	(0.0001)	(0.0005)	0.91	0.008	.	0.21	.
41X 2951 Zn2A	0.032	.	0.0037	0.142	1.37	.	0.0123	0.0011	0.0027	0.0040	.	.	(0.0015)	0.209
41X 2951 Zn1A	0.029	.	0.0005	0.083	0.79	.	0.0029	0.0013	0.0038	0.0042	.	.	(0.0007)	0.278
41X 4380 Zn6D	0.0260	0.0047	0.0466	0.0064	0.0327	0.0307	0.0044	0.200	0.0073	0.427	(0.002)	.	0.101	0.0029
41X 4380 Zn5C	0.0215	0.0308	0.0571	0.0075	0.071	.	0.00165	0.035	0.00147	0.140	0.0061	.	0.0101	0.339
41X 4380 Zn3C	0.0203	0.0103	0.0950	0.0029	0.073	.	0.0220	0.0180	0.0120	0.180	0.0046	.	0.080	0.125
41X 0336 Zn1L	0.0177	.	0.0067	.	0.0088	0.0106	0.0062	0.0102	0.0009	1.007	.	.	0.0051	.
41X 4380 Zn2C	0.0153	0.0076	0.284	0.0027	0.0288	.	0.0243	0.0087	0.0023	0.268	0.0093	.	0.0021	0.0251
41X GLV5B	0.0139	0.0098	0.0136	.	0.0103	0.0443	0.0014	.	0.0025	0.0166	0.148	.	0.0172	.
41X ZNi2A	0.0135	0.0050	0.0010	.	0.0056	0.0061	.	.	1.97	0.0172	.	.	0.141	.
41X 4380 Zn10A	0.0004	.	0.0007	0.117	0.0022	0.49	0.184	.	0.063	0.0043	0.0005	.	0.0014	.

Number	Al	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Si	Sn	Ti
--------	----	----	----	----	----	----	----	----	----	----	----	----	----	----

Number	Ag	As	Co	In	Tl
--------	----	----	----	----	----

41X GLV10A	.	.	0.0002	.	.
41X GLV9A	.	.	0.0005	.	.
41X GLV4E	.	0.0002	0.0061	.	.
41X GLV11A	.	.	(0.0001)	.	Sr:(0.0004)
41X 4380 Zn4D	.	.	0.0018	.	.
41X GLV6B	.	.	0.0061	.	V:<0.0005
41X GLV7A	.	0.0016	.	.	.
41X 0336 Zn3K	.	0.0003	.	.	.
41X GLV3C	.	0.0036	0.0034	.	.
41X 4380 Zn9A
41X GLV1E	.	(0.0004)	0.0008	.	.
41X CGLF	.	.	(<0.001)	(<0.001)	last of stock
41X 4380 Zn7D
41X GLV8A
41X GLV8B
41X 4380 Zn8D	0.0140
41X GLV2C	.	0.0017	0.0055	.	.
41X 2951 Zn3A
41X GLV2A	.	<0.001	.	.	last of stock
41X ZNiBiA
41X 4380 Zn1D	0.0012
41X 0336 Zn5A
41X 2951 Zn2A
41X 2951 Zn1A
41X 4380 Zn6D	0.0030	.	0.0091	.	.
41X 4380 Zn5C
41X 4380 Zn3C
41X 0336 Zn1L	.	0.0008	.	.	.
41X 4380 Zn2C
41X GLV5B	.	0.00044	0.0011	.	.
41X ZNi2A
41X 4380 Zn10A

Number	Ag	As	Co	In	Tl
--------	----	----	----	----	----